


BIS(ALKYL- OR CYCLOALKYL-PHENYLETHYNYL)ANTHRACENES

The invention relates to novel fluorescer compounds and to the use of those compounds in mixtures which are useful for generating chemiluminescence and to the use of such mixtures for generating chemiluminescence.

5 Zweig and Maulding, in U.S. Patents Nos. 3,557,233 and 3,729,426, and Maulding, in U.S. Patent No. 3,888,786 described 9,10-bis(phenylethynyl)anthracenes substituted by chloro, bromo, fluoro, or lower alkyl groups and their use as fluorescers with certain oxalic-type compounds which
10 react with peroxide to produce chemiluminescence. The invention provides fluorescers for chemiluminescent mixtures that will have higher chemiluminescence efficiencies as measured by the quantum yield, and will have higher light output as measured by the light capacity,
15 than those described by Zweig and Maulding.

Summary of the Invention

The invention provides novel fluorescer compounds having the formula (I),



(I)

30 wherein R is selected from the group consisting of C₄ to C₂₂ alkyl, and C₄ to C₈ cycloalkyl.

There are also provided novel mixtures which can form one component in a system for generating chemiluminescence. These mixtures comprise (a) a

fluorescer compound of formula (I) above, and a chemiluminescent reactant, (as hereinafter defined) and optionally a diluent, in proportions and concentrations to produce chemiluminescence when the mixtures are

5 reacted with a peroxide component (as hereinafter defined) in the presence of a diluent.

The invention further provides a process for generating chemiluminescence by reacting a mixture of the above composition with a peroxide component.

10 The preferred fluorescers of the present invention are particularly distinguished from the prior art fluorescers in chemiluminescent mixtures by the fact that mixtures with the new fluorescers provide higher quantum yields, about 15-16%, versus about 9%, for 9,10-bis(phenyl-
15 ethynyl)anthracene, and they provide higher light capacities, about 380-550 lumen-hours per liter, versus about 280 lumen-hours per liter for 9,10-bis(phenylethynyl)-anthracene.

Compounds of formula (I) can be prepared by
20 reacting about two molecular proportions of the lithium salt of a selected phenylacetylene with anthraquinone to obtain a dihydrodihydroxybis(phenylethynyl)anthracene, which is then converted to the corresponding 9,10-bis-(phenylethynyl)anthracene by methods described in more

detail in the Maulding, U.S. Patent No. 3,911,038).

Illustrative examples of compounds of formula (I) include the following:

- 5 9,10-bis(p-n-hexylphenylethynyl)-
 anthracene,
- 9,10-bis(p-n-octylphenylethynyl)-
 anthracene,
- 9,10-bis(p-2-ethylhexylphenylethy-
 nyl)anthracene,
- 10 9,10-bis(p-n-dodecylphenylethy-
 nyl)anthracene,
- 9,10-bis(p-cyclohexylphenylethy-
 nyl)anthracene,
- 9,10-bis(p-n-butylphenylethynyl)-
15 anthracene,

and the like.

Presently the most preferred compound of formula (I) for use in chemiluminescent mixtures is 9,10-bis(p-n-octylphenylethynyl)anthracene.

20 The term "chemiluminescence," as employed herein, is defined as the generation of electromagnetic radiation between about 300 and 1200 nanometers by means of a chemical reaction.

 The term "chemiluminescent reactant" is defined
25 as any compound which enters into a chemical reaction
with a peroxide component to produce in the presence of a fluorescer of
Formula (I) and a diluent, chemiluminescence. The preferred chemiluminescent reactants for use in this invention are oxalic acid esters, and
certain oxamides, which are described for example in U.S.
30 Patents Nos. 3,597,362, 3,888,786, and 4,226,738.

 The term "composition for reaction with a peroxide component to generate chemiluminescence," as employed herein, is defined as a mixture of a compound of
35 formula (I) and a chemiluminescent reactant in a diluent
in concentrations sufficient to produce chemiluminescence
by admixing with a peroxide component. Thus, the initial
concentrations of the compound of formula (I). the

reactant compound, as well as the ingredients of the peroxide component in the final reaction mixture, must be sufficient to produce chemiluminescence.

The term "admixing" as used herein, means
5 "reacting" or sufficiently bringing together component reactants to obtain chemiluminescence.

The fluorescer compound of formula (I) must not readily react with the peroxide component, or with the chemiluminescent reactant, and must be at least partially
10 soluble in the diluent employed.

The composition for reaction with a peroxide component to generate chemiluminescence preferably comprise a diluent which will solubilize the fluorescer compound of formula (I) and the chemiluminescent reactant
15 to provide initial concentrations in the reacting system of about 10^{-3} M to about 10M, more preferably about 10^{-1} M to about 1M, of the reactant compound and about 10^{-5} M to about 10^{-1} M, more preferably about 10^{-3} M to 10^{-2} M, of the fluorescer compound. This liquid diluent must be
20 relatively unreactive toward the other ingredients of the chemiluminescent mixture.

The molar concentrations of the chemiluminescent reactant, and the fluorescer compound in the composition for reaction with a peroxide component to generate
25 chemiluminescence i.e. in the composition before addition and reaction with the peroxide component, is preferably 1.1-2.5, more preferably about 1.2-1.3, times the molar concentrations of the same materials in the final reacting system.

30 Typical diluents which can be used in the composition for reaction with a peroxide component include esters, ethers, aromatic hydrocarbons, chlorinated aliphatic and aromatic hydrocarbons such as those described for the use in U.S. Patents 3,749,679 and
35 3,888,786. The most preferred diluent is dibutyl phthalate. Solvent combinations may be used but such

combinations should not include strongly electron donating solvents, strongly acidic, or strongly basic solvents.

The term "diluent" as used herein, is defined as a liquid solvent, or vehicle, for the compound of formula (I) and the chemiluminescent reactant.

The term "peroxide component," as used herein, means a solution of a hydroperoxide compound in a suitable solvent.

The term "hydroperoxide compound" includes (1) hydrogen peroxide and (2) hydrogen peroxide-producing compounds.

Hydrogen peroxide is the preferred hydroperoxide compound. Anhydrous forms of hydrogen peroxide, such as sodium perborate, sodium peroxide, and the like, may be used. Generally, whenever hydrogen peroxide is contemplated to be employed, any suitable compound may be substituted which will produce hydrogen peroxide.

Solvents which can be employed for the peroxide component include any liquid which is relatively unreactive toward the hydroperoxide, the chemiluminescent reactant, and the fluorescer compound, and which accommodates a solubility to provide at least 0.01M hydroperoxide solution. Solvents suitable for the hydroperoxide compound include water; alcohols, such as ethanol, tertiary butanol, or octanol; ethers, such as diethyl ether, diamyl ether, tetrahydrofuran, dioxane, dibutyldiethyleneglycol, perfluoropropyl ether, and 1,2-di-methoxyethane; and esters, such as ethyl acetate, ethyl benzoate, dimethyl phthalate, dioctylphthalate, propyl formate. Solvent combinations can, of course, be used such as combinations of the above with anisole, tetralin, and chlorobenzene, providing said solvent combination accommodates hydroperoxide solubility. However, strong electron donor solvents such as dimethyl formamide, dimethyl sulfoxide and hexamethyl-phosphoramide should not, in general, be used as a major solvent

for the peroxide component.

The preferred solvent for the peroxide component is a mixture of about 80 volume percent dimethyl phthalate and about 20 volume percent tertiary butanol.

5 The hydrogen peroxide concentration in the peroxide component suitably may range from about 0.2M to about 15M. Preferably, the concentration ranges from about 1M to about 2M.

10 The lifetime and intensity of the chemiluminescent light emitted can be regulated by the use of certain regulators such as:

(1) by the addition of a catalyst which changes the rate of reaction of the hydroperoxide compound with the compound of formula (I). Catalysts which accomplish
15 that objective include those described in M. L. Bender, "Chem. Revs.," Vol. 60, p. 53 (1960). Also, catalysts which alter the rate of reaction or the rate of chemiluminescence include those accelerators of U.S. Patent No. 3,775,366, and decelerators of U.S. Patent
20 Nos. 3,691,085 and 3,704,231, or

(2) by the variation of the hydroperoxide compound. Both the type and the concentration of the hydroperoxide compound are critical for the purpose of regulation.

25 Preferably, a weakly basic accelerator, such as sodium salicylate, is included in the peroxide component to control the lifetime of the chemical lighting system. The concentration of weakly basic accelerator used in the peroxide component may range from about 10^{-6} M to
30 about 10^{-2} M, preferably from about 10^{-4} M to about 10^{-3} M.

The initial concentration of the ingredients of the peroxide component in the chemiluminescent reacting system is generally about 0.15 to 0.60 of their concentrations in the peroxide component since the
35 peroxide component preferably comprises about 15 to about 60 volume percent of the final reaction mixture.

The concentration of the hydroperoxide compound in the chemiluminescent reaction is at least equal to the molar concentration of the chemiluminescent reactant and is preferably 1.2 to 5.0 times the concentration of the chemiluminescent reactant in the reacting system described above. The optimum concentrations must be determined experimentally for each specific system.

The following examples are illustrative of the present invention. All parts are by weight unless otherwise indicated.

Example 1

Preparation of 9,10-Bis(p-n-octylphenylethynyl)anthracene

Lithium amide (2.4635 grams; 0.1073 mole), dry dioxane (160 mls), and p-n-octylphenylacetylene (22.22 grams of 90% purity; 0.0933 mole) are added, under a blanket of argon, to a reaction vessel equipped with a thermometer, stirrer, argon inlet, and reflux condenser, and the resulting mixture is heated to 80°C, stirred for 2.5 hours, and then cooled to room temperature.

Anthraquinone (9.2077 grams; 0.0442 mole) and additional dry dioxane (50 mls) are added and the resulting mixture is stirred at 100°C for 56 hours.

The reaction mixture is cooled to 15°C, a solution of stannous chloride dihydrate (33.5 grams) in a mixture of N,N-dimethylformamide (70 mls) and glacial acetic acid (10 mls) is added and the resulting mixture is stirred at 100°C for 5 hours. The reaction mixture is then cooled to room temperature, stirred for 16 hours, and then cooled to 10°C. Glacial acetic acid (100 mls) and dilute sulfuric acid (100 mls) are added and the resulting mixture is stirred at ambient temperature for one hour.

The reaction mixture is allowed to settle and the supernatant liquor is decanted from a dark brown gummy residue. The residue is triturated with water (200 mls), stirred with the water for 0.5 hour, and


allowed to settle. The water is decanted and the residue is dissolved in toluene (400 mls). The resulting solution is filtered and the filtrate is concentrated under vacuum to obtain a dark brown residue. The residue is redissolved in toluene, treated with anhydrous magnesium sulfate, DARCO (Registered Trade Mark) Decolorizing Carbon (ICI Americas, Inc.), and Magnesol* (Trademark, FMC Corporation) and stirred at reflux for one hour while azeotropically removing water by means of a Dean-Stark trap. The hot reaction mixture is then filtered through a bed of diatomaceous earth, and the filtrate is concentrated to dryness to obtain a dark semi-solid. The latter is recrystallized from hexane (120 mls) to obtain 3.2 grams of a yellow crystalline solid, mp 131-133°C. Calculated for $C_{46}H_{50}$: C, 91.64%; H, 8.36%. Found: C, 90.63%; H, 8.45%.

Example 2

Preparation of 9,10-Bis(p-n-dodecylphenylethynyl)anthracene

Lithium amide (1.8712 grams; 0.0815 mole), dry dioxane (135 mls), and p-n-dodecylphenylacetylene (19.14 grams; 0.0708 mole) are added, under a blanket of argon, to a reaction vessel equipped with a thermometer, argon inlet, stirrer, and reflux condenser, and the resulting mixture is heated to reflux, stirred for 2.5 hours, and then cooled to room temperature. Anthraquinone (6.9754 grams; 0.0335 mole) is added and the mixture is heated again and stirred at reflux for 15 hours.

The reaction mixture is cooled to room temperature, a solution of stannous chloride dihydrate (25.4 grams) in N,N-dimethylformamide (55 mls) is added and the mixture is heated and stirred at 100°C for 5 hours. The reaction mixture is again cooled and stirred at room temperature for 15 hours. Glacial acetic acid (150 mls) and dilute sulfuric acid (150 mls; 5N) are then added, followed by addition of warm cyclohexane (400 mls). The reaction mixture is stirred for 30 minutes, then allowed to

- separate into two phases and the lower layer is removed. The upper layer is dried over anhydrous magnesium sulfate, then treated with DARCO (Registered Trade Mark) carbon and HYFLO (Registered Trade Mark) Super-Cel (Johns-
- 5 Manville Sales Corporation), and stirred for one hour at ambient temperature. The mixture is then filtered and the filter cake is washed with cyclohexane. The filtrate and washing liquid are combined
- 

and the mix is concentrated under vacuum to obtain a brown solid. The solid is slurried in cold isopropanol, filtered, rinsed with cold isopropanol then dried to obtain 8.5 grams of a bright yellow solid. Recrystallization from methylcyclohexane gives a yellow solid which melts at 111-113°C.

Calculated for $C_{54}H_{66}$: C, 90.70%; H, 9.30%

Found: C, 90.02%; H, 9.35%

Examples 3-5

Determination of Chemiluminescence

Solutions of 7.5 mls of bis(6-carbopentoxo-2,4,5-trichlorophenyl)oxalate (CPPO) and selected fluoresters (defined in Table I) are made in dibutyl phthalate. Each solution is mixed with 2.5 mls of a peroxide component which consists of hydrogen peroxide and sodium salicylate in 80% dimethyl phthalate-20% (by volume) tertiary butanol. Each of the chemiluminescent reaction mixtures contains initial concentrations of 0.38 M hydrogen peroxide, 1.56×10^{-4} M sodium salicylate, 0.08M CPPO, and 2.25×10^{-3} M of the fluorester. Quantitative measurements of the chemiluminescence of the solutions are carried out by means of a Hirt-Roberts radiometer-spectrophotometer using the procedure described in the Journal of Organic Chemistry, Volume 44, page 4115 (1979). The results are shown in Table I. The fluorester compounds of Examples 1 and 2 provided significantly higher light capacities and quantum yields than the comparison fluorester (Example 5) which was selected because it is a prior art fluorester of choice for most oxalate ester chemiluminescent compositions.

TABLE I

<u>Example</u>	<u>Fluorescer</u>	<u>Light Capacity (a)</u>	<u>Percent</u> <u>Quantum Yield (b)</u>	<u>T75 (c)</u>
3	Compound of Example 1	382	15.9	94
4	Compound of Example 2	380	15.4	69
5	9,10-Bis(phenylethynyl)anthracene	279	12.5	53

(a) Lumen hours per liter

(b) Einsteins per mole x 100

(c) Time (in minutes) required for 75% of the total light to be emitted

29

Examples 6-8

The procedure of Example 3 is followed in all details except varying concentrations of the compound of Example 1, and 0.10M CPPO are used. The results are shown in Table II.

5

10

15

20

25

30

35

TABLE II

<u>Example</u>	<u>Conc. of Fluorescer (M)</u>	<u>Light Capacity</u>	<u>Percent</u>	
			<u>Quantum Yield</u>	<u>T75</u>
6	0.00225	366	12.2	101
7	0.00450	397	12.9	76
8	0.00675	365	11.6	110

Examples 9-13

The procedure of Example 3 is followed in every detail except 0.00450M of the compound of Example 1, and varying concentrations of CPPO were used as shown in Table III. The results are shown in Table III.

10

15

20

25

30


35

TABLE III

Example	Conc. of CPPO (M)	Light Capacity	Percent	
			Quantum Yield	T75
9	0.05	235	15.2	26
10	0.08	340	13.6	87
11	0.10	422	13.4	88
12	0.15	546	11.5	167
13	0.20	535	8.5	150

**CLAIMS:**

1. A compound defined by the formula:



wherein R is selected from the group consisting of C_4 to C_{22} alkyl and C_4 to C_8 cycloalkyl.

2. 9,10-Bis(p-n-octylphenylethynyl)anthracene.
 3. 9,10-Bis(p-n-dodecylphenylethynyl)anthracene.
 4. A composition comprising a chemiluminescent reactant, as hereinbefore defined, and a compound according to any preceding claim.
 5. A composition according to Claim 4, and including also a diluent as hereinbefore defined.
 6. A process for generating chemiluminescence, which comprises mixing a composition according to Claim 5, with a peroxide component, as hereinbefore defined, to provide concentrations that will produce chemiluminescence.
 7. A process for generating chemiluminescence, according to Claim 6 and substantially as described in any one of Examples 3, 4 and 6 to 13 herein.
-