

Description

NON STOICHIOMETRIC TETRAGONAL COPPER ALKALINE EARTH SILICATE PHOSPHORS AND METHOD OF PREPARING THE SAME

Technical Field

- [1] The present invention relates to Alkaline Earth Silicate phosphors, and more particularly to non stoichiometric tetragonal Copper Alkaline Earth Silicate phosphors activated by divalent europium for using them as temperature stable luminescent materials for ultraviolet or daylight excitation.

Background Art

- [2] Stoichiometric silicates such as Orthosilicates, Disilicates and Chlorosilicates are well known as converter materials for short or long wave excitation like ultraviolet as well as daylight radiation. (G. Roth; et al. "Advanced Silicate Phosphors for improved white LED" (Phosphor Global summit Seoul/Korea, March 5-7, 2007))
- [3] Especially, blue light excitation from an LED leads to a white light or color for demand for several applications. In the last years, the use of silicates has been increasing for LED application.
- [4] The LEDs and especially the High Power LEDs produce a lot of heat during operation. Additionally, LEDs have to withstand high ambient temperature above 80°C. Phosphors themselves have a system depending on temperature-behavior. The brightness of most phosphors is decreasing with increasing temperatures.
- [5] This so-called temperature quenching depends on the interactions between activator and host lattice and is influenced by the composition of the matrix, structure, lattice effects, concentration as well as the kind of activator. In particular, the strength of the bonding within the crystal matrix is influencing the extension of the lattice parameters and from this the emission properties of the activator ions.
- [6] Furthermore, by increasing the temperature the oscillation of the ions within the lattice becomes higher. Because of this, the probability of an interaction with the activator ions becomes higher resulting in an increasing loss of exciting energy in form of heat. This so-called Photon-Photon Coupling strongly depends on the structure and the surrounding of the activator ions. The more rigid is the crystal lattice, the lower is the interaction between ions and activator.
- [7] The brightness of Orthosilicates, Disilicates as well as Chlorosilicates activated by divalent Europium decreases strongly with higher temperatures up to 150°C because the lattice is not so rigid and the strength of the bonding is not so high.
- [8] This effect leads e.g. to a changing of the color of the LED during operation. This is

a serious disadvantage of the use of common Silicates known until now for LED applications. Furthermore, the sensitivity against water is comparably high caused by the weak lattice and a highly heteropolar bonding between the Silicate ion and the Alkaline Earth ions.

- [9] Silicate phosphors have been developed in the recent years as luminescent materials for white LEDs. (WO 02/054503, WO 02/054502, WO 2004/085570)
- [10] Orthosilicates as luminescent material with an excitability from short ultraviolet radiation up to visible light can be used as phosphors for fluorescent lamps. (Barry, T.L., "Fluorescence of Eu^{2+} -activated phases in binary Alkaline Earth Orthosilicate systems," J. Electrochem. Soc., 115, 1181 (1968))
- [11] Co-doped Tristrontium-silicates are disclosed as yellow-orange luminescent material (H.G. Kang, J.K. Park, J.M-Kom, S.C. Choi; Solid State Phenomena, Vol 124-126 (2007) 511-514), Divalent europium as activator for silicates (S.D. Jee, J.K. Park, S.H. Lee; "Photoluminescent properties of Eu^{2+} activated Sr_3SiO_5 Phosphors," J. Mater Sci. 41 (2006) 3139-3141 and Barry, T.L.; "Equilibria and Eu^{2+} luminescence of subsolidus phases bounded by $\text{Ba}_3\text{MgSi}_2\text{O}_8$, $\text{Sr}_3\text{MgSi}_2\text{O}_8$ and $\text{Ca}_3\text{MgSi}_2\text{O}_8$," J. Electrochem. Soc., 115, 733, 1968), and fluorescence for excitation by UV and blue radiation is disclosed in several Silicate systems as Orthosilicates and Disilicates. (G.Blasse, W.L.Wanmaker, J.W. ter Vrugt and a. Bril; "Fluorescence of Europium $^{2+}$ -activated silicates," Philips Res. Repts 23, 189-200, 1968)
- [12] All these phosphors have the disadvantage that they have strong temperature quenching and a strong shift of the emission band with the temperature. The emission intensity can be dropped down to 50% at 150°C.

Disclosure of Invention

Technical Problem

- [13] An object of the present invention is to provide more stable phosphors with a more rigid surrounding of the activator ions in a Silicate matrix and to provide Silicate phosphors with high temperature stability and lower sensitivity against humidity.
- [14] Other object of the present invention is to provide high temperature stable tetragonal Copper Alkaline Earth Silicate phosphors activated by at least divalent Europium which emits light between about 500nm to 630nm and a manufacturing method thereof.
- [15] Another object of the present invention is to provide luminescent tetragonal Copper Alkaline Earth Silicate for LED applications, which have high color temperature range from about 2,000K to 8,000K or 10,000K showing a CRI of 80~95, especially 90~95, when mixed together with other phosphors.

Technical Solution

- [16] The energetic ground level of divalent Europium $4f^7$ can be excited by ultraviolet as well as blue radiation. Divalent Europium emits light in dependence on the crystal field splitting from around 365 nm in the ultraviolet region at small crystal field splitting, e.g. in Tetra borate phosphors, up to 650 nm with red emission at high crystal field splitting, e.g. in Nitrides.
- [17] The emission itself depends on both the covalence, the so-called nephelauxetic effect, and the strength of the crystal field. The strength of the crystal field depends on the distance of activator ions and oxygen within the host lattice. Both effects lead to decreasing and splitting of the excited $4f^65d$ level of divalent Europium and result in a shifting of the emission to longer wavelength and smaller energy of the emission.
- [18] The difference between exciting radiation and emitting radiation is the Stokes shift. In Orthosilicates, Disilicates as well as Chlorosilicates, the Stokes shift is between 160 nm and 360 nm, and depends on the exciting radiation as well as the excitability of divalent Europium within the host lattice.
- [19] In Orthosilicates, e.g. the activator ion Europium $2+$ is surrounded by oxygen ions in different distance caused by the orthorhombic structure. Best temperature stability has been observed with Barium rich systems, in which the Europium ions have shortened the host lattice and stabilized the crystal structure.
- [20] The introduction of more Strontium or Calcium or other cations besides Barium into the Orthosilicate lattice can disturb the symmetry near of the activator ions and leads to energetic traps and stronger interactions between Europium and the lattice traps. These traps play an important role within the temperature quenching process, and the energy transfer process within the crystal is disturbed. Furthermore, the sensitivity against humidity is increasing with increasing number of lattice defects like traps.
- [21] An important point is the reduction of interactions between the rare earth metal Europium and the stabilization of its surrounding. That has been realized by developing Tetragonal Copper Alkaline Earth Silicates (CSE) activated by divalent Europium. Divalent Copper ions within tetragonal silicate structure lead to lattice parameters (e.g. $(\text{Cu, Sr})_3\text{SiO}_5$ with $a=6.91\text{\AA}$; $c=9.715\text{\AA}$) smaller than for tetragonal lattice without copper (Sr_3SiO_5 with $a=6.93\text{\AA}$; $c=9.73\text{\AA}$).
- [22] The lattice parameters are strongly different from lattice parameters of the well-known Orthosilicates with $a=5.682\text{\AA}$, $b=7.09\text{\AA}$ and $c=9.773\text{\AA}$. Here, the surrounding of divalent Europium is influenced by the orthorhombic structure.
- [23] Tetragonal Copper Alkaline Earth Silicates show more stable temperature behavior above 100°C . Here, copper is very important for the phosphor preparation. By incorporation of copper into a common Alkaline Earth Silicate, three effects could be obtained.
- [24] Firstly, copper is accelerating the solid state reaction during the heating process.

Secondly, copper containing phosphors show improved emission intensities compared to luminescent materials having not that component in the host lattice and is stabilizing the surrounding around the activator. Thirdly, the copper containing phosphors show a shifting of the emission to longer wavelength.

- [25] Copper as a basic element doesn't react as activator but the use of this ion leads to an influence on the crystal field splitting as well as the covalence. Surprisingly, the incorporation of copper accelerates the solid state reaction during temperature processing and leads to homogeneous high brightness phosphor which is stable at high temperatures.
- [26] Copper(II) has a smaller ionic radius (about 60 pm) and electro-negativity (1.8) is higher than the electro-negativity of Barium, Strontium and Calcium (1). Furthermore, Copper(II) has a positive electrochemical reduction potential of +0.342 in contradiction to the negative potential of Alkaline Earth metals (-2.8 to -2.9). It is shown that copper is stabilizing the emission of Europium within the silicate host lattice.
- [27] Furthermore, the water stability can be improved. It is known that Alkaline Earth Silicate phosphors are unstable in water, air humidity, water steam or polar solvents.
- [28] Silicates with orthorhombic as well as Akermanite or Merwinite structures show more or less high sensitivity to water, air humidity, water steam or polar solvents caused by high basicity. Due to higher covalence and a lower basicity as well as a positive reduction potential, the incorporation of copper as a basic matrix component in a host lattice improves the behavior of luminescent silicates against water, air humidity, water steam or polar solvents.
- [29] The disadvantage of the strong temperature dependence can be overcome by changing the composition of the phosphor and additionally by introducing copper into such a tetragonal silicate matrix and by preparing special non stoichiometric copper Alkaline Earth Silicates with a high temperature calcinations procedure.
- [30] The present invention provides high temperature stable tetragonal Copper Alkaline Earth Silicate phosphors activated by at least divalent Europium which emits light within the range of 500nm to 630nm and a manufacturing method thereof. These phosphors show a better stability against water and humidity and can be used with advantage for high brightness LED applications. The phosphors are represented as the following formula 1.
- [31]
- [32] [Formula 1]
- [33] $(\text{Ba}_u\text{Sr}_v\text{Ca}_w\text{Cu}_x)_{3-y}(\text{Zn,Mg,Mn})_z\text{Si}_{1+b}\text{O}_{5+2b}:\text{Eu}_a$
- [34]
- [35] A tetragonal non stoichiometric silicate is provided where Copper is basically an essential part of the matrix with $u+v+w+x=1$, $y=z+a$, $z \leq 2$, $0 < x \leq 1$, $0 < a \leq 0.5$ and

$0 < b < 0.5$.

- [36] The phosphors may be made by a multi-step high temperature solid state reaction between the starting materials comprising a surplus of SiO_2 and metal compounds, e. g. metal oxides and metal carbonates, which decompose at high temperatures into oxides. The high temperature solid state reaction may be performed between 800°C and 1550°C .

Advantageous Effects

- [37] According to embodiments of the present invention, more stable silicate phosphors with a more rigid surrounding of the activator ions in a Silicate matrix and with high temperature stability and lower sensitivity against humidity can be provided. Furthermore, high temperature stable tetragonal Copper Alkaline Earth Silicate phosphors activated by at least divalent Europium which emits light between about 500nm to 630nm and a manufacturing method thereof can be provided. In addition, luminescent tetragonal Copper Alkaline Earth Silicate for LED applications, which have high color temperature range from about 2,000K to 8,000K or 10,000K showing a CRI of 80~95, especially 90~95, when mixed together with other phosphors, can be provided.

Brief Description of the Drawings

- [38] Fig. 1 shows emission spectra of new non-stoichiometric Oxyorthosilicates compared with stoichiometric phosphors; both with and without Copper at 450 nm excitation wavelength.
- [39] Fig. 2 shows the influence of Ba on the emission spectra of new tetragonal Oxyorthosilicates.
- [40] Fig. 3 shows X-ray diffraction patterns of a non stoichiometric Copper containing Oxy-Orthosilicate having tetragonal structure.
- [41] Fig. 4 shows X-ray diffraction patterns of a non-stoichiometric yellow emitting Orthosilicate having Olivine structure.
- [42] Fig. 5 shows X-ray diffraction patterns of a blue emitting Ortho-Disilicate having Merwinite structure.
- [43] Fig. 6 shows X-ray diffraction patterns of a non-stoichiometric Oxyorthosilicate with 0.4 Mol Ba.
- [44] Fig. 7 shows X-ray diffraction patterns of a stoichiometric Strontium-Oxyorthosilicate
- [45]

Mode for the Invention

- [46] (example 1)
- [47] Manufacturing method of the luminescent material represented following formula 2 is described.

[48]

[49] [Formula 2]

[50] $\text{Cu}_{0.05}\text{Sr}_{2.91}\text{Si}_{1.05}\text{O}_{5.1}\cdot\text{Eu}_{0.04}$

[51]

[52] As starting materials for 1 Mol phosphor, CuO (3.98g), SrCO₃ (429.60g), SiO₂ (63.09g), Eu₂O₃ (14.08g) and/or any combinations thereof are used. The starting materials in form of very pure oxides as well as carbonates are mixed with the appropriate surplus of Silica together with small amounts of flux (NH₄Cl 16g). In a first step, the mixture is fired in an alumina crucible at 1,350°C in an inert gas atmosphere (N₂ or noble gas) for 2~4 hours. After pre-firing, the material is milled. In a second step, the mixture is fired in an alumina crucible at 1,350°C in weakly reducing atmosphere for additional 4 hours. Then, the material is milled, washed, dried and sieved. The luminescent material has an emission maximum at about 580 nm (shown in Fig. 2), and crystallizes in the tetragonal structure (shown in Fig. 3) which is clearly different from the Orthosilicates (shown in Figs. 4 and 5).

[53] In table 1, results of the X-ray diffraction analysis are written down. There is evidence from Fig. 3-6 and table 1 that the structure has been changed caused by non-stoichiometry and Copper.

[54] This difference can also be seen clearly by comparing Fig. 3 for a non-stoichiometric and Fig.7 for a stoichiometric Oxy-Orthosilicate, especially for the diffraction pattern in the region 2Θ=32-42°.

[55]

[56] Table 1

[Table 1]

[Table]

Powder X-ray spacing of the 15 strongest reflections (Cu-K_{α1} radiation) of some Silicate phosphors compared with data from Literature.

No	stoichiometric Sr ₃ SiO ₅ (*)[Å]	Non-stoichiometric Ortho-silicate Sr _{1.78} Ba _{0.16} Eu _{0.06} Si _{1.04} O _{4.08} [nm]	Non-stoichiometric Ortho-Disilicate Ba _{2.44} Sr _{0.5} MgEu _{0.06} Si _{2.07} O _{8.14} [nm]	Non-stoichiometric Oxy-Orthosilicate Sr _{2.94} Cu _{0.02} Eu _{0.04} Si _{1.03} O _{5.06} [nm]	Non-stoichiometric Oxy-Orthosilicate Sr _{2.7} 4Cu _{0.02} Ba _{0.2} Eu _{0.04} Si _{1.03} O _{5.06} [nm]	Non-stoichiometric Oxy-Orthosilicate Sr _{2.54} Cu _{0.02} Ba _{0.4} Eu _{0.04} Si _{1.03} O _{5.06} [nm]
1	3.595	0.4418	0.4023	0.5388	0.3642	0.3639
2	3.512	0.4063	0.2892	0.3633	0.2992	0.2988
3	2.967	0.3300	0.2793	0.2990	0.2927	0.2925
4	2.903	0.3042	0.2293	0.2923	0.2701	0.2707
5	2.675	0.2904	0.2007	0.2693	0.2461	0.2458
6	2.444	0.2847	0.1821	0.2460	0.2354	0.2356
7	2.337	0.2837	0.1771	0.2352	0.2201	0.2199
8	2.187	0.2416	0.1687	0.2201	0.1899	0.1898
9	1.891	0.2328	0.1630	0.1816	0.1818	0.1820
10	1.808	0.2176	0.1612	0.1771	0.1774	0.1778
11	1.660	0.2055	0.1395	0.1703	0.1705	0.1707
12	1.589	0.2030	0.1338	0.1667	0.1667	0.1666
13	1.522	0.1889	0.1282	0.1595	0.1598	0.1602
14	1.489	0.1842	0.1256	0.1568	0.1569	0.1569
15	1.343	0.1802	0.1206	0.1526	0.1527	0.1528

[57] * Data from Literature for Sr₃SiO₅ in (10 = 1nm): R.W. Nurse, *J. Appl. Chem.*, 2, May, 1952, 244-246

[58]

[59] (example 2)

[60] Manufacturing method of 1 Mol of the luminescent material represented following formula 3 is described.

[61]

[62] [Formula 3]

[63] $\text{Cu}_{0.05}\text{Sr}_{2.51}\text{Ba}_{0.4}\text{Si}_{1.03}\text{O}_{5.06}:\text{Eu}_{0.04}$

[64]

[65] As starting materials for 1 Mol phosphor, CuO (3.98g), SrCO_3 (376.46g), BaCO_3 (78.94g), SiO_2 (61.89g), Eu_2O_3 (14.08g) and/or any combinations thereof are used. The starting materials in form of very pure oxides as well as carbonates are mixed with a surplus of Silica together with small amounts of flux (NH_4Cl - 26.7g). In a first step, the mixture is fired in an alumina crucible at 1,300°C in an inert gas atmosphere for 2~6 hours. After pre-firing, the material is milled again. In a second step, the mixture is fired in an alumina crucible at 1,385°C in weakly reducing atmosphere for additional 6 hours. Then, the material is milled, washed, dried and sieved. The luminescent material has an emission maximum at 582 nm (shown in Fig. 2). The structure is analogously to example 1 as shown in table 1 and Fig. 3.

[66] By substitution of only 0.2 Mol Barium for Strontium results in an emission between 1 and 3 in Fig. 2 and to a change in the structure.

[67]

[68] (example 3)

[69] Manufacturing method of the luminescent material represented following formula 4 is described.

[70]

[71] [Formula 4]

[72] $\text{Cu}_{0.03}\text{Sr}_{2.92}\text{Ca}_{0.01}\text{Si}_{1.03}\text{O}_{5.06}:\text{Eu}_{0.04}$

[73]

[74] As starting materials, CuO (5.57g), SrCO_3 (431.08g), CaCO_3 (1.0g), SiO_2 (61.89g), Eu_2O_3 (14.08g) and/or any combinations thereof are used. The starting materials in form of very pure oxides as well as carbonates are mixed with a surplus of Silica together with small amounts of flux (NH_4 24g). In a first step, the mixture is fired in an alumina crucible at 1,300°C in an inert gas atmosphere for 2~6 hours. After pre-firing, the material is milled again. In a second step, the mixture is fired in an alumina crucible at 1,370°C in weakly reducing atmosphere for additional 6 hours. Then, the material is milled, washed, dried and sieved. The luminescent material has an emission maximum at 586 nm.

[75] In the following table 2, Relative brightness of various non stoichiometric Copper Alkaline Earth Silicates at 25°C, 100°C, 125°C and 150°C compared with YAG and common Silicate phosphors under 455 nm excitation is summarized.

[76]

[77] Table 2

[Table 2]

[Table]

Relative brightness of non-stoichiometric Copper Alkaline Earth Silicates at 25°C, 100°C, 125°C and 150°C compared with YAG and common Silicate phosphors under 455 nm excitation

Composition	Excitation wavelength(nm)	Emission Maximum (nm)	25°C	100°C	125°C	150°C
YAG	455	562	100	92	86	79
(Ba,Sr) ₂ SiO ₄ :Eu(565nm)	455	565	100	92	78	63
(Sr,Ca) ₂ SiO ₄ :Eu(612nm)	455	612	100	87	73	57
Sr _{2.96} SiO ₅ :Eu _{0.04}	455	582	100	96	94	90
Cu _{0.05} Sr _{2.91} Si _{1.05} O _{5.1} :Eu _{0.04}	455	580	100	98	97	94
Cu _{0.05} Sr _{2.51} Ba _{0.4} Si _{1.03} O _{5.06} :Eu _{0.04}	455	600	100	96	95	92
Cu _{0.07} Sr _{2.88} Ca _{0.01} Si _{1.03} O _{5.06} :Eu _{0.04}	455	586	100	95	94	91
Cu _{0.1} Ba _{0.1} Sr _{2.56} Mg _{0.1} Mn _{0.1} Si _{1.06} O _{5.12} :Eu _{0.04}	455	575	100	96	94	92
Cu _{0.1} Ba _{0.2} Sr _{2.46} Mg _{0.1} Ca _{0.1} Si _{1.08} O _{5.16} :Eu _{0.04}	455	572	100	95	94	91
Cu _{0.2} Ba _{0.1} Sr _{2.56} Zn _{0.1} Si _{1.02} O _{5.04} :Eu _{0.04}	455	574	100	97	95	93

[78] Non-stoichiometric Oxy-Orthosilicates also show higher emission efficiency compared with the stoichiometric ones. In both cases the incorporation of Cu²⁺ as host component leads to an improvement of brightness and emission efficiency as can be taken from Fig. 1 for typical orange emitting species.

[79] In the following table 3, sensitivity of non stoichiometric Copper containing new phosphors against humidity and temperature compared to common Silicate phosphors is summarized. Here, the brightness is measured under 450 nm excitation wavelength with time exposed to the condition of 85°C temperature and saturated humidity.

[80]

[81] Table 3

[Table 3]

[Table]

Sensitivity of non stoichiometric Copper containing new phosphors against humidity and temperature compared to common Silicate phosphors

Sample	Brightness[%]					
	0 hrs	24 hrs	100 hrs	200 hrs	500 hrs	1000 hrs
Commercial yellow Orthosilicate (565nm)	100	98.3	98.7	93.3	84.7	79.3
Example 1	100	99.6	99.2	97.8	94.8	91.5
Example 2	100	98.9	99.1	96.4	93.9	90.7
Example 3	100	99.0	98.7	98.2	95.4	93.8

[82] All new phosphors show a much better stability against water and humidity than common Orthosilicates as can be taken from table 3.

【Claims】

【Claim 1】

Non stoichiometric luminescent material for light emitting device, the non stoichiometric luminescent material being an Oxyorthosilicate phosphor having tetragonal crystal structure and having more silicon in the crystal lattice than that in the crystal lattice of Oxyorthosilicate phosphors having stoichiometric tetragonal crystal structure.

【Claim 2】


Non stoichiometric luminescent material according to claim 1, wherein the luminescent material contains divalent Copper within the matrix and Europium as activator.

【Claim 3】

Non stoichiometric luminescent material according to claim 1 or 2, wherein the luminescent material is excited by radiation between 250 nm and 500 nm.

【Claim 4】

Non stoichiometric luminescent material according to claim 1 or 2, wherein the luminescent material comprises a silicate represented as the formula



wherein, $u+v+w+x=1$, $y=z+a$, $z \geq 2$, $0 < x \leq 1$, $0 < a \leq 0.5$ and $0 < b < 0.5$.

【Claim 5】

Non stoichiometric luminescent material according to claim 1 or 2, wherein the luminescent material emits light at the long-wave side of the exciting radiation.

【Claim 6】

Non stoichiometric luminescent material according to claim 1 or 2, wherein the luminescent material emits light having wavelength between 500 nm and 630 nm.

【Claim 7】

Non stoichiometric luminescent material according to claim 1 or 2, wherein the luminescent material is used in combination with a light emitting device emitting excitation radiation to produce white light or color on demand.

【Claim 8】

Non stoichiometric luminescent material according to claim 1 or 2, wherein the luminescent material is used in combination with a primary blue emitting device to produce white light with color temperature between 2000K and 10000K and CRI of $R_a=80\sim95$.

【Claim 9】

Non stoichiometric luminescent material according to claim 1 or 2, wherein the luminescent material is made by a multi-step high temperature solid state reaction between starting materials comprising a surplus of SiO_2 and metal compounds which decompose at high temperatures into oxides.

【Claim 10】

Non stoichiometric luminescent material according to claim 9, wherein the temperature of each step of the multi-step high temperature solid state reaction is between 800°C and 1550°C .