

HIGH TRANSMISSION GLASSES

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This application claims the benefit of priority under 35 U.S.C. § 119 of U.S. Provisional Application Serial No. 62/479497 filed on March 31, 2017, the content of which is relied upon and incorporated herein by reference in its entirety.

BACKGROUND

[0002] Side lit back light units include a light guide plate (LGP) that is usually made of high transmission plastic materials such as polymethylmethacrylate (PMMA). Although such plastic materials present excellent properties such as light transmission, these materials exhibit relatively poor mechanical properties such as rigidity, coefficient of thermal expansion (CTE) and moisture absorption.

[0003] Accordingly, it would be desirable to provide an improved light guide plate having attributes that achieve an improved optical performance in terms of light transmission, solarization, scattering and light coupling as well as exhibiting exceptional mechanical performance in terms of rigidity, CTE, and moisture absorption.

SUMMARY

[0004] Examples of the subject matter pertain to compounds, compositions, articles, devices, and methods for the manufacture of light guide plates and back light units including such light guide plates made from glass. In some examples, light guide plates (LGPs) are provided that have similar or superior optical properties to light guide plates made from PMMA and that have exceptional mechanical properties such as rigidity, CTE and dimensional stability in high moisture conditions as compared to PMMA light guide plates.

[0005] Principles and examples of the present subject matter relate in some examples to a light guide plate for use in a backlight unit. In some examples the glass article or light guide plate (in some examples) can comprise a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face, forming four edges around the front and back faces, wherein the glass sheet comprises between about 70 mol % to about 85 mol% SiO₂, between about 0 mol% to about 5 mol% Al₂O₃, between about 0 mol% to about 5 mol% B₂O₃, between about 0 mol% to about 10 mol% Na₂O, between about 0 mol% to about 12 mol% K₂O, between

about 0 mol% to about 4 mol% ZnO, between about 3 mol% to about 12 mol% MgO, between about 0 mol% to about 5 mol% CaO, between about 0 mol% to about 3 mol% SrO, between about 0 mol% to about 3 mol% BaO, and between about 0.01 mol% to about 0.5 mol% SnO₂.

[0005a] The present disclosure relates to a glass article comprising a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face, forming four edges around the front and back faces, wherein the glass sheet comprises between about 70 mol % to about 85 mol% SiO₂, between about 0 mol% to about 5 mol% Al₂O₃, between about 0 mol% to about 5 mol% B₂O₃, between about 0 mol% to about 10 mol% Na₂O, between about 0 mol% to about 12 mol% K₂O, between about 0 mol% to about 4 mol% ZnO, between about 3 mol% to about 12 mol% MgO, between about 0 mol% to about 5 mol% CaO, between about 0 mol% to about 3 mol% SrO, between about 0 mol% to about 3 mol% BaO, and between about 0.01 mol% to about 0.5 mol% SnO₂.

[0006] The present disclosure relates to a glass article comprising a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet comprises greater than about 80 mol % SiO₂, between about 0 mol% to about 0.5 mol% Al₂O₃, between about 0 mol% to about 0.5 mol% B₂O₃, between about 0 mol% to about 0.5 mol% Na₂O, between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, between about 0 mol% to about 0.5 mol% CaO, between about 0 mol% to about 0.5 mol% SrO, between about 0 mol% to about 0.5 mol% BaO, and between about 0.01 mol% to about 0.11 mol% SnO₂.

[0007] The present disclosure relates to a glass article comprising a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet is substantially free of Al₂O₃ and B₂O₃ and comprises greater than about 80 mol % SiO₂, between about 0 mol% to about 0.5 mol% Na₂O, between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, and between about 0.01 mol% to about 0.11 mol% SnO₂. In some examples, the glass sheet is substantially free of B₂O₃, Na₂O, CaO, SrO, or BaO, and combinations thereof.

[0008] The present disclosure relates to a glass article comprising a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet comprises an alumina free, potassium silicate composition comprising greater than about 80 mol % SiO_2 , between about 8 mol% to about 11 mol% K_2O , between about 0.01 mol% to about 4 mol% ZnO , between about 6 mol% to about 10 mol% MgO , and between about 0.01 mol% to about 0.11 mol% SnO_2 . In some examples, the glass sheet is substantially free of B_2O_3 , Na_2O , CaO , SrO , or BaO , and combinations thereof.

[0009] The present disclosure relates to a glass article comprising a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the

glass sheet comprises between about 72.82 mol % to about 82.03 mol% SiO₂, between about 0 mol% to about 4.8 mol% Al₂O₃, between about 0 mol% to about 2.77 mol% B₂O₃, between about 0 mol% to about 9.28 mol% Na₂O, between about 0.58 mol% to about 10.58 mol% K₂O, between about 0 mol% to about 2.93 mol% ZnO, between about 3.1 mol% to about 10.58 mol% MgO, between about 0 mol% to about 4.82 mol% CaO, between about 0 mol% to about 1.59 mol% SrO, between about 0 mol% to about 3 mol% BaO, and between about 0.08 mol% to about 0.15 mol% SnO₂. In further examples, the glass sheet is substantially free of Al₂O₃, B₂O₃, Na₂O, CaO, SrO, or BaO, and combinations thereof.

[0009a] In one aspect, the present disclosure relates to a glass article comprising a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet comprises between 72.82 mol % to 82.03 mol% SiO₂, between 0 mol% to 4.8 mol% Al₂O₃, between 0 mol% to 2.77 mol% B₂O₃, between 0 mol% to 9.28 mol% Na₂O, between 0.58 mol% to 10.58 mol% K₂O, between 0 mol% to 2.93 mol% ZnO, between 3.1 mol% to 10.58 mol% MgO, between 0 mol% to 4.82 mol% CaO, between 0 mol% to 1.59 mol% SrO, between 0 mol% to 3 mol% BaO, and between 0.08 mol% to 0.15 mol% SnO₂, wherein the glass has a color shift < 0.005 and wherein the glass article is a light guide plate. In further examples, the glass sheet is substantially free of Al₂O₃, B₂O₃, Na₂O, CaO, SrO, or BaO, and combinations thereof.

[00010] The present disclosure relates to a glass article comprising a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet is substantially free of Al₂O₃ and B₂O₃ and comprises greater than about 80 mol % SiO₂, and wherein the glass has a color shift < 0.005. In some examples, the glass sheet comprises between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, and between about 0.01 mol% to about 0.11 mol% SnO₂.

[00011] The present disclosure relates to a glass article comprising a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet is substantially free of Al₂O₃, B₂O₃, Na₂O, CaO, SrO, and BaO, and wherein the glass has a color shift < 0.005. In some examples, the glass sheet comprises greater than about 80 mol % SiO₂. In some examples, the glass sheet comprises between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, and between about 0.01 mol% to about 0.11 mol% SnO₂.

art from that description or recognized by practicing the methods as described herein, including the detailed description which follows, the claims, as well as the appended drawings.

[00013] It is to be understood that both the foregoing general description and the following detailed description present various examples of the disclosure, and are intended to provide an overview or framework for understanding the nature and character of

the claims. The accompanying drawings are included to provide a further understanding of the disclosure, and are incorporated into and constitute a part of this specification. The drawings illustrate various examples of the disclosure and together with the description serve to explain the principles and operations of the disclosure.

BRIEF DESCRIPTION OF THE DRAWINGS

[00014] The following detailed description can be further understood when read in conjunction with the following drawings.

[00015] FIG. 1 is a pictorial illustration of an exemplary embodiment of a light guide plate;

[00016] FIG. 2 is a graph showing percentage light coupling versus distance between an LED and LGP edge;

[00017] FIG. 3 is a cross sectional illustration of an exemplary LCD panel with a LGP in accordance with one or more embodiments;

[00018] FIG. 4 is a cross sectional illustration of an exemplary LCD panel with a LGP according to another embodiment; and

[00019] FIG. 5 is a pictorial illustration showing an LGP with adhesion pads according to additional embodiments.

DETAILED DESCRIPTION

[00020] Described herein are light guide plates, methods of making light guide plates and backlight units utilizing light guide plates in accordance with embodiments of the present invention.

[00021] Current light guide plates used in LCD backlight applications are typically made from PMMA material since this is one of the best materials in term of optical transmission in the visible spectrum. However, PMMA presents mechanical problems that make large size (e.g., 50 inch diagonal and greater) displays challenging in term of mechanical design, such as, rigidity, moisture absorption, and coefficient of thermal expansion (CTE).

[00022] Exemplary LGPs made from glass, however, have an advantage over those made from plastics such as PMMA due to the increased rigidity, better moisture absorption, and low CTE of glass. Exemplary LGPs according to the instant disclosure can provide a

plates the color shift Δy can be reported as $\Delta y = y(L_2) - y(L_1)$ where L_2 and L_1 are Z positions along the panel or substrate direction away from the source launch (e.g., LED or otherwise) and where $L_2 - L_1 = 0.5$ meters, wherein smaller differences between point 1 and point 2 translate to less color shift in the respective LGP. To achieve a low color shift, an exemplary LGP absorption curve should take on a certain shape, e.g., blue absorption at 450nm should be lower than red absorption at 630nm. Thus, the lower the blue absorption is relative to the red absorption, the lower the color shift in the LGP. Control of optical absorption in exemplary embodiments, specifically, that of Cr and Ni can be achieved by manipulating the optical basicity of the glass.

[00023] With regard to rigidity, conventional LCD panels are made of two pieces of thin glass (color filter substrate and TFT substrate) with a PMMA light guide and a plurality of thin plastic films (diffusers, dual brightness enhancement films (DBEF) films, etc.). Due to the poor elastic modulus of PMMA, the overall structure of the LCD panel does not have sufficient rigidity, and additional mechanical structure is necessary to provide stiffness for the LCD panel. It should be noted that PMMA generally has a Young's modulus of about 2 GPa, while certain exemplary glasses have a Young's modulus ranging from about 60 GPa to 90 GPa or more.

[00024] Regarding moisture absorption, humidity testing shows that PMMA is sensitive to moisture and size can change by about 0.5%. For a PMMA panel having a length of one meter, this 0.5% change can increase the length by 5mm, which is significant and makes the mechanical design of a corresponding backlight unit challenging. Conventional means to solve this problem is leaving an air gap between the light emitting diodes (LEDs) and the PMMA light guide plate (LGP) to let the material expand. A problem with this approach is that light coupling is extremely sensitive to the distance from the LEDs to the LGP, which can cause the display brightness to change as a function of humidity. FIG. 2 is a graph showing percentage light coupling versus distance between an LED and LGP edge. With reference to FIG. 2, a relationship is shown which illustrates the drawbacks of conventional measures to solve challenges with PMMA. More specifically, FIG. 2 illustrates a plot of light coupling versus LED to LGP distance assuming both are 2mm in height. It can be observed that the further the distance between LED and LGP, a less efficient light coupling is made between the LED and LGP.

[00025] With regard to CTE, the CTE of PMMA is about $75 \times 10^{-6} \text{ } ^\circ\text{C}^{-1}$ and has relatively low thermal conductivity (0.2 W/m/K) while some glasses have a CTE of about $8 \times 10^{-6} \text{ } ^\circ\text{C}^{-1}$ and a thermal conductivity of 0.8 W/m/K. Of course, the CTE of other glasses can vary and such

a disclosure should not limit the scope of the claims appended herewith. PMMA also has a transition temperature of about 105°C, and when used as an LGP, a PMMA LGP material can become very hot whereby its low conductivity makes it difficult to dissipate heat.

Accordingly, using glass instead of PMMA as a material for light guide plates provides benefits in this regard, but conventional glass has a relatively poor transmission compared to PMMA due mostly to iron and other impurities. Also some other parameters such as surface roughness, waviness, and edge quality polishing can play a significant role on how a glass light guide plate can perform.

[00026] In exemplary embodiments, a LGP can be positioned between layers of optical films (e.g., diffuser, DBEF, etc.) on the front face thereof and a reflector film or other reflector features (e.g., lenticulars, quantum dots etc.) on the back face thereof. The reflector films direct light from the vertical plane of the LGP towards an LCD, and the optical films condition the light for the LCD. When white light interacts with both these layers and the LGP, some light may be lost to scattering and absorption. This loss leads to color shift and/or a decrease in brightness. The magnitude of the color shift seen in the LGP can be dictated by the shape of its absorption curve over the visible spectrum, which in turn can be dictated by the base glass matrix, the concentration of tramp metals, and the tramp metal redox state within the LGP.

[00027] The cost associated with manufacturing LGPs can be dependent upon the glass composition. For example, while melting process parameters can be manipulated to shift the optical absorption demonstrated by a particular glass composition, this cannot be used to completely remove the tramp metal absorption from the visible portion of the spectrum. Additionally, the cost of high purity raw materials (those that are processed to contain very low amounts of tramp metals) are in some cases up to eight times more expensive than standard raw materials. For this reason, it is important to design glass compositions that minimize the use of the most expensive raw materials. Conventional glass LGPs have utilized compositions in the sodium aluminosilicate composition space. However, the cost of such compositions are somewhat prohibitive to profitability and thus exemplary compositions described herein include alumina free, potassium silicate compositions to enable lower cost LGPs.

[00028] FIG. 1 is a pictorial illustration of an exemplary embodiment of a light guide plate. With reference to FIG. 1, an illustration is provided of an exemplary embodiment having a shape and structure of an exemplary light guide plate comprising a sheet of glass 100 having a first face 110, which may be a front face, and a second face opposite the first

face, which may be a back face. The first and second faces may have a height, H, and a width, W. The first and/or second face(s) may have a roughness that is less than 0.6 nm, less than 0.5 nm, less than 0.4 nm, less than 0.3 nm, less than 0.2 nm, less than 0.1 nm, or between about 0.1 nm and about 0.6 nm.

[00029] The glass sheet may have a thickness, T, between the front face and the back face, where the thickness forms four edges. The thickness of the glass sheet may be less than the height and width of the front and back faces. In various embodiments, the thickness of the plate may be less than 1.5% of the height of the front and/or back face. Alternatively, the thickness, T, may be less than about 3 mm, less than about 2 mm, less than about 1 mm, or between about 0.1 mm to about 3 mm. The height, width, and thickness of the light guide plate may be configured and dimensioned for use in an LCD backlight application.

[00030] A first edge 130 may be a light injection edge that receives light provided for example by a light emitting diode (LED). The light injection edge may scatter light within an angle less than 12.8 degrees full width half maximum (FWHM) in transmission. The light injection edge may be obtained by grinding the edge without polishing the light injection edge. The glass sheet may further comprise a second edge 140 adjacent to the light injection edge and a third edge opposite the second edge and adjacent to the light injection edge, where the second edge and/or the third edge scatter light within an angle of less than 12.8 degrees FWHM in reflection. The second edge 140 and/or the third edge may have a diffusion angle in reflection that is below 6.4 degrees. It should be noted that while the embodiment depicted in FIG. 1 shows a single edge 130 injected with light, the claimed subject matter should not be so limited as any one or several of the edges of an exemplary embodiment 100 can be injected with light. For example, in some embodiments, the first edge 130 and its opposing edge can both be injected with light. Such an exemplary embodiment may be used in a display device having a large and or curvilinear width W. Additional embodiments may inject light at the second edge 140 and its opposing edge rather than the first edge 130 and/or its opposing edge. Thicknesses of exemplary display devices can be less than about 10 mm, less than about 9 mm, less than about 8 mm, less than about 7 mm, less than about 6 mm, less than about 5 mm, less than about 4 mm, less than about 3 mm, or less than about 2 mm.

[00031] Generally, LGPs use either white light LEDs or blue light LEDs. The presence of transition metals in the glass causes the formation of absorption bands in the visible light region. These absorption bands can result in a decrease in the amount of light passing through the glass (a viewer would perceive this as a decrease in LCD screen brightness) and result in an increase in color shift. Thus, exemplary embodiments can

maximize brightness and minimize color shift by controlling transition metals including iron, nickel and chromium (each of which are particularly damaging to the transmission of glass and increase color shift due to the location of the bands and the absorption coefficients (intensity) of these bands). Exemplary embodiments described herein, however, minimize the effect of these absorption bands by the structure of the respective glass network which shifts some of these bands to a higher wavelength, e.g., increasing the transmission at 450 and 550 nm. Exemplary alumina free, potassium silicate compositions described herein provide a glass network which was found to decrease the intensity of the absorption bands by changing the equilibrium state of the transition metal (e.g., Cr, Ni) to more be reduced, that is, by decreasing the absorption at lower wavelengths. For example, the Ni absorption in exemplary compositions described herein are better than sodium aluminosilicate compositions due to the use of K_2O in the place of Na_2O . This is due in part to the larger bond length necessitated by K_2O bonding shifting, e.g., Ni absorption away from 450nm towards longer wavelengths. Such a shift dramatically increases an exemplary LGP 450nm transmission and provides a competitive advantage for both color shift and possible use of blue LEDs in LGP assemblies.

[00032] The decrease in the absorption coefficients discovered in exemplary alumina free, potassium silicate compositions provides an additional advantage: the glass can have a higher concentration of tramp metals but still maintain the transmission and the color shift required by the industry. This directly results in an additional cost savings opportunity due to the utilization of lower purity raw materials equating to lower costs. It was also discovered that the exemplary alumina free, potassium silicate compositions described herein results in a reduction in manufacturing costs. For example, manufacturing cost was reduced by changing melting process parameters such as flow. Exemplary alumina free, potassium silicate compositions enable high flow in a fusion draw process which generally requires a viscosity curve that minimizes the difference between the melting viscosity (200P) and the draw viscosity (35kP) to control the cooling rate of the glass melt, and in this situation provide a steeper viscosity curve resulting in a higher the flow rate. Exemplary viscosity curves of embodiments described herein also resulted in an improved melting furnace or tank lifetime due to lower wear of refractory (e.g., zirconia) materials.

[00033] In various embodiments, the glass composition of the glass sheet may comprise less than 50 ppm iron (Fe) concentration. In some embodiments, there may be less than 25 ppm Fe, or in some embodiments the Fe concentration may be about 20 ppm or less.

In additional embodiments, the glass sheet may be formed by a polished float glass, a fusion draw process, a slot draw process, a redraw process, or another suitable forming process.

[00034] According to one or more embodiments, the LGP can be made from a glass comprising colorless oxide components selected from the glass formers SiO_2 , Al_2O_3 , and/or B_2O_3 . The exemplary glass may also include fluxes to obtain favorable melting and forming attributes. Such fluxes include alkali oxides (Li_2O , Na_2O , K_2O , Rb_2O and Cs_2O) and alkaline earth oxides (MgO , CaO , SrO , ZnO and BaO). In one embodiment, the glass contains constituents in the range of between about 70 mol % to about 85 mol% SiO_2 , between about 0 mol% to about 5 mol% Al_2O_3 , between about 0 mol% to about 5 mol% B_2O_3 , between about 0 mol% to about 10 mol% Na_2O , between about 0 mol% to about 12 mol% K_2O , between about 0 mol% to about 4 mol% ZnO , between about 3 mol% to about 12 mol% MgO , between about 0 mol% to about 5 mol% CaO , between about 0 mol% to about 3 mol% SrO , between about 0 mol% to about 3 mol% BaO , and between about 0.01 mol% to about 0.5 mol% SnO_2 . Other glass compositions include a glass sheet having greater than about 80 mol % SiO_2 , between about 0 mol% to about 0.5 mol% Al_2O_3 , between about 0 mol% to about 0.5 mol% B_2O_3 , between about 0 mol% to about 0.5 mol% Na_2O , between about 8 mol% to about 11 mol% K_2O , between about 0.01 mol% to about 4 mol% ZnO , between about 6 mol% to about 10 mol% MgO , between about 0 mol% to about 0.5 mol% CaO , between about 0 mol% to about 0.5 mol% SrO , between about 0 mol% to about 0.5 mol% BaO , and between about 0.01 mol% to about 0.11 mol% SnO_2 . Further glass compositions include a glass sheet that is substantially free of Al_2O_3 and B_2O_3 and comprises greater than about 80 mol % SiO_2 , between about 0 mol% to about 0.5 mol% Na_2O , between about 8 mol% to about 11 mol% K_2O , between about 0.01 mol% to about 4 mol% ZnO , between about 6 mol% to about 10 mol% MgO , and between about 0.01 mol% to about 0.11 mol% SnO_2 . In some embodiments, the glass sheet is substantially free of B_2O_3 , Na_2O , CaO , SrO , or BaO , and combinations thereof.

[00035] Additional glass compositions include a glass sheet that is an alumina free, potassium silicate composition comprising greater than about 80 mol % SiO_2 , between about 8 mol% to about 11 mol% K_2O , between about 0.01 mol% to about 4 mol% ZnO , between about 6 mol% to about 10 mol% MgO , and between about 0.01 mol% to about 0.11 mol% SnO_2 . In some embodiments, the glass sheet is substantially free of B_2O_3 , Na_2O , CaO , SrO , or BaO , and combinations thereof. Further glass compositions include a glass sheet having between about 72.82 mol % to about 82.03 mol% SiO_2 , between about 0 mol% to about 4.8 mol% Al_2O_3 , between about 0 mol% to about 2.77 mol% B_2O_3 , between about 0 mol% to

about 9.28 mol% Na₂O, between about 0.58 mol% to about 10.58 mol% K₂O, between about 0 mol% to about 2.93 mol% ZnO, between about 3.1 mol% to about 10.58 mol% MgO, between about 0 mol% to about 4.82 mol% CaO, between about 0 mol% to about 1.59 mol% SrO, between about 0 mol% to about 3 mol% BaO, and between about 0.08 mol% to about 0.15 mol% SnO₂. In further embodiments, the glass sheet is substantially free of Al₂O₃, B₂O₃, Na₂O, CaO, SrO, or BaO, and combinations thereof.

[00036] Further glass compositions include a glass sheet substantially free of Al₂O₃ and B₂O₃ and comprises greater than about 80 mol % SiO₂, and wherein the glass has a color shift < 0.005. In some embodiments, the glass sheet comprises between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, and between about 0.01 mol% to about 0.11 mol% SnO₂. Additional glass compositions include a glass sheet that is substantially free of Al₂O₃, B₂O₃, Na₂O, CaO, SrO, and BaO, wherein the glass has a color shift < 0.005. In some embodiments, the glass sheet comprises greater than about 80 mol % SiO₂. In some embodiments, the glass sheet comprises between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, and between about 0.01 mol% to about 0.11 mol% SnO₂.

[00037] In some glass compositions described herein, SiO₂ can serve as the basic glass former. In certain embodiments, the concentration of SiO₂ can be greater than 60 mole percent to provide the glass with a density and chemical durability suitable for a display glasses or light guide plate glasses, and a liquidus temperature (liquidus viscosity), which allows the glass to be formed by a downdraw process (e.g., a fusion process). In terms of an upper limit, in general, the SiO₂ concentration can be less than or equal to about 80 mole percent to allow batch materials to be melted using conventional, high volume, melting techniques, e.g., Joule melting in a refractory melter. As the concentration of SiO₂ increases, the 200 poise temperature (melting temperature) generally rises. In various applications, the SiO₂ concentration is adjusted so that the glass composition has a melting temperature less than or equal to 1,750°C. In various embodiments, the mol% of SiO₂ may be in the range of about 70% to about 85%, or in the range of about 72.82% and 82.03%, or alternatively in the range of about 75% to about 85%, or in the range of about 80% to about 85%, and all subranges therebetween. In additional embodiments, the mol% of SiO₂ may be greater than about 80%, greater than about 81%, or greater than about 82%.

[00038] Al₂O₃ is another glass former used to make the glasses described herein. Higher mole percent Al₂O₃ can improve the glass's annealing point and modulus but can

increase melting and batch costs. In various embodiments, the mol% of Al_2O_3 may be in the range of about 0% to about 5%, or alternatively in the range of about 0% to about 4.8%, or in the range of about 0% to about 4%, or in the range of about 0% to about 3%, and all subranges therebetween. In additional embodiments, the mol% of Al_2O_3 may be less than about 0.1%. In other embodiments, the glass is substantially free of Al_2O_3 . For the avoidance of doubt, substantially free should be interpreted to mean that the glass does not have a constituent unless it was intentionally batched or added in the respective melting process and therefore its mol% is negligible or less than 0.01 mol%. With reference to these ranges of Al_2O_3 , manufacturing costs for exemplary embodiments were significantly reduced as Al_2O_3 is an expensive raw material to purchase in pure form.

[00039] B_2O_3 is both a glass former and a flux that aids melting and lowers the melting temperature. It has an impact on both liquidus temperature and viscosity. Increasing B_2O_3 can be used to increase the liquidus viscosity of a glass. To achieve these effects, the glass compositions of one or more embodiments may have B_2O_3 concentrations that are equal to or greater than 0.1 mole percent; however, some compositions may have a negligible amount of B_2O_3 . As discussed above with regard to SiO_2 , glass durability is very important for display applications. Durability can be controlled somewhat by elevated concentrations of alkaline earth oxides, and significantly reduced by elevated B_2O_3 content. Annealing point decreases as B_2O_3 increases, so it may be helpful to keep B_2O_3 content low. Further, it was discovered that B_2O_3 shifts Fe redox to Fe^{3+} thereby impacting the blue transmission. Thus, a reduction in B_2O_3 was found to yield better optical properties in some embodiments. Thus, in various embodiments, the mol% of B_2O_3 may be in the range of about 0% to about 5%, or alternatively in the range of about 0% to about 4%, or in the range of about 0% to about 3%, in the range of about 0% to about 2.77%, and all subranges therebetween. In some embodiments, the glass may be substantially free of B_2O_3 .

[00040] In addition to the glass formers (SiO_2 , Al_2O_3 , and B_2O_3), the glasses described herein also include alkaline earth oxides. In one embodiment, at least three alkaline earth oxides are part of the glass composition, e.g., MgO , CaO , BaO , and SrO . The alkaline earth oxides provide the glass with various properties important to melting, fining, forming, and ultimate use. Accordingly, to improve glass performance in these regards, in one embodiment, the $(\text{MgO}+\text{CaO}+\text{SrO}+\text{BaO})/\text{Al}_2\text{O}_3$ ratio is between 0 and 2.0. As this ratio increases, viscosity tends to decrease more strongly than liquidus temperature, and thus it is increasingly difficult to obtain suitably high values for $T_{35k} - T_{liq}$. In embodiments that are

substantially free of alumina, the ratio $(\text{MgO}+\text{CaO}+\text{SrO}+\text{BaO})/\text{Al}_2\text{O}_3$ cannot be calculated (i.e., Al_2O_3 is zero or negligible).

[00041] For certain embodiments of this disclosure, the alkaline earth oxides may be treated as what is in effect a single compositional component. This is because their impact upon viscoelastic properties, liquidus temperatures and liquidus phase relationships are qualitatively more similar to one another than they are to the glass forming oxides SiO_2 , Al_2O_3 and B_2O_3 . However, the alkaline earth oxides CaO, SrO and BaO can form feldspar minerals, notably anorthite ($\text{CaAl}_2\text{Si}_2\text{O}_8$) and celsian ($\text{BaAl}_2\text{Si}_2\text{O}_8$) and strontium-bearing solid solutions of same, but MgO does not participate in these crystals to a significant degree. Therefore, when a feldspar crystal is already the liquidus phase, a superaddition of MgO may serve to stabilize the liquid relative to the crystal and thus lower the liquidus temperature. At the same time, the viscosity curve typically becomes steeper, reducing melting temperatures while having little or no impact on low-temperature viscosities.

[00042] The inventors have found that the addition of small amounts of MgO may benefit melting by reducing melting temperatures, forming by reducing liquidus temperatures and increasing liquidus viscosity, while preserving high annealing points. In various embodiments, the glass composition comprises MgO in an amount in the range of about 3 mol% to about 12 mol%, or in the range of about 6 mol% to about 10 mol%, or in the range of about 3.1 mol% to about 10.58 mol%, and all subranges therebetween.

[00043] Without being bound by any particular theory of operation, it is believed that calcium oxide present in the glass composition can produce low liquidus temperatures (high liquidus viscosities), high annealing points and moduli, and CTE's in the most desired ranges for display and light guide plate applications. It also contributes favorably to chemical durability, and compared to other alkaline earth oxides, it is relatively inexpensive as a batch material. However, at high concentrations, CaO increases the density and CTE. Furthermore, at sufficiently low SiO_2 concentrations, CaO may stabilize anorthite, thus decreasing liquidus viscosity. Accordingly, in one or more embodiment, the CaO concentration can be between 0 and 5 mol%. In various embodiments, the CaO concentration of the glass composition is in the range of about 0 mol% to about 4.82 mol%, or in the range of about 0 mol% to about 4 mol%, or in the range of about 0 mol% to about 3 mol%, or in the range of about 0 mol% to about 0.5 mol%, or in the range of about 0 mol% to about 0.1 mol%, and all subranges therebetween. In other embodiments, the glass is substantially free of CaO.

[00044] SrO and BaO can both contribute to low liquidus temperatures (high liquidus viscosities). The selection and concentration of these oxides can be selected to avoid an

increase in CTE and density and a decrease in modulus and annealing point. The relative proportions of SrO and BaO can be balanced so as to obtain a suitable combination of physical properties and liquidus viscosity such that the glass can be formed by a downdraw process. In various embodiments, the glass comprises SrO in the range of about 0 to about 2.0 mol%, or between about 0 mol% to about 1.59 mol%, or about 0 to about 1 mol%, and all subranges therebetween. In other embodiments, the glass is substantially free of SrO. In one or more embodiments, the glass comprises BaO in the range of about 0 to about 2 mol%, or between 0 to about 1.5 mol%, or between 0 to about 1.0 mol%, and all subranges therebetween. In other embodiments, the glass is substantially free of BaO.

[00045] In addition to the above components, the glass compositions described herein can include various other oxides to adjust various physical, melting, fining, and forming attributes of the glasses. Examples of such other oxides include, but are not limited to, TiO₂, MnO, V₂O₃, Fe₂O₃, ZrO₂, ZnO, Nb₂O₅, MoO₃, Ta₂O₅, WO₃, Y₂O₃, La₂O₃ and CeO₂ as well as other rare earth oxides and phosphates. In one embodiment, the amount of each of these oxides can be less than or equal to 2.0 mole percent, and their total combined concentration can be less than or equal to 5.0 mole percent. In some embodiments, the glass composition comprises ZnO in an amount in the range of about 0 to about 4.0 mol%, or about 0 to about 3.5 mol%, or about 0 to about 3.01 mol%, or about 0 to about 2.0 mol%, and all subranges therebetween. In other embodiments, the glass composition comprises from about 0.1 mol % to about 1.0 mol % titanium oxide; from about 0.1 mol % to about 1.0 mol % vanadium oxide; from about 0.1 mol % to about 1.0 mol % niobium oxide; from about 0.1 mol % to about 1.0 mol % manganese oxide; from about 0.1 mol % to about 1.0 mol % zirconium oxide; from about 0.1 mol % to about 1.0 mol % tin oxide; from about 0.1 mol % to about 1.0 mol % molybdenum oxide; from about 0.1 mol % to about 1.0 mol % cerium oxide; and all subranges therebetween of any of the above listed transition metal oxides. The glass compositions described herein can also include various contaminants associated with batch materials and/or introduced into the glass by the melting, fining, and/or forming equipment used to produce the glass. The glasses can also contain SnO₂ either as a result of Joule melting using tin-oxide electrodes and/or through the batching of tin containing materials, e.g., SnO₂, SnO, SnCO₃, SnC₂O₂, etc.

[00046] It was also discovered that increasing silica content and/or adding ZnO to some embodiments improved the surface durability of the glass. Thus, in some embodiments the glass composition comprises ZnO in an amount in the range of about 0 to about 4 mol%, or about 0.01 to about 4 mol%, or about 0 to about 2.93 mol%, and all subranges therebetween

[00047] The glass compositions described herein can contain some alkali constituents, e.g., these glasses are not alkali-free glasses. As used herein, an "alkali-free glass" is a glass having a total alkali concentration which is less than or equal to 0.1 mole percent, where the total alkali concentration is the sum of the Na_2O , K_2O , and Li_2O concentrations. In some embodiments, the glass comprises Li_2O in the range of about 0 to about 3.0 mol%, in the range of about 0 to about 2.0 mol%, or in the range of about 0 to about 1.0 mol%, and all subranges therebetween. In other embodiments, the glass is substantially free of Li_2O . In other embodiments, the glass comprises Na_2O in the range of about 0 mol% to about 10 mol%, in the range of about 0 mol% to about 9.28 mol%, in the range of about 0 to about 5 mol%, in the range of about 0 to about 3 mol%, or in the range of about 0 to about 0.5 mol%, and all subranges therebetween. In other embodiments, the glass is substantially free of Na_2O . In some embodiments, the glass comprises K_2O in the range of about 0 to about 12.0 mol%, in the range of about 8 to about 11 mol%, in the range of about 0.58 to about 10.58 mol%, and all subranges therebetween. With reference to these ranges of K_2O , Na_2O , and other alkali materials, it was discovered that contaminant constituent (e.g., Ni, Fe, Cr) absorbance was better due to the larger bond length necessitated by K_2O bonding which shifts the constituent (Ni, Fe, Cr) absorption away from 450 nm towards longer wavelengths. This shift dramatically increases the 450 nm transmission of exemplary embodiments thereby providing a competitive advantage for both color shift and use of blue LEDs in LGPs. Further, it was also unexpectedly discovered that the lower absorption bands of Ni, Fe, and/or Cr allow for the utilization of less pure raw materials while maintaining properties of the current glass which decreases overall cost.

[00048] In some embodiments, the glass compositions described herein can have one or more or all of the following compositional characteristics: (i) an As_2O_3 concentration of at most 0.05 to 1.0 mol%; (ii) an Sb_2O_3 concentration of at most 0.05 to 1.0 mol%; (iii) a SnO_2 concentration of at most 0.25 to 3.0 mol%.

[00049] As_2O_3 is an effective high temperature fining agent for display glasses, and in some embodiments described herein, As_2O_3 is used for fining because of its superior fining properties. However, As_2O_3 is poisonous and requires special handling during the glass manufacturing process. Accordingly, in certain embodiments, fining is performed without the use of substantial amounts of As_2O_3 , i.e., the finished glass has at most 0.05 mole percent As_2O_3 . In one embodiment, no As_2O_3 is purposely used in the fining of the glass. In such cases, the finished glass will typically have at most 0.005 mole percent As_2O_3 as a result of

contaminants present in the batch materials and/or the equipment used to melt the batch materials.

[00050] Although not as toxic as As_2O_3 , Sb_2O_3 is also poisonous and requires special handling. In addition, Sb_2O_3 raises the density, raises the CTE, and lowers the annealing point in comparison to glasses that use As_2O_3 or SnO_2 as a fining agent. Accordingly, in certain embodiments, fining is performed without the use of substantial amounts of Sb_2O_3 , i.e., the finished glass has at most 0.05 mole percent Sb_2O_3 . In another embodiment, no Sb_2O_3 is purposely used in the fining of the glass. In such cases, the finished glass will typically have at most 0.005 mole percent Sb_2O_3 as a result of contaminants present in the batch materials and/or the equipment used to melt the batch materials.

[00051] Compared to As_2O_3 and Sb_2O_3 fining, tin fining (i.e., SnO_2 fining) is less effective, but SnO_2 is a ubiquitous material that has no known hazardous properties. Also, for many years, SnO_2 has been a component of display glasses through the use of tin oxide electrodes in the Joule melting of the batch materials for such glasses. The presence of SnO_2 in display glasses has not resulted in any known adverse effects in the use of these glasses in the manufacture of liquid crystal displays. However, high concentrations of SnO_2 are not preferred as this can result in the formation of crystalline defects in display glasses. In one embodiment, the concentration of SnO_2 in the finished glass is less than or equal to 0.5 mole percent, in the range of about 0.01 to about 0.5 mol%, in the range of about 0.01 to about 0.11 mol%, from about 0.08 to about 0.15 mol%, and all subranges therebetween.

[00052] Tin fining can be used alone or in combination with other fining techniques if desired. For example, tin fining can be combined with halide fining, e.g., bromine fining. Other possible combinations include, but are not limited to, tin fining plus sulfate, sulfide, cerium oxide, mechanical bubbling, and/or vacuum fining. It is contemplated that these other fining techniques can be used alone. In certain embodiments, maintaining the $(\text{MgO}+\text{CaO}+\text{SrO}+\text{BaO})/\text{Al}_2\text{O}_3$ ratio and individual alkaline earth concentrations within the ranges discussed above makes the fining process easier to perform and more effective.

[00053] In one or more embodiments and as noted above, exemplary glasses can have low concentrations of elements that produce visible absorption when in a glass matrix. Such absorbers include transition elements such as Ti, V, Cr, Mn, Fe, Co, Ni and Cu, and rare earth elements with partially-filled f-orbitals, including Ce, Pr, Nd, Sm, Eu, Tb, Dy, Ho, Er and Tm. Of these, the most abundant in conventional raw materials used for glass melting are Fe, Cr and Ni. Iron is a common contaminant in sand, the source of SiO_2 , and is a typical contaminant as well in raw material sources for aluminum, magnesium and calcium.

Chromium and nickel are typically present at low concentration in normal glass raw materials, but can be present in various ores of sand and must be controlled at a low concentration. Additionally, chromium and nickel can be introduced via contact with stainless steel, e.g., when raw material or cullet is jaw-crushed, through erosion of steel-lined mixers or screw feeders, or unintended contact with structural steel in the melting unit itself. The concentration of iron in some embodiments can be specifically less than 50ppm, more specifically less than 40ppm, or less than 25 ppm, and the concentration of Ni and Cr can be specifically less than 5 ppm, and more specifically less than 2ppm. In further embodiments, the concentration of all other absorbers listed above may be less than 1ppm for each. In various embodiments the glass comprises 1 ppm or less of Co, Ni, and Cr, or alternatively less than 1 ppm of Co, Ni, and Cr. In various embodiments, the transition elements (V, Cr, Mn, Fe, Co, Ni and Cu) may be present in the glass at 0.1 wt% or less. In some embodiments, the concentration of Fe can be < about 50 ppm, < about 40 ppm, < about 30 ppm, < about 20 ppm, or < about 10 ppm.

[00054] In other embodiments, it has been discovered that the addition of certain transition metal oxides that do not cause absorption from 300 nm to 650 nm and that have absorption bands < about 300 nm will prevent network defects from forming processes and will prevent color centers (e.g., absorption of light from 300 nm to 650 nm) post UV exposure when curing ink since the bond by the transition metal oxide in the glass network will absorb the light instead of allowing the light to break up the fundamental bonds of the glass network. Thus, exemplary embodiments can include any one or combination of the following transition metal oxides to minimize UV color center formation: from about 0.1 mol % to about 3.0 mol % zinc oxide; from about 0.1 mol % to about 1.0 mol % titanium oxide; from about 0.1 mol % to about 1.0 mol % vanadium oxide; from about 0.1 mol % to about 1.0 mol % niobium oxide; from about 0.1 mol % to about 1.0 mol % manganese oxide; from about 0.1 mol % to about 1.0 mol % zirconium oxide; from about 0.1 mol % to about 1.0 mol % arsenic oxide; from about 0.1 mol % to about 1.0 mol % tin oxide; from about 0.1 mol % to about 1.0 mol % molybdenum oxide; from about 0.1 mol % to about 1.0 mol % antimony oxide; from about 0.1 mol % to about 1.0 mol % cerium oxide; and all subranges therebetween of any of the above listed transition metal oxides. In some embodiments, an exemplary glass can contain from 0.1 mol% to less than or no more than about 3.0 mol% of any combination of zinc oxide, titanium oxide, vanadium oxide, niobium oxide, manganese oxide, zirconium oxide, arsenic oxide, tin oxide, molybdenum oxide, antimony oxide, and cerium oxide.

[00055] Even in the case that the concentrations of transition metals are within the above described ranges, there can be matrix and redox effects that result in undesired absorption. As an example, it is well-known to those skilled in the art that iron occurs in two valences in glass, the +3 or ferric state, and the +2 or ferrous state. In glass, Fe^{3+} produces absorptions at approximately 380, 420 and 435 nm, whereas Fe^{2+} absorbs mostly at IR wavelengths. Therefore, according to one or more embodiments, it may be desirable to force as much iron as possible into the ferrous state to achieve high transmission at visible wavelengths. One non-limiting method to accomplish this is to add components to the glass batch that are reducing in nature. Such components could include carbon, hydrocarbons, or reduced forms of certain metalloids, e.g., silicon, boron or aluminum. However it is achieved, if iron levels were within the described range, according to one or more embodiments, at least 10% of the iron in the ferrous state and more specifically greater than 20% of the iron in the ferrous state, improved transmissions can be produced at short wavelengths. Thus, in various embodiments, the concentration of iron in the glass produces less than 1.1 dB/500 mm of attenuation in the glass sheet.

[00056] LCD panel rigidity

[00057] One attribute of LCD panels is the overall thickness. In conventional attempts to make thinner structures, lack of sufficient stiffness has become a serious problem. Stiffness, however, can be increased with an exemplary glass LGP since the elastic modulus of glass is considerably larger than that of PMMA. In some embodiments, to obtain a maximum benefit from a stiffness point of view, all elements of the panel can be bonded together at the edge.

[00058] FIG. 3 is a cross sectional illustration of an exemplary LCD panel with a LGP in accordance with one or more embodiments. With reference to FIG. 3, an exemplary embodiment of a panel structure 500 is provided. The structure comprises an LGP 100 mounted on a back plate 550 through which light can travel and be redirected toward the LCD or an observer. A structural element 555 may affix the LGP 100 to the back plate 550, and create a gap between the back face of the LGP and a face of the back plate. A reflective and/or diffusing film 540 may be positioned between the back face of the LGP 100 and the back plate 550 to send recycled light back through the LGP 100. A plurality of LEDs, organic light emitting diodes (OLEDs), or cold cathode fluorescent lamps (CCFLs) may be positioned adjacent to the light injection edge 130 of the LGP, where the LEDs have the same width as the thickness of the LGP 100, and are at the same height as the LGP 100. In other embodiments, the LEDs have a greater width and/or height as the thickness of the LGP 100.

Conventional LCDs may employ LEDs or CCFLs packaged with color converting phosphors to produce white light. One or more backlight film(s) 570 may be positioned adjacent the front face of the LGP 100. An LCD panel 580 may also be positioned above the front face of the LGP 100 with a structural element 585, and the backlight film(s) 570 may be located in the gap between the LGP 100 and LCD panel 580. Light from the LGP 100 can then pass through the film 570, which can backscatter high angle light and reflect low angle light back toward the reflector film 540 for recycling and may serve to concentrate light in the forward direction (e.g., toward the user). A bezel 520 or other structural member may hold the layers of the assembly in place. A liquid crystal layer (not shown) may be used and may comprise an electro-optic material, the structure of which rotates upon application of an electric field, causing a polarization rotation of any light passing through it. Other optical components can include, e.g., prism films, polarizers, or TFT arrays, to name a few. According to various embodiments, the angular light filters disclosed herein can be paired with a transparent light guide plate in a transparent display device. In some embodiments, the LGP can be bonded to the structure (using optically clear adhesive OCA or pressure sensitive adhesive PSA) where the LGP is placed in optical contact with some of the structural elements of the panel. In other words, some of the light may leak out of the light guide through the adhesive. This leaked light can become scattered or absorbed by those structural elements. As explained above, the first edge where the LEDs are coupled into the LGP and the two adjacent edges where the light needs to be reflected in TIR can avoid this problem if properly prepared.

[00059] Exemplary widths and heights of the LGP generally depend upon the size of the respective LCD panel. It should be noted that embodiments of the present subject matter are applicable to any size LCD panel whether small (<40" diagonal) or large (>40" diagonal) displays. Exemplary dimensions for LGPs include, but are not limited to, 20", 30", 40", 50", 60" diagonal or more.

[00060] FIG. 4 is a cross sectional illustration of an exemplary LCD panel with a LGP according to another embodiment. With reference to FIG. 4, additional embodiments can utilize a reflective layer. Losses in some embodiments can be minimized by inserting a reflective surface between the LGP and the epoxy by either metalizing the glass with, for instance, silver or inkjet print with reflective ink. In other embodiments, highly reflective films (such as Enhanced Specular Reflector films (made by 3M)) may be laminated with the LGP.

[00061] FIG. 5 is a pictorial illustration showing an LGP with adhesion pads according to additional embodiments. With reference to FIG. 5, adhesion pads instead of a continuous

adhesive can be used in which the pads 600 are shown as a series of dark squares. Thus, to limit the surface of LGP that is optically connected to the structural elements, the illustrated embodiment can employ 5 x 5 mm square pads every 50 mm to provide sufficient adhesion where extracted light is less than 4%. Of course, the pads 600 may be circular or another polygon in form and may be provided in any array or spacing and such a description should not limit the scope of the claims appended herewith.

[00062] Color shift compensation

[00063] In prior glasses although decreasing iron concentration minimized absorption and yellow shift, it was difficult to eliminate it completely. The Δx , Δy in the measured for PMMA for a propagation distance of about 700mm was 0.0021 and 0.0063. In exemplary glasses having the compositional ranges described herein, the color shift Δy was < 0.015 and in exemplary embodiments was less than 0.0021, and less than 0.0063. For example, in some embodiments, the color shift was measured as 0.007842 and in other embodiments was measured as 0.005827. In other embodiments, an exemplary glass sheet can comprise a color shift Δy less than 0.015, such as ranging from about 0.001 to about 0.015 (e.g., about 0.001, 0.002, 0.003, 0.004, 0.005, 0.006, 0.007, 0.008, 0.009, 0.010, 0.011, 0.012, 0.013, 0.014, or 0.015). In other embodiments, the transparent substrate can comprise a color shift less than 0.008, less than about 0.005, or less than about 0.003. Color shift may be characterized by measuring variation in the x and/or y chromaticity coordinates along a length L using the CIE 1931 standard for color measurements for a given source illumination. For exemplary glass light-guide plates the color shift Δy can be reported as $\Delta y = y(L_2) - y(L_1)$ where L_2 and L_1 are Z positions along the panel or substrate direction away from the source launch (e.g., LED or otherwise) and where $L_2 - L_1 = 0.5$ meters. Exemplary light-guide plates described herein have $\Delta y < 0.015$, $\Delta y < 0.005$, $\Delta y < 0.003$, or $\Delta y < 0.001$. The color shift of a light guide plate can be estimated by measuring the optical absorption of the light guide plate, using the optical absorption to calculate the internal transmission of the LGP over 0.5 m, and then multiplying the resulting transmission curve by a typical LED source used in LCD backlights such as the Nichia NFSW157D-E. One can then use the CIE color matching functions to compute the (X,Y,Z) tristimulus values of this spectrum. These values are then normalized by their sum to provide the (x,y) chromaticity coordinates. The difference between the (x,y) values of the LED spectrum multiplied by the 0.5 m LGP transmission and the (x,y) values of the original LED spectrum is the estimate of the color shift contribution of the light guide material. To address residual color shift, several exemplary solutions may be implemented. In one

embodiment, light guide blue painting can be employed. By blue painting the light guide, one can artificially increase absorption in red and green and increase light extraction in blue. Accordingly, knowing how much differential color absorption exists, a blue paint pattern can be back calculated and applied that can compensate for color shift. In one or more embodiments, shallow surface scattering features can be employed to extract light with an efficiency that depends on the wavelength. As an example, a square grating has a maximum of efficiency when the optical path difference equals half of the wavelength. Accordingly, exemplary textures can be used to preferentially extract blue and can be added to the main light extraction texture. In additional embodiments, image processing can also be utilized. For example, an image filter can be applied that will attenuate blue close to the edge where light gets injected. This may require shifting the color of the LEDs themselves to keep the right white color. In further embodiments, pixel geometry can be used to address color shift by adjusting the surface ratio of the RGB pixels in the panel and increasing the surface of the blue pixels far away from the edge where the light gets injected.

[00064] Exemplary compositions as heretofore described can thus be used to achieve a strain point ranging from about 512 °C to about 653 °C, from about 540 °C to about 640 °C, or from about 570 °C to about 610 °C and all subranges therebetween. An exemplary annealing point can range from about 564 °C to about 721 °C, from about 580 °C to about 700 °C, and all subranges therebetween. An exemplary softening point of a glass ranges from about 795 °C to about 1013 °C, from about 820 °C to about 990 °C, or from about 850 °C to about 950 °C and all subranges therebetween. The density of exemplary glass compositions can range from about 2.34 gm/cc @ 20 °C to about 2.56 gm/cc @ 20 °C, from about 2.35 gm/cc @ 20 °C to about 2.55 gm/cc @ 20 °C, or from about 2.4 gm/cc @ 20 °C to about 2.5 gm/cc @ 20 °C and all subranges therebetween. CTEs (0-300 °C) for exemplary embodiments can range from about $64 \times 10^{-7}/^{\circ}\text{C}$ to about $77 \times 10^{-7}/^{\circ}\text{C}$, from about $66 \times 10^{-7}/^{\circ}\text{C}$ to about $75 \times 10^{-7}/^{\circ}\text{C}$, or from about $68 \times 10^{-7}/^{\circ}\text{C}$ to about $73 \times 10^{-7}/^{\circ}\text{C}$ and all subranges therebetween.

[00065] Certain embodiments and compositions described herein have provided an internal transmission from 400-700 nm greater than 90%, greater than 91%, greater than 92%, greater than 93%, greater than 94%, and even greater than 95%. Internal transmittance can be measured by comparing the light transmitted through a sample to the light emitted from a source. Broadband, incoherent light may be cylindrically focused on the end of the material to be tested. The light emitted from the far side may be collected by an integrating sphere fiber coupled to a spectrometer and forms the sample data. Reference data is obtained

by removing the material under test from the system, translating the integrating sphere directly in front of the focusing optic, and collecting the light through the same apparatus as the reference data. The absorption at a given wavelength is then given by:

$$absorption(dB/m) = \frac{-10 \log \frac{T_{sample\ data}}{T_{reference\ data}}}{(Pathlength_{sample\ data} - Pathlength_{reference\ data})}$$

The internal transmittance over 0.5 m is given by:

$$Transmittance(\%) = 100 \times 10^{-absorption \times 0.5/10}$$

Thus, exemplary embodiments described herein can have an internal transmittance at 450 nm with 500 mm in length of greater than 85%, greater than 90%, greater than 91%, greater than 92%, greater than 93%, greater than 94%, and even greater than 95%. Exemplary embodiments described herein can also have an internal transmittance at 550 nm with 500 mm in length of greater than 90%, greater than 91%, greater than 92%, greater than 93%, greater than 94%, and even greater than 96%. Further embodiments described herein can have a transmittance at 630 nm with 500 mm in length of greater than 85%, greater than 90%, greater than 91%, greater than 92%, greater than 93%, greater than 94%, and even greater than 95%.

[00066] In one or more embodiments, the LGP has a width of at least about 1270 mm and a thickness of between about 0.5 mm and about 3.0 mm, wherein the transmittance of the LGP is at least 80% per 500 mm. In various embodiments, the thickness of the LGP is between about 1 mm and about 8 mm, and the width of the plate is between about 1100 mm and about 1300 mm.

[00067] In one or more embodiments, the LGP can be strengthened. For example, certain characteristics, such as a moderate compressive stress (CS), high depth of compressive layer (DOL), and/or moderate central tension (CT) can be provided in an exemplary glass sheet used for a LGP. One exemplary process includes chemically strengthening the glass by preparing a glass sheet capable of ion exchange. The glass sheet can then be subjected to an ion exchange process, and thereafter the glass sheet can be subjected to an anneal process if necessary. Of course, if the CS and DOL of the glass sheet are desired at the levels resulting from the ion exchange step, then no annealing step is required. In other embodiments, an acid etching process can be used to increase the CS on appropriate glass surfaces. The ion exchange process can involve subjecting the glass sheet to a molten salt bath including KNO₃, preferably relatively pure KNO₃ for one or more first temperatures within the range of about 400 - 500 °C and/or for a first time period within the

range of about 1-24 hours, such as, but not limited to, about 8 hours. It is noted that other salt bath compositions are possible and would be within the skill level of an artisan to consider such alternatives. Thus, the disclosure of KNO_3 should not limit the scope of the claims appended herewith. Such an exemplary ion exchange process can produce an initial CS at the surface of the glass sheet, an initial DOL into the glass sheet, and an initial CT within the glass sheet. Annealing can then produce a final CS, final DOL and final CT as desired.

[00068] EXAMPLES

[00069] The following examples are set forth below to illustrate the methods and results according to the disclosed subject matter. These examples are not intended to be inclusive of all embodiments of the subject matter disclosed herein, but rather to illustrate representative methods and results. These examples are not intended to exclude equivalents and variations of the present disclosure which are apparent to one skilled in the art.

[00070] Efforts have been made to ensure accuracy with respect to numbers (e.g., amounts, temperature, etc.) but some errors and deviations should be accounted for. Unless indicated otherwise, temperature is in $^{\circ}\text{C}$ or is at ambient temperature, and pressure is at or near atmospheric. The compositions themselves are given in mole percent on an oxide basis and have been normalized to 100%. There are numerous variations and combinations of reaction conditions, e.g., component concentrations, temperatures, pressures and other reaction ranges and conditions that can be used to optimize the product purity and yield obtained from the described process. Only reasonable and routine experimentation will be required to optimize such process conditions.

[00071] The glass properties set forth herein and in Table 1 below were determined in accordance with techniques conventional in the glass art. Thus, the linear coefficient of thermal expansion (CTE) over the temperature range 25-300 $^{\circ}\text{C}$ is expressed in terms of $\times 10^{-7}/^{\circ}\text{C}$ and the annealing point is expressed in terms of $^{\circ}\text{C}$. These were determined from fiber elongation techniques (ASTM references E228-85 and C336, respectively). The density in terms of grams/cm³ was measured via the Archimedes method (ASTM C693). The melting temperature in terms of $^{\circ}\text{C}$ (defined as the temperature at which the glass melt demonstrates a viscosity of 200 poises) was calculated employing a Fulcher equation fit to high temperature viscosity data measured via rotating cylinders viscometry (ASTM C965-81).

[00072] The liquidus temperature of the glass in terms of $^{\circ}\text{C}$ was measured using the standard gradient boat liquidus method of ASTM C829-81. This involves placing crushed glass particles in a platinum boat, placing the boat in a furnace having a region of gradient

temperatures, heating the boat in an appropriate temperature region for 24 hours, and determining by means of microscopic examination the highest temperature at which crystals appear in the interior of the glass. More particularly, the glass sample is removed from the Pt boat in one piece, and examined using polarized light microscopy to identify the location and nature of crystals which have formed against the Pt and air interfaces, and in the interior of the sample. Because the gradient of the furnace is very well known, temperature vs. location can be well estimated, within 5-10 °C. The temperature at which crystals are observed in the internal portion of the sample is taken to represent the liquidus of the glass (for the corresponding test period). Testing is sometimes carried out at longer times (e.g. 72 hours), to observe slower growing phases. The liquidus viscosity in poises was determined from the liquidus temperature and the coefficients of the Fulcher equation. If included, Young's modulus values in terms of GPa were determined using a resonant ultrasonic spectroscopy technique of the general type set forth in ASTM E1875-00e1.

[00073] The exemplary glasses of the tables herein were prepared using a commercial sand as a silica source, milled such that 90% by weight passed through a standard U.S. 100 mesh sieve. Alumina was the alumina source, periclase was the source for MgO, limestone the source for CaO, strontium carbonate, strontium nitrate or a mix thereof was the source for SrO, barium carbonate was the source for BaO, and tin (IV) oxide was the source for SnO₂. The raw materials were thoroughly mixed, loaded into a platinum vessel suspended in a furnace heated by silicon carbide glowbars, melted and stirred for several hours at temperatures between 1600 and 1650°C to ensure homogeneity, and delivered through an orifice at the base of the platinum vessel. The resulting patties of glass were annealed at or near the annealing point, and then subjected to various experimental methods to determine physical, viscous and liquidus attributes.

[00074] These methods are not unique, and the glasses of the tables herein can be prepared using standard methods well-known to those skilled in the art. Such methods include a continuous melting process, such as would be performed in a continuous melting process, wherein the melter used in the continuous melting process is heated by gas, by electric power, or combinations thereof.

[00075] Raw materials appropriate for producing exemplary glasses include commercially available sands as sources for SiO₂; alumina, aluminum hydroxide, hydrated forms of alumina, and various aluminosilicates, nitrates and halides as sources for Al₂O₃; boric acid, anhydrous boric acid and boric oxide as sources for B₂O₃; periclase, dolomite (also a source of CaO), magnesia, magnesium carbonate, magnesium hydroxide, and various

forms of magnesium silicates, aluminosilicates, nitrates and halides as sources for MgO; limestone, aragonite, dolomite (also a source of MgO), wolastonite, and various forms of calcium silicates, aluminosilicates, nitrates and halides as sources for CaO; and oxides, carbonates, nitrates and halides of strontium and barium. If a chemical fining agent is desired, tin can be added as SnO₂, as a mixed oxide with another major glass component (e.g., CaSnO₃), or in oxidizing conditions as SnO, tin oxalate, tin halide, or other compounds of tin known to those skilled in the art.

[00076] The glasses in the tables herein can contain SnO₂ as a fining agent, but other chemical fining agents could also be employed to obtain glass of sufficient quality for display applications. For example, exemplary glasses could employ any one or combinations of As₂O₃, Sb₂O₃, CeO₂, Fe₂O₃, and halides as deliberate additions to facilitate fining, and any of these could be used in conjunction with the SnO₂ chemical fining agent shown in the examples. Of these, As₂O₃ and Sb₂O₃ are generally recognized as hazardous materials, subject to control in waste streams such as might be generated in the course of glass manufacture or in the processing of TFT panels. It is therefore desirable to limit the concentration of As₂O₃ and Sb₂O₃ individually or in combination to no more than 0.005 mol%.

[00077] In addition to the elements deliberately incorporated into exemplary glasses, nearly all stable elements in the periodic table are present in glasses at some level, either through low levels of contamination in the raw materials, through high-temperature erosion of refractories and precious metals in the manufacturing process, or through deliberate introduction at low levels to fine tune the attributes of the final glass. For example, zirconium may be introduced as a contaminant via interaction with zirconium-rich refractories. As a further example, platinum and rhodium may be introduced via interactions with precious metals. As a further example, iron may be introduced as a tramp in raw materials, or deliberately added to enhance control of gaseous inclusions. As a further example, manganese may be introduced to control color or to enhance control of gaseous inclusions.

[00078] Hydrogen is inevitably present in the form of the hydroxyl anion, OH⁻, and its presence can be ascertained via standard infrared spectroscopy techniques. Dissolved hydroxyl ions significantly and nonlinearly impact the annealing point of exemplary glasses, and thus to obtain the desired annealing point it may be necessary to adjust the concentrations of major oxide components so as to compensate. Hydroxyl ion concentration can be controlled to some extent through choice of raw materials or choice of melting system. For example, boric acid is a major source of hydroxyls, and replacing boric acid with boric oxide

can be a useful means to control hydroxyl concentration in the final glass. The same reasoning applies to other potential raw materials comprising hydroxyl ions, hydrates, or compounds comprising physisorbed or chemisorbed water molecules. If burners are used in the melting process, then hydroxyl ions can also be introduced through the combustion products from combustion of natural gas and related hydrocarbons, and thus it may be desirable to shift the energy used in melting from burners to electrodes to compensate. Alternatively, one might instead employ an iterative process of adjusting major oxide components so as to compensate for the deleterious impact of dissolved hydroxyl ions.

[00079] Sulfur is often present in natural gas, and likewise is a tramp component in many carbonate, nitrate, halide, and oxide raw materials. In the form of SO₂, sulfur can be a troublesome source of gaseous inclusions. The tendency to form SO₂-rich defects can be managed to a significant degree by controlling sulfur levels in the raw materials, and by incorporating low levels of comparatively reduced multivalent cations into the glass matrix. While not wishing to be bound by theory, it appears that SO₂-rich gaseous inclusions arise primarily through reduction of sulfate (SO₄⁼) dissolved in the glass. The elevated barium concentrations of exemplary glasses appear to increase sulfur retention in the glass in early stages of melting, but as noted above, barium is required to obtain low liquidus temperature, and hence high *T_{35k-Tliq}* and high liquidus viscosity. Deliberately controlling sulfur levels in raw materials to a low level is a useful means of reducing dissolved sulfur (presumably as sulfate) in the glass. In particular, sulfur is preferably less than 200ppm by weight in the batch materials, and more preferably less than 100ppm by weight in the batch materials.

[00080] Reduced multivalents can also be used to control the tendency of exemplary glasses to form SO₂ blisters. While not wishing to be bound to theory, these elements behave as potential electron donors that suppress the electromotive force for sulfate reduction. Sulfate reduction can be written in terms of a half reaction such as SO₄⁼ → SO₂ + O₂ + 2e⁻ where e⁻ denotes an electron. The “equilibrium constant” for the half reaction is $K_{eq} = \frac{[SO_2][O_2][e^-]^2}{[SO_4=]}$ where the brackets denote chemical activities. Ideally one would like to force the reaction so as to create sulfate from SO₂, O₂ and 2e⁻. Adding nitrates, peroxides, or other oxygen-rich raw materials may help, but also may work against sulfate reduction in the early stages of melting, which may counteract the benefits of adding them in the first place. SO₂ has very low solubility in most glasses, and so is impractical to add to the glass melting process. Electrons may be “added” through reduced multivalents. For example, an appropriate electron-donating half reaction for ferrous iron (Fe²⁺) is expressed as 2Fe²⁺ → 2Fe³⁺ + 2e⁻

[00081] This “activity” of electrons can force the sulfate reduction reaction to the left, stabilizing SO_4^{2-} in the glass. Suitable reduced multivalents include, but are not limited to, Fe^{2+} , Mn^{2+} , Sn^{2+} , Sb^{3+} , As^{3+} , V^{3+} , Ti^{3+} , and others familiar to those skilled in the art. In each case, it may be important to minimize the concentrations of such components so as to avoid deleterious impact on color of the glass, or in the case of As and Sb, to avoid adding such components at a high enough level so as to complicate waste management in an end-user’s process.

[00082] In addition to the major oxide components of exemplary glasses, and the minor or tramp constituents noted above, halides may be present at various levels, either as contaminants introduced through the choice of raw materials, or as deliberate components used to eliminate gaseous inclusions in the glass. As a fining agent, halides may be incorporated at a level of about 0.4 mol% or less, though it is generally desirable to use lower amounts if possible to avoid corrosion of off-gas handling equipment. In some embodiments, the concentrations of individual halide elements are below about 200ppm by weight for each individual halide, or below about 800ppm by weight for the sum of all halide elements.

[00083] In addition to these major oxide components, minor and tramp components, multivalents and halide fining agents, it may be useful to incorporate low concentrations of other colorless oxide components to achieve desired physical, solarization, optical or viscoelastic properties. Such oxides include, but are not limited to, TiO_2 , ZrO_2 , HfO_2 , Nb_2O_5 , Ta_2O_5 , MoO_3 , WO_3 , ZnO , In_2O_3 , Ga_2O_3 , Bi_2O_3 , GeO_2 , PbO , SeO_3 , TeO_2 , Y_2O_3 , La_2O_3 , Gd_2O_3 , and others known to those skilled in the art. By adjusting the relative proportions of the major oxide components of exemplary glasses, such colorless oxides can be added to a level of up to about 2 mol% to 3 mol% without unacceptable impact to annealing point, *T_{35k-Tliq}* or liquidus viscosity. For example, some embodiments can include any one or combination of the following transition metal oxides to minimize UV color center formation: from about 0.1 mol % to about 3.0 mol % zinc oxide; from about 0.1 mol % to about 1.0 mol % titanium oxide; from about 0.1 mol % to about 1.0 mol % vanadium oxide; from about 0.1 mol % to about 1.0 mol % niobium oxide; from about 0.1 mol % to about 1.0 mol % manganese oxide; from about 0.1 mol % to about 1.0 mol % zirconium oxide; from about 0.1 mol % to about 1.0 mol % arsenic oxide; from about 0.1 mol % to about 1.0 mol % tin oxide; from about 0.1 mol % to about 1.0 mol % molybdenum oxide; from about 0.1 mol % to about 1.0 mol % antimony oxide; from about 0.1 mol % to about 1.0 mol % cerium oxide; and all subranges therebetween of any of the above listed transition metal oxides. In some embodiments, an exemplary glass can contain from 0.1

mol% to less than or no more than about 3.0 mol% of any combination of zinc oxide, titanium oxide, vanadium oxide, niobium oxide, manganese oxide, zirconium oxide, arsenic oxide, tin oxide, molybdenum oxide, antimony oxide, and cerium oxide.

[00084] Table 1 shows examples of glasses (samples 1-106) with high transmissibility as described herein.

TABLE 1

	1	2	3	4	5	6	7
SiO ₂	80.53	80.59	80.24	76.24	79.6	79.13	82.03
Al ₂ O ₃	0	0	0	4.8	0.6	1.71	0
B ₂ O ₃	1.7	0	0	0	0	1.63	2.52
Li ₂ O	0	0	0	0	0	0	0
Na ₂ O	1.4	0	0.96	11.36	1.59	3.14	1.88
K ₂ O	7.61	9.66	8.76	0.58	8.6	6.47	6.92
ZnO	0	1.87	0	0	0	0	0
MgO	7.8	7.7	9.79	6.89	9.49	7	6.54
CaO	0.03	0.03	0.03	0	0	0.03	0
SrO	0	0	0	0	0	0	0
BaO	0.72	0	0	0	0	0.76	0
SnO ₂	0.15	0.1	0.15	0.11	0.1	0.1	0.1
Fe ₂ O ₃	0.06	0.06	0.06	0.02	0.02	0.02	0.02
ZrO ₂	0	0	0	0	0	0	0
R ₂ O/Al ₂ O ₃				2.49	16.98	5.62	
(R ₂ O+RO)/Al ₂ O ₃				3.92	32.80	10.18	
RO/Al ₂ O ₃				1.44	15.82	4.56	
SiO ₂ +Al ₂ O ₃ +B ₂ O ₃	82.23	80.59	80.24	81.04	80.20	82.47	84.55
(SiO ₂ +Al ₂ O ₃ +B ₂ O ₃)-RO	74.40	72.86	70.42	74.15	70.71	75.44	78.01
(SiO ₂ +Al ₂ O ₃ +B ₂ O ₃)-RO-R ₂ O	65.39	63.20	60.70	62.21	60.52	65.83	69.21
(SiO ₂ +B ₂ O ₃)-Al ₂ O ₃	82.23	80.59	80.24	71.44	79.00	79.05	84.55
(SiO ₂ +B ₂ O ₃)-Al ₂ O ₃ -R ₂ O	73.22	70.93	70.52	59.50	68.81	69.44	75.75
(SiO ₂ +B ₂ O ₃)-Al ₂ O ₃ -RO	73.68	72.86	70.42	64.55	69.51	71.26	78.01
R ₂ O - (Al ₂ O ₃ + B ₂ O ₃)	7.31	9.66	9.72	7.14	9.59	6.27	6.28
Strain	564	611	647	549	575	563	568
anneal	618	673	667	602	636	618	622
Soft	866	938.2	927.2	854.7	913.4		863.3
CTE	67	70.2	69.9			66.7	64.5
density	2.399	2.387	2.36	2.387	2.359	2.367	2.366
strain (bbv)	562.3	615.3	590.4	549.8	547.9	562.4	563.1
anneal (bbv)	615.6	671.1	647.9	600.4	632.4	615.2	615.7
last bbv visc	12.0295	12.0147	12.0198	12.003	12.0212	12.0151	656.1
last bbv T	656	714.7	691.4	640.1	676.8	656.2	12.0046
soft (ppv)							
CTE curve (heat)							
CTE curve (cool)							

Poisson							
shear (Mpsi)							
Young's (Mpsi)							
SOC							
nD							
Viscosity							
A	-2.467	-2.838	-2.979	-2.047	-2.96	-2.295	-2.205
B	7072.677	7606.729	8077.687	6539.143	8150.27	7063.69	6643.2
To	168.2	202.6	152.9	174.6	132.8	162.5	188.8
T(200P)	1652	1683	1683	1679	1682	1699	1663
T(400)	1563	1601	1600	1581	1598	1605	1571
T(35K)	1177	1233	1227	1167	1219	1195	1173
T(soft)	747	806	787	728	774	748	744
T(200P) - T(35kP)	475	450	456	512	463	504	490
72hr gradient boat							
air	1260	980	1055	<781	1230	1050	1250
int	1100	955	1040	<781	<843	950	1140
Pt	1085	945	980	<781	<843	950	1140
liq phase	Unknown	Cristobalite /quartz	Cristobalite	No Devit	No Devit	Cristobalite	cristobalite
int liq visc							
T(35kP)-T(liq_int)	77	278	187			245	33

	8	9	10	11	12	13	14
SiO2	78.84	78.63	77.51	80.26	72.82	82.12	81.07
Al2O3	1.39	2.64	2.9	0.95	2.91	0	0
B2O3	0	2.56	1.28	0	0.93	0	1.89
Li2O	0	0	0	0	0	0	0
Na2O	1.3	2.93	4.83	0.01	0.03	0.03	0
K2O	8.54	6.19	4.78	9.78	9.37	8.92	9.16
ZnO	0	0	0	0	0	2.53	0
MgO	9.77	5.57	3.87	8.82	5.43	6.16	7.65
CaO	0.03	0.03	3.32	0.06	4.82	0.03	0.03
SrO	0	0	0	0	1.59	0	0
BaO	0	1.33	1.41	0	2	0	0
SnO2	0.1	0.1	0.1	0.1	0.1	0.15	0.15
Fe2O3	0.02	0.02	0	0	0	0.06	0.06
ZrO2	0	0	0	0.03	0	0	0
R2O/Al2O3	7.08	3.45	3.31	10.31	3.23		
(R2O+RO)/Al2O3	14.13	6.08	6.28	19.65	7.99		
RO/Al2O3	7.05	2.63	2.97	9.35	4.76		
SiO2+Al2O3 +B2O3	80.23	83.83	81.69	81.21	76.66	82.12	82.96
(SiO2+Al2O3 +B2O3)-RO	70.43	78.23	74.50	72.33	64.82	75.93	75.28
(SiO2+Al2O3 +B2O3)-RO-R2O	60.59	69.11	64.89	62.54	55.42	66.98	66.12
(SiO2+B2O3)-Al2O3	77.45	78.55	75.89	79.31	70.84	82.12	82.96
(SiO2+B2O3)-Al2O3-R2O	67.61	69.43	66.28	69.52	61.44	73.17	73.80
(SiO2+B2O3)-Al2O3-RO	67.65	71.62	67.29	70.43	57.00	75.93	75.28
R2O - (Al2O3 + B2O3)	8.45	3.92	5.43	8.84	5.56	8.95	7.27

Strain		558	541	630	596	611	611
anneal		610	590	694	647	672	668
Soft			818.2	973.4	868.7	938.6	914.6
CTE		66	70.6	69.3	77.6	65.3	66.4
density	2.359	2.418	2.46	2.352	2.541	2.389	2.363
strain (bbv)	604.3	558	540.3	630.9	597.4	607	609.8
anneal (bbv)	662.3	609.4	588.2	689.1	647.3	664.1	663.4
last bbv visc	12.0012	12.0093	12.0294	12.0253	12.0122	12.002	12.0259
last bbv T	708.3	649.3	625.4	734.4	686.4	708	704.7
soft (ppv)							
CTE curve (heat)							
CTE curve (cool)							
Poisson	0.2			0.197			
shear (Mpsi)	3.96			3.8			
Young's (Mpsi)	9.5			9.1			
SOC							
nD							
Viscosity							
A	-3.092	-1.843	-1.709	-2.735	-2.14	-2.874	-2.413
B	8336.899	6252.518	5692.936	7588.096	5650.253	7902.572	6733.483
To	156	197.8	210.9	220.3	287.1	176.9	238.4
T(200P)	1702	1707	1631	1727	1559	1704	1667
T(400)	1620	1604	1531	1642	1479	1620	1581
T(35K)	1248	1177	1121	1263	1132	1242	1206
T(soft)	805	737	707	828	762	802	792
T(200P) - T(35kP)	454	530	510	464	427	462	461
72hr gradient boat							
air	1150	935	970	1135	1130	1225	1130
int	945	915	965	<847	975		1050
Pt	945	905	965	<847	975		1020
liq phase	Unknown	Albite	Forsterite	No Devit	Diopside (K silicate)	Unknown	Cristobalite /quartz
int liq visc							
T(35kP)-T(liq_int)	303	262	156	416	157	1242	156

	15	16	17	18	19	20	21
SiO2	80.15	80.48	80.4	78.92	76.96	78.99	81.89
Al2O3	0	0	0	1.59	3.98	1.71	0
B2O3	0	0	0	0	0	1.56	2.71
Li2O	0	0	0	0	0	0	0
Na2O	0	0	0	3.87	9.28	1.46	0
K2O	9.78	9.74	9.73	6.66	2.25	8	8.77
ZnO	0	2.86	0.94	0	0	0	0
MgO	9.83	6.74	8.74	8.83	7.41	7.48	6.5
CaO	0.04	0.03	0.03	0	0	0.03	0
SrO	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0.65	0
SnO2	0.15	0.1	0.1	0.1	0.1	0.1	0.1
Fe2O3	0.06	0.06	0.06	0.02	0.02	0.02	0.02
ZrO2	0	0	0	0	0	0	0
R2O/Al2O3				6.62	2.90	5.53	
(R2O+RO)/Al2O3				12.18	4.76	10.30	
RO/Al2O3				5.55	1.86	4.77	

SiO ₂ +Al ₂ O ₃ +B ₂ O ₃	80.15	80.48	80.40	80.51	80.94	82.26	84.60
(SiO ₂ +Al ₂ O ₃ +B ₂ O ₃)-RO	70.28	73.71	71.63	71.68	73.53	74.75	78.10
(SiO ₂ +Al ₂ O ₃ +B ₂ O ₃)-RO-R ₂ O	60.50	63.97	61.90	61.15	62.00	65.29	69.33
(SiO ₂ +B ₂ O ₃)-Al ₂ O ₃	80.15	80.48	80.40	77.33	72.98	78.84	84.60
(SiO ₂ +B ₂ O ₃)-Al ₂ O ₃ -R ₂ O	70.37	70.74	70.67	66.80	61.45	69.38	75.83
(SiO ₂ +B ₂ O ₃)-Al ₂ O ₃ -RO	70.28	73.71	71.63	68.50	65.57	70.68	78.10
R ₂ O - (Al ₂ O ₃ + B ₂ O ₃)	9.78	9.74	9.73	8.94	7.55	6.19	6.06
Strain		613	616	553	543		608
anneal		674	678	609	596		664
Soft	943	935	944.4	885.4	857		908.5
CTE	70.3	70.5	69.8				64.8
density	2.358	2.404	2.371	2.367	2.383	2.366	2.362
strain (bbv)	614.9	612	614.5	550.9	542.8	588.9	610.9
anneal (bbv)	673	668.5	672.1	606.8	594.8	643.6	664.3
last bbv visc	12.0347	12.0057	12.0234	12.027	12.0159	12.0266	12.008
last bbv T	716.8	712.2	715.9	649.6	635.2	686.1	705
soft (ppv)							
CTE curve (heat)							
CTE curve (cool)							
Poisson							
shear (Mpsi)							
Young's (Mpsi)							
SOC							
nD							
Viscosity							
A	-2.995	-2.766	-2.828	-2.705	-2.221	-2.326	-2.138
B	7911.978	7433.453	7616.818	7816.921	6897.122	7073.181	6347.024
To	190.5	209.1	203.2	119	150.7	193.2	256.4
T(200P)	1684	1676	1688	1681	1676	1722	1686
T(400)	1604	1594	1606	1592	1581	1628	1595
T(35K)	1240	1226	1236	1197	1170	1223	1206
T(soft)	811	803	808	746	726	778	790
T(200P) - T(35kP)	444	450	452	484	506	499	480
72hr gradient boat							
air	<850	980	1060	<736	<816	<840	1225
int	<850	980	<834	<736	<816	<840	1090
Pt	<850	980	<834	<736	<816	<840	1090
liq phase		Cristobalite /quartz	Cristobalite	No Devit	No Devit	trace unknown	cristobalite
int liq visc							
T(35kP)-T(liq_int)		246	402			383	116

	22	23	24	25	26	27	28
SiO ₂	79.86	79.7	74.05	78.75	80.46	80.28	80.99
Al ₂ O ₃	1.7	0	2.91	1.7	1.95	0	0
B ₂ O ₃	2.45	0	1.23	0	0	0	0
Li ₂ O	0	0	0	0	0	0	0
Na ₂ O	2.95	0	4.88	3.77	0.01	0.01	4.77

K2O	6.01	9.35	4.73	6.27	9.6	9.69	4.7
ZnO	0	0	0	0	0	0	2.75
MgO	5.61	10.79	5.29	9.36	7.81	9.83	6.56
CaO	0.03	0.03	4.79	0.03	0.05	0.07	0.03
SrO	0	0	0.01	0	0	0	0
BaO	1.28	0	2	0	0	0	0
SnO2	0.1	0.1	0.11	0.1	0.1	0.09	0.15
Fe2O3	0.02	0.02	0	0.02	0	0	0.06
ZrO2	0	0	0	0	0.03	0.03	0
R2O/Al2O3	5.27		3.30	5.91	4.93		
(R2O+RO)/Al2O3	9.34		7.46	11.43	8.96		
RO/Al2O3	4.07		4.15	5.52	4.03		
SiO2+Al2O3 +B2O3	84.01	79.70	78.19	80.45	82.41	80.28	80.99
(SiO2+Al2O3 +B2O3)-RO	78.37	68.88	68.10	71.06	74.55	70.38	74.40
(SiO2+Al2O3 +B2O3)-RO-R2O	69.41	59.53	58.49	61.02	64.94	60.68	64.93
(SiO2+B2O3)-Al2O3	80.61	79.70	72.37	77.05	78.51	80.28	80.99
(SiO2+B2O3)-Al2O3-R2O	71.65	70.35	62.76	67.01	68.90	70.58	71.52
(SiO2+B2O3)-Al2O3-RO	73.69	68.88	60.28	67.66	70.65	70.38	74.40
R2O - (Al2O3 + B2O3)	4.81	9.35	5.47	8.34	7.66	9.70	9.47
Strain	553		541		644	622	536
anneal	605		588		710	686	590
Soft			805.3		992.4	953.2	849
CTE	65.9		74.2		67.5	70.1	65.9
density	2.416	2.356	2.511	2.367	2.35	2.353	2.408
strain (bbv)	551.9	632.5	538.9	566	648.6	625.6	233.1
anneal (bbv)	602.8	690.6	585.6	621.4	707.8	682.7	585.1
last bbv visc	12.0233	12.0139	12.0311	12.0019	12.0036	12.0132	12.0327
last bbv T	642	735.8	621.7	665.1	754.4	727.7	625.1
soft (ppv)							
CTE curve (heat)							
CTE curve (cool)							
Poisson		0.198		0.202	0.197	0.203	
shear (Mpsi)		3.84		4.11	3.82	3.77	
Young's (Mpsi)		9.19		9.88	9.14	9.07	
SOC							
nD							
Viscosity							
A	-1.986	-3.071	-1.876	-2.687	-2.895	-3.052	-2.454
B	6365.7	7967.918	5521.828	7778.016	8095.232	7967.489	7148.62
To	187.6	207.6	224.4	135.6	211.1	198.9	131.8
T(200P)	1672	1691	1546	1695	1769	1687	1635
T(400)	1575	1612	1457	1606	1684	1608	1546
T(35K)	1162	1254	1084	1211	1299	1248	1153
T(soft)	730	829	699	760	851	821	717
T(200P) - T(35kP)	510	437	462	484	470	439	482
72hr gradient boat							
air	895	<822	1005	<786	900	1205	1230
int	895	<822	1000	<786		<821	1200
Pt	880	<822	980	<786		<821	1200
liq phase	Cristobalite	No Devit	Diopside	No Devit	No Devit	No Devit	Unknown

int liq visc							
T(35kP)-T(liq_int)	267		84		454	428	-47

	29	30	31	32	33	34	35
SiO2	81.57	81.58	81.18	80.03	79.93	78.61	77.81
Al2O3	0	0	0	0.13	0.9	1.74	2.88
B2O3	1.66	1.5	1.01	0	1.6	2.39	2.75
Li2O	0	0	0	0	0	0	0
Na2O	1.39	0.91	0	0.42	1.46	2.95	4.8
K2O	7.58	8.03	9.11	9.53	8.05	6.15	4.66
ZnO	0	0	1.69	0	0	0	0
MgO	6.85	7.74	6.83	9.77	7.16	6.88	3.1
CaO	0.03	0.03	0.03	0	0.03	0.03	2.77
SrO	0	0	0	0	0	0	0
BaO	0.71	0	0	0	0.75	1.13	1.13
SnO2	0.15	0.15	0.08	0.1	0.1	0.1	0.1
Fe2O3	0.06	0.06	0.06	0.02	0.02	0.02	0
ZrO2	0	0	0	0	0	0	0
R2O/Al2O3				76.54	10.57	5.23	3.28
(R2O+RO)/Al2O3				151.69	19.39	9.85	5.72
RO/Al2O3				75.15	8.82	4.62	2.43
SiO2+Al2O3+B2O3	83.23	83.08	82.19	80.16	82.43	82.74	83.44
(SiO2+Al2O3+B2O3)-RO	76.35	75.31	75.33	70.39	75.24	75.83	77.57
(SiO2+Al2O3+B2O3)-RO-R2O	67.38	66.37	66.22	60.44	65.73	66.73	68.11
(SiO2+B2O3)-Al2O3	83.23	83.08	82.19	79.90	80.63	79.26	77.68
(SiO2+B2O3)-Al2O3-R2O	74.26	74.14	73.08	69.95	71.12	70.16	68.22
(SiO2+B2O3)-Al2O3-RO	75.64	75.31	75.33	70.13	72.69	71.22	70.68
R2O - (Al2O3 + B2O3)	7.31	7.44	8.10	9.82	7.01	4.97	3.83
Strain	559	586	606	600		566	540
anneal	614	642	666	662		620	587
Soft	863.9	896.4	917.5	935.7			808
CTE	67.1	65.5	69			64.1	68.2
density	2.395	2.36	2.39	2.354	2.363	2.365	2.449
strain (bbv)	554.9	584.1	604.5	602.8	582.1	565.4	539.3
anneal (bbv)	607.8	638.5	660.5	661.1	636.2	618.4	586.1
last bbv visc	12.021	12.0031	12.0225	12.0238	12.0088	12.0153	12.0055
last bbv T	648	680.6	703.4	706.1	678.4	659.3	622.5
soft (ppv)							
CTE curve (heat)							
CTE curve (cool)							
Poisson							
shear (Mpsi)							
Young's (Mpsi)							
SOC							
nD							
Viscosity							

A	-2.34	-2.386	-2.634	-3.057	-2.324	-2.059	-1.453
B	6842.252	6949.189	7165.241	8100.77 9	6963.842	6659.292	5228.43
To	171.6	197.7	214.7	169.1	192.6	186.1	233.7
T(200P)	1646	1680	1667	1681	1698	1713	1626
T(400)	1556	1591	1583	1601	1606	1615	1523
T(35K)	1166	1200	1213	1235	1207	1195	1106
T(soft)	737	770	793	801	769	750	700
T(200P) - T(35kP)	480	480	454	446	491	518	520
72hr gradient boat							
air	1250	1215	1020	985	980	990	925
int	1105	1110	1020	<786	985	990	930
Pt	1100	1110	1020	<786	990	990	920
liq phase	Unknown	Cristobalite /quartz	Cristobalite /quartz	No Devit	Cristobalite	Cristobalite	Cristobalite
int liq visc							
T(35kP)- T(liq_int)	61	90	193		222	205	176

	36	37	38	39	40	41	42
SiO2	72.36	80.24	80.3	80.48	79.88	81.33	78.94
Al2O3	2.92	1.95	0	0	0.21	1.78	0.53
B2O3	1.25	0	0	0	0	0.9	0
Li2O	0	0	0	0	0	0	0
Na2O	4.86	2.86	4.91	0.98	0.72	0	4.18
K2O	4.75	6.87	4.86	8.75	9.32	9.23	7.55
ZnO	0	0	0	1.86	0	0	0
MgO	5.46	7.9	9.68	7.75	9.74	6.62	8.64
CaO	4.73	0.05	0.04	0.03	0	0	0.03
SrO	1.58	0	0	0	0	0	0
BaO	1.99	0	0	0	0	0	0
SnO2	0.1	0.1	0.15	0.1	0.1	0.1	0.1
Fe2O3	0	0	0.06	0.06	0.02	0.02	0.02
ZrO2	0	0.03	0	0	0	0	0
R2O/Al2O3	3.29	4.99			47.81	5.19	22.13
(R2O+RO)/Al2O3	8.00	9.07			94.19	8.90	38.49
RO/Al2O3	4.71	4.08			46.38	3.72	16.36
SiO2+Al2O3 +B2O3	76.53	82.19	80.30	80.48	80.09	84.01	79.47
(SiO2+Al2O3 +B2O3)-RO	64.76	74.24	70.58	72.70	70.35	77.39	70.80
(SiO2+Al2O3 +B2O3)-RO-R2O	55.15	64.51	60.81	62.97	60.31	68.16	59.07
(SiO2+B2O3)-Al2O3	70.69	78.29	80.30	80.48	79.67	80.45	78.41
(SiO2+B2O3)- Al2O3-R2O	61.08	68.56	70.53	70.75	69.63	71.22	66.68
(SiO2+B2O3)- Al2O3-RO	56.93	70.34	70.58	72.70	69.93	73.83	69.74
R2O - (Al2O3 + B2O3)	5.44	7.78	9.77	9.73	9.83	6.55	11.20
Strain	537	577	531	549	592	625	
anneal	584	637	587	640	654	687	
Soft	795	933	853	907.5	930.5	960.7	

CTE	76.9	69.1	68.3	70.4		65.5	
density	2.56	2.356	2.365	2.39	2.356	2.35	2.37
strain (bbv)	536.1	576.2	534.3	583.9	596.2	631.9	512.1
anneal (bbv)	582.1	633.6	587.3	640.1	653.2	689	564.1
last bbv visc	12.0253	12.0103	12.0096	12.0014	12.0269	12.0091	12.0192
last bbv T	617.9	678.5	627.2	684.2	697.5	732.8	604.5
soft (ppv)							
CTE curve (heat)							
CTE curve (cool)							
Poisson		0.184					0.201
shear (Mpsi)		4.06					3.96
Young's (Mpsi)		9.69					9.51
SOC							
nD							
Viscosity							
A	-1.854	-2.02	-2.592	-2.818	-3.072	-2.476	-2.501
B	5298.62	6432.263	7462.031	7670.71	8209.559	7389.733	7259.613
To	236.2	220	116.2	166.6	153.8	222.6	104.6
T(200P)	1511	1709	1641	1665	1682	1770	1616
T(400)	1425	1612	1553	1582	1601	1678	1527
T(35K)	1064	1200	1162	1209	1232	1275	1135
T(soft)	692	766	720	776	794	827	697
T(200P) - T(35kP)	447	509	479	456	450	495	481
72hr gradient boat							
air	>1245	<781	1210	1010	<756	1020	<812
int	1015	<781	1145	1010	<756	1020	<812
Pt	980	<781	1145	1005	<756	1015	<812
liq phase	Diopside	No Devit	Unknown	Cristobalite/quartz	No Devit	unknown	No Devit
int liq visc							
T(35kP)-T(liq_int)	49	419	17	199		255	

	43	44	45	46	47	48	49
SiO2	77.81	80.24	81.33	80.85	81.05	77.37	81.71
Al2O3	2.85	1.95	0	0	0	3.54	0.84
B2O3	2.77	0	0	1.98	1.9	0	1.73
Li2O	0	0	0	0	0	0	0
Na2O	4.85	5.84	1.97	1.89	0	8.26	0
K2O	4.71	3.92	8.7	7.39	9.26	3.02	9.01
ZnO	0	0	0	0	1.85	0	0
MgO	5.74	7.88	7.76	7.65	5.76	7.68	6.58
CaO	0.03	0.05	0.03	0.03	0.02	0	0
SrO	0	0	0	0	0	0	0
BaO	1.13	0	0	0	0	0	0
SnO2	0.1	0.09	0.15	0.15	0.1	0.1	0.1
Fe2O3	0	0	0.06	0.06	0.06	0.02	0.02
ZrO2	0	0.03	0	0	0	0	0
R2O/Al2O3	3.35	5.01				3.19	10.73
(R2O+RO)/Al2O3	5.78	9.07				5.36	18.56
RO/Al2O3	2.42	4.07				2.17	7.83
SiO2+Al2O3 +B2O3	83.43	82.19	81.33	82.83	82.95	80.91	84.28
(SiO2+Al2O3 +B2O3)-RO	77.66	74.26	73.54	75.15	77.17	73.23	77.70
(SiO2+Al2O3	68.10	64.50	62.87	65.87	67.91	61.95	68.69

+B2O3)-RO-R2O							
(SiO2+B2O3)-Al2O3	77.73	78.29	81.33	82.83	82.95	73.83	82.60
(SiO2+B2O3)-Al2O3-R2O	68.17	68.53	70.66	73.55	73.69	62.55	73.59
(SiO2+B2O3)-Al2O3-RO	70.83	70.36	73.54	75.15	77.17	66.15	76.02
R2O - (Al2O3 + B2O3)	3.94	7.81	10.67	7.30	7.36	7.74	6.44
Strain	545	552	528	566	605	542	616
anneal	594	610	585	620	662	595	674
Soft	830.2	893.4	850.8	862.3	906	861.8	934.4
CTE	67.9	66.8			67.2		65.2
density	2.425	2.359	2.361	2.372	2.397	2.38	2.355
strain (bbv)	543.6	564.6	524.4	567.9	604.9	541.3	615.8
anneal (bbv)	591.9	614.8	579.3	620	659	593.4	671.3
last bbv visc	12.0214	12.0076	12.0342	12.0058	12.0213	12.0102	12.0256
last bbv T	629.5	654	620.8	659.6	700.5	634.1	714
soft (ppv)							
CTE curve (heat)							
CTE curve (cool)							
Poisson		0.186					
shear (Mpsi)		4.2					
Young's (Mpsi)		9.95					
SOC							
nD							
Viscosity							
A	-1.583	-2.236	-2.634	-2.301	-2.102	-2.282	-2.368
B	5761.239	7082.798	7705.419	6681.202	6169.221	7075.248	6852.746
To	206	156.8	95.6	192.7	263.9	138.9	237.9
T(200P)	1689	1718	1657	1644	1665	1683	1706
T(400)	1583	1621	1567	1555	1575	1588	1617
T(35K)	1146	1201	1169	1169	1192	1175	1229
T(soft)	714	747	717	747	784	726	803
T(200P) - T(35kP)	543	517	488	475	473	508	477
72hr gradient boat							
air	870	1050	1210	1250	1020	<727	1110
int	860	1020	1015	1070	1020	<727	965
Pt	880	1015	1015	1075	1010	<727	965
liq phase	Cristobalite	Cristobalite	Cristobalite/quartz	Cristobalite/quartz	Cristobalite/quartz	No Devit	cristobalite
int liq visc							
T(35kP)-T(liq_int)	286	181	154	99	172		264

	50	51	52	53
SiO2	80.1	77.67	80.49	82.25
Al2O3	0.38	3.45	2.94	0
B2O3	0	0	0	1.75
Li2O	0	0	0	0
Na2O	0	7.67	0.01	1.88
K2O	10.58	3.14	9.54	8.11
ZnO	0	0	0	0
MgO	8.78	7.91	6.87	5.78
CaO	0.03	0.03	0.02	0.02
SrO	0	0	0	0

BaO	0	0	0	0
SnO2	0.1	0.1	0.1	0.15
Fe2O3	0.02	0.02	0	0.06
ZrO2	0	0	0.03	0
R2O/Al2O3	27.84	3.13	3.25	
(R2O+RO)/Al2O3	51.03	5.43	5.59	
RO/Al2O3	23.18	2.30	2.34	
SiO2+Al2O3 +B2O3	80.48	81.12	83.43	84.00
(SiO2+Al2O3 +B2O3)-RO	71.67	73.18	76.54	78.20
(SiO2+Al2O3 +B2O3)-RO-R2O	61.09	62.37	66.99	68.21
(SiO2+B2O3)-Al2O3	79.72	74.22	77.55	84.00
(SiO2+B2O3)-Al2O3-R2O	69.14	63.41	68.00	74.01
(SiO2+B2O3)-Al2O3-RO	70.91	66.28	70.66	78.20
R2O - (Al2O3 + B2O3)	10.20	7.36	6.61	8.24
Strain			653	535
anneal			721	590
Soft			1013.6	835.5
CTE			66.3	
density	2.356	2.372	2.347	2.369
strain (bbv)	599.8	552	658.4	535.9
anneal (bbv)	656.5	605	719.4	588.3
last bbv visc	12.0187	12.0067	12.0034	12.0284
last bbv T	700.8	646.6	767.4	628
soft (ppv)				
CTE curve (heat)				
CTE curve (cool)				
Poisson	0.196	0.197	0.197	
shear (Mpsi)	3.72	4.24	3.86	
Young's (Mpsi)	8.9	10.14	9.24	
SOC				
nD				
Viscosity				
A	-2.759	-2.273	-2.928	-2.051
B	7511.478	7130.141	8440.123	6304.72
To	201.5	147.2	202.2	180.4
T(200P)	1686	1706	1816	1629
T(400)	1603	1610	1728	1535
T(35K)	1230	1193	1332	1136
T(soft)	802	740	867	714
T(200P) - T(35kP)	456	513	484	493
72hr gradient boat				
air	<817	910	1145	1205
int	<817	<781	925	1125
Pt	<817	<781		1110
liq phase	No Devit	unknown	unknown	Cristobalite /quartz
int liq visc				
T(35kP)-T(liq_int)			407	11

[00085] As noted in the above table an exemplary glass article in some embodiments can comprise a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face, forming four edges around the front and back faces, wherein the glass sheet comprises between about 70 mol % to about 85 mol% SiO₂, between about 0 mol% to about 5 mol% Al₂O₃, between about 0 mol% to about 5 mol% B₂O₃, between about 0 mol% to about 10 mol% Na₂O, between about 0 mol% to about 12 mol% K₂O, between about 0 mol% to about 4 mol% ZnO, between about 3 mol% to about 12 mol% MgO, between about 0 mol% to about 5 mol% CaO, between about 0 mol% to about 3 mol% SrO, between about 0 mol% to about 3 mol% BaO, and between about 0.01 mol% to about 0.5 mol% SnO₂.

[00086] In other embodiments, the glass article can comprise a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet comprises greater than about 80 mol % SiO₂, between about 0 mol% to about 0.5 mol% Al₂O₃, between about 0 mol% to about 0.5 mol% B₂O₃, between about 0 mol% to about 0.5 mol% Na₂O, between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, between about 0 mol% to about 0.5 mol% CaO, between about 0 mol% to about 0.5 mol% SrO, between about 0 mol% to about 0.5 mol% BaO, and between about 0.01 mol% to about 0.11 mol% SnO₂.

[00087] In further embodiments, the glass article can comprise a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet is substantially free of Al₂O₃ and B₂O₃ and comprises greater than about 80 mol % SiO₂, between about 0 mol% to about 0.5 mol% Na₂O, between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, and between about 0.01 mol% to about 0.11 mol% SnO₂. In some embodiments, the glass sheet is substantially free of B₂O₃, Na₂O, CaO, SrO, or BaO, and combinations thereof.

[00088] In additional embodiments, the glass article can comprise a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet comprises an alumina free, potassium silicate composition comprising greater than about 80 mol % SiO₂, between about 8 mol% to about 11 mol% K₂O, between

about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, and between about 0.01 mol% to about 0.11 mol% SnO₂. In some embodiments, the glass sheet is substantially free of B₂O₃, Na₂O, CaO, SrO, or BaO, and combinations thereof.

[00089] In some embodiments, the glass article can comprise a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet comprises between about 72.82 mol % to about 82.03 mol% SiO₂, between about 0 mol% to about 4.8 mol% Al₂O₃, between about 0 mol% to about 2.77 mol% B₂O₃, between about 0 mol% to about 9.28 mol% Na₂O, between about 0.58 mol% to about 10.58 mol% K₂O, between about 0 mol% to about 2.93 mol% ZnO, between about 3.1 mol% to about 10.58 mol% MgO, between about 0 mol% to about 4.82 mol% CaO, between about 0 mol% to about 1.59 mol% SrO, between about 0 mol% to about 3 mol% BaO, and between about 0.08 mol% to about 0.15 mol% SnO₂. In further embodiments, the glass sheet is substantially free of Al₂O₃, B₂O₃, Na₂O, CaO, SrO, or BaO, and combinations thereof.

[00090] In further embodiments, the glass article can comprise a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet is substantially free of Al₂O₃ and B₂O₃ and comprises greater than about 80 mol % SiO₂, and wherein the glass has a color shift < 0.005. In some embodiments, the glass sheet comprises between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, and between about 0.01 mol% to about 0.11 mol% SnO₂.

[00091] In additional embodiments, the glass article can comprise a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces, wherein the glass sheet is substantially free of Al₂O₃, B₂O₃, Na₂O, CaO, SrO, and BaO, and wherein the glass has a color shift < 0.005. In some embodiments, the glass sheet comprises greater than about 80 mol % SiO₂. In some embodiments, the glass sheet comprises between about 8 mol% to about 11 mol% K₂O, between about 0.01 mol% to about 4 mol% ZnO, between about 6 mol% to about 10 mol% MgO, and between about 0.01 mol% to about 0.11 mol% SnO₂.

[00092] In any of the aforementioned embodiments, the glass has a color shift < 0.008 or < 0.005. In some embodiments, the glass has a strain temperature between about 512 °C and 653 °C. In further embodiments, the glass has an annealing temperature between about

564 °C and 721 °C. In additional embodiments, the glass has a softening temperature between about 795 °C and 1013 °C. In some embodiments, the glass has a CTE between about $64 \times 10^{-7}/^{\circ}\text{C}$ to about $77 \times 10^{-7}/^{\circ}\text{C}$. In further embodiments, the glass has a density between about 2.34 gm/cc @ 20 C and about 2.56 gm/cc @ 20 C. In yet additional embodiments, the glass article is a light guide plate having a thickness between about 0.2 mm and about 8 mm. Such a light guide plate may be manufactured from a fusion draw process, slot draw process, or a float process. In further embodiments, the glass comprises less than 1 ppm each of Co, Ni, and Cr. In some embodiments, the concentration of Fe is < about 20 ppm or < about 10 ppm. In some embodiments, the transmittance at 450 nm with at least 500 mm in length is greater than or equal to 85%, the transmittance at 550 nm with at least 500 mm in length is greater than or equal to 90%, or the transmittance at 630 nm with at least 500 mm in length is greater than or equal to 85%, and combinations thereof. In further embodiments, the glass sheet is chemically strengthened. In additional embodiments, the glass comprises between 0.1 mol% to no more than about 3.0 mol% of one or combination of any of ZnO, TiO₂, V₂O₃, Nb₂O₅, MnO, ZrO₂, As₂O₃, SnO₂, MoO₃, Sb₂O₃, and CeO₂.

[00093] It will be appreciated that the various disclosed embodiments may involve particular features, elements or steps that are described in connection with that particular embodiment. It will also be appreciated that a particular feature, element or step, although described in relation to one particular embodiment, may be interchanged or combined with alternate embodiments in various non-illustrated combinations or permutations.

[00094] It is also to be understood that, as used herein the terms “the,” “a,” or “an,” mean “at least one,” and should not be limited to “only one” unless explicitly indicated to the contrary. Thus, for example, reference to “a ring” includes examples having two or more such rings unless the context clearly indicates otherwise. Likewise, a “plurality” or an “array” is intended to denote “more than one.” As such, a “plurality of droplets” includes two or more such droplets, such as three or more such droplets, etc., and an “array of rings” comprises two or more such droplets, such as three or more such rings, etc.

[00095] Ranges can be expressed herein as from “about” one particular value, and/or to “about” another particular value. When such a range is expressed, examples include from the one particular value and/or to the other particular value. Similarly, when values are expressed as approximations, by use of the antecedent “about,” it will be understood that the particular value forms another aspect. It will be further understood that the endpoints of each of the ranges are significant both in relation to the other endpoint, and independently of the other endpoint.

[00096] The terms “substantial,” “substantially,” and variations thereof as used herein are intended to note that a described feature is equal or approximately equal to a value or description. For example, a “substantially planar” surface is intended to denote a surface that is planar or approximately planar. Moreover, as defined above, “substantially similar” is intended to denote that two values are equal or approximately equal. In some embodiments, “substantially similar” may denote values within about 10% of each other, such as within about 5% of each other, or within about 2% of each other.

[00097] Unless otherwise expressly stated, it is in no way intended that any method set forth herein be construed as requiring that its steps be performed in a specific order. Accordingly, where a method claim does not actually recite an order to be followed by its steps or it is not otherwise specifically stated in the claims or descriptions that the steps are to be limited to a specific order, it is no way intended that any particular order be inferred.

[00098] While various features, elements or steps of particular embodiments may be disclosed using the transitional phrase “comprising,” it is to be understood that alternative embodiments, including those that may be described using the transitional phrases “consisting” or “consisting essentially of,” are implied. Thus, for example, implied alternative embodiments to a device that comprises A+B+C include embodiments where a device consists of A+B+C and embodiments where a device consists essentially of A+B+C.

[00099] It will be apparent to those skilled in the art that various modifications and variations can be made to the present disclosure without departing from the spirit and scope of the disclosure. Since modifications combinations, sub-combinations and variations of the disclosed embodiments incorporating the spirit and substance of the disclosure may occur to persons skilled in the art, the disclosure should be construed to include everything within the scope of the appended claims and their equivalents.

What is claimed is:

1. A glass article, comprising:

a glass sheet with a front face having a width and a height, a back face opposite the front face, and a thickness between the front face and back face forming four edges around the front and back faces,

wherein the glass sheet comprises:

between 72.82 mol % to 82.03 mol% SiO₂,

between 0 mol% to 4.8 mol% Al₂O₃,

between 0 mol% to 2.77 mol% B₂O₃,

between 0 mol% to 9.28 mol% Na₂O,

between 0.58 mol% to 10.58 mol% K₂O,

between 0 mol% to 2.93 mol% ZnO,

between 3.1 mol% to 10.58 mol% MgO,

between 0 mol% to 4.82 mol% CaO,

between 0 mol% to 1.59 mol% SrO,

between 0 mol% to 3 mol% BaO, and

between 0.08 mol% to 0.15 mol% SnO₂

wherein the glass has a color shift < 0.005 and wherein the glass article is a light guide plate.

2. The glass article of Claim 1, wherein the glass sheet is substantially free of Al₂O₃, B₂O₃, Na₂O, CaO, SrO, or BaO, and combinations thereof.

3. The glass article of Claim 1, wherein the glass has a strain temperature between 512 °C and 653 °C, an annealing temperature between 564 °C and 721 °C, a softening temperature between 795 °C and 1013 °C, a CTE between 64 x 10⁻⁷/ °C to 77 x 10⁻⁷/ °C, or a density between 2.34 gm/cc @ 20 C and 2.56 gm/cc @ 20 C.

4. The glass article of Claim 1, wherein the thickness of the plate is between 0.2 mm and 8 mm.

5. The glass article of Claim 1, wherein the glass comprises less than 1 ppm each of Co, Ni, and Cr.

6. The glass article of Claim 1, wherein the transmittance at 450 nm with at least 500 mm in length is greater than or equal to 85%, the transmittance at 550 nm with at least 500 mm in length is greater than or equal to 90%, or the transmittance at 630 nm with at least 500 mm in length is greater than or equal to 85%, and combinations thereof.
7. The glass article of Claim 1, wherein the glass sheet is chemically strengthened.
8. The glass article of Claim 7, wherein the glass comprises between 0.1 mol% to no more than about 3.0 mol% of one or combination of any of ZnO, TiO₂, V₂O₃, Nb₂O₅, MnO, ZrO₂, As₂O₃, SnO₂, MoO₃, Sb₂O₃, and CeO₂.