

- 1 -

TITLE: METALLOCENES AND CATALYST COMPOSITIONS
DERIVED THEREFROM

FIELD

5

This invention relates to metallocene compounds and their use in the preparation of catalyst compositions for olefin polymerization, particularly propylene homo- and copolymerization. The present invention also relates to polymerisation processes using such catalyst compositions and polymer compositions obtainable by these processes.

10

BACKGROUND

15

The use of metallocene compositions in olefin polymerization is well known. Metallocenes containing substituted, bridged indenyl derivatives are noted for their ability to produce isotactic propylene polymers having high isotacticity and narrow molecular weight distribution. Considerable effort has been made toward obtaining metallocene produced propylene polymers having ever-higher molecular weight and melting point and, thus, ever better strength (impact) properties, while maintaining suitable catalyst activity.

20

25

Toward this end researchers have found that there is a direct relationship between the way in which a metallocene is substituted and the molecular structure of the resulting polymer. For the substituted, bridged indenyl type metallocenes, it is now well established that the type and arrangement of substituents on the indenyl groups, as well as the type of bridge connecting the indenyl groups, determines such polymer attributes as molecular weight and melting point.

indenyl groups, as well as the type of bridge connecting the indenyl groups, determines such polymer attributes as molecular weight and melting point.

For example, U. S. Patent Nos. 5,840,644 and 5,770,753, incorporated herein by reference in their entireties, describe certain metallocenes containing aryl-substituted indenyl derivatives as ligands, which are said to provide propylene polymers having high isotacticity, narrow molecular weight distribution and very high molecular weight.

Likewise, U. S. Patent No. 5,936,053, incorporated herein by reference in its entirety, describes certain metallocene compounds said to be useful for producing high molecular weight propylene polymers. These metallocenes have a specific hydrocarbon substituent at the 2 position and an unsubstituted aryl substituent at the 4 position on each indenyl group of the metallocene compound.

WO 98/40419 and WO 99/42497 both describe certain supported catalyst systems for producing propylene polymers having high melting point. Metallocene compositions and their activators are often combined with a support material in order to obtain a catalyst system that is less likely to cause reactor fouling. However, it is known that supported metallocene catalyst systems tend to result in a polymer having lower melting point than would otherwise be obtained if the metallocene were not supported.

Much of the current research in this area has been directed toward using metallocene catalyst systems under commercially relevant process conditions, to obtain propylene polymers having melting points higher than known metallocene catalyst systems and close to, or as high as, propylene polymers obtained using conventional, Ziegler-Natta catalyst systems. The present inventors have discovered metallocene compounds that not only have this capability, but retain it upon supportation.


Additionally, it would be desirable to have available metallocenes which not only afford propylene homopolymers having high melting points of (i.e., high

stereotacticity), but also elastomeric copolymers having the high molecular weights required for the production of, e.g., impact copolymers, thereby making possible the production of satisfactory *in situ* blends of, e.g., propylene homopolymer and ethylene-propylene rubbers (EPR's) with a single catalyst composition in a single reactor or in a series of two or more reactors. The present inventors have found metallocene compounds which in combination with a cocatalyst (activator) make both propylene homopolymers having high melting points and elastomeric copolymers that are suitable for the production of impact copolymers in combination with these propylene homopolymers.

SUMMARY OF THE INVENTION

The present invention relates to novel metallocene compounds capable of providing propylene homo- and copolymers having high melting point and high molecular weight. The present invention further relates to metallocene catalyst compositions comprising one or more of these compounds and one or more activators or cocatalysts, and optionally, support material, and to the use of such catalyst compositions in polymerization, in particular propylene polymerization.

In one aspect, the present invention provides metallocene compounds represented by formula (I):



wherein:

M^1 is selected from titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten;

R^1 and R^2 are selected from hydrogen, halogen, hydroxy, C_1 - C_{10} alkyl groups, C_1 - C_{10} alkoxy groups, C_6 - C_{14} aryl groups, C_6 - C_{14} aryloxy groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups and C_7 - C_{40} arylalkenyl groups; or R^1 and R^2 are joined together to form a C_4 - C_{40} alkanediyl group or a conjugated diene ligand which is coordinated to M^1 in a metallacyclopentene fashion; or R^1 and R^2 represent a conjugated diene, optionally substituted with one or more groups independently selected from hydrocarbyl, trihydrocarbysilyl and trihydrocarbysilylhydrocarbyl groups, said diene having a total of up to 40 atoms not counting hydrogen and forming a π complex with M^1 ;

R^3 is selected from hydrogen, halogen, C_1 - C_{10} alkyl groups, C_6 - C_{14} aryl groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups, C_8 - C_{40} arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$ radicals wherein each R' is independently selected from halogen, C_1 - C_{10} alkyl groups and



C₆-C₁₄ aryl groups; provided that if R¹ and R² both are halogen and R¹³ is dimethylsilanediyl, R³ is different from methyl and ethyl;

R⁴, R⁵, R⁶ and R⁷ are each independently selected from hydrogen, halogen, C₁-C₁₀ alkyl groups, C₆-C₁₄ aryl groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups; or two or more adjacent radicals R⁵, R⁶ and R⁷ together with the atoms connecting them may form one or more rings;

R⁸, R⁹, R¹⁰ and R¹¹ are each independently as defined for R⁴, R⁵, R⁶ and R⁷, provided that two or more adjacent radicals R⁸, R⁹, R¹⁰ and R¹¹ together with the atoms connecting them may form one or more rings;

R¹² is selected from halogen, C₁-C₁₀ alkyl groups, C₆-C₁₄ aryl groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups;

R¹³ is selected from




-B(R¹⁴)-, -Al(R¹⁴)-, -Ge-, -Sn-, -O-, -S-, -SO-, -SO₂-, -N(R¹⁴)-, -CO-, -P(R¹⁴)-, -P(O)(R¹⁴)-, -B(NR¹⁴R¹⁵)- and -B[N(SiR¹⁴R¹⁵R¹⁶)₂]-;

wherein:

R¹⁴, R¹⁵ and R¹⁶ are each independently selected from hydrogen, halogen, C₁-C₂₀ alkyl groups, C₆-C₃₀ aryl groups, C₁-C₂₀ alkoxy groups, C₂-C₂₀ alkenyl groups,

C₇-C₄₀ arylalkyl groups, C₈-C₄₀ arylalkenyl groups and C₇-C₄₀ alkylaryl groups, or R¹⁴ and R¹⁵, together with the atom(s) connecting them, form a ring; and M³ is selected from carbon, silicon, germanium and tin; or R¹³ is represented by the formula



wherein:


R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹, R²², R²³ and R²⁴ are each independently selected from hydrogen, halogen, hydroxy, C₁-C₁₀ alkyl groups, C₁-C₁₀ alkoxy groups, C₆-C₁₄ aryl groups, C₆-C₁₄ aryloxy groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups and C₈-C₄₀ arylalkenyl groups; or two or more adjacent radicals R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹, R²², R²³ and R²⁴, including R²⁰ and R²¹, together with the atoms connecting them, form one or more rings; and M² represents one or more carbon atoms, or a silicon, germanium or tin atom.

In preferred embodiments of the above compound, M¹ is selected from titanium, zirconium and hafnium and R¹ and R² are selected from chlorine, C₁-C₆ alkyl groups, C₆-C₁₀ aryl groups, C₇-C₁₂ arylalkyl groups and C₇-C₁₂ alkylaryl groups.

R³ may be a C₃-C₆ alkyl group such as, e.g., a branched C₃-C₄ alkyl group and, in particular, an isopropyl group, or may be a phenyl group.

Preferably at least one of R⁴ and R⁸, and most preferred both of them, represent hydrogen atoms.

In the above formula, M^3 may be selected from carbon and silicon, and R^{14} , R^{15} and R^{16} may independently be selected from C_1 - C_4 alkyl groups and C_6 - C_{10} aryl groups. Moreover, when R^{13} is represented by the formula




R^{17} , R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} and R^{24} may each be hydrogen, with M^2 representing a silicon atom.

R^{12} may be selected from C_1 - C_6 alkyl groups and C_6 - C_{10} aryl groups, a preferred meaning being phenyl. In another embodiment, R^{11} is different from hydrogen and may represent, e.g., a C_1 - C_4 alkyl group.

Particularly preferred compounds of the above formula include those wherein R^1 and R^2 are selected from chlorine, methyl, neopentyl and benzyl, R^3 is selected from C_3 - C_4 alkyl groups, each of R^4 and R^8 is hydrogen, and R^{12} is selected from C_1 - C_4 alkyl groups and C_6 - C_{10} aryl groups; wherein R^3 is selected from branched C_3 - C_4 alkyl groups and R^{12} is selected from C_6 - C_{10} aryl groups; wherein R^3 is selected from isopropyl, isobutyl, sec-butyl, tert-butyl and phenyl groups, and R^{12} is selected from n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, phenyl, tolyl, benzyl and naphthyl groups; and wherein M^1 is selected from zirconium and hafnium; R^1 and R^2 are selected from chlorine, C_1 - C_3 alkyl groups and C_6 - C_{10} aryl groups; R^3 is selected from C_3 - C_6 alkyl groups and C_6 - C_{10} aryl groups; R^4 and R^8 are hydrogen; R^5 , R^6 , R^7 , R^9 , R^{10} and R^{11} are each independently selected from hydrogen, halogen and C_1 - C_3 alkyl groups; R^{12} is

selected from C₃-C₆ alkyl groups and C₆-C₁₀ aryl groups; and R¹³ is selected from di(C₁-C₄ alkyl)silanediyl, diphenylsilanediyl, (C₁-C₄ alkyl)phenylsilanediyl, diphenylmethanediyl and C₂-C₄ alkanediyl and alkenediyl radicals, and groups of the formula



wherein:

R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹, R²², R²³ and R²⁴ are each independently selected from hydrogen, halogen and C₁-C₃ alkyl groups; and M² represents a carbon or silicon atom.

In another aspect R¹³ may be selected from di(C₁-C₄ alkyl)silanediyl, diphenylsilanediyl, (C₁-C₄ alkyl)phenylsilanediyl, C₂-C₄ alkanediyl and alkenediyl, di(C₁-C₄ alkyl)amidoborane and bis[tri(C₁-C₄ alkyl)silyl]amidoborane radicals.

Other preferred compounds of the above formula may comprise not more than 2 % of the meso isomer.

In another aspect the metallocenes of this invention are represented by the above formula (I), wherein:

M¹ is selected from titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten;

R¹ and R² are selected from hydrogen, halogen, hydroxy, C₁-C₁₀ alkyl groups, C₁-C₁₀ alkoxy groups, C₆-C₁₄ aryl groups, C₆-C₁₄ aryloxy groups, C₂-C₁₀ alkenyl


groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups and C₇-C₄₀ arylalkenyl groups; or R¹ and R² are joined together to form an alkanediyl group or a conjugated C₄-C₄₀ diene ligand which is coordinated to M¹ in a metallacyclopentene fashion; or R¹ and R² represent a conjugated diene,
 5 optionally substituted with one or more groups independently selected from hydrocarbyl, trihydrocarbylsilyl and trihydrocarbylsilylhydrocarbyl groups, said diene having a total of up to 40 atoms not counting hydrogen and forming a π complex with M¹;

R³ is selected from hydrogen, halogen, C₁-C₁₀ alkyl groups, C₆-C₁₄ aryl groups,
 10 C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups;

R⁴, R⁵, R⁶ and R⁷ are each independently selected from hydrogen, halogen, C₁-C₁₀
 15 alkyl groups, C₆-C₁₄ aryl groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups; or two or more adjacent radicals R⁵, R⁶ and R⁷ together with the atoms connecting them may form one or
 20 more rings; R⁸, R⁹, R¹⁰ and R¹¹ are each independently as defined for R⁴, R⁵, R⁶ and R⁷, provided that two or more adjacent radicals R⁸, R⁹, R¹⁰ and R¹¹ together with the atoms connecting them may form one or more rings;

R¹² is selected from halogen, C₁-C₁₀ alkyl groups, C₆-C₁₄ aryl groups, C₂-C₁₀
 25 alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups;

R¹³ is selected from di(C₆-C₁₂ aryl)silanediyl, (C₁-C₆ alkyl)(C₆-C₁₂ aryl)silanediyl, and groups of the formula



wherein:

R^{17} , R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} and R^{24} are each independently selected from hydrogen, halogen, hydroxy, C_1 - C_{10} alkyl groups, C_1 - C_{10} alkoxy groups, C_6 - C_{14} aryl groups, C_6 - C_{14} aryloxy groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups and C_8 - C_{40} arylalkenyl groups; or two or more adjacent radicals R^{17} , R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} and R^{24} , including R^{20} and R^{21} , together with the atoms connecting them, form one or more rings; and M^2 represents a carbon, silicon or germanium atom.

Preferred embodiments of these compounds are those already given above.

The present invention also provides a catalyst composition which comprises the product of a compound of at least one of the above metallocene compounds of the present invention and a cocatalyst. The cocatalyst may be a compound comprising a noncoordinating anion (e.g., a noncoordinating anion comprising at least one unit of the formula $-B(C_6F_5)_3$) and/or may be an alumoxane, e.g., methylalumoxane. The catalyst composition may comprises a support material, e.g., an inorganic material such as silica, alumina, silica-alumina and magnesium chloride.

Preferred support materials include silica having a surface area ranging from 10 to 700 m^2/g , a total pore volume ranging from 0.1 to 4.0 cc/g and an average particle size ranging from 10 to 500 μm .

Another aspect of the present invention is a polymerization process which comprises contacting, under polymerization conditions, one or more ethylenically unsaturated monomers and a catalyst composition as defined above.

5 The ethylenically unsaturated monomers preferably are selected from monoolefins, diolefins and mixtures thereof. Illustrative and non-limiting examples of suitable monoolefins are compounds of the formula $R^aCH=CHR^b$ wherein R^a and R^b are each independently selected from hydrogen, alkyl and alkenyl radicals having 1 to 14 carbon atoms or, together with the carbon atoms to
10 which they are connected, form a ring having 4 to 8 carbon atoms. Preferred monoolefins include ethylene and α -olefins having from 3 to 12 carbon atoms such as, e.g., propylene, 1-butene, 4-methyl-1-pentene, 1-hexene, 1-octene and mixtures thereof. In a preferred embodiment, the ethylenically unsaturated monomers consist essentially of ethylene and propylene.

15 In one aspect of the above process the temperature ranges from about 30° C to about 80° C. In another aspect, the process is carried out at a pressure ranging from about 5 to about 64 bar.

20 The present invention also provides a polymer composition comprising:
(a) propylene polymer comprising at least about 99 % by weight of units derived from propylene and having a melting point of at least about 155° C; and (b) olefin copolymer comprising from about 40 to about 70 % by weight of units derived from propylene and having an intrinsic viscosity of at least about 1.8; the
25 composition made with a single catalyst composition. Component (a) may be a homopolypropylene or a copolymer of propylene and at least one monoolefin selected from ethylene and α -olefins having from 4 to 12 carbon atoms, the copolymer containing at least about 99.5 % by weight of units derived from propylene. Component (b) may contain from about 30 to about 60 % by weight of ethylene and/or components (a) and (b) together may contain a total of about 1.5
30 to about 20 % by weight of ethylene.

In a preferred composition of the present invention component (a) has a melting point of at least about 156°C, more preferred at least about 157° C, and/or component (b) has an intrinsic viscosity of at least about 2.0, more preferred at least about 2.2. The composition preferably has a molecular weight distribution, M_w/M_n , of not higher than about 3.5, more preferably not higher than about 3.0.

In another preferred embodiment the catalyst composition used to make the polymer composition is based on a bridged zirconocene compound.

DETAILED DESCRIPTION

In the following detailed description, unless otherwise stated, all percentages, parts, ratios, etc., are by weight.

Also, unless otherwise stated, a reference to a compound or component includes the compound or component by itself, its individual stereoisomers and any mixtures thereof, of as well as any combination with other compounds or components, such as mixtures of compounds.

Further, when an amount, concentration, or other value or parameter, is given as a list of upper preferable values and lower preferable values, this is to be understood as specifically disclosing all ranges formed from any pair of an upper preferred value and a lower preferred value, regardless whether ranges are separately disclosed.

Additionally, as utilized herein, the following terms have the meanings indicated below.

The term "product" in connection with the catalyst composition of the present invention includes any species that is different in any respect from the completely independent and individual materials, i.e., the metallocene compound (catalyst precursor) and the cocatalyst (activator). By way of illustrative, non-

limiting example, these individual materials may have interacted or even reacted, giving rise to a contact product and/or reaction product.

The term "alkyl", means a straight-chain, branched-chain or cyclic alkyl radical. Examples of such radicals include, but are not limited to, methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, pentyl, iso-amyl, hexyl, 2-ethylhexyl, octyl, cyclopentyl, cyclohexyl and the like. The cyclic alkyl radicals may be substituted with one or more straight-chain and/or branched-chain alkyl radicals (i.e., may be alkylcycloalkyl radicals such as , e.g., methylcyclohexyl etc.). Conversely, the straight-chain and branched-chain alkyl radicals may be substituted with one or more cyclic alkyl radicals (i.e., may be cycloalkylalkyl radicals such as cyclohexylmethyl etc.). Moreover, unless indicated otherwise, the above alkyl radicals may be substituted by one or more groups preferably and independently selected from halogen (e.g., F, Cl, Br), alkoxy (e.g., methoxy, ethoxy, propoxy, butoxy and the like), hydroxy, amino, monoalkylamino (e.g., methylamino, ethylamino, propylamino and the like) and dialkylamino (e.g., dimethylamino, diethylamino, dipropylamino, diisopropylamino, piperidino and the like) and trihydrocarbylsilyl (e.g., trimethylsilyl, triphenylsilyl and the like).

The term "alkenyl" means "alkyl" as defined above having one or more double and/or triple bonds. Examples of alkenyl radicals include, but are not limited to, ethenyl, propenyl, allyl, butenyl, propargyl, 1,4-butadienyl, isopropenyl, cyclopentenyl, cyclohexenyl, cyclooctenyl, cyclopentadienyl, cyclohexadienyl, cyclooctadienyl and the like.

The term "alkoxy" means an alkyl or alkenyl ether radical wherein the terms "alkyl" and "alkenyl" are as defined above. Examples of suitable alkyl ether radicals include, but are not limited to, methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, iso-butoxy, sec-butoxy, tert-butoxy, allyloxy, trifluoromethoxy and the like.

The term "aryl" means an aromatic radical, for example, a phenyl, naphthyl, azulenyl, phenanthryl or anthracenyl radical and the like which optionally contains one or more (e.g., 2 or 3) heteroatoms (preferably selected from N, O and S and combinations thereof) in the ring and/or carries one or more identical or different substituents, for example, alkoxy, aryl, halogen, hydroxy, amino, monoalkylamino, dialkylamino, nitro, trihydrocarbylsilyl, alkyl-CO, alkylsulfonyl, alkyl-OCO etc., these terms being as defined herein. Illustrative, non-limiting examples of aryl radicals are phenyl, naphthyl, fluorenyl, chlorophenyl, dichlorophenyl, fluorophenyl, perfluorophenyl, hydroxyphenyl, anisyl, biphenyl, nitrophenyl, acetylphenyl, aminophenyl, pyridyl, pyridazyl, quinolyl, and the like. When carbon numbers are given herein for aryl radicals, ring heteroatoms are counted as carbon atoms.

The term "aryloxy" means an aryl ether radical wherein the term "aryl" is as defined above.

The term "alkylaryl" means an aryl radical carrying at least one alkyl and/or alkenyl radical as ring substituent, the terms "aryl", "alkyl" and "alkenyl" being as defined above. Illustrative, non-limiting examples of alkylaryl groups are tolyl, xylyl, mesityl, ethylphenyl, trifluoromethylphenyl, vinylphenyl, cumyl, methylpyridyl and the like.

The term "arylalkyl" means an alkyl radical carrying at least one aryl group wherein the terms "aryl" and "alkyl" are as defined above, provided that the aryl radical may have one or more alkyl substituents. Illustrative, non-limiting examples of arylalkyl groups are benzyl, phenethyl, diphenylmethyl, tolylmethyl, naphthylmethyl and the like.

The term "arylalkenyl" means an alkenyl radical carrying at least one aryl substituent wherein the terms "aryl" and "alkenyl" are as defined above, provided that the aryl radical may have one or more alkyl substituents. Illustrative, non-

limiting examples of arylalkenyl groups are styryl, methylstyryl, phenylpropenyl, 1-phenyl-1,4-butadienyl and the like.

The term "halogen" means fluorine, chlorine, bromine and iodine.

5

The term "hydrocarbyl" encompasses alkyl, alkenyl, arylalkyl, arylalkenyl and alkylaryl groups as defined above. Preferred hydrocarbyl groups comprise 1 to 20, more preferred 1 to 10, and most preferred 1 to 6 carbon atoms. Illustrative, non-limiting examples are methyl, ethyl, propyl and phenyl.

10

Unless specified otherwise herein, preferred meanings of the various groups defined above are:

Alkyl: linear and branched alkyl groups having 1 to 8, particularly 1 to 6, and even more preferred, 1 to 4 carbon atoms (such as, e.g., methyl, ethyl, propyl and isopropyl). If present, substituents are preferably selected from halogen and alkoxy, more preferred from F, Cl, methoxy and ethoxy, most preferred from F and Cl.

15

Alkoxy: the preferred alkyl groups connected to an oxygen atom, more preferred methoxy and ethoxy.

20

Alkenyl: linear and branched alkenyl groups having 2 to 8, particularly 2 to 6, and even more preferred, 2 to 4 carbon atoms (such as, e.g., vinyl, allyl, and 2-butenyl). If present, substituents are preferably selected from halogen and alkoxy, more preferred from F, Cl, methoxy and ethoxy, most preferred from F and Cl.

25

Aryl: aryl groups containing 6 to 12, more preferred 6 to 10 carbon atoms, such as, e.g., phenyl, naphthyl and biphenyl. Preferably no heteroatoms are present in the ring system. If present, substituents are preferably selected from

30

halogen and alkoxy, more preferred from F, Cl, methoxy and ethoxy, most preferred from F and Cl.

5 Aryloxy: the preferred aryl groups attached to an oxygen atom. Most preferred are phenoxy and naphthoxy.

10 Arylalkyl and alkylaryl: the preferred aryl groups in combination with the preferred alkyl groups, the total number of carbon atoms being 7 to 20, more preferred 7 to 12. Particularly preferred examples include benzyl, phenethyl, tolyl and xylyl.

15 Arylalkenyl: the preferred aryl groups in combination with the preferred alkenyl groups, the total number of carbon atoms being 8 to 20, more preferred 8 to 12. Particularly preferred examples include styryl and chlorostyryl.

Halogen: F, Cl and Br, more preferred F and Cl.

20 Preferred meanings of the various constituents of the compounds of formula (I) above are as follows, it being understood that these preferred meanings are defined as above, including the preferred embodiments of a particular meaning. For example, "alkyl" means an alkyl group as defined above, preferred meanings thereof being also as defined above.

25 M^1 : titanium, zirconium, hafnium; more preferred are zirconium and hafnium, with zirconium being most preferred.

30 R^1 and R^2 : halogen (more preferred Cl and Br), alkyl (more preferred methyl and neopentyl), aryl (more preferred phenyl), alkylaryl (more preferred tolyl) and arylalkyl (more preferred benzyl); or R^1 and R^2 are joined together to form a C_{4-6} alkanediyl group or a conjugated C_4-C_6 diene ligand which is coordinated to M^1 in a metallacycloalkane or -cycloalkene fashion; or R^1 and R^2 represent a conjugated diene, optionally substituted with one or more groups

independently selected from alkyl, aryl, trialkylsilyl and trialkylsilylalkyl groups, said diene having a total of up to 30, e.g., up to 24 atoms not counting hydrogen and forming a π complex with M^1 . Illustrative, non-limiting examples of conjugated dienes are 1,4-diphenyl-1,3-butadiene, 1,3-pentadiene, 2-methyl-1,3-pentadiene, 2,4-hexadiene, 1-phenyl-1,3-pentadiene, 1,4-dibenzyl-1,3-butadiene, 1,4-ditolyl-1,3-butadiene, 1,4-bis(trimethylsilyl)-1,3-butadiene, and 1,4-dinaphthyl-1,3-butadiene. While R^1 and R^2 may be different, they are preferably the same. The most preferred meanings of R^1 and R^2 are Cl and methyl.

R^3 : alkyl, aryl, alkylaryl and arylalkyl. More preferred meanings are methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, phenyl, naphthyl, tolyl and benzyl, even more preferred isopropyl, benzyl and phenyl. Most preferred is isopropyl.

R^4 , R^5 , R^6 and R^7 : hydrogen, alkyl and aryl (particularly phenyl), more preferred hydrogen and alkyl. Illustrative, non-limiting examples are hydrogen, methyl and ethyl. For R^4 a particularly preferred meaning is hydrogen. In another preferred embodiment, all of R^4 , R^5 , R^6 and R^7 are hydrogen.

R^8 , R^9 , R^{10} and R^{11} : hydrogen, alkyl, arylalkyl (particularly benzyl) and aryl (particularly phenyl), more preferred hydrogen and alkyl. Illustrative, non-limiting examples are hydrogen, methyl and ethyl. For R^8 a particularly preferred meaning is hydrogen. In another preferred embodiment, all of R^8 , R^9 , R^{10} and R^{11} are hydrogen. While in still another preferred embodiment at least one of R^9 and R^{11} is different from hydrogen, it is particularly preferred for R^{11} to be different from hydrogen when R^{12} represents methyl or ethyl.

R^{12} : alkyl, aryl, alkylaryl, arylalkyl and trialkylsilyl. More preferred meanings are methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, phenyl, naphthyl, (o-, m- and p-)tolyl, benzyl and trimethylsilyl, in particular, isopropyl and phenyl. Most preferred is phenyl.

R¹³: dialkylsilanediyl, diarylsilanediyl, (aryl)(alkyl)silanediyl, amidoborane, alkylene, arylalkylene and arylene, the latter groups being derived from the defined alkyl, arylalkyl and aryl radicals. More preferred as alkyl and aryl groups are methyl, ethyl, propyl, butyl and phenyl. More preferred alkylene, arylalkylene and arylene radicals are ethylene, propylene, butylene, phenylmethylene and diphenylmethylene as well as phenylene. More preferred dialkylsilanediyl, diarylsilanediyl and (aryl)(alkyl)silanediyl radicals are dimethylsilanediyl, diethylsilanediyl, dipropylsilanediyl, dibutylsilanediyl, methylphenylsilanediyl and diphenylsilanediyl. More preferred amidoborane radicals are dialkylamidoborane, diarylamidoborane and bis(trialkylsilyl)-amidoborane radicals. Illustrative, non-limiting examples thereof are dimethylamidoborane, diethylamidoborane, diisopropylamidoborane, diphenylamidoborane and bis(trimethylsilyl)amidoborane. Other preferred meanings of R¹³ are 9-fluorenyl and 9-silafluorenyl. R¹³ is usually connected to the 1-positions of the indenyl ring systems.

The following are particularly preferred metallocenes:

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

5 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

10 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

15 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

20 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

25 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

30 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

5 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

10 dimethylsilanediylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

15 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

20 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

25 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

30 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

5 dimethylsilanediylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dichloride;

10 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dichloride;

15 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dichloride;

20 dimethylsilanediylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dichloride;

25 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dichloride;

30 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}zirconium
dichloride;

5 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}zirconium

10 dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}zirconium dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium

15 dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium
dichloride;

20 dimethylsilanediylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium
25 dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}zirconium
dichloride;

30 dimethylsilanediylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

5 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

10 dimethylsilanediylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dichloride;

15 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dichloride;

20 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dichloride;

25 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

30 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-

zirconium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-

zirconium dichloride;

5 dimethylsilanediylbis{1-[2-phenyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

10 dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

15 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

20 dimethylsilanediylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

25 dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium
dichloride;

30 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium
dichloride;

5 dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}
zirconium dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium
dichloride;

10 dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}
zirconium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}
zirconium dichloride;

15 dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}zirconium
dimethyl;

20 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}zirconium
dimethyl;

25 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}zirconium
dimethyl;

30 dimethylsilanediylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dimethyl;

5 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dimethyl;

10 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dimethyl;

15 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dimethyl;

20 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dimethyl;

25 dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dimethyl;

30 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}zirconium
dimethyl;

5 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}zirconium
dimethyl;

10 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

15 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

20 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

25 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

30 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dimethyl;

5 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dimethyl;

10 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dimethyl;

15 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
20 dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dimethyl;

25 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
30 dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;
dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

5 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;
dimethylsilanediylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;
dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;
dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;
dimethylsilanediylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;
dimethylsilanediylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
10 dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
dimethyl;

15 dimethylsilanediylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
20 dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium
dimethyl;

25 dimethylsilanediylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium
30 dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium
dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}zirconium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}zirconium dimethyl;

5 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dimethyl;

10 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dimethyl;

15 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dimethyl;

20 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dimethyl;

25 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dimethyl;

30 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

5 dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

10 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

15 dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

20 dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

25 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

30 dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

5 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

10 dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} hafnium dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} hafnium dichloride;

15 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} hafnium dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} hafnium dichloride;

20 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]} hafnium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]} hafnium dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} hafnium dichloride;

25 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} hafnium dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} hafnium dichloride;

30 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} hafnium dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]} hafnium dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

5 dimethylsilanediylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}hafnium dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

10 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

15 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

20 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

25 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

30 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

5 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

10 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

15 dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

20 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

25 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

30 dimethylsilanediylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

5 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

10 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

15 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

20 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

25 dimethylsilanediylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

30 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;
dimethylsilanediylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

5 dimethylsilanediylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

10 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

15 dimethylsilanediylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

20 dimethylsilanediylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

25 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

30 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

5 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

10 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trimethylsilylphenyl)indenyl]} hafnium
dichloride;

15 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trimethylsilylphenyl)indenyl]}-
hafnium dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trimethylsilylphenyl)indenyl]} hafnium
dichloride;

20 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trimethylsilylphenyl)indenyl]} hafnium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-
hafnium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-
hafnium dichloride;

25 dimethylsilanediylbis{1-[2-phenyl, 4-(2-trimethylsilylphenyl)indenyl]} hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium
dichloride;

30 dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium
dichloride;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dichloride;

5 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dichloride;

10 dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium
dichloride;

15 dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

20 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

25 dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

30 dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}
hafnium dichloride;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dichloride;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium

dichloride;

5 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

10 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

15 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} hafnium
20 dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} hafnium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]} hafnium dimethyl;

25 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]} hafnium
dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]} hafnium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]} hafnium dimethyl;

30 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]} hafnium
dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dimethyl;

5 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dimethyl;

10 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

15 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

20 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

25 dimethylsilanediylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

30 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

5 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

10 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

15 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

20 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

25 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

30 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

5 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

10 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

15 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

20 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

25 dimethylsilanediylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

30 dimethylsilanediylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

5 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

10 dimethylsilanediylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

15 dimethylsilanediylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

20 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium dimethyl;

25 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium dimethyl;

30 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dimethyl;

5 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dimethyl;

10 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dimethyl;

15 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dimethyl;

20 dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dimethyl;

25 dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dimethyl;

30 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium dimethyl;

5 dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium dimethyl;

10 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dimethyl;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium dimethyl;

15 dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium dimethyl;

20 dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium dimethyl;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

25 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium dimethyl;

30 9-silafluorendiylbis{1-[2-methyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-ethyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

5 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

10 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride;

15 9-silafluorendiylbis{1-[2-methyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-ethyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride;

20 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride;

25 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride;

30 9-silafluorendiylbis{1-[2-methyl, 4-(2-n-propylphenyl)indenyl]}zirconium dichloride;

9-silafluorendiylbis{1-[2-ethyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

5 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

10 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

15 9-silafluorendiylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-methyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

20 9-silafluorendiylbis{1-[2-ethyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

30 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-methyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

5 9-silafluorendiylbis{1-[2-ethyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

10 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

15 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

20 9-silafluorendiylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-methyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-ethyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

25 9-silafluorendiylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

30 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

5 9-silafluorendiylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-methyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

10 9-silafluorendiylbis{1-[2-ethyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

15 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

20 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

25 9-silafluorendiylbis{1-[2-methyl, 4-(2-tert-butylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-ethyl, 4-(2-tert-butylphenyl)indenyl]}zirconium
dichloride;

30 9-silafluorendiylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dichloride;

5 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dichloride;

10 9-silafluorendiylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-methyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-ethyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

15 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

20 9-silafluorendiylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

30 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

5 9-silafluorendiylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

10 9-silafluorendiylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

15 9-silafluorendiylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-methyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium dichloride;

20 9-silafluorendiylbis{1-[2-ethyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium dichloride;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium dichloride;

30 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-zirconium dichloride;

9-silafluorendiylbis{1-[2-methyl, 4-(2-trimethylsilylphenyl)indenyl]} zirconium dichloride;

5 9-silafluorendiylbis{1-[2-ethyl, 4-(2-trimethylsilylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

10 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

15 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

20 9-silafluorendiylbis{1-[2-phenyl, 4-(2-trimethylsilylphenyl)indenyl]}-zirconium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dichloride;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dichloride;

30 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium
dichloride;

5 9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium
dichloride;

10 9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

15 9-silafluorendiylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium
dichloride;

20 9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium
dichloride;

25 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}
zirconium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}
zirconium dichloride;

30 9-silafluorendiylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium
dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

5 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

10 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

15 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

20 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

25 9-silafluorendiylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium dimethyl;

30 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium dimethyl;

5 9-silafluorendiylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]} zirconium dimethyl;

10 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]} zirconium dimethyl;

15 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium dimethyl;

20 9-silafluorendiylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]} zirconium dimethyl;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]} zirconium dimethyl;

30 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]} zirconium dimethyl;

5 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium dimethyl;

10 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium dimethyl;

15 9-silafluorendiylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dimethyl;

20 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dimethyl;

25 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dimethyl;

30 9-silafluorendiylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dimethyl;

5 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dimethyl;

10 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;

15 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]} zirconium dimethyl;

20 9-silafluorendiylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dimethyl;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dimethyl;

30 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dimethyl;

5 9-silafluorendiylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dimethyl;

10 9-silafluorendiylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dimethyl;

15 9-silafluorendiylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}

20 zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium dimethyl;

25 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium dimethyl;

30 9-silafluorendiylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-trimethylsilylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-trimethylsilylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-trimethylsilylphenyl)indenyl]} zirconium dimethyl;

5 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-trimethylsilylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-trimethylsilylphenyl)indenyl]} zirconium dimethyl;

10 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-trimethylsilylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-trimethylsilylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

15 9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

20 9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

25 9-silafluorendiylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

30 9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium dimethyl;

5 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium dimethyl;

10 9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium dimethyl;

15 9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium dimethyl;

20 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}hafnium dichloride;

25 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}hafnium dichloride;

30 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}hafnium dichloride;

5 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}hafnium

10 dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}hafnium

15 dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

20 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

25 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

30 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

5 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

10 9-silafluorendiylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

15 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

20 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

25 9-silafluorendiylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

30 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

5 9-silafluorendiylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

10 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

15 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

20 9-silafluorendiylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

30 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

5 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium dichloride;

10 9-silafluorendiylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

15 9-silafluorendiylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

20 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

25 9-silafluorendiylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

30 9-silafluorendiylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

5 9-silafluorendiylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium
dichloride;

10 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium
dichloride;

15 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium
dichloride;

20 9-silafluorendiylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dichloride;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dichloride;

30 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-trimethylsilylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium dichloride;

5 9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium dichloride;

10 9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium dichloride;

15 9-silafluorendiylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dichloride;

20 9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dichloride;

25 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dichloride;

30 9-silafluorendiylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dichloride;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

5 9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

10 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium
dichloride;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}hafnium
dimethyl;

15 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}hafnium
dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

20 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}hafnium
dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}hafnium
dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

25 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

30 9-silafluorendiylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

5 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

10 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}hafnium dimethyl;

15 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium dimethyl;

20 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium dimethyl;

25 9-silafluorendiylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

30 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

5 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

10 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

15 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

20 9-silafluorendiylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;
9-silafluorendiylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

30 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

5 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

10 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

15 9-silafluorendiylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

20 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

25 9-silafluorendiylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

30 9-silafluorendiylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

5 9-silafluorendiylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

10 9-silafluorendiylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

15 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

20 9-silafluorendiylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium dimethyl;

25 9-silafluorendiylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium dimethyl;

30 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium dimethyl;

5 9-silafluorendiylbis{1-[2-isopropyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium dimethyl;

10 9-silafluorendiylbis{1-[2-isobutyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium dimethyl;

15 9-silafluorendiylbis{1-[2-phenyl, 4-(2-trimethylsilylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

20 9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

25 9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

30 9-silafluorendiylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium dimethyl;

9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dimethyl;

5 9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dimethyl;

10 9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dimethyl;

9-silafluorendiylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

15 9-silafluorendiylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

9-silafluorendiylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

20 9-silafluorendiylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

9-silafluorendiylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

9-silafluorendiylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

25 9-silafluorendiylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium dichloride;

30 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]} zirconium
dichloride;

5 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} zirconium
dichloride;

10 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

15 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

20 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

25 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

30 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]} zirconium dichloride;

5 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]} zirconium dichloride;

10 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium dichloride;

15 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]} zirconium dichloride;

20 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

25 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

30 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

5 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

10 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dichloride;

15 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

20 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

25 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}zirconium
dichloride;

30 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}zirconium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dichloride;

5 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

10 dimethylamidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

15 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

20 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

25 dimethylamidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}
zirconium dichloride;

30 dimethylamidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}

zirconium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}

zirconium dichloride;

5 dimethylamidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}

10 zirconium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dichloride;

15 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium
20 dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dichloride;

25 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

30 zirconium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-
zirconium dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

5 dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

10 dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

15 dimethylamidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

20 dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

25 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

30 dimethylamidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}
zirconium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

5 dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

10 zirconium dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium
dimethyl;

15 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} zirconium
dimethyl;

20 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]} zirconium
dimethyl;

25 dimethylamidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} zirconium

30 dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}zirconium
dimethyl;

5 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}zirconium
dimethyl;

10 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}zirconium
dimethyl;

15 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}zirconium
20 dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}zirconium
dimethyl;

25 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}
zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}zirconium
30 dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}
zirconium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}zirconium
dimethyl;

5 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

10 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

15 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}zirconium
20 dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

25 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium
30 dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}zirconium
dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}

zirconium dimethyl;

5 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}

10 zirconium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}

zirconium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

15 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}zirconium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}zirconium

20 dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}zirconium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dimethyl;

25 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}zirconium

30 dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

5 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

10 dimethylamidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}
zirconium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}
zirconium dimethyl;

15 dimethylamidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}
zirconium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}
20 zirconium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}
zirconium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium
dimethyl;

25 dimethylamidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}
zirconium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}
zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium
30 dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}
zirconium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-β-naphthylphenyl)indenyl]}

zirconium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-β-naphthylphenyl)indenyl]}

zirconium dimethyl;

5 dimethylamidoboranebis{1-[2-phenyl, 4-(2-β-naphthylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-

10 zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dimethyl;

15 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}- zirconium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-

20 zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

25 dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}

30 zirconium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

5 dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

10 dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

15 dimethylamidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

20 dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

25 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

30 dimethylamidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}hafnium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

5 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

10 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

15 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

20 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

25 dimethylamidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

30 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

5 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

10 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

15 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

20 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

25 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

30 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

5 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

10 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

15 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
20 dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

25 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
30 dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

5 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

10 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

15 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

20 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

25 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

30 dimethylamidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}
hafnium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dichloride;

5 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dichloride;

10 dimethylamidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dichloride;

15 dimethylamidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dichloride;

20 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dichloride;

25 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dichloride;

30 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

5 dimethylamidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dichloride;

10 dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}
hafnium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dichloride;

15 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}
hafnium dichloride;

20 dimethylamidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium
dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

25 dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

30 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

dimethylamidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dichloride;

5 dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dichloride;

10 dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dichloride;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium dichloride;

15 dimethylamidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium dichloride;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

20 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

25 dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

30 dimethylamidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}hafnium

dimethyl;

5 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}hafnium

10 dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}hafnium

dimethyl;

15 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium

20 dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium

dimethyl;

25 dimethylamidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}hafnium

30 dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

5 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}hafnium
dimethyl;

10 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

15 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

20 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

25 dimethylamidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

30 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dimethyl;

5 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

10 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

15 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
20 dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dimethyl;

25 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
30 dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium

dimethyl;

5 dimethylamidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium

dimethyl;

10 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium

dimethyl;

15 dimethylamidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium

20 dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}

hafnium dimethyl;

25 dimethylamidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}

30 hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dimethyl;

5 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium dimethyl;

10 dimethylamidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dimethyl;

15 dimethylamidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dimethyl;

20 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}- hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

25 dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]} hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

30 dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium

dimethyl;

5 dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

10 hafnium dimethyl;

dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

15 dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium

dimethyl;

dimethylamidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}

20 hafnium dimethyl;

dimethylamidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

25 dimethylamidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

dimethylamidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

30 hafnium dimethyl;

dimethylamidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium

dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

5 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

10 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}hafnium
dichloride;

15 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

20 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

25 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}hafnium
dichloride;

30 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium dichloride;

5 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]} hafnium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium dichloride;

10 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]} hafnium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]} hafnium dichloride;

15 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]} hafnium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]} hafnium dichloride;

20 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]} hafnium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]} hafnium dichloride;

25 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]} hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]} hafnium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]} hafnium dichloride;

30 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]} hafnium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]} hafnium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

5 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

10 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

15 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

20 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}
hafnium dichloride;

25 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

30 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}
hafnium dichloride;

5 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

10 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}
hafnium dichloride;

15 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

20 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

25 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

30 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium
dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}

hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}

hafnium dichloride;

5 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}

hafnium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}

hafnium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}

10 hafnium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}

hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dichloride;

15 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}

20 hafnium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dichloride;

25 diisopropylamidoboranebis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-

hafnium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-

30 hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

hafnium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

5 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium dichloride;

10 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}
hafnium dichloride;

15 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}
hafnium dichloride;

20 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

25 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

30 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}
hafnium dichloride;

5 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}
hafnium dichloride;

10 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}
hafnium dichloride;

15 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}
hafnium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}
hafnium dichloride;

20 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

25 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

30 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} hafnium
dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

5 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

10 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}hafnium dimethyl;

15 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]} hafnium dimethyl;

20 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]} hafnium dimethyl;

25 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]} hafnium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}

30 hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]} hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]} hafnium dimethyl;

5 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]} hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]} hafnium dimethyl;

10 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

15 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

20 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium dimethyl;

25 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]} hafnium dimethyl;

30 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

5 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

10 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

15 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

20 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

25 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

30 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

5 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

10 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

15 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dimethyl;

20 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dimethyl;

25 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dimethyl;

30 diisopropylamidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]} hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dimethyl;

5 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}

10 hafnium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-

hafnium dimethyl;

15 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-

20 hafnium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

hafnium dimethyl;

25 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}

30 hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}

hafnium dimethyl;

5 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}

10 hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

15 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

20 hafnium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

25 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}

30 hafnium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}

hafnium dimethyl;

5 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}

zirconium dichloride;

10 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}

zirconium dichloride;

15 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}
zirconium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} zirconium
dichloride;

20 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

25 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

30 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

5 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}

10 zirconium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]} zirconium
dichloride;

15 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}

20 zirconium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

25 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}

30 zirconium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

5 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

10 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]} zirconium dichloride;

15 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]} zirconium dichloride;

20 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]} zirconium dichloride;

25 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dichloride;

30 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}

zirconium dichloride;

5 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}

10 zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dichloride;

15 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}

20 zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

25 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

30 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]} zirconium
dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

5 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

10 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

15 diisopropylamidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

20 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

25 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium dichloride;

30 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}- zirconium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-
zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
zirconium dichloride;

5 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-
zirconium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
zirconium dichloride;

10 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
zirconium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-
zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

15 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

20 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

25 diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}
zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

30 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium dichloride;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dichloride;

5 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}

10 zirconium dichloride;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

15 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

20 zirconium dichloride;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dichloride;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

25 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

30

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

5 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

10 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

15 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]} zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}

20 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dimethyl;

25 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]} zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}

30 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]} zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dimethyl;

5 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}

10 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dimethyl;

15 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}

20 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}

zirconium dimethyl;

25 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}

30 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}zirconium dimethyl;

5 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium dimethyl;

10 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

15 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

20 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}zirconium dimethyl;

25 diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}zirconium dimethyl;

30 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dimethyl;

5 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

10 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

15 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

20 diisopropylamidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}

zirconium dimethyl;

25 diisopropylamidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}
zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}

30 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dimethyl;

5 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}

10 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dimethyl;

15 diisopropylamidoboranebis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-

20 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dimethyl;

25 diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-

30 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

5 diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}

10 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dimethyl;

15 diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}

20 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dimethyl;

25 diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}

30 zirconium dimethyl;

diisopropylamidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dimethyl;

5 diisopropylamidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dimethyl;

diisopropylamidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}

10 zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}

zirconium dichloride;

15 bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}

20 zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}

zirconium dichloride;

25 bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}

30 zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}

zirconium dichloride;

5 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}

10 zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

15 bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}

20 zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

25 bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}

30 zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}

zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dichloride;

5 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dichloride;

10 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dichloride;

15 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dichloride;

20 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dichloride;

25 bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dichloride;

30 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

5 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

10 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

15 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

20 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dichloride;

25 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}
zirconium dichloride;

30 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]]}
zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]]}
zirconium dichloride;

5 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]]} zirconium
dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)-
indenyl]]} zirconium dichloride;

10 bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)-
indenyl]]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)-
indenyl]]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)-
indenyl]]} zirconium dichloride;

15 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)-
indenyl]]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)-
indenyl]]} zirconium dichloride;

20 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)-
indenyl]]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)-
indenyl]]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)-
indenyl]]} zirconium dichloride;

25 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)-
indenyl]]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)-
indenyl]]} zirconium dichloride;

30 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)-
indenyl]]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)-
indenyl]]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2- β -naphthylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)-inderyl]}zirconium dichloride;

5 bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)-inderyl]}zirconium dichloride;

10 bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)-inderyl]}zirconium dichloride;

15 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)-inderyl]}zirconium dichloride;

20 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)-inderyl]}zirconium dichloride;

25 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)-inderyl]}zirconium dichloride;

30 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)-inderyl]}zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)-indenyl]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)-indenyl]} zirconium dichloride;

5 bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)-indenyl]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)-indenyl]} zirconium dichloride;

10 bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)-indenyl]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)-indenyl]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dichloride;

15 bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dichloride;

20 bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dichloride;

25 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dichloride;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

30 bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}
zirconium dimethyl;

5 bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}
zirconium dimethyl;

10 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}
zirconium dimethyl;

15 bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}
zirconium dimethyl;

20 bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}
zirconium dimethyl;

25 bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}
zirconium dimethyl;

30 bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}
zirconium dimethyl;

5 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}
zirconium dimethyl;

10 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}
zirconium dimethyl;

15 bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}
20 zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dimethyl;

25 bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}
30 zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dimethyl;

5 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dimethyl;

10 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}
zirconium dimethyl;

15 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}
20 zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dimethyl;

25 bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}
zirconium dimethyl;

30 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dimethyl;

5 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dimethyl;

10 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}
zirconium dimethyl;

15 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}
zirconium dimethyl;

20 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}
zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-biphenyl)indenyl]} zirconium
dimethyl;

25 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)-
indenyl]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)-
indenyl]} zirconium dimethyl;

30 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)-
indenyl]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)-
indenyl]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)-indenyl]}zirconium dimethyl;

5 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2- α -naphthylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)-indenyl]}zirconium dimethyl;

10 bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)-indenyl]}zirconium dimethyl;

15 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)-indenyl]}zirconium dimethyl;

20 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2- β -naphthylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)-indenyl]}zirconium dimethyl;

25 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)-indenyl]}zirconium dimethyl;

30 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)-indenyl]}zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)-indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)-indeny]} zirconium dimethyl;

5 bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)-indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indeny]} zirconium dimethyl;

10 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)-indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)-indeny]} zirconium dimethyl;

15 bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2,3-dimethylphenyl)-indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)-indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)-indeny]} zirconium dimethyl;

20 bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)-indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)-indeny]} zirconium dimethyl;

25 bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)-indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)-indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)-indeny]} zirconium dimethyl;

30 bis(trimethylsilyl)amidoboranebis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)-indeny]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dimethyl;

5 bis(trimethylsilyl)amidoboranebis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dimethyl;

10 bis(trimethylsilyl)amidoboranebis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dimethyl;

bis(trimethylsilyl)amidoboranebis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)-indenyl]} zirconium dimethyl;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}
zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium

η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediyibis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium

η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

10 zirconium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium

η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediyibis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediyibis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediyibis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediyibis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-
diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-
diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-
diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -1,4-
diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -1,4-
diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium
 η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -
1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-
hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium
 η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 dimethylsilanediylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 dimethylsilanediylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 dimethylsilanediylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 dimethylsilanediyibis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

10 dimethylsilanediyibis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

dimethylsilanediyibis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediyibis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediyibis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediyibis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediyibis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediyibis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediyibis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediyibis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediyibis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediyibis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

- 9-silafluorenediylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 5 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 10 9-silafluorenediylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 15 9-silafluorenediylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 20 9-silafluorenediylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 25 9-silafluorenediylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;
- 30 1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]} zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]} zirconium
 η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]} zirconium η^4 -
1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]} - zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]} zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium

η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium

η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]}

10 zirconium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]}zirconium

η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2-methylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-isobutyl, 4-(2-methylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-methylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-methylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-phenyl, 4-(2-methylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-isopropyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-phenyl, 4-(2-ethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2-n-propylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-n-propyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2-isopropylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-n-propyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-isobutyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2-n-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-isopropyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-isobutyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-phenyl, 4-(2-isobutylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-isopropyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-phenyl, 4-(2-sec-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-propyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2-tert-butylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-n-propyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2-biphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-n-propyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-isobutyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

- 9-silafluorenediylbis{1-[2-phenyl, 4-(2- α -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-n-propyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 5 9-silafluorenediylbis{1-[2-isopropyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-n-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-isobutyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 10 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 15 9-silafluorenediylbis{1-[2-phenyl, 4-(2- β -naphthylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-n-propyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-isopropyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 20 9-silafluorenediylbis{1-[2-n-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-isobutyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 25 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 9-silafluorenediylbis{1-[2-phenyl, 4-(2-trifluoromethylphenyl)indenyl]}-hafnium η^4 -1,4-diphenyl-1,3-butadiene;
- 30

9-silafluorenediylbis{1-[2-n-propyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-n-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

10 9-silafluorenediylbis{1-[2-sec-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-tert-butyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2,3-dimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

15 9-silafluorenediylbis{1-[2-n-propyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2,3,4-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

20 9-silafluorenediylbis{1-[2-n-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isobutyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

25 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-phenyl, 4-(2,3,4-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

30 9-silafluorenediylbis{1-[2-n-propyl, 4-(2,3,5-trimethylphenyl)indenyl]}hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-isopropyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-n-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

5 9-silafluorenediylbis{1-[2-isobutyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;

9-silafluorenediylbis{1-[2-sec-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene;


10 9-silafluorenediylbis{1-[2-tert-butyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene; and

9-silafluorenediylbis{1-[2-phenyl, 4-(2,3,5-trimethylphenyl)indenyl]} hafnium η^4 -1,4-diphenyl-1,3-butadiene.

The above names represent the individual stereoisomers as well as mixtures of any ratios thereof. For example, "dimethylsilanediylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium dichloride" represents *rac*-dimethylsilanediylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium dichloride, *meso*-dimethylsilanediylbis{1-[2-n-propyl, 4-(2-methylphenyl)indenyl]} zirconium dichloride and any mixtures of these compounds.

Moreover, "biphenyl" in the above names is synonymous with "phenylphenyl".

"9-silafluorenediyl-" refers to a group of the following formula:




The metallocenes of this invention are prepared according to general techniques known from the literature, for example U.S. Patent Nos. 5,789,634 and 5,840,644 (both fully incorporated herein by reference).

5

Generally, metallocenes of this type are synthesized as shown below (for $R^4=H$) where (a) is an aryl-coupling reaction between a 4-halosubstituted indene and an aryl Grignard reagent catalyzed by $NiCl_2(PPh_3)_2$ in ether-type solvents at room temperature to reflux. Product is usually purified by column chromatography or distillation. (b) is a deprotonation via a metal salt of an alkyl anion (e.g. $n-BuLi$) to form an indenide followed by reaction with an appropriate bridging precursor (e.g. Me_2SiCl_2). Reactions are usually done in ether-type solvents at ambient temperatures. The final product is purified by column chromatography or distillation; and (c) is double deprotonation via an alkyl anion (e.g. $n-BuLi$) to form a dianion followed by reaction with a metal halide (e.g. $ZrCl_4$). The reactions are usually done in ether-type or aromatic solvents at ambient temperatures. The final products are obtained by recrystallization of the crude solids.


10

15



The metallocenes of this invention are highly active catalyst components for the polymerization of olefins. They can form different stereoisomers and are preferably employed as chiral racemates. However, it is also possible to use the individual enantiomers in the (+) or (-) form. The individual stereoisomers allow an optically active polymer to be prepared. In some cases it may be desirable to remove the meso form of the metallocenes, since the polymerization-active center (the metal atom) in these compounds is no longer chiral due to the mirror symmetry at the central metal atom and it is, therefore, not possible to produce a highly isotactic polymer. If the meso form is not removed, atactic polymer is formed in addition to isotactic polymer. For certain applications (e.g., if a random copolymer of propylene and ethylene and/or any other monoolefin and/or diene is to be made) this may be entirely desirable. Accordingly, racemic metallocenes contaminated with not more than about 5 %, preferably not more than about 2 %, and even more preferred not more than about 1%, of the meso form represent a particularly preferred embodiment of the metallocenes of the present invention. In another preferred embodiment, the meso form of a metallocene of the present invention is contaminated with not more than about 5 %, preferably not more than about 2 %, and even more preferred not more than about 1%, of the racemic form.

Rac/meso metallocene isomer separation is facilitated when metallocenes containing certain bridging groups are prepared. This has been found to be true when the bridging group, R^{13} , is represented by the formula:



wherein M^2 and R^{17} to R^{24} are as defined above.

Metallocenes are generally used in combination with some form of activator in order to create an active catalyst system. The terms "activator" and "cocatalyst" are used interchangeably and are defined herein to mean any compound or component, or combination of compounds or components, capable of enhancing the ability of one or more metallocenes to polymerize olefins.

Alkylalumoxanes such as methylalumoxane (MAO) are commonly used as metallocene activators. The alumoxanes which may be employed according to the present invention are not particularly limited. They include oligomeric linear and/or cyclic alkylalumoxanes of the general formula $R-(Al(R)-O)_n-AlR_2$ for oligomeric, linear alumoxanes and $(-Al(R)-O-)_m$ for oligomeric cyclic alumoxanes wherein n usually is 1-40, preferably 10-20, m usually is 3-40, preferably 3-20, and R usually is a C_1 - C_8 alkyl group (e.g., methyl, ethyl, n -propyl, isopropyl, n -butyl and isobutyl), and preferably methyl to provide methylalumoxane (MAO). MAO is a mixture of oligomers with a very wide distribution of molecular weights and usually with an average molecular weight of about 1200. MAO is typically kept in solution in toluene. It is also possible to use, for the present purpose, alumoxanes of the type just described wherein the alkyl groups in the above general formulae are different. A preferred example thereof is modified methylalumoxane (MMAO) wherein in comparison to MAO a part of the methyl groups is replaced by other alkyl groups. Alumoxane solutions, particularly methylalumoxane solutions, may be obtained from commercial vendors as solutions having various concentrations. There are a variety of methods for preparing alumoxane, non-limiting examples of which are described in U.S. Patent Nos. 4,665,208, 4,952,540, 5,091,352, 5,206,199, 5,204,419, 4,874,734, 4,924,018, 4,908,463, 4,968,827, 5,308,815, 5,329,032, 5,248,801, 5,235,081, 5,103,031, 6,001,766 and EP-A-0 561 476, EP-B1-0 279 586, EP-A-0 594-218 and WO 94/10180, each fully incorporated herein by reference.

Generally the atomic ratio of Al in the alumoxane to metal in the metallocene compound is at least about 10 : 1, more preferably at least about 50 : 1, and most preferred at least about 80 : 1. On the other hand said ratio is

generally not higher than about 1,000 : 1, particularly not higher than about 500 : 1, with a ratio of not higher than about 300 : 1 being particularly preferred.

Ionizing activators may also be used to activate metallocenes. These
5 activators are neutral or ionic, or are compounds such as tri(n-butyl)ammonium
tetrakis(pentafluorophenyl)borate, which ionize the neutral metallocene
compound. Unlike alumoxane cocatalysts, these ionizing activators can usually be
employed in a molar ratio with respect to the metallocene which is much closer to
1:1 (e.g., less than 5:1, less than 2:1, and preferably about 1:1). Such ionizing
10 compounds may contain an active proton, or some other cation associated with,
but not coordinated or only loosely coordinated to, the remaining ion of the
ionizing compound. Combinations of activators may also be used, for example,
alumoxane and ionizing activator combination, see for example, WO 94/07928
(incorporated herein by reference in its entirety).

15 Descriptions of ionic catalysts for coordination polymerization comprised
of metallocene cations activated by noncoordinating anions appear in the early
work in EP-A-0 277 003, EP-A-0 277 004 and U.S. Patent No. 5,198,401 and
WO-A-92/00333 (each fully incorporated herein by reference). These teach
20 desirable methods of preparation wherein metallocenes are protonated by an anion
precursor such that an alkyl/hydride group is abstracted from a transition metal to
make it both cationic and charge-balanced by the non-coordinating anion.
Suitable ionic salts include tetrakis-substituted borate or aluminum salts having
fluorinated aryl-constituents such as phenyl, biphenyl and naphthyl.

25 The term "noncoordinating anion" (NCA) means an anion which either
does not coordinate to said cation or which is only weakly coordinated to said
cation thereby remaining sufficiently labile to be displaced by a neutral Lewis
base. "Compatible" non-coordinating anions are those which are not degraded to
30 neutrality when the initially formed complex decomposes. Further, the anion will
not transfer an anionic substituent or fragment to the cation so as to cause it to
form a neutral four coordinate metallocene compound and a neutral by-product

from the anion. Non-coordinating anions useful in accordance with this invention are those which are compatible, stabilize the metallocene cation in the sense of balancing its ionic charge at +1, yet retain sufficient lability to permit displacement by an ethylenically or acetylenically unsaturated monomer during polymerization.

The use of ionizing ionic compounds not containing an active proton but capable of producing both the active metallocene cation and a non-coordinating anion is also known. See, for example, EP-A-0 426 637 and EP-A- 0 573 403 (each fully incorporated herein by reference). An additional method of making the ionic catalysts uses ionizing anion precursors which are initially neutral Lewis acids but form the cation and anion upon ionizing reaction with the metallocene compounds, for example the use of tris(pentafluorophenyl)borane. See EP-A-0 520732 (incorporated herein by reference in its entirety). Ionic catalysts for addition polymerization can also be prepared by oxidation of the metal centers of transition metal compounds by anion precursors containing metallic oxidizing groups along with the anion groups, see EP-A-0 495 375 (fully incorporated herein by reference).

Where the metal ligands include halogen moieties (for example, chloride) which are not capable of ionizing abstraction under standard conditions, they can be converted via known alkylation reactions with organometallic compounds such as lithium or aluminum hydrides or alkyls, alkylalumoxanes, Grignard reagents, etc. See EP-A-0 500 944 and EP-A1-0 570 982 (each fully incorporated herein by reference) for *in situ* processes describing the reaction of alkyl aluminum compounds with dihalo-substituted metallocene compounds prior to or with the addition of activating anionic compounds.

Methods for supporting ionic catalysts comprising metallocene cations and NCAs are described in WO 9950311, U.S. Patent Nos. 5,643,847 and 5,972,823, U.S. Patent Application No. 09/184358, filed November 2, 1998 and U.S. Patent

Application No. 09/184389, filed November 2, 1998 (each fully incorporated herein by reference).

When the activator for the metallocene supported catalyst composition is a NCA, preferably the NCA is first added to the support composition followed by the addition of the metallocene catalyst. When the activator is MAO, preferably the MAO and metallocene catalyst are dissolved together in solution. The support is then contacted with the MAO/metallocene catalyst solution. Other methods and orders of addition will be apparent to those skilled in the art.

The catalyst compositions of this invention preferably comprise a support. Suitable supports include porous particulate materials, such as for example, talc, inorganic oxides, inorganic chlorides such as magnesium chloride, and resinous materials such as polyolefins or other polymers.

Preferably, the support materials are porous inorganic oxide materials, which include those from the Periodic Table of Elements of Groups 2, 3, 4, 5, 13 or 14 metal/metalloid oxides. Silica, alumina, silica-alumina, and mixtures thereof are particularly preferable. Other inorganic oxides that may be employed either alone or in combination with the silica, alumina or silica-alumina are magnesia, titania, zirconia, and the like.

In one preferred embodiment the support material is porous silica, more preferably porous silica which has a surface area in the range of not less than 10, preferably not less than 50, and most preferred not less than 100 m²/g, but usually not more than 700, preferably not more than 500, and most preferred not more than 400 m²/g. The total pore volume thereof usually is not less than 0.1, preferably not less than 0.5, and most preferred not less than 0.8 cc/g, whereas the pore volume generally is not higher than 4.0, preferably not higher than 3.5, most preferred not higher than 3.0 cc/g. The average particle size of the porous silica should be at least 10, preferably at least 20, and most preferred at least 30 μm, the maximum value thereof usually being not higher than 500, preferably not higher

than 200, and most preferred not higher than 100 μm . The average pore size of typical porous support materials usually is at least 10, preferably at least 50, and even more preferably at least 75 Å. Average pore sizes should generally not be higher than 1000, preferably not higher than 500, and most preferred not higher than 350 Å. It may be particularly desirable to dehydrate the silica at a temperature of from 100°C to 800°C anywhere from 3 to 24 hours.

The metallocene, activator and support material may be combined in any number of ways. More than one metallocene may also be used. Examples of suitable support techniques are described in U. S. Patent Nos. 4,808,561 and 4,701,432 (each fully incorporated herein by reference). Preferably metallocene and activator are combined and their contact product is supported on the porous support material as described in U. S. Patent No. 5,240,894 and WO 94/28034, WO 96/00243, and WO 96/00245 (each fully incorporated herein by reference). Alternatively, the metallocenes may be preactivated separately and then combined with the support material either separately or together. If the metallocenes are separately supported, then preferably, they are dried and then combined as a powder before use in polymerization.

Regardless of whether the metallocene(s) and their activator are separately precontacted or whether the metallocene(s) and activator are combined at once, in some instances it may be preferred that the total volume of reaction solution applied to the porous support is less than 4 times the total pore volume of the porous support, more preferably less than 3 times the total pore volume of the porous support and even more preferably in the range of from more than 1 to less than 2.5 times the total pore volume of the porous support. Procedures for measuring the total pore volume of porous support are well known in the art. One such method is described in Volume 1, Experimental Methods in Catalyst Research, Academic Press, 1968, pages 67-96, fully incorporated herein by reference.

The supported catalyst system may be used directly in polymerization or the catalyst system may be prepolymerized using methods well known in the art. For details regarding prepolymerization, see U. S. Patent Nos. 4,923,833 and 4,921,825, and EP 0 279 863 and EP 0 354 893 (each fully incorporated herein by reference).

The metallocene catalyst systems described herein are useful in the polymerization of all types of olefins. This includes polymerization processes which produce homopolymers, copolymers, terpolymers and the like as well as block copolymers and impact copolymers. These polymerization processes may be carried out in solution, in suspension or in the gas phase, continuously or batchwise, or any combination thereof, in one or more steps, usually at a temperature not lower than 30, preferably not lower than 50, most preferred not lower than 80° C, and not higher than 200, preferably not higher than 120, most preferred not higher than 100°C. Preferably, the polymerization or copolymerization is carried out using olefins of the formula $R^a-CH=CH-R^b$. In this formula, R^a and R^b are identical or different and are a hydrogen atom or an alkyl or alkenyl radical having 1 to 14 carbon atoms. Alternatively, R^a and R^b may form a ring together with the carbon atoms connecting them. Examples of such olefins are ethylene, propylene, 1-butene, 1-hexene, 4-methyl-1-pentene, and 1-octene, vinylcyclohexane, norbornene and norbornadiene. In particular, propylene and ethylene are polymerized. The metallocenes and metallocenes catalyst systems of this invention are most suitable for the polymerization of propylene based polymers.

If necessary, hydrogen is added as a molecular-weight regulator and/or in order to increase the activity. The overall pressure in the polymerization system usually is at least about 0.5 bar, preferably at least about 2 bar, most preferred at least about 5 bar. Pressures higher than about 100, e.g., higher than about 80 bar and, in particular, higher than about 64 bar are usually not preferred.

Typically, the metallocene is used in the polymerization in a concentration, based on the transition metal, of not less 10^{-4} , preferably not less than 10^{-3} mol, and not higher than 10^{-7} , preferably not higher than 10^{-4} mol, of transition metal per dm^3 of solvent or per dm^3 of reactor volume. When alumoxane is used as the cocatalyst, it is used in a concentration of usually not less than 10^{-4} , preferably not less than 10^{-5} mol, and not higher than 10^{-1} , preferably not higher than 10^{-2} mol, per dm^3 of solvent or per dm^3 of reactor volume. The other cocatalysts mentioned are used in an approximately equimolar amount (e.g., from about 1.2 : 1 to about 1 : 1.2) with respect to the metallocene. In principle, however, higher concentrations are also possible.

If the polymerization is carried out as a suspension or solution polymerization, an inert solvent which is customary for the Ziegler low-pressure process is typically used for example, the polymerization is carried out in an aliphatic or cycloaliphatic hydrocarbon; examples of which are propane, butane, hexane, heptane, isooctane, cyclohexane and methylcyclohexane. It is also possible to use mineral spirit or a hydrogenated diesel oil fraction. Toluene can also be used. The polymerization is preferably carried out in the liquid monomer(s). If inert solvents are used, the monomer(s) is (are) metered in gas or liquid form.

Before addition of the catalyst, in particular of the supported catalyst system, another alkylaluminum compound, such as, for example, trimethylaluminum, triethylaluminum, triisobutylaluminum, trioctylaluminum or isoprenylaluminum, may additionally be introduced into the reactor in order to render the polymerization system inert (for example to remove catalyst poisons present in the olefin). This compound is added to the polymerization system in a concentration of from 100 to 0.01 mmol of Al per kg of reactor contents. Preference is given to triisobutylaluminum and triethylaluminum in a concentration of from 10 to 0.1 mmol of Al per kg of reactor contents. This allows the molar Al/M^1 ratio to be selected at a low level in the synthesis of a supported catalyst system.

In principle, however, the use of further substances for catalysis of the polymerization reaction is unnecessary, i.e., the systems according to the invention can be used as the only catalysts for the polymerization of olefins.

5 The process according to the invention is distinguished by the fact that the metallocenes described can give propylene polymers of very high molecular weight, melting point, and very high stereotacticity, with high catalyst activities in, e.g., the temperature range from about 40°C to about 100°C, such as the industrially particularly interesting polymerization temperature range of from
10 about 50°C to about 80°C .

 The catalyst systems of this invention are capable of providing polymers, particularly propylene homopolymers and copolymers, of exceptionally high molecular weight and melting point even when used in processes under
15 commercially relevant conditions of temperature, pressure and catalyst activity. Preferred melting points of olefin polymers comprising at least about 99 % by weight, preferably are at least about 99.3 % by weight and most preferred at least 99.5 % by weight of units derived from propylene (the remainder being preferably derived from one or more compounds selected from ethylene and 1-olefins
20 comprising 4 to 12 carbon atoms, most preferred ethylene) are as high as 155°C, e.g., as high as 156°C, more preferably at least 157°C, even more preferably at least 158°C, and may be as high as 160°C or even higher (these melting points being determined by DSC according to the procedure described in the Examples below).

25 With respect to molecular weights, copolymers made with the catalyst systems of the present invention such as, e.g., ethylene/propylene rubbers (EPR's) or ethylene/propylene/diene copolymers (EPDM's), usually have an intrinsic viscosity, measured in decalin at 135° C, of usually at least about 1.8, preferably at
30 least about 2.0, and more preferred at least about 2.1 (e.g., at least about 2.2). This enables the production of very satisfactory impact copolymers (ICP's), such as *in*

situ blends of propylene homopolymer or copolymer as discussed above of high melting point (and preferably also high molecular weight) and propylene copolymers (such as EPR's and/or EPDM's) of high intrinsic viscosity with a single catalyst system (and, preferably, in a single reactor). For this purpose, the copolymers generally will have an ethylene content of at least about 30, preferably at least about 35, more preferred at least about 40 weight % and not more than about 60, preferably not more than about 50 weight %. The ethylene content of the ICP's usually will be at least about 1.5, preferably at least about 3 weight percent and up to about 20, preferably up to about 15, weight %.

The homo- and copolymers made with the catalyst systems of the present invention (e.g., those containing units derived from propylene, or from propylene and ethylene) also have a narrow molecular weight distribution, M_w/M_n , usually of not higher than about 3.5, preferably not higher than about 3.0, more preferred not higher than about 2.5 and sometimes even not higher than about 2.2. They also are distinguished by low xylene and n-hexane extractables contents. Often the xylene extractables and/or the n-hexane extractables of these homo- and copolymers will amount to less than about 2.0, preferably less than about 1.5, even more preferred less than about 1.0 weight %. A general description of the procedure for measuring the xylene extractables (solubles) is found in J. C. Randall, J. Poly. Sci.: Part A Polymer Chemistry, Vol. 36, 1527-1542 (1998), incorporated herein by reference in its entirety. Hexane extractions are performed by weighing the polymer sample in a dried soxhlet thimble. Hexane is heated to reflux through the thimble in the soxhlet apparatus. When the extraction is complete the solvent is evaporated, and the sample dried under the appropriate vacuum. The amount of extractables is determined by weight. The thimble containing the insoluble polymer is dried in a vacuum oven and the weight of the recovered polymer is determined.

The polymer compositions of the present invention are also characterized by a relatively narrow molecular weight distribution. Their values of M_w/M_n (as determined by Gel Permeation Chromatography using polystyrene standards, see

Examples below) usually are not higher than about 3.5, often not higher than about 3.0, e.g., not higher than about 2.7.

Catalyst systems of this invention are capable of providing propylene
5 polymers having high stereospecificity and regiospecificity. Isotactic propylene
polymers prepared according to the processes of this invention may have a
proportion of 2,1-inserted propene units of less than about 0.5%, at a triad tacticity
of greater than about 98% (see, for example, the results summarized in Table 21C,
below). Preferably, there is no measurable proportion of 2,1-inserted propene
10 units. Triad tacticity is determined using ^{13}C -NMR according to J.C. Randall,
Polymer Sequence Determination: Carbon-13 NMR Method, Academic Press
New York 1978, incorporated herein by reference in its entirety.

Polymers prepared using the processes described herein find uses in all
15 applications including fibers, injection-molded parts, films, pipes, and wire and
cable applications. Non-limiting examples include carpet fibers and primary and
secondary carpet backing; slit tape applications such as tarpaulins, erosion
abatement screens, sand bags, fertilizer and feed bags, swimming pool covers,
intermediate bulk container (IBC) bags; non-woven applications for spunbonded,
20 melt blown and thermobonded carded web applications such as disposable diaper
liners, feminine hygiene products, tarpaulins and tent fabrics, and hospital
garments; apparel applications such as socks, T-shirts, undergarments, bicycle
shorts, sweat bands, football undershirts, hiking socks and other outdoor sporting
apparel; cordage applications such as mooring and towing lines and rope
25 applications; netting applications such as safety fences, geogrids for soil
stabilization; injection molded applications such as appliance parts in automatic
dishwashers and clothes washers, hand tools and kitchen appliances; consumer
product applications such as outdoor furniture, luggage, infant car seats, ice
coolers, yard equipment; medical applications such as disposable syringes and
30 other hospital and laboratory devices; rigid packaging made by injection molding,
blow molding or thermoforming such as margarine tubs, yogurt containers and
closures, commercial bottles and ready-to-eat food containers; transportation

applications such as automotive interior trim, instrument panels, bumper fascia, grills and external trim parts, battery cases; film applications such as snack packages and other food packaging and film labels, packing tapes and pressure sensitive labels; wire and cable applications such as wire insulation .

5

While the present invention has been described and illustrated by reference to particular embodiments, it will be appreciated by those of ordinary skill in the art, that the invention lends itself to many different variations not illustrated herein. For these reasons, then, reference should be made solely to the appended claims for purposes of determining the true scope of the present invention.

10

Although the appendant claims have single dependencies in accordance with U.S. patent practice, each of the features in any of the appendant claims can be combined with each of the features of other appendant claims or the main claim.

15

EXAMPLES

All air sensitive experiments were carried out in nitrogen purged dry boxes. All solvents were purchased from commercial sources. Aluminum alkyls were purchased as hydrocarbon solutions from commercial sources. The commercial methylalumoxane ("MAO") was purchased from Albemarle as a 30 wt % solution in toluene.

20
25

EXAMPLE 1

Racemic dimethylsilanediylbis{1-[2-methyl, 4-phenylindenyl]}zirconium dichloride was obtained from commercial sources and used as received.

30

Supported Metallocene Catalyst System 1

In a 100 mL round bottom flask racemic dimethylsilanediybis{1-[2-methyl, 4-phenylindenyl]}zirconium dichloride (0.055 g) was added to the above MAO solution (6.74 g, 7.2 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about 2 hours and twenty two minutes. The supported catalyst was recovered as a light orange, free flowing solid (5.63 g).

EXAMPLE 2

2-Methyl, 4-(3-methylphenyl)-indene

3-Bromotoluene (10.0 g, 58 mmol) and magnesium turnings (2.0 g, 83 mmol) were taken up in 150 mL of Et₂O (diethyl ether) and stirred at room temperature overnight to form the Grignard solution. In a separate flask, NiCl₂(PPh₃)₂ (1.8 g, 2.8 mmol) and 4-chloro-2-methylindene (9.5 g, 58 mmol) were dissolved in 150 mL of Et₂O. The Grignard solution was added dropwise to this solution and allowed to stir overnight at reflux. After overnight stirring, the reaction was slowly quenched with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 6.3 g (48 %).

Lithium{1-[2-methyl, 4-(3-methylphenyl)indenide]}

2-Methyl, 4-(3-methylphenyl)-indene (6.3 g, 28 mmol) was dissolved in 100 mL of pentane. To this solution was added 11 mL of n-BuLi (n-butyl lithium; 2.5M in hexane) and the reaction was allowed to stir 5 hours at room temperature.

A yellow-white solid precipitated from the solution and was collected by frit filtration and washed with additional pentane. Yield: 6.0 g (95%).

Dimethylsilanediylbis{1-[2-methyl, 4-(3-methylphenyl)indene]}

5 Me_2SiCl_2 (dichlorodimethylsilane; 0.83 g, 6.5 mmol) was dissolved in 80 ml of THF. While stirring, lithium{1-[2-methyl, 4-(3-methylphenyl)indenide]} (3.0 g, 13 mmol) was added as a dry powder and the contents were allowed to stir at reflux overnight. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in
10 vacuo, and the crude product was isolated. Yield: 2.4 g (74 %)

Dimethylsilanediylbis{1-[2-methyl,4-(3-methylphenyl)indenyl]} zirconium
dichloride

15 Dimethylsilanediylbis{1-[2-methyl,4-(3-methylphenyl)indene]} (2.4 g, 4.6 mmol) was dissolved in 50 mL of Et_2O . To this solution was added 3.7 mL of n-BuLi (2.5M in hexane) and stirred for 3 hours. The solution was then cooled to -35 °C and ZrCl_4 (1.1 g, 5.9 mmol) was added as a dry powder and the reaction was stirred at room temperature overnight. The solvent was removed in vacuo and the residue was taken up in toluene. The solution was filtered through a celite
20 packed frit to remove LiCl, concentrated and cooled to -35 °C to induce crystallization. Yellow-orange crystals of the racemic isomer were isolated. Yield: 260 mg (8.6%).

Supported Metallocene Catalyst System 2

25 In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(3-methylphenyl)indenyl]}zirconium dichloride (0.058 g) was added to the above MAO-toluene solution (6.74 g) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates were added dehydrated silica (4.0 g, Davison 948
30 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about 2 hours and

twenty nine minutes. The supported catalyst was recovered as a reddish orange, free flowing solid (5.58 g).

EXAMPLE 3

2-Methyl, 4-(3,5-dimethylphenyl)-indene

4-Chloro-2-methylindene (8.9 g, 54 mmol) and $\text{NiCl}_2(\text{PPh}_3)_2$ (1.8g, 2.8 mmol) were dissolved in 150 mL of Et_2O . 3,5-Dimethylphenylmagnesium bromide (10g, 54 mmol) as Et_2O solution was added to the solution and the reaction was stirred overnight at room temperature. After overnight stirring the reaction was slowly quenched with H_2O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% $\text{HCl}(\text{aq})$, and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 5.6 g (44%).

Lithium{1-[2-methyl, 4-(3,5-dimethylphenyl)indenide]}

2-Methyl, 4-(3,5-dimethylphenyl)-indene (5.6 g, 23.9 mmol) was dissolved in 80 mL of pentane. To this solution was added 9.6 mL of $n\text{-BuLi}$ (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 4.5 g (80 %).

Dimethylsilanediylbis{1-[2-methyl, 4-(3,5-dimethylphenyl)indene]}

Me_2SiCl_2 (1.2 g, 9.4 mmol) was dissolved in 80 mL of THF. While stirring, lithium{1-[2-methyl, 4-(3,5-dimethylphenyl)indenide]} (4.5 g, 18.7 mmol) was added as a dry powder and the contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid (4.23 g, 87 %).

Dimethylsilanediylbis{1-[2-methyl, 4-(3,5-dimethylphenyl)indenyl]}zirconium
dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(3,5-dimethylphenyl)indene]} (4.23 g, 8.0 mmol) was dissolved in 60 mL of Et₂O. While stirring, 6.4 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 2 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (1.58 g, 8.0 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. 0.23 g (5.0%) of pure racemic compound was obtained.

Supported Metallocene Catalyst System 3

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(3,5-dimethylphenyl)indenyl]}zirconium dichloride (0.061 g) was added to the above MAO-toluene solution (6.74 g, 7.35 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two hours and twenty six minutes. The supported catalyst was recovered as a light orange, free flowing solid (5.36 g).

EXAMPLE 4

2-Methyl, 4-(2-methylphenyl)-indene

2-Bromotoluene (8.8 g, 51 mmol) and magnesium turnings (2.4 g, 102 mmol) were taken up in 100 mL of Et₂O (diethyl ether) and stirred at room temperature for 4 hours to form the Grignard solution. In a separate flask, NiCl₂(PPh₃)₂ (1.8 g, 2.8 mmol) and 4-chloro-2-methylindene (8.4 g, 51 mmol) were dissolved in 300 mL of Et₂O. The Grignard solution was added dropwise to this solution and allowed to stir overnight at reflux. After overnight stirring, the

reaction was slowly quenched with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq) and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 5.3 g (47 %).

Lithium{1-[2-methyl, 4-(2-methylphenyl)indenide]}

2-Methyl, 4-(2-methylphenyl)indene (5.3 g, 5.9 mmol) was dissolved in 100 mL of pentane. To this solution was added 9.6 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 5 hours at room temperature. A yellow-white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 4.6 g (87%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2-methylphenyl)indene]}

Me₂SiCl₂ (1.3 g, 10 mmol) was dissolved in 80 mL of pentane and 60 ml of THF. While stirring, lithium{1-[2-methyl, 4-(2-methylphenyl)-indenide]} (4.6 g, 20 mmol) was added as a dry powder and the contents were allowed to stir at reflux for 4 hours. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo, and the crude product was isolated as a viscous oil. Yield: 3.5 g (69 %).

Dilithium dimethylsilanediylbis{1-[2-methyl, 4-(2-methylphenyl)indenide]}

Dimethylsilanediylbis{1-[2-methyl, 4-(2-methylphenyl)indene]} (3.5 g, 4.8 mmol) was dissolved in 80 mL of Et₂O. To this solution was added 5.4 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir for 3 hours. The solution was filtered through a celite-packed frit and the solvent was removed in vacuo to produce a flaky white solid, which was washed with pentane. Yield of solid: 3.0 g (86%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2-methylphenyl)indenyl]} zirconium
dichloride

Dilithiumdimethylsilanediylbis{1-[2-methyl,4-(2-methylphenyl)indenide]}
(3.0g, 5.9 mmol) was dissolved in 80 mL of Et₂O and cooled to -30 °C. To this
5 solution was added ZrCl₄ (1.37 g, 5.9 mmol) as a dry powder and the reaction was
stirred at room temperature overnight. The solvent was removed in vacuo and the
residue was taken up in toluene. The solution was filtered through a celite packed
frit to remove LiCl, concentrated and cooled to -35 °C to induce crystallization.
Yellow-orange crystals of the racemic isomer were isolated. Yield: 220 mg
10 (5.1%).

Supported Metallocene Catalyst System 4

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl,4-(2-
methylphenyl)indenyl]}zirconium dichloride (0.058 g) was added to the above
15 MAO-toluene solution (6.74 g, 7.35 mL) and stirred for twenty minutes. The
resultant mixture was filtered through a medium glass frit funnel and washed with
toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g,
Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty
minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator
20 until the liquid evaporated and then the solid was further dried a total of about 2
hours and thirty two minutes. The supported catalyst was recovered as a salmon
orange, free flowing solid (5.34 g).

EXAMPLE 5

2-Methyl, 4-(2-ethylphenyl)-indene

2-Ethylphenylbromide (10.0 g, 46 mmol) and magnesium turnings (2.0 g,
83 mmol) were taken up in 150 mL of Et₂O and stirred at room temperature for 4
hours to form the Grignard solution. In a separate flask, NiCl₂(PPh₃)₂ (1.8 g, 2.8
mmol) and 4-chloro-2-methylindene (7.5 g, 46 mmol) were dissolved in 150 mL
30 of Et₂O. The Grignard solution was added dropwise to this solution and allowed
to stir overnight at reflux. After overnight stirring, the reaction was slowly
quenched with H₂O to neutralize unreacted Grignard. Thereafter the solution was

treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 7.6 g (71 %).

5

Lithium{1-[2-methyl, 4-(2-ethylphenyl)indenide]}

2-Methyl, 4-(2-ethylphenyl)-indene (7.6 g, 32 mmol) was dissolved in 80 mL of pentane. To this solution was added 13 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 5 hours at room temperature. A yellow-white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 7.0 g (92%).

10

Dimethylsilanediylbis{1-[2-methyl, 4-(2-ethylphenyl)indene]}

Me₂SiCl₂ (0.82 g, 6.4 mmol) was dissolved in 80 mL of pentane and 50 mL of THF. While stirring, lithium{1-[2-methyl, 4-(2-ethylphenyl)indenide]} (3.0 g, 13 mmol) was added as a dry powder and the contents were allowed to stir at reflux overnight. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo, and the crude product was isolated as a fluffy white solid. Yield: 2.8 g (86%).

15

Dimethylsilanediylbis{1-[2-methyl, 4-(2-ethylphenyl)indenyl]} zirconium
dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(2-ethylphenyl)indene]} (2.5 g, 4.7 mmol) was dissolved in 50 mL of Et₂O. To this solution was added 4.4 mL of n-BuLi (2.5M in hexane) and the solution was allowed to stir at room temperature for 2 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (1.1 g, 4.7 mmol) was added as a dry powder. The reaction was allowed to warm to room temperature and was stirred overnight. The solution was filtered through a celite-packed frit to remove LiCl, concentrated, and cooled to -35 °C to induce crystallization. Yellow-orange crystals of the racemic isomer were obtained. Yield: 170 mg (5.2%).

20

25

30

Supported Metallocene Catalyst System 5

In a 100 mL round bottom flask dimethylsilanediybis{1-[2-methyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride (0.061 g) was added to the above MAO-toluene solution (6.74 g) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two hours and thirty three minutes. The supported catalyst was recovered as a pink, free flowing solid (5.57 g).

EXAMPLE 6

2-Methyl, 4-(2-isopropylphenyl)-indene

2-Isopropylbromobenzene (10 g, 45 mmol) and magnesium (2.4 g, 100 mmol) were combined in 200 mL of diethyl ether and stirred at room temperature overnight to form a Grignard solution. 4-Chloro-2-methylindene (7.4 g, 45 mmol) and $\text{NiCl}_2(\text{PPh}_3)_2$ (1.8g, 2.8 mmol) were dissolved in 150 mL of Et_2O . To this was added the Grignard solution and the reaction was stirred overnight at room temperature. After overnight stirring, the reaction was slowly quenched with H_2O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% $\text{HCl}(\text{aq})$, and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 4.4 g (39%).

Lithium{1-[2-methyl, 4-(2-isopropylphenyl)indenide]}

2-Methyl, 4-(2-isopropylphenyl)-indene (4.4 g, 18 mmol) was dissolved in 80 mL of pentane. To this solution was added 7.0 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 4.0 g (90 %).

Dimethylsilanediylbis{1-[2-methyl, 4-(2-isopropylphenyl)indene]}

Me₂SiCl₂ (1.0 g, 7.7 mmol) was dissolved in 80 mL of THF. While stirring, lithium{1-[2-methyl, 4-(2-isopropylphenyl)indenide]} (4.0 g, 15.5 mmol) was added as a dry powder and the contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid (2.1 g, 48 %).

Dimethylsilanediylbis{1-[2-methyl, 4-(2-isopropylphenyl)indenyl]}zirconium dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(2-isopropylphenyl)indene]} (2.1 g, 3.8 mmol) was dissolved in 60 mL of Et₂O. While stirring, 3.0 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 2 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (0.88 g, 3.8 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. 0.34 g (13%) of pure racemic compound was obtained.

Supported Metallocene Catalyst System 6

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(2-isopropylphenyl)indenyl]}zirconium dichloride (0.063 g) was added to the above MAO-toluene solution (6.74 g, 7.2 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two hours and twenty two minutes. The supported catalyst was recovered as a light orange, free flowing solid (5.56 g).

EXAMPLE 72-Methyl, 4-(2-biphenyl)-indene

Magnesium (2.0 g, 83 mmol), 2-bromobiphenyl (10 g, 43 mmol) were added together in 100 mL of diethyl ether and allowed to stir overnight at reflux to form a Grignard solution. 4-Chloro-2-methylindene (6.4 g, 43 mmol) and NiCl₂(PPh₃)₂ (1.5 g, 2.3 mmol) were dissolved in 150 mL of Et₂O. The Grignard solution was added and the reaction was stirred overnight at reflux. After overnight stirring, the reaction was slowly quenched with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 3.9 g (32%).

Lithium{1-[2-methyl, 4-(2-biphenyl)indenide]}

2-Methyl, 4-(2-biphenyl)-indene (3.9 g, 14 mmol) was dissolved in 100 mL of pentane. To this solution was added 5.6 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 3.0 g (76%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2-biphenyl)indenide]}

Me₂SiCl₂ (0.67 g, 5.2 mmol) was dissolved in 60 mL of diethyl ether. While stirring, lithium{1-[2-methyl, 4-(2-biphenyl)indenide]} (3.0 g, 10 mmol) was added as a dry powder and a few drops of THF were added to catalyze the reaction. The contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid. Yield: 2.3g (72%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2-biphenyl)indenyl]}zirconium
dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(2-biphenyl)indene]} (2.3 g, 3.7 mmol) was dissolved in 50 mL of Et₂O. While stirring, 3.0 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 0.5 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (0.87 g, 3.7 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. 0.22 g (7.5%) of pure racemic isomer was isolated.

Supported Metallocene Catalyst System 7

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(2-biphenyl)indenyl]}zirconium dichloride (0.058 g) was added to the above MAO-toluene solution (5.68 g, 6.05 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (11.8 mL). To the combined filtrates was added dehydrated silica (3.37 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about 2 hours and twelve minutes. The supported catalyst was recovered as a pink-red, free flowing solid (4.58 g).

EXAMPLE 8

2-Methyl, 4-(4-biphenyl)-indene

4-Bromobiphenyl (10 g, 39 mmol) and magnesium (2.0 g, 83 mmol) were combined in 100 mL of diethyl ether and stirred at room temperature overnight to form a Grignard solution. 4-Chloro-2-methylindene (6.4 g, 39 mmol) and NiCl₂(PPh₃)₂ (1.8g, 2.8 mmol) were dissolved in 150 mL of Et₂O. To this was added the Grignard solution and the reaction was stirred overnight at room temperature. After overnight stirring, the reaction was slowly quenched with H₂O

to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 5.3 g (44%).

Lithium{1-[2-methyl, 4-(4-biphenyl)indenide]}

2-Methyl, 4-(4-biphenyl)-indene (5.3 g, 19 mmol) was dissolved in 80 mL of pentane. To this solution was added 7.5 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 3.4 g (64 %).

Dimethylsilanediylbis{1-[2-methyl, 4-(4-biphenyl)indene]}

Me₂SiCl₂ (0.77 g, 5.9 mmol) was dissolved in 80 mL of THF. While stirring, lithium{1-[2-methyl, 4-(4-biphenyl)indenide]} (3.4 g, 12 mmol) was added as a dry powder and the contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid (1.8 g, 49%).

Dimethylsilanediylbis{1-[2-methyl, 4-(4-biphenyl)indenyl]} zirconium
dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(4-biphenyl)indene]} (1.8 g, 2.9 mmol) was dissolved in 60 mL of Et₂O. While stirring, 2.3 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 2 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (0.67 g, 5.2 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. 0.093 g (4.1%) of pure racemic compound was obtained.

Supported Metallocene Catalyst System 8

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(4-biphenyl)indenyl]}zirconium dichloride (0.075 g) was mixed with the above MAO-toluene solution (7.2 g, 7.8 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about 2 hours and twenty seven minutes. The supported catalyst was recovered as a reddish pink, free flowing solid (5.25 g).

EXAMPLE 9

2-Methyl, 4-(4-tert-butylphenyl)-indene

Magnesium (3.4 g, 141 mmol) and 4-tert-butylbromobenzene (20 g, 94 mmol) were added together in 200 mL of diethyl ether and allowed to stir overnight at reflux to form a Grignard solution. 4-Chloro-2-methylindene (15.4 g, 94 mmol) and $\text{NiCl}_2(\text{PPh}_3)_2$ (1.5 g, 2.3 mmol) were dissolved in 200 mL of Et_2O . The Grignard solution was added and the reaction was stirred overnight at reflux. After overnight stirring, the reaction was slowly quenched with H_2O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% $\text{HCl}(\text{aq})$, and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 9.8 g (40%).

Lithium{1-[2-methyl, 4-(4-tert-butylphenyl)indenide]}

2-Methyl, 4-(4-tert-butylphenyl)-indene (4.0 g, 15 mmol) was dissolved in 100 mL of pentane. To this solution was added 6.1 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 4.0 g (99%).

Dimethylsilanediylbis{1-[2-methyl, 4-(4-tert-butylphenyl)indene]}

Me₂SiCl₂ (0.98 g, 7.6 mmol) was dissolved in 50 mL of diethyl ether. While stirring, lithium{1-[2-methyl, 4-(4-tert-butylphenyl)indenide]} (4.0 g, 15 mmol) was added as a dry powder and a few drops of THF were added to catalyze the reaction. The contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield an oil. The crude oil was loaded onto a silica gel column and eluted with hexane. Yield of product was 2.4 g (54%).

Dimethylsilanediylbis{1-[2-methyl, 4-(4-tert-butylphenyl)indenyl]}zirconium dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(4-tert-butylphenyl)indene]} (2.4 g, 4.1 mmol) was dissolved in 40 mL of Et₂O. While stirring, 5.6 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 0.5 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (0.96 g, 4.1 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. Yield of product was 1.4 g (46%) as 1:1 mixture of racemic and meso isomers.

Supported Metallocene Catalyst System 9

In a 100 mL round bottom flask a racemic/meso mixture of dimethylsilanediylbis{1-[2-methyl,4-(4-tert-butylphenyl)indenyl]}zirconium dichloride (0.030 g) was added to the above MAO-toluene solution (3.37 g, 3.6 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (7 mL). To the combined filtrates was added dehydrated silica (2.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and

then the solid was further dried a total of about 2 hours and fifteen minutes. The supported catalyst was recovered as a pinkish, free flowing solid (2.55 g).

EXAMPLE 10

2-Methyl, 4-(2,3-dimethylphenyl)-indene

3-Bromo-*o*-xylene (12.0 g, 64 mmol) and magnesium turnings (2.3 g, 96 mmol) were taken up in 200 mL of Et₂O and stirred at room temperature overnight to form a Grignard solution. In a separate flask, NiCl₂(PPh₃)₂ (1.8 g, 2.8 mmol) and 4-chloro-2-methylindene (11 g, 64 mmol) were dissolved in 100 mL of Et₂O. The Grignard solution was added dropwise to this solution and allowed to stir overnight at reflux. After overnight stirring, the reaction was slowly quenched with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 6.6 g (44 %).

Lithium{1-[2-methyl, 4-(2,3-dimethylphenyl)indenide]}

2-Methyl, 4-(2,3-dimethylphenyl)-indene (6.6 g, 28 mmol) was dissolved in 200 mL of pentane. To this solution was added 11 mL of n-BuLi (2.5M in hexane) and 3 mL of diethyl ether and the reaction was allowed to stir 1 hour at room temperature. A yellow-white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 6.5 g (99%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,3-dimethylphenyl)indenide]}

Me₂SiCl₂ (0.81 g, 6.3 mmol) was dissolved in 40 ml of THF. While stirring, lithium{1-[2-methyl, 4-(2,3-dimethylphenyl)indenide]} (3.0 g, 13 mmol) was added as a dry powder and the contents were allowed to stir at reflux overnight. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane solution was cooled and white crystals of the product precipitated from solution. Yield: 3.3 g (100%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium
dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(2,3-dimethylphenyl)indene]} (3.3 g, 6.3 mmol) was dissolved in 50 mL of Et₂O. To this solution was added 5.0 mL of n-BuLi (2.5M in hexane) and stirred for 3 hours. The solution was then cooled to -30 °C and ZrCl₄ (1.5 g, 6.3 mmol) was added as a dry powder and the reaction was stirred at room temperature overnight. The solvent was removed in vacuo and the residue was taken up in toluene. The solution was filtered through a celite packed frit to remove LiCl, concentrated and cooled to -35C to induce crystallization. Yellow-orange crystals of the racemic isomer were isolated. Yield: 220 mg (5.1%).

Supported Metallocene Catalyst System 10

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium dichloride (0.061 g) was added to the above MAO-toluene solution (6.74 g, 7.2 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about 2 hours and thirty minutes. The supported catalyst was recovered as a pink, free flowing solid (5.53 g).

EXAMPLE 11

2-Methyl, 4-(2,4-dimethylphenyl)-indene

4-Bromo-*m*-xylene (15 g, 80 mmol) and magnesium turnings (2.9 g, 120 mmol) were taken up in 200 mL of diethyl ether and stirred at room temperature overnight to form a Grignard solution. In a separate flask, NiCl₂(PPh₃)₂ (1.8 g, 2.8 mmol) and 4-chloro-2-methylindene (13 g, 80 mmol) were dissolved in 100 mL of Et₂O. The Grignard solution was added dropwise to this solution and allowed to stir overnight at reflux. After overnight stirring, the reaction was slowly quenched

with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded
5 onto a silica gel column and eluted with hexane. Yield: 11 g (59 %).

Lithium{1-[2-methyl, 4-(2,4-dimethylphenyl)indenide]}

2-Methyl, 4-(2,4-dimethylphenyl)-indene (11 g, 28 mmol) was dissolved in 200 mL of pentane. To this solution was added 19 mL of n-BuLi (2.5M in
10 hexane) and 3 mL of diethyl ether and the reaction was allowed to stir 1 hour at room temperature. A yellow-white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 11 g (99%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,4-dimethylphenyl)indene]}

15 Me₂SiCl₂ (0.83 g, 6.4 mmol) was dissolved in 40 ml of THF. While stirring, lithium{1-[2-methyl, 4-(2,4-dimethylphenyl)indenide]} (3.0 g, 13 mmol) was added as a dry powder and the contents were allowed to stir at reflux overnight. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane solution was cooled and
20 white crystals of the product precipitated from solution. Yield: 3.3 g (100%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,4-dimethylphenyl)indenyl]}zirconium
dichloride

25 Dimethylsilanediylbis{1-[2-methyl, 4-(2,4-dimethylphenyl)indene]} (3.3 g, 6.3 mmol) was dissolved in 50 mL of Et₂O. To this solution was added 5.0 mL of n-BuLi (2.5M in hexane) and stirred for 3 hours. The solution was then cooled to -30 °C and ZrCl₄ (1.5 g, 6.3 mmol) was added as a dry powder and the reaction was stirred at room temperature overnight. The solvent was removed in vacuo and the residue was taken up in toluene. The solution was filtered through a celite
30 packed frit to remove LiCl, concentrated and cooled to -35 °C to induce crystallization. Yellow-orange crystals of the racemic isomer were isolated. Yield: 700 mg (16%).

Supported Metallocene Catalyst System 11

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(2,4-dimethylphenyl)indenyl]}zirconium dichloride (0.061 g) was added to the above MAO-toluene solution (6.74 g, 7.2 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two hours and fifteen minutes. The supported catalyst was recovered as a pinkish red, free flowing solid (5.68 g).

EXAMPLE 12

2-Methyl, 4-(2,6-dimethylphenyl)-indene

2-Bromo-*m*-xylene (10.0 g, 54 mmol) and magnesium turnings (2.4 g, 100 mmol) were taken up in 150 mL of Et₂O and stirred at room temperature for 4 hours to form a Grignard solution. In a separate flask, NiCl₂(PPh₃)₂ (1.8 g, 2.8 mmol) and 4-chloro-2-methylindene (8.9 g, 54 mmol) were dissolved in 150 mL of Et₂O. The Grignard solution was added dropwise to this solution and allowed to stir overnight at reflux. After overnight stirring, the reaction was slowly quenched with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 4.0 g (32 %).

Lithium{1-[2-methyl, 4-(2,6-dimethylphenyl)indenide]}

2-Methyl, 4-(2,6-dimethylphenyl)-indene (4.0 g, 17 mmol) was dissolved in 80 mL of pentane. To this solution was added 6.8 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 2 hours at room temperature. A

yellow-white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 4.0 g (100%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,6-dimethylphenyl)indenyl]}

5 Me_2SiCl_2 (1.1 g, 8.5 mmol) was dissolved in 80 ml of THF. While stirring, lithium{1-[2-methyl, 4-(2,6-dimethylphenyl)indenyl]} (4.0 g, 17 mmol) was added as a dry powder and the contents were allowed to stir at reflux overnight. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane solution was cooled and white crystals
10 of the product precipitated from solution. Yield: 1.7 g (86%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,6-dimethylphenyl)indenyl]}zirconium
dichloride

15 Dimethylsilanediylbis{1-[2-methyl, 4-(2,6-dimethylphenyl)indenyl]} (1.4 g, 2.7 mmol) was dissolved in 80 mL of Et_2O . To this solution was added 2.2 mL of n-BuLi (2.5M in hexane) and the solution was allowed to stir at room temperature for 2 hours. After this time, the solution was cooled to -35°C and ZrCl_4 (0.63 g, 2.7 mmol) was added as a dry powder. The reaction was allowed to warm to room temperature and was stirred overnight. The solution was filtered
20 through a celite-packed frit to remove LiCl, concentrated, and cooled to -35°C to induce crystallization. Yellow-orange crystals of the racemic isomer were obtained. Yield: 450 mg (24%).

Supported Metallocene Catalyst System 12

25 In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(2,6-dimethylphenyl)indenyl]}zirconium dichloride (0.061 g) was added to the above MAO-toluene solution (6.74 g, 7.3 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g,
30 Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40°C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two

hours and forty one minutes. The supported catalyst was recovered as a reddish orange, free flowing solid (5.39 g).

EXAMPLE 13

2-Methyl, 4-(2,5-dimethylphenyl)-indene

2-Bromo-*p*-xylene (20 g, 108 mmol) and magnesium turnings (4.0 g, 162 mmol) were taken up in 300 mL of Et₂O and stirred at room temperature overnight to form a Grignard solution. In a separate flask, NiCl₂(PPh₃)₂ (1.8 g, 2.8 mmol) and 4-chloro-2-methylindene (18 g, 108 mmol) were dissolved in 200 mL of Et₂O. The Grignard solution was added dropwise to this solution and allowed to stir overnight at reflux. After overnight stirring, the reaction was slowly quenched with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 9.2 g (36 %).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,5-dimethylphenyl)indene]}

2-Methyl, 4-(2,5-dimethylphenyl)-indene (4.0 g, 17 mmol) was dissolved in 30 mL of Et₂O and cooled to -30°C. To this solution was added 6.8 mL of *n*-BuLi (2.5M in hexane) and the reaction was allowed to stir 1 hour at room temperature. Me₂SiCl₂ (1.1 g, 8.5 mmol) was dissolved in 20 mL of THF and added dropwise to the reaction and the contents were allowed to stir at reflux overnight. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo and the remaining residue was loaded onto a silica gel column and eluted with hexane. Yield of product was 2.8g (62%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,5-dimethylphenyl)indenyl]}zirconium
dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(2,5-dimethylphenyl)indene]} (2.8 g, 5.3 mmol) was dissolved in 50 mL of Et₂O. To this solution was added 4.3 mL of n-BuLi (2.5M in hexane) and stirred for 3 hours. The solution was then cooled to -30 °C and ZrCl₄ (1.2 g, 5.3 mmol) was added as a dry powder and the reaction was stirred at room temperature overnight. The solvent was removed in vacuo and the residue was taken up in toluene. The solution was filtered through a celite packed frit to remove LiCl, and concentrated and cooled to -35 °C to induce crystallization. Yellow-orange crystals of the racemic isomer were isolated. Yield: 60 mg (1.6%).

Supported Metallocene Catalyst System 13

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(2,5-dimethylphenyl)indenyl]}zirconium dichloride (0.061 g) was added to the above MAO-toluene solution (6.74 g, 7.3 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two hours and thirty three minutes. The supported catalyst was recovered as a reddish pink, free flowing solid (5.48 g).

EXAMPLE 14

2-Methyl, 4-(2,3,4-trimethylphenyl)-indene

2,3,4-Trimethylbromobenzene (10 g, 50 mmol) and magnesium turnings (2.4 g, 100 mmol) were taken up in 150 mL of Et₂O and stirred at room temperature overnight to form a Grignard solution. In a separate flask, NiCl₂(PPh₃)₂ (1.8 g, 2.8 mmol) and 4-chloro-2-methylindene (8.3 g, 50 mmol) were dissolved in 200 mL of Et₂O. The Grignard solution was added dropwise to this solution and allowed to stir overnight at reflux. After overnight stirring, the

reaction was slowly quenched with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 5.5 g (44 %).

Lithium{1-[2-methyl, 4-(2,3,4-trimethylphenyl)indenide]}

2-Methyl, 4-(2,3,4-trimethylphenyl)-indene (5.5 g, 22 mmol) was dissolved in 200 mL of pentane. To this solution was added 8.9 mL of n-BuLi (2.5M in hexane) and 3 mL of diethyl ether and the reaction was allowed to stir 1 hour at room temperature. A yellow-white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 5.3 g (97%).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,3,4-trimethylphenyl)indene]}

Me₂SiCl₂ (0.76 g, 5.9 mmol) was dissolved in 40 ml of THF. While stirring, lithium{1-[2-methyl, 4-(2,3,4-trimethylphenyl)indenide]} (3.0 g, 12 mmol) was added as a dry powder and the contents were allowed to stir at reflux overnight. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo, and the crude product was isolated. Yield: 3.5 g (100 %).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(2,3,4-trimethylphenyl)indene]} (3.5 g, 5.9 mmol) was dissolved in 50 mL of Et₂O. To this solution was added 9.4 mL of n-BuLi (2.5M in hexane) and stirred for 1 hour. The solution was then cooled to -30 °C and ZrCl₄ (1.4 g, 5.9 mmol) was added as a dry powder and the reaction was stirred at room temperature overnight. The solvent was removed in vacuo and the residue was taken up in toluene. The solution was filtered through a celite packed frit to remove LiCl, concentrated and cooled to -35 °C to induce

crystallization. Yellow-orange crystals of the racemic isomer were isolated. Yield: 350 mg (8.0%).

Supported Metallocene Catalyst System 14

5 In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium dichloride (0.063 g) was added to the above MAO-toluene solution (6.74 g, 7.2 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g,
10 Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two hours and twenty minutes. The supported catalyst was recovered as an orange, free flowing solid (5.29 g).

EXAMPLE 15

2-Methyl, 4-(2,4,5-trimethylphenyl)-indene

2,4,5-Trimethylbromobenzene (10 g, 50 mmol) and magnesium (2.4 g, 100 mmol) were combined in 200 mL of diethyl ether and stirred at room temperature overnight to form a Grignard solution. 4-Chloro-2-methylindene (8.3 g, 50 mmol)
20 and $\text{NiCl}_2(\text{PPh}_3)_2$ (1.8g, 2.8 mmol) were dissolved in 150 mL of Et_2O . To this was added the Grignard solution and the reaction was stirred overnight at room temperature. After overnight stirring, the reaction was slowly quenched with H_2O to neutralize unreacted Grignard. The solution was subsequently treated with 100
25 mL of 10% $\text{HCl}(\text{aq})$, and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 6.0 g (48%).

Lithium{1-[2-methyl, 4-(2,4,5-trimethylphenyl)indenide]}

30 2-Methyl, 4-(2,4,5-trimethylphenyl)-indene (6.0 g, 24 mmol) was dissolved in 80 mL of pentane. To this solution was added 9.7 mL of n-BuLi

(2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 5.5 g (92 %).

5 Dimethylsilanediylbis{1-[2-methyl, 4-(2,4,5-trimethylphenyl)indene]}

Me₂SiCl₂ (0.76 g, 5.9 mmol) was dissolved in 80 mL of THF. While stirring, lithium{1-[2-methyl, 4-(2,4,5-trimethylphenyl)indenide]} (3.0 g, 12 mmol) was added as a dry powder and the contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken
10 up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid (2.9 g, 88 %).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,4,5-trimethylphenyl)indenyl]}zirconium
dichloride

15 Dimethylsilanediylbis{1-[2-methyl, 4-(2,4,5-trimethylphenyl)indene]} (2.9 g, 5.2 mmol) was dissolved in 60 mL of Et₂O. While stirring, 4.1 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 2 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (1.2 g, 5.2 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then
20 removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. 0.52 g (14%) of pure racemic compound was obtained.

25 Supported Metallocene Catalyst System 15

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(2,4,5-trimethylphenyl)indenyl]}zirconium dichloride (0.063 g) was added to the above MAO-toluene solution (6.74 g, 7.3 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with
30 toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator

until the liquid evaporated and then the solid was further dried a total of about two hours and thirty minutes. The supported catalyst was recovered as an orangish, free flowing solid (5.54 g).

5

EXAMPLE 16

2-Methyl, 4-(2,3,5,6-tetramethylphenyl)-indene

2,3,5,6-Tetramethylbromobenzene (10 g, 47 mmol) and magnesium (2.4 g, 100 mmol) were combined in 200 mL of diethyl ether and stirred at room temperature overnight to form a Grignard solution. 4-Chloro-2-methylindene (7.7 g, 47 mmol) and $\text{NiCl}_2(\text{PPh}_3)_2$ (1.8g, 2.8 mmol) were dissolved in 150 mL of Et_2O . To this was added the Grignard solution and the reaction was stirred overnight at room temperature. After overnight stirring, the reaction was slowly quenched with H_2O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% $\text{HCl}(\text{aq})$, and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 8.4 g (68%).

20

Lithium{1-[2-methyl, 4-(2,3,5,6-tetramethylphenyl)indenide]}

2-Methyl, 4-(2,3,5,6-tetramethylphenyl)-indene (8.4 g, 32 mmol) was dissolved in 80 mL of pentane. To this solution was added 13 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 8.0 g (95 %).

25

Dimethylsilanediylbis{1-[2-methyl, 4-(2,3,5,6-tetramethylphenyl)indene]}

Me_2SiCl_2 (0.72 g, 5.5 mmol) was dissolved in 80 mL of THF. While stirring, lithium{1-[2-methyl, 4-(2,3,5,6-tetramethylphenyl)indenide]} (3.0 g, 11 mmol) was added as a dry powder and the contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken

30

up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid (2.6 g, 81 %).

Dimethylsilanediylbis{1-[2-methyl, 4-(2,3,5,6-tetramethylphenyl)indenyl]}
zirconium dichloride

Dimethylsilanediylbis{1-[2-methyl, 4-(2,3,5,6-tetramethylphenyl)indene]} (2.6 g, 4.4 mmol) was dissolved in 60 mL of Et₂O. While stirring, 3.8 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 2 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (1.0 g, 4.4 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. 0.71 g (22%) of pure racemic compound was obtained.

Supported Metallocene Catalyst System 16

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-methyl, 4-(2,3,5,6-tetramethylphenyl)indenyl]}zirconium dichloride (0.66 g) was added to the above MAO-toluene solution (6.74 g, 7.3 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two hours and twenty minutes. The supported catalyst was recovered as a reddish pink, free flowing solid (5.77 g).

EXAMPLE 17

2-Isopropyl, 4-(3-biphenyl)-indene

Magnesium (3.0 g, 125 mmol) and 3-bromobiphenyl (15 g, 65 mmol) were added together in 100 mL of diethyl ether and allowed to stir overnight at reflux to form a Grignard solution. 4-Chloro-2-isopropylindene (12.4 g, 65 mmol) and

NiCl₂(PPh₃)₂ (1.5 g, 2.3 mmol) were dissolved in 150 mL of Et₂O. The Grignard solution formed was added and the reaction was stirred overnight at reflux. After overnight stirring, the reaction was slowly quenched with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 8.9 g (45%).

Lithium{1-[2-isopropyl, 4-(3-biphenyl)indenide]}

2-Isopropyl, 4-(3-biphenyl)-indene (8.9 g, 29 mmol) was dissolved in 150 mL of pentane. To this solution was added 11.5 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 7.5 g (84%).

Dimethylsilanediylbis{1-[2-isopropyl, 4-(3-biphenyl)indene]}

Me₂SiCl₂ (0.62 g, 4.8 mmol) was dissolved in 60 mL of diethyl ether. While stirring, lithium{1-[2-isopropyl, 4-(3-biphenyl)indenide]} (3.0 g, 9.5 mmol) was added as a dry powder and a few drops of THF was added to catalyze the reaction. The contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid. Yield: 3.2g (100%).

Dimethylsilanediylbis{1-[2-isopropyl, 4-(3-biphenyl)indenyl]}zirconium
dichloride

Dimethylsilanediylbis{1-[2-isopropyl, 4-(3-biphenyl)indene]} (3.2 g, 4.7 mmol) was dissolved in 50 mL of Et₂O. While stirring, 3.8 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 0.5 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (1.1 g, 4.7 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then

removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. 1.2 g (30%) of pure racemic isomer was isolated.

5

Supported Metallocene Catalyst System 17

In a 100 mL round bottom flask dimethylsilanediybis{1-[2-isopropyl, 4-(3-biphenyl)indenyl]}zirconium dichloride (0.070 g) was added to the above MAO-toluene solution (6.74 g, 7.3 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two hours and twenty seven minutes. The supported catalyst was recovered as a light purple, free flowing solid (5.46 g).

10

15

EXAMPLE 18

2-Isopropyl, 4-(2-methylphenyl)-indene

4-Chloro-2-isopropylindene (9.8 g, 51 mmol) and $\text{NiCl}_2(\text{PPh}_3)_2$ (1.8g, 2.8 mmol) were dissolved in 150 mL of Et_2O . 2-Methylphenylmagnesium bromide (51 mmol) as a Et_2O solution was added to the solution and the reaction was stirred overnight at room temperature. After overnight stirring, the reaction was slowly quenched with H_2O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% $\text{HCl}(\text{aq})$, and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 6.6 g (52%).

20

25

30

Lithium{1-[2-isopropyl, 4-(2-methylphenyl)indenide]}

2-Isopropyl, 4-(2-methylphenyl)-indene (6.6 g, 26.5 mmol) was dissolved in 80 mL of pentane. To this solution was added 10.6 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 5.8 g (88%).

Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indene]}

Me₂SiCl₂ (0.88 g, 6.8 mmol) was dissolved in 60 mL of THF. While stirring, lithium{1-[2-isopropyl, 4-(2-methylphenyl)indenide]} (3.5 g, 13.7 mmol) was added as a dry powder and the contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid (3.0 g).

Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride

Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indene]} (3.0 g, 5.4 mmol) was dissolved in 60 mL of Et₂O. While stirring, 4.5 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 2 hours. After this time, the solution was cooled to -35 °C and ZrCl₄ (1.25 g, 5.4 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. 0.26 g (6.7%) of pure racemic compound was obtained.

Supported Metallocene Catalyst System 18

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride (0.064 g) was added to the above MAO-toluene solution (6.74 g, 7.15 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene

(14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about two hours and seventeen minutes. The supported catalyst was recovered as a pink-purple, free flowing solid (5.36 g).

EXAMPLE 19

2-Isopropyl, 4-(2,3-dimethylphenyl)-indene

4-Chloro-2-isopropylindene (10.4 g, 54 mmol) and $\text{NiCl}_2(\text{PPh}_3)_2$ (1.5 g, 2.3 mmol) were dissolved in 80 mL of Et_2O . 2,3-Dimethylphenylmagnesium bromide (54 mmol) as a Et_2O solution was added to the solution and the reaction was stirred overnight at room temperature. After overnight stirring, the reaction was slowly quenched with H_2O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq) , and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield: 5.3 g (37%).

Lithium{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenide]}

2-Isopropyl, 4-(2,3-dimethylphenyl)-indene (5.3 g, 20 mmol) was dissolved in 80 mL of pentane. To this solution was added 8.1 mL of $n\text{-BuLi}$ (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 4.8 g (90%).

Dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indene]}

Me_2SiCl_2 (1.2 g, 8.9 mmol) was dissolved in 80 mL of diethyl ether. While stirring, lithium{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenide]} (4.8 g, 18 mmol) was added as a dry powder and a few drops of THF were added to catalyze the reaction. The contents were allowed to stir overnight at room

temperature. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid (5.2 g).

5 Dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium dichloride

Dimethylsilanediylbis{1-[2-isopropyl,4-(2,3-dimethylphenyl)indene]} (5.2 g, 8.9 mmol) was dissolved in 60 mL of Et₂O. While stirring, 7.2 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 2 hours. 10 After this time, the solution was cooled to -35°C and ZrCl₄ (2.1 g, 8.9 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated and chilled to -35 °C to induce crystallization. 0.23 g (3.5%) of pure racemic 15 compound was obtained.

Supported Metallocene Catalyst System 19

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium dichloride (0.066 g) was added to the 20 above MAO-toluene solution (6.74 g, 7.2 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator 25 until the liquid evaporated and then the solid was further dried a total of about two hours and twenty eight minutes. The supported catalyst was recovered as a red-purple, free flowing solid (5.81 g).

EXAMPLE 20

30 **Supported Metallocene Catalyst System 20**

In a 10-ml vial 2.71 g (0.535 mmol) of an 11.05 wt% solution of tris-(perfluorophenyl)borane in toluene was massed. 0.10 g (0.615 mmol) of N,N-

dimethylaniline (Aldrich, 98+%) was added followed by 5.0 g of toluene. A pink solution resulted. This solution was pipetted into a 250 ml round bottom flask containing 5.0 g of silica (Grace Davison, calcined at 500°C with 3-wt% (NH₄)₂SiF₆) and a magnetic stir bar. 10 g of toluene was used to rinse the vial,
5 pipette, and the sides of the flask. The flask was heated to 50 °C in an oil bath. The mixture was stirred for 38 minutes. 0.057 g (0.065 mmol) of dimethylsilanediylbis{1-[2-isopropyl,4-(2-biphenyl)indenyl]}zirconium dimethyl was added to the flask as a solid to produce a brown slurry. Stirring was continued for 35 minutes at 50 °C. After this time, the stirring and heating were
10 discontinued. The solvent was stripped in vacuo to give 5.25 g. Composition by mass balance: Zirconium: 0.012 mmol/g catalyst, Boron: 0.12 mmol/g catalyst.

EXAMPLE 21

Supported Metallocene Catalyst System 21

15 In a 100 mL round bottom flask dimethylsilanediyl{1-[2-isopropyl-4-(2-biphenyl)indenyl]}zirconium dichloride (0.074 g) was added to the above MAO-toluene solution (6.74 g, 7.2 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison
20 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about 2 hours and thirty one minutes. The supported catalyst was recovered as a light reddish purple, free flowing solid (5.28 g).

EXAMPLE 22

2-Isopropyl, 4-(2-biphenyl)-indene

25 Magnesium (2.0 g, 83 mmol) and 2-bromobiphenyl (10 g, 43 mmol) were added together in 100 mL of diethyl ether and allowed to stir overnight at reflux to
30 form a Grignard solution. 4-Chloro-2-isopropylindene (7.5 g, 43.4 mmol) and NiCl₂(PPh₃)₂ (1.5 g, 2.3 mmol) were dissolved in 150 mL of Et₂O. The Grignard solution was added and the reaction was stirred overnight at reflux. After

overnight stirring, the reaction was slowly quenched with H₂O to neutralize unreacted Grignard. The solution was subsequently treated with 100 mL of 10% HCl(aq), and neutralized with saturated sodium bicarbonate aqueous solution. The organic layer was dried with magnesium sulfate and the solvent was removed by rotary evaporation. The remaining residue was loaded onto a silica gel column and eluted with hexane. Yield was 8.1 g (61%).

Lithium{1-[2-isopropyl, 4-(2-biphenyl)indenide]}

2-Isopropyl, 4-(2-biphenyl)-indene (4.0 g, 13 mmol) was dissolved in 100 mL of pentane. To this solution was added 5.2 mL of n-BuLi (2.5M in hexane) and the reaction was allowed to stir 4 hours at room temperature. A white solid precipitated from solution and was collected by frit filtration and washed with additional pentane. Yield: 2.7 g (67%).

Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indene]}

Me₂SiCl₂ (0.55 g, 4.3 mmol) was dissolved in 60 mL of diethyl ether. While stirring, lithium{1-[2-isopropyl, 4-(2-biphenyl)indenide]} (2.7 g, 8.6 mmol) was added as a dry powder and a few drops of THF were added to catalyze the reaction. The contents were allowed to stir overnight at room temperature. The solvent was removed in vacuo and the residue was taken up in pentane and filtered to remove LiCl salts. The pentane was removed in vacuo to yield a flaky white solid. Yield: 2.1g (72%).

Dimethylsilanediylbis{1-[2-isopropyl, 4-(2biphenyl)indenyl]}zirconium
dichloride

Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indene]} (2.1 g, 3.1 mmol) was dissolved in 60 mL of Et₂O. While stirring, 2.5 mL of n-BuLi (2.5M in hexane) was added and allowed to stir at room temperature for 0.5 hours. After this time, the solution was cooled to -35°C and ZrCl₄ (0.73 g, 3.1 mmol) was added and allowed to stir at room temperature for 3 hours. The solvent was then removed in vacuo and the residue was taken up in a mixture of methylene chloride and pentane and filtered to remove LiCl salts. The filtrate was then concentrated

and chilled to -35 °C to induce crystallization. 0.29 g (11%) of pure racemic isomer was isolated.

Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}zirconium
dimethyl

Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}zirconium dichloride (0.4 g, 490 µmol) was dissolved in 50 mL of toluene. To this solution was added 1.8 mL of MeMgBr (3.0M in Et₂O) and the reaction was stirred at 90°C for 5 hours. After this time, the reaction was cooled to room temperature and 10 mL each of SiCl₄ and 1,4-dioxane was added. The solution was filtered through celite and the solvent was removed in vacuo. The resulting solids were washed with pentane. Yield: 0.18 g (44%).

Supported Metallocene Catalyst System 22

In a 100 mL round bottom flask dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}zirconium dimethyl (0.070 g) was added to the above MAO-toluene solution (6.74 g, 7.2 mL) and stirred twenty minutes. The resultant mixture was filtered through a medium glass frit funnel and washed with toluene (14 mL). To the combined filtrates was added dehydrated silica (4.0 g, Davison 948 Regular, 600°C dehydration). This slurry was stirred for twenty minutes, then dried at 40 °C for two minutes under vacuum on a rotary evaporator until the liquid evaporated and then the solid was further dried a total of about 2 hours and thirty four minutes. The supported catalyst was recovered as a light purple, free flowing solid (5.56 g).

POLYMERIZATIONS

Isotactic Polypropylene Homopolymer

5 The polymerization procedure for producing homopolymers with the above supported metallocene catalyst systems was as follows. In a clean, dry two liter autoclave which had been flushed with propylene vapor, TEAL (triethyl aluminum) scavenger (0.3 mL, 1.5M) was added. Hydrogen gas was added at this point. The reactor was closed and filled with 800 mL of liquid propylene. After
10 heating the reactor to 70 °C , the catalyst was added by washing in with propylene (200 mL). After the indicated time, typically one hour, the reactor was cooled, and the excess propylene vented. The polymer was removed and dried.

Isotactic Polypropylene Random Copolymer (RCP)

15 The polymerization procedure for producing ethylene random copolymers (RCP) with the above supported metallocene catalyst systems was as follows. In a clean, dry two liter autoclave which had been flushed with propylene vapor, TEAL scavenger (0.3 mL, 1.5M) was added. Hydrogen gas was added at this
20 point, if used. The reactor was closed and filled with 800 mL of liquid propylene. After heating the reactor to 60 °C , an overpressure of ethylene, as indicated by the “delta kPa”, was slowly added while maintaining 60°C. The ethylene inlet was closed while the catalyst was added by washing in with propylene (200 mL). Immediately after addition the ethylene inlet was reopened and the desired
25 overpressure of ethylene was maintained. After the indicated time, typically one hour, the reactor was cooled, and the excess propylene vented. The polymer was removed and dried.

Impact Copolymers (ICP)

The polymerization procedure for producing ICP with the above supported metallocene catalyst systems was as follows. In a clean, dry two liter autoclave which had been flushed with propylene vapor, TEAL scavenger (0.3 mL, 1.5M) was added. Hydrogen gas was added at this point. The reactor was closed and filled with 800 mL liquid propylene. After heating the reactor to 70 °C, the catalyst was added by washing in with propylene (200 mL). After the indicated time, typically one hour, the reactor was vented to about 170 psig (1172 kPa) pressure and then an ethylene/propylene gas mixture was passed through the reactor at the rates indicated while maintaining 200 psig (1379 kPa). At the end of the gas phase stage, typically 90 to 150 minutes, the reactor was vented and cooled under N₂. The granular ICP polymer was removed and dried.

POLYMER ANALYSIS

Results are shown in Tables 1-22 (A and B) below. The numbering of the Tables corresponds to the numbering of the above Examples (Supported
5 Metalocene Catalyst Systems). Molecular weight determinations were made by gel permeation chromatography (GPC) according to the following technique. Molecular weights and molecular weight distributions were measured using a Waters 150°C gel permeation chromatograph equipped with Shodex (Showa Denko) AT-80 M/S columns and a differential refractive index (DRI) detector
10 operating at 145°C with 1,2,4-trichlorobenzene as the mobile phase at a 1.0 mL/min. flow rate. The sample injection volume was 300 microliters. The columns were calibrated using narrow polystyrene standards to generate a universal calibration curve. The polypropylene calibration curve was established using $k = 8.33 \times 10^{-5}$ and $a = 0.800$ as the Mark-Houwink coefficients. The
15 numerical analyses were performed using Waters "Millennium" software.

DSC melting points were determined on commercial DSC instruments and were reported as the second melting point. The polymer sample was heated to 230.0°C for ten minutes and then cooled from 230°C to 50°C at 10°C/minute.
20 The sample was held at 50°C for five minutes. The second melt was then recorded as the sample was heated from 50°C to 200°C at a rate of 10°C/minute. The peak temperature was recorded as the second melting point.

The results summarized in Table 21C were obtained by following the
25 procedures described in J.C. Randall, Polymer Sequence Determination: Carbon-13 NMR Method, Academic Press New York 1978, supra.

ICP POLYMER EXTRACTION METHOD

30 The ICP polymer was dissolved in hot xylene and then allowed to cool overnight. After filtration the insolubles were dried. The xylene soluble portion

was evaporated and the soluble material recovered. The IV (intrinsic viscosity) of the recovered soluble material was measured in decalin at 135°C by using known methods and instruments such as a Schott A VSPRO Viscosity Automatic Sampler.

5 At very high ICP MFR this method can extract some low molecular weight isotactic PP and thus lower the observed IV.

ICP POLYMER FRACTIONATION METHOD

10

The ICP samples were sent to Polyhedron Laboratories, Inc. to be fractionated and analyzed by GPC. A general description of the procedure is found in J. C. Randall, J. Poly. Sci.: Part A Polymer Chemistry, Vol. 36, 1527-1542 (1998), supra.

- 220 -

TABLE 1A
Dimethylsilanediylbis{1-[2-methyl, 4-phenylindenyl]}zirconium dichloride

RUN #	TEMP. (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
1	60	67	274.7	4.10	0	0	60	-
2	60	45	71.7	1.59	0	0	60	-
3	60	40	134.1	3.35	68.9	0	60	-
4	60	42	221.5	5.27	137.9	0	60	-
5	60	30	121.3	4.04	379.2	0	60	-
6	60	30	130.2	4.34	482.6	0	60	-
7	60	30	101.8	3.39	137.9	0	60	-
8	70	45	293.5	6.52	-	77.5	60	-
9	70	31	198.9	6.42	-	77.5	60	-
10	70	30	291.9	9.73	-	77.5	60/150	4.0/1.0
11	70	30	231.3	7.71	-	77.5	60/90	4.0/1.0
12	70	30	224.8	7.49	-	77.5	60/90	4.1/0.9
13	70	30	209.9	7.00	-	77.5	60/90	3.6/1.4
14	70	30	208.2	6.94	-	77.5	60/90	4.0/1.0

TABLE 1B
Dimethylsilanediylbis{1-[2-methyl, 4-phenylindenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total Rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV of Copolymer (dl/g)
1	-	-	-	0.16	149.2	600.0	2.00	-
2	-	-	-	0.54	148.2	664.9	1.92	-
3	0.67	-	-	0.84	142.0	349.0	2.09	-
4	1.28	-	-	2.57	138.4	280.0	1.95	-
5	3.77	-	-	6.48	121.4	255.0	2.04	-
6	4.43	-	-	5.95	116.0	301.0	2.30	-
7	1.44	-	-	2.05	137.5	330.4	2.23	-
8	-	-	-	99.6	150.3	120.6	3.01	-
9	-	-	-	58.95	150.9	135.7	3.15	-
10	13.23	49.20	26.89	178.5	151.2	81.2	3.37	0.7520
11	7.58	47.37	16.00	134.05	150.6	98.4	3.25	0.687
12	7.82	50.04	15.63	127.16	150.0	100.4	3.11	0.708
13	5.3	38.96	13.60	201.9	150.43	91.2	3.28	0.779
14	0.47	64.32	0.73	97.1	150.8	116.8	3.42	Not submitted

- 222 -

TABLE 2A
Dimethylsilanediylbis{1-[2-methyl, 4-(3-methylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
15	60	45	106.7	2.37	0	0	60	-
16	60	46	232.5	5.05	68.9	0	60	-
17	60	45	285.1	6.34	137.9	0	60	-
18	60	21	132.0	6.29	241.3	0	60	-
19	70	20	220.1	11.01	-	77.5	60/90	4.0/1.0
20	70	22	197.9	9.00	-	54.3	60/90	4.0/1.0
21	70	46	242.0	5.26	-	54.3	30	-
22	70	21	146.5	6.98	-	54.3	60	-
23	70	20	145.3	7.27	-	108.5	60	-
24	70	20	117.4	5.87	-	77.5	60	-
25	70	20	158.9	7.95	-	108.5	60/90	4.0/1.0

TABLE 2B
Dimethylsilanediylbis{1-[2-methyl, 4-(3-methylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW (X 10 ⁻³)	MWD	IV of Copolymer (dl/g)
15	-	-	-	0.08	149.43	797.1	2.05	-
16	0.15	-	-	0.87	144.10	425.0	1.82	-
17	1.1	-	-	2.48	139.97	318.2	1.82	-
18	2.0	-	-	4.50	134.17	280.6	1.93	-
19	7.431	50.60	14.69	15.68	151.1	195.7	3.37	0.684
20	9.699	49.32	19.67	6.27	150.7	302.9	3.82	0.772
21	-	-	-	2.48	151.03	334.5	2.26	-
22	-	-	-	1.61	150.97	336.3	2.22	-
23	-	-	-	91.78	151.90	125.0	3.24	-
24	-	-	-	39.82	151.63	154.3	2.76	-
25	6.454	51.06	12.64	Not submitted	151.3	83.6	3.11	0.832

TABLE 3A
Dimethylsilanediylbis{1-[2-methyl, 4-(3,5-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP. (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
26	60	45	72.7	1.6	0	0	60	-
27	60	45	111.9	2.5	34.5	0	60	-
28	60	47	155.6	3.3	68.9	0	60	-
29	60	46	204.9	4.5	137.9	0	60	-
30	60	45	244.5	5.4	241.3	0	60	-
31	70	30	251.2	8.4	-	54.3	60/90	4.0/1.0
32	70	30	236.8	7.9	-	54.3	60/90	3.6/1.4
33	70	32	259.5	8.7	-	54.3	60/90	4.2/0.8
34	70	33	249.4	7.6	-	54.3	60/90	4.4/0.6
35	70	33	186.8	5.7	-	54.3	60	-

TABLE 3B
Dimethylsilanediylbis{1-[2-methyl, 4-(3,5-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW (X 10 ⁻³)	MWD	IV Of Copolymer (dl/g)
26	-	-	-	0.0245	150.9	937.7	2.10	-
27	-	-	-	0.17	148.3	671.3	2.15	-
28	0.18	-	-	0.59	145.03	463.6	2.01	-
29	1.1	-	-	2.68	140.9	303.8	1.89	-
30	1.8	-	-	3.98	135.43	255.7	1.74	-
31	8.11	49.7	16.3	4.54	152.57	281.1	3.51	0.866
32	5.34	40.32	13.2	6.25	151.97	284.5	3.57	0.861
33	9.98	58.47	17.1	7.07	152.43	220.4	3.00	1.420
34	14.42	61.66	23.4	19.43	152.1	179.4	2.57	1.091
35	-	-	-	1.79	151.30	327.9	1.98	-

- 226 -

TABLE 4A
DimethylsilanediyIbis{1-[2-methyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
36	60	47	33.0	0.70	0	0	60	-
37	60	45	118.7	2.64	68.9	0	60	-
38	60	45	197.7	4.39	137.9	0	60	-
39	60	47	340.7	7.25	241.3	0	60	-
40	70	33	273.4	8.28	-	77.5	60/90	4.0/1.0
41	70	20	222.9	11.15	-	77.5	60/90	4.0/1.0
42	70	22	228.0	10.36	-	77.5	60/90	4.1/0.9
43	70	20	222.3	11.12	-	77.5	60/90	3.6/1.4
44	70	20	175.4	8.77	-	54.3	60/90	4.0/1.0
45	70	20	161.0	8.05	-	54.3	60/90	4.1/0.9
46	70	20	174.0	8.70	-	54.3	60/90	3.6/1.4
47	70	21	189.6	9.03	-	54.3	60/120	4.0/1.0
48	70	20	132.1	6.61	-	54.3	60	-
49	70	20	159.1	7.96	-	77.5	60.0	-

TABLE 4B
Dimethylsilanediylbis{1-[2-methyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV of Copolymer (dl/g)
36	-	-	-	0.09	146.5	912.2	2.17	-
37	0.67	-	-	0.52	136.63	499.0	2.33	-
38	1.24	-	-	0.61	132.57	449.8	2.22	-
39	2.1	-	-	0.69	126.77	499.8	2.01	-
40	-	-	-	111.98	144.63	115.1	2.41	-
41	6.951	48.87	14.22	140.01	145.7	99.7	2.59	1.429
42	7.88	52.43	15.03	133.9	145.37	100.9	2.74	1.287
43	5.576	38.33	14.55	83.2	144.90	111.8	2.34	1.046
44	7.353	48.96	15.02	29.14	145.10	143.3	2.50	1.446
45	8.809	51.90	16.97	20.42	145.17	154.3	2.42	1.448
46	6.013	35.55	16.91	35.55	144.97	151.8	2.32	1.355
47	10.84	47.31	22.91	20.36	145.63	152.6	2.39	1.648
48	-	-	-	26.76	146.17	179.9	2.64	-
49	-	-	-	95.55	145.97	124.3	2.96	-

TABLE 5A
Dimethylsilanediyldibis{1-[2-methyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
50	60	48	19.5	0.41	0	0	60	-
51	60	46	28.2	0.61	34.5	0	60	-
52	60	45	36.0	0.80	68.9	0	60	-
53	60	45	44.9	1.00	137.9	0	60	-
54	60	45	69.6	1.55	241.3	0	60	-
55	70	152	256.1	1.68	-	54.3	35/90	4.0/1.0
56	70	75	228.9	3.05	-	54.3	60	-
57	70	74	337.4	4.56	-	54.3	60/90	4.0/1.0
58	70	33	134.7	4.08	-	54.3	60/90	4.0/1.0
59	70	33	118.8	3.60	-	54.3	60/90	3.6/1.4
60	70	31	123.0	3.97	-	54.3	60/90	4.4/0.6
61	70	31	130.8	4.22	-	54.3	60/90	4.2/0.8
62	70	31	85.9	2.77	-	54.3	60	-

- 229 -

TABLE 5B
Dimethylsilanediylbis{1-[2-methyl, 4-(2-ethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV of Copolymer (dl/g)
50	-	-	-	0.038	147.97	786.3	2.14	-
51	Trace	-	-	0.088	144.3	670.7	2.60	-
52	0.83	-	-	0.092	139.63	635.7	2.58	-
53	1.7	-	-	0.16	134.17	621.5	2.21	-
54	2.6	-	-	0.2	127.5	642.0	2.06	-
55	-	-	-	15.17	147.1	232.3	2.56	-
56	-	-	-	15.72	147.10	214.4	2.42	-
57	12.68, 12.74	50.79, 50.59	24.97, 25.18	18.43	147.77	160.7	2.49	1.889
58	7.107	48.48	14.66	97.17	145.7	103.1	2.64	1.788
59	6.874	38.31	17.94	31.95	145.83	136.9	2.50	1.746
60	12.59	60.64	20.76	48.37	145.63	130.2	2.57	2.15
61	9.74	52.29	18.63	52.52	146.03	133.8	2.42	2.02
62	-	-	-	34.83	146.03	172.6	2.43	-

TABLE 6A
Dimethylsilanediylbis{1-[2-methyl, 4-(2-isopropylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
63	60	46	15.1	0.33	0	0	60	-
64	70	21	63.3	3.01	-	54.3	60	-
65	70	60	243.1	4.05	-	54.3	60/90	4.0/1.0
66	70	61	159.5	2.61	-	54.3	60	-
67	70	61	221.4	3.63	-	54.3	60/90	3.6/1.4
68	70	61	199.8	3.28	-	54.3	60/90	4.2/0.8

TABLE 6B
Dimethylsilanediylbis{1-[2-methyl, 4-(2-isopropylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW (X10-3)	MWD	IV of Copolymer (dl/g)
63	-	-	-	0.099	148.23	690.1	2.38	-
64	-	-	-	125.8	144.70	115.0	2.59	-
65	14.64	51.63	28.36	9.8	145.03	167.1	2.83	2.34
66	-	-	-	40.59	144.77	146.2	3.04	-
67	9.487	41.48	22.87	24.72	144.23	158.1	2.60	1.94
68	13.26	54.58	24.29	15.4	145.3	167.6	2.77	2.46

TABLE 7A
Dimethylsilanediylbis{1-[2-methyl, 4-(2-biphenyl)indenyl]}zirconium dichloride

RUN #	Temp (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
69	60	48	102.9	2.14	0	0	60	-
70	70	23	290.6	12.63	-	54.3	60/90	4.0/1.0
71	70	20	216.4	10.82	-	54.3	60	-
72	70	20	271.1	13.56	-	54.3	60/120	4.0/1.0
73	70	20	141.5	7.08	-	54.3	60/90	4.2/0.8
74	70	21	260.4	12.4	-	54.3	60/90	3.6/1.4
75	70	20	231.2	11.56	-	54.3	60/90	4.2/0.8

TABLE 7B
Dimethylsilanediylbis{1-[2-methyl, 4-(2-biphenylyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW (X10-3)	MWD	IV of Copolymer (dl/g)
69	-	-	-	0.052	148.63	772.9	1.92	-
70	6.066	46.64	13.01	19.18	150.30	156.5	2.35	1.338
71	-	-	-	12.93	150.70, minor 136.9	194.7	2.00	-
72	7.476	45.74	16.34	14.69	149.83	167.4	2.13	1.30
73	6.001	53.32	11.25	62.35	149.9	126.9	1.95	1.06
74	4.605	35.36	13.02	13.98	151.7	186.8	2.46	1.06
75	7.778	53.54	14.53	13.05	150.77	166.0	2.23	1.36

TABLE 8A
Dimethylsilanediylbis{1-[2-methyl, 4-(4-biphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
76	60	48	69.6	1.45	0	0	60	-
77	70	22	110.2	5.01	-	54.3	60	-
78	70	21	120.9	5.76	-	54.3	60/90	4.0/1.0
79	70	20	131.7	6.07	-	54.3	60/120	4.0/1.0
80	70	20	121.3	6.07	-	54.3	60/90	4.2/0.8
81	70	23	135.0	5.87	-	54.3	60/90	3.6/1.4

TABLE 8B
Dimethylsilanediylbis{1-[2-methyl, 4-(4-biphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW (X10-3)	MWD	IV Of Copolymer (dl/g)
76	-	-	-	0.046	145.57	662.3	2.06	-
77	-	-	-	4.36	147.3	244.6	2.23	-
78	4.18	56.56	7.39	13.17	148.5	185.0	3.30	0.79
79	8.58	52.12	16.46	29.02	148.43	191.2	3.69	0.62
80	10.31	56.37	18.29	23.12	149.9	177.2	2.99	0.81
81	5.535	42.06	13.16	18.13	148.3	218.0	3.87	0.69

TABLE 9A
Dimethylsilanediylbis{1-[2-methyl, 4-(4-tert-butylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	H ₂ (mmole)	Time split (min.)
82	60	48	9.9	0.21	0	60
83	70	30	27.2	0.91	54.3	60

TABLE 9B
Dimethylsilanediylbis{1-[2-methyl, 4-(4-tert-butylphenyl)indenyl]}zirconium dichloride

RUN #	Final MFR (g/10 min.)	Melting Point (°C)	MW (X10 ⁻³)	MWD
82	0.0725	150.9	979.3	2.68
83	33.04	152.9	159.7	3.03

TABLE 10A
Dimethylsilanediylbis{1-[2-methyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
84	60	45	26.2	0.58	0	0	60	-
85	70	20	67.8	3.39	-	54.3	60/90	4.0/1.0
86	70	60	262.2	4.37	-	54.3	60/90	4.0/1.0
87	70	60	174.8	2.91	-	54.3	60	-
88	70	60	212.5	3.54	-	54.3	60/90	4.1/0.9
89	70	60	255.1	4.25	-	54.3	60/90	3.6/1.4
90	70	60	264.0	4.40	-	54.3	60/120	4.0/1.0
91	70	61	205.9	3.38	-	62.0	60/90	4.0/1.0
92	70	62	257.8	4.16	-	69.8	60/90	4.0/1.0
93	70	61	199.5	3.27	-	77.5	60/90	4.0/1.0
94	70	61	213.4	3.50	-	93	60/90	4.0/1.0

TABLE 10B
Dimethylsilanediylbis{1-[2-methyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW (X 10 ⁻³)	MWD	IV Of Copolymer (dl/g)
84	-	-	-	0.023	149.3	963.8	2.32	-
85	9.417	46.86	20.10	28.72	148.37	139.0	3.39	1.92
86	14.21	50.48	28.15	2.31	149.63	253.4	2.58	2.21
87	-	-	-	5.02	150.37	264.0	2.69	-
					minor 137.46			
88	14.65, 14.64	52.46, 52.37	27.93, 27.95	2.54	150.37	263.8	2.75	2.232
89	12.99, 13.1	38.1, 37.65	34.09, 34.79	4.56	151.17	218.0	2.72	2.487
90	22.8, 22.45	53.16, 52.62	42.89, 42.66	3.64	150.3	205.8	3.30	2.268
91	15.81	51.87	30.48	9.77	149.57	165.6	2.54	1.968
92	20.94	51.96	40.30	5.47	150.37	206.4	3.14	1.558
93	13.24	51.07	25.93	40.22	149.83	131.2	3.58	2.007
94	12.18	45.24	26.92	39.73	149.03	150.3	4.28	2.711

TABLE 11A
Dimethylsilanediylbis{1-[2-methyl, 4-(2,4-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
95	60	47	41.6	0.89	0	0	60	-
96	70	32	322.9	10.09	-	54.3	60/120	4.0/1.0
97	70	20	168.2	8.41	-	54.3	60/90	4.0/1.0
98	70	20	180.1	9.01	-	54.3	60/90	4.1/0.9
99	70	20	177.1	8.86	-	54.3	60/90	3.6/1.4
100	70	20	181.0	9.05	-	54.3	60/120	4.0/1.0
101	70	21	138.2	6.58	-	54.3	60	-

TABLE 11B
Dimethylsilanediylbis{1-[2-methyl, 4-(2,4-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV Of Copolymer (dl/g)
95	-	-	-	0.073	145.63	954.8	2.28	-
96	16.62	52.43	31.70	9.53	144.23	166.3	3.81	1.582
97	8.092, 8.171	48.83, 49.08	16.57, 16.64	24.3	144.23	153.1	2.21	1.047
98	7.83	54.21	14.44	76.69	143.1	117.7	2.36	1.89
99	5.484	39.52	13.88	67.85	144.03	132.6	2.66	1.28
100	9.509	50.14	18.96	41.15	144.3	122.4	2.43	1.46
101	-	-	-	72.39	144.83	132.3	2.25	-

TABLE 12A
Dimethylsilanediylbis{1-[2-methyl, 4-(2,6-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
102	60	46	6.9	0.15	0	0	60	-
103	60	45	95.4	2.12	68.9	0	60	-
104	60	46	110.0	2.39	137.9	0	60	-
105	60	45	99.6	2.21	241.3	0	60	-
106	70	22	37.5	1.70	-	54.3	60	-
107	70	77	87.7	1.14	-	54.3	60	-
108	70	75	128.5	1.71	-	54.3	60/60	4.0/1.0
109	70	150	190.0	1.27	-	46.5	60/60	4.0/1.0
110	70	150	174.4	1.16	-	38.8	60/60	4.0/1.0
111	70	150	153.6	1.02	-	31.0	60/60	4.0/1.0
112	70	151	136.1	-	-	23.3	60/60	4.0/1.0

TABLE 12B
Dimethylsilanediyldibis{1-[2-methyl, 4-(2,6-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV Of Copolymer (dl/g)
102	-	-	-	Not det.	148.1	307.0	3.52	-
103	1.20	-	-	76.15	137.7	123.0	2.34	-
104	2.10	-	-	68.21	133.63	144.2	2.59	-
105	3.70	-	-	66.58	128.43	139.2	2.38	-
106	-	-	-	344.51	148.63	121.1	3.30	-
107	-	-	-	140.44	147.9	120.6	3.53	-
108	5.044	43.14	11.69	596.49	147.3	77.3	5.66	0.678
109	9.546	45.29	21.08	136.53	147.9	102.6	3.63	0.844
110	11.86	44.81	26.47	108.99	148.17	105.2	2.33	0.778
111	12.06	45.83	26.31	103.02	147.03	106.1	3.69	0.834
112	12.89	44.96	28.67	78.06	147.57	114.1	3.12	0.456

TABLE 13A
Dimethylsilanediylbis{1-[2-methyl, 4-(2,5-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
113	60	47	53.2	1.13	0	0	60	-
114	60	49	95.0	1.94	34.5	0	60	-
115	60	47	110.0	2.34	68.9	0	60	-
116	60	46	139.3	3.03	137.9	0	60	-
117	60	47	184.6	3.93	241.3	0	60	-
118	70	22	96.6	4.39	-	54.3	60	-
119	70	30	159.6	5.32	-	54.3	60/90	4.0/1.0
120	70	30	164.1	5.47	-	54.3	60/120	4.0/1.0
121	70	30	129.2	4.31	-	54.3	60	-
122	70	30	169.6	5.65	-	54.3	60/90	3.6/1.4

TABLE 13B
Dimethylsilanediylbis{1-[2-methyl, 4-(2,5-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW (X 10 ⁻³)	MWD	IV Of Copolymer (dl/g)
113	-	-	-	0.0275	149.77	815.9	2.09	-
114	0.1	-	-	0.225	147.23	574.2	2.31	-
115	0.32	-	-	0.51	144.03	460.2	1.90	-
116	1.2	-	-	1.22	139.70	346.0	1.99	-
117	2.0	-	-	4.78	134.83	297.2	2.00	-
118	-	-	-	1.07	151.03	385.5	2.23	-
119	6.99	51.82	13.49	6.98	151.9	248.0	3.50	0.895
120	9.66	50.95	18.84	5.33	152.17	236.8	3.20	1.161
121	-	-	-	2.02	151.37	357.3	2.27	-
122	4.968	42.16	11.78	7.77	152.03	220.0	3.28	0.826

TABLE 14A
Dimethylsilanediylbis{1-[2-methyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
123	60	45	44.8	1.00	0	0	60	-
124	70	21	98.2	4.68	-	54.3	60	-
125	70	20	131.5	6.58	-	54.3	60/90	1.0/4.0
126	70	20	134.3	6.72	-	54.3	60/90	3.6/1.4
127	70	21	109.4	5.21	-	54.3	60/90	4.1/0.9
128	70	21	137.4	6.54	-	54.3	60/120	4.0/1.0

TABLE 14B
Dimethylsilanediylbis{1-[2-methyl, 4-(2,3,4-trimethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV Of Copolymer (dl/g)
123	-	-	-	No flow	148.43	820.1	2.18	-
124	-	-	-	2.28	148.77	306.1	2.41	-
125	10.9	47.12	23.13	1.12	148.70	310.4	2.60	2.08
126	7.221	37.00	19.51	2.04	149.23	273.7	3.21	1.82
127	10.50	51.77	20.28	1.23	149.50	302.4	2.90	1.99
128	16.71	48.63	34.36	0.91	148.97	260.1	2.43	2.63

TABLE 15A
Dimethylsilanediylbis{1-[2-methyl, 4-(2,4,5-trimethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
129	60	47	45.6	0.97	0	0	60	-
130	60	45	106.0	2.36	68.9	0	60	-
131	60	46	134.8	2.93	137.9	0	60	-
132	60	45	266.6	5.92	241.3	0	60	-
133	60	45	62.5	1.39	34.5	0	60	-
134	70	30	195.1	6.50	-	54.3	60/90	4.0/1.0
135	70	30	194.0	6.47	-	54.3	60	-
136	70	30	242.3	8.08	-	54.3	60/90	3.6/1.4
137	70	31	216.0	6.97	-	54.3	60/90	4.2/0.8
138	70	30	231.5	7.72	-	54.3	60/90	4.4/0.6
139	70	31	270.2	8.72	-	54.3	60/120	4.0/1.0

- 248 -

TABLE 15B
Dimethylsilanediylbis{1-[2-methyl, 4-(2,4,5-trimethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV Of Copolymer (dl/g)
129	-	-	-	0.048	148.60	914.8	2.46	-
130	-	-	-	0.37	139.98	625.1	3.14	-
131	-	-	-	0.43	133.78	568.4	2.58	-
132	-	-	-	0.52	129.92	545.2	2.32	-
133	-	-	-	0.165	144.04	672.0	3.05	-
134	9.56	47.94	19.94	2.50	148.3	274.4	2.98	1.93
135	-	-	-	9.68	148.17	232.7	2.80	-
136	6.492	37.9	17.13	4.54	149.77	235.0	2.55	1.676
137	10.69	55.99	19.09	8.04	147.85	203.2	3.06	1.880
138	18.17	62.73	28.97	2.24	147.17	264.9	2.70	2.077
139	10.56	50.91	20.74	15.56	147.30	168.9	3.04	1.825

TABLE 16A
Dimethylsilanediyldis{1-[2-methyl, 4-(2,3,5,6-tetramethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
140	60	46	7.2	0.16	0	0	60	-
141	60	45	82.6	1.84	34.5	0	60	-
142	60	45	166.5	3.70	68.9	0	60	-
143	60	45	185.6	4.12	137.9	0	60	-
144	60	45	257.3	5.72	241.3	0	60	-
145	70	31	97.2	3.14	-	54.3	60/90	4.0/1.0
146	70	151	333.5	2.21	-	54.3	60/79	4.0/1.0
147	70	76	184.4	2.43	-	54.3	60/90	4.0/1.0
148	70	75	123.1	1.64	-	23.3	60/90	4.0/1.0
149	70	152	240.7	1.58	-	23.3	60/60	4.0/1.0
150	70	152	164.2	1.08	-	23.3	60	-
151	70	77	176.6	2.29	-	54.3	60	-
152	70	150	200.2	1.33	-	15.5	60/90	4.0/1.0
153	70	152	202.6	1.33	-	7.8	60/90	4.0/1.0

- 250 -

TABLE 16B
Dimethylsilanediyibis{1-[2-methyl, 4-(2,3,5,6-tetramethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV Of Copolymer (dl/g)
140	-	-	-	-	149.24	181.4	1.85	-
141	-	-	-	66.43	144.10	120.8	2.00	-
142	-	-	-	70.51	139.03	118.4	1.92	-
143	-	-	-	78.03	134.57	119.3	2.13	-
144	-	-	-	63.79	130.23	136.4	1.92	-
145	4.699	47.11	9.97	1612.72	150.03 (155.5)	65.7	2.95	0.807
146	8.684	44.91	19.34	248.26	150.23	102.1	2.70	0.836
147	6.34	45.05	14.07	343.29	149.1	67.6	1.36	0.892
148	12.96	42.65	30.39	81.54	149.03	107.0	2.46	0.996
149	12.44	45.84	27.14	124.68	149.1	93.9	2.63	0.875
150	-	-	-	100.79	151.03	108.1	1.96	-
151	-	-	-	Too fast	149.63	59.6	2.41	-
152	19.18	45.6	42.06	90.68	148.63	106.1	2.96	0.973
153	20.76	44.63	46.52	95.07	148.9	114.4	3.04	0.891

TABLE 17A
Dimethylsilanediybis{1-[2-isopropyl, 4-(3-biphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
154	60	302	16.0	0.05	0	0	60	-
155	70	61	81.8	1.34	-	46.5	60/120	4.0/1.0
156	70	60	74.7	1.25	-	46.5	60/120	4.4/0.6
157	70	60	62.0	1.03	-	46.5	60	-
158	70	62	48.0	0.77	-	31.0	60	-
159	70	60	22.0	0.37	-	15.5	60	-

TABLE 17B
Dimethylsilanediylbis{1-[2-isopropyl, 4-(3-biphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV Of Copolymer (dl/g)
154	-	-	-	15.26	150.37	227.8	2.04	-
155	5.011	41.67	12.03	118.14	151.97	134.6	2.88	1.88
156	9.911	53.91	18.38	52.09	152.77	164.9	3.71	2.95
157	-	-	-	259.61	150.83	104.3	2.38	-
158	-	-	-	116.54	150.97	125.2	2.28	-
159	-	-	-	102.01	151.17	128.0	2.05	-

- 253 -

TABLE 18A
Dimethylsilanediyldibis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
160	60	46	2.7	0.06	0	0	60	-
161	60	300	56.3	0.19	0	0	60	-
162	70	61	158.2	2.59	-	46.5	60/120	4.0/1.0
163	70	60	139.9	2.33	0	46.5	60	-
164	70	61	168.9	2.77	-	46.5	60/120	4.4/0.6
165	70	60	42.3	0.70	0	15.5	60	-
166	70	61	94.7	1.55	0	31.0	60	-
167	70	300	159.8	0.53	0	7.8	60	-
168	70	300	51.4	0.17	0	7.8	21	-
169	70	300	276.2	0.92	-	7.8	64/180	4.0/1.0

TABLE 18B
Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-methylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW (X10 ⁻³)	MWD	IV of Copolymer (dl/g)
160	-	-	-	Not submitted	153.5	178.2	2.13	-
161	-	-	-	30.48	154.83	197.2	2.12	-
162	3.584	43.25	8.29	971.02	152.17	75.6	2.50	1.121
163	-	-	-	1013.8	152.1	70.9	2.27	-
					(157.17 minor)			
164	4.62	57.52	8.03	954.7	151.57	69.2	2.39	2.083
165	-	-	-	142.5	152.91	120.1	2.38	-
166	-	-	-	420.7	152.1	91.7	2.19	-
167	-	-	-	129.85	153.23	127.3	3.62	-
168	-	-	-	268.69	152.97	108.1	4.41	-
169	15.07, 14.24	48.96, 47.85	30.8, 29.8	11.94	154.1	238.1	14.49	1.993

TABLE 19A
Dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
170	60	306	55.0	0.18	-	0	60	-
171	70	122	130.8	1.07	-	7.8	60	-
172	70	122	123.9	1.02	-	7.8	60/90	4.0/1.0
173	70	122	106.3	0.87	-	7.8	60/90	4.1/0.9
174	70	122	88.9	0.73	-	7.8	60/90	3.6/1.4
175	70	121	108.3	0.89	-	7.8	60/120	4.0/1.0
176	70	123	146.8	1.19	-	15.5	60/90	4.0/1.0
177	70	124	140.7	1.13	-	15.5	60/90	4.2/0.8
178	70	122	92.2	0.76	-	15.5	60	-

- 256 -

TABLE 19B
Dimethylsilanediylbis{1-[2-isopropyl, 4-(2,3-dimethylphenyl)indenyl]}zirconium dichloride

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV Of Copolymer (dl/g)
170	-	-	-	16.93	153.1	190.3	2.09	-
171	-	-	-	70.15	151.63	157.1	2.78	-
172	10.54	44.28	23.80	10.07	153.03	215.0	3.21	2.18
173	16.11	47.0	34.28	2.21	152.5	262.2	3.52	2.68
174	8.036	31.63	25.41	19.22	151.7	191.5	2.83	2.35
175	18.04	44.83	40.24	1.56	152.23	261.1	3.96	1.62
176	7.447	43.78	17.01	32.4	151.77	170.8	2.94	1.73
177	14.43	49.56	29.12	7.46	152.3	213.5	3.53	1.99
178	-	-	-	110.54	151.3	119.2	2.43	-

TABLE 20A
Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenylyl)indenyl]}zirconium dimethyl/NCA

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
179	60	45	<0.5	<0.01	0	0	60	-
180	60	303	<0.5	<0.01	0	0	60	-
181	70	60	84.2	1.4	0	46.5	60	-
182	70	121	147.6	1.22	0	46.5	60	-
183	70	120	192.3	1.60	-	46.5	60/120	4.0/1.0
184	70	122	32.8	0.27	0	15.5	60	-
185	70	120	195.6	1.63	-	46.5	60/120	4.4/0.6
186	70	123	198.8	1.62	0	46.5	60	-
187	70	121	42.0	0.35	0	23.3	60	-

TABLE 20B
Dimethylsilanediybis{1-[2-isopropyl, 4-(2-biphenylyl)indenyl]}zirconium dimethyl/NCA

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV Of Copolymer (dl/g)
179	-	-	-	-	-	-	-	-
180	-	-	-	-	-	-	-	-
181	-	-	-	390.37	158.38	88.1	2.17	-
182	-	-	-	228.3	158.3	101.0	2.19	-
183	4.283	37.52	11.42	165.76	157.77	103.7	2.51	1.54
184	-	-	-	99.02	158.57	132.0	2.07	-
185	4.304	55.95	7.69	148.85	157.7, minor 160.4	107.7	2.42	1.98
186	-	-	-	511.88	156.84, minor 161.44	77.4	2.23	-
187	-	-	-	126.76	158.03	132.1	2.40	-

TABLE 21A
Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenylyl)indenyl]}zirconium dichloride/MAO

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
188	60	45	5.6	0.12	0	0	60	-
189	60	300	83.7	0.28	0	0	60	-
190	70	60	188.0	3.13	-	46.5	60/120	4.0/1.0
191	70	61	201.6	3.30	-	46.5	60	-
192	70	60	234.8	3.91	-	46.5	60/120	4.4/0.6
193	70	60	66.9	1.12	-	15.5	60	-
194	70	61	107.5	1.76	-	31.0	60	-
195	70	301	125.8	0.42	-	7.8	25	-
196	70	63	150.8	2.39	-	46.5	60	-
197	70	150	222.9	1.49	-	31.0	60	-
198	70	150	233.0	1.55	-	31.0	60	-

- 260 -

TABLE 21B
Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}zirconium dichloride/MAO

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW (X10 ⁻³)	MWD	IV of Copolymer (dl/g)
188	-	-	-	-	158.10	266.9	2.21	-
189	-	-	-	2.56	158.90	285.1	2.19	-
190	3.588	40.79	8.80	102.36	157.77	132.3	3.26	1.86
191	-	-	-	74.31	157.10	129.1	2.53	-
192	5.476	55.13	9.93	82.31	157.57	142.6	3.15	2.46
193	-	-	-	11.04	157.90	211.8	2.55	-
194	-	-	-	24.95	156.70	169.1	2.41	-
195	-	-	-	39.42	157.57	168.4	2.12	-
196	-	-	-	158.6	156.04, minor 160.7	114.3	2.43	-
197	-	-	-	33.95	156.85, minor 160.14	149.7	2.30	-
198	-	-	-	35.57	157.25	150.7	2.30	-

TABLE 21C
Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenylyl)indenyl]}zirconium dichloride/MAO

RUN #	Meso Run Length (Monomer Units)	Diad (%)	Stereo Misinsertions /10000 Monomer Units	2,1-Misinsertions /10000 Monomer Units	1,3-Misinsertions /10000 Monomer Units	Xylene Solubles (wt %)	Xylene Insolubles (wt %)
191	245	99.6	23.9	0	16.7	0.53	99.64
197	278	99.6	20.0	0	15.9	0.87	99.09

TABLE 22A
Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenylyl)indenyl]}zirconium dimethyl/MAO

RUN #	TEMP (°C)	Cat. Amount (mg)	Yield (g)	Efficiency (Kg/g cat)	C ₂ = (delta kPa)	H ₂ (mmole)	Time split (min.)	C ₂ =/C ₃ = flow rates (l/min.)
199	70	61	168.4	2.76	0	46.5	60	-
200	70	101	180.2	1.78	0	31.0	60	-
201	70	101	186.1	1.84	-	31.0	60	-
202	70	62	141.3	2.28	-	31.0	60/120	4.4/0.6
203	70	60	138.5	2.31	-	31.0	60/120	4.4/0.6

TABLE 22B
Dimethylsilanediylbis{1-[2-isopropyl, 4-(2-biphenyl)indenyl]}zirconium dimethyl/MAO

RUN #	Total Ethylene (wt %)	Ethylene in Rubber (wt%)	Total rubber (wt %)	Final MFR (g/10 min.)	Melting Point (°C)	MW ($\times 10^{-3}$)	MWD	IV Of Copolymer (dl/g)
199	-	-	-	143.13	156.04, minor 160.17	175.9	21.02	-
200	-	-	-	38.98	160.37	149.9	2.22	-
201	-	-	-	26.82	155.71	153.4	2.31	-
202	5.817	55.61	10.46	26.41	157.77	172.5	3.29	3.14
203	5.549	56.39	9.84	44.55	157.77	165.6	2.99	2.85
	-							

The metallocenes in the above Examples and Tables are represented by formula (I) as follows:

- 5 M^1 = zirconium,
 R^1, R^2 = Cl (methyl in Examples 20 and 22),
 R^4, R^5, R^6, R^7 = H
 R^{13} = Me_2Si


Ex.(Table)	R^3	R^{12}	R^{11}	R^{10}	R^9	R^8
1	Me	H	H	H	H	H
2	Me	H	Me	H	H	H
3	Me	H	Me	H	Me	H
4	Me	Me	H	H	H	H
5	Me	Et	H	H	H	H
6	Me	iso-Pr	H	H	H	H
7	Me	Ph	H	H	H	H
8	Me	H	H	Ph	H	H
9	Me	H	H	tert-Bu	H	H
10	Me	Me	Me	H	H	H
11	Me	Me	H	Me	H	H
12	Me	Me	H	H	H	Me
13	Me	Me	H	H	Me	H
14	Me	Me	Me	Me	H	H
15	Me	Me	H	Me	Me	H
16	Me	Me	Me	H	Me	Me
17	iso-Pr	H	Ph	H	H	H
18	iso-Pr	Me	H	H	H	H
19	iso-Pr	Me	Me	H	H	H
20	iso-Pr	Ph	H	H	H	H
21	iso-Pr	Ph	H	H	H	H
22	iso-Pr	Ph	H	H	H	H

- 10 Me = Methyl; Et = Ethyl; iso-Pr = Isopropyl; tert-Bu = tert. Butyl; Ph = Phenyl

WHAT IS CLAIMED IS:

1. A bridged bis(2- R^3 -4-phenyl-indenyl) R^1R^2 metallocene wherein:
 the phenyl rings are substituted at the 2' positions (R^{12}) by radicals which may be
 5 identical or different halogen atoms, C_1 - C_{10} alkyl groups, C_6 - C_{14} aryl groups, C_2 -
 C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups, C_8 - C_{40}
 arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$ radicals;
 the radicals R^3 are selected from hydrogen, halogen, C_1 - C_{10} alkyl groups, C_6 - C_{14}
 aryl groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl
 10 groups, C_8 - C_{40} arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$
 radicals wherein each R' is independently selected from halogen, C_1 - C_{10} alkyl
 groups and C_6 - C_{14} aryl groups; provided that if R^1 and R^2 both are halogen and R^{13}
 is dimethylsilanediyl, then R^3 is different from methyl and ethyl.

2. A compound of claim 1 represented by the formula:



wherein:

M¹ is selected from titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten;

R¹ and R² are selected from hydrogen, halogen, hydroxy, C₁-C₁₀ alkyl groups, C₁-C₁₀ alkoxy groups, C₆-C₁₄ aryl groups, C₆-C₁₄ aryloxy groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups and C₇-C₄₀ arylalkenyl groups; or R¹ and R² are joined together to form a C₄-C₄₀ alkanediyl group or a conjugated C₄-C₄₀ diene ligand which is coordinated to M¹ in a metallacyclopentene fashion; or R¹ and R² represent a conjugated diene, optionally substituted with one or more groups independently selected from hydrocarbyl, trihydrocarbylsilyl and trihydrocarbylsilylhydrocarbyl groups, said diene having a total of up to 40 atoms not counting hydrogen and forming a π complex with M¹;

R³ is selected from hydrogen, halogen, C₁-C₁₀ alkyl groups, C₆-C₁₄ aryl groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups; provided that if R¹ and R² both are halogen and R³ is dimethylsilanediyl, R³ is different from methyl and ethyl;



R⁴, R⁵, R⁶ and R⁷ are each independently selected from hydrogen, halogen, C₁-C₁₀ alkyl groups, C₆-C₁₄ aryl groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups; or two or more adjacent radicals R⁵, R⁶ and R⁷ together with the atoms connecting them may form one or more rings;

R⁸, R⁹, R¹⁰ and R¹¹ are each independently as defined for R⁴, R⁵, R⁶ and R⁷, provided that two or more adjacent radicals R⁸, R⁹, R¹⁰ and R¹¹ together with the atoms connecting them may form one or more rings ;

R¹² is selected from halogen, C₁-C₁₀ alkyl groups, C₆-C₁₄ aryl groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals

wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups;

R¹³ is selected from



5


-B(R¹⁴)-, -Al(R¹⁴)-, -Ge-, -Sn-, -O-, -S-, -SO-, -SO₂-, -N(R¹⁴)-, -CO-, -P(R¹⁴)-
-P(O)(R¹⁴)-, -B(NR¹⁴R¹⁵)- and -B[N(SiR¹⁴R¹⁵R¹⁶)₂]-;

wherein:

10 R¹⁴, R¹⁵ and R¹⁶ are each independently selected from hydrogen, halogen, C₁-C₂₀ alkyl groups, C₆-C₃₀ aryl groups, C₁-C₂₀ alkoxy groups, C₂-C₂₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₈-C₄₀ arylalkenyl groups and C₇-C₄₀ alkylaryl groups, or R¹⁴ and R¹⁵, together with the atom(s) connecting them, form a ring; and

M³ is selected from carbon, silicon, germanium and tin; or

15 R¹³ is represented by the formula



wherein:

R^{17} , R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} and R^{24} are each independently selected from hydrogen, halogen, hydroxy, C_1 - C_{10} alkyl groups, C_1 - C_{10} alkoxy groups, C_6 - C_{14} aryl groups, C_6 - C_{14} aryloxy groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups and C_8 - C_{40} arylalkenyl groups; or two or more adjacent radicals R^{17} , R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} and R^{24} , including R^{20} and R^{21} , together with the atoms connecting them, form one or more rings; and M^2 represents one or more carbon atoms, or a silicon, germanium or tin atom.

3. The compound of claim 2, wherein M^1 is selected from titanium, zirconium and hafnium.

4. The compound of claim 1 or 2, wherein R^1 and R^2 are selected from chlorine, C_1 - C_6 alkyl groups, C_6 - C_{10} aryl groups, C_7 - C_{12} arylalkyl groups and C_7 - C_{12} alkylaryl groups.

5. The compound of claim 1 or 2, wherein R^1 and R^2 are methyl groups.

6. The compound of claim 4, wherein R^3 is selected from C_3 - C_6 alkyl groups and phenyl.


7. The compound of claim 4, wherein R^3 is selected from branched C_3 - C_4 alkyl groups.

8. The compound of claim 1 or 2, wherein R^3 is an isopropyl group.

9. The compound of claims 2 to 8, wherein R^4 is hydrogen.

10. The compound of claim 3, wherein M^3 is selected from carbon and silicon, and R^{14} , R^{15} and R^{16} are independently selected from C_1 - C_4 alkyl groups and C_6 - C_{10} aryl groups.

11. The compound of claim 3, wherein R^{13} is represented by the formula



wherein:

R^{17} , R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} and R^{24} each are hydrogen; and

M^2 represents a silicon atom.

12. The compound of any of claims 1 to 11 wherein R^{12} is selected from C_1 - C_6 alkyl groups and C_6 - C_{10} aryl groups.

13. The compound of any of claims 1 to 12, wherein R^{12} is phenyl.

14. The compound of any of claims 2 to 13, wherein at least one of R^4 and R^8 is hydrogen.

15. The compound of any of claims 2 to 11, wherein R^{12} is C_1 - C_2 alkyl and R^{11} is different from hydrogen.


16. The compound of any of claims 2 to 15, wherein each of R^4 and R^8 is hydrogen.

17. The compound of claim 2, wherein R^1 and R^2 are selected from chlorine, methyl, neopentyl and benzyl, R^3 is selected from C_3 - C_4 alkyl groups, each of R^4 and R^8 is hydrogen, and R^{12} is selected from C_1 - C_4 alkyl groups and C_6 - C_{10} aryl groups.

18. The compound of any of claims 2 to 17, wherein R^3 is selected from branched C_3 - C_4 alkyl groups and R^{12} is selected from C_6 - C_{10} aryl groups.

19. The compound of any of claims 2 to 17, wherein R^3 is selected from isopropyl, isobutyl, sec-butyl, tert-butyl and phenyl groups, and R^{12} is selected from n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, phenyl, tolyl, benzyl and naphthyl groups.

20. The compound of claim 2, wherein M^1 is selected from zirconium and hafnium; R^1 and R^2 are selected from chlorine, C_1 - C_3 alkyl groups and C_6 - C_{10} aryl groups; R^3 is selected from C_3 - C_6 alkyl groups and C_6 - C_{10} aryl groups; R^4 and R^8 are hydrogen; R^5 , R^6 , R^7 , R^9 , R^{10} and R^{11} are each independently selected from hydrogen and C_1 - C_3 alkyl groups; R^{12} is selected from C_3 - C_6 alkyl groups and C_6 - C_{10} aryl groups; and R^{13} is selected from di(C_1 - C_4 alkyl)silanediyl, diphenylsilanediyl, (C_1 - C_4 alkyl)phenylsilanediyl, diphenylmethanediyl and C_2 - C_4 alkanediyl and alkenediyl radicals and groups of the formula




wherein:

R^{17} , R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} and R^{24} are each independently selected from hydrogen, halogen and C_1 - C_3 alkyl groups; and M^2 represents a carbon or silicon atom.

21. The compound of claim 20, wherein R^{13} is selected from di(C_1 - C_4 alkyl)silanediyl, diphenylsilanediyl, (C_1 - C_4 alkyl)phenylsilanediyl, C_2 - C_4 alkanediyl and alkenediyl, di(C_1 - C_4 alkyl)amidoborane and bis[tri(C_1 - C_4 alkyl)lsilyl]amidoborane radicals.

5

22. A compound represented by the formula:



10

wherein:

M^I is selected from titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten;

15

R^1 and R^2 are selected from hydrogen, halogen, hydroxy, C_1 - C_{10} alkyl groups, C_1 - C_{10} alkoxy groups, C_6 - C_{14} aryl groups, C_6 - C_{14} aryloxy groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups and C_7 - C_{40} arylalkenyl groups; or R^1 and R^2 are joined together to form an alkanediyl group or a conjugated C_4 - C_{40} diene ligand which is coordinated to M^I in a


metallacyclopentene fashion; or R^1 and R^2 represent a conjugated diene, optionally substituted with one or more groups independently selected from hydrocarbyl, trihydrocarbylsilyl and trihydrocarbylsilylhydrocarbyl groups, said diene having a total of up to 40 atoms not counting hydrogen and forming a π complex with M^1 ;

R^3 is selected from hydrogen, halogen, C_1 - C_{10} alkyl groups, C_6 - C_{14} aryl groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups, C_8 - C_{40} arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$ radicals wherein each R' is independently selected from halogen, C_1 - C_{10} alkyl groups and C_6 - C_{14} aryl groups;

R^4 , R^5 , R^6 and R^7 are each independently selected from hydrogen, halogen, C_1 - C_{10} alkyl groups, C_6 - C_{14} aryl groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups, C_8 - C_{40} arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$ radicals wherein each R' is independently selected from halogen, C_1 - C_{10} alkyl groups and C_6 - C_{14} aryl groups; or two or more adjacent radicals R^5 , R^6 and R^7 together with the atoms connecting them may form one or more rings; R^8 , R^9 , R^{10} and R^{11} are each independently as defined for R^4 , R^5 , R^6 and R^7 , provided that two or more adjacent radicals R^8 , R^9 , R^{10} and R^{11} together with the atoms connecting them may form one or more rings;

R^{12} is selected from halogen, C_1 - C_{10} alkyl groups, C_6 - C_{14} aryl groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups, C_8 - C_{40} arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$ radicals wherein each R' is independently selected from halogen, C_1 - C_{10} alkyl groups and C_6 - C_{14} aryl groups;

R^{13} is selected from groups of the formula



wherein:

R^{17} , R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} and R^{24} are each independently selected from hydrogen, halogen, hydroxy, C_1 - C_{10} alkyl groups, C_1 - C_{10} alkoxy groups, C_6 - C_{14} aryl groups, C_6 - C_{14} aryloxy groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups and C_8 - C_{40} arylalkenyl groups; or two or more adjacent radicals R^{17} , R^{18} , R^{19} , R^{20} , R^{21} , R^{22} , R^{23} and R^{24} , including R^{20} and R^{21} , together with the atoms connecting them, form one or more rings; and M^2 represents a carbon, silicon or germanium atom.

23. The compound of claim 22, wherein R^3 is selected from C_3 - C_6 alkyl groups and phenyl.

24. The compound of claim 23, wherein R^3 is an isopropyl group.

25. The compound of claim 22 or 23, wherein R^{12} is selected from C_1 - C_6 alkyl groups and C_6 - C_{10} aryl groups.

26. The compound of any of claims 22 to 26, wherein R^{12} is phenyl.


27. The compound of claim 28, wherein each of R^4 and R^8 is hydrogen.

28. A catalyst composition comprising the product of a compound of claims 1 2 or 22 and a cocatalyst.

29. The catalyst composition of claim 28, which further comprises a support material.

30. The catalyst composition of claim 28, wherein the support material is selected from silica, alumina, silica-alumina, magnesium chloride and mixtures thereof.

31. A polymerization process comprising contacting, under polymerization conditions, one or more ethylenically unsaturated monomers and a catalyst composition, said catalyst composition comprising the product of a compound represented by formula (I) and a cocatalyst:



wherein:

M^1 is selected from titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten;

R^1 and R^2 are selected from hydrogen, halogen, hydroxy, C_1 - C_{10} alkyl groups, C_1 - C_{10} alkoxy groups, C_6 - C_{14} aryl groups, C_6 - C_{14} aryloxy groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups and C_7 - C_{40} arylalkenyl groups; or R^1 and R^2 are joined together to form a C_4 - C_{40} alkanediyl group or a conjugated C_4 - C_{40} diene ligand which is coordinated to M^1 in a metallacyclopentene fashion; or R^1 and R^2 represent a conjugated diene, optionally substituted with one or more groups independently selected from hydrocarbyl, trihydrocarbylsilyl and trihydrocarbylsilylhydrocarbyl groups, said diene having a total of up to 40 atoms not counting hydrogen and forming a π complex with M^1 ;



R^3 is selected from hydrogen, halogen, C_1 - C_{10} alkyl groups, C_6 - C_{14} aryl groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups, C_8 - C_{40} arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$ radicals wherein each R' is independently selected from halogen, C_1 - C_{10} alkyl groups and C_6 - C_{14} aryl groups; provided that if R^1 and R^2 both are halogen and R^{13} is dimethylsilanediyl, R^3 is different from methyl and ethyl;

R^4 , R^5 , R^6 and R^7 are each independently selected from hydrogen, halogen, C_1 - C_{10} alkyl groups, C_6 - C_{14} aryl groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups, C_8 - C_{40} arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$ radicals wherein each R' is independently selected from halogen, C_1 - C_{10} alkyl groups and C_6 - C_{14} aryl groups; or two or more adjacent radicals R^5 , R^6 and R^7 together with the atoms connecting them may form one or more rings;

R^8 , R^9 , R^{10} and R^{11} are each independently as defined for R^4 , R^5 , R^6 and R^7 , provided that two or more adjacent radicals R^8 , R^9 , R^{10} and R^{11} together with the atoms connecting them may form one or more rings ;

R^{12} is selected from halogen, C_1 - C_{10} alkyl groups, C_6 - C_{14} aryl groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups, C_8 - C_{40} arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$ radicals wherein each R' is independently selected from halogen, C_1 - C_{10} alkyl groups and C_6 - C_{14} aryl groups;

R^{13} is selected from




-B(R¹⁴)-, -Al(R¹⁴)-, -Ge-, -Sn-, -O-, -S-, -SO-, -SO₂-, -N(R¹⁴)-, -CO-, -P(R¹⁴)-
 5 -P(O)(R¹⁴)-, -B(NR¹⁴R¹⁵)- and -B[N(SiR¹⁴R¹⁵R¹⁶)₂]-;

wherein:

R¹⁴, R¹⁵ and R¹⁶ are each independently selected from hydrogen, halogen, C₁-C₂₀
 alkyl groups, C₆-C₃₀ aryl groups, C₁-C₂₀ alkoxy groups, C₂-C₂₀ alkenyl groups,
 C₇-C₄₀ arylalkyl groups, C₈-C₄₀ arylalkenyl groups and C₇-C₄₀ alkylaryl groups, or
 10 R¹⁴ and R¹⁵, together with the atom(s) connecting them, form a ring; and

M³ is selected from carbon, silicon, germanium and tin; or

R¹³ is represented by the formula



wherein:

R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹, R²², R²³ and R²⁴ are each independently selected from
 15 hydrogen, halogen, hydroxy, C₁-C₁₀ alkyl groups, C₁-C₁₀ alkoxy groups, C₆-C₁₄
 aryl groups, C₆-C₁₄ aryloxy groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl

groups, C₇-C₄₀ alkylaryl groups and C₈-C₄₀ arylalkenyl groups; or two or more adjacent radicals R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹, R²², R²³ and R²⁴, including R²⁰ and R²¹, together with the atoms connecting them, form one or more rings; and M² represents one or more carbon atoms, or a silicon, germanium or tin atom.

5

32. The process of claim 31, wherein R¹ and R² are selected from chlorine, C₁-C₆ alkyl groups, C₆-C₁₀ aryl groups, C₇-C₁₂ arylalkyl groups and C₇-C₁₂ alkylaryl groups.

10

33. The process of claims 31 or 32, wherein R³ is selected from C₃-C₆ alkyl groups and phenyl.

34. The process of claims 31 or 32, wherein R³ is an isopropyl group.

15

35. The process of any of claims 31 to 34, wherein R¹² is selected from C₁-C₆ alkyl groups and C₆-C₁₀ aryl groups.

36. The process of any of claims 31 to 34, wherein R¹² is phenyl.

20

37. The process of claims 31 or 32, wherein R³ is selected from isopropyl, isobutyl, sec-butyl, tert-butyl and phenyl groups, and R¹² is selected from n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, phenyl, tolyl, benzyl and naphthyl groups.

25

38. The process of any of claims 31 to 37, wherein the catalyst composition further comprises a support material.

39. The process of claim 38, wherein the catalyst composition further comprises an inorganic support material.

30

40. The process of any of claims 31 to 39, wherein said monoolefins comprise compounds of the formula R^aCH=CHR^b wherein R^a and R^b are each


independently selected from hydrogen, alkyl and alkenyl radicals having 1 to 14 carbon atoms or, together with the carbon atoms to which they are connected, form a ring having 4 to 8 carbon atoms.

5 41. The process of claim any of claims 31 to 39, wherein said ethylenically unsaturated monomers consist essentially of ethylene and/or propylene.

42. The process of any of claims 31 to 41, wherein said process is carried out at a temperature ranging from 30° C to 80° C.

10 43. The process of claim 31, wherein R¹ and R² are selected from chlorine, C₁-C₆ alkyl groups, C₆-C₁₀ aryl groups, C₇-C₁₂ arylalkyl groups and C₇-C₁₂ alkylaryl groups, R³ is selected from C₃-C₆ alkyl groups and phenyl, each of R⁴ and R⁸ is hydrogen, R¹² is selected from n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl,
15 tert-butyl, phenyl, tolyl, benzyl and naphthyl groups, the cocatalyst is selected from compounds comprising noncoordinating anions, alumoxanes and mixtures thereof, wherein the catalyst composition further comprises a support material selected from silica, alumina, silica-alumina, magnesium chloride and mixtures thereof, and wherein said one or more ethylenically unsaturated monomers
20 comprise at least ethylene and propylene.

44. A polymerization process comprising contacting, under polymerization conditions, one or more ethylenically unsaturated monomers and a catalyst composition, said catalyst composition comprising the product of a compound
25 represented by formula (I) and a cocatalyst:



wherein:

M^1 is selected from titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten;

R^1 and R^2 are selected from hydrogen, halogen, hydroxy, C_1 - C_{10} alkyl groups, C_1 - C_{10} alkoxy groups, C_6 - C_{14} aryl groups, C_6 - C_{14} aryloxy groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups and C_7 - C_{40} arylalkenyl groups; or R^1 and R^2 are joined together to form an alkanediyl group or a conjugated C_4 - C_{40} diene ligand which is coordinated to M^1 in a metallacyclopentene fashion; or R^1 and R^2 represent a conjugated diene, optionally substituted with one or more groups independently selected from hydrocarbyl, trihydrocarbylsilyl and trihydrocarbylsilylhydrocarbyl groups, said diene having a total of up to 40 atoms not counting hydrogen and forming a π complex with M^1 ;


R^3 is selected from hydrogen, halogen, C_1 - C_{10} alkyl groups, C_6 - C_{14} aryl groups, C_2 - C_{10} alkenyl groups, C_7 - C_{40} arylalkyl groups, C_7 - C_{40} alkylaryl groups, C_8 - C_{40} arylalkenyl groups, and $-NR'_2$, $-SR'$, $-OR'$, $-SiR'_3$, $-OSiR'_3$ and $-PR'_2$ radicals

wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups;

R⁴, R⁵, R⁶ and R⁷ are each independently selected from hydrogen, halogen, C₁-C₁₀ alkyl groups, C₆-C₁₄ aryl groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups; or two or more adjacent radicals R⁵, R⁶ and R⁷ together with the atoms connecting them may form one or more rings; R⁸, R⁹, R¹⁰ and R¹¹ are each independently as defined for R⁴, R⁵, R⁶ and R⁷, provided that two or more adjacent radicals R⁸, R⁹, R¹⁰ and R¹¹ together with the atoms connecting them may form one or more rings;

R¹² is selected from halogen, C₁-C₁₀ alkyl groups, C₆-C₁₄ aryl groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups, C₈-C₄₀ arylalkenyl groups, and -NR'₂, -SR', -OR', -SiR'₃, -OSiR'₃ and -PR'₂ radicals wherein each R' is independently selected from halogen, C₁-C₁₀ alkyl groups and C₆-C₁₄ aryl groups;

R¹³ is selected from groups of the formula



wherein:

R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹, R²², R²³ and R²⁴ are each independently selected from hydrogen, halogen, hydroxy, C₁-C₁₀ alkyl groups, C₁-C₁₀ alkoxy groups, C₆-C₁₄ aryl groups, C₆-C₁₄ aryloxy groups, C₂-C₁₀ alkenyl groups, C₇-C₄₀ arylalkyl groups, C₇-C₄₀ alkylaryl groups and C₈-C₄₀ arylalkenyl groups; or two or more adjacent radicals R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹, R²², R²³ and R²⁴, including R²⁰ and R²¹, together with the atoms connecting them, form one or more rings; and

M² represents a carbon, silicon or germanium atom.

45. A polymer composition comprising:

(a) propylene polymer comprising at least 99 % by weight of units derived from propylene and having a melting point of at least 155° C; and

(b) olefin copolymer comprising from 40 to 70 % by weight of units derived from propylene and having an intrinsic viscosity of at least 1.8;

the composition made with a single catalyst composition.

46. The polymer composition of claim 45, wherein component (a) is selected from homopolypropylene and copolymers of propylene and at least one monoolefin selected from ethylene and α -olefins having from 4 to 12 carbon atoms, said copolymers containing at least 99.5 % by weight of units derived from propylene.

47. The polymer composition of claims 45 or 46, wherein component (b) comprises from 30 to 60 % by weight of units derived from ethylene.

48. The polymer composition of claim 47, wherein components (a) and (b) together contain a total of 1.5 to 20 % by weight of units derived from ethylene.

49. The polymer composition of any of claims 45 to 48, wherein component (a) has a melting point of at least 156° C.

50. The polymer composition of any of claims 45 to 49, wherein component (a) has a melting point of at least 157° C.

51. The polymer composition of any of claims 45 to 49, wherein component (b) has an intrinsic viscosity of at least 2.0.

52. The polymer composition of any of claims 45 to 49, wherein component (b) has an intrinsic viscosity of at least 2.2.

53. The polymer composition of any of claims 45 to 52, wherein the composition has a M_w/M_n of not higher than 3.5.

5 54. The polymer composition of any of claims 45 to 52, wherein the composition has a M_w/M_n of not higher than 3.0.

55. The polymer composition of any of claims 45 to 54, wherein component (a) is selected from homopolypropylene and copolymers of propylene and at least one monoolefin selected from ethylene and α -olefins having from 4 to 12 carbon atoms, said copolymers containing at least 99.5 % by weight of units derived from propylene, component (b) comprises from 30 to 60 % by weight of units derived from ethylene, and components (a) and (b) together contain a total of 1.5 to 20 % by weight of units derived from ethylene, wherein component (a) has a melting point of at least 157° C and component (b) has an intrinsic viscosity of at least 2.0, and wherein the composition has a M_w/M_n of not higher than 3.5.

10

15

56. The polymer composition of any of claims 45 to 55, wherein the catalyst composition is supported.