



G00001

1

A METHOD AND DEVICE FOR IMPROVING THE
QUALITY OF FRESH CONCRETE AND PREVENTING
ADHESION AND HARDENING OF FRESH CONCRETE
IN A ROTARY MIXER DRUM OF A CONCRETE MIXER
TRUCK AND/OR IN A CONCRETE MIXING PLANT

1. BACKGROUND OF INVENTION

1-1. Field of the Invention

This invention relates to a method of and device for improving the quality of fresh concrete and preventing adhesion and hardening of the fresh concrete, and more particularly, to a method of and device for improving the quality of fresh concrete and preventing adhesion and hardening of fresh concrete in a rotary mixer drum of a concrete mixer truck and/or in a concrete mixing plant whereby cold or warm air is selectively and continuously delivered into a rotary mixer drum of the concrete mixer truck and/or into a stationary mixer drum during just before or just after unloading the fresh concrete and also just before washing the inside of the rotary mixer drum to maintain the temperature of the fresh concrete at a required temperature, and to delay a hardening time of the fresh concrete, and subsequently water is sprayed into the rotary and/or stationary mixer drum after having finished discharging the remaining fresh concrete to wash away the latter before it has hardened.



166166

1-2. Description of the Prior Art

Concrete is an artificial stony material which is used for foundations, etc. made by mixing cement, sand and broken stones, etc. with water, and allowing the mixture to harden.

Quick hardening and solid concrete is indispensable for building material. These solid and quick hardening properties of concrete may be disadvantageous sometimes.

As shown in FIG. 1, a conventional rotary mixer drum 20 is rotatably mounted on a chassis 10a of a mixer truck 10 with a hydraulic motor 12 which is linked to a gear 16 by a roller chain 14, the gear 16 being provided at a central portion of a bottom portion 20b of the rotary mixer drum 20.

There has been an annoying problem in the conventional concrete mixer truck 10 and in the concrete mixing plant that chemical reaction of the mixed fresh concrete advances to adhere on a plurality of rotary blades and around an inner periphery of a rotary concrete drum, etc. and hardens thereon.

The concrete once adhered and hardened on the rotary blades and the inner periphery of the rotary mixer drum 20 of the concrete mixer truck 10 and in the concrete mixing plant is hardly scraped off.

It has been customary in the art that the remaining fresh concrete in a bottom portion of a

rotary mixer drum 20 of a concrete mixer truck 10 and/or in a concrete mixing plant and is washed away by water after the fresh concrete has been discharged or unloaded out of the rotary mixer drum 20.

The temperature in the rotary mixer drum 20 rises over a range between about 40 - 50 degree C. under the blazing sun in summer, resulting in shortening both a hardening time and delivery range of the fresh concrete and also decreasing the strength of the hardened concrete.

In addition, when the mixed fresh concrete is unloaded out of the conventional rotary mixer drum 20 of the concrete mixer truck 10, the temperature in the rotary mixer drum 20 rises suddenly so that the remaining fresh concrete hardens in a short time.

Moreover, inasmuch as the temperature in the rotary mixer drum 20 itself is rather high, the fresh concrete gathers at a bottom portion of the rotary mixer drum 20 before it is unloaded, and agitation of the fresh concrete is not fully carried out, thus accelerating adhesion and hardening of the fresh concrete.

To this end, even when water is sprayed into the rotary mixer drum 20 immediately after the fresh concrete has been unloaded, the remaining fresh concrete once hardened cannot be washed away.

Accordingly, it is required that an operator must enter the rotary mixer drum 20 to scrape or tear the hardened concrete by a hammer.

Washing by water is usually carried out immediately after the fresh concrete has been unloaded from the batcher type concrete mixer, but even if any kind of washing by water is carried out, a certain amount of the adhered concrete increases.

In practice, it is necessary that the operator must carry out scraping the adhered concrete off the rotary mixer drum 20 of both of the concrete mixer truck 10 and of the concrete mixing plant once in a week.

It is very dangerous for the operator to enter the rotary mixer drum 20 of the concrete mixer truck 10 and of the concrete mixing plant in order to scrape the adhered and hardened concrete off the rotary mixer drum 20.

A number of fatal accidents have been reported regrettably every year that the rotary mixer drum 20 is carelessly driven to rotate without a knowledge that the operator is within the rotary mixer drum 20 mounted on the concrete mixer truck 10.

In order to avoid such an accident, a safety device with a sensor for detecting the operator within the rotary mixer drum 20 has been proposed.

Washing by water and scraping operation by the operator within the rotary mixer drum 20 would not

be out so that a complete safe measure cannot be expected.

It is stipulated under the JIS (the Japanese Industrial Standards) that time between from mixing fresh concrete to beginning unloading the fresh concrete must be within 90 minutes.

When the time has passed 90 minutes, the temperature of the mixed fresh concrete rises so that the fresh concrete is deteriorated by the high temperature to shorten a delivery range.

Accordingly, the fresh concrete thus mixed is likely refused by a user as the product below the standards.

It is said that concrete mixing and its transportation are the battle against time.

In another embodiment, some cooling systems or refrigerators, each using liquefied gas, have been proposed to cool the fresh concrete itself temporarily so that the strength of the placed concrete is increased, crack of the deposited concrete is prevented and a quality of the concrete is maintained.

Among them are many cooling systems, through which fresh concrete is directly cooled prior to transportation.

One of the conventional cooling systems is characterized in that the fresh concrete is cooled at a building site or a construction field.

Mounted on the concrete mixer truck is another

conventional cooling system, through which liquefied gas is directly injected into the fresh concrete (see Japanese Patent Publication No.229507/1986, not-examined).

It should be appreciated, however, that liquefied gas is very expensive, and although it may be suitable for a temporary cooling of fresh concrete, a large amount of liquefied gas is required for continuous cooling during transportation.

Another embodiment has been proposed, wherein flakes of crushed ice are mixed into fresh concrete in a rotary mixer drum, but there is a disadvantage that when there remain the flakes of crushed ice in the fresh concrete at the time of placing the latter, there occur openings or gaps at the crushed ice in the fresh concrete, thus deteriorating the strength of the hardened concrete.

On the other hand, when the rotary mixer drum 20 is exposed to the open air in a cold season to drop the temperature in the former, the strength of the mixed fresh concrete decreases.

In order to eliminate this disadvantage, a countermeasure that a mixture ratio of cement is changed in accordance with the temperature of the open air has been worked out. The mixing adjustment therefor is very troublesome, and the material cost increases too.

Adhesion and hardening of the remaining cement

occur as well in the rotary mixer drum in the cold season which is even fewer than at a high temperature.

2 - SUMMARY OF THE INVENTION

A principal object of this invention is to provide a method for improving the quality of fresh concrete and preventing adhesion and hardening of fresh concrete on a plurality of rotary blades and around an inner periphery of a rotary mixer drum of a concrete mixer truck and/or of a concrete mixing plant whereby cold or warm air is selectively and continuously delivered into the rotary mixer drum to maintain a temperature of the fresh concrete in a required temperature degree, to delay a hardening time of the fresh concrete and to extend a delivery range thereof.

Another object of this invention is to provide a device for improving the quality of fresh concrete and preventing adhesion and hardening of fresh concrete on a plurality of rotary blades and around an inner periphery of a rotary mixer drum of a concrete mixer truck and/or of a concrete mixing plant whereby cold or warm air is selectively and continuously delivered into the rotary mixer drum to maintain a temperature of the fresh concrete at a required temperature range, to delay a hardening time of the fresh concrete and to extend a delivery range thereof.

Another object of this invention is to provide a method for improving the quality of fresh concrete and preventing adhesion and hardening of fresh concrete on a plurality of rotary blades and around an inner periphery of a rotary mixer drum of a concrete mixer truck and/or of a concrete mixing plant whereby cold air is continuously delivered into the rotary mixer drum at a high temperature to maintain a temperature of the fresh concrete at a required low temperature degree, to delay a hardening time of the fresh concrete and to extend a delivery range thereof.

Another object of this invention is to provide a device whereby a long distance transportation of the fresh concrete can be carried out easily without deteriorating the quality of fresh concrete and preventing adhesion and hardening of the fresh concrete on an inner periphery of a rotary mixer drum of a concrete mixer truck and/or of a concrete mixing plant.

Another object of this invention is to provide a device whereby time for transporting the fresh concrete in the rotary mixer drum can be elongated as long as possible without using a concrete mixing relay base.

Another object of this invention is to provide a device whereby washing by water of the remaining fresh concrete in a rotary mixer drum of a concrete

mixing truck and/or of a concrete mixing plant can be carried out easily and safely so that a scrapping operation of the adhered concrete by an operator in the rotary mixer drum can be discontinued, thus avoiding a fatal accident.

Another object of this invention is to provide a device for manufacturing fresh concrete in a rotary mixer drum of a concrete mixer truck whereby the fresh concrete can be manufactured even at a region where neither a fresh concrete mixing plant nor a concrete mixing relay base is located, thus enabling to manufacture the fresh concrete effectively without bring concrete material such as sand, cement and water respectively.

Another object of this invention is to provide a device whereby only cold air is delivered into a rotary mixer drum of a concrete mixer truck so as to prevent adhesion of the remaining fresh concrete after most of the fresh concrete has been discharged.

Another object of this invention is to provide a device whereby placing of fresh concrete can be carried out both at either high or low temperature.

Another object of this invention is to provide a device for preventing adhesion and hardening of fresh concrete in a rotary mixer drum of a concrete mixer truck wherein a part or whole portion of an exterior casing of the rotary mixer drum is deta-

chably covered with heat insulating material.

Still another object of this invention is to provide a device for preventing adhesion and hardening of fresh concrete in a rotary mixer drum of a concrete mixer truck having a compact and simple hot and cold air blower which can be easily manufactured and mounted on a rotary mixer truck at a reasonable price.

3 - BRIEF DESCRIPTION OF THE DRAWINGS

These and other objects, features, and advantage of this invention will become more apparent from the following description of the preferred embodiments taken in conjunction with the accompanying drawings, in which;

FIG. 1 is a perspective view of a conventional rotary mixer drum mounted on a concrete mixer truck;

FIG. 2 is a perspective view of a rotary concrete mixer in accordance with this invention, seen from the back position;

FIG. 3 is a side elevation of the rotary concrete mixer shown in FIG. 2;

FIG. 4 is a side elevation of the rotary concrete mixer, which is similar to FIG. 3, with a rotary mixer drum being partially cut away;

FIG. 5 is an enlarged partial sectional view, taken along the lines V - V of FIG. 4;

FIG. 6 is a front elevation of an air conditioner for supplying cold air into a concrete mixing plant;

FIG. 7 is a plan view of a heat insulating material to be covered around a rotary mixer drum and an air blast duct of this invention;

FIG. 8 is an enlarged partial sectional view showing an air supplying device of another embodiment of this invention;

FIG. 9 is an enlarged sectional view of a cold and warm air blower mounted on an agitation type rotary concrete mixer; and

FIG. 10 is an enlarged sectional view of a cold and hot air blower mounted on a batcher concrete rotary mixing plant.

4-DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

This invention is concerned with a method and device for preventing adhesion and hardening of fresh concrete in a rotary mixer drum of a concrete mixer truck.

Referring to FIGS. 2 - 4, a blower 24 is mounted on a chassis 10a of a concrete mixer truck 10 to locate between a driver's cab 10b and a rotary mixer drum 20 for continuously blowing cold air in the mixed fresh concrete in the rotary mixer drum 20.

A water tank 22 is provided on the chassis 10a to wash an inner periphery of the rotary mixer drum

20.

Located above and adjacent to the rotary mixer drum 20 is a blower duct 26, one end portion 26a of which is connected to the blower 24 and another end portion 26b is introduced to enter partially a hopper 20a of the rotary mixer drum 20.

A temperature sensor or thermometer (not shown) is provided at one end portion 26b of the air duct 26 in order to take the inner temperature in the rotary mixer drum 20.

When detected by the temperature sensor that the temperature of the mixed fresh concrete in the rotary mixer drum 20 rises over the predetermined range, the blower 24 is driven to deliver cold air to reduce the temperature and to maintain the predetermined range (between about 1 degree C. and about 15 degree C.).

It should be understood that when the open air temperature outside the rotary mixer drum 20 is 28 degree C. and the temperature in the rotary mixer drum 20 rises about 15 degree C., the air blower 24 is driven to deliver cold air for dropping the temperature by about 3 degree C., thus maintaining the temperature in the rotary mixer drum 20 below about 12 degree C.

When the open air temperature outside the rotary mixer drum 20 is about 12 degree C., the temperature in the former rises over that of the

open air, and unless any measure is taken, the temperature in the rotary mixer drum 20 rises over about 15 degree C., so that even if the open air temperature is below about 15 degree C., the air blower 24 is driven to deliver cold air into the rotary mixer drum 20.

In summer, the daytime open air temperature outside the rotary mixer drum 20 is always higher than about 15 degree C.

On the other hand, the open air temperature outside the rotary mixer drum 20 is likely lower than the open air temperature in winter.

Accordingly, a set cooling temperature of the air blower 24 is mechanically set to - 10 degree C. during a season between May and October with the rotary mixer drum 20 covered with a heat insulating material without using a temperature control such as the temperature sensor, and the set cooling temperature may be set to +5 degree C. during a season between November and next April.

It is possible to choose a more detailed set temperature.

In an embodiment shown in FIG. 10, it is possible to adjust a temperature of a mixed fresh concrete in the rotary mixer drum 20 by adjusting a temperature of water (usually at a room temperature) delivered into the rotary mixer drum 20 together with cement due to synergistic effect of the

adjustment of cold and hot air, thus maintaining the temperature between at 1 degree C. and 5 degree C. in summer, and at a temperature between at 30 and 70 degree C. in autumn and winter.

The one end portion 22a of the air duct 22 must be provided to locate into the upper portion of the rotary mixer drum 20 so that cold air is flowed downwardly into the rotary mixer drum 20 in order to cool a whole inner periphery thereof.

It should be appreciated that when cold air is delivered into the fresh concrete in the rotary mixer drum 20 of the conventional agitator type concrete mixer truck (see the Japanese Patent Publication No.229507/1986, not examined), air bubbles are produced into the fresh concrete, thus deteriorating the strength of the fresh concrete so that the one end portion 22a of the air duct 22 must not be located at the intermediate or bottom portion of the rotary mixer drum 20.

The air blower 24 can be driven by a domestic electric power source or by an automobile engine so that continuous cooling may be carried out.

A cost of producing cold air by using the electric power source or automobile engine is substantially small than that of using liquefied gas.

It becomes possible to carry out a long hour continuous cooling for the fresh concrete in accordance with the agitation type concrete mixer truck

on which the rotary mixer drum 20 is rotatably mounted and driven by the truck engine (not shown).

This invention brings about another advantage that even if the mixed fresh concrete is transported at a low temperature for long hours, deterioration of the fresh concrete can be prevented.

The temperature in the rotary mixer drum 20 rises as high as above 40 degree C. under direct sunlight in summer.

As shown in FIGS. 9 and 10, heat insulating material 28 covered around an outer periphery of the rotary mixer drum 20 will prevent the temperature rise effectively, help decrease load to a motor of the air blower 24 and decrease energy consumption as well.

The heat insulating material 28 is not required for the rotary mixer drum 20 at a low temperature in winter. To this end, it is preferable to wind detachably the heat insulating material 28 around the rotary mixer drum 20.

In order to apply the heat insulating material, a monkey belt including a vinyl sheet 28b, a plurality of long and narrow heat insulating material 28b made of forming polystyrol pasted on the vinyl sheet 28b and several fixing means such as hooks or adhesive tapes 28d provided along one end portion of the vinyl sheet 28b is wound around the rotary mixer drum 20.

A bottom portion 20a of the rotary mixer drum 20, which is not exposed to the sunlight, is not covered with the heat insulating material 28, but a side peripheral portion 20b and an upper peripheral portion 20c are covered with the heat insulating material to have a remarkable heat insulating effect.

As shown in FIGS. 7 and , the heat insulating material 28 made of forming polystyrol is wound around the air duct 26 in order to prevent temperature rise and to increase energy efficiency.

A water tank 26 is mounted on the concrete mixer truck 10 to wash away the inner periphery of the rotary mixer drum 20.

In accordance with this invention, cold air is continuously delivered into the rotary mixer drum 20 to maintain the inside temperature thereof less than about 15 degree C. so that hardening time of the mixed fresh concrete may be remarkably delayed.

In FIG. 9, there is shown another embodiment of a cold and warm air blower 30 instead of the blower 24 described in the foregoing paragraphs.

More particularly, the cold and warm air blower 30 is rotatably mounted on an agitation rotary concrete mixer 10 which includes a casing 30a comprising a dehumidifier 34 located in a casing 32 and having a rotary dehumidifying plant 36 driven by a pulley 36a engaged with the plate 36 and a

driving gear 38a of a motor 38.

A heater 40 is located near the rotary dehumidifying plate 36, and an intake pipe 42 having a compressor 44 at its middle portion and an exhaust pipe 46, both being connected at an outside plate of the casing 32.

Another intake pipe 54 is connected to another side plate of the casing 32 to face the heater 40.

The dehumidifier 34 is connected through a duct 48 to a casing 52 of an air conditioner 50 which comprises a heat exchanger 54 located at an upper portion of the casing 52 and a base operating unit 56 provided at a lower portion thereof, both of the heat exchanger 54 and the base operating unit 56 being connected with each other by a duct 48.

The base operating unit 56 comprises a compressor, motor and refrigerant container (not shown).

A control panel 60 is connected to the base operating unit 56 by an electrical wire 68.

A duct fan 62 is provided at a connected portion of the duct 48 and the casing 52.

One end portion 26a of the blower duct 26 is penetrated through the casing 32 to connect with the casing 52 of the air conditioner 50.

Another duct fan 62a is provided at a connected portion of the casing 52 and the blower duct 26, and a damper 66 is provided into the blower duct 26 to locate near the duct fan 62a.

Another end portion 26a of the blower duct 26 is extended to enter partially a hopper 20a of the rotary mixer drum 20.

A drain cock 62 is provided at a bottom portion of the casing 52.

The control panel 60 is also connected to the driving unit 20b, duct fans 62, 62a, motor 38, heater 40 and compressor 44.

In FIG. 10, another cold and warm air blower 30 is mounted on a batcher plant (not shown) which includes a dehumidifier 34, an air conditioner 50 and other same units as those of the example shown in FIG. 9, but a stationery concrete mixing tank 70 is mounted on the batcher plant.

It can be understood from the drawing that a rotatable shaft 72 having a plurality of agitators 74 around the shaft 72 is extended horizontally near a bottom portion 70a to penetrate their outer end portions 72a, 72b through a pair of openings 70a, one end portions 72a being linked to a driving unit 76 provided on the bottom portion and linked to the control panel 60 by the electrical wire 68.

Owing to the season and local outer temperature, either cold or warm air is selectively delivered into the rotary concrete mixer drum 20 of the agitation concrete mixer truck 10 or the stationary mixer tank 70 of the batcher plant, thus maintaining the temperature of the mixed fresh concrete

within a predetermined range, keeping the quality of the mixed fresh concrete, and delaying hardening time thereof.

The method and device of this invention can elongate time for transporting the fresh concrete without using a concrete mixing relay base, and at the same time the ordinary scrapping operation of mixer drum 20 can be discontinued.

It should be understood that change and modifications to the preferred embodiment described above will be apparent to those skilled in the art. It is intended that the foregoing description be regarded as illustrative rather than limiting, and that it is the following claims, including all equivalents thereof, which are intended to define the scope of the invention.

CLAIMS

- (1) A method of preventing adhesion and hardening of mixed fresh concrete on a plurality of rotary blades and an inner periphery of a rotary and/or stationary mixer drum of a concrete mixer truck and/or of a concrete mixing plant which comprises:
- (a) a step of delivering continuously cold air into mixed fresh concrete in a rotary and/or stationary concrete mixer drum of a concrete mixer truck and/or a concrete mixing plant when the open air temperature outside the mixer drum is high;
 - (b) a step of delivering continuously warm air into the mixed fresh concrete in the rotary concrete mixer of the concrete mixer truck when the open air temperature outside the mixer drum is low in order to maintain the temperature of the fresh concrete within a predetermined range and to delay a hardening time of the mixed fresh concrete; and
 - (c) a step of spraying water into the rotary mixer drum.
- (2) A method of preventing adhesion and hardening of mixed fresh concrete as claimed in Claim (1) which comprises:
- (a) a step of delivering selectively and continuously cold or warm air into said rotary and/or stationary mixer drum of a concrete mixer truck and/or of a concrete mixing plant during just before or just after unloading the mixed fresh

concrete and also just before washing the inside of the rotary or stationary mixer drum; and
(b) a step of spraying water into the rotary mixer drum.

- (3) A method of preventing adhesion and hardening of mixed fresh concrete as claimed in Claim (1) which comprises:

a step of selectively and continuously delivering dehumidified cold or warm air into said rotary and/or stationary mixer drum of the concrete mixer truck and/or of the concrete mixing plant.

- (4) A device for preventing adhesion and hardening of mixed fresh concrete on a plurality of rotary blades and an inner periphery of a rotary and/or stationary mixer drum of a concrete mixer truck and/or of a concrete mixing plant which comprises:
- (a) an air blower mounted on a chassis of a concrete mixer truck to locate near a rotary mixer drum for continuously delivering cold air into said rotary mixer drum;
- (b) a blower duct provided on said rotary mixer drum, one end portion of said blower duct being connected to said blower, and another end portion located to enter partially a hopper of said rotary mixer drum; and
- (c) a water tank mounted on said chassis to locate between a driver's cab and said rotary mixer drum.

- (5) A device for preventing adhesion and hardening

of mixed fresh concrete on a plurality of rotary blades and an inner periphery of a rotary mixer drum of a concrete mixer truck as claimed in Claim (4), wherein said blower duct and said rotary mixer drum have heat insulating material covered detachably around an outer periphery of said blower duct and said rotary mixer drum.

(6) A device for preventing adhesion and hardening of mixed fresh concrete on a plurality of rotary blades and an inner periphery of a rotary mixer drum of a concrete mixer truck as claimed in Claims (4) and (5), wherein said heat insulating material is made of forming polystyrol.

(7) A device for preventing adhesion and hardening of mixed fresh concrete on a plurality of rotary blades and an inner periphery of a rotary and/or stationary mixer drum of a concrete mixer truck and/or of a concrete mixing plant as claimed in Claims (4) and (5), which comprises:

(a) a cold and warm air blower mounted on a chassis of a concrete mixer truck to locate near a rotary mixer drum for continuously and selectively delivering cold or warm air into said rotary mixer drum, said blower including a casing which comprises a dehumidifying plate driven by a pulley engaged with the plate and a driving gear of a motor, a heater located near the rotary dehumidifying plate, an intake pipe having a com-

pressor at its middle portion and an exhaust pipe, both being connected at an outside plate of said casing, another intake pipe connected to another side plate of the casing to face the heater, dehumidifier connected through a duct to a casing of an air conditioner;

(b) said air conditioner comprising a heat exchanger located at an upper portion of the casing and a base operating unit provided at a lower portion thereof, both of the heat exchanger and the base operating unit being connected with each other by a duct;

(c) said base operating unit comprising a motor and refrigerant container;

(d) a control panel connected to said base operating unit by an electrical wire, and

(e) a duct fan provided at a connected portion of the duct and the casing, one end portion of the blower duct being penetrated through the casing to connect with the casing of the air conditioner, another duct fan provided at a connected portion of the casing and the blower duct, a damper provided into the blower duct to locate near the duct fan, another end portion of the blower duct extending to enter partially a hopper of the rotary mixer drum, a drain cock provided at a bottom portion of the casing, said control panel being connected to the driving unit, duct fans, motor heater and

compressor.

- (8) A device for preventing adhesion and hardening of mixed fresh concrete on a plurality of rotary blades and an inner periphery of a rotary mixer drum of a concrete mixer truck as claimed in Claim (7), wherein a heat insulating layer is wound around the rotary mixer drum.

A METHOD AND DEVICE FOR IMPROVING THE
QUALITY OF FRESH CONCRETE AND PREVENTING
ADHESION AND HARDENING OF FRESH CONCRETE
IN A ROTARY MIXER DRUM OF A CONCRETE MIXER
TRUCK AND/OR IN A CONCRETE MIXING PLANT

ABSTRACT

A method of and device for preventing adhesion and hardening of mixed fresh concrete on a plurality of rotary blades and an inner periphery of a rotary and/or stationary mixer drum of a concrete mixer truck and/or of a concrete mixing plant which comprises delivering selectively and continuously cold air into mixed fresh concrete in a rotary and/or stationary concrete mixer drum of a concrete mixer truck and/or a concrete mixing plant when the open air temperature outside the mixer drum is high, delivering continuously warm air into the mixed fresh concrete in the rotary concrete mixer of the concrete mixer truck when the open air temperature outside the mixer drum is low in order to maintain the temperature of the fresh concrete within a predetermined range and to delay a hardening time of the mixed fresh concrete, and spraying water into the rotary mixer drum.