

**MINERAL COMPOSITION BASED ON A MIXED SOLID
PHASE OF CALCIUM AND MAGNESIUM CARBONATES
AND PROCESS FOR PREPARING SUCH A COMPOSITION**

5 The present invention relates to a mineral composition containing a mixed solid phase of calcium and magnesium carbonates, to a process for preparing such composition and the use thereof.

 Synthetic calcium carbonates are known chiefly for uses as fillers (paper, paint, plastics....). For these applications it is particularly known to synthesize
10 dense carbonates, calcite in particular having scalenohedral, rhombohedral or prismatic morphology or aragonite having acicular morphology.

 Compositions containing synthetic calcium and magnesium carbonates are also known, used in particular in the field of paper manufacture and plastic materials.

15 For example compositions can be cited according to patent applications EP-A-2322581 and DE-A-3245103. The first discloses plate-like particles of magnesium carbonates in the form of hydromagnesite in a mixture with colloidal calcium carbonate, well-suited as fillers for paper or plastic materials. The second discloses scalenohedral particles of calcium carbonate (i.e. of rice grain shape) in
20 a mixture with plate-like particles of basic magnesium carbonate. The respective carbonates do not form a composite.

 The compositions described in European patent EP-B-0526121 are formed of a uniform mixture of particles of calcium carbonate having an acicular aragonite crystalline structure with columnar particle configuration and particles of slaked
25 magnesium carbonate with plate-like particle configuration. These compositions are obtained by carbonatation of aqueous solutions of calcium and magnesium hydroxides using a complex process requiring the use of a variable CO₂ flow rate.

 A Japanese patent application JP-63-123810 is also known which describes a process for producing a mineral composition containing a mixed solid phase of
30 calcium and magnesium carbonates. This process comprises carbonatation of an aqueous suspension of basic magnesium carbonate to which is continuously added an aqueous suspension of magnesium hydroxide and calcium hydroxide. Carbonatation is conducted with fast CO₂ flow rate which gives rise to the

formation of spherical, porous particles of basic magnesium carbonate on the seed nuclei of basic magnesium carbonate initially contained in suspension, the pores of these particles being partly filled with calcium carbonate. This composition is very dense and intended for the production of fillers for the manufacturing of paper, paints, plastic materials, or for the medical sector.

It is the objective of the present invention to develop mineral compositions particularly intended for the building industry. In this sector there is a need for example to develop mineral compositions able to offer an alternative of interest to polyurethane or phenolic foams usually used in heat insulation panels for example.

Mineral materials have the advantage compared with organic foams of having a longer lifetime, distinctly improved flame resistance and reduced environmental impact. Whereupon it is desirable that these new mineral compositions should have thermal properties similar to those of known foam materials. There is therefore a need to develop mineral materials having high, controlled volume porosity and low density whilst maintaining acceptable mechanical properties (resistance to bending, to compression, to impacts...).

In a porous medium, by thermal conductivity is meant a value λ which is the sum of i) the ratio of the thermal conductivity of the gas contained in the pores to the volume fraction of the pores in the composition and of ii) the ratio of the thermal conductivity of the solid material to the volume fraction of this solid material in the composition. The thermal conductivity of gases is generally in the order of 10^{-2} W/K/m and that of solids in the order of 1 to 10^2 W/K/m; the larger the volume fraction of gas (and hence of pores) in the composition the lower the thermal conductivity of the composition and the better the insulating property of the material.

A process to prepare a mineral composition containing a mixed solid phase of calcium and magnesium carbonates has already been provided, starting from crude dolomite that is calcined and then at least partly slaked (international patent application WO2013139957).

To solve the problem set forth above, there is provided according to the invention a process to prepare a mineral composition containing a mixed solid phase of calcium and magnesium carbonates, comprising:

-i) preparing, in an aqueous phase, a solid phase containing at least one calcium compound selected from among calcium hydroxide ($\text{Ca}(\text{OH})_2$), calcium carbonate and the mixtures thereof and at least one magnesium compound selected from among magnesium oxide (MgO), magnesium hydroxide ($\text{Mg}(\text{OH})_2$), at least partly slaked dolomite and the mixtures thereof, the weight of said solid phase being between 5 and 15 % of the total weight of the suspension;

-ii) carbonatation of said solid phase in suspension by injecting a CO_2 -containing gas into said suspension heated to a temperature of 55 to 90 °C at a CO_2 flow rate of 2.5 to 15 $\text{dm}^3/\text{min}/\text{kg}$ of said solid phase of the suspension, with decreasing of the pH of the suspension down to a value below 9 and stabilisation of the electrical conductivity of the suspension, carbonatation being halted as soon as this electrical conductivity stabilisation is observed; and

-iii) obtaining a mixed solid phase of synthetic calcium and magnesium carbonates formed of a crystallized calcic portion and a plate-like crystallized magnesian portion, the crystals of the calcic portion and those of the magnesian portion being aggregated in the form of composite aggregates, these aggregates themselves being at least partly agglomerated in the form of agglomerates, said calcic portion comprising at least one carbonate selected from the group formed by calcite, aragonite and the mixtures thereof, said magnesian portion comprising hydromagnesite in plate-like form, said mixed solid phase of carbonates of said mineral composition having a bulk density of 250 kg/m^3 or lower and of 80 kg/m^3 or higher measured as per standard EN 459.2.

The process of the invention has the advantage of being simple to implement and allows carbonatation to be performed in a single step.

In the meaning of the present invention, by stabilisation of the electrical conductivity is meant a period longer than 15 minutes during which the electrical conductivity measured in the suspension does not vary by more than 0.5 mS/cm upwards or downwards, preferably a period of 30 minutes during which the electrical conductivity measured in the suspension does not vary by more than 0.5 mS/cm upwards or downwards, and advantageously a period of 30 minutes during which the electrical conductivity measured in the suspension does not vary by more than 0.3 mS/cm upwards or downwards. Depending on operating conditions

this stabilisation phase may of greater or lesser length. In some variants of the process it may last up to 60 minutes and even longer.

If said at least one calcic compound is in the form of calcium carbonate, it may advantageously be a calcium carbonate of filler type ($d_{98} < 150 \mu\text{m}$, preferably $d_{98} < 50 \mu\text{m}$), a finely ground calcium carbonate (Ground Calcium Carbonate - GCC) e.g. with $d_{98} < 50 \mu\text{m}$, preferably $d_{98} < 20 \mu\text{m}$) a synthetic calcium carbonate (Precipitated Calcium Carbonate – PCC) or a residue derived from incomplete calcining of limestone.

If said at least one calcic compound is in the form of calcium hydroxide, this hydroxide is obtained by slaking calcium oxide. According to one embodiment of the invention, this slaking is obtained with said aqueous phase during said preparation of a suspension. According to another embodiment of the invention, before said preparation of a suspension, the process comprises preliminary at least partial slaking of calcium oxide (CaO) to said calcium hydroxide. This preliminary slaking can dry slaking or near-dry slaking. It may also be wet slaking to produce a suspension, in particular a milk of lime, which is then optionally screened, milled and/or diluted for said preparing of the suspension.

This preliminary slaking is advantageously performed with water, water containing at least one additive or water already containing at least a portion of said at least one magnesium compound that is part of said solid phase in suspension.

The calcium oxide CaO used for this slaking may be quicklime derived for example from calcining limestone, this calcining possibly having been incomplete, the lime then containing a fraction of calcium carbonate.

If said at least one magnesium compound is in the form of magnesium oxide, this magnesium oxide can be obtained using conventional MgO synthesis methods or from the calcining of a magnesium ore (e.g. dolomite or magnesite).

If said at least one magnesium compound is in the form of magnesium hydroxide this can be obtained using conventional synthesis methods of $\text{Mg}(\text{OH})_2$ or advantageously by at least partial slaking of MgO. At least partly slaked dolomite has the general formula $a\text{Ca}(\text{OH})_2 \cdot x\text{Mg}(\text{OH})_2 \cdot y\text{MgO}$ where a, x and y are molar coefficients in particular with $0.8 \leq a/(x+y) \leq 1.2$. This dolomite can be obtained by at least partial slaking of dolomitic quicklime.

According to one preparation mode of the invention, this at least partial slaking of the magnesium compound is ensured, during said preparation of a suspension, by said aqueous phase.

According to another embodiment of the invention the process, before said preparation of a suspension, comprises prior at least partial slaking of the magnesium compound in particular magnesium oxide (MgO), to said magnesium hydroxide. This prior slaking can be dry slaking or near-dry slaking. Said prior slaking may also be wet slaking to produce a milk of magnesia which is then optionally screened, milled and/or diluted for said preparing of the suspension.

Said prior slaking is advantageously performed with water, water containing at least one additive or water already containing at least a portion of said at least one calcic compound that is part of said solid phase in suspension.

Preferably the solid phase of the suspension has a Ca/Mg molar ratio of between 0.4 and 4.0. This molar ratio is advantageously higher than 1.2. In particular, it may also be 3.0 or lower, more particularly 2.5 or lower.

It is to be noted that in the process of the invention, there is no provision for the placing of solely dolomite in suspension, whether or not slaked.

Preferably, said at least one magnesium compound forming part of the solid phase of the suspension is selected from among magnesium oxide, magnesium hydroxide and the mixtures thereof. In this case the prepared suspension has a solid phase which does not contain any dolomite whether or not slaked.

Provision can also be made so that said at least one magnesium compound is at least partly slaked dolomite, optionally in a mixture with magnesium oxide, magnesium hydroxide or a mixture thereof, but so as to obtain a Ca/Mg molar ratio higher than 1.2 and of 4.0 or lower, in particular 3.0 or lower, optionally 2.5 or lower in said solid phase of the suspension.

Calcium carbonates generally have a smaller specific surface area than hydromagnesite and a higher bulk density. As a result over and above a certain Ca/Mg ratio, in particular beyond $\text{Ca/Mg} = 4.0$, the proportion of calcium carbonate in the product obtained with the process of the present invention becomes too high to allow the achieving of specific surface areas higher than $10 \text{ m}^2/\text{g}$ and of bulk densities lower than 250 kg/m^3 .

Carbonatation of the solid phase in suspension is advantageously conducted at a temperature between 60 and 80 °C, preferably 70 °C or lower, more particularly 65 °C or lower. Carbonatation at a lower temperature in particular at a temperature below 55°C, more particularly below 50 °C, generally promotes the formation of a magnesium carbonate in nesquehonite form rather than hydromagnesite form. Therefore the mixed solid phase of carbonates of said mineral composition thus formed generally has a bulk density that is too high, in particular higher than 250 kg/dm³ even higher than 300 kg/dm³ together with thermal conductivity that is also too high.

At this carbonatation step it is preferably provided that the CO₂ should be injected pure at 100 volume % or diluted in a carrier gas, air in particular, at a CO₂ volume concentration in the carrier gas of 15 to 50 %, in particular 15 to 25 %. The total injection rate (carrier gas and CO₂) may advantageously be in the order of 15 to 55 dm³/min/kg of solid phase in suspension. The flow rate of CO₂ (excluding the carrier gas) is advantageously between 2.5 and 9.5 dm³/min/kg in particular between 5 and 9.5 dm³/min/kg of solid phase in suspension.

At this carbonatation step (step ii of the process of the present invention) the changes in the electrical conductivity of the suspension are dependent upon the choice of solid phase in the suspension.

If said calcic compound is in the form of calcium hydroxide or contains calcium hydroxide, the electrical conductivity starts to decrease rapidly and sharply translating precipitation of calcium carbonate. On the other hand, when said at least one calcic compound is exclusively in the form of calcium carbonate, it does not undergo any reaction during carbonatation and therefore has no influence on the electrical conductivity of the suspension.

Carbonatation of the magnesium compound is accompanied by an increase in the electrical conductivity of the suspension initially on account of the formation of magnesium bicarbonate ions. In parallel with this dissolution the precipitation of the bicarbonate ions to hydromagnesite takes place which, at a second stage, leads either to a decrease in electrical conductivity or at least to stabilisation thereof. This increase followed by decrease or stabilisation related to carbonatation of the magnesium compound occurs right at the start of the carbonatation step when the calcic compound is in calcium carbonate form, or

after precipitation of the calcium carbonate when said calcic compound is initially in the form of calcium hydroxide.

At all events, the pH of the suspension (initially close to 9 when the calcic compound is in the form of calcium carbonate and between 12 and 13 when the calcic compound is in calcium hydroxide form) decreases throughout the carbonatation reaction of the solid phase in suspension to reach values lower than 9, in particular lower than 8.5 and more particularly lower than 8.3. Even if this pH is reached, the reaction is only halted however when the afore-described stabilisation step of electrical conductivity is observed.

During placing in suspension and carbonatation the suspension may advantageously be held under agitation e.g. at a speed of 350 to 650 rpm.

According to one embodiment of the invention, after carbonatation the process further comprises a solid-liquid separation step between said carbonatated mixed solid phase and said aqueous phase of said suspension.

Advantageously the mixed solid phase can then be at least partly dried.

The present invention also relates to a mineral composition containing a mixed solid phase of synthetic calcium and magnesium carbonates, which can be prepared using the process of the invention. This composition is formed of a crystallized calcic portion and a crystallized magnesium portion in plate-like form, the crystals of the calcic portion and those of the magnesium portion being aggregated in the form of composite aggregates, these aggregates themselves being at least partly agglomerated in the form of agglomerates, said calcic portion comprising at least one carbonate selected from the group formed by calcite, aragonite and the mixtures thereof, said magnesium portion comprising hydromagnesite in plate-like form, said mixed solid phase of carbonates of said mineral composition having a bulk density of 250 kg/m^3 or lower and 80 kg/m^3 or higher, measured as per standard EN 459.2, and a Ca/Mg molar ratio of between 0.4 and 4.0. Advantageously in this composition the mixed solid phase has a Ca/Mg molar ratio higher than 1.2. Advantageously the Ca/Mg molar ratio may be 3 or lower and in particular 2.5 or lower.

Preferably, the calcic portion of said mineral composition contains less than 30 weight %, more preferably less than 20 weight %, further preferably less than 10 weight % even less than 5 weight % of aragonite.

Advantageously the calcic portion of said mineral composition is essentially formed of calcite.

The composition of the present invention may further comprise an aqueous phase, said composition then being in the form of a suspension or paste. It may
 5 also be in solid form, in particular powder form and have a humidity level of between 0 and 4 %, in particular between 0.1 and 4 %, more preferably 3 % of lower, further preferably 2 % or lower by weight of water relative to the total weight of the composition.

According to one embodiment of the invention, said mixed solid phase is
 10 milled to obtain particles of size 2 mm or smaller.

Calcite and aragonite are two crystalline structures of calcium carbonate CaCO_3 . Hydromagnesite also called basic magnesium carbonate has the formula $\text{Mg}_5(\text{CO}_3)_4(\text{OH})_2 \cdot 4\text{H}_2\text{O}$ or $4\text{MgCO}_3 \cdot \text{Mg}(\text{OH})_2 \cdot 4\text{H}_2\text{O}$. In X-ray diffraction databases (International Centre for Diffraction Data (ICDD) database), hydromagnesite
 15 corresponds to datasheets carrying references 00-025-0513 (monoclinic) and 01-070-1177 (orthorhombic). It should not be confused with magnesite, a magnesium carbonate of formula MgCO_3 , or with nesquehonite a slaked magnesium carbonate of formula $\text{MgCO}_3 \cdot 3\text{H}_2\text{O}$ which are to be avoided according to the invention.

20 By the expression "bulk density" according to the invention is meant the ratio between the mass of the material and the apparent volume of all agglomerates or grains measured in accordance with standard EN 459.2.

The low bulk density of the composition obtained according to the invention results from a large porous volume i.e. a high incorporation of gas in the mixed
 25 solid phase which has several layers of porosity: within the crystal aggregates, within the agglomerates of aggregates and even between the agglomerates or grains.

By the expression "porous volume" according to the invention is meant a global porous volume corresponding to the different porosities described above
 30 and measured by mercury intrusion porosimetry.

It is generally acknowledged that the bulk density of a standard hydromagnesite is between 200 and 400 kg/m^3 . Synthetic calcium carbonates have a bulk density usually between 250 and 600 kg/m^3 .

Against every expectation, the composition of the invention containing a mixed solid phase of calcium carbonate and hydromagnesite has a bulk density lower than 250 kg/m^3 for a Ca/Mg molar ratio of between 0.4 and 4.

5 This result is all the more surprising as it allows reduced thermal conductivity values to be reached, for the mineral composition of the invention, in the order of 25 to 45 mW/K/m, in particular in the order of 35 to 40 mW/K/m.

The mixed solid phase of the composition of the invention therefore has particular aspects that are not found in usual pure phases of hydromagnesite or synthetic calcium carbonate type.

10 The explanation would appear to lie in the fact that the mixed solid phase of calcium and magnesium has a mixed crystalline structure which provides for a better compromise between porosity, extent of aggregation and organisation of crystals in relation to one another. This compromise results in low bulk density and therefore in low thermal conductivity. This effect can be obtained using the
15 process of the invention which is particularly designed to reach the particular characteristics of low bulk density and hence low thermal conductivity of the solid phase of the composition according to the invention.

The mixed solid phase of the mineral composition according to the invention may have a specific surface area of $10 \text{ m}^2/\text{g}$ or higher, more particularly higher
20 than $12 \text{ m}^2/\text{g}$ and preferably $15 \text{ m}^2/\text{g}$ or higher and possibly reaching $25 \text{ m}^2/\text{g}$.

By the expression "specific surface area" used in the present invention is meant the specific surface area measured by nitrogen adsorption manometry and calculated using the Brunauer, Emmett and Teller model (BET method).

The mixed solid phase of the composition of the invention therefore has an
25 unexpected advantage in that its specific surface area is larger than that of usual ground calcium carbonates (GCCs) or synthetic calcium carbonates which have a specific surface area in the order of 3 to $15 \text{ m}^2/\text{g}$, most often less than $10 \text{ m}^2/\text{g}$.

In the composition of the invention the hydromagnesite content is between 5 and 80 weight %, advantageously between 5 and 71 weight %, preferably
30 between 15 and 50 weight % and more preferably between 25 and 35 weight % relative to the weight of said mixed solid phase.

Advantageously said calcic portion is contained in the composition of the invention in an amount ranging from 20 to 85 %, advantageously 29 to 85 %,

preferably 50 to 75 weight % in particular 60 to 70 weight % relative to the total weight of said mixed solid phase. The total magnesium portion represents an amount ranging from 5 to 71 %, advantageously 15 to 50 %, preferably 20 to 40 % and more preferably 25 to 35 weight % of the total weight of the mixed solid phase.

In a dry powder of a preferred composition of the invention the following components can be distinguished (in weight %):

- calcium carbonate CaCO_3 (calcite and optionally traces of aragonite): 29-85 %;
- portlandite Ca(OH)_2 : 0 - 2 %;
- hydromagnesite $\text{Mg}_5(\text{CO}_3)_4(\text{OH})_2 \cdot 4\text{H}_2\text{O}$: 5 - 71 %
- brucite Mg(OH)_2 : 0 - 10 %, preferably 0 - 7 % more preferably 0 - 3%;
- periclase MgO : 0 - 2 %;
- magnesium oxyhydroxide $\text{Mg}_3\text{O}_2(\text{OH})_2$: 0 - 5 %, preferably 0 - 2 %.

Preferably, in the mineral composition of the invention, the bulk density of the mixed solid phase is 220 kg/m^3 or lower, more preferably 200 kg/m^3 or lower, even 180 kg/m^3 or lower.

In one advantageous composition of the present invention, the mixed solid phase of the mineral composition has thermal conductivity of between 25 and 45 mW/K/m, in particular between 28 and 40 mW/K/m.

According to one advantageous embodiment of the invention, the proportion of the mixed solid phase is in the range of 5 to 65 weight % relative to the total weight of the composition and a liquid medium is contained in a proportion in the range of 35 to 95 weight % relative to the total weight of the mineral composition.

According to one advantageous embodiment of the invention, the mixed solid phase is composed of agglomerates milled to particles of size 2 mm or smaller, preferably 1 mm or smaller, more preferably of $200 \mu\text{m}$ or smaller and in particular of $80 \mu\text{m}$ or smaller. Advantageously these agglomerates have a d_{50} larger than $5 \mu\text{m}$, advantageously larger than $7 \mu\text{m}$ and a d_{95} larger than $10 \mu\text{m}$, advantageously larger than $20 \mu\text{m}$.

According to the invention, the aggregates of the mixed solid phase are formed of a calcic core on which hydromagnesite plates are aggregated.

The aggregates may have substantially spherical morphology.

The mean size of 80 % of the volume of the aggregates may be in the order of 1 to 30 μm , preferably 3 to 20 μm and in particular 5 to 15 μm . The plate width of 80 % of the volume of the hydromagnesite plates is in the order of 0.5 to 10 μm , preferably 0.5 to 5 μm .

5 The hydromagnesite plates are not aggregated at random. The aggregates of the invention generally have shape resembling a desert rose.

A dry powder having a preferred mineral composition of the invention could have the following characteristics:

- bulk density: 100 - 250 kg/m^3
- 10 - thermal conductivity: 25 - 45 mW/K/m
- BET specific surface area: 10 - 35 m^2/g
- < 100 μm pore volume: 1 - 5 cm^3/g
- humidity: 0 - 4 %.

15 The composition of the invention may further comprise additives facilitating the preparation filtration, storage and/or grinding (de-agglomeration) of said composition, in particular to improve the stability of the suspensions of the invention.

Advantageously, the mixed solid phase can be milled or de-agglomerated to obtain particles of size 2 mm or smaller, preferably 1 mm or smaller, more preferably 200 μm or smaller and in particular 80 μm or smaller. The drying operation can be performed simultaneously with de-agglomeration or grinding.

The present invention also concerns the use in building materials of a mineral composition of the invention or of a composition obtained using the process of the invention.

25 This composition can particularly be contemplated as raw material for the preparation of thermal insulation materials, in particular thermal insulation panels in the form of mineral sheets or foams, or in mortars, renderings, concretes in particular as thermal insulating component.

30 One use of the composition of the invention that can be envisaged is also as filler in polymer materials, rubbers, paper, paints, cosmetic products, in particular as low density and/or high porosity mineral fillers. This composition can also be envisaged as viscosifying or rheological agent e.g. in mineral suspensions, glues, bitumen or asphalt. The use thereof can be envisaged for water or gas

treatment or in the field of catalysis or as carrier for perfumes, flavourings, active ingredients to ensure gradual and/or delayed release into their medium of use;

Other details and particular aspects of the invention will become apparent from the description given below as non-limiting examples in which the percentages given are weight percentages when not specified.

Appended Figures 1, 5, 8 and 10 give the curves of pH and electrical conductivity changes throughout the carbonatation reaction in examples 1, 4, 6 and 7. Figures 2, 3, 4A, 4B, 6, 7, 9 and 11 are scanning electron microscope (SEM) images illustrating the crystalline structure of the compositions obtained in Examples 1 to 7.

In the examples, bulk density was measured in accordance with standard EN 459.2. When measuring thermal conductivity, which is dependent on the extent of packing of the sample, a second non-normalised density value is obtained which must be indicated to have knowledge of the measurement conditions of thermal conductivity.

Thermal conductivity was measured on bulk material following the teachings of standards ISO 8301 or NF EN 12664. More specifically, thermal conductivity such as indicated in the present invention was measured on the mixed solid phase of the mineral composition obtained according to the invention i.e. on a powder previously dried at 105 °C and having humidity lower than 4 weight %. If the composition of the invention was in the form of a suspension or paste, said powder was obtained by filtration, drying and grinding of this composition.

Measurement was carried out in a flow meter (Netzsch Heat Flow Meter HFM 463/3IE Lambda Series) on bulk powder placed in a mould of larger size than the flow meter. The preparation of the powder bed in the mould was such that the surface of the powder bed was as flat as possible and the density of the powder bed, on which thermal conductivity was to be measured, was equal to the bulk density previously measured on each powder following the method described in standard EN 459.2 to within 20 %, if possible to within 15 %. A single measurement was made at 20 °C with a 20 °C temperature difference between the two sides of the sample (i.e. 10 °C for one side and 30 °C for the other).

The specific surface area was measured using the BET method based on measurement of nitrogen adsorption manometry, and $< 100 \mu\text{m}$ pore volume was measured by mercury intrusion.

5 **Example 1: Carbonatation at 70 °C of a suspension of magnesium hydroxide and ground calcium carbonate with Ca/Mg (mol) in the order of 0.5**

A/ Raw materials

The ground calcium carbonate and magnesium hydroxide were industrial products. According to chemical analysis by X-ray fluorescence spectrometry with
 10 additional thermogravimetric analysis, the magnesium hydroxide contained $95.0 \pm 0.5 \%$ $\text{Mg}(\text{OH})_2$, $< 1.0 \%$ MgO , $2.5 \pm 0.5 \%$ CaCO_3 , and impurities chiefly SiO_2 , Al_2O_3 and Fe_2O_3 . It was in the form of a suspension containing 53 % solids and the remainder water. The ground calcium carbonate contained $> 95 \%$ CaCO_3 and impurities again chiefly SiO_2 , Al_2O_3 , Fe_2O_3 . This calcium carbonate was a natural
 15 limestone which was simply industrially ground. Laser measurement of particle size distribution gave a d_{98} value in the order of $12 \mu\text{m}$ ($\pm 2 \mu\text{m}$).

B/ Preparation of the suspension

4.9 of ground calcium carbonate and 5.8 kg of magnesium hydroxide (dry
 20 equivalent) were placed in suspension in about 80 dm^3 water (water provided by the suspension of $\text{Mg}(\text{OH})_2$ completed with mains water) to obtain a mixed suspension. The weights of ground calcium carbonate and magnesium hydroxide were determined to obtain a Ca/Mg molar ratio in the order of 0.5. The dry extract (solid content) of this suspension was 10.7 weight %. This suspension was placed
 25 in a reactor of 100 dm^3 capacity equipped with a double jacket and provided with an agitation system and heating system. This reactor was also equipped with a pH probe, electrical conductivity probe and temperature probe. The suspension was kept under agitation and the temperature brought to $70 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$.

30 C/ Carbonatation

When the suspension reached the temperature of $70 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$, injection of CO_2 was initiated in the form of a gas composed of 15 % by volume CO_2 and 85 % by volume air. The CO_2 carrier gas was injected via a nozzle located at the bottom

of the reactor. The gas flow rates in the suspension corresponded to 55 dm³/min of CO₂ and 314 dm³/min of air i.e. 5.1 dm³/min CO₂ and 29.3 dm³/min air per kg of solid in the starting suspension (ground calcium carbonate and magnesium hydroxide). Throughout carbonatation the electrical conductivity of the suspension and its pH were recorded. The pH of the suspension before carbonatation was 9.0. Throughout carbonatation the conversion of magnesium hydroxide to carbonate was accompanied by a) a reduction in pH and b) an increase up to a maximum followed by a decrease and then stabilisation of electrical conductivity (Figure 1). The reaction was halted after a stabilisation time of 1 hour of electrical conductivity at 3.6 mS/cm. After this carbonatation, the pH of the suspension was only 8.0. The increase in electrical conductivity at the start of the carbonatation reaction indicates the formation of soluble magnesium bicarbonate. The following decrease corresponds to precipitation of the hydromagnesite.

D/ Post-synthesis treatments

After carbonatation, the distribution of particle size in suspension was measured by laser particle size measurement by placing a few drops of the suspension in methanol. The d₅₀ of this suspension was 11.6 µm and its d₉₅ 26.3 µm. The suspension was then filtered through a Büchner, placed in an oven at 105°C to dry for 48 hours and the dried solid was milled to obtain a powder of particle size smaller than 2 mm and having humidity of less than 3 %.

According to X-ray diffraction analysis with additional thermogravimetric analysis the product obtained contained 56 ± 2 % CaCO₃ (calcite), 40 ± 2 % hydromagnesite and 4 ± 1 % brucite Mg(OH)₂. Its bulk density measured according to standard EN 459.2 was 173 kg/m³. The specific surface area was 16.5 m²/g (BET method based on nitrogen adsorption manometry after degassing a few hours at 190°C). Thermal conductivity was 37.2 mW/K/m for a density at the time of measurement of 185 kg/m³. Figure 2 is a scanning electron microscope image of the product obtained. This photograph shows that the (plate-like) hydromagnesite formed by carbonatation of the magnesium hydroxide has crystallized on the surface of the particles of ground calcium carbonate.

Example 2: Carbonatation at 70 °C of a suspension of magnesium hydroxide and ground calcium carbonate with Ca/Mg (mol) in the order of 0.9.

This example is fully similar to Example 1, solely the weights of ground calcium carbonate and magnesium hydroxide are different.

5 This time 6.5 kg of ground calcium carbonate and 4.2 kg of magnesium hydroxide (dry equivalent) were placed in suspension in about 80 dm³ water (water provided by the suspension of Mg(OH)₂ completed with mains water) to obtain a mixed suspension. The weights of ground calcium carbonate and magnesium hydroxide were determined to obtain a Ca/Mg molar ratio this time in the order of
10 0.9. The dry extract (solid content) of this suspension was 11.3 %.

 This suspension was placed in the same reactor as used in Example 1 and carbonatation was conducted under exactly similar conditions to those of the carbonatation described in Example 1. As described in Example 1, the electrical conductivity of the suspension increased right at the start of the carbonatation
15 reaction, reached a maximum before showing a distinct decrease and then stabilising. Again the reaction was halted after stabilisation of the electrical conductivity of the suspension for 40 minutes at 4.0 mS/cm ($\pm$ 0.1 mS/cm). At this point the pH of the suspension initially of 9.1 dropped to 8.1.

 After carbonatation, the particle size distribution in the suspension was
20 again measured and showed a d₅₀ value of 12.4 μ m and d₉₅ value of 30.1 μ m. The suspension was then filtered, dried and the solid obtained was milled as in Example 1.

 According to X-ray diffraction analysis with additional thermogravimetric analysis, the product obtained contained 70 $\pm$ 2 % CaCO₃ (calcite), 26 $\pm$ 2 % hydromagnesite and 4 $\pm$ 1 % brucite. Its bulk density measured according to
25 standard EN 459.2 was 211 kg/m³. The specific surface area was 12.3 m²/g. Thermal conductivity was 38.1 mW/K/m for a density at the time of measurement of 225 kg/m³. Figure 3 illustrates the product obtained. This photograph, as in Figure 2, shows that the hydromagnesite formed by carbonation of magnesium
30 hydroxide has crystallized on the surface of the particles of ground calcium carbonate.

Example 3: Carbonatation at 70 °C of a suspension of magnesium hydroxide and ground calcium carbonate with Ca/Mg (mol) in the order of 1.6.

This example is fully comparable with Examples 1 and 2. The weights of ground calcium carbonate and magnesium hydroxide were again different and the
5 ground calcium carbonate was derived from another source this time with a d_{98} in the order of 36 μm .

This time, 7.9 kg of ground calcium carbonate and 2.8 kg of magnesium hydroxide (dry equivalent) were placed in suspension in about 80 dm^3 of water (water provided by the suspension of $\text{Mg}(\text{OH})_2$ completed with mains water) to
10 obtain a mixed suspension. The weights of ground calcium carbonate and magnesium hydroxide were determined this time to obtain a Ca/Mg molar ratio in the order of 1.6. The dry extract (solid content) of this suspension was 12.5 %.

This suspension was placed in the same reactor as used in the preceding examples and carbonatation was performed under exactly similar conditions to
15 those described in Examples 1 and 2. As previously, the electrical conductivity of the suspension increased right at the start of the carbonatation reaction, reached a maximum before distinctly decreasing and then stabilising. The reaction was halted when the electrical conductivity was stable at 3.4 mS/cm ($\pm 0.2 \text{ mS/cm}$) for 30 minutes. At this moment the pH of the suspension, initially 9.4, dropped to 8.3.

20 After carbonatation the distribution of particle size in suspension was again measured and gave a d_{50} value of 9.3 μm and d_{95} value of 22.7 μm . The suspension was then filtered, dried and the solid obtained was milled as in the above examples.

According to X-ray diffraction analysis with additional thermogravimetric
25 analysis the product obtained contained $59 \pm 2 \%$ CaCO_3 (calcite), $37 \pm 2 \%$ hydromagnesite and about $4 \% \pm 1 \%$ brucite $\text{Mg}(\text{OH})_2$. Its bulk density measured according to standard EN 459.2 was 214 kg/m^3 . The specific surface area was $11.5 \text{ m}^2/\text{g}$ (BET method based on nitrogen adsorption manometry). Thermal conductivity was 37.6 mW/K/m for a density at the time of measurement of 222
30 kg/m^3 . Figures 4A and 4B illustrate the product obtained. These photographs show that the product is homogeneous and that the hydromagnesite plates again cover the particles of ground calcium carbonate.

Example 4: Carbonatation at 60 °C of a suspension of dolomite and ground calcium carbonate with Ca/Mg (mol) in the order of 1.5

This example was inspired from the preceding examples but this time the ground calcium carbonate was placed in suspension not with a suspension of
 5 $\text{Mg}(\text{OH})_2$ but with a previously prepared suspension of at least partly slaked dolomite.

At a first step 5.8 kg of dolomitic quicklime of particle size 0-3 mm were placed in 23.0 kg of water heated to 55 °C. This suspension was placed under agitation for 30 minutes, time during which the dolomite was at least partly slaked.
 10 After a slaking time of 30 minutes, an additional 20.0 kg of water and 3.0 kg of ground calcium carbonate (same GCC as in Example 3) were added and agitation continued for 20 minutes. The weights of dolomite and ground calcium carbonate were determined to obtain a Ca/Mg ratio of 1.5. The suspension obtained was passed through a 200 μm screen to remove the coarsest particles (in particular
 15 unfired particles initially contained in the dolomitic quicklime). The screened suspension was then diluted to a dry extract (solid content) of 9.4 % and 80 dm^3 of this suspension were placed in the 100 dm^3 reactor already used in all the preceding examples.

Carbonatation this time was conducted at 60 °C. The CO_2 flow rate was 45
 20 dm^3/min and the air flow rate 180 dm^3/min , i.e. a volume concentration of 20 % CO_2 in the gas, i.e. also about 6.0 dm^3/min CO_2 and 24.0 dm^3/min air per kg of solid contained in the suspension before carbonatation.

Throughout carbonatation (Figure 5), the electrical conductivity of the suspension started by decreasing and this decrease was accompanied by a drop
 25 in pH from 12.2 to 9.4. These results are proof of carbonatation of the calcic portion of the at least partly slaked dolomite to form a calcium carbonate (PCC) *in situ* in addition to the starting ground calcium carbonate (GCC). After some slowing of the reaction, the electrical conductivity again slowly increased before finally stabilising for 20 minutes at 8.0 mS/cm (± 0.1 mS/cm). This second phase
 30 of the reaction was accompanied by a second drop in pH down to 8.1 and translated the competition between formation of hydromagnesite and dissolution of $\text{Mg}(\text{OH})_2$ (and possibly of already-formed hydromagnesite) to bicarbonate ions of Mg.

After carbonatation, the distribution of particle size in suspension was again measured and gave a d_{50} value of 8.8 μm . The suspension was then filtered, dried and the solid obtained was milled as in the above examples.

According to X-ray diffraction analysis with additional thermogravimetric analysis the product obtained contained $64 \pm 2 \%$ CaCO_3 (calcite), $32 \pm 2 \%$ hydromagnesite, the remainder being composed of $\text{Mg}(\text{OH})_2$ and $\text{Mg}_3\text{O}_2(\text{OH})_2$. Its bulk density measured according to standard EN 459.2 was 161 kg/m^3 . The specific surface area was $17.7 \text{ m}^2/\text{g}$ (BET method based on nitrogen adsorption manometry). Thermal conductivity was 36.4 mW/K/m for a density at the time of measurement of 177 kg/m^3 . Figure 6 illustrates the product obtained. This photograph again shows that the crystallization hydromagnesite plates takes place on the surface of the particles of CaCO_3 (PCC formed *in situ* and GCC).

Example 5: Carbonation at 60 °C of a suspension of dolomite and ground calcium carbonate with Ca/Mg (mol) in the order of 2.0.

This example is fully comparable with Example 4 above but this time with a Ca/Mg ratio in the order of 2.0.

At a first step 4.7 kg of the same dolomitic quicklime used in Example 4 were placed in 19 kg of water heated to 55 °C. This suspension was again left under agitation for 30 minutes. After the slaking time of 30 minutes, an additional 20 kg of water and 4.7 kg of ground calcium carbonate (GCC the same as in Example 4) were added and agitation continued for 20 minutes. As previously, the suspension obtained was subjected to 200 μm screening. It was then diluted to a dry extract of 11.4 %. 80 dm^3 of this suspension were placed in the 100 dm^3 reactor.

Carbonatation was again performed at 60 °C with the same flow rates of CO_2 and air. The dry extract of the suspension being different from that of the suspension in Example 4, these flow rates corresponded this time to $4.9 \text{ dm}^3/\text{m}$ CO_2 and $19.7 \text{ dm}^3/\text{min}$ air per kg of solid contained in the suspension before carbonatation.

Throughout carbonatation, the changes in electrical conductivity of the suspension and in pH were similar to those described in Example 5. The reaction

was halted when the electrical conductivity stabilised for 20 minutes at 8.0 mS/cm (± 0.2 mS/cm).

After carbonatation the distribution of particle size in suspension was again measured and led to a d50 value of 7.6 μm . The suspension was then filtered,
5 dried and the solid obtained was milled as in the above examples.

According to X-ray diffraction analysis followed by thermogravimetric analysis, the product obtained contained 71 ± 2 % CaCO_3 (calcite), 26 ± 2 % hydromagnesite, the remainder being composed of $\text{Mg}(\text{OH})_2$ and $\text{Mg}_3\text{O}_2(\text{OH})_2$. Its bulk density measured according to standard EN 459.2 was 247 kg/m^3 . The
10 specific surface area was 12.6 m^2/g (BET method based on nitrogen adsorption manometry). Thermal conductivity was 38.7 mW/K/m for a density at the time of measurement of 244 kg/m^3 . Figure 7 illustrates the product obtained.

**Example 6: Carbonatation at 60 °C of a suspension prepared by slaking a
15 quicklime with a suspension of $\text{Mg}(\text{OH})_2$ (with Ca/Mg (mol) in the order of 1.2).**

This example was similar to Examples 4 and 5 above in that the conditions of carbonatation of the suspension were identical. On the other hand, the suspension prepared before carbonatation was different.

20 In this example the suspension to be carbonatated was obtained, as provided by one embodiment of the invention, by preliminary slaking of quicklime (CaO) in a suspension of $\text{Mg}(\text{OH})_2$. No ground calcium carbonate (GCC) was used for preparing the suspension. The suspension of $\text{Mg}(\text{OH})_2$ was the same as the one used above in Examples 1 to 3. This suspension of $\text{Mg}(\text{OH})_2$ was diluted with
25 water to obtain a dry extract of 20.0 %. 4.8 kg of quicklime (obtained by calcining a calcium carbonate) were mixed with 20.0 kg of this diluted suspension of $\text{Mg}(\text{OH})_2$. This corresponded to 4.8 kg of quicklime CaO , 4.0 kg of $\text{Mg}(\text{OH})_2$ and 16.0 kg of water, i.e. a Ca/Mg molar ratio of about 1.2. This mixture was left under agitation for about 30 minutes during which the quicklime was slaked with the water derived
30 from the suspension of $\text{Mg}(\text{OH})_2$. On completion of this step, the solid phase in suspension was mostly composed of $\text{Ca}(\text{OH})_2$ and $\text{Mg}(\text{OH})_2$ with traces of CaCO_3 (unfired particles in the quicklime and/or in $\text{Mg}(\text{OH})_2$) and of non-slaked CaO and impurities. The suspension was passed through a 200 μm screen then diluted to a

dry extract 6.9 %. 80 dm³ of this diluted suspension were placed in the 100 dm³ reactor. Carbonatation was again performed at 60 °C with 45 dm³/min CO₂ and 180 dm³/min air i.e. 8.2 dm³/min CO₂ and 32.6 dm³/air per kg of solid phase in suspension.

5 As in Examples 4 and 5, throughout carbonatation (Figure 8) the electrical conductivity of the suspension started by decreasing strongly and this decrease was accompanied by a drop in pH from 12.5 to 9.3. These results were the sign of *in situ* carbonatation of the calcic portion of the solid phase i.e. of the slaked lime Ca(OH)₂ to CaCO₃ (PCC). The electrical conductivity then increased rapidly due to
10 dissolution of the magnesium portion (Mg(OH)₂ to bicarbonate ions of Mg. After a certain time, the electrical conductivity again decreased, a sign of hydromagnesite precipitation. Finally, the electrical conductivity stabilised and the reaction was halted after 1 hour at 9.7 mS/cm (± 0.2 mS/cm). This second phase of the reaction corresponding to the reaction of the magnesium portion was accompanied by a
15 second drop in pH to 7.9.

After carbonatation, the d₅₀ of this carbonated suspension was 8.1 µm. The suspension was then filtered, dried and the solid obtained was milled as in the preceding examples.

According to X-ray diffraction analysis with additional thermogravimetric
20 analysis, the product obtained contained 51 ± 2 % CaCO₃ (calcite), 45 ± 2 % hydromagnesite, the remainder being composed of Mg(OH)₂ and Mg₃O₂(OH)₂. Its bulk density measured in accordance with standard EN 459.2 was 152 kg/m³. The specific surface area was 17.0 m²/g. Thermal conductivity was 36.4 mW/K/m for a density at the time of measurement of 154 kg/m³. Figure 9 is a scanning electron
25 microscope image of the product obtained. This photograph shows well crystallized hydromagnesite plates.

Example 7: Carbonatation at 60 °C of a magnesian lime with Ca/Mg (mol) in the order of 2.9.

30 In this example the raw material was a magnesian limestone containing 75.6 % CaCO₂, 22.1 % MgCO₃, the remainder being impurities (chiefly SiO₂ but also Al₂O₃ and Fe₂O₃). The molar ratio between Ca and Mg in this case was therefore in the order of 2.9. This limestone (calibre 5-15 mm) was calcined for 2 h

at 980 °C in a laboratory electric oven. After calcining, partly calcined magnesian lime was obtained. During calcining, while decarbonation of MgCO_3 to MgO was complete, that of CaCO_3 to CaO was only incomplete. The calcined product therefore contained MgO , CaO , CaCO_3 and impurities, the CaCO_3 content being in the order of 44 % after thermogravimetric analysis of the calcined sampled (950 °C at 5 °C/min under nitrogen).

About 6.5 kg of this calcined product were placed in 19.5 dm³ water previously heated to 55 °C and the slaking reaction was continued for about 1 hour after agitation (300 rpm). After this slaking reaction, the suspension contained Mg(OH)_2 and Ca(OH)_2 produced by slaking of MgO and CaO , but also non-slaked magnesium oxide MgO , the CaCO_3 derived from incomplete calcining of the starting magnesian limestone and the impurities contained in this source of magnesian limestone. The suspension obtained was passed through a 200 µm screen and diluted to obtain a dry extract (solid content) of 7.6 % by weight. 80 cm³ of this suspension were placed in the reactor of 100 dm³ capacity.

Carbonation was again performed at 60 °C with 45 dm³/min CO_2 and 180 dm³/min air, i.e. 7.4 dm³/min CO_2 and 29.6 dm³/min air per kg of solid phase in suspension.

The onset of changes in electrical conductivity of the suspension and in pH occurred in similar manner to Example 6 i.e. with distinct simultaneous decrease in electrical conductivity and drop in pH corresponding to precipitation of calcium carbonate (PCC) from the slaked lime contained in the suspension (Figure 10). At the end of this first step the pH of the suspension was about 9.5.

Then again in similar manner to Example 6, the conductivity rapidly increased due to production of bicarbonate ions of Mg. While in Example 6 (Figure 8) the conductivity again decreased before stabilising, here (Figure 10) no decrease was observed and conductivity gradually stabilised after the increase related to the bicarbonate ions. This difference between this Example 7 and Example 6 is probably related to the reactivity of the Mg sources.

After carbonation, the d_{50} of this suspension was 7.0 µm. The suspension was then filtered, dried and the solid obtained milled as in the preceding examples.

According to X-ray diffraction analysis with additional thermogravimetric analysis the product obtained contained 68 ± 2 % CaCO_3 (calcite), 28 ± 2 %

hydromagnesite, the remainder being composed of $\text{Mg}(\text{OH})_2$ and $\text{Mg}_3\text{O}_2(\text{OH})_2$. Its bulk density measured in accordance with standard EN 459.2 was 221 kg/m^3 . The specific surface area was $17.4 \text{ m}^2/\text{g}$. Thermal conductivity was 37.4 mW/K/m for a density measured at the time of measurement of 213 kg/m^3 . Figure 11 is scanning electron microscope image of the product obtained. This photograph shows well-crystallized hydromagnesite plates.

The invention is evidently in no way limited to these examples and numerous modifications can be made thereto without departing from the scope of the appended claims.

10

15

CLAIMS

1.- A process for preparing a mineral composition containing a mixed solid
5 phase of calcium and magnesium carbonates, comprising:

- i) preparing, in an aqueous phase, a suspension of a solid phase
containing at least one calcium compound selected from among calcium
hydroxide, calcium carbonate and the mixtures thereof and at least one
magnesium compound selected from among magnesium oxide, magnesium
10 hydroxide, at least partly slaked dolomite, and the mixtures thereof, the weight of
said solid phase being between 5 and 15 % of the total weight of the suspension;

-ii) conducting carbonatation of said solid phase in suspension by injecting
a CO₂- containing gas into said suspension heated to a temperature of 55 to 90 °C
at a CO₂ flow rate of 2.5 to 15 dm³/min/kg of said solid phase of the suspension,
15 with a drop in the pH of the suspension down to a value below 9 and stabilisation
of the electrical conductivity of the suspension, carbonatation being halted as soon
this stabilisation of electrical conductivity is observed; and

-iii) obtaining a mixed solid phase of synthetic calcium and magnesium
carbonates formed of a crystallized calcic portion and a plate-like crystallized
20 magnesian portion, the crystals of the calcic portion and those of the magnesian
portion being aggregated in the form of composite aggregates, these aggregates
themselves being at least partly agglomerated in the form of agglomerates, said
calcic portion comprising at least one carbonate selected from the group formed
by calcite, aragonite and the mixtures thereof, said magnesian portion comprising
25 hydromagnesite in plate-like form, said mixed solid phase of carbonates of said
mineral composition having a bulk density of 250 kg/m³ or lower and of 80 kg/m³
or higher measured in accordance with standard EN 459.2.

2. The process according to claim 1, characterized in that said solid
phase of the suspension has a Ca/Mg molar ratio of between 0.4 and 4.0, in
30 particular higher than 1.2.

3. The process according to claim 2, characterized in that the solid
phase of the suspension has a Ca/Mg molar ratio of 3.0 or lower, in particular 2.5
or lower.

4. The process according to one of claims 1 to 3, characterized in that said at least one magnesium compound is selected from among magnesium oxide, magnesium hydroxide and the mixtures thereof.

5 5. The process according to one of claims 1 to 3, characterized in that said at least one magnesium compound is at least partly slaked dolomite, optionally in a mixture with magnesium oxide, magnesium hydroxide or a mixture thereof, so as to obtain a Ca/Mg molar ratio higher than 1.2 and of 4.0 or lower, in particular 3.0 or lower in said solid phase of the suspension.

10 6. The process according to one of claims 1 to 5 characterized in that, at said preparing of a suspension, it comprises slaking by said aqueous phase of calcium oxide (CaO) to said calcium hydroxide.

7. The process according to one of claims 1 to 5 characterized in that, before said preparation of a suspension, it comprises preliminary at least partial slaking of calcium oxide (CaO) to said calcium hydroxide.

15 8. The process according to claim 7, characterized in that said preliminary slaking is dry slaking or near-dry slaking.

9. The process according to claim 7, characterized in that said preliminary slaking is wet slaking to produce a milk of lime which is then optionally screened, milled and/or diluted for said preparation of the suspension.

20 10. The process according to any of claims 7 to 9, characterized in that said preliminary slaking is performed with water, water containing at least one additive or water already containing at least a portion of said at least one magnesium compound that is part of said solid phase in suspension.

25 11. The process according to one of claims 1 to 10 characterized in that, at said preparation of a suspension, it comprises at least partial slaking by said aqueous phase of magnesium oxide (MgO) to said magnesium hydroxide.

12. The process according to one of claims 1 to 10 characterized in that, before said preparation of a suspension, it comprises prior at least partial slaking of magnesium oxide (MgO) to said magnesium hydroxide.

30 13. The process according to claim 12, characterized in that said prior slaking is dry or near-dry slaking.

14. The process according to claim 12, characterized in that said prior slaking is wet slaking so as to produce a milk of magnesia which is optionally screened, milled and/or diluted for said preparation of the suspension.

5 15. The process according to any of claims 12 to 14, characterized in that said prior slaking is performed with water, water containing at least one additive or water already containing at least a portion of said at least one calcium compound that is part of said solid phase in suspension.

10 16. The process according to one of claims 1 to 15 further comprising, after carbonatation, a solid-liquid separation step between said carbonatated solid mixed phase and said aqueous phase of said suspension.

17. The process according to claim 16 wherein said mixed solid phase is subsequently at least partly dried.

18. The process according to any of claims 1 to 17 wherein said mixed solid phase is milled to obtain particles of size 2 mm or smaller.

15 19. The process according to any of claims 1 to 18 wherein said carbonatation temperature is between 60 and 80 °C.

20. The process according to any of claims 1 to 19, characterized in that the gas injected into said suspension contains CO₂ at a concentration of 10 to 100 % by volume.

20 21. A mineral composition containing a mixed solid phase of synthetic calcium and magnesium carbonates, formed of a crystallized calcium portion and a plate-like crystallized magnesium portion, the crystals of the calcium portion and those of the magnesium portion being aggregated in the form of composite aggregates, these aggregates themselves being at least partly agglomerated in
25 the form of agglomerates, said calcic portion comprising at least one carbonate selected from the group formed by calcite, aragonite and the mixtures thereof, said magnesian portion comprising hydromagnesite in plate-like form, said mixed solid phase of carbonates of said mineral composition having a bulk density of 250 kg/m³ or lower and of 80 kg/m³ or higher measured in accordance with standard
30 EN 459.2, and a Ca/Mg molar ratio of between 0.4 and 4.0, in particular higher than 1.2.

22. The composition according to claim 21 wherein the mixed solid phase has a Ca/Mg molar ratio higher than 1.2 and of 3.0 or lower, in particular 2.5 or lower.

5 23. The mineral composition according to one of claims 21 and 22 further comprising an aqueous phase, said mineral composition being in the form of a suspension or paste.

10 24. The mineral composition according to one of claims 21 to 22 wherein said mineral composition is in solid form, powder form in particular, and has a humidity level of between 0 and 4 % by weight of water relative to the total weight of the composition.

25. The mineral composition according to any of claims 21 to 24, characterized in that the aggregates of the mixed solid phase are formed of a calcic core on which hydromagnesite plates are aggregated.

15 26. The use of a composition according to any of claims 21 to 25, or of a composition obtained with the process according to any of claims 1 to 20, in building materials.

27. The use of a composition according to any of claims 21 to 25, or of a composition obtained with the process of any of claims 1 to 20, as constituent of thermal insulating materials, in particular in thermal insulation panels.