

AN ENCAPSULATED PARTICLE

FIELD OF THE INVENTION

[0001] The present invention generally relates to an encapsulated particle, specifically to
5 an encapsulated particle comprising a core particle and a polyurethane layer disposed about the
core particle and comprising the reaction product of an isocyanate component and an isocyanate-
reactive component comprising a graft polyol.

DESCRIPTION OF THE RELATED ART

[0002] Encapsulated particles, such as controlled-release fertilizers, are known in the
10 agricultural art. Such encapsulated particles typically include one or more polyurethane layers
disposed about a core particle, typically a fertilizer, such as urea. Thickness and integrity of the
polyurethane layer limits dissolution rate of the encapsulated particles, specifically, a rate that
the core particle degrades releasing itself, e.g. a “payload”, into soil that includes moisture.

[0003] Unfortunately, many conventional encapsulated particles include inconsistent
15 thickness of the polyurethane layer, which results in accelerated dissolution rates. As known in
the agricultural art, such accelerated dissolution rates lead to waste and phytotoxicity, i.e., toxic
effect of the fertilizer on plant growth. Further, many conventional encapsulated particles have
polyurethane layers with integrity problems, since the polyurethane layers include defects, such
as cracks, pits, depressions, etc. When a polyurethane layer including such defects is disposed
20 about the core particle, the cracks, pits, and/or depressions allow water and other liquids to per-
meate the polyurethane layer, thus prematurely contacting and dissolving the core particle. To
cure such defects, multiple polyurethane layers must typically be disposed about the core particle
resulting in a time consuming and expensive manufacturing process for forming the encapsulated
particles. Yet further, many conventional encapsulated particles are prone to breakage, due to
25 the polyurethane layer lacking adequate hardness and resiliency. Such breakage reduces shelf
life of the encapsulated particles, and results in waste during storage, handling, and use of the
encapsulated particles.

[0004] Accordingly, there remains an opportunity to provide encapsulated particles with improved moisture resistance, improved swelling resistance, improved hydrophobicity, reduced manufacturing cost, and improved resiliency and toughness. There also remains an opportunity to provide encapsulated particles with extended and more predictable dissolution rates. There
5 also remains an opportunity to provide a method of forming such encapsulated particles.

SUMMARY OF THE INVENTION AND ADVANTAGES

[0005] An encapsulated particle comprises a core particle and a polyurethane layer disposed about the core particle. The polyurethane layer comprises the reaction product of an isocyanate component and an isocyanate-reactive component. The isocyanate-reactive component
10 comprises a graft polyol having a continuous phase and polymeric particles. A method of forming the encapsulated particle comprises the steps of providing the core particle, applying the isocyanate and isocyanate-reactive components to the core particle, and reacting the isocyanate and isocyanate-reactive components to form the polyurethane layer.

[0006] The present invention provides a unique combination of the isocyanate and isocyanate-reactive component. The graft polyol of the isocyanate-reactive component imparts the encapsulated particle with improved moisture resistance, improved swelling resistance, reduced manufacturing cost, and improved toughness. The polyurethane layer of the encapsulated particle provides for extended and more predictable dissolution rates of the encapsulated particle. The method of forming the encapsulated particle of the present invention generally results in a
15 uniform, complete, and defect-free polyurethane layer disposed about the core particle. As such, a thinner and less expensive polyurethane layer disposed about the core particle can be employed. Furthermore, the encapsulated particle and the components thereof are shelf-stable thereby allowing for more effective storage and subsequent usage of the encapsulated particle and the components thereof.
20

BRIEF DESCRIPTION OF THE DRAWINGS

[0007] Other advantages of the present invention will be readily appreciated, as the same becomes better understood by reference to the following detailed description when considered in connection with the accompanying drawings wherein:

[0008] Figure 1 is a cross-section of an encapsulated particle of the present invention;

5 [0009] Figure 2 is a chart illustrating dissolution rates of comparative examples;

[0010] Figure 3 is another chart illustrating dissolution rates of comparative examples;
and

[0011] Figure 4 is a chart illustrating dissolution rates of inventive examples of the present invention.

10

DETAILED DESCRIPTION OF THE INVENTION

[0012] Referring to the Figures, wherein like numerals indicate like parts throughout the several views, an encapsulated particle of the present invention is shown generally at **10**. The encapsulated particle **10** comprises a core particle **12**. In certain embodiments, the core particle **12** comprises a fertilizer. Typically, the fertilizer is selected from the group of nitrogen, phosphate, potash, sulfur, and combinations thereof. Suitable fertilizers, for purposes of the present invention, are commercial available from a variety of suppliers known to those of ordinary skill in the art.

15

[0013] In one embodiment, the fertilizer is nitrogen based. Examples of suitable fertilizers that are nitrogen based, for purposes of the present invention, include anhydrous ammonia, urea, ammonium nitrate, urea ammonium nitrate, calcium ammonium nitrate, and combinations thereof. In another embodiment, the fertilizer is phosphate based. Examples of suitable fertilizers that are phosphate based, for purposes of the present invention, include phosphoric acid, mono-ammonium phosphate, ammonium polyphosphate, ammonium phosphate sulfate, and combinations thereof. In yet another embodiment, the fertilizer is potash based. Examples of
25 suitable fertilizers that are potash based, for purposes of the present invention, include potash,

ammonium nitrate, and combinations thereof. In further embodiments, the fertilizer is sulfur based. Examples of suitable fertilizers that are sulfur based, for purposes of the present invention, include ammonium sulfate, sulfuric acid, and combinations thereof.

[0014] In other embodiments, the core particle **12** comprises a biocide. Examples of biocides, for purposes of the present invention, include herbicides, insecticides, fungicides, and combinations thereof. It is to be appreciated that alternative forms of core particles **12** can also be used, i.e., core particles **12** that are not fertilizers or biocides, such as flame retardants. Other core particles **12**, suitable for the purposes of the present invention, include but are not limited to bulbs and seeds, such as grass seeds, flower seeds, etc.

[0015] The core particle **12** is typically present in the encapsulated particle **10** in an amount of from about 75 to about 99, more typically from about 90 to about 99, and most typically from about 96 to about 98, parts by weight, based on 100 parts by weight of the encapsulated particle **10**. It is to be appreciated that the encapsulated particle **10** can include any combination of two or more of the aforementioned core particles **12**. In such embodiments, the core particle **12** can comprise, but is not limited to, a blend of core particle compositions, individual sub-particles of the core particle **12**, and/or layers of different core particle compositions. For example, the core particle **12** can comprise an inner-core comprising urea with an outer-core disposed about the inner-core comprising sulfur. Typically, the core particle **12** is anhydrous, or at least anhydrous on its outermost surface (i.e., the core particle **12** is dry) to prevent premature reaction and/or degradation during manufacture and/or storage of the encapsulated particle **10**.

[0016] The core particle **12** can be of various sizes and shapes. Typically, the core particle **12** is substantially spherical, having an average diameter of from about 0.1 to about 5, more typically from about 0.1 to about 2.5, and most typically from about 0.25 to about 1, millimeters (mm). It is to be appreciated that other sizes and/or shapes of core particles **12** can also be used, such as irregular, oblong or platelet shaped particles. In one embodiment, the core particles **12**

are quite large. For example, the core particle **12** can take the form of a conventional tree spike shape, such that the encapsulated particle **10** is an encapsulated tree spike (not shown).

[0017] The encapsulated particle **10** further comprises a polyurethane layer **14** disposed about the core particle **12**. For purposes of the present invention, it is to be understood that the terminology “disposed about” encompasses both partial and complete covering of the core particle **12** by the polyurethane layer **14**. Typically, the core particle **12** is completely covered by the polyurethane layer **14**, thereby protecting the core particle **12** from exposure to environmental conditions, such as from premature exposure to moisture. The polyurethane layer **14** typically has an average thickness that mimics thicknesses of conventional encapsulation layers, e.g. conventional fertilizer encapsulation layers, such as a thickness of from about 50 to about 200, more typically from about 100 to 150, most typically about 125 to about 150, microns. It is to be appreciated that the polyurethane layer **14** can be formed into various thicknesses depending on one or more desired properties, such as dissolution rates of the encapsulated particles **10**.

[0018] The polyurethane layer **14** comprises the reaction product of an isocyanate component and an isocyanate-reactive component. The isocyanate component is typically a polyisocyanate having two or more isocyanate functional (NCO) groups. Suitable polyisocyanates, for purposes of the present invention include, but are not limited to, conventional aliphatic, cycloaliphatic, araliphatic and aromatic isocyanates. In certain embodiments, the isocyanate component is selected from the group of diphenylmethane diisocyanates (MDIs), polymeric diphenylmethane diisocyanates (PMDIs), and combinations thereof. Polymeric diphenylmethane diisocyanates are also referred to in the art as polymethylene polyphenylene polyisocyanates. Examples of other suitable isocyanates, for purposes of the present invention include, but are not limited to, toluene diisocyanates (TDIs), hexamethylene diisocyanates (HDIs), isophorone diisocyanates (IPDIs), naphthalene diisocyanates (NDIs), and combinations thereof.

[0019] In certain embodiments, the isocyanate component is an isocyanate-terminated prepolymer. The isocyanate-terminated prepolymer is a reaction product of an isocyanate and a polyol and/or a polyamine, as understood in the polyurethane art. The isocyanate may be any type of isocyanate known to those skilled in the polyurethane art, such as one of the polyisocyanates described above. If employed to make the isocyanate-terminated prepolymer, the polyol is typically selected from the group of ethylene glycol, diethylene glycol, propylene glycol, dipropylene glycol, butane diol, glycerol, trimethylolpropane, triethanolamine, pentaerythritol, sorbitol, and combinations thereof. If employed to make the isocyanate-terminated prepolymer, the polyamine is typically selected from the group of ethylene diamine, toluene diamine, diaminodiphenylmethane and polymethylene polyphenylene polyamines, aminoalcohols, and combinations thereof. Examples of suitable aminoalcohols include ethanolamine, diethanolamine, triethanolamine, and combinations thereof. It is to be appreciated that the isocyanate-terminated prepolymer may be formed from a combination of two or more of the aforementioned polyols and/or polyamines.

[0020] The isocyanate component may also be a modified isocyanate, such as, carbodiimides, allophanates, isocyanurates, and biurets. Other suitable isocyanates, for purposes of the present invention, include those described in U.S. Patent Publication No. 2005/0266245 to Mente et al., the disclosure of which is incorporated herein by reference in its entirety.

[0021] Specific examples of suitable isocyanate components, for purposes of the present invention, are commercially available from BASF Corporation of Florham Park, NJ, under the trademark LUPRANATE[®], such as LUPRANATE[®] M, LUPRANATE[®] MI, LUPRANATE[®] M20, LUPRANATE[®] M20SB, LUPRANATE[®] M20HB, and LUPRANATE[®] M20FB isocyanates.

[0022] The polyurethane layer **14** is typically present in the encapsulated particle **10** in an amount of from about 25 to about 1, more typically from about 10 to about 1, and most typically

from about 4 to about 2, parts by weight, based on 100 parts by weight of the encapsulated particle **10**. Generally, the present invention provides for less material use, e.g. less isocyanate component use, relative to prior art encapsulated particles.

[0023] The isocyanate component typically has a viscosity which is suitable for specific applications of the isocyanate component to the core particle **12**, such as by spraying, fogging, and/or atomizing the isocyanate component to apply the isocyanate component to the core particle **12**. Typically, the isocyanate component has a viscosity of from about 10 to about 5,000, more typically from about 25 to about 2,500, and most typically from about 50 to about 200, cps at 25°C according to ASTM D2196. Regardless of the application technique, the viscosity of the isocyanate component should be sufficient to adequately coat the core particle **12**.

[0024] In certain embodiments, the isocyanate component has a nominal functionality of from about 1 to about 5, more typically from about 1.5 to about 4, and most typically from about 2.0 to about 2.7. In certain embodiments, the isocyanate component has an NCO content of from about 20 to about 50, more typically from about 25 to about 40, and most typically from about 30 to about 33, wt. % based on 100 parts by weight of the isocyanate component. The aforementioned NCO contents generally provide a high molecular crosslink density of the isocyanate component that aids in the formation of a defect free polyurethane layer **14**, and also provide the isocyanate component with more chemical bonds per unit of mass to improve cost efficiency.

[0025] The isocyanate component is typically present in an amount of from about 1 to about 50, more typically from about 1 to about 25, yet more typically from about 1 to about 15, most typically from about 5 to about 10, and yet most typically about 7, parts by weight, based on 100 parts by weight of the reaction product. It is to be appreciated that the isocyanate component may include any combination of the aforementioned isocyanates and/or isocyanate-terminated prepolymers.

[0026] The isocyanate-reactive component comprises a graft polyol. In one embodiment, the graft polyol is a polymer polyol. In other embodiments, the graft polyol is selected from the group of polyharnstoff (PHD) polyols, polyisocyanate polyaddition (PIPA) polyols, and combinations thereof. It is to be appreciated that the isocyanate-reactive component can comprise any combination of the aforementioned graft polyols. In certain embodiments, the isocyanate-reactive component may also comprise other components including a supplemental polyol and/or other standard urethane resin components, as further described below. In another embodiment, the isocyanate-reactive component consists of the graft polyol.

[0027] Graft polyols may also be referred to in the art as graft dispersion polyols or graft polymer polyols. Graft polyols are well known to those skilled in the polyurethane art and include products, i.e., polymeric particles **16**, obtained by the *in-situ* polymerization of one or more vinyl monomers, e.g. styrene monomers and/or acrylonitrile monomers, and a macromer in a polyol, e.g. a polyether polyol. In one embodiment, the isocyanate-reactive component is a styrene-acrylonitrile graft polyol. PHD polyols are typically formed by *in-situ* reaction of a diisocyanate with a diamine in a polyol to give a stable dispersion of polyurea particles. PIPA polyols are similar to PHD polyols, except that the dispersion is typically formed by *in-situ* reaction of a diisocyanate with an alkanoamine instead of a diamine, to give a polyurethane dispersion in a polyol. It is to be appreciated that the present invention is not limited to any particular method of making the graft polyol.

[0028] The isocyanate-reactive component comprises a continuous phase. The continuous phase of the isocyanate-reactive component is not generally miscible with the isocyanate component, which provides for increased coverage of the polymeric particles **16** with reactive groups, such as hydroxyl functional (OH) groups. Such reactive groups can further impart crosslinking in the polyurethane layer **14**, once the reactive groups are reacted. The polymeric particles **16** are further described below. In certain embodiments, as alluded to above, both the

continuous phase and the polymeric particles **16** are reactive with the isocyanate component. These embodiments are described in greater detail below.

[0029] Typically, the continuous phase of the isocyanate-reactive component comprises a polyol. The polyol is generally the polyol employed for forming the graft polyol, as described and exemplified above. Such a polyol can be referred to in the art as a “carrier” polyol; however, a distinct polyol separate from the polymeric particles **16** may also be employed in addition to or alternate to the carrier polyol. The polyol generally has at least two hydroxyl functional (OH) groups reactive with the isocyanate component. The polyol may be the same as or different than the polyol previously described and exemplified above with description of the isocyanate-terminated prepolymer. The isocyanate-reactive component can comprise a polyester polyol, a polyether polyol, and combinations thereof. Further, the polyol can be selected from the group of, but is not limited to, aliphatic polyols, cycloaliphatic polyols, aromatic polyols, heterocyclic polyols, and combinations thereof. More specific examples of suitable polyols are selected from the group of, but are not limited to, glycerols, propylene glycols, sucrose-initiated polyols, sucrose/glycerine-initiated polyols, trimethylolpropane-initiated polyols, and combinations thereof. In certain embodiments, the polyol is (or is derived from) a “natural” oil, e.g. corn oil, cottonseed oil, castor oil, etc. Typically, in these embodiments, castor oil is used. In such embodiments, the continuous phase of the isocyanate-reactive component typically comprises castor oil. Castor oil is typically very hydrophobic and has a high hydroxyl number, which is useful for purposes of the present invention. Castor oil is also readily commercially available from a variety of suppliers. Employing natural oils, e.g. castor oil, provides an opportunity for natural and sustainable raw material use.

[0030] In certain embodiments, the polyol is a hydrophobic polyol. In a specific embodiment, the polyol is a hydrophobic polyether polyol. In another specific embodiment, the polyol is a hydrophobic polyester polyol. The hydrophobic polyol contains alkylene oxides. In

these embodiments, the hydrophobic polyol typically has from about 0 to about 50, more typically from about 2 to about 20, and most typically from about 5 to about 15, parts by weight of ethylene oxide (EO), based on 100 parts by weight of the alkylene oxides of the hydrophobic polyol. In other embodiments, the hydrophobic polyol typically has at least 60, more typically at least 70, and most typically at least 80, parts by weight propylene oxide (PO), based on 100 parts by weight of the alkylene oxides. Accordingly, in these embodiments, the hydrophobic polyol is a propylene oxide rich polyol, which imparts the hydrophobic polyol with hydrophobicity, and therefore further imparts the polyurethane layer **14** of the encapsulated particle **10** with hydrophobicity.

[0031] In certain embodiments, the alkylene oxides of the hydrophobic polyol comprise a mixture of ethylene oxide and propylene oxide. In another embodiment, the alkylene oxides of the hydrophobic polyol include only propylene oxide, i.e., the hydrophobic polyol does not include other alkylene oxides, such as ethylene oxide. In certain embodiments, the hydrophobic polyol comprises other types of alkylene oxides known in the polyurethane art, e.g. butylene oxide (BO), in combination with propylene oxide, and optionally, in combination with ethylene oxide. The alkylene oxides of the hydrophobic polyol may be arranged in various configurations, such as a random (heteric) configuration, a block configuration, a capped configuration, or a combination thereof. For example, in one embodiment, the hydrophobic polyol comprises a heteric mixture of ethylene oxide and propylene oxide.

[0032] In certain embodiments, the hydrophobic polyol is terminally capped with ethylene oxide. The hydrophobic polyol typically has a terminal cap of from about 5 to about 25, more typically from about 5 to about 20, and most typically from about 10 to about 15, parts by weight ethylene oxide, based on 100 parts by weight of the hydrophobic polyol. It is to be appreciated that in certain embodiments, the ethylene oxide may only be present in the terminal ethylene oxide cap; however, in other embodiments, the ethylene oxide may also be present

along with the propylene oxide, and optionally, with other alkylene oxides, e.g. butylene oxide, in the alkylene oxides of the hydrophobic polyol. Generally, for purposes of the present invention, increased propylene oxide content of the hydrophobic polyol is preferred in order to impart increased hydrophobicity to the polyurethane layer **14** of the encapsulated particle **10**.

5 **[0033]** Suitable hydrophobic polyols, for purposes of the present invention include, but are not limited to, glycerine-initiated, trimethylolpropane-initiated, propylene glycol-initiated, and sucrose-initiated polyether polyols, and combinations thereof. In one embodiment, the hydrophobic polyol is a glycerine-initiated polyether polyol. In another embodiment, the hydrophobic polyol is a glycerine-initiated polyester polyol. The alkylene oxides of the hydrophobic
10 polyol generally extend from the respective initiator portion of the hydrophobic polyol.

[0034] As introduced above, the isocyanate-reactive component comprises polymeric particles **16**. Such polymeric particles **16** may be referred to in the art as a discontinuous phase of the isocyanate-reactive component. The polymeric particles **16** are generally large in size due to their macromer constituents, i.e., the polymeric particles **16** have micrometer or larger dimensions, such as micrometer or larger diameters. In certain embodiments, the polymeric particles
15 **16** have average diameters ranging from about 0.1 to about 10 microns, more typically from about 0.1 to about 1.5 microns. In other embodiments, the polymeric particles **16** have average diameters less than 0.1 microns, which imparts the isocyanate-reactive component with nanopolymeric particles **16**. It is to be appreciated that the polymeric particles **16** can include nano-
20 and micro- size (or smaller and/or larger) particles.

[0035] As introduced above, the polymeric particles **16** typically comprise the reaction product of monomers selected from the group of styrenes, e.g. alpha-methyl styrene, acrylonitriles, esters of acrylic and methacrylic acids, ethylenically unsaturated nitriles, amines, amides, and combinations thereof. In certain embodiments, the polymeric particles **16** comprise the further reaction of a macromer, such as a polyol having an unsaturation, e.g. one of more olefinic
25

groups, which permits chemical incorporation of the polymeric particle **16**, as described above. In these embodiments, it is believed that the polymeric particles **16** can impart crosslinking in the polyurethane layer **14**, due to reactive groups attached to the polymeric particles **16**, e.g. OH groups imparted by the polyol, which can react with the isocyanate component.

5 **[0036]** In one embodiment, the polymeric particles **16** comprise styrene acrylonitrile (SAN) copolymers, which are the reaction product of styrene monomers and acrylonitrile monomers, as understood in the art. Typically, the SAN copolymers have a weight ratio of styrene to acrylonitrile of from about 30:70 to about 70:30, more typically about 40:60 to about 60:40, yet more typically from about 45:55 to about 60:40, most typically about 50:50 to about 10 60:40, and yet most typically from about 55:45 to about 60:40. In one embodiment, the SAN copolymers have a weight ratio of styrene to acrylonitrile of about 66.7:33.3. In another embodiment, the polymeric particles **16** are urea, which are the reaction product of an amine monomer and an isocyanate functional (NCO) group, such as an NCO group of a diisocyanate. In yet another embodiment, the polymeric particles **16** are urethane, which are the reaction prod-
15 uct of an alcohol monomer and an NCO group, such as an NCO group of a diisocyanate.

[0037] Typically, the polymeric particles **16** are present in the isocyanate-reactive component in an amount of from about 5 to about 70, more typically from about 15 to about 55, and most typically from about 25 to about 50, parts by weight, based on 100 parts by weight of the isocyanate-reactive component. In one embodiment, the polymeric particles **16** are present in the
20 isocyanate-reactive component in an amount of about 65 parts by weight based on 100 parts by weight of the isocyanate-reactive component. Generally, increasing the amount of polymeric particles **16** increases water repellency of the polyurethane layer **14** of the encapsulated particle **10**. It is also believed that the polymeric particles **16** impart increased resiliency for the encapsulated particle **10** relative to prior art encapsulated particles.

[0038] The graft polyol typically has a molecular weight of from about 400 to about 20,000, more typically from about 500 to about 10,000, yet more typically from about 600 to about 5,000, and most typically from about 700 to about 3,000. In one embodiment, the graft polyol has a molecular weight of about 730. In another embodiment, the graft polyol has a molecular weight of about 3,000.

[0039] Other suitable graft polyols and methods of making the same, for purposes of the present invention, include those described in U.S. Patent Nos. 4,522,976 to Grace et al.; 5,093,412 to Mente et al.; 5,179,131 to Wujcik et al.; 5,223,570 to Huang et al.; 5,594,066 to Heinemann et al.; 5,814,699 to Kratz et al.; 6,034,146 to Falke et al.; 6,103,140 to Falke et al.; 6,352,658 to Chang et al.; 6,432,543 to Harrison et al.; 6,472,447 to Lorenz et al.; 6,649,107 to Harrison et al.; and 7,179,882 to Adkins et al., the disclosures of which are incorporated herein by reference in their entirety.

[0040] Specific examples of suitable graft polyols, for purposes of the present invention, are commercially available from BASF Corporation of Florham Park, NJ, under the trademark PLURACOL[®], such as PLURACOL[®] 1365, PLURACOL[®] 4600, PLURACOL[®] 4650, PLURACOL[®] 4800, PLURACOL[®] 4815, PLURACOL[®] 4830, and PLURACOL[®] 4850 graft polyols. It is to be appreciated that the isocyanate-reactive component can include any combination of two or more of the aforementioned graft polyols. Detailed information on graft polyols is described on pages 104 and 105 of THE POLYURETHANES HANDBOOK (David Randall & Steve Lee eds., John Wiley & Sons, Ltd. 2002), which are incorporated herein in their entirety. An example of a suitable method for making a graft polyol dispersion, for purposes of the present invention, is free radical polymerization reaction of acrylonitrile, styrene, and a polyether polyol macromer, each of the aforementioned components having at least one olefin group, the polyether polyol further including at least one hydroxyl group, and the reaction taking place in the presence of an initiator, e.g. a free radical polymerization initiator, and optionally, in the pres-

ence of additional polyol, which may be the same or different than the aforementioned polyether polyol.

[0041] The isocyanate-reactive component typically has a viscosity which is suitable for specific applications of the isocyanate-reactive component to the core particle **12**, such as by spraying, fogging and/or atomizing the isocyanate-reactive component to apply the isocyanate-reactive component to the core particle **12**. Typically, the isocyanate-reactive component has a viscosity of from about 100 to about 10,000, more typically from about 500 to about 5,000, and most typically from about 500 to about 3,000, cps at 25°C according to ASTM D2196. Regardless of application technique, the viscosity of the isocyanate-reactive component should be sufficient to adequately coat the core particle **12**.

[0042] Typically, the isocyanate-reactive component is present in an amount of from about 99 to about 50, more typically from about 99 to about 75, yet more typically from about 99 to about 85, most typically from about 95 to about 90, and yet most typically about 93, parts by weight, based on 100 parts by weight of the reaction product. It is to be appreciated that the isocyanate-reactive component may include any combination of the aforementioned polyols, polymeric particles, and/or graft polyols.

[0043] The isocyanate and isocyanate-reactive components can be present in the polyurethane layer **14** in various weight ratios. Generally, the graft polyol must be present in an effective amount to impart hydrophobicity to the polyurethane layer **14**, as well as other physical properties described herein, such as resiliency for the encapsulated particle **10**.

[0044] Typically, the isocyanate and isocyanate-reactive components are applied to the core particle **12** in a ratio of about 1.5 to 1, more typically about 1.25 to 1, and most typically about 1.1 to 1, based on the respective reactive sites of the isocyanate and isocyanate-reactive components as understood in the art. Such a ratio may be referred to in the polyurethane art as an isocyanate index, and is well understood by those of ordinary skill in the art.

[0045] As alluded to above, the reaction may further comprise an auxiliary polyol, different than the polyol employed as (or in) the isocyanate-reactive component. Suitable polyols for use as the auxiliary polyol are as described and exemplified above with description of the isocyanate-terminated prepolymer. The auxiliary polyol can be used for various purposes. For example, an auxiliary polyol having a higher functionality (relative to the polyol of the graft polyol) can be employed to provide additional reactive functional groups for reaction with the isocyanate component, or an auxiliary polyol can be employed to increase or decrease viscosity of the isocyanate-reactive component. If employed, the auxiliary polyol may be employed in various amounts.

[0046] The reaction product may further comprise the additive component. If employed, the additive component is typically selected from the group of parting agents, catalysts, fillers, plasticizers, stabilizers, cross-linking agents, chain-extending agents, chain-terminating agents, air releasing agents, wetting agents, surface modifiers, moisture scavengers, desiccants, viscosity reducers, reinforcing agents, colorants, anti-oxidants, compatibility agents, ultraviolet light stabilizers, thixotropic agents, anti-aging agents, lubricants, coupling agents, solvents, rheology promoters, thickeners, anti-static agents, and combinations thereof. If employed, the additive component may be present in various amounts. It is to be appreciated that the additive component may include any combination of the aforementioned additives, if employed.

[0047] In certain embodiments, the additive component comprises a catalyst component.

In one embodiment, the catalyst component comprises a tin catalyst. Suitable tin catalysts, for purposes of the present invention, include tin(II) salts of organic carboxylic acids, e.g. tin(II) acetate, tin(II) octoate, tin(II) ethylhexanoate and tin(II) laurate. In one embodiment, the organometallic catalyst comprises dibutyltin dilaurate, which is a dialkyltin(IV) salt of an organic carboxylic acid. Specific examples of suitable organometallic catalyst, e.g. dibutyltin dilaurates, for purposes of the present invention, are commercially available from Air Products and Chemi-

cals, Inc. of Allentown, PA, under the trade name DABCO[®]. The organometallic catalyst can also comprise other dialkyltin(IV) salts of organic carboxylic acids, such as dibutyltin diacetate, dibutyltin maleate and dioctyltin diacetate.

[0048] Examples of other suitable catalysts, for purposes of the present invention, in-

5 clude iron(II) chloride; zinc chloride; lead octoate; tris(dialkylaminoalkyl)-s-hexahydrotriazines including tris(N,N-dimethylaminopropyl)-s-hexahydrotriazine; tetraalkylammonium hydroxides including tetramethylammonium hydroxide; alkali metal hydroxides including sodium hydroxide and potassium hydroxide; alkali metal alkoxides including sodium methoxide and potassium isopropoxide; and alkali metal salts of long-chain fatty acids having from 10 to 20 carbon atoms
10 and/or lateral OH groups.

[0049] Further examples of other suitable catalysts, specifically trimerization catalysts, for purposes of the present invention, include N,N,N-dimethylaminopropylhexahydrotriazine, potassium, potassium acetate, N,N,N-trimethyl isopropyl amine/formate, and combinations thereof. A specific example of a suitable trimerization catalyst is commercially available from

15 Air Products and Chemicals, Inc. under the trade name POLYCAT[®].

[0050] Yet further examples of other suitable catalysts, specifically tertiary amine catalysts, for purposes of the present invention, include dimethylaminoethanol, dimethylaminoethoxyethanol, triethylamine, N,N,N',N'-tetramethylethylenediamine, N,N-dimethylaminopropylamine, N,N,N',N',N''-pentamethyldipropylenetriamine, tris(dimethylaminopropyl)amine, N,N-dimethylpiperazine, tetramethylimino-bis(propylamine), dimethylbenzylamine, trimethylamine, triethanolamine, N,N-diethyl ethanolamine, N-methylpyrrolidone, N-methylmorpholine, N-ethylmorpholine, bis(2-dimethylamino-ethyl)ether, N,N-dimethylcyclohexylamine (DMCHA), N,N,N',N',N''-pentamethyldiethylenetriamine, 1,2-dimethylimidazole, 3-(dimethylamino) propylimidazole, and combinations thereof. Specific

examples of suitable tertiary amine catalysts are commercially available from Air Products and Chemicals, Inc. under the trade name POLYCAT[®].

[0051] If employed, the catalyst component can be employed in various amounts. It is to be appreciated that the catalyst component may include any combination of the aforementioned
5 catalysts. In certain embodiments, the encapsulated particles **10** are formed in the absence of catalyst.

[0052] In certain embodiments, the additive component comprises a colorant, such as a dye and/or a pigment, for coloring the polyurethane layer **14**. The colorant allows completeness of the polyurethane layer **14** to be visually evaluated and can provide various marketing advan-
10 tages. If employed, the colorant can be employed in various amounts.

[0053] Typically, the polyurethane layer **14** is substantially free of water. By “substantially free”, it is meant that in these embodiments, water is present in an amount no greater than about 5, more typically no greater than about 2.5, yet more typically no greater than about 1, and most typically approaching or equaling 0, parts by weight, based on 100 parts by weight of the
15 polyurethane layer **14**. Those of ordinary skill in the art appreciate that if the polyurethane layer **14** is completely free of water, the polyurethane layer **14** is anhydrous. It is generally preferred that the polyurethane layer **14** has little to no water to prevent the encapsulated particle **10** from prematurely degrading, such as by softening, rupturing, or sticking/agglomerating to other adjacent encapsulated particles **10** or surfaces. Such degradation can cause premature release of the
20 core particle **14**, and waste. Water can also be detrimental to the core particle **14** depending on the specific core particle **12** employed to form the encapsulated particle **10**.

[0054] In certain embodiments, the polyurethane layer **14** is substantially free of a wax, such as paraffin. By “substantially free”, it is meant that in these embodiments, wax is present in an amount no greater than about 5, more typically no greater than about 2.5, yet more typically
25 no greater than about 1, and most typically approaching or equaling 0, parts by weight, based on

100 parts by weight of the polyurethane layer **14**. Typically, the polyurethane layer **14** has little to no wax to allow for a uniform polyurethane layer **14**, which can prevent water from permeating the polyurethane layer **14**. However, wax can be employed in the polyurethane layer **14** if compatible with the specific components employed. Alternatively, or in addition, wax can be
5 used as a supplemental coating layer disposed over the polyurethane layer **14** (not shown).

[0055] In certain embodiments, the polyurethane layer **14** includes a concentration of the isocyanate-reactive component proximal to the core particle **12** and a concentration of the isocyanate component distal to the core particle **12** and adjacent to the concentration of the isocyanate-reactive component. In other words, there is generally a concentration gradient in the
10 polyurethane layer **14**, with the concentration gradient having an innermost portion **18** comprising mostly the isocyanate-reactive component and an outermost portion **20** comprising mostly the isocyanate component. Such a concentration gradient can be appreciated with reference to Figure 1. It is also to be appreciated that the encapsulated particle **10** and the concentration gradient are not drawn to scale in Figure 1, as such what is depicted is merely for illustrative purposes. In these embodiments, the polyurethane layer **14** provides a substantially uniform covering for the core particle **12**, with the concentration of the isocyanate component imparting a resilient coating for the encapsulated article **10**, and the concentration of the isocyanate-reactive component imparting a uniform coating over the core particle **12** for the encapsulated particle **10**. It is believed that the orientation of concentrations is beneficial, because the isocyanate-reactive
20 component is (initially) “stickier” relative the isocyanate component, and therefore adheres to the core particle **12** better during manufacture, while the isocyanate component is free to subsequently react (after manufacture) with moisture in the atmosphere to impart a hard outer coating. Generally, this orientation also imparts the encapsulated particles **10** with excellent flow properties, i.e., they are free flowing, which can be useful during application of the encapsulated particles **10** to a substrate, e.g. to the ground. In other embodiments, the aforementioned concentra-
25

tions are switched in orientation relative to the core particle **12**, such that the concentration gradient is reversed (not shown). In yet other embodiments, the polyurethane layer **14** is substantially uniform, i.e., the polyurethane layer **14** does not generally include the concentration gradient (not shown). Methods of forming these specific polyurethane layers **14** are described further
5 below.

[0056] The isocyanate component and the isocyanate-reactive component of the reaction product may be supplied to consumers for use by various means, such as in railcars, tankers, large sized drums and containers or smaller sized drums, totes, and kits. For example, one drum can contain the isocyanate component and another drum can contain the isocyanate-reactive
10 component. Providing the components to consumers separately reduces premature reaction of the components and provides for increased formulation flexibility for forming the reaction product and therefore the encapsulated particle **10**. For example, a consumer can select a specific isocyanate component and a specific isocyanate-reactive component, and amounts thereof, to prepare the polyurethane layer **14** therefrom. Various types of core particles **12** can also be em-
15 ployed. If other components are employed, such as the auxiliary polyol and/or the additive component, e.g. the colorant, such components can be provided separately or premixed with one of or both of the isocyanate component and the isocyanate-reactive component.

[0057] To form the encapsulated particle **10**, the core particle **12** is provided. The isocyanate component and the isocyanate-reactive component are then applied to the core particle **12**.
20 Upon contact (and while under reaction conditions understood in the polyurethane art), the isocyanate component and the isocyanate-reactive component begin to react to form the polyurethane layer **14** disposed about the core particle **12** to form the encapsulated particle **10**.

[0058] In one embodiment, the isocyanate-reactive component is applied to the core particle **12** prior to applying the isocyanate component to the core particle **12**. As introduced above,
25 and as illustrated in Figure 1, this embodiment is useful for forming the concentration gradient

having the concentration of the isocyanate-reactive component proximal, e.g. disposed about, the core particle **12** to form an isocyanate-reactive layer with the isocyanate component disposed about and reacting with the isocyanate-reactive layer. In another embodiment, the isocyanate component is applied to the core particle **12** prior to applying the isocyanate-reactive component to the core particle **12**. As introduced above, this embodiment is useful for forming the concentration gradient having the concentration of the isocyanate component proximal, e.g. disposed about, the core particle **12** to form an isocyanate layer with the isocyanate-reactive component disposed about and reacting with the isocyanate layer.

[0059] In one embodiment, the isocyanate component and the isocyanate-reactive component are pre-blended to form a mixture. The mixture is then applied to the core particle **12** to form the encapsulated particle **10**. As introduced above, this embodiment is useful for forming a uniform polyurethane layer **14**, i.e., the polyurethane layer **14** is substantially free of the concentration gradients as described in the embodiments above, and instead, has a uniform dispersion of the polymeric particles **16** disposed throughout the polyurethane layer **14**.

[0060] The components can be applied by various methods known in the art. Examples of suitable methods of encapsulation, for purposes of the present invention, include bulk coating, tumbling, sheet coating, pan coating, fluidized-bed coating, co-extrusion, spraying and spinning disk encapsulation. Such methods and other encapsulation methods are well known to those of ordinary skill in the polyurethane and chemical engineering art. In certain embodiments, the components are sprayed, atomized, and/or fogged onto the core particle **12**, typically core particles **12**, while the core particles **12** are being agitated in suitable equipment. Typically, spraying, atomizing, and/or fogging the components onto the core particle **12** results in a uniform, complete, and defect-free polyurethane layer **14** disposed about the core particle **12**. Spraying, atomizing, and/or fogging the components also results in a thinner and less expensive polyurethane layer **14** disposed about the core particle **12**. However, several application steps can be used to

build-up the thickness of the polyurethane layer **14**, if so desired. Spraying, atomizing and fogging of the components can occur via use of nozzles, such as one nozzle for each component supplied thereto, or nozzles that have two or more components premixed and supplied thereto. Generally, at least one nozzle applies the isocyanate component, and at least one nozzle applies the isocyanate-reactive component, to the core particle **12**. As described and exemplified above, various orders of application can be employed to form the polyurethane layer **14**.

[0061] To maximize coverage of the core particles **12**, the components are generally applied by spraying droplets or atomizing or fogging particles of the components onto the core particles **12** as the core particles **12** are being tumbled in a rotary blender or similar apparatus. As another example, the core particles **12** can be coated with the components in a rotary drum blender equipped with at least one, typically at least two spinning disk atomizers. Tumblers, drums, or rollers including baffles can also be used, as understood in the art. Alternatively, the core particles **12** can be provided directly to a carrier, e.g. a screened conveyor belt and the components can be applied to the core particles **12**, e.g. by spraying or sheeting, to form the encapsulated particles **10**. Further, at least one of the components, e.g. the isocyanate-reactive component, can already be present on the core particles **12**, such that the remaining component(s) of the reaction product, e.g. the isocyanate component, can then be applied to the core particles **12** and to the isocyanate-reactive component to form the polyurethane layer **14**. Prior to the polyurethane layer **14** fully curing, the encapsulated particles **10** are typically kept moving to avoid agglomeration.

[0062] The amount of the components to be applied and mixed with the core particles **12** is dependant upon several variables including the specific components employed, the size and type of core particle **12** used, the intended use of the encapsulated particle **10**, desired thickness of the polyurethane layer **14**, and the desired properties of the encapsulated particle **10**.

[0063] The encapsulated particles **10** can be of various sizes and shapes. Typically, the encapsulated particles **10** are substantially spherical, having an average diameter of from about 0.5 to about 7.5, more typically from about .5 to about 3, and most typically from about 1 to about 2, millimeters (mm); however, the encapsulated particles **10** can be of other shapes, such as irregular, pocked, oblong or platelet shaped encapsulated particles **10**.

[0064] Without being bound or limited by any particular theory, it is believed that the isocyanate-reactive imparts a certain degree of water repellency to the encapsulated particle **10**. Specifically, it is believed that the graft polyol of the polyurethane layer **14** imparts such water repellency. One method by which the isocyanate-reactive component of the present invention imparts water repellency is by at least partially coating a surface of the core particle **12**, thus decreasing surface tension of the surface. Another method by which the isocyanate-reactive component imparts water repellency is that the isocyanate-reactive component at least partially fills capillaries within the core particle **12** and/or polyurethane layer **14** thus providing a barrier to capillary uptake of water. Further, it is believed that the isocyanate-reactive component reduces formation of micro- and/or nano-cracks from forming within the polyurethane layer **14**, during or after cure to form the encapsulated particle **10**. Yet further, if such cracks are already present in the core particle **12**, the isocyanate-reactive component at least partially fills such cracks, as alluded to above with description of the capillaries. It is believed that the blocking of water and filling of cracks reduces degradation problems such as swelling and agglomeration when the encapsulated particle **10** is exposed to atmospheric moisture during storage and handling. This increases shelf life of the encapsulated particle **10**, and increasing robustness and resiliency of the encapsulated particle **10** during transport (e.g. shipping) and handling. Such blocking and filling also better controls dissolution of the encapsulated particle **10**, as described further below. It is further believed that such “filling” largely occurs due to the polymeric particles **16** of the graft polyol. Specifically, it is believed that the polymeric particles **16** of the isocyanate-

reactive component at least partially fill these cracks, if present. In addition to filling cracks, in certain embodiments, the polymeric particles **16** are reactive with the isocyanate component, which can increase strength and toughness of the polyurethane layer **14**. Other benefits imparted by the graft polyol are described further below.

5 **[0065]** The encapsulated particles **10** can be supplied to consumers in the same manner as the components employed to form them, as described and exemplified above for the isocyanate and isocyanate-reactive components. Typically, the encapsulated particles **10** are supplied in bags, such as paper and/or plastic bags containing about one (1) to about eighty (80) pounds of the encapsulated particles **10** for ease of handling and use. It is to be appreciated that such bags
10 can include other nutrients and/or fillers in addition to the encapsulated particles **10**, such as those typically included along with conventional fertilizers. In certain embodiment, the bags can include both encapsulated and non-encapsulated particles. It is also to be appreciated that the bags can included different grades of encapsulated particles **10**, such as ones having different dissolution rates, which can be imparted by different polyurethane layer **14** thicknesses.

15 **[0066]** It is to be appreciated that various types of the encapsulated particles **10** can be supplied to consumers in blends, such as encapsulated particles **10** having different core particles **12**, e.g. different types of fertilizers, such as nitrogen and potash, nitrogen and sulfur, etc. The encapsulated particles **10** can also be of different physical properties, such as different sizes and shapes, different dissolution rates, different hardness, etc. Such properties are described below.
20 Generally, the encapsulated particles **10** do not agglomerate, such that the encapsulated particles **10** are pourable for ease of use, i.e., are free flowing, and thereby do not clog apparatuses used to supplying and/or spreading of the encapsulated particles **10**, such as by use of a fertilizer spreader.

[0067] The encapsulated particles **10** can be of various hardness (or “crush” strength)
25 depending on several variables including, the specific components and amounts thereof em-

ployed, size and shape of the core particle **12**, size and shape of the encapsulated particle **10**, and thickness of the polyurethane layer **14**. Typically, the encapsulated particle **10** has an excellent hardness relative to prior art encapsulated particles. Hardness of the encapsulated particles **10** provides for longer life of the encapsulated particles **10**, such that the encapsulated particles **10** have excellent handling and storage/shelf life. Specifically, the polyurethane layer **14** of the present invention provides for increased resiliency of the encapsulated particle **10**, relative to conventional encapsulated particles. It is believed that the polymeric particles **16** of the polyurethane layer **14** provide for such resiliency, by serving as a cushion/impact absorbers for the encapsulated particle **10**. Typically, the encapsulated particles **10** have a shelf life of at least about 1, more typically at least about 5, and most typically at least about 10, months. It is to be appreciated that the encapsulated particles **10** can have a near infinite shelf life, more typically 20 or more years, based in part upon exposure (or lack thereof) to moisture.

[0068] The encapsulated particle **10** of the present invention is also useful for providing the core particle **12**, e.g. fertilizer, in a time-released manner. Time release, i.e., time required for the polyurethane layer **14** to be perforated such that the core particle **12** can be released to the surrounding environment, depends on several variables including, the specific components and amounts thereof employed, size and shape of the core particle **12**, size and shape of the encapsulated particle **10**, and thickness of the polyurethane layer **14**. Such a determination can be easily tested by placing the encapsulated particles **10** in a beaker full of water, such that the encapsulated particles **10** are completely covered by the water. Perforations of the polyurethane layer **14** can be evaluated upon visual inspection of the encapsulated particles **10**, and/or by observing changes in clarity of the water. Perforations can range from pin-holing in or sloughing off of the polyurethane layer **14**. It is to be appreciated that time release only applies if the polyurethane layer **14** fully envelops the core particle **12**; otherwise, the core particle **12** is already at least partially exposed to the surrounding environment.

[0069] Time release of the encapsulated particle **10** is also associated with dissolution rate of the encapsulated particle **10**, as introduced above. As understood in the art, dissolution rate is a measurement of how much of the core particle **12** is dispersed into the surrounding environment. For example, the amount of fertilizer released to the surrounding soil over time once the encapsulated particle **10** is exposed to moisture, e.g. from rain or irrigation. The encapsulated particles **10** have excellent dissolution rates relative to prior art encapsulated particles, which can be appreciated with reference to Figures 2, 3 and 4, and the EXAMPLES section below. Generally, the encapsulated particles **10** of the present invention have a uniform dissolution rate, i.e., a near steady-state release of the core particle **12** over a period of time. Alternatively, or in addition to, the encapsulated particles **10** of the present invention have a time-delayed release, e.g. the core particle **12** will begin to dissolve and therefore release some period of time after the encapsulated particles **10** are first exposed to a sufficient amount of moisture to permeate the polyurethane layer **14**.

[0070] One way in which such dissolution works is by the polyurethane layer **14** becoming permeated such that that water can enter into the encapsulated particle **10**. After entry of water, the water can interact with the core particle **12**, e.g. fertilizer. For example, if the core particle **12** comprises a nitrogen based fertilizer, after water migrates through the polyurethane layer **14**, the nitrogen based fertilizer dissolves into solution inside the encapsulated particle **10**, and the solution then migrates out through the polyurethane layer **14** into surrounding soil to deliver the nitrogen. When the core particle **12** is a fertilizer, water and/or other liquids generally cannot permeate the polyurethane layer **14** too quickly, thus preventing the water and/or other liquids from rapidly dissolving the core particle **12**, thus preventing phytotoxicity, and providing for more predictable and controlled dissolution rates.

[0071] The following examples, illustrating the encapsulated particles of the present invention, are intended to illustrate and not to limit the present invention.

EXAMPLES

[0072] Encapsulated particles are prepared in beakers. First, an isocyanate-reactive component, specifically a polyol, is heated and added drop-wise to a beaker containing core particles, specifically urea spheres (i.e., fertilizer), to form a polyol-urea mixture. The polyol-urea mixture is swirled gently using a foam mix blade to ensure distribution of the polyol around the urea spheres. Next, an isocyanate component is heated and added to the polyol-urea mixture and manually swirled to ensure complete contact between the urea spheres and the reaction product of the polyol and the isocyanate component. Complete contact results in a polyurethane layer disposed about the urea spheres. The urea spheres coated by the reaction product are subsequently stirred with a foam mix blade to minimize agglomeration resulting in a free flowing group of encapsulated particles, i.e., encapsulated urea spheres.

[0073] Overall, the polyurethane layers are applied at 2 wt% and 4 wt% based on total urea weight to measure differences imparted by varying thicknesses. Such differences are indicated in tables 1-3 below. All of the polyurethane layers (or coatings) are applied at a 1.1 to 1 (isocyanate to polyol) ratio based on reactive sites, i.e., NCO to OH functional groups. Some comparative examples lack one or more of the aforementioned components, as indicated in tables 1 and 2 below. The same types of urea and isocyanate component are used for all of the examples, and are described in further detail below.

[0074] A screening trial to measure dissolution rates of various encapsulated particles is conducted. The particles are placed in the bottom of a coarse-grade sintered glass funnel. Urea release is measured by washing 15 grams of the particles 5 times with 500 ml of cold tap water. The water is poured rapidly in the funnel corresponding to about 2 inches of rain for each rinse. The water is allowed to percolate through the encapsulated particles and at "its own rate" under the force of gravity, without applying any suction. Filtrate (or rinsate) is collected and placed in

sample vials. The samples of rinsate are analyzed for urea content using standard analytical methods. Results for dissolution rates for each of the particles is indicated in tables 1-3 below.

TABLE 1

Rinsate Number	Core Particle	Iso. Comp. at 2 wt. %	Comparative 1 at 2 wt. %	Comparative 1 at 4 wt. %
1	29.5	10.5	3.7	1.7
2	1.1	10.5	7.3	2.7
3	1.1	0.7	5.8	4
4	1	0.5	5.1	4.4
5	1.2	0.5	3.7	3.6

- 5 **[0075]** “Core Particle” are just particles of the urea without any coating. The same urea is used in all the examples herein and is a conventional grade urea, which is available from a variety of suppliers. As shown above and in Figure 2, the urea (uncoated) essentially all eluted in the first rinse, which validates the method employed for determining dissolution rates of the particles.
- 10 **[0076]** “Iso. Comp.” are particles of the urea with a 2 wt.% coating of the isocyanate component only. The isocyanate component is a polymeric methylene diphenyl diisocyanate (pMDI) with a functionality of approximately 2.7, an NCO content of 31.5, and a viscosity of 200 centipoise at 25°C. The isocyanate component is commercially available from BASF Corporation of Florham Park, NJ under the trade name of LUPRANATE[®] M20S. The same isocyanate
- 15 component is used in all the examples herein (but for Core Particle). As shown above and in Figure 2, the urea quickly eluted in the first two rinses indicating that the isocyanate component alone does not provide adequate protection for the urea spheres.
- 20 **[0077]** “Comparative 1” (Comp. 1) are particles of the urea with a 2 and 4 wt.% coating of the isocyanate component and a polyol reaction product. The polyol is castor oil and has a hydroxyl number of 162 and a nominal functionality of 3. As shown above and in Figure 3, dissolution rates of Comp. 1 can be appreciated.

TABLE 2

Rinsate Number	Comparative 2 at 2 wt. %	Comparative 2 at 4 wt. %	Comparative 3 at 2 wt. %	Comparative 4 at 4 wt. %
1	0.6	15.3	9.5	18
2	5.5	9.4	9.6	10.4
3	5.4	2.9	7.5	1.4
4	1	1.7	2.6	0.7
5	-	0.9	2.6	6.5

[0078] “Comparative 2” (Comp. 2) are particles of the urea with a 2 and 4 wt.% coating of the isocyanate component and a polyol reaction product. The polyol is a glycerine-initiated, propoxylated polyol and has a hydroxyl number range of 388-408, a nominal functionality of 3, and a viscosity of 360 centipoise at 25°C. The polyol is commercially available from BASF Corporation under the trade name PLURACOL[®] GP430. As shown above and in Figure 3, dissolution rates of Comp. 2 can be appreciated. The “-” indicates that data was not collected for the rinsate.

[0079] “Comparative 3” (Comp. 3) are particles of the urea with a 2 wt.% coating of the isocyanate component and a polyol reaction product. The polyol is a glycerine-initiated, propoxylated polyol and has a hydroxyl number range of 222-237, a nominal functionality of 3, and a viscosity of 270 centipoise at 25°C. The polyol is commercially available from BASF Corporation under the trade name PLURACOL[®] GP730. As shown above and in Figure 3, dissolution rates of Comp. 3 can be appreciated.

[0080] “Comparative 4” (Comp. 4) are particles of the urea with a 4 wt.% coating of the isocyanate component and a polyol reaction product. The polyol is a polyol derived from an aromatic amine-based initiator including propylene oxide (PO) and ethylene oxide (EO) and has a hydroxyl number of 390, a nominal functionality of 4, and a viscosity of 10,500 centipoise at 25°C. The polyol is commercially available from BASF Corporation under the trade name PLURACOL[®] P824. As shown above and in Figure 3, dissolution rates of Comp. 4 can be appreciated.

TABLE 3

Rinsate Number	Inventive 1 at 2 wt. %	Inventive 1 at 2 wt. %	Inventive 1 at 4 wt. %	Inventive 2 at 2 wt. %	Inventive 2 at 4 wt. %
1	3.7	3.6	3.8	7.9	15.8
2	5.4	5.4	4.7	5.2	11.4
3	5.6	5.2	4.7	4	15
4	6.6	4.7	4.3	1.8	0.7
5	4.6	4.4	18.3	2.4	-

[0081] “Inventive 1” (Inv. 1) are particles of the urea with a 2 and 4 wt.% coating of the isocyanate component and a polyol reaction product. The polyol is a graft polyol including castor oil as a continuous phase and SAN particles as polymeric particles. Two trials were run at 2 wt.% for reproducibility purposes. As shown above and in Figure 4, dissolution rates of Inv. 1 can be appreciated.

[0082] “Inventive 2” (Inv. 2) are particles of the urea with a 2 and 4 wt.% coating of the isocyanate component and a polyol reaction product. The polyol is a secondary hydroxyl-terminated graft polyether triol having a hydroxyl number of 27-31, a nominal functionality of 3, and a viscosity of 4,340 centipoise at 25°C. The graft polyol includes 44 wt.% SAN particles as polymeric particles. The graft polyol is commercially available from BASF Corporation under the trade name PLURACOL[®] 4600. As shown above and in Figure 4, dissolution rates of Inv. 2 can be appreciated. The “-” indicates that data was not collected for the rinsate.

[0083] Generally, the encapsulated particles of the present invention had more uniform dissolution rates relative to the comparative examples of particles. While some points may indicate fluctuations in dissolution rates of the inventive examples, it is believed that this is due to plugging in the filter which caused greatly extended contact time for each rinse, therefore increasing the amount of urea present in the respective rinsate. Further, the encapsulated particles of the present invention were generally more resilient to breakage relative to the comparative particles.

[0084] The present invention has been described herein in an illustrative manner, and it is to be understood that the terminology which has been used is intended to be in the nature of words of description rather than of limitation. Many modifications and variations of the present invention are possible in light of the above teachings. The invention may be practiced otherwise than as specifically described within the scope of the appended claims.

CLAIMS

What is claimed is:

1. An encapsulated particle comprising:
a core particle; and
5 a polyurethane layer disposed about said core particle and comprising the reaction product of
an isocyanate component, and
an isocyanate-reactive component comprising a graft polyol having a continuous phase and polymeric particles.
- 10 2. An encapsulated particle as set forth in claim 1, wherein said graft polyol is a polymer polyol.
3. An encapsulated particle as set forth in claim 1, wherein said graft polyol is selected from the group of polymer polyols, polyharnstoff (PHD) polyols, polyisocyanate polyaddition (PIPA) polyols, and combinations thereof.
- 15 4. An encapsulated particle as set forth in any one of claims 1-3, wherein said isocyanate component is selected from the group of polymeric diphenylmethane diisocyanates (PMDI), diphenylmethane diisocyanates (MDI), and combinations thereof.
5. An encapsulated particle as set forth in any one of claims 1-4, wherein said core particle comprises a fertilizer.
- 20 6. An encapsulated particle as set forth in claim 1, wherein
said core particle comprises a fertilizer,
said isocyanate component is selected from the group of polymeric diphenylmethane diisocyanates (PMDI), diphenylmethane diisocyanates (MDI), and combinations thereof, and

said isocyanate-reactive component comprises a polymer polyol having a continuous phase and polymeric particles, the continuous phase comprising a polyol having at least two hydroxyl functional (OH) groups.

7. An encapsulated particle as set forth in any one of claims 1-2 or 4-6, wherein said
5 polymeric particles comprise styrene acrylonitrile (SAN) copolymers.

8. An encapsulated particle as set forth in any one of claims 1-7, wherein said polymeric particles are present in said isocyanate-reactive component in an amount of from about 5 to about 70 parts by weight based on 100 parts by weight of said isocyanate-reactive component.

9. An encapsulated particle as set forth in any one of claims 1-5 or 7-8, wherein said
10 continuous phase comprises a hydrophobic polyol having at least two hydroxyl functional (OH) groups.

10. An encapsulated particle as set forth in any one of claims 1-9, wherein said continuous phase comprises castor oil.

11. An encapsulated particle as set forth in any one of claims 1-10, wherein said polyurethane layer has an average thickness of from about 50 to about 200 microns.
15

12. An encapsulated particle as set forth in any one of claims 1-11, wherein I) said polyurethane layer includes a concentration of said isocyanate-reactive component proximal to said core particle and a concentration of said isocyanate component distal to said core particle and adjacent to said concentration of said isocyanate-reactive component, or wherein II) said polyurethane layer includes a concentration of said isocyanate component proximal to said core particle and a concentration of said isocyanate-reactive component distal to said core particle and adjacent to said concentration of said isocyanate component.
20

13. A method of forming an encapsulated particle, said method comprising the steps of:
providing a core particle;

applying an isocyanate component and an isocyanate-reactive component comprising a graft polyol having a continuous phase and polymeric particles to the core particle; and

reacting the isocyanate component and the isocyanate-reactive component to form a polyurethane layer disposed about the core particle to form the encapsulated particle.

5 14. A method as set forth in claim 13, wherein I) the isocyanate-reactive component is applied to the core particle prior to applying the isocyanate component to the core particle, or wherein II) the isocyanate component is applied to the core particle prior to applying the isocyanate-reactive component to the core particle.

10 15. A method as set forth in claim 13 or 14, wherein
the core particle comprises a fertilizer,
the isocyanate component is selected from the group of polymeric diphenylmethane diisocyanates (PMDI), diphenylmethane diisocyanates (MDI), and combinations thereof, and
the isocyanate-reactive component comprises a polymer polyol having a continuous phase and polymeric particles, the continuous phase comprising a polyol having at least two hydroxyl functional (OH) groups.
15