

Electroactive Material

The present invention relates to an electroactive material comprising silicon; the use of such a material in the preparation of an electrode; an electrode including the electroactive silicon material of the invention; the use of an electrode in the preparation of an electrochemical cell and to an electrochemical cell or battery including such an electrode.

The use of silicon as an active anode material in secondary batteries such as lithium ion batteries is well known. Early forms of these lithium ion batteries were prepared using bulk silicon electrodes, thin film silicon electrodes and silicon powder electrodes. Subsequently, silicon comprising electrodes including silicon comprising pillars, rods, fibres and wires have been prepared. Silicon comprising particles having a surface array of pillars have also been used in the fabrication of lithium ion batteries. US 2008/0241647 discloses a cylindrical lithium battery comprising silicon or silicon alloy particles having dimensions in the range 5µm to 15µm. According to US 2008/0241647, batteries including silicon particles having dimensions outside this range exhibit inadequate performance; particles with diameters of less than 5µm give batteries with inadequate capacity, whereas batteries including particles having diameters greater than 15µm exhibit inadequate mechanical properties due to stresses arising from the expansion and contraction of the silicon material during the charge and discharge cycles of the battery. The particles used in the cylindrical batteries of US 2008/0241647 are prepared by chemical vapour deposition of silane onto seeded polycrystalline silicon. These particles are characterised by the presence of crystallites with dimensions of between 30 and 100nm. The polycrystalline nature of these particles means that each particle includes a large number of grain boundaries.

US 2009/0253033 discloses an anode active material suitable for use in lithium ion secondary batteries. The anode material comprises silicon or silicon alloy particles with dimensions of between 500nm and 20µm. These particles are manufactured using techniques such as vapour deposition, liquid phase deposition or spraying techniques.

US 6,334,939 and US 6,514,395 each disclose silicon based nano-structures for use as anode materials in lithium ion secondary batteries. Such nano-structures include cage-like spherical particles, rods or wires having nanoscale dimensions. Rods or wires having diameters in the range 1 to 50nm and lengths in range 500nm to 10µm can be prepared by laser ablation using an iron catalyst. Other techniques such as solution synthesis and chemical vapour deposition are also disclosed as being useful. Iron Germanium alloy nanostructures comprising a mixture of particles having a dimension in the range 1 to 50 nm and micron length rods having a diameter in the range 5 to 30nm can also be prepared using laser ablation. Similar nanostructures are disclosed in US 6334939 and CN1447916A

JP 04035760B discloses silicon based anode materials comprising carbon-coated silicon fibres having diameters in the range 10nm to 50µm for use in lithium ion secondary batteries.

US 2007/0281216 discloses an anode active material for a lithium secondary battery comprising a mixture of silicon nano-particles, graphite, carbon black and a binder. The silicon nano-particles comprise either thread-like particles having a primary particle size in the range 20 to 200nm and a specific surface area of 11m²/g or spherical particles having a primary particle size in the range 5 to 50nm and a specific surface area of 170m²/g. The silicon particles and threads are prepared using techniques such as chemical vapour deposition. Anodes exhibiting a capacity of up to 1000mA/g over 50 cycles are illustrated. The life of the battery is significantly increased if the battery is operated at a limited voltage level.

US 2010/0143798 discloses a solid nano-composite particulate composition for use in lithium ion batteries. The nano-composite particles comprise an electroactive material in the form of fine particles, rods, wires, fibres and tubes; nano-graphene platelets and a protective matrix. The electro-active material includes silicon comprising nano-structures having a typical diameter of 60nm. Solid nano-composite particles were prepared by dispersing a mixture of the electro-active material and nano-graphene platelets having an average diameter of 60nm in a polymeric matrix and spray drying the resulting mixture to produce nano-composite particles having an average diameter in the range 1µm to 5µm.

US 2008/0261112 discloses an electrode material including an electroactive material comprising a mixture of silicon comprising particles and nano-wires. The nano-wires are entangled to form a network, which is in contact with the particles. The electroactive composition is prepared by placing a silicon comprising material in a thermal plasma at a temperature of between 600 and 1500°C to give a composition comprising a mixture of silicon comprising particles having a diameter of about 5µm and silicon comprising fibres having a diameter in the range 30 to 50nm. The components of the compositions become both entangled with and fused to adjacent components during the fabrication process. Further, the fabrication process means that the composition as a whole is fused to the current collector and anodes prepared in the way do not include additional components such as a binder or a conductive additive. Although it is alleged that these compositions are able to both accommodate silicon expansion during lithium intercalation and reduce the build up of an irreversible capacity over the lifetime of the cell, the diameter of the nano-wires present in the composition mean that they have a relatively high surface area and it is expected that the compositions of US 2008/0261112 will exhibit a relatively high first cycle loss as a result

of SEI (Surface Electrolyte Interphase) formation. In addition the fused nature of the composition is expected to result in the build up of heave over the lifetime of the cell, leading to delamination of the electrode material, an undesirable increase in cell volume and a potentially hazardous build up of pressure.

5 US 7,767,346 discloses an electroactive particulate material comprising a porous composite of carbon and silicon prepared by pulverising a mixture of silicon metal, a carbon source such as polyvinyl alcohol and a pore forming agent such as oxalic acid in a ball mill and then sintering the pulverised mixture at a temperature of between 700 and 1000°C for 10 hours to give a composite structure comprising a network of carbon coated silicon fibres and
10 powders. This networked structure is then further pulverised to give the electroactive particulate material, which can be combined with graphite and a binder to prepare anodes for inclusion in a lithium ion battery. It will be appreciated that electrode structures comprising these materials do not comprise a network of silicon fibres and particles extending over the entirety of the electrode structure; the electrode comprises islands of
15 network like composite particles distributed within a matrix of binder and graphite.

US 2009/0269677 discloses an electrode material comprising a three dimensional structure of metal fibres having a plurality of anode active particles distributed therein. The metal fibres are selected from the group comprising titanium, iron, copper, silver, aluminium, zinc, cobalt, nickel and chromium and typically have a diameter in the range 500nm to 50µm and
20 an aspect ratio (ratio of the length to the diameter of the fibre) of greater than 2. The anode active particles typically comprise silicon comprising particles having a diameter in the range 0.1 to 30µm. Electrode structures having a porosity in the range 20 to 95% and a tensile strength in the range 0.1N/mm to 168N/mm are prepared by dipping a structure comprising a network of metal fibres in a solution of electro-active particles. The metal network structure
25 may be in the form of a free standing network or may be applied to a substrate such as a copper current collector. The fibre/powder electrode thus produced can be used in the fabrication of lithium ion batteries.

The silicon structures described above have been prepared using a variety of techniques. For example, the use of epitaxial and non-epitaxial vapour growth techniques in the
30 production of silicon nano-wires having cross-sectional diameters in the range 20 to 500nm and aspect ratios of greater than 10, 50 or 100 is disclosed in US 7,273,732.

An alternative approach to using the epitaxial, solution and chemical vapour deposition techniques taught in the above-mentioned documents for the production of silicon fibres, pillars or rods is disclosed in US 7,402,829; WO 2007/083155; WO 2007/083152; WO
35 2009/010758 and WO 2010/040985. US 7,402,829 discloses the use of island lithography

and etching for fabricating silicon pillars on a silicon substrate and using the integrated structure in an anode. Such pillars have diameters in the range 0.1 to 1 μ m and lengths in the range 1 to 10 μ m. WO 2007/083155 discloses how to prepare silicon fibres for an anode that have been detached from a silicon substrate etched using a similar technique. This produces
5 fibres with a diameter in the range 0.05 to 0.5 μ m and a length in the range 20 to 300 μ m.

WO 2007/083152 uses an alternative nucleation and etching process for the preparation of silicon based pillars and fibres having a diameter in the range 0.2 to 0.6 μ m. The length of the pillars or fibres depends upon whether the etching step is carried out in the same solution as the solution in which nucleation occurred. If the etching step is carried out in a
10 separate solution, fibre lengths of 70 to 75 μ m are observed. If the etching step is carried out in the same solution, fibre lengths of 20 to 100 μ m, typically 85 to 100 μ m are observed.

WO 2009/010758 discloses a method for preparing silicon fibres or pillars detached from etched metallurgical grade silicon granules having diameters in the range 10 μ m to 1mm as starting materials. The silicon granules are etched to produce particles bearing pillars or
15 fibres having a diameter in the range 0.1 to 0.5 μ m and a length in the range 4 to 100 μ m. The pillars or fibres are then detached from the granule substrate and can be used in the fabrication of lithium ion batteries.

An additional suitable etching method is disclosed in WO2010/040985. It should be noted that the fibres or pillars produced using the etching techniques described above are typically
20 single crystal structures, which are devoid of individual crystallites and therefore grain boundaries, or they are polycrystalline with only a few grains.

WO 2009/010758 and WO 2009/010757 describe methods of fabricating anode active materials using detached fibres of the type disclosed above. These fibres can be used as the electrochemically active material in an anode of a lithium ion secondary battery. Often these
25 fibres or wires form part of a composite material (usually known as an anode mix) used in the fabrication of an anode. The anode mix may include other components such as a binder, a conductive carbon material and optionally graphite (or other electroactive forms of carbon). This anode mix is typically mixed with a solvent and/or water to create a slurry, which is applied to a thin metal foil, such as copper foil, to a predetermined layer thickness and then
30 allowed to dry. This process produces an entangled "felt" or "mat" of silicon fibres, which are randomly connected with each other either directly or indirectly through the other components of the mix, and are also connected with the copper foil which acts as the current collector of the electrode. Anodes fabricated according to the methods described above can be incorporated into lithium ion batteries. During the first charge-discharge cycle of a battery
35 including an anode of the type described above, the silicon fibres will tend to fuse together

where they touch each other, strengthening the connectivity of the felt. By the term connected it should be understood to mean, in relation to the present invention, that each of the silicon comprising elements from which the felt or mat are constructed are in electrical contact, either via physical connections or interfaces, with the electrolyte and optionally with one or more other electroactive elements and/or one or more conductive elements that may be present in the mix as well as the current collector. During operation of the cell, it is essential that all the electroactive elements in the anode are connected to at least one other electroactive element and/or to at least one conductive element such that they form a network with a low resistance to the movement of both electrons and ions and provide an efficient interface between the electrolyte and the current collector.

As disclosed in WO 2009/010757, silicon fibres can also be formed into a felt or a mat and bonded together either through the application of heat and pressure or by providing the fibres with a metallic bridging element, prior to the first charge-discharge cycle of the anode. WO 2009/010768 further discloses that a felt comprising silicon fibres can be formed by directly bonding the silicon to the current collector. Felts comprising bonded fibres exhibit improved conductivity compared to non-bonded materials because of the increased connectivity between the fibres.

It is well known that a random arrangement of spheres has a maximum packing density of 64% (the Bernal sphere packing factor); in other words the randomly arranged spheres cannot fill more than 64% of a fixed volume. In fact every particle shape has its own unique, size invariant maximum random packing density. As disclosed in "Improving the Density of Jammed Disordered Packings Using Ellipsoids" by A. Donev, I. Cisse, D. Sachs, E.A. Variano, F.H. Stillinger, R. Connelly, S. Torquato and P.M. Chaikin, Science February 2004, pp990-993, particles such as spheroids and ellipsoids with low aspect ratios can have higher random packing densities, in excess of 70%, but for high aspect ratio particles the maximum random packing density decreases. As disclosed in "Random packings of spheres and spherocylinders simulated by mechanical contraction" by S.R. Williams and A.P. Philipse, Phys. Rev. E, 67, 051301, 2003, the maximum random packing density of stiff rods with high aspect ratios (e.g. >10) appears to vary approximately as 5 divided by the aspect ratio. For example, this predicts that stiff rods of diameter 100nm and length 10 µm would theoretically have a maximum random packing density of approximately 5 divided by the aspect ratio of 100, or approximately 5%.

US 2009/117466 discloses compositions for use as anode materials in a lithium ion secondary battery, the composition comprising a mixture of micron or nano-meter scaled electroactive particles such as silicon or aluminium and graphite flakes. Anodes comprising

these compositions are allegedly characterised by reduced fragmentation of electrode material and better cycling stability.

WO 2007/136164 discloses anode compositions comprising composite particles, each composite particle comprising nano-particles of an electroactive material such as silicon, tin, aluminium, germanium or lead surrounded by graphite flakes. Either the void space between the nano-particles and the flakes and/or the surface of the composite particle can be filled or covered with amorphous or soft carbon. Compositions including these composite particles allegedly exhibit good conductivity and improved low temperature and cycling characteristics.

- 10 WO 2008/139157 discloses anode materials for lithium ion batteries, the anode materials comprising silicon based structures selected from tubes, threads, fibres, flakes and ribbons. These silicon structures allegedly increase conductivity within an anode composition, reduce delamination of the anode material and increase cycle life.

- 15 It has been observed that the initial felt structures (both bonded or unbonded) produced using the silicon based fibre products obtained from the etching techniques described above have an inherent porosity, (that is they contain voids or spaces between the fibres) which

arises as a result of the maximum attainable packing density that can be obtained for a random arrangement of fibres within a defined volume. However, the silicon fibres as described above are able to flex or bend to a limited extent. This flexibility together with the aspect ratio of the silicon fibres produces electrode or anode materials having a higher packing density compared to electrode or anode materials prepared from rigid silicon rods described in the prior art, for example. It will be appreciated, therefore, that the porosity of an anode material comprising nano-structured silicon will depend, to a large extent, on the shape and relative proportions of the silicon nano-structures from which the material is formed.

The inherent porosity (pores or voids) in the electrode structure provides the silicon fibres with space into which they can expand in response to the intercalation or insertion of lithium that occurs during the charging cycle of the battery. These pores or voids also provide a route for the electrolyte to penetrate the whole of the electrode structure, which means that the electrolyte will be in contact with as much of the surface of the silicon material as possible during charging and discharging of the anode. This porosity is important as it provides a path by which the lithium can be intercalated into the bulk of the silicon material so that the lithiation of the silicon is as uniform as possible throughout the anode mass. However, the presence of an excessive number of pores within the anode structure means that the mass of anode active material per unit area is generally low compared to bulk silicon anodes or anode materials prepared using more closely packed particulate silicon, for example. This means that the inherent capacity of the anode is also correspondingly less.

A further problem that has been observed for anode structures comprising silicon fibres, rods and wires is an effect known as "heave" in which the silicon fibres making up the bulk of the silicon electrode material expand as an aggregate body away from the surface of the current collector during lithium intercalation rather than expanding substantially independently into the pores or voids present in the uncharged composite. Heave causes a temporary increase in the thickness of the electrode, which may increase the internal stresses within the battery. Although this bulk does appear to survive the heave process and is able to substantially resume its original configuration on release of the lithium from the silicon fibres initially, over time de-lamination of the anode material may occur. Further, the methods and costs associated with the manufacture of these silicon structures are generally involved and not cost effective and further refinement of these production methods with a view, in particular, to a reduction in the costs associated therewith is needed. There is a need, therefore, for a silicon-based electroactive material that addresses the problems of the prior art outlined above. In particular there is a need for a silicon based electroactive material that is at least able to accommodate one or more of the stresses arising from the expansion and

contraction of the material during the charging and discharging phases of the battery and which also has an improved capacity performance, a longer cycle life and a more cost-efficient method of manufacture compared to the fibre-containing anode materials of the prior art. The present invention addresses that need.

5 A first aspect of the invention comprises a composition comprising a plurality of elongate elements and a plurality of particles, the elongate elements and particles each comprising a metal or semi-metal selected from one or more of the group comprising silicon, tin, germanium and aluminium or mixtures thereof, characterised in that

- 10 a. the elongate elements are selected from one or more of the group comprising fibres, tubes, threads, ribbons and flakes and
- b. the particles are selected from one or more of the group comprising pillared particles, porous particles and porous particle fragments.

In one embodiment of the first aspect of the invention the composition is modified in that

- 15 a. the elongate elements are selected from one or more of the group comprising fibres having a diameter in the range 100 to 500nm, tubes, ribbons and flakes; and
- b. the particles comprise native silicon particles.

In a further embodiment of the first aspect of the invention the composition is modified in that

- 20 a. the elongate element is a pillared particle having an overall diameter in the range 20 to 30µm and pillar lengths of up to 10µm; and
- b. the particles are selected from one or more of the group comprising native particles, porous particles and porous particle fragments.

25 Compositions of the type described herein are electroactive and can be used in the fabrication of electrodes for use in batteries such as lithium ion batteries, sodium ion batteries or magnesium ion batteries, for example. It should be understood that although the invention relates, in general, to compositions including elongate elements and particles comprising a metal or semi-metal selected from one or more of silicon, tin, germanium and aluminium, it will be specifically described herein with reference to compositions comprising

30 elongate elements and particles in which the metal or semi-metal is a silicon comprising material selected from the group comprising substantially pure silicon, a silicon alloy or a material selected from the group comprising silicon oxide, silicon nitride and silicon boride providing the silicon comprising material is electroactive.

The term "silicon comprising material" as used herein should be understood to mean that the material consists, comprises or includes silicon within its structure. Further, it should be appreciated, therefore, that the scope of the invention is not limited to silicon comprising materials as defined above but extends to compositions comprising elongate elements and particles comprising, consisting or including a metal or semi-metal selected from one or more of the group comprising tin, germanium and aluminium and mixtures thereof. Such compositions may also be referred to as compositions comprising metal or semi-metal comprising elongate elements and metal or semi-metal comprising particles respectively. It will be appreciated that, as specified herein above, the metal or semi-metal may suitably be provided in a substantially pure form, in the form of an alloy or in the form of an oxide, nitride or boride as described above. In this respect all references to "silicon comprising elongate elements" and "silicon comprising particles" should be interpreted to include elongate elements consisting, comprising and including a metal or a semi-metal respectively. Although the invention will be specifically described in relation to "silicon comprising elongate elements" and "silicon comprising particles" it should be understood that the scope of the

invention extends to include elongate elements and/or particles consisting, comprising or including elements other than silicon. In this respect, the elongate elements and particles of the first aspect of the invention will hereafter be specifically referred to as "silicon comprising elongate elements" and "silicon comprising particles" respectively.

- 5 For the avoidance of doubt, it should be appreciated that the silicon comprising elongate elements and silicon comprising particles included in the composition according to the first aspect of the invention may include solid elongate elements, solid particles, hollow tubes and porous and hollow particles respectively formed from a single silicon-comprising material, solid elongate elements, solid particles, tubes and porous and hollow particles
- 10 having a silicon comprising coating provided on a core other than silicon and solid elongate elements, solid particles, tubes and porous and hollow particles having a core comprising a first silicon comprising material and a coating comprising a second silicon comprising material. Where the silicon comprising elongate elements and particles comprise a silicon coating, the cores of these coated elements can be selected from materials such as carbon,
- 15 a suitably conductive metal such as copper, nickel, aluminium or gold; a conductive ceramic or a silicon comprising material having a different composition to the silicon comprising material used for the coating. Preferred cores include carbon based cores such as hard carbon or graphite or a suitable metal. The silicon comprising materials used to form the elongate elements, tubes and particles of the composition according to the first aspect of the
- 20 invention can include a substantially pure silicon, a silicon-alloy or a ceramic type silicon material selected from the group comprising silicon oxide, silicon boride and silicon nitride. A substantially pure silicon will suitably have a purity of from 90% to 99.999%, preferably 90% to 99.99%, more preferably 90% to 99.95% and especially 95% to 99.95% and will include high purity silicon used in the manufacture of semi-conductors as well as metallurgical grade
- 25 silicon such as the Silgrain[®] material produced by Elkem of Norway. A substantially pure silicon may include impurities to further improve the conductivity of the material. Suitable desirable impurities include boron, nitrogen, tin, phosphorous, aluminium and germanium. The impurities are preferably present in an amount up to 1% by weight of the silicon, which provides a balance between cost and performance. Suitable silicon-alloys comprise 50 to
- 30 90wt% silicon. The composition of the first aspect of the invention is an electroactive material that is able to form an alloy with lithium and which can also be used in the fabrication of electrodes, preferably anodes for use in lithium ion secondary batteries or batteries based around alternative ions as the charge carrier, for example sodium ion or magnesium ion batteries. By the term "electroactive material" it should be understood to mean that the
- 35 material is able to accommodate and release lithium or other alkali ions, or magnesium ions from its structure during the charging and discharging cycles of a battery. The silicon

comprising elongate elements may comprise discrete elongate elements only or may include structures in which the elongate element includes a silicon comprising particle in its structure.

The silicon comprising particles and elongate elements of the first aspect of the invention are preferably formed into a felt-like structure or mat in which the fibres and particles are either

randomly entangled or are in the form an ordered arrangement within the composition. Preferably the elongate elements and particles are randomly entangled. Such entanglement results in a structure in which the elongate silicon comprising elements and silicon

comprising particles are randomly connected with each other, either directly or indirectly through any other components present in the composition. By the term connected it should be understood to mean, in relation to the present invention, that each of the silicon

comprising elements from which the felt or mat are constructed are in electrical contact, either via physical connections or interfaces, with the electrolyte and optionally with one or more other electroactive elements and/or one or more conductive elements that may be

present in the mix as well as the current collector. It should be understood that the inclusion of the elongate elements of high aspect ratio significantly increases the potential number of connection points between elements in the mix, whilst the inclusion of structurally simpler particles can reduce the overall manufacturing cost per unit mass. The inclusion of particles

also increases the mass of silicon present in the electrode structure, thereby increasing the capacity of an electrode comprising this mixture relative to that of an electrode comprising elongate elements only. The felt like structure or mat can be formed as a layer on a current

collector such as copper foil or can be in the form of a free standing felt or mat and can be used in the fabrication of electrodes, preferably anodes for use in lithium ion batteries. It

should be appreciated that the entanglement of the elongate elements and particles of the first aspect of the invention results in the formation of a network of elongate elements and particles that extends across the entirety of a substrate, such as a copper current collector.

Without wishing to be constrained by theory, it is believed that the formation of an extended network of elongate elements and particles over the surface of the current collector improves both the connectivity within an electrode structure compared to known electrodes and the

cycle life. In a preferred embodiment of the first aspect of the invention, the composition may optionally include, in addition to the silicon elements, one or more additional components selected from the group comprising a binder, a conductive material and a non-silicon

comprising electroactive material, such as graphite. It is particularly preferred that the compositions of the first aspect of the invention include a binder since it is the binder, which

binds, adheres or connects the elongate elements and particles of the composition to the current collector. In an especially preferred embodiment of the first aspect of the invention

there is provided a composition comprising a plurality of silicon comprising elongate elements, a plurality of silicon comprising particles and a binder; such a composition is also known as a composite electrode or anode material, since it is this material that is connected to a current collector during the fabrication of composite electrodes, preferably composite anodes. Additional components selected from the group comprising a conductive material, a viscosity adjuster, a filler, a cross-linking accelerator, a coupling agent and an adhesive accelerator may optionally be added to the especially preferred embodiment according to the first aspect of the invention. These additional components are generally referred to as non-silicon comprising components. These non-silicon comprising components generally comprise carbon as a major constituent, but may comprise silicon as a minor constituent.

By the term "electrode material" it should be understood to mean a material comprising an electroactive material, which can be applied, bonded or connected to a current collector. By the term "composite electrode material" it should be understood to mean a material comprising a mixture, preferably a substantially homogeneous mixture, of an electroactive material, a binder and optionally one or more further ingredients selected from the group comprising a conductive material, a viscosity adjuster, a filler, a cross-linking accelerator, a coupling agent and an adhesive accelerator. The components of the composite material are suitably mixed together to form a homogeneous composite electrode material that can be applied as a coating to a substrate or current collector to form a composite electrode layer. Preferably the components of the composite electrode material are mixed with a solvent to form an electrode mix, which electrode mix can then be applied to a substrate or current collector and dried to form the composite electrode material.

By the term "electrode mix" it should be understood to mean compositions including a slurry or dispersion of an electroactive material in a solution of a binder as a carrier or solvent. It should also be understood to mean a slurry or dispersion of an electroactive material and a binder in a solvent or liquid carrier.

Further the term "composite electrode" should, in the context of the present invention, be understood to mean an electrode structure comprising a current collector having an electroactive material or a composite electrode material applied, bonded, adhered or connected thereto. The current collector may be provided in the form of a sheet or a mesh. The electroactive material may be in the form of a coating applied thereto. The coating may be provided in the form of a felt or a mat, the felt or mat being applied, bonded, adhered or connected to the current collector.

It will be appreciated, therefore, that the total volume of the electrode or anode material, V_T (either in the form of a freestanding felt or mat or in the form of a layer applied to a current

collector) can be expressed in terms of the volume taken up by the solid elements such as silicon, graphite, conductive material and binder that may be present in the material as well as the volume defined by the empty spaces generated within the material as a result of the random packing of the solid elements. The total volume can therefore be expressed as

5 follows:

$$V_T = V_{Si} + V_B + V_C + V_G + V_P$$

Where V_T is the total volume of the anode material; V_{Si} is the total volume of electro-active silicon elements in the anode material; V_B is the total volume of the binder; V_C is the total volume of conductive material (where present, V_G is the total volume of additional electroactive material (such as graphite, where present) and V_P is the total volume occupied
10 by the pores or voids within the anode material. The total pore volume, V_P , of a material is otherwise known as the porosity and can be expressed as a percentage of the total volume V_T .

It will be further appreciated that because the volume of the silicon-comprising material expands by a factor of up to approximately 400% when the material is charged, the porosity
15 of the electrode decreases. Without being constrained by theory, it is believed that the total porosity of the electrode in the charged state at first cycle should be in the range 20 to 30%, preferably 25% to ensure that access of the electrolyte to the components of the material is not inhibited in this charged state. The porosity of the electrode may decrease over the lifetime of a cell including the electrode due to the build up of SEI layers on the surface of the
20 silicon particles and elongate elements and loss of cohesiveness within the composite structure.

Without wishing to be further constrained by theory, the porosity of the uncharged material will depend, in part, on the nature of the components used in the formation of the anode material and the relative proportions in which they are present. It is important, however, that
25 the nature of the components and the relative proportions in which they are present is sufficient to achieve a porosity of between 20 and 30% when the material is in the charged state. The material will typically have a porosity of between 35 and 80% in the uncharged state, preferably between 40 and 75%.

The anode porosity, V_{Si}^u , of an uncharged anode mix comprising an electroactive material consisting of both silicon comprising and a further non-silicon comprising electroactive
30 material can be reduced relative to the anode porosity, V_{Si}^u , of an uncharged anode mix of equivalent volume comprising an electroactive material comprising only silicon comprising material, so that the porosity in the charged state is the same in both cases when the silicon

is lithiated to the same capacity value. This reduction in porosity in the uncharged state can be expressed as follows:

$$V_{Si}^u - V_{Sig}^u = V_G(1 - 1/\alpha)$$

where V_{Sig}^u is the volume occupied by pores in an uncharged material comprising an electroactive material comprising an electroactive material comprising silicon and a further non-silicon comprising electroactive material, V_{Si}^u is the volume occupied by pores in an uncharged material comprising an electroactive material comprising silicon only, V_G is the volume of the additional electroactive material, and α is the average volume expansion factor of the silicon-comprising electroactive material (in other words, the volume V of the silicon comprising electroactive material increases to αV at the end of the charge cycle with the insertion of lithium ions). This calculation assumes that the silicon comprising electroactive material has the same volume expansion factor in each case, that the volume expansion of the further electroactive material is minimal and can be neglected and that the porosity of each anode mix in the final charged state is the same.

Without wishing to be still further constrained by theory, it is believed that the overall structure of the material of the first aspect of the invention and hence its electrical and mechanical properties will depend upon the relative dimensions, volumes and shapes of all the components (silicon and non-silicon comprising components) from which the material is formed as well as the proportions in which they are present. Where the material comprises a plurality of elongate elements and a plurality of particles having diameters that are no more than three times larger than the diameter of the elongate elements, it is believed that the particles will tend to be dispersed within the voids created by the random entanglement of the elongate elements and the resulting structure will have a relatively high capacity. It will be appreciated that it is not desirable for a particle to occupy the entire space of a void within the felt structure, since this would otherwise inhibit the expansion of the silicon comprising elongate elements and particles within the structure and lead to stresses within and buckling of the electrode material. A particle will most preferably occupy between 5 and 50% of the volume of each pore, so that expansion of the silicon material due to intercalation of lithium ions can be accommodated. However it is advantageous for the particles to stay conductively connected to the elongate elements and therefore they should not be too small. Furthermore as the particle diameter decreases, the surface area to volume ratio of the particle increases causing a higher amount of Solid Electrolyte Interphase (SEI) material to be formed during charging which reduces the cycling efficiency. Therefore the diameter of the particles is preferably at least as large as the diameter of the elongate elements.

Without wishing to be constrained by theory, it is believed that where the material includes particles having diameters that are significantly larger, for example more than a factor of three larger, than those of the elongate elements, then the dispersal of particles and elongate fibres will depend upon the length of the elongate elements relative to the diameter of the fibres. If the average length of the elongate elements is less than half the particle diameter, these elongate elements will tend to be dispersed within the voids created by the particles and the elongate element volume should exceed the inter-particle volume that would exist in a packed particle-only mix to maintain good connectivity.

Without wishing to be further constrained by theory it is believed that where the length of the elongate element is greater than half the particle diameter, the elongate elements will tend to occupy space between adjacent particles rather than the inter-void space created by particles and result in a structure in which the inter-particle contact is minimised. The actual structure will depend upon the relative ratio of the volume of elongate elements to the volume of particles present in the structure. Where the volume of elongate elements exceeds that of the particles, the structure of composition comprises a network in which islands of particles are distributed within a matrix of elongate elements.

Compositions in which either the elongate elements partially fill the voids between particles or which comprise a network in which islands of particles are distributed within a matrix of elongate elements results in the formation of anodes, which exhibit better cycle-ability compared to an anode comprising silicon comprising particles only; it is believed that this is because the composition of the present invention is better able to accommodate the stresses arising from the intercalation of lithium, whilst maintaining a good connectivity between all the elements in the mix compared to an anode mix comprising silicon comprising particles only. The partial filling of the pores or voids in the electrode structure means that it also exhibits good capacity characteristics, higher than that attained with anode mixes comprising only elongate elements with a limit on the maximum achievable packing density. The materials of the first aspect of the invention are therefore able to exhibit good capacity characteristics over a prolonged period of time.

As disclosed above, the compositions of the present invention comprising a plurality of silicon comprising elongate elements and a plurality of silicon comprising particles can be used to fabricate electrode or anode materials. The electrodes or anodes so prepared are characterised by good connectivity both within the material itself and between the material and the electrolyte and current collector respectively, good capacity performance over a prolonged number of cycles and a reduced manufacturing cost due to the low cost of the materials used. An electrode or anode mix or material (composition) according to the first

preferred embodiment of the first aspect of the invention will suitably comprise 50 to 90% of an electroactive material by weight, preferably 60 to 80% and especially 70 to 80%. The electroactive material suitably comprises the silicon comprising elongate elements and silicon comprising particles according to the first aspect of the invention and optionally a further material that is also electroactive. Examples of further electroactive materials are provided herein.

The elongate silicon comprising electroactive elements can be selected from one or more structures selected from the group comprising fibres, tubes, ribbons and flakes. By the term "fibre" it should be understood to mean an element defined by two smaller dimensions and one larger dimension, the aspect ratio of the larger dimension to the smallest dimension being in the range 5:1 to 1000:1. Elongate elements having an aspect ratio of 40:1 to 100:1 are preferred. In this respect the term "fibre" may be used interchangeably with the terms pillars, threads and wires. As indicated above, where the material according to the first aspect of the invention includes a silicon comprising fibre, this fibre preferably has a diameter in the range 50 to 2000nm, preferably 50 to 1000nm, more preferably 100nm to 500nm, most preferably 150nm to 200nm and especially 100 to 350nm. Silicon fibres or elongate elements having a diameter of from 150nm to 200nm are especially preferred. Silicon fibres having a diameter of 50nm or less are not preferred as their small diameter means that they have a large surface area to volume ratio, which results in capacity loss due to the build up of an SEI layer during the charging phases of the battery. Silicon comprising fibres of the first aspect of the invention suitably have a length in the range 0.8µm to 100µm, preferably 1µm to 50µm, more preferably 2µm to 40µm and especially 10 to 15µm. A first embodiment of the first aspect of the invention the elongate element has a diameter of from 150nm to 200nm and a length of from 10 to 15µm. The term elongate element also includes a particle having one or more pillars provided on the surface thereof, where the pillars have a length in the range 1 to 100µm. Such pillars may be formed integrally with the particle core in or may be formed independently of the particle core. Silicon-comprising pillared particles having an overall diameter of 20 to 30µm, preferably 25µm and pillar lengths of up to 10µm, preferably 4 to 6µm are preferred.

Alternatively, where the silicon comprising elongate elements comprise ribbons, tubes or flakes, these are each suitably defined by three separate dimensions. The ribbon includes a first dimension, which is smaller in size than the other two dimensions; a second dimension, which is larger than the first dimension and a third dimension, which is larger than both the first and second dimension. The flake includes a first dimension, which is smaller in size than the other two dimensions; a second dimension, which is larger than the first dimension and a third dimension, which is similar to or marginally larger than the second dimension. The tube

includes a first dimension, the tube wall thickness, which is smaller in size than the other two dimensions, a second dimension, the outer diameter of the tube wall, which is larger than the first dimension and a third dimension, the tube length, which is larger than both the first and second dimension. For ribbons, tubes and flakes, the first dimension is suitably of the order of 0.08 μ m to 2 μ m, preferably 0.1 μ m to 0.5 μ m. The second dimension is suitably at least two or three times larger than the first dimension for ribbons and between 10 and 200 times the first dimension for flakes and between 2.5 and 100 times the first dimension for tubes. The third dimension should be 10 to 200 times as large as the first dimension for both ribbons and flakes and between 10 to 500 times as large as the first dimension for tubes. The total length of the third dimension may be as large as 500 μ m, for example.

Elongate elements including ribbons having a thickness in the range 0.08 μ m to 1 μ m, a width in the range 240nm to 300nm, a length in the range 0.8 μ m to 20 μ m and an aspect ratio in the range 10:1 to 200:1. Ribbons having a thickness of 0.25 μ m, a width of 0.5 μ m and a length of 50 μ m are particularly preferred. Where the elongate elements include flakes, these may have a thickness in the range 80nm to 100nm, a width in the range 0.8 μ m to 10 μ m, a length in the range 0.8 μ m to 20 μ m and an aspect ratio in the range 10:1 to 200:1. Flakes having a thickness of 0.25 μ m, a width of 3 μ m and a length of 50 μ m are particularly preferred. Where the elongate elements include tubes, these typically have a wall thickness in the range 0.08 μ m to 2 μ m, an outer wall diameter of between 2.5 and 100 times larger than the wall thickness and a length of between 10 and 500 times as large as the wall thickness. Tubes having a wall thickness of 0.08 to 0.5 μ m, an outer diameter of 0.2 to 5 μ m and a length of at least five times the outer diameter are particularly preferred.

The silicon comprising electroactive particles of the material of the first aspect of the invention may be in the form of native particles, pillared particles, porous particles, porous particle fragments or porous pillared particles. Typically the particles have an average diameter in the range 80nm to 15 μ m.

By the term "native particle" it is to be understood to mean particles that have not been subjected to an etching step. Such particles typically have a principle diameter in the range 1 μ m to 15 μ m, preferably 3 μ m to 10 μ m and especially 4 μ m to 6 μ m and are obtained by milling bulk or particulate silicon, preferably metallurgical grade silicon or high purity waste silicon produced during semi-conductor manufacture to the size required. By the term "Pillared Particles" it is to be understood to mean particles comprising a core and a plurality of pillars extending there from, where the pillars have a length in the range 0.5 to 10 μ m, preferably 1 to 5 μ m. Pillared particles can be prepared by etching silicon particles having dimensions in the range 5 to 40 μ m, preferably 15 to 25 μ m using the procedure set out in

WO 2009/010758. Such pillared particles include particles having a principle diameter in the range 5 to 15 μ m, 15 to 25 μ m and 25 to 35 μ m. Particles having a principle diameter in the range 5 to 15 μ m typically include pillars having heights in the range 0.5 to 3 μ m. Particles having a principle diameter in the range 15 to 25 μ m typically include pillars having heights in the range 1 to 5 μ m. Particles having a principle diameter in the range 25 to 35 μ m typically include pillars having heights in the range 1 to 10 μ m, preferably 1 to 5 μ m. Pillared particles having a core diameter of 14 to 16 μ m and a pillar length of 4 to 6 μ m are particularly preferred.

A second preferred embodiment of the first aspect of the invention provides a composition comprising elongate elements having a diameter of from 150 to 200nm and a length of 10 to 15µm and particles having a diameter in the range 1 to 8µm with a D_{50} diameter of 4 to 6µm, preferably 4µm. (The D_{50} diameter is the diameter at which 50% of the volume of particles present in the sample have a diameter of this value or less). The elongate elements and particles are both suitably silicon-comprising elongate elements and particles as described herein above. The silicon-comprising elongate elements suitably comprise 5 to 95% by weight of the composition of the first aspect of the invention and the silicon-comprising particles suitably comprise 95 to 5% by weight of the composition of the first aspect of the invention. Compositions comprising 90wt% silicon fibres having a diameter of 150 to 200nm and a length of 10 to 15µm and 10wt% silicon particles having a diameter in the range 1 to 8µm with a D_{50} of 4µm were observed to maintain a charging capacity of 1900mAh/g at a coat weight of 9.7g/m² using a constant current charging regime for between 130 and 170 cycles. Compositions comprising 10wt% silicon fibres having a diameter of 150 to 200nm and a length of 10 to 15µm and 90wt% silicon particles having a diameter in the range 1 to 8µm with a D_{50} of 4µm were observed to maintain a charging capacity of 1200mAh/g at a coat weight of 16.5g/m² using a constant current charging regime for more between 175 and 185 cycles. A third preferred embodiment according to the first aspect of the invention provides a composition comprising silicon-comprising pillared particles having an overall diameter of from 14 to 40µm, with a D_{50} of 24µm and silicon particles having a diameter in the range 1 to 8µm with a D_{50} of 4µm. Preferably the composition comprises 30 to 70wt% each of the silicon-comprising pillared particle and the silicon-comprising particles as specified above. Compositions comprising 50wt% of each of the pillared particles and particles having a diameter in the range 1 to 8µm with a D_{50} of 4µm are especially preferred as these were observed to maintain a charging capacity of 1100mAh/g at a coat weight of 13g/m² for more than 330 cycles using a constant current charging regime.

By the term "Porous particle" it should be understood to mean particles having a network of voids or channels extending there through. These voids or channels include voids or channels that are enclosed or partially enclosed within the total volume of the particle as well as particles having channels extending into the interior of the particle from its surface. The porous particles are generally characterised by a substantially spherical shape and a relatively smooth surface morphology. The term "porous particle" should also be understood to include a particulate material comprising a random or ordered network of linear, branched or layered elongate elements, wherein one or more discrete or interconnected void spaces or channels are defined between the elongate elements of the network; the elongate elements suitably include linear, branched or layered fibres, tubes, wires, pillars, rods,

ribbons or flakes. Layered elongate elements include structures in which the elongate elements are fused together. The branched elongate elements typically have a diameter in the range 50 to 100nm with branches every 100 to 400nm. By the term porous particle fragment it should be understood to include all fragments derived from silicon comprising porous particles as defined herein above. Such fragments include structures having a substantially irregular shape and surface morphology, these structures being derived from the silicon material originally defining or bounding the pores or network of pores within the porous particle from which the fragment structures are derived, without themselves comprising pores, channels or a network of pores or channels. These fragments will hereafter be referred to as fractals. The surface morphology of these fractal structures (which are devoid of pores or channels or a network of pores or channels) may include indentations or irregularities arising from the pores or channels or network of pores or channels originally bounded by the silicon structure. These fractal fragments will typically be characterised by the presence of peaks and troughs extending over the surface thereof and will include particles having a spiky appearance as well as those including a plurality of ridges extending from the surface of the particle. The peaks are characterised by a peak height and a peak width. The peak height is defined as the distance between the base of the peak (the place where the peak merges with the body of the fractal) and the apex of the peak. The peak width is defined as the minimum distance between one side of the peak and the other at half height. The term silicon comprising porous particle fragment also includes porous particle fragments comprising a network of pores and/or channels defined and separated by silicon comprising walls. These fragments will herein after be referred to as pore containing fragments. By the term "pore" or "channel" as defined in relation to porous particles from which the fragments are derived as well as the porous particle fragments themselves, it should be understood to mean a void or channel enclosed or partially enclosed within the total volume of the particle as well as a channel extending into the interior of the particle from its surface. The fractal can also be defined by the average thickness of the fractal body; this value is typically identical to the average thickness (smallest dimension) of an elongate element derived from a porous particle comprising a network of elongate elements or the average thickness of the electroactive material separating two adjacent pores within a pore containing porous particle.

These pore and/or channel comprising porous particle fragments are also characterised by an irregular shape and surface morphology. In contrast, the porous particles from which the fragments are derived are characterised by a substantially spherical shape and a relatively smooth surface morphology. Where the fractals and pore containing porous particle fragments are described together hereinafter they will collectively be referred to as silicon

comprising porous particle fragments. The network of pores and/or channels suitably comprises a three dimensional arrangement of pores and/or channels extending through the volume of the particle in which the pore and/or channel openings are provided on two or more planes over the surface of the pore containing porous particle fragment. Porous particles typically have a principle diameter in the range 1 to 15 μm , preferably 3 to 15 μm and contain pores having diameters in the range 1nm to 1500nm, preferably 3.5 to 750nm and especially 50nm to 500nm. Such particles are typically fabricated using techniques such as stain etching of silicon particles or wafers or by etching particles of silicon alloy, such as an alloy of silicon with aluminium. Methods of making such porous particles are well known and are disclosed, for example, in US 2009/0186267, US 2004/0214085 and US 7,569,202. The term "particle" in relation to the particles referred to herein includes essentially spherical and non-spherical particles. Non-spherical particles include cubic, prismatic and decahedral shaped particles having a principle diameter and a minor diameter. It is preferred that the aspect ratio of the principle diameter to the minor diameter is in the range 3:1, preferably 2:1 and especially 1:1.

The silicon comprising elongate elements of the present invention may be prepared by any suitable methods known to a person skilled in the art, for example using the methods disclosed in WO 2009/010758, WO 2009/010757 and WO 2007/083155. The elongate elements are preferably prepared from single crystalline wafers or from single crystalline or polycrystalline silicon particles having a dimension in the range 80 to 800 μm . Silgrain™ silicon particles having dimensions in the range 80 μm to 0.8mm that can be used in the manufacture of elongate elements can be obtained by grinding and sieving any one of the Silgrain materials sold by Elkem of Norway. Suitable Silgrain products that can be used in the preparation of elongate elements (fibres) (and also pillared particles) include Silgrain™ Coarse having dimensions in the range 0.2 to 2mm, Silgrain™ HQ having dimensions in the range 0.2 to 0.8mm and Jetmilled Silgrain™ having dimensions in the range 15 to 425 μm . These Silgrain products typically contain from 97.8 to 99.8% silicon and include impurities such as iron, Aluminium, Calcium and Titanium.

The silicon comprising elongate elements and particles may include a coating, preferably a coating made with carbon, such as amorphous carbon, graphite, electroactive hard carbon, conductive carbon, carbon based polymers or carbon black. Coats are typically applied to the silicon structures to a thickness of between 5 and 40% by weight of the coated silicon structure. Methods of coating silicon particles and elongate elements are known to a person skilled in the art and include chemical vapour deposition, pyrolysis and mechanofusion techniques. Carbon coating of silicon structures through the use of Chemical Vapour Deposition techniques is disclosed in US 2009/0239151 and US 2007/0212538. Pyrolysis

methods are disclosed in WO 2005/011030, JP 2008/186732, CN 101442124 and JP 04035760. Carbon coatings are able to assist in controlling the formation and stability of SEI layers on the surface of the anode. As indicated above coatings other than carbon based coatings can be used. Examples of suitable alternative coatings include compounds such as lithium fluoride or lithium salts of cyclic organic carbonate species or suitable metals such as aluminium, copper, gold and tin as well as conductive ceramic materials. Lithium based coatings can be obtained by reacting silicon with a solution of LiF or exposing silicon to a solution comprising a mixture of lithium ions and a cyclic or acyclic carbonate.

As indicated above, the silicon component of the electroactive material according to the first aspect of the invention preferably comprises 5 to 95% by weight of elongate elements, preferably 10 to 90wt%, more preferably 15 to 90% by weight, most preferably from 20 to 70%, for example from 30 to 50%. As indicated above, the elongate elements may be selected from one or more of the group comprising fibres, ribbons, pillared particles or flakes.

The silicon comprising component of the material according to the first aspect of the invention preferably comprises from 5 to 95% by weight of silicon comprising particles, preferably 10 to 90%, more preferably from 10 to 85%, more preferably from 30 to 80% and especially from 50 to 70% of silicon comprising particles by weight of the silicon component. As indicated above, the silicon comprising particles may be selected from one or more of the group comprising native particles, pillared particles and porous particles.

Compositions comprising fibres and/or ribbons as elongate elements and pillared particles are preferred because this provides the most efficient connectivity between the silicon comprising components of the electroactive material of the first aspect of the invention, whilst minimising the stresses that occur as a result of the volume changes that occur during the charging phase of the battery cycle. Native particles and/or porous particles may also be preferably added to the composition, since this has been found to improve the homogeneity of the composition. A fourth embodiment of the first aspect of the invention therefore provides a composition in which the silicon comprising component comprises one or more components selected from the group silicon comprising fibres, silicon comprising ribbons, pillared particles and optionally native particles and/or porous particles. The pillared particles preferably have a dimension in the range 5 to 35 μm and comprise pillars having a width in the range 80nm to 250nm and a length in the range 0.5 to 5 μm . The elongate elements preferably have a diameter in the range 80 to 250 nm and a length in the range 0.8 to 100 μm . The native particles, where present, preferably have a diameter in the range 1 to 8 μm with a D_{50} of 4 μm . Without wishing to be constrained by theory, it is believed that the

selection of pillared particles characterised by the dimensions given ensures that the particles tend to occupy the voids or pores created by the entanglement of the fibres or ribbons upon formation of the felt structure rather than contribute to the creation of additional pores or voids. The entanglement of the particle pillars with the fibres or ribbons of the mat ensures that the particles are retained within the felt structure during the charge and discharge phase of the battery, which maximises the connectivity between the silicon comprising components of the electroactive material per se and also between the silicon comprising components and any other conductive materials present therein, thereby improving the capacity of an anode prepared using the material according to the first aspect of the invention. Further, because the elongate elements and the particles are retained within the structure through entanglement rather than through close packing of particles, there is sufficient space to accommodate the inherent volume changes of the material that occur during the charging and discharging phases of a battery cell, for example. This entangled structure therefore improves both the capacity and cycle-ability of a material including this structure and hence its long term performance. Further, because the silicon structures used in the manufacture of the electrode or anode materials according to the invention are themselves relatively easy and inexpensive to produce, the associated costs of fabricating anodes or electrodes from such materials is consequently low.

In a fifth embodiment of the first aspect of the invention there is provided a composition comprising silicon fibres having a diameter (d) in the range 0.1 to 0.8 μm and silicon particles having a diameter (D) in the range 0.2 to 2.5 μm . The ratio of the diameter of the particles " D " to the diameter of the fibres " d " will depend, in part, on the packing density of the fibres and the relative volume of the fibres and particles within the material. Where the packing density of the fibres is in the range 3 to 30%, preferably 5 to 25%, it is preferred to use particles having a diameter that is not more than 2 to 3 times that of the diameter of the fibres. The volume ratio of the particle component of the electroactive material to the fibre component is preferably in the range 2:1 to 0.5:1. Without wishing to be constrained by theory, it is believed that the material of the third embodiment of the first aspect of the invention provides for good contact between the silicon components after many charging and discharging cycles of a battery.

A sixth embodiment of the first aspect of the invention provides a composition comprising silicon fibres having a diameter (d) in the range 0.08 to 0.3 μm and silicon particles having a diameter (D) in the range 0.4 to 10 μm and where $D > 3d$. The weight ratio of silicon particles to silicon fibres is in the range 9:1 to 1:9, suitably 4:1 to 0.6:1 and preferably, for example, 3:1 to 2:1. Preferably the composition according to the sixth embodiment of the first aspect of the invention comprises silicon fibres having a diameter in the range 100 to 200nm and a

length in the range 10 to 15µm and native silicon particles having a diameter in the range 1 to 8µm with a D₅₀ of 4µm. The ratio of fibres to native particles for compositions comprising fibres having a diameter in the range 100nm to 200nm and a length 10 to 15µm and native silicon particles having a diameter in the range 1 to 8µm with a D₅₀ of 4µm is preferably 9:1 since electrodes prepared using such compositions have a good stability and reduced delamination compared to electrodes of the prior art; batteries prepared with this 9:1 ratio of fibres and native particles also exhibit good capacity retention when charged to 1200mAh/g at constant current conditions over more than 150 cycles. Compositions in which the ratio of fibres to native particles is 1:9 also exhibit good capacity retention when charged to 1200mAh/g at constant current conditions over more than 150 cycles. However, some delamination of the electrode material was observed.

A seventh embodiment of the first aspect of the invention provides a composition comprising pillared particles of silicon and native silicon particles. The pillared particles of silicon provide both an elongate silicon comprising component and a particulate component and comprise a core having a diameter or thickness of less than 20µm, preferably 5-15µm and pillars having diameters around 50nm-0.2µm (for example 70nm to 0.2µm) and heights of 1-5µm attached to the core with a packing density (or fractional coverage of the core surface area) of less than 50%, preferably in the region of 25-30%. Pillared particles having an overall diameter in the range 20 to 30µm, preferably 25µm and pillar lengths of up to 10µm, preferably 4 to 6µm are preferred. The native silicon particles suitably have a diameter of 30% to 100% of the diameter of the pillared particle core (e.g. 2-15µm) and may comprise between 30 and 80% of the total weight of silicon present in the material. Preferably the native silicon particles have an overall diameter in the range 1 to 8µm and a D₅₀ of 4µm. It will be appreciated that the relative proportion of pillared particles to native silicon particles in the material will depend, in part, on the relative diameters of the components. The weight ratio of pillared particles to native particles in the silicon-comprising component of the composition is suitably in the range 90:10 to 10:90, preferably 70:30 to 30:70 and especially 50:50. Native particles having a relative diameter in the ranges stated above will generally fill any inter-particle spaces created by the pillared particles. A particular example would be native particles having a diameter of 5µm and comprising 30% by weight of the silicon component mixed with pillared particles having a core diameter of 10µm. Alternatively, in a particularly preferred embodiment, there is provided a composition comprising 50wt% of the silicon component of pillared particles having an overall diameter in the range 20 to 30µm, preferably 25µm and pillar lengths of up to 10µm, preferably 4 to 6µm and 50wt% native silicon particles having an overall diameter in the range 1 to 8µm and a D₅₀ of 4µm. Batteries prepared using these compositions and charged and discharged under constant current

conditions exhibit a capacity retention of 1200mAh/g over more than 300 cycles. An electrode or anode material according to any of the preferred embodiments of the first aspect of the invention will suitably comprise 50 to 90% of an electroactive material by weight of the electrode or anode material, preferably 60 to 80% and especially 70 to 80%.

- 5 The electroactive material suitably comprises from 40 to 100% by weight silicon comprising elongate elements and particles, preferably 50 to 90% and especially 60 to 80%. Electrode materials comprising 70wt% of a silicon comprising electroactive material are especially preferred. The electroactive material may include additional components selected from the group comprising non-silicon comprising electroactive materials; graphite and transition
- 10 metal oxides or chalcogenides such as MoO_2 , WO_2 , MnV_2O_6 and TiS_2 ; aluminium and its compounds, tin and its compounds; germanium compounds, including germanium nano-wires; and ceramics such as, for example, titanate ceramics and bismuth selenide. These additional components suitably comprise 5 to 40% by weight of the electrode or anode material or mix.
- 15 In a preferred embodiment of the first aspect of the invention, the composition comprises, in addition to the silicon comprising elongate elements and particles, an electroactive carbon material. These electroactive carbons may be present in an amount comprising 2 to 50%, preferably 4 to 50%, for example 8 to 50% of the total weight of the electroactive material. Examples of suitable electroactive carbons include graphite, hard carbon, carbon
- 20 microbeads and carbon flakes, nanotubes and nanographitic platelets. Suitable graphite materials include natural and synthetic graphite materials having a particle size in the range 5 to $30\mu\text{m}$. Electroactive hard carbon suitably comprises spheroidal particles having a diameter in the range 2 to $50\mu\text{m}$, preferably 20 to $30\mu\text{m}$ and an aspect ratio of 1:1 to 2:1. Carbon microbeads having a diameter in the range 2 to $30\mu\text{m}$ can be used. Suitable carbon
- 25 flakes include flakes derived from either graphite or graphene.

- The binder is a component used to bind the components of the anode mix together either upon formation of the felt like mat or on application of the components to the current collector. The binder helps to maintain the integrity of the anode mix when used in battery cells. It also functions to help the anode mix adhere to the current collector. The binder can
- 30 be added in an amount of 0 to 30%, preferably 6 to 20%, more preferably 6 to 14% and especially 12% by weight based on the weight of the anode mix. Examples of binders include, but are not limited to, polyvinylidene fluoride, polyacrylic acid, modified polyacrylic acid, carboxymethylcellulose, modified carboxymethylcellulose, polyvinyl alcohol, fluorocopolymers such as copolymers of

hexafluoroethylene, polyimide, polyacrylic acid, styrene butadiene rubber and thermo or photopolymerizable materials including, but not limited to, monomers, oligomers and low molecular weight polymers and mixtures thereof which are polymerizable by light irradiation and/or heat treatment. Examples of polymerizable monomers include epoxy, urethane, acrylate, silicon and hydroxyl based monomers and acrylic derivatives which may be used alone or in combination. Polymerisation of these materials is initiated with light irradiation or heat treatment. The polymerizable oligomer is a polymerisation product of from 2 to 25 monomers and may be formed into polymers having a higher degree of polymerisation by light irradiation or heat treatment. The term polymerizable low molecular weight polymer includes linear polymers and cross-linked polymers having a low degree of polymerisation or a low viscosity. Examples of such polymers include polyester acrylate, epoxy acrylate, urethane acrylate and polyurethane.

Preferably the binder is selected from one or more of a polyacrylic acid, a modified polyacrylic acid or alkali metal salts thereof. Lithium and sodium salts are preferred. Suitably the polyacrylic acid binder has a molecular weight in the range 150,000 to 700,000, preferably 250,000 to 550,000, especially 450,000. Polyacrylic acid binders and sodium polyacrylic acid binders are able to bind to silicon materials containing impurities and are an ionically conductive component within the assembled cell. Suitably the silicon materials used will have a silicon purity of 90% to 99.999%, preferably 90% to 99.99%, more preferably 90% to 99.95% and especially 95% to 99.95% and will include high purity silicon used in the manufacture of semi-conductors as well as metallurgical grade silicon such as the Silgrain® material produced by Elkem of Norway. Silicon materials having a purity of less than 99.95% may be advantageous because these materials can be cheaper and the impurities can improve conductivity. However if the level of impurities is too high the performance of the active material in the cell can be reduced and a purity in the range 90% to 99.95% is preferred, for example, 95% to 99.9%. It will be appreciated therefore, that the silicon comprising elongate elements, particles and other silicon comprising components used in the preparation of compositions according to the first aspect of the invention may be derived from metallurgical grade silicon which can reduce the materials cost compared to compositions containing higher purity grades of silicon. Batteries including electrodes containing compositions of the first aspect of the invention, which include a binder comprising polyacrylic acid, a modified polyacrylic acid or an alkali salt thereof exhibit a significant reduction in first cycle loss and longer cycling.

A particularly preferred eighth embodiment of the first aspect of the invention provides a composition comprising 10 to 95% by weight of silicon comprising components, including silicon comprising elongate elements and particles, 5 to 85% by weight of non-silicon

comprising components and 0.5 to 15% by weight of a binder comprising polyacrylic acid and/or an alkali metal salt thereof. Preferred alkali metal salts include those derived from lithium, sodium or potassium. Preferably the silicon comprising components have a purity in the range 90 to 99.95% or in the range 95 to 99.9%.

- 5 A further preferred ninth embodiment of the first aspect of the invention provides a composition in the form of an electrode material, the composition comprising 60 to 80wt% and preferably 70wt% of an electroactive silicon-comprising material, 10 to 15wt%, preferably 12 to 14wt% of a binder, 0 to 4wt% graphite and 6 to 18wt%, preferably 6 to 12wt% and especially 6wt% of a conductive carbon. Especially preferred electrode
- 10 compositions comprise 70wt% of a silicon-comprising material comprising a mixture of silicon-comprising fibres and silicon-comprising native particles in a ratio of from 90:10 to 10:90, 14wt% of a binder comprising polyacrylic acid or an alkali metal salt thereof, 4wt% of graphite and 12wt% of a conductive carbon. Compositions comprising 70wt% of a silicon-comprising material comprising a 50:50 mixture of native particles and pillared particles,
- 15 12wt% of a binder comprising polyacrylic acid or an alkali metal salt thereof, 12wt% graphite and 6wt% of a conductive carbon. The native silicon particles typically have a diameter in the range 1 to 8µm with a D_{50} of 4µm. The silicon fibres typically have a diameter in the range 100 to 200nm, preferably 150nm to 200nm and a length in the range 10 to 15µm. The silicon pillared particles typically have an overall diameter in the range 14 to 40µm, preferably
- 20 25µm.

A viscosity adjuster may be present and is a component used to adjust the viscosity of the anode mix so that the mixing process and the application of the material to a current collector can be easily carried out. The viscosity adjuster can be added in an amount of 0 to 30% by weight based on the total weight of the anode mix. Examples of viscosity adjusters

25 include, but are not limited to, carboxymethylcellulose, polyvinylidene fluoride and polyvinyl alcohol. Where appropriate, in order to adjust the viscosity of the anode mix, a solvent such as N-methyl pyrrolidone (NMP) may be used in an amount of 0 to 30% based on the total weight of the anode mix. In this case the solvent is removed before or after any polymerization or curing process.

- 30 A conductive material may also be present and is a component used to further improve the conductivity of the electrode or anode mix or material and may be added in an amount of 1 to 20% by weight based on the total weight of the anode mix. There is no particular limit to the conductive material so long as it has suitable conductivity without causing chemical changes in a battery in which it is included. Suitable examples of conductive materials
- 35 include hard carbon; graphite, such as natural or artificial graphite; carbon blacks such as

carbon black, acetylene black, ketjen black, channel black; conductive fibres such as carbon fibres (including carbon nanotubes) and metallic fibre; metallic powders such as carbon fluoride powder, aluminium powder and nickel powder; conductive whiskers such as zinc oxide and potassium titanate; conductive metal oxides such as titanium oxide and polyphenylene derivatives. Suitably the total amount of conductive carbon and electroactive carbon (such as graphite) comprises 4 to 85% of the total electroactive material by weight.

A filler is a further ingredient that may be present and can be used to inhibit anode expansion. There is no particular limit to the filler so long as it does not cause chemical changes in the fabricated battery and is a fibrous material. As examples of filler there may be used olefin polymers such as polyethylene and polypropylene and fibrous materials such as glass fibre and carbon fibres.

A coupling agent, if present, is a material used to increase adhesive strength between the active material and the binder and is characterised by having two or more functional groups. The coupling agent may be added in an amount of up to 0 to 30% by weight based on the weight of the binder. There is no particular limit to the coupling agent so long as it is a material in which one functional group forms a chemical bond via reaction with a hydroxyl or carboxyl group present on the surface of the silicon, tin or graphite-based active material, and the other functional group forms a chemical bond via reaction with the nanocomposite according to the present invention. Examples of coupling agents that can be used in the present invention include silane based coupling agents such as triethoxysilylpropyl tetrasulphide, mercaptopropyl triethoxysilane, aminopropyl triethoxysilane, chloropropyl triethoxysilane, vinyl triethoxysilane, methacryloxypropyl triethoxysilane, glycidoxypopyl triethoxysilane, isocyanopropyl triethoxysilane and cyanopropyl triethoxysilane.

An adhesive accelerator may be added in an amount of less than 10% by weight based on the weight of the binder. There is no particular limit to the nature of the adhesive accelerator so long as it is a material that improves the adhesive strength of the anode mix to the current collector. Examples of adhesive accelerators include oxalic acid, adipic acid, formic acid, acrylic acid and derivatives, itaconic acid and derivatives and the like. The silicon comprising components or structures of the composition of the first aspect of the invention suitably comprise a high purity polycrystalline silicon material as well as polycrystalline silicon materials comprising either n-type or p-type dopants as impurities. Polycrystalline silicon materials comprising n-type or p-type dopants are preferred because these materials exhibit a greater conductivity compared to that of high purity polycrystalline silicon. Polycrystalline silicon materials comprising p-type dopants are preferred; these materials suitably include one or more impurities selected from aluminium, boron or gallium as dopants.

The electrode materials can be characterised in relation to their density and their porosity.

The electrode materials of the first aspect of the invention typically have density in the range 0.3 to 0.9g/cm², preferably 0.4 to 0.8g/cm². Electrode materials comprising a mixture of silicon-comprising fibres and silicon-comprising native particles in a ratio of 10:90 are characterised by a density of 0.79g/cm². Electrode materials comprising a mixture of silicon-comprising fibres and silicon-comprising native particles in a ratio of 90:10 are characterised by a density of 0.43g/cm². Further, the electrode materials of the first aspect of the invention typically have a porosity in the range 65 to 95%, preferably 65 to 85%. Electrode materials comprising a mixture of silicon-comprising fibres and silicon-comprising native particles in a ratio of 10:90 are characterised by a porosity of 69%. Electrode materials comprising a mixture of silicon-comprising fibres and silicon-comprising native particles in a ratio of 90:10 are characterised by a porosity of 83%.

The composition of the first aspect of the invention can be easily manufactured and a second aspect of the invention provides a method of preparing an electroactive material according to the first aspect of the invention, the method comprising the steps of mixing

- a. a plurality of metal or semi-metal comprising elongate elements selected from one or more of the group comprising fibres, tubes, threads, ribbons and flakes with
- b. a plurality of metal or semi-metal comprising particles selected from one or more of the group comprising pillared particles, porous particles and porous particle fragments.

The method of the second aspect of the invention can be modified in that

- a. the elongate elements are selected from one or more of the group comprising fibres or threads having a diameter in the range 100 to 500nm, tubes, ribbons and flakes; and
- b. the particles comprise native silicon particles.

A further modification of the method of the second aspect of the invention involves mixing an elongate element with a particulate element, wherein

- a. the elongate element is a pillared particle having an overall diameter in the range 20 to 30µm and pillar lengths of up to 10µm; and
- b. the particles are selected from one or more of the group comprising native particles, porous particles and porous particle fragments.

Additional components may be used in the preparation of the material according to the first aspect of the invention. In a first embodiment of the second aspect of the invention there is provided a method of preparing a composition according to the first aspect of the invention, the method comprising mixing a plurality of elongate silicon comprising elements with a
5 plurality of silicon comprising particles and adding thereto one or more components selected from the group comprising a binder, a conductive material, a viscosity adjuster, a filler, a cross-linking accelerator, a coupling agent and an adhesive accelerator. The material prepared according to this first embodiment can be used in the manufacture of electrodes, preferably anodes for use in lithium ion batteries. In a preferred embodiment of the second
10 aspect of the invention, the method comprises the steps of mixing a plurality of elongate silicon comprising elements with a plurality of silicon comprising particles and a binder.

As discussed above, the composition according to the first aspect of the invention can be used in the manufacture of an electrode. The electrode is typically an anode. The electrodes are preferably used in the manufacture of a lithium secondary battery. A third aspect of the
15 invention therefore provides an electrode comprising a composition according to the first aspect of the invention and a current collector. The composition according to the first aspect of the invention is suitably provided in the form of an electrode or anode mix or material, said mix or material comprising a plurality of elongate silicon comprising elements, a plurality of silicon comprising particles, a binder and optionally one or more components selected from
20 the group comprising a conductive material and optionally a further electroactive material.

The anode mix can be provided in the form of a free-standing felt or mat for connection to a current collector. Alternatively the anode mix can be in the form of a layer, which is adhered to a substrate and connected to a current collector. In a particularly preferred embodiment, the substrate is a current collector and the electrode or anode mix or material is in the form of a layer applied thereto. The components of the anode mix from which the felt or mat is formed are preferably randomly entangled to provide optimum connectivity between the elements. The electrodes of the third aspect of the invention are easily prepared and a fourth aspect of the invention provides a method for fabricating an electrode comprising the steps of forming a slurry from a mixture comprising a plurality of silicon comprising elongate elements, a plurality of silicon comprising particles, a binder and a solvent; casting the slurry onto a substrate and drying the product to remove the solvent. The dried product is in the form of a cohesive mass which may be removed from the substrate, connected to a current collector and used as an electrode. Alternatively, where the composition according to the first aspect of the invention is adhered to the current collector as a result of casting and drying the slurry, the resulting cohesive mass will be connected to a current collector. In a preferred embodiment of the first aspect of the invention the anode mix is cast as a layer onto a substrate, which is itself a current collector. Additional components selected from the group comprising a conductive material, a viscosity adjuster, a filler, a cross-linking accelerator, a coupling agent and an adhesive accelerator may also be included in the slurry mixture. Examples of suitable conductive materials, viscosity adjusters, fillers, cross-linking accelerators, coupling agents and adhesive accelerators are provided above. Suitable solvents include N-methylpyrrolidone. Other suitable solvents known to a person skilled in the art of electrode design may also be used. The relative proportions of each of the components of the anode mix and the solvent, which are used in the manufacture of the electrode will depend, in part, on the dimensions of the elongate silicon comprising elements used in the mixture.

Suitable current collectors for use in electrodes according to the fourth aspect of the invention include copper foil, aluminium foil, nickel foil, carbon, conducting polymers and any other conductive materials. The current collectors typically have a thickness in the range 10 to 50 μ m. Current collectors can be coated with the electrode mix on one side or can be coated with the electrode mix on both sides. In a preferred embodiment of the fifth aspect of the invention compositions of the first aspect of the invention is preferably applied to one or both surfaces of the current collector to a thickness of between 1mg/cm² and 6mg/cm² per surface such that the total thickness of the electrode (current collector and coating) is in the range 40 μ m to 1mm where only one surface of the current collector is coated or in the range 70 μ m to 1mm where both surfaces of the current collector are coated. In a preferred

embodiment, the electrode or anode mix or material is applied to a thickness of between 30 and 40µm onto one or both surfaces of a copper substrate having a thickness of between 10 and 15µm. The current collector may be in the form of a continuous sheet or a porous matrix or it may be in the form of a patterned grid defining within the area prescribed by the grid metallised regions and non-metallised regions. Where the current collector comprises a continuous sheet, the electrode may be readily manufactured by applying a slurry of the anode mix directly to the current collector. Where the current collector comprises a metallised grid, this metallised grid may be formed onto a non-stick substrate such as PTFE to give a metallised non-stick surface (such as metallised PTFE) and the slurry of the anode mix is applied to the metallised non-stick surface and dried to give a metallised mat or felt.

In one embodiment of the fourth aspect of the invention, the electrode may be formed by casting the composition according to the first aspect of the invention onto a substrate thereby to form a self supporting structure and connecting a current collector directly thereto.

In a preferred embodiment of the fourth aspect of the invention, a mixture of silicon comprising elongate elements, a plurality of silicon comprising particles, a binder and optionally one or more components selected from the group comprising a conductive material, a viscosity adjuster, a filler, a cross-linking accelerator, a coupling agent and an adhesive accelerator in a solvent is applied to a substrate and dried to remove the solvent. The resulting product can be removed from the substrate and used as a self supporting electrode structure. Alternatively, in a further embodiment, the composition according to the first aspect of the invention is cast onto a current collector and dried to form an electrode including a first layer comprising a composition according to the first aspect of the invention applied to a current collector.

The electrode of the third aspect of the invention can be used as an anode in the formation of a lithium secondary battery. A fifth aspect of the invention provides a secondary battery comprising a cathode, an anode comprising an electroactive material according to the first aspect of the invention and an electrolyte.

The cathode is typically prepared by applying a mixture of a cathode active material, a conductive material and a binder to a cathode current collector and drying. Examples of cathode active materials that can be used together with the anode active materials of the present invention include, but are not limited to, layered compounds such as lithium cobalt oxide, lithium nickel oxide or compounds substituted with one or more transition metals such as lithium manganese oxides, lithium copper oxides and lithium vanadium oxides. Examples of suitable cathode materials include LiCoO_2 , $\text{LiCo}_{0.99}\text{Al}_{0.01}\text{O}_2$, LiNiO_2 , LiMnO_2 , $\text{LiCo}_{0.5}\text{Ni}_{0.5}\text{O}_2$, $\text{LiCo}_{0.7}\text{Ni}_{0.3}\text{O}_2$, $\text{LiCo}_{0.8}\text{Ni}_{0.2}\text{O}_2$, $\text{LiCo}_{0.82}\text{Ni}_{0.18}\text{O}_2$, $\text{LiCo}_{0.8}\text{Ni}_{0.15}\text{Al}_{0.05}\text{O}_2$, $\text{LiNi}_{0.4}\text{Co}_{0.3}\text{Mn}_{0.3}\text{O}_2$ and

$\text{LiNi}_{0.33}\text{Co}_{0.33}\text{Mn}_{0.34}\text{O}_2$. The cathode current collector is generally of a thickness of between 3 to 500 μm . Examples of materials that can be used as the cathode current collector include aluminium, stainless steel, nickel, titanium and sintered carbon.

The electrolyte is suitably a non-aqueous electrolyte containing a lithium salt and may include, without limitation, non-aqueous electrolytic solutions, solid electrolytes and inorganic solid electrolytes. Examples of non-aqueous electrolyte solutions that can be used include non-protic organic solvents such as N-methylpyrrolidone, propylene carbonate, ethylene carbonate, butylenes carbonate, dimethyl carbonate, diethyl carbonate, gamma butyrolactone, 1,2-dimethoxy ethane, 2-methyl tetrahydrofuran, dimethylsulphoxide, 1,3-dioxolane, formamide, dimethylformamide, acetonitrile, nitromethane, methylformate, methyl acetate, phosphoric acid trimester, trimethoxy methane, sulpholane, methyl sulpholane and 1,3-dimethyl-2-imidazolidione.

Examples of organic solid electrolytes include polyethylene derivatives polyethyleneoxide derivatives, polypropylene oxide derivatives, phosphoric acid ester polymers, polyester sulphide, polyvinyl alcohols, polyvinylidene fluoride and polymers containing ionic dissociation groups.

Examples of inorganic solid electrolytes include nitrides, halides and sulphides of lithium salts such as Li_5Ni_2 , Li_3N , LiI , LiSiO_4 , Li_2SiS_3 , Li_4SiO_4 , LiOH and Li_3PO_4 .

The lithium salt is suitably soluble in the chosen solvent or mixture of solvents. Examples of suitable lithium salts include LiCl , LiBr , LiI , LiClO_4 , LiBF_4 , $\text{LiB}_{10}\text{C}_{20}$, LiPF_6 , LiCF_3SO_3 , LiAsF_6 , LiSbF_6 , LiAlCl_4 , $\text{CH}_3\text{SO}_3\text{Li}$ and $\text{CF}_3\text{SO}_3\text{Li}$.

Where the electrolyte is a non-aqueous organic solution, the battery is provided with a separator interposed between the anode and the cathode. The separator is typically formed of an insulating material having high ion permeability and high mechanical strength. The separator typically has a pore diameter of 0.01 to 100 μm and a thickness of 5 to 300 μm . Examples of suitable separators include microporous polyethylene films.

The battery according to the fifth aspect of the invention can be used to drive a device, which relies on battery power for its operation. Such devices include mobile phones, laptop computers, GPS devices, motor vehicles and the like. A sixth aspect of the invention therefore includes a device including a battery according to the fifth aspect of the invention.

It will also be appreciated that the invention can also be used in the manufacture of solar cells, fuel cells and the like.

The invention will now be described with reference to the following non-limiting examples. Variations on these falling within the scope of the invention will be evident to a person skilled in the art.

Examples

5 Example 1 - Preparation of Electrode Materials

Example 1a - Fibres

The fibres were prepared by etching either p or n-type silicon wafers to produce pillars of around 10µm high and diameters of from 100-200nm, using a method set out in US7402829 or US2010/0151324 and then removing pillars from the wafer ultrasonically to produce
10 fibres. The silicon fibres produced are characterised by a BET value of around 10-11 m²/g.

Alternatively, the fibres can be produced by etching native silicon particles having an overall diameter in the range 40 to 200µm using the method set out in WO2010040985 or EP2204868 and removing the pillars from the etched surface.

Example 1b - Native Silicon Particles

15 These were used as supplied. Specifically silicon particles comprising p-type doped metallurgical grade silicon having a purity of 99.8%, a diameter in the range 1 to 8µm, with a D₅₀ of 4µm and a BET value of around 5m²/g were used in the preparation of compositions according to the first aspect of the invention. The particles were sold as Silgrain® J230 and were supplied by Elkem of Norway

20

Example 1c - Pillared Particles

Pillared particles were prepared by etching p-type metallurgical grade silicon powder particles having a purity of 99.8% and a diameter in the range 14 to 40µm, with a D₅₀ of 24µm in accordance with the methods set out in US 2011/0067228, WO2010040985 or
25 WO2010040986. The silicon powder particles used as the starting materials in the preparation of pillared particles were obtained from Elkem of Norway and were sold as Silgrain® J320. The pillared particles produced were characterised by an overall diameter in the range 14 to 40µm, with a D₅₀ of 24µm.

Example 2 - Preparation of Anodes

30 Example 2a – Anode 1

A silicon mix (1) was prepared by mixing 90wt% of native silicon particles as described above with 10wt% silicon fibres prepared in accordance with the procedure set out in Example 1a above.

5 A composite electrode mix was prepared by mixing the silicon mix (1) with a sodium polyacrylic acid binder, graphite and carbon black in the proportions 70 : 14 : 4: 12 (Si : Polyacrylic acid : Graphite: Carbon Black). The Si material and the Carbon black were high shear stirred as an aqueous solution for several hours.

10 The polyacrylic acid binder was added (as a 10wt% solution in water) and the resulting composite was further mixed by a dual asymmetric centrifugation technique for 10 minutes to give Anode Mix 1, which was then cast onto electrodeposited Cu foil to a coat weight of approximately 16.5g/cm². Coat weights of 15 – 30 g/m² are typically used for electrochemical testing in a Soft Pack Pair cell. The coat was characterised by a density of 0.79g/cm³ and a porosity of 69%.

Example 2a – Anode 2

15 A silicon mix (2) was prepared by mixing 10wt% of native silicon particles as described in Example 1b above with 90wt% silicon fibres prepared in accordance with the procedure set out in Example 1a above.

20 A composite electrode mix was prepared by mixing the silicon mix (2) with a sodium polyacrylic acid binder, graphite and carbon black in the proportions 70 : 14 : 4: 12 (Si : Polyacrylic acid : Graphite: Carbon Black). The Si material and the Carbon black were high shear stirred as an aqueous solution for several hours.

25 The polyacrylic acid binder was added (as a 10wt% solution in water) and the resulting composite was further mixed by a dual asymmetric centrifugation technique for 10 minutes to give Anode Mix 2, which was then cast onto electrodeposited Cu foil to a coat weight of approximately 9.7g/cm² and were used in the manufacture of a Soft Pack Pair cell. The composite coat was characterised by a density of 0.43g/cm³ and a porosity of 83%.

Example 2c - Anode 3

30 A silicon mix (3) was prepared by mixing 50wt% native silicon particles as set out above with 50wt% of pillared particles as described in Example 1c above with 50wt% native silicon particles as described in Example 1b above.

A composite electrode mix was prepared by mixing the silicon mix (3) with a sodium polyacrylic acid binder, graphite and carbon black in the proportions 70 : 12 : 12: 6 (Si :

Polyacrylic acid : Graphite: Carbon Black). The Si material and the Carbon black were high shear stirred as an aqueous solution for several hours.

The polyacrylic acid binder was added (as a 10wt% solution in water) and the resulting composite was further mixed by a dual asymmetric centrifugation technique for 10 minutes to give Anode Mix 3, which was then cast onto electrodeposited Cu foil to a coat weight of approximately 13g/cm² and were used in the manufacture of a Soft Pack Pair cell. The composite coat was characterised by a density of 0.43g/cm³ and a porosity of 83%.

Example 3 – Preparation of Batteries (Cells)

Negative electrodes (anodes) 1, 2 and 3 were prepared as described above. Electrode pieces were cut to the required size, and then dried overnight in a vacuum oven at 120 °C, under dynamic vacuum. Slightly smaller pieces of standard lithium ion cathode material were prepared in a similar manner (active component either lithium cobalt oxide or a mixed metal oxide (MMO) i.e. $\text{LiNi}_{0.80}\text{Co}_{0.15}\text{Al}_{0.05}\text{O}_2$). Tags were ultrasonically welded to exposed areas of copper and aluminium on the two electrode pieces. Then the electrodes were wrapped between a continuous layer of porous polyethylene separator (Tonen), so that there was one layer of separator between the two electrodes. The winding was placed in an aluminium laminate bag, and the tags were thermally sealed along one edge. The cell was filled with the required quantity of electrolyte under partial vacuum, and the electrolyte was allowed to disperse into the pores. The bag was then vacuum sealed, and the cells were allowed to soak for a further thirty minutes before the start of cycle testing. Cells 1, 2 and 3 prepared from the negative electrodes 1, 2 and 3 were tested as set out below.

Example 4 – Performance data on cells

Cells produced as described in Example 3 were cycled using Arbin battery cycling units using a constant capacity charge/discharge method. Discharge capacities close to either 1200 mAh/g (Cell 1), 1900mAh/g (cell 2) and 1000mAh/g (Cell 3) was maintained over more than 130 cycles. Table 1 lists discharge capacities for cells 1, 2 and 3 (4 repeats) comprising an MMO cathode, prepared as described above and cycled at a constant capacity of 1200mAh/g (Cell 1), 1900mAh/g (Cell 2) and 1000mAh/g (Cell 3) until the cell fails (number of cycles until the discharge capacity falls below 80% of the first cycle discharge capacity).

From Table 1 it can be seen that Cell 1 (90:10 native particles:fibres) failed after 175 to 185 cycles. Some delamination of the electrode material was observed on failure.

Cell 2 (10:90 native particles:fibres) failed after 130 to 170 cycles. However, the non delamination of the composite anode was observed.

Cell 3 (50:50 native particles:pillared particles) failed after more than 300 cycles. The integrity of the composite anode was maintained throughout.

Composition			Coat Composition Si:Binder:Graphite:C	Density of Coating Material	Porosity of Coating	No Cycles charging cell to 1200mAh/g or 1.95mAh/cm ²	No Cycles charging cells to 1900mAh/g or 1.9mAh/cm ²	No Cycles charging cells to 1100mAh/g or 1.6mAh/cm ²	Fibre dimensions	Particle dimensions	ppSi dimensions
Fibre	Powder	ppSi From J318									
10	90		70:14:4:12	0.79g/cc	69%	175-185			(d) 150- 200nm (l) 10- 15µm	4.5µm Silgrain® J230 powder from Elkem of Norway	(d)25µm pillar height:3- 4µm Prepared by etching Silgrain® J318 powder particles
90	10		70:14:4:12	0.43g/cc	83%		130-170				
	50	50	70:12:12:6					>300			

Table 1

1 Cells were continuously charged and discharged to and from the capacity indicated using constant current conditions until the cell capacity dropped to

below 80% of its initial value. The number of cycles indicates the cycle number at which this drop in capacity occurred.

Claims

1. A composition comprising a plurality of elongate elements and a plurality of particles, the elongate elements and particles each comprising a metal or semi-metal selected from one or more of the group comprising silicon, tin, germanium and aluminium or mixtures thereof, characterised in that
 - a. the elongate elements are selected from one or more of the group comprising fibres, tubes, ribbons and flakes and
 - b. the particles are selected from one or more of the group comprising pillared particles, porous particles and porous particle fragments.
2. A composition according to claim 1 modified in that
 - a. the elongate elements are selected from one or more of the group comprising fibres having a diameter in the range 100 to 500nm, tubes, ribbons and flakes; and
 - b. the particles comprise native silicon particles.
3. A composition according to claim 1 or claim 2, modified in that
 - a. the elongate element is a pillared particle; and
 - b. the particles are selected from one or more of the group comprising native particles, porous particles and porous particle fragments.
4. A composition according to any one of the preceding claims, wherein the particles have an average diameter in the range 80nm to 15µm and include particles selected from one or more of:
 - a. native particles having an average diameter in the range 1 to 8µm, with a D₅₀ of 4µm;
 - b. porous particles comprising a random or ordered network of linear, branched or layered elongate elements having one or more discrete or interconnected void spaces or channels defined there between.
 - c. pillared particles have an overall diameter in the range 20 to 30µm;
 - d. pillared particles having a principle diameter in the range 5 to 15µm;
 - e. pillared particles having a principle diameter in the range 15 to 25µm;
 - f. pillared particles having a principle diameter in the range 25 to 35µm; and
 - g. pillared particles have a pillar length of up to 10µm.
5. A composition according to any one of the preceding claims, wherein the elongate elements are selected from one or more of:
 - a. fibres having a diameter in the range 150 to 200nm and a length in the range 10 to 15µm

- b. ribbons having a thickness in the range 0.08 μ m to 1 μ m, a width in the range 240nm to 300nm, a length in the range 0.8 μ m to 20 μ m and an aspect ratio in the range 10:1 to 200:1;
 - c. flakes having a thickness in the range 80nm to 100nm, a width in the range 0.8 μ m to 10 μ m, a length in the range 0.8 μ m to 20 μ m and an aspect ratio in the range 10:1 to 200:1; and
 - d. tubes having a wall thickness in the range 0.08 μ m to 2 μ m, an outer wall diameter of between 2.5 and 100 times larger than the wall thickness and a length of between 10 and 500 times as large as the wall thickness.
- 6. A composition according to any one of the preceding claims, wherein the diameter of the particles is at least three times the diameter of the elongate element and the weight ratio of the electroactive elongate elements to electroactive particles is in the range 9:1 to 1:9.
- 7. A composition according to any one of claims 1 to 6, wherein the diameter of the particle is not more than three times the diameter of the elongate elements and the volume ratio of the electroactive particles to electroactive elongate elements is in the range 2:1 to 0.5:1.
- 8. A composition according to any one of claims 1 to 6, wherein:
 - a. the volume of the elongate elements is more than that of the particles; and
 - b. the diameter of the particle is less than twice the length of the elongate element.
- 9. A composition according to any one of the preceding claims, wherein the metal or semi-metal is a silicon comprising material selected from substantially pure silicon, silicon alloy and a material selected from silicon oxide, silicon nitride and silicon boride or mixtures thereof wherein optionally at least some of the elongate elements or particles comprise silicon with a purity in the range 90% to 99.95%.
- 10. A composition according to any one of the preceding claims, which comprises 50 to 90% by weight of an electroactive material and optionally one or more components selected from a binder, a conductive material, and optionally a non-silicon comprising electroactive material.
- 11. A composition according to any one of the preceding claims, wherein the electroactive material comprises 40 to 100% by weight silicon comprising elongate elements, silicon comprising particles and further silicon comprising components.
- 12. A composition according to any one of the preceding claims comprising 70wt% of a silicon-comprising material comprising a mixture of silicon-comprising fibres and silicon-comprising native particles in a ratio of from 90:10 to 10:90, 14wt% of a binder

comprising polyacrylic acid or an alkali metal salt thereof, 4wt% of graphite and 12wt% of a conductive carbon.

13. A composition according to any one of claims 1 to 11, comprising 70wt% of a silicon-comprising material comprising a 50:50 mixture of native particles and pillared particles, 12wt% of a binder comprising polyacrylic acid or an alkali metal salt thereof, 12wt% graphite and 6wt% of a conductive carbon

14. A method of manufacturing a composition according to any one of claims 1 to 13, comprising the steps of mixing

a. a plurality of metal or semi-metal comprising elongate elements selected from one or more of the group comprising fibres, tubes, threads, ribbons and flakes with

b. a plurality of metal or semi-metal comprising particles selected from one or more of the group comprising pillared particles, native particles, porous particles and porous particle fragments with the proviso that when the elongate elements are fibres or threads, these fibres or threads have a diameter in the range 100 to 500nm; and

c. optionally combining the elongate elements and particles according to paragraphs (a) and (b) with a binder or with one or more components selected from the group comprising a conductive material, a viscosity adjuster, a filler, a cross-linking accelerator, a coupling agent and an adhesive accelerator, and wherein optionally the metal or semi-metal comprising elongate elements or particles are silicon comprising elongate elements or particles.

15. A method according to claim 14 modified in that

a. the elongate element is a pillared particle; and

b. the particles are selected from one or more of the group comprising native particles, porous particles and porous particle fragments, wherein optionally the metal or semi-metal comprising elongate elements or particles are silicon comprising elongate elements or particles.

16. Use of a composition according to any one of claims 1 to 13, in the manufacture of a secondary battery.

17. An electrode comprising a current collector and a composition according to any one of claims 1 to 13.

18. A battery comprising a cathode, an anode comprising a material according to any one of claims 1 to 13 and an electrolyte.

19. A device employing a battery according to claim 18.