

Compositions and methods for dental mineralization

Field of the invention

The present invention relates to compositions for mineralizing a dental surface, in particular tooth enamel. Methods of mineralizing hypomineralized lesions (including
5 subsurface lesions) in the tooth enamel caused by various conditions such as dental caries, dental corrosion and fluorosis are also provided.

Background of the invention

Common causes of hypomineralized lesions are caries and fluorosis.

Dental caries result from the demineralization of hard tissue of the teeth usually
10 because of fermentation of dietary sugar by dental plaque odontopathogenic bacteria. Dental caries is still a major public health problem. Further, restored tooth surfaces can be susceptible to further dental caries around the margins of the restoration. Even though the prevalence of dental caries has decreased through the use of fluoride in most developed countries, the disease remains a major public health problem. Dental
15 erosion or corrosion is the loss of tooth mineral by dietary or regurgitated acids. Dental hypersensitivity is due to exposed dentinal tubules through loss of the protective mineralized layer, cementum. Dental calculus is the unwanted accretion of calcium phosphate minerals on the tooth surface. All these conditions, dental caries, dental erosion, dental hypersensitivity and dental calculus are therefore imbalances in the level
20 of calcium phosphates.

Enamel fluorosis (mottling) has been recognized for nearly a century, however, the aetiological role of fluoride was not identified until 1942. The characteristic appearance of fluorosis may be differentiated from other enamel disturbances. The clinical features of fluorotic lesions of enamel (FLE) represent a continuum ranging from fine opaque
25 lines following the perikymata, to chalky, white enamel. The presence of a comparatively highly mineralized enamel outer surface and a hypomineralized subsurface in the fluorotic lesion simulates the incipient enamel "white spot" carious lesion. With increasing severity, both the depth of enamel involved in the lesion and the degree of hypomineralization increases. The development of fluorosis is highly
30 dependent on the dose, duration and timing of fluoride exposure and is believed to be related to elevated serum fluoride concentrations. Chalky "white spot" lesions may also

form on developing teeth in children such as after treatment with antibiotics or fever. Such lesions indicate areas of hypomineralization (i.e. too little mineralization) of the tooth enamel.

Depending on lesion severity, fluorosis has been managed clinically by restorative replacement or micro-abrasion of the outer enamel. These treatments are unsatisfactory because they involve restorations or removal of tooth tissue. What is desired is a treatment that will mineralize the hypomineralized enamel to produce a natural appearance and structure.

Specific complexes of casein phosphopeptides and amorphous calcium phosphate ("CPP-ACP", available commercially as Recaldent®) have been shown to remineralize enamel subsurface lesions *in vitro* and *in situ* (Reynolds, 1998; Shen *et al.*, 2001; Reynolds *et al.*, 2003).

WO 98/40406 in the name of The University of Melbourne (the contents of which are herein incorporated fully by reference) describes casein phosphopeptide-amorphous calcium phosphate complexes (CPP-ACP) and CPP-stabilized amorphous calcium fluoride phosphate complexes (CPP-ACFP) which have been produced at alkaline pH. Such complexes have been shown to prevent enamel demineralization and promote remineralization of enamel subsurface lesions in animal and human *in situ* caries models (Reynolds, 1998). Improved casein phosphopeptide-amorphous calcium phosphate complexes (CPP-ACP) and CPP-stabilized amorphous calcium fluoride phosphate complexes (CPP-ACFP) have also been described in WO2006/056013 and WO2006/135982.

The CPP which are active in forming the complexes do so whether or not they are part of a full-length casein protein. Examples of active (CPP) that can be isolated after tryptic digestion of full length casein have been specified in US Patent No. 5,015,628 and include peptides Bos α_{s1} -casein X-5P (f59-79), Bos β -casein X 4P (f1-25), Bos α_{s2} -casein X-4P (f46-70) and Bos α_{s2} -casein X-4P (f1-21).

There is a need to provide improved or alternative treatments for hypomineralized lesions.

Reference to any prior art in the specification is not, and should not be taken as, an acknowledgment or any form of suggestion that this prior art forms part of the common general knowledge in Australia or any other jurisdiction or that this prior art could

reasonably be expected to be ascertained, understood and regarded as relevant by a person skilled in the art.

Summary of the invention

- In one aspect, the present invention provides a method of mineralizing a dental surface or subsurface comprising contacting the dental surface or subsurface with a compound that is capable of increasing or maintaining the pH of a solution and a mineralizing agent. Preferably, the mineralizing agent is stabilized amorphous calcium phosphate (ACP) and/or amorphous calcium fluoride phosphate (ACFP). Typically, the compound is capable of maintaining the pH of a solution between 7 to 9, preferably about 7.5.
- 5 Preferably, the compound is provided in an amount effective to raise the pH of intra-lesion fluid of a dental lesion from 6 to 7.5. The compound is capable of increasing the pH of a solution that has an acidic pH (i.e. less than pH 7). The dental surface is preferably dental enamel. In one embodiment the dental surface is a lesion in the enamel, such as a lesion caused by caries, dental erosion or fluorosis.
- 10 A compound which is capable of increasing or maintaining the pH of a solution includes a compound which can accept hydrogen cations (protons) or, more generally, donate a pair of valence electrons. Preferably, the compound is a base. The compound may not necessarily normally be regarded as a base, for example a polypeptide with numerous acidic and basic residues but nonetheless has the ability to maintain or increase the pH
- 20 of a solution between 7 to 9, preferably 7.5. The compound is capable of increasing the pH of a solution that has an acidic pH (i.e. less than pH 7). For example, the compound is capable of increasing the pH of the acidic intra-lesion fluid of a subsurface lesion requiring remineralisation. Preferably, the compound is provided in an amount effective to raise the pH of intra-lesion fluid of a dental lesion from 6 to 7.5. In one embodiment, a
- 25 compound which is capable of increasing or maintaining the pH of a solution is an alkali which has the capacity to release hydroxide ions.

A compound which is capable of increasing or maintaining the pH of a solution also includes a compound that can maintain as a buffer the pH of a neutral or basic solution (i.e. pH greater than or equal to 7) when the neutral or basic solution is exposed to an acid. Typically, the compound is capable of maintaining the pH of a solution between 7

30 to 9, preferably about 7.5.

Any pharmaceutically acceptable compounds described as a base are suitable for use in the invention. Typically, the base is suitable for oral use. Preferably, the compound

acts as a base, i.e. only releases hydroxide ions or donates electrons, in the presence of an acid. The base may be a free-base form, or in a pharmaceutically acceptable salt form. Non-limiting examples of bases suitable for use in the invention include hydroxides, chlorides, borates, phosphates including hydrogen phosphates and dihydrogen phosphates, citrates, carbonates, bicarbonates, hypochlorites (such as sodium hypochlorite), amines and any salt forms thereof including an alkali metal salt forms. More specifically, non-limiting examples of suitable pharmaceutically acceptable bases include ammonium hydroxide, sodium hydroxide, potassium hydroxide, lithium hydroxide, calcium hydroxide, magnesium hydroxide, ferrous hydroxide, zinc hydroxide, sodium hypochlorite, copper hydroxide, aluminum hydroxide, ferric hydroxide, isopropylamine, trimethylamine, diethylamine, triethylamine, tripropylamine, ethanolamine, 2-dimethylaminoethanol, 2-diethylaminoethanol, lysine, arginine, histidine or urea. A hypofluorite capable of acting as a base as described herein is also useful in the invention as the agent for increasing or maintaining pH. A suitable hypofluorite would react *in situ*, being a surface or subsurface lesion, to produce fluoride ions and hydroxide (or another base) ions. As one skilled in the art will appreciate a potentially favourable outcome of the production of fluoride ions is that fluoride ions can substitute for hydroxide in the crystal structure of apatite forming fluorapatite.

Preferably the ACP and/or ACFP is phosphopeptide (PP)-stabilized. Preferably, the phosphopeptide (as defined below) is a casein phosphopeptide. Preferably, the ACP or ACFP is in the form of a casein phosphopeptide stabilized ACP or ACFP complex.

In a preferred embodiment, the phosphopeptide stabilized amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP) complex has tightly bound and loosely bound calcium, wherein the tightly bound calcium in the complex is less than the tightly bound calcium in an ACP or ACFP complex formed at a pH of 7.0. Optionally, the ACP or ACFP is predominantly in a basic form.

In a preferred embodiment, the calcium ion content of the stabilized ACP or ACFP complex is in the range of about 30 to 100 moles of calcium per mole of PP. More preferably, the calcium ion content is in the range of about 30 to about 50 moles of calcium per mole of PP.

In any aspect or embodiments as described herein, the stabilized ACP and/or ACFP may be in a formulation with additional calcium phosphate. Typically, the formulation

includes a PP stabilized ACP and/or ACFP complex together with at least an equal amount by weight of calcium phosphate.

In a preferred embodiment the ACP and/or ACFP is in the form of a casein phosphopeptide stabilized ACP and/or ACFP complex.

- 5 Preferably, the phase of the ACP is predominantly a basic phase, wherein the ACP comprises predominantly the species Ca^{2+} , PO_4^{3-} and OH^- . The basic phase of ACP may have the general formula $[\text{Ca}_3(\text{PO}_4)_2]_x[\text{Ca}_2(\text{PO}_4)(\text{OH})]$ where $x \geq 1$. Preferably $x = 1-5$. More preferably, $x = 1$. Preferably the two components of the formula are present in equal proportions. Accordingly, in one embodiment, the basic phase of ACP has the
10 formula $\text{Ca}_3(\text{PO}_4)_2\text{Ca}_2(\text{PO}_4)(\text{OH})$.

- Preferably, the phase of the ACFP is predominantly a basic phase, wherein the ACFP comprises predominantly the species Ca^{2+} , PO_4^{3-} and F^- . The basic phase of ACFP may have the general formula $[\text{Ca}_3(\text{PO}_4)_2]_x[\text{Ca}_2(\text{PO}_4)\text{F}]_y$ where $x \geq 1$ when $y = 1$ or where $y \geq 1$ when $x = 1$. Preferably, $y = 1$ and $x = 1-3$. More preferably, $y = 1$ and $x =$
15 1. Preferably the two components of the formula are present in equal proportions. Accordingly, in one embodiment, the basic phase of ACFP has the formula $\text{Ca}_3(\text{PO}_4)_2\text{Ca}_2(\text{PO}_4)\text{F}$.

In one embodiment, the ACP complex consists essentially of phosphopeptides, calcium, phosphate and hydroxide ions and water.

- 20 In one embodiment, the ACFP complex consists essentially of phosphopeptides, calcium, phosphate, fluoride and hydroxide ions and water.

- In a further aspect of the present invention there is provided a method of mineralizing a dental surface comprising providing a compound which is capable of increasing or maintaining the pH of a solution and a source of ACP or ACFP. In a preferred
25 embodiment the dental surface is enamel. Preferably the compound which is capable of increasing or maintaining the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

- In a further aspect of the present invention there is provided a method for treating
30 fluorosis comprising contacting a fluorotic lesion in tooth enamel with a compound which is capable of increasing or maintaining the pH of a solution and stabilized ACP and/or ACFP. Preferably the compound which is capable of increasing or maintain the pH of a

solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In a further aspect of the present invention there is provided a method for treating dental caries comprising contacting a caries lesion in tooth enamel with a compound which is capable of increasing or maintaining the pH of a solution and stabilized ACP and/or ACFP. Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In a further aspect of the present invention there is provided a method for treating dental erosion comprising contacting a lesion in tooth enamel caused by erosion with a compound which is capable of increasing or maintaining the pH of a solution and stabilized ACP and/or ACFP. Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In a further aspect of the present invention there is provided a method for reducing white spot lesions on the tooth enamel comprising contacting a white spot lesion with a compound which is capable of increasing or maintaining the pH of a solution and stabilized ACP and/or ACFP. Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In a further aspect of the present invention there is provided a method for remineralizing a lesion in tooth enamel comprising contacting the lesion with a compound which is capable of increasing or maintaining the pH of a solution and stabilized ACP and/or ACFP. Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In a further aspect of the invention there is provided a method for remineralizing a lesion in tooth enamel comprising contacting the lesion with stabilized ACP and/or ACFP followed by administering a composition containing sodium bicarbonate or urea. Preferably, the composition is a mouthrinse or mouthwash containing sodium bicarbonate or urea.

In one embodiment, the compound which is capable of increasing or maintaining the pH of a solution is not sodium hypochlorite (NaOCl) and a composition of the invention is sodium hypochlorite (NaOCl) free.

5 In any aspect or embodiment of the invention described herein, the compound which is capable of increasing or maintaining the pH of a solution is administered concurrently with, as a pre-treatment to, or as a post-treatment to a source of stabilized ACP or ACFP. Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

10 In any aspect or embodiment of the invention described herein, the compound which is capable of increasing or maintaining the pH of a solution is administered concurrently with or as a post-treatment to a source of stabilized ACP or ACFP. Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium
15 bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In any aspect or embodiment of the invention described herein, the compound which is capable of increasing or maintaining the pH of a solution and stabilized ACP or ACFP is applied to the mouth, tooth or lesion by the subject in need of treatment or by a dental health care professional.

20 In any aspect or embodiment of the invention described herein, the ACP and/or ACFP is phosphopeptide (PP)-stabilized. Preferably, the phosphopeptide (as defined below) is a casein phosphopeptide. Preferably, the ACP or ACFP is in the form of a casein phosphopeptide stabilized ACP or ACFP complex.

The compound which is capable of increasing or maintaining the pH of a solution may
25 be contacted with the dental surface for a period of about 1 to 60 minutes, or for about 1 to 30 minutes. In one embodiment, the compound which is capable of increasing or maintaining the pH of a solution is contacted with the dental surface for about 20 minutes.

Preferably the stabilized ACP and/or ACFP are contacted with the dental surface for a
30 period of about 1 minute to 2 hours, or 5 minutes to 60 minutes or about 10 minutes. The stabilized ACP and/or ACFP may be repeatedly applied to the dental surface over a period of 1 day to several months.

In one embodiment, the compound which is capable of increasing or maintaining the pH of a solution is contacted with the dental surface 1 to 60 minutes, or 1 to 30 minutes, or 1 to 5 minutes prior to contacting the dental surface with the stabilized ACP and/or ACFP.

- 5 In one embodiment, the compound which is capable of increasing or maintaining the pH of a solution is contacted with the dental surface 1 to 60 minutes, or 1 to 30 minutes, or 1 to 5 minutes after contacting the dental surface with the stabilized ACP and/or ACFP.

In a further aspect of the present invention there is provided a method for mineralizing a tooth surface comprising applying a stabilized ACP and/or ACFP complex and a
10 compound which is capable of increasing or maintaining the pH of a solution to a tooth surface. Preferably the tooth surface is tooth enamel. Typically, the tooth surface is tooth enamel containing a lesion selected from the group consisting of one or more of a white spot lesion; a fluorotic lesion; a caries lesion; or a lesion caused by tooth erosion. Preferably, the stabilized ACP and/or ACFP complex and a compound which is capable
15 of increasing or maintaining the pH of a solution is contained in the same composition that is applied to the tooth surface. Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

- 20 In one embodiment, the dental surface is in need of such treatment. Therefore the invention includes in addition to the steps of any method described herein a step of identifying a subject suffering fluorosis, dental caries, dentinal hypersensitivity or dental calculus, a white spot lesion; a fluorotic lesion; a caries lesion; or a lesion caused by tooth erosion.

- 25 In one aspect, the present invention provides a composition for mineralizing a dental surface or subsurface comprising a compound that is capable of increasing or maintaining the pH of a solution and a mineralizing agent. Preferably, the mineralizing agent is stabilized amorphous calcium phosphate (ACP) and/or amorphous calcium fluoride phosphate (ACFP). Preferably, the compound that is capable of increasing or
30 maintaining the pH of a solution is present in an amount effective to raise the pH of a dental lesion from 6.0 to 7.5. Preferably, the compound that is capable of increasing or maintaining the pH of a solution is any one or more of the compounds described herein,

preferably a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

Any composition described herein may be a physiologically acceptable composition formulated as a toothpaste, toothpowder, liquid dentifrice, mouthwash, mouthrinse, mouth spray, varnish, dental cement, troche, chewing gum, lozenge, dental paste, gingival massage cream, gargle tablet, dairy product and other foodstuffs.

Any composition described herein can be used in any one of the methods described herein. The composition is a physiologically acceptable composition as described herein.

In another aspect, the present invention provides a composition comprising a compound that is capable of increasing or maintaining the pH of a solution and a mineralizing agent for use in mineralizing a dental surface or subsurface. Preferably, the mineralizing agent is stabilized amorphous calcium phosphate (ACP) and/or amorphous calcium fluoride phosphate (ACFP). Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In a further aspect, there is provided a method of treating or preventing one or more of each of dental caries, tooth decay, dental erosion and fluorosis, comprising the steps of administering a compound capable of increasing or maintaining the pH of a solution to the teeth of a subject followed by administering an ACP or ACFP complex or composition. Topical administration of the complex is preferred. The method preferably includes the administration of the complex in a formulation as described above. Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In a further aspect there is provided the use of a compound capable of increasing or maintaining the pH of a solution and a stabilized amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP) in the manufacture of a composition for the treatment and/or prevention of one or more of dental caries, tooth decay, dental erosion and fluorosis. Preferably the compound which is capable of increasing or maintain the pH of a solution is a base. The base may be any base described herein,

including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In a further aspect there is provided a composition comprising as an active agent a compound capable of increasing or maintaining the pH of a solution and a stabilized
5 amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP) for mineralizing a dental surface or subsurface. Typically, mineralizing a dental surface or subsurface is for the treatment and/or prevention of one or more of dental caries, tooth decay, dental erosion and fluorosis.

In any method or use of the invention there is further provided a step of applying a
10 source of fluoride ions. The source of fluoride ions may be applied simultaneously as the compound which is capable of increasing or maintaining the pH of a solution and the source of ACP or ACFP. Alternatively, the source of fluoride ions may be applied prior to, or after, the compound which is capable of increasing or maintaining the pH of a solution, or the source of ACP or ACFP.

15 The present invention also provides a composition comprising a compound that is capable of increasing or maintaining the pH of a solution and a mineralizing agent. Preferably, the mineralizing agent is stabilized-amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP). Preferably, the composition further includes a pharmaceutically acceptable carrier, diluent or excipient. Preferably the
20 compound which is capable of increasing or maintaining the pH of a solution is a base. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

In a preferred embodiment of each aspect of the invention, the phosphopeptide stabilized amorphous calcium phosphate (ACP) or amorphous calcium fluoride
25 phosphate (ACFP) complex in the composition has tightly bound and loosely bound calcium, wherein the bound calcium in the complex is less than the tightly bound calcium in an ACP or ACFP complex formed at a pH of 7.0. Optionally, the ACP or ACFP is predominantly in a basic form.

In another preferred embodiment of each aspect of the invention, the calcium ion
30 content of the stabilized ACP or ACFP complex in the composition is in the range of about 30 to 100 moles of calcium per mole of PP. More preferably, the calcium ion content is in the range of about 30 to about 50 moles of calcium per mole of PP.

In any embodiment, the ACP and/or ACFP in the composition can be in the form of a casein phosphopeptide stabilized ACP and/or ACFP complex.

In another aspect the invention is a physiologically acceptable composition including stabilized amorphous calcium phosphate (ACP) and/or amorphous calcium fluoride phosphate (ACFP) as described herein, a base and an excipient, diluent or carrier suitable for oral administration. The base may be any base described herein, including, but not limited to, sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

The invention also relates to a kit for the treatment or prevention of one or more of dental caries, fluorosis and dental erosion including (a) a compound capable of increasing or maintaining the pH of a solution and (b) a stabilized-ACP and/or stabilized-ACFP complex in a pharmaceutically acceptable carrier. Desirably, the kit further includes instructions for their use for the mineralization of a dental surface in a patient in need of such treatment. The instructions may describe the use of the kit to treat or prevent one or more of each of dental caries, tooth decay, dental erosion and fluorosis. In one embodiment, the agent and the complex are present in suitable amounts for treatment of a patient. Preferably, the stabilized ACP and/or ACFP is phosphopeptide (PP)-stabilized. Preferably, the phosphopeptide (as defined below) is a casein phosphopeptide. Preferably, the ACP or ACFP is in the form of a casein phosphopeptide stabilized ACP or ACFP complex.

The composition or kit of the invention may further include a source of fluoride ions. The fluoride ions may be from any suitable source. A source of fluoride ions may include free fluoride ions or fluoride salts. Examples of sources of fluoride ions include, but are not limited to the following: sodium fluoride, sodium monofluorophosphate, stannous fluoride, sodium silicofluoride, silver fluoride, amine fluoride or any metal ion fluoride salt. A source of fluoride ions may be a hypofluorite. These sources of fluoride ions may be provided in solution (typically an aqueous solution), or a suspension.

Detailed description of the embodiments

Further aspects of the present invention and further embodiments of the aspects described in the preceding paragraphs will become apparent from the following description, given by way of example and with reference to the accompanying drawings. It will be understood that the invention disclosed and defined in this specification extends to all alternative combinations of two or more of the individual features

mentioned or evident from the text or drawings. All of these different combinations constitute various alternative aspects of the invention.

Reference will now be made in detail to certain embodiments of the invention. While the invention will be described in conjunction with the embodiments, it will be understood
5 that the intention is not to limit the invention to those embodiments. On the contrary, the invention is intended to cover all alternatives, modifications, and equivalents, which may be included within the scope of the present invention as defined by the claims.

One skilled in the art will recognize many methods and materials similar or equivalent to those described herein, which could be used in the practice of the present invention.

10 The present invention is in no way limited to the methods and materials described.

All of the patents and publications referred to herein are incorporated by reference in their entirety.

For purposes of interpreting this specification, terms used in the singular will also include the plural and vice versa.

15 As used herein, except where the context requires otherwise, the term "comprise" and variations of the term, such as "comprising", "comprises" and "comprised", are not intended to exclude further additives, components, integers or steps. As used herein, except where the context requires otherwise, "comprise" and "include" can be used interchangeably.

20 In one aspect, the present invention provides a method of mineralizing a dental surface or subsurface comprising contacting the dental surface or subsurface with a compound that is capable of increasing or maintaining the pH of a solution and a mineralizing agent. A dental subsurface is typically a hypomineralized lesion such that the compound and mineralizing agent contacted to the dental surface migrates through any surface
25 layer, i.e. pellicle and/or plaque, through the porous dental surface to the region requiring mineralization. Preferably, the mineralizing agent is stabilized amorphous calcium phosphate (ACP) and/or amorphous calcium fluoride phosphate (ACFP). The dental surface is preferably dental enamel. The dental surface may be a lesion in the enamel, such as a lesion caused by caries, dental erosion or fluorosis.

30 Any compound that is capable of increasing or maintaining the pH of a solution can be used in the method of the present invention. Without being bound by any theory or mode of action it is believed that the maintenance of a basic pH during intra-lesion

mineralization minimises any restriction on the mineralization process by any acidic molecular species. Therefore, it is believed that the compound which is capable of increasing or maintaining the pH of a solution promotes mineralization by neutralising acid produced during the mineralization process.

- 5 Mineralization of dental surfaces can be significantly enhanced by increasing the pH of a lesion during the process of mineralization. In particular, it has been found that the mineralization of enamel by stabilized soluble forms of ACP (CPP-ACP) and ACFP (CPP-ACFP) is enhanced by a compound that increases the intra-lesion pH if the intra-lesion pH is acidic or maintains the intra-lesion pH if the intra-lesion pH is neutral or
10 basic. For example, during the development of caries, the pH of the intra-lesion fluid may be 6 or below. The compound one that can raise, or maintain, the pH at which remineralization of a hypomineralised surface or subsurface can occur.

The compound which is capable of increasing or maintaining the pH of a solution may be contacted with the dental surface for a period of about 1 to 60 minutes, or for about 1
15 to 30 minutes. In one embodiment, the compound which is capable of increasing or maintaining the pH of a solution is contacted with the dental surface for about 20 minutes. An example of how this is achieved is formulating the compound into an oral composition, such as a paste, and then contacting or applying the composition to the dental surface. The oral composition, such as a paste, has sufficient viscosity to be
20 retained on the tooth for the required time period.

Preferably the stabilized ACP and/or ACFP is contacted with the dental surface for a period of about 1 minute to 2 hours, or 5 minutes to 60 minutes or about 10 minutes. The stabilized ACP and/or ACFP may be repeatedly applied to the dental surface over a period of 1 day to several months.

- 25 In one embodiment, the compound which is capable of increasing or maintaining the pH of a solution is contacted with the dental surface 1 to 60 minutes, or 1 to 30 minutes, or 1 to 5 minutes prior to contacting the dental surface with the stabilized ACP and/or ACFP.

In one embodiment, the compound which is capable of increasing or maintaining the pH
30 of a solution is contacted with the dental surface 1 to 60 minutes, or 1 to 30 minutes, or 1 to 5 minutes after contacting the dental surface with the stabilized ACP and/or ACFP.

In a further aspect of the present invention there is provided a method for mineralizing a tooth surface comprising applying an ACP and/or ACFP complex and a compound which is capable of increasing or maintaining the pH of a solution to a tooth surface. Preferably the tooth surface is tooth enamel. Typically, the tooth surface is tooth enamel containing a lesion selected from the group consisting of one or more of a white spot lesion; a fluorotic lesion; a caries lesion; or a lesion caused by tooth erosion.

In one embodiment, the dental surface is in need of such treatment. Therefore, in another aspect, the invention includes in addition to the steps of any method described herein a step of identifying a subject suffering fluorosis, dental caries, dentinal hypersensitivity or dental calculus, a white spot lesion; a fluorotic lesion; a caries lesion; or a lesion caused by tooth erosion.

In another aspect, the present invention provides a composition comprising a compound that is capable of increasing or maintaining the pH of a solution and a mineralizing agent for use in mineralizing a dental surface or subsurface.

A compound which is capable of increasing or maintaining the pH of a solution includes a compound which can accept hydrogen cations (protons) or, more generally, donate a pair of valence electrons. Preferably, the compound may commonly be a base. The compound is capable of increasing the pH of a solution that has an acidic pH (i.e. less than pH 7). Preferably, the compound is capable of raising the pH of intra-lesion fluid of a dental lesion from 6 to 7.5. In one embodiment, a compound which is capable of increasing or maintaining the pH of a solution is an alkali which has the capacity to release hydroxide ions.

A compound which is capable of increasing or maintaining the pH of a solution also includes a compound that can maintain as a buffer the pH of a neutral or basic solution (i.e. pH greater than or equal to 7) when the neutral or basic solution is exposed to an acid. Typically, the compound is capable of maintaining the pH of a solution between 7 to 9, preferably about 7.5. As used herein reference to the increasing or maintaining the pH of a solution includes increasing or maintaining the pH the fluid in a subsurface lesion, i.e. intra-lesion fluid.

Any pharmaceutically acceptable compounds described as a base are suitable for use in the invention. Typically, the base is suitable for oral use. Preferably, the compound acts as a base, i.e. only releases hydroxide ions or donates electrons, in the presence of an acid. The base may be a free-base form, or in a pharmaceutically acceptable salt

form. Non-limiting examples of bases suitable for use in the invention include hydroxides, chlorides, borates, phosphates including hydrogen phosphates and dihydrogen phosphates, citrates, carbonates, bicarbonates, hypochlorites, amines and any salt forms thereof including an alkali metal salt forms. More specifically, non-limiting
5 examples of suitable pharmaceutically acceptable bases include ammonium hydroxide, sodium hydroxide, potassium hydroxide, lithium hydroxide, calcium hydroxide, magnesium hydroxide, ferrous hydroxide, zinc hydroxide, copper hydroxide, aluminum hydroxide, ferric hydroxide, isopropylamine, trimethylamine, diethylamine, triethylamine, tripropylamine, ethanolamine, 2-dimethylaminoethanol, 2-diethylaminoethanol, lysine,
10 arginine, histidine. A hypofluorite capable of acting as a base as described herein is also useful in the invention as the agent for increasing or maintaining pH. A suitable hypofluorite would react in situ to produce fluoride ions and hydroxide (or another base) ions. One skilled in the art will appreciate that fluoride ions can substitute for hydroxide in the crystal structure of apatite forming fluorapatite.

15 A stabilized-ACP or ACFP complex as described in the current specification may be the "closed" complexes are shown in Figure 2 of Cross *et al.*, 2007 *Current Pharmaceutical Design*, 13, 793-800.

A stabilized-ACP or ACFP complex as referred to herein includes a stabilized-ACP or ACFP complex as described in WO2006/056013 the contents of which are incorporated
20 by reference.

In a preferred embodiment, the phosphopeptide stabilized amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP) complex has tightly bound and loosely bound calcium, wherein the bound calcium in the complex is less than the tightly bound calcium in an ACP or ACFP complex formed at a pH of 7.0.

25 Optionally, the ACP or ACFP is predominantly in a basic form.

A stabilized-ACP or ACFP complex as referred to herein include a stabilized-ACP or ACFP complex formed at a pH of below 7.0. Preferably the complex is formed at a pH in the range of about 5.0 up to but below 7.0. More preferably the complex is formed at a pH range of about 5.0 to about 6.0. In a preferred embodiment, the complex is formed
30 at a pH of about 5.0 or about 5.5. Preferably, the ACP or ACFP in the complex is predominantly in a basic form.

A stabilized-ACP may be produced by a method comprising the steps of:

- (i) obtaining a solution comprising at least one phosphopeptide and;
- (ii) admixing solutions comprising calcium ions, phosphate ions and hydroxide ions, while maintaining the pH at about 7.0 or below.

A stabilized ACFP may be produced by a method comprising the steps of:

- 5 (i) obtaining a solution comprising at least one phosphopeptide and;
- (ii) admixing solutions comprising calcium ions, phosphate ions, hydroxide ions and fluoride ions, while maintaining the pH at about 7.0 or below.

The hydroxide ions may be titrated into the solution to maintain the phosphopeptide solution at an essentially constant pH. The calcium and phosphate ions may be titrated
10 into the phosphopeptide solution with constant mixing and at a rate that avoids the formation of a calcium phosphate precipitate in the phosphopeptide solution.

A phosphopeptide stabilized amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP) complex may also include wherein the ACP in the complex has tightly bound and loosely bound calcium, wherein the tightly bound calcium
15 in the complex is less than the tightly bound calcium in an ACP or ACFP complex formed at a pH of 7.0 and the ACP or ACFP is predominantly in a basic form, obtainable or obtained by a method comprising:

- a) admixing a first solution comprising calcium ions, a second solution comprising phosphate ions, and optionally a third solution comprising
20 fluoride ions, to a solution comprising phosphopeptides and a solvent with a pH of from about 5 up to but below 7; and
- b) maintaining the pH of the solution at about 5.0 up to but below 7.0 during the admixing by adding hydroxide ions.

"Tightly" and "loosely" bound calcium and phosphate can be determined using analytical
25 ultrafiltration as shown in Example 2. Briefly, the solution of phosphopeptide, calcium, phosphate and optionally fluoride admixed while maintaining the pH at about 7.0 or below can be first filtered through a 0.1 micron filter to remove free calcium and phosphate that is not associated with the complexes. This free calcium and phosphate is present in the filtrate and discarded. Any free calcium or phosphate that is not
30 associated in any way with the complexes would not be bioavailable, i.e. delivered by the phosphopeptide to the tooth. The retentate from the 0.1 micron filtration can be

further analyzed by centrifugation through a 3000 mw cutoff filter at 1,000 g for 15 min. The resulting filtrate contains calcium and phosphate that is loosely bound or associated with the complexes. At this centrifugal force calcium and phosphate that is not tightly bound to the complexes are released and move into the filtrate. The calcium and phosphate that is tightly bound in the complexes is retained in the retentate. The amount of tightly bound calcium and phosphate in the retentate can then be determined by subtracting the amount of calcium and phosphate in the filtrate from the total amount of calcium and phosphate in the retentate of the 0.1 micron filtration.

A stabilized-ACP or ACFP complex as referred to herein include a stabilized-ACP or ACFP complex as described in WO2006/135982 the contents of which are incorporated by reference.

A "superloaded" phosphopeptide or phosphoprotein (PP) is a phosphopeptide or phosphoprotein that has been superloaded with calcium and phosphate ions. The calcium ions of the superloaded PP may be in the range 30-1000 mol Ca per mole of PP, or in the range of 30-100 or 30-50 mole Ca per mole of PP. In another embodiment, the mol Ca per mol of PP is at least 25, 30, 35, 40, 45 or 50. It can be a stabilized-amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP) complex. The complex may be formed at any pH (eg 3-10). Preferably the phosphopeptide includes the sequence -A-B-C-, where A is a phosphoamino acid, preferably phosphoserine, B is any amino acid including a phosphoamino acid and C is glutamic acid, aspartic acid or a phosphoamino acid. The phosphoamino acid may be phosphoserine.

In one aspect, the present invention includes a phosphopeptide or phosphoprotein (PP) stabilized amorphous calcium phosphate or amorphous calcium fluoride phosphate complex having a calcium ion content greater than about 30 moles of calcium per mole of PP. In a preferred embodiment, the calcium ion content is in the range of about 30 to 100 moles of calcium per mole of PP. More preferably, the calcium ion content is in the range of about 30 to about 50 moles of calcium per mole of PP.

The invention also provides a phosphopeptide or phosphoprotein (PP) stabilized-amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP) complex produced by a method comprising the steps of:

- (i) obtaining solutions comprising calcium, inorganic phosphate and fluoride (optional); and

- (ii) admixing (i) with a solution comprising PP-ACP.

In a preferred embodiment, the PP is casein phosphopeptide (CPP).

In a further aspect, the present invention also includes use of a formulation of a PP stabilized ACP and/or ACFP complex together with at least an equal amount by weight of calcium phosphate. Preferably the calcium phosphate is CaHPO_4 or calcium lactate or any other soluble calcium phosphate compound. Preferably, the calcium phosphate (e.g. CaHPO_4) is dry blended with the PP stabilized ACP and/or ACFP complex. In a preferred embodiment, the PP-ACP and/or PP-ACFP complex: calcium phosphate ratio is about 1:1-50, more preferably about 1: 1-25, more preferably about 1:5-15. In one embodiment, the PP-ACP and/or PP-ACFP complex: calcium phosphate ratio is about 1:10.

The oral care formulation that includes a phosphopeptide or phosphoprotein (PP) stabilized amorphous calcium phosphate (ACP) and/or amorphous calcium fluoride phosphate (ACFP) complex having a calcium ion content greater than about 30 moles of calcium per mole of PP when used in the oral cavity may be produced by a method including the steps of:

- (i) obtaining a powder including a PP-ACP and/or PP-ACFP complex;
- (ii) dry blending with an effective amount of calcium phosphate; and
- (iii) formulating the dry blended PP-ACP and/or PP-ACFP and calcium phosphate mixture into an oral care formulation.

Preferably, the form of calcium phosphate for dry blending is any soluble calcium phosphate including, but not limited to, CaHPO_4 , Ca_2HPO_4 and calcium lactate.

The present invention also provides a method of mineralizing a dental surface or subsurface including the steps of:

- (i) contacting the dental surface with a protein disrupting agent, and
- (ii) contacting the dental surface with a composition of the invention.

The dental surface is preferably dental enamel. In one embodiment the dental surface is a lesion in the enamel, such as a lesion caused by caries, dental erosion or fluorosis. Any suitable protein disrupting agent can be used in the method of the present invention. The agent is required to reduce the proteinaceous barrier formed over the surface to be treated, such as the pellicle over teeth. Examples of suitable agents

include bleach, detergent, chaotropic agents such as urea, high phosphate concentrations, cocktails of proteases (e.g. endopeptidases, proteinases and exopeptidases) and any other protein solubilizing, disrupting or hydrolysing agent. Examples of suitable bleaches include sodium hypochlorite (NaOCl), and cabamide
5 peroxide bleaches. In a preferred embodiment, the bleach is an alkaline bleach. In a further preferred embodiment the alkaline bleach is NaOCl. The protein disrupting agent acts to solubilize and partially or wholly remove proteins from the dental surface, particularly proteins of the pellicle.

A composition as described herein may further include free fluoride ions. The fluoride
10 ions may be from any suitable source. A source of fluoride ions may include free fluoride ions or fluoride salts. Examples of sources of fluoride ions include, but are not limited to the following: sodium fluoride, sodium monofluorophosphate, stannous fluoride, sodium silicofluoride and amine fluoride. These may be provided in solution (typically an aqueous solution), or a suspension.

15 The fluoride ions are preferably present in the composition in an amount greater than 1ppm. More preferably, the amount is more than 3 ppm. In another embodiment, it is preferably more than 10 ppm. In typical embodiments described below, the amount may be several hundred or thousand ppm. The fluoride content is typically measured as a ppm in oral compositions in the manner commonly used in the art. Where the
20 fluoride is provided from a source with the stabilized ACP, the ppm refers to the concentration of the fluoride in that source, typically a solution or suspension of bioavailable fluoride.

In any aspect or embodiments as described herein, the stabilized ACP and/or ACFP is phosphopeptide (PP)-stabilized. Preferably, the phosphopeptide (as defined below) is a
25 casein phosphopeptide. Preferably, the ACP or ACFP is in the form of a casein phosphopeptide stabilized ACP or ACFP complex.

"Phosphopeptide" in the context of the description of this invention means an amino acid sequence in which at least one amino acid is phosphorylated. Preferably, the phosphopeptide includes one or more of the amino acid sequence -A-B-C-, where A is a
30 phosphoamino residue, B is any amino acyl residue including a phosphoamino residue and C is selected from a glutamyl, aspartyl or phosphoamino residue. Any of the phosphoamino residues may independently be a phosphoserine residue. B is desirably a residue the side-chain of which is neither relatively large nor hydrophobic. It may be Gly,

Ala, Val, Met, Leu, Ile, Ser, Thr, Cys, Asp, Glu, Asn, Gln or Lys. Preferably at least two of the phosphoamino acids in the sequence are preferably contiguous. Preferably the phosphopeptide includes the sequence A-B-C-D-E, where A, B, C, D and E are independently phosphoserine, phosphothreonine, phosphotyrosine, phosphohistidine, glutamic acid or aspartic acid, and at least two, preferably three, of the A, B, C, D and E are a phosphoamino acid. In a preferred embodiment, the phosphoamino acid residues are phosphoserine, most preferably three contiguous phosphoserine residues. It is also preferred that D and E are independently glutamic or aspartic acid.

In one embodiment, the ACP or ACFP is stabilized by a casein phosphopeptide (CPP), which is in the form of intact casein or fragment of the casein, and the complex formed preferably has the formula $[CPP(ACP)_6]_n$ or $[(CPP)(ACFP)_6]_n$ where n is equal to or greater than 1, for example 6. The complex formed may be a colloidal complex, where the core particles aggregate to form large (eg 100 nm) colloidal particles suspended in water. Thus, the PP can be a casein protein or a phosphopeptide.

The PP may be from any source; it may be present in the context of a larger polypeptide, including a full length casein polypeptide, or it may be isolated by tryptic or other enzymatic or chemical digestion of casein, or other phosphoamino acid rich proteins such as phosphitin, or by chemical or recombinant synthesis, provided that it comprises the sequence -A-B-C- or A-B-C-D-E as described above. The sequence flanking this core sequence may be any sequence. However, those flanking sequences in α_{s1} (59-79), β (1-25), α_{s2} (46-70) and α_{s2} (1-21) are preferred. The flanking sequences may optionally be modified by deletion, addition or conservative substitution of one or more residues. The amino acid composition and sequence of the flanking region are not critical.

The phosphopeptide may be selected from any described in WO2006/056013, WO2006/135982 or US Patent No. 5,015,628.

Examples of conservative substitutions are shown in Table 1 below.

TABLE 1

Original Residue	Exemplary Conservative Substitution	Preferred Conservative Substitution
Ala	Val, Leu, Ile	Val
Asn	Gln Lys His Phe	Gln

Original Residue	Exemplary Conservative Substitution	Preferred Conservative Substitution
Gln	Asn	Asn
Gly	Pro	Pro
Ile	Leu, Val, Met, Ala, Phe	Leu
Leu	Ile, Val, Met, Ala, Phe	Ile
Lys	Arg, Gln, Asn	Arg
Phe	Leu, Val, Ile, Ala	Leu
Pro	Gly	Gly
Ser	Thr	Thr
Val	Ile, Leu, Met, Phe, Ala	Leu
Asp	Glu	Glu
Thr	Ser	Ser
Trp	Tyr	Tyr
Tyr	Trp Phe Thr Ser	Phe

The flanking sequences may also include non-naturally occurring amino acid residues. Commonly encountered amino acids which are not encoded by the genetic code, include:

- 5 2-amino adipic acid (Aad) for Glu and Asp;
- 2-aminopimelic acid (Apm) for Glu and Asp;
- 2-aminobutyric (Abu) acid for Met, Leu, and other aliphatic amino acids;
- 2-aminoheptanoic acid (Ahe) for Met, Leu and other aliphatic amino acids;
- 2-aminoisobutyric acid (Aib) for Gly;
- 10 cyclohexylalanine (Cha) for Val, and Leu and Ile;
- homoarginine (Har) for Arg and Lys;
- 2, 3-diaminopropionic acid (Dpr) for Lys, Arg and His;
- N-ethylglycine (EtGly) for Gly, Pro, and Ala;
- N-ethylasparagine (EtAsn) for Asn, and Gln;
- 15 Hydroxyllysine (Hyl) for Lys;

- allohydroxylysine (AHyl) for Lys;
- 3-(and 4) hydroxyproline (3Hyp, 4Hyp) for Pro, Ser, and Thr;
- alloisoleucine (Alle) for Ile, Leu, and Val;
- p-amidinophenylalanine for Ala;
- 5 N-methylglycine (MeGly, sarcosine) for Gly, Pro, Ala.
- N-methylisoleucine (Melle) for Ile;
- Norvaline (Nva) for Met and other aliphatic amino acids;
- Norleucine (Nle) for Met and other aliphatic amino acids;
- Ornithine (Orn) for Lys, Arg and His;
- 10 Citrulline (Cit) and methionine sulfoxide (MSO) for Thr, Asn and Gln;
- N-methylphenylalanine (MePhe), trimethylphenylalanine, halo (F, Cl, Br and I) phenylalanine, triflourylphenylalanine, for Phe.

In one embodiment, the PP is one or more phosphopeptides selected from the group consisting of $\alpha_{s1}(59-79)$, $\beta(1-25)$, $\alpha_{s2}(46-70)$ and $\alpha_{s2}(1-21)$.

- 15 In another embodiment of the invention, the stabilized ACFP or ACP complex and a compound capable of increasing or maintaining the pH of a solution is incorporated into oral compositions such as toothpaste, mouth washes or formulations for the mouth to aid in the prevention and/or treatment of dental caries, tooth decay, dental erosion or fluorosis. The ACFP or ACP complex may comprise 0.01-50% by weight of the
- 20 composition, preferably 1.0-50%. For oral compositions, it is preferred that the amount of the CPP-ACP and/or CPP-ACFP administered is 0.01 - 50% by weight, preferably 1.0% - 50% by weight of the composition. In a particularly preferred embodiment, the oral composition of the present invention contains about 2% CPP-ACP, CPP-ACFP or a mixture of both. The oral composition of this invention which contains the above-
- 25 mentioned agents may be prepared and used in various forms applicable to the mouth such as dentifrice including toothpastes, toothpowders and liquid dentifrices, mouthwashes, mouthrinses, mouth sprays, varnish, dental cement, troches, chewing gums, dental pastes, gingival massage creams, gargle tablets, dairy products and other foodstuffs. The oral composition according to this invention may further include
- 30 additional well known ingredients depending on the type and form of a particular oral composition.

In certain preferred forms of the invention the oral composition may be substantially liquid in character, such as a mouthwash, rinse or spray. In such a preparation the vehicle is typically a water-alcohol mixture desirably including a humectant as described below. Generally, the weight ratio of water to alcohol is in the range of from about 1:1 to about 20:1. The total amount of water-alcohol mixture in this type of preparation is typically in the range of from about 70 to about 99.9% by weight of the preparation. The alcohol is typically ethanol or isopropanol. Ethanol is preferred.

In other desirable forms of this invention, the composition may be substantially solid or pasty in character, such as toothpowder, a dental tablet or a toothpaste (dental cream) or gel dentifrice. The vehicle of such solid or pasty oral preparations generally contains dentally acceptable polishing material. Examples of polishing materials are water-insoluble sodium metaphosphate, potassium metaphosphate, tricalcium phosphate, dihydrated calcium phosphate, anhydrous dicalcium phosphate, calcium pyrophosphate, magnesium orthophosphate, trimagnesium phosphate, calcium carbonate, hydrated alumina, calcined alumina, aluminium silicate, zirconium silicate, silica, bentonite, and mixtures thereof. Other suitable polishing material include the particulate thermosetting resins such as melamine-, phenolic, and urea-formaldehydes, and cross-linked polyepoxides and polyesters. Preferred polishing materials include crystalline silica having particle sizes of up to about 5 microns, a mean particle size of up to about 1.1 microns, and a surface area of up to about 50,000 cm²/g., silica gel or colloidal silica, and complex amorphous alkali metal aluminosilicate.

When visually clear gels are employed, a polishing agent of colloidal silica, such as those sold under the trademark SYLOID as Syloid 72 and Syloid 74 or under the trademark SANTOCEL as Santocel 100, alkali metal aluminosilicate complexes are particularly useful since they have refractive indices close to the refractive indices of gelling agent-liquid (including water and/or humectant) systems commonly used in dentifrices.

Many of the so-called "water insoluble" polishing materials are anionic in character and also include small amounts of soluble material. Thus, insoluble sodium metaphosphate may be formed in any suitable manner, for example as illustrated by Thorpe's Dictionary of Applied Chemistry, Volume 9, 4th Edition, pp. 510-511. The forms of insoluble sodium metaphosphate known as Madrell's salt and Kurrol's salt are further examples of suitable materials. These metaphosphate salts exhibit only a minute solubility in water,

and therefore are commonly referred to as insoluble metaphosphates (IMP). There is present therein a minor amount of soluble phosphate material as impurities, usually a few percent such as up to 4% by weight. The amount of soluble phosphate material, which is believed to include a soluble sodium trimetaphosphate in the case of insoluble metaphosphate, may be reduced or eliminated by washing with water if desired. The insoluble alkali metal metaphosphate is typically employed in powder form of a particle size such that no more than 1% of the material is larger than 37 microns.

The polishing material is generally present in the solid or pasty compositions in weight concentrations of about 10% to about 99%. Preferably, it is present in amounts from about 10% to about 75% in toothpaste, and from about 70% to about 99% in toothpowder. In toothpastes, when the polishing material is silicious in nature, it is generally present in an amount of about 10-30% by weight. Other polishing materials are typically present in amount of about 30-75% by weight.

In a toothpaste, the liquid vehicle may comprise water and humectant typically in an amount ranging from about 10% to about 80% by weight of the preparation. Glycerine, propylene glycol, sorbitol and polypropylene glycol exemplify suitable humectants/carriers. Also advantageous are liquid mixtures of water, glycerine and sorbitol. In clear gels where the refractive index is an important consideration, about 2.5 - 30% w/w of water, 0 to about 70% w/w of glycerine and about 20-80% w/w of sorbitol are preferably employed.

Toothpaste, creams and gels typically contain a natural or synthetic thickener or gelling agent in proportions of about 0.1 to about 10, preferably about 0.5 to about 5% w/w. A suitable thickener is synthetic hectorite, a synthetic colloidal magnesium alkali metal silicate complex clay available for example as Laponite (e.g. CP, SP 2002, D) marketed by Laporte Industries Limited. Laponite D is, approximately by weight 58.00% SiO₂, 25.40% MgO, 3.05% Na₂O, 0.98% Li₂O, and some water and trace metals. Its true specific gravity is 2.53 and it has an apparent bulk density of 1.0 g/ml at 8% moisture.

Other suitable thickeners include Irish moss, iota carrageenan, gum tragacanth, starch, polyvinylpyrrolidone, hydroxyethylpropylcellulose, hydroxybutyl methyl cellulose, hydroxypropyl methyl cellulose, hydroxyethyl cellulose (e.g. available as Natrosol), sodium carboxymethyl cellulose, and colloidal silica such as finely ground Syloid (e.g. 244). Solubilizing agents may also be included such as humectant polyols such propylene glycol, dipropylene glycol and hexylene glycol, cellosolves such as methyl

cellosolve and ethyl cellosolve, vegetable oils and waxes containing at least about 12 carbons in a straight chain such as olive oil, castor oil and petrolatum and esters such as amyl acetate, ethyl acetate and benzyl benzoate.

It will be understood that, as is conventional, the oral preparations will usually be sold or otherwise distributed in suitable labelled packages. Thus, a jar of mouth rinse will have a label describing it, in substance, as a mouth rinse or mouthwash and having directions for its use; and a toothpaste, cream or gel will usually be in a collapsible tube, typically aluminium, lined lead or plastic, or other squeeze, pump or pressurized dispenser for metering out the contents, having a label describing it, in substance, as a toothpaste, gel or dental cream.

Organic surface-active agents may be used in the compositions of the present invention to achieve increased prophylactic action, assist in achieving thorough and complete dispersion of the active agent throughout the oral cavity, and render the instant compositions more cosmetically acceptable. The organic surface-active material is preferably anionic, non-ionic or ampholytic in nature and preferably does not interact with the active agent. It is preferred to employ as the surface-active agent a detergent material which imparts to the composition detergent and foaming properties. Suitable examples of anionic surfactants are water-soluble salts of higher fatty acid monoglyceride monosulfates, such as the sodium salt of the monosulfated monoglyceride of hydrogenated coconut oil fatty acids, higher alkyl sulfates such as sodium lauryl sulfate, alkyl aryl sulfonates such as sodium dodecyl benzene sulfonate, higher alkylsulfo-acetates, higher fatty acid esters of 1,2-dihydroxy propane sulfonate, and the substantially saturated higher aliphatic acyl amides of lower aliphatic amino carboxylic acid compounds, such as those having 12 to 16 carbons in the fatty acid, alkyl or acyl radicals, and the like. Examples of the last mentioned amides are N-lauroyl sarcosine, and the sodium, potassium, and ethanolamine salts of N-lauroyl, N-myristoyl, or N-palmitoyl sarcosine which should be substantially free from soap or similar higher fatty acid material. The use of these sarconite compounds in the oral compositions of the present invention is particularly advantageous since these materials exhibit a prolonged marked effect in the inhibition of acid formation in the oral cavity due to carbohydrates breakdown in addition to exerting some reduction in the solubility of tooth enamel in acid solutions. Examples of water-soluble non-ionic surfactants suitable for use are condensation products of ethylene oxide with various reactive hydrogen-

containing compounds reactive therewith having long hydrophobic chains (e.g. aliphatic chains of about 12 to 20 carbon atoms), which condensation products ("ethoxamers") contain hydrophilic polyoxyethylene moieties, such as condensation products of poly (ethylene oxide) with fatty acids, fatty alcohols, fatty amides, polyhydric alcohols (e.g. sorbitan monostearate) and polypropyleneoxide (e.g. Pluronic materials).

The surface active agent is typically present in amount of about 0.1-5% by weight. It is noteworthy, that the surface active agent may assist in the dissolving of the active agent of the invention and thereby diminish the amount of solubilizing humectant needed.

Various other materials may be incorporated in the oral preparations of this invention such as whitening agents, preservatives, silicones, chlorophyll compounds and/or ammoniated material such as urea, diammonium phosphate, and mixtures thereof. These adjuvants, where present, are incorporated in the preparations in amounts which do not substantially adversely affect the properties and characteristics desired.

Any suitable flavouring or sweetening material may also be employed. Examples of suitable flavouring constituents are flavouring oils, e.g. oil of spearmint, peppermint, wintergreen, sassafras, clove, sage, eucalyptus, marjoram, cinnamon, lemon, and orange, and methyl salicylate. Suitable sweetening agents include sucrose, lactose, maltose, sorbitol, xylitol, sodium cyclamate, perillartine, AMP (aspartyl phenyl alanine, methyl ester), saccharine, and the like. Suitably, flavour and sweetening agents may each or together comprise from about 0.1% to 5% more of the preparation.

The compositions of this invention can also be incorporated in lozenges, or in chewing gum or other products, e.g. by stirring into a warm gum base or coating the outer surface of a gum base, illustrative of which are jelutong, rubber latex, vinylite resins, etc., desirably with conventional plasticizers or softeners, sugar or other sweeteners or such as glucose, sorbitol and the like. The composition of the invention may be a dual phase composition wherein each phase permits release of components over different time periods. For example, in use a dual phase composition may release stabilized ACP and/or ACFP, preferably CPP-ACP and/or CPP-ACFP, from a first phase at a faster rate than a compound that is capable of increasing or maintaining the pH of a solution from a second phase. Preferably, the dual phase composition is a dual phase chewing gum.

In a further aspect, the invention provides compositions including pharmaceutical compositions comprising any of the ACFP and/or ACP complexes as described above together with a compound capable of increasing or maintaining the pH of a solution and

a pharmaceutically-acceptable carrier. Such compositions may be selected from the group consisting of dental, anticariogenic compositions and therapeutic compositions. Dental compositions or therapeutic compositions may be in the form of a gel, liquid, solid, powder, cream or lozenge. Therapeutic compositions may also be in the form of tablets or capsules. In one embodiment, the ACP and/or ACFP complexes are substantially the only remineralizing active components of such a composition. For example, a crème formulation may be employed containing: water; glycerol; CPP-ACP; D-sorbitol; silicon dioxide; sodium carboxymethylcellulose (CMC-Na); propylene glycol; titanium dioxide; xylitol; phosphoric acid; guar gum; zinc oxide; sodium saccharin; ethyl p-hydroxybenzoate; magnesium oxide; butyl p hydroxybenzoate and propyl p-hydroxybenzoate.

The invention further includes a formulation described above provided together with instructions for its use to treat or prevent any one or more of dental caries or tooth decay, dental erosion and fluorosis.

In one embodiment, the active components of the composition consist essentially of the compound capable of increasing or maintaining the pH of a solution and stabilized ACP and/or ACFP. It is believed, without being bound by any theory or mode of action, that the stabilized ACP and/or ACFP and the compound capable of increasing or maintaining the pH of a solution are central to the therapeutic or preventative effect of the above embodiments of the invention, and thus embodiments consisting essentially of those components (with carriers, excipients and the like as required) are included within the scope of the invention.

The invention also relates to a kit for the treatment or prevention of one or more of dental caries, fluorosis and dental erosion including (a) a compound capable of increasing or maintaining the pH of a solution and (b) a CPP-ACP or CPP-ACFP complex in a pharmaceutically acceptable carrier. Desirably, the kit further includes instructions for their use for the mineralization of a dental surface in a patient in need of such treatment. The instructions may describe the use of the kit to treat or prevent one or more of each of dental caries, tooth decay, dental erosion and fluorosis. In one embodiment, the agent and the complex are present in suitable amounts for treatment of a patient. The instructions may direct the user to apply the a compound capable of increasing or maintaining the pH of a solution before, simultaneously or after a CPP-ACP or CPP-ACFP complex in a pharmaceutically acceptable carrier.

In another aspect a kit of the invention is constructed so that a compound capable of increasing or maintaining the pH of a solution is dispensed simultaneously or after a CPP-ACP or CPP-ACFP complex in a pharmaceutically acceptable carrier.

- 5 In a further aspect, there is provided a method of treating or preventing one or more of each of dental caries, tooth decay, dental erosion and fluorosis, comprising the steps of administering a compound capable of increasing or maintaining the pH of a solution to the teeth of a subject followed by administering an ACP or ACFP complex or composition. Topical administration of the complex is preferred. The method preferably includes the administration of the complex in a formulation as described above.
- 10 In a further aspect there is provided the use of a compound capable of increasing or maintaining the pH of a solution and a stabilized amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP) in a manufacture of a composition for the treatment and/or prevention of one or more of dental caries, tooth decay, dental erosion and fluorosis.
- 15 In a further aspect there is provided a composition comprising as an active agent a compound capable of increasing or maintaining the pH of a solution and a stabilized amorphous calcium phosphate (ACP) or amorphous calcium fluoride phosphate (ACFP) for mineralizing a dental surface or subsurface. Typically, mineralizing a dental surface or subsurface is for the treatment and/or prevention of one or more of dental caries,
- 20 tooth decay, dental erosion and fluorosis.

According to a further aspect of the invention there is provided a composition for dental restoration, including a dental restorative material to which has been added a composition of the invention. The base of the dental restorative material can be a glass ionomer cement, a composite material or any other restorative material which is

25 compatible. It is preferred that the amount of stabilized ACP or ACFP, preferably CPP-ACP complex or CPP-ACFP complex, included in the dental restorative material is 0.01-80% by weight, preferably 0.5 10% and more preferably 1-5% by weight. The dental restorative material of this invention which contains the above mentioned agents may be prepared and used in various forms applicable to dental practice. The dental

30 restorative material according to this embodiment may further include other ions, eg. antibacterial ions Zn^{2+} , Ag^+ , etc or other additional ingredients depending on the type and form of a particular dental restorative material. It is preferable that the pH of dental restorative material according to this embodiment be between 2-10, more preferably 5-9

and even more preferably 5-7. It is preferable that the pH of the dental restorative material containing the CPP-ACP complex or ACP complex be in the range of about 2 to 10, more preferably in the range of about 5 to 9 and even more preferably in the range of about 5 to 7.

- 5 According to a further aspect of the invention there is provided a varnish including a compound that is capable of increasing or maintaining the pH of a solution and a mineralizing agent. Preferably, the mineralizing agent is any stabilized ACP and/or ACP complex as described herein.

10 It will be clearly understood that, although this specification refers specifically to applications in humans, the invention is also useful for veterinary purposes. Thus in all aspects the invention is useful for domestic animals such as cattle, sheep, horses and poultry; for companion animals such as cats and dogs; and for zoo animals.

The invention will now be further described with reference to the following non-limiting examples.

- 15 One example of a mineralizing composition or agent comprises the following (in decreasing order of proportion):

water

glycerol

CPP-ACP

20 D-sorbitol

silicon dioxide

sodium carboxymethylcellulose (CMC-Na)

propylene glycol

titanium dioxide

25 xylitol

phosphoric acid

guar gum

zinc oxide

sodium saccharin

ethyl p-hydroxybenzoate

magnesium oxide

butyl p-hydroxybenzoate

propyl p-hydroxybenzoate

- 5 Such a composition is available from GC corporation under the name Tooth Mousse™. This is suitable for use after a compound capable of increasing or maintaining the pH of a solution and is in the form of a paste or crème to facilitate its retention on teeth for a suitable period. Alternatively, this mineralizing composition may contain a compound capable of increasing or maintaining the pH of a solution.

10 **Example 1**

Preparation of CPP-ACFP and CPP-ACP solutions

Stock solutions of 3.25M CaCl₂, 1.25 M Na₂HPO₄, 1M NaOH and 1M NaF were added in approximately thirty aliquots to a 10 - 15 % w/v tryptic digest of casein until a final concentration of approximately 78 mM Ca²⁺, 48 mM phosphate and 12 mM fluoride
15 concentrations were obtained. The solutions were added slowly (that is, less than approximately 1% volume addition per minute). An aliquot of the phosphate solution was added first, followed by an aliquot of the calcium solution. The pH was maintained at 7.0, 6.5, 6.0, 5.5 and 5.0 using the NaOH with thorough mixing. The sodium hydroxide solution was added automatically by a pH stat with the addition of the
20 hydroxide ions usually being after each addition of the calcium ions. After addition of the calcium ions, phosphate ions, hydroxide ions and fluoride ions the solution was filtered through a 0.1 micron filter to concentrate 1-2 fold. The retentate may be washed with water to remove salts and inactive (and bitter tasting) peptides if desired. CPP-ACP solutions were prepared as above without the addition of fluoride.

25 **Example 2**

Determining loosely and tightly bound calcium and phosphate

At the completion of the titration and filtration for each pH in Example 1, a sample of each retentate was taken and less than 10% collected as a filtrate using a 3000 molecular weight cut-off Centriprep 3 ultrafiltration membrane. The Centripreps
30 containing the samples were centrifuged at 1,000 g for 15 min in a Beckman J2-21 centrifuge using a JA 10.5 rotor. The original sample before Centriprep centrifugation

and a sample of the filtrate after Centriprep centrifugation were taken for analysis of calcium, phosphate and fluoride concentrations. The analysis of the original sample gave total calcium, phosphate and fluoride ion concentrations and the analysis of the filtrate gave loosely bound calcium, phosphate and fluoride concentrations. The difference between the total and loosely bound concentrations is the tightly bound concentration of Ca, Pi and F by the CPP.

Example 3

Preparation of CPP-ACFP and CPP-ACP solutions

Recaldent® (CPP-ACP) was purchased from Recaldent Pty Ltd, Victoria, Australia. The product (#841117) contained 14.3% calcium, 22.3% phosphate and 47% casein phosphopeptide on a weight basis. The product was dissolved at 0.5% and adjusted to pH 5.5 by the addition of HCl. Calcium and phosphate ions were then added by titrating 3.25 M CaCl_2 and 2M NaH_2PO_4 while keeping the pH at 5.5 with the addition of 2.5 M NaOH. The titration of calcium and phosphate ions was continued until the solution became translucent. The concentration of calcium and phosphate added was recorded. The solution may also be formed by titrating calcium and phosphate ions into a 0.5% CPP-ACP solution and letting the pH fall to 5.5 by the addition of further calcium phosphate.

TABLE 2

Calcium and phosphate levels of normal and superloaded CPP-ACP

	Calcium		Phosphate	
	mmol/L	mol/mol CPP	mmol/L	mol/mol CPP
Normal 0.5% w/v CPP-ACP	17.8	22.8	11.6	14.8
Superloaded 0.5 w/v CPP-ACP (sCPP-ACP)	37.8	48.3	23.6	30.2

These results demonstrate that CPP-ACP can be superloaded with calcium and phosphate ions to produce thermodynamically stable complexes in a metastable solution.

Example 4

Preparation of a formulation of CPP-ACP and calcium phosphate

In another example Recaldent® (CPP-ACP) powder was dry blended with CaHPO₄ powder in the ratio CPP-ACP:CaHPO₄ equals 1:10 on a weight basis. This powder was

5 then added to sugar-free gum and toothpaste formulations at 1-5% w/w.

Example 5

A topical crème may be produced in accordance with the present invention having the following ingredients:

Water

10 glycerol

Stabilized ACP and/or ACFP

A compound capable of increasing or maintaining the pH of a solution

D-sorbitol

sodium carboxymethylcellulose (CMC-Na)

15 propylene glycol

silicon dioxide

titanium dioxide

xylitol

phosphoric acid

20 sodium fluoride

flavouring

sodium saccharin

ethyl p-hydroxybenzoate

propyl p-hydroxybenzoate

25 butyl p-hydroxybenzoate

Example 6

A mouthrinse formulation be produced in accordance with the present invention having the following composition:

	Water
	Alcohol
5	Poloxamer 407
	Sodium Lauryl Sulphate
	Stabilized ACP and/or ACFP
	A compound capable of increasing or maintaining the pH of a solution
	Sodium Fluoride
10	Flavours
	Sodium Saccharin
	Ethyl p-hydroxybenzoate
	Propyl p-hydroxybenzoate
	Butyl p-hydroxybenzoate

15 **Example 7**

A sugar-free chewing gum formulation be produced in accordance with the present invention having the following composition:

	Crystalline sorbitol/mannitol/xylitol
	Gum base
20	Calcium carbonate
	Glycerine
	Stabilized ACP and/or ACFP
	A compound capable of increasing or maintaining the pH of a solution
	Sodium Fluoride
25	Flavour oil
	Water

Example 8

The effectiveness of the invention could be demonstrated by the experiments described below. Seven premolar teeth with FLE (Thylstrup Fejerskov Index, TF = 3) could be selected from teeth extracted for orthodontic reasons from healthy patients aged 10-28 years from the Royal Dental Hospital of Melbourne, Australia. Informed patient consent should be obtained for the extracted teeth and the study protocol approved by the Human Research Ethics Committee of The University of Melbourne. All specimens should then be debrided of adherent soft tissue and stored in 18 % w/v formalin acetate solution at room temperature.

- 10 The teeth are then cleaned with a rotating rubber cup and pumice and rinsed in double de-ionized water (DDW) (Fejerskov et al., 1988). The anatomical crowns are sectioned from the roots using a water-cooled diamond blade. Each crown is sectioned to provide a pair of enamel blocks each containing a FLE. A 4x4 mm² window should be created over each lesion by placing a rectangular piece of Parafilm® (American National Can, Chicago, Ill., USA.) over the lesion and covering the surrounding enamel with nail varnish (Revlon™, New York, USA). The parafilm would then be carefully removed to reveal the enamel lesion window which was divided into halves as control and test windows. The control window was covered with nail varnish. The two lesions of each specimen should be randomly assigned to one of two remineralization groups; Group I – treatment with 5% w/v CPP-ACFP or CPP-ACP and Group II – treatment with 5% w/v CPP-ACFP or CPP-ACP immediately following pre-conditioning with a compound that is capable of increasing or maintaining the pH of a solution. Group II could alternatively be simultaneous addition of CPP-ACFP or CPP-ACP with a compound that is capable of increasing or maintaining the pH of a solution. Alternatively, Group II could be addition of CPP-ACP or CPP-ACFP followed by a compound that is capable of increasing or maintaining the pH of a solution.

CPP-ACFP is obtained from Recaldent Pty Ltd (Melbourne, Australia) and contains 47.6% w/w CPP, 15.7% w/w Ca²⁺, 22.9% w/w PO₄³⁻ and 1.2% w/w F⁻. The CPP-ACFP is dissolved in distilled and deionized water at 5% w/v and adjusted to pH 7.0 with HCl.

- 30 For the first group, each specimen should be placed in 2ml of 5 % w/v, CPP-ACFP in a 5ml plastic vial at 37°C. The CPP-ACFP solution should be changed daily for 10 days. For the second group, each specimen should be placed in solution containing a compound that is capable of increasing or maintaining the pH of a solution for 20mins,

rinsed and then placed in 2ml of 5 % w/v CPP-ACFP in a 5ml plastic vial at 37°C. The CPP-ACFP solution may be changed daily for 10 days.

5 A Chroma Meter (Minolta ChromaMeter CR241, Minolta, Japan) is used to record surface reflectance. Surface reflectance measurement is established in L*a*b* color space by the Commission de L'Eclairage in 1978, and measurements relate to human colour perception in three colour dimensions (Commision Internationale de L'Eclaige, 1978). The L* values represent colour gradients from white to black, a* values represent colour gradients from green to red, and b* values represent colour gradients from blue to yellow (Commision Internationale de L'Eclaige, 1978). Only L* value measurements
10 can be used with whiter colours having a higher reading, and darker colours a lower reading. To ensure a reproducible position of specimens in the Chroma Meter, a wax mold for each sample can be prepared and stored. All samples were air-dried with a dental triplex syringe for 60s before each measurement. Individual specimens can be repositioned ten times both before and after treatment, and colour reflectance L* values
15 were recorded.

Each specimen is removed from the mineralizing solution and rinsed in DDW for 60s and blotted dry with blotting paper. The nail varnish on the control window is removed gently with acetone. The control and test windows are then separated by cutting through the midline between the windows. The two half-slabs should then placed with the lesion
20 windows parallel and embedded in cold curing methacrylate resin (Paladur, Heraeus Kulzer, Germany). The two paired enamel half-slabs are sectioned, and subjected to microradiography and microdensitometric image analysis to determine mineral content exactly as described by Shen et al. (2001).

An area free of defects close to the midline of each microradiographic image of each
25 lesion (control and test) can be chosen and scanned six times (Shen et al., 2001). Each scan comprised 200 readings, taken from the enamel surface to the mid-enamel region to include the total fluorotic lesion. The test (CPP-ACFP-treated) lesion should be scanned to exactly the same depth as the control (untreated) lesion. The gray values obtained from each scan are converted to the equivalent thickness of aluminium (tA) using the image of the aluminium stepwedge included with each section (Shen et al.,
30 2001). Using the formula of Angmar et al. (1963), the percentage volume of mineral was obtained for each reading as follows: $V = (52.77(tA) - 4.54) / tS$. Where: V = volume of

mineral as a percentage; tA = the relative thickness of aluminium obtained from the gray value scanned; and tS = section thickness (80 μm).

From the densitometric profile of [(vol % min versus lesion depth (mm)] for each lesion DZ values were calculated using trapezoidal integration (Reynolds, 1997). The difference between the area under the profile of the untreated fluorotic enamel in the control window with adjacent normal enamel is designated DZ_f , and the difference between the area under the CPP-ACFP-treated fluorotic enamel in the test window and adjacent normal enamel is designated DZ_r . Percentage mineralization (%M) of the fluorotic lesion was therefore $(1 - DZ_r / (DZ_f) \times 100$ (Reynolds, 1997).

- Following the microradiography the sections containing both control and mineralized FLE can be subjected to Energy Dispersive X-ray Analysis (EDAX) as described previously (Reynolds, 1997). Mean L^* values can be compared using a one way classification analysis of variance (ANOVA) with a Scheffe multiple comparison. The mean %M values can also be compared using a one-way ANOVA. Overall mean L^* and %M values are analysed using a paired data Student's t-test.

Example 9

The Effect of Hypochlorite on Enamel Subsurface Remineralization by CPP-ACP.

- Human tooth enamel demineralized subsurface lesions were prepared using the method of Reynolds, (1997). J Dent Res 76:1587-1595. The enamel surface was removed by polishing to remove all adsorbed protein. This removed around 50 - 100 μm of enamel to expose an uncoated, polished enamel surface for the study. Furthermore, the acid buffer used to produce the subsurface lesions did not contain protein such that no protein would have entered these subsurface lesions. A 1% w/v CPP-ACP pH 5.0 solution was prepared using Recaldent® [Kraft Foods], a commercial source of CPP-ACP that is prepared as per Example 1 at a pH of 5.0. All blocks were remineralized with the 1% CPP-ACP pH 5 solution for 7 days at 37°C. However, half were exposed to a 1% v/v sodium hypochlorite solution for 1 min at the start of the CPP-ACP remineralization period. In other words, the sodium hypochlorite and CPP-ACP were simultaneously exposed to the subsurface lesion. After remineralization the enamel blocks were embedded, sectioned and subjected to transverse microradiography and densitometric image analysis as previously described by

Reynolds (1997) to determine percent mineral content gain (%Remineralization) shown in Table 3. A one way analysis of variance with differences in means determined using a Tukey HSD post hoc comparison showed that the treatment with hypochlorite significantly increased the level of remineralization by the CPP-ACP solution by 31%.

- 5 Without being bound by any theory or mode of action it is believed that the mechanism of enhanced CPP-ACP remineralization by the hypochlorite is related to the diffusion of the hypochlorite into the enamel subsurface lesions. Once in the lesion fluid it slowly decomposed, thereby releasing chlorine, oxygen, sodium and hydroxide ions.



- 10 This slow breakdown of the hypochlorite in the enamel subsurface lesion produced base (hydroxide ions) which increased the degree of saturation of hydroxyapatite in the intra-lesion fluid as a result of the additional hydroxide ions. It is believed that the formation of hydroxyapatite is inhibited by protons which may be released as ACP converts to hydroxyapatite or which are present in lower pH environments such as during
15 caries formation. In these ways, the additional hydroxide ions, or pH maintained at or above neutral, facilitates the formation of hydroxyapatite (mineralization) by the CPP-ACP in the lesion. Hence hypochlorite is a non-limiting example of an intra-lesion base producing compound that will drive remineralization by CPP-ACP or CPP-ACFP.

TABLE 3

- 20 Remineralization of Enamel Subsurface lesions by 1% w/v CPP-ACP with and without 1% v/v Hypochlorite treatment

Treatment	Lesion Depth	ΔZ_d	ΔZ_r	$\Delta Z_d - \Delta Z_r$	%Remin.
1% CPP-ACP	109.16 $\pm$ 11.89	3316.59 $\pm$ 601.49	2153.24 $\pm$ 417.85 ^c	1163.35 $\pm$ 352.97	34.82 $\pm$ 6.88
1% CPP-ACP and 1% Hypochlorite	106.65 $\pm$ 16.80	2986.46 $\pm$ 725.39	1629.30 $\pm$ 446.94	1357.16 $\pm$ 365.43	45.48 $\pm$ 5.49
p-value					p < 0.001

- It will be understood that the invention disclosed and defined in this specification extends to all alternative combinations of two or more of the individual features
25 mentioned or evident from the text or figures or tables. All of these different combinations constitute various alternative aspects of the invention.

REFERENCES

- Fejerskov O, Baelum V, Manji F, Moller I (1988). Dental Fluorosis - A handbook for health workers Copenhagen: Munksgard.
- 5 • Reynolds EC (1998). Anticariogenic complexes of amorphous calcium phosphate stabilized by casein phosphopeptides: a review. Spec Care Dentist 18:8-16.
- Reynolds EC, Cai F, Shen P, Walker GD (2003). Retention in plaque and remineralization of enamel lesions by various forms of calcium in a mouthrinse or sugar-free chewing gum. J Dent Res 82:206-11.
- 10 • Shen P, Cai F, Nowicki A, Vincent J, Reynolds EC (2001). Remineralization of enamel subsurface lesions by sugar-free chewing gum containing casein phosphopeptide-amorphous calcium phosphate. J Dent Res 80:2066-70.

CLAIMS

1. A kit for the treatment or prevention of one or more of dental caries, fluorosis and dental erosion including (a) a compound capable of increasing or maintaining the pH of a solution and (b) a mineralizing agent selected from a CPP-ACP or CPP-ACFP complex in a pharmaceutically acceptable carrier, wherein the compound that is capable of increasing or maintaining the pH of a solution contacts the dental surface or subsurface after the mineralizing agent.
2. Use of a mineralizing agent in the manufacture of a first composition and use of a compound that is capable of increasing or maintaining the pH of a solution in the manufacture of a second composition, the first and second compositions is to be used to mineralize a dental surface or subsurface, wherein the second composition is to be applied to the dental surface or subsurface after the first composition.
3. The use according to claim 2, wherein the dental surface is a lesion in enamel, caused by caries, dental erosion or fluorosis.
4. The use according to claim 2 or 3, wherein the mineralizing agent is stabilized amorphous calcium phosphate (ACP) and/or amorphous calcium fluoride phosphate (ACFP).
5. The use according to any one of claims 2 to 4, wherein the mineralizing agent is casein phosphopeptide stabilized amorphous calcium phosphate (CPP-ACP) and/or casein phosphopeptide stabilized amorphous calcium fluoride phosphate (CPP-ACFP).
6. The use according to claim 4 or 5, wherein the stabilized amorphous calcium phosphate (ACP) and/or amorphous calcium fluoride phosphate (ACFP) is in the form of a toothpaste, toothpowder, liquid dentifrice, mouthwash, mouthrinse, mouth spray, varnish, dental cement, troche, chewing gum, lozenge, dental paste, gingival massage cream, gargle tablet, dairy product and other foodstuffs.
7. The use according to any one of claims 2 to 6, wherein the compound that is capable of increasing or maintaining the pH of a solution is capable of producing hydroxide ions.
8. The use according to any one of claims 2 to 7, wherein the compound is capable of maintaining the pH of a solution between 7 to 9.

9. The use according to claim 8, wherein the compound is capable of maintaining the pH of a solution at about 7.5.

10. The use according to any one of claims 2 to 7, wherein the compound is provided in an amount effective to raise the pH of intra-lesion fluid of a dental lesion from 6 to 7.5.

11. The use according to any one of claims 2 to 10, wherein the compound that is capable of increasing or maintaining the pH of a solution is sodium bicarbonate, sodium hypochlorite, a hypofluorite or urea.

12. The use according to claim 11, wherein the sodium bicarbonate is provided in the form of a mouthrinse or mouthwash.

13. Use of a compound that is capable of increasing the pH of a solution that has an acidic pH in the manufacture of a composition for promoting mineralization of a dental surface or subsurface in a subject who has received a mineralizing agent to a dental surface or subsurface.