

METHOD OF PRODUCING BAMBOO FIBERS

This invention relates to an effective and efficient method of producing bamboo fibers in which the inner thin skin portion (medullary layer) of bamboo has been removed.

A method of producing fibers from bamboo has been proposed, for example, in Japanese Patent Laid-Open No. 63-7903, according to which bamboo fibers are obtained by explosive opening, which results in large variations in length and diameter of the obtained bamboo fibers. Thus, the method cannot be regarded as ideal for the production of fibers as a material for industrial use.

In view of this, the present inventors have proposed method of producing bamboo fibers quickly and efficiently (Japanese Patent Application Nos. 2-402672 and 3-193161) and, through subsequent study, they have found that, to produce bamboo fibers as a material for industrial use, it was desirable to remove the thin portion inside the bamboo. In the case, for example, of bamboo-fiber reinforced cement panels which are produced by mixing bamboo fibers with cement and shaping the mixture into panels, use of bamboo fibers from which the inner thin skin portion has been removed provides a flexural strength approximately 15% higher than when using bamboo fibers with the inner thin skin portion.

Accordingly, an object of the present invention is to provide a method which makes it possible to obtain bamboo fibers in which the inner

thin skin portion has been separated out.

In accordance with this invention, there is provided a method for producing bamboo fibers comprising a first step of crushing bamboo in the direction of its growth by means of a rolling machine; a second of fiberizing the crushed bamboo, obtained in the first step, by means of a hammer-mill-type grinding machine; and a third step of separating the inner thin skin portion bamboo from the bamboo fibers obtained in the second step.

Fig. 1 is a schematic diagram showing an apparatus used in the third step of the method of the invention.

The present invention will now be described in detail.

In accordance with this invention, bamboo is first crushed by a rolling machine and then fiberized by a hammer-mill-type grinding machine having a specific mechanism. The inner thin skin portion of the bamboo existing in the bamboo fibers is then separated therefrom.

First, leaves are removed from the felled bamboo, which is then passed through a rolling machine as it is or after being cut into pieces of a predetermined size, and is crushed by the rolling machine. The rolling machine used in the first step of the method of this invention may be a generally used-type such as a roll-type rolling machine or a stamping-type rolling machine. When the bamboo is cut into pieces, the size of the pieces must naturally be equal to or larger than the length of the fibers to be produced.

After the first step, the crushed bamboo is fiberized in the

second step by using a hammer-mill-type grinding machine having a specific mechanism. In the present invention the grinding machine may be a horizontal-type grinding machine such as an MHM series manufactured by Miike Tekkosho K.K., which machine comprises a hammer of a special configuration (fixed or suspended type). The hammer is attached to a tool holder (hammer holder) provided on the main spindle adapted to rotate at high speed. Bamboo is continuously fed into a hopper and instantaneously crushed to be fiberized by the impact cutting and crushing action of the hammer rotating at high speed, with the end of the hammer being appropriately spaced apart from the tool holder positioned above. The fibers are then adjusted to a desired length as they pass through a screen provided below, and are then continuously discharged from the grinding machine, thus providing bamboo fibers. It is not desirable to skip over the first step and process bamboo directly in the second step since most of bamboo will then be pulverized, resulting in a substantial reduction in the yield of fibers.

In the third step of this invention, the inner thin skin portion of bamboo, mixed in with the bamboo fibers obtained in the second step, is separated therefrom. The operation of the third step can be conducted ① by mechanically process or ② immersion process in water.

① Mechanical separation:

The mechanical separation process can be conducted by using, for example, an apparatus as shown in Fig. 1. This apparatus is based on an opening machine. The bamboo fibers obtained in the second step are

supplied from a chute 3 through a feed conveyor 4 to a pair of feeding rolls 5, from which they are scattered onto a conveyor 7 by way of a number of triangular teeth on a rotating drum 2 provided inside a housing 1. The rotating drum 2 is operated at high speed (at approximately 1000 r.p.m). The conveyor 7 only extends up to a position near the center line of the rotating drum 2, and the thin skin portion of the bamboo generally falls short of the conveyor and is collected in a thin skin portion collecting vessel 8 by a blade 6 that is mounted under the said conveyor 7.

② Separation by immersion in water:

When the bamboo fibers obtained in the second step are immersed in water, the thin skin portion of bamboo, which is mixed in with bamboo fibers, floats on the surface of the water as fragments. By removing there fragments, the bamboo fibers and the thin skin portion can be easily separated from each other.

The method of the present invention will be illustrated with reference to the following example, to which the invention is not intended to be limited.

Example 1

(1) First step for crushing bamboo by rolling:

The first step was executed by using a rolling machine equipped with a roll made of carbon steel (S45C) and having a diameter of 150mm, and an effective roll length of 500mm. The rolling operation was performed under the following condition: pressure: 25 kg/cm<sup>2</sup>; feeding roll speed:

15m/min.; and production rate: 180kg/hour. The bamboo used had been cut into pieces having a length of approximately 1m after having the leaves removed.

By the first step, the bamboo was split into sheaves along the direction of growth, each sheaf exhibiting a multitude of slits at intervals of approximately 0.1 to 3mm extending in the direction of growth.

(2) Second step for fiberizing bamboo by a hammer-mill-type grinding machine:

An MHM horizontal-type grinding machine manufactured by Miike Tekkosho K.K. was used as the hammer-mill-type grinding machine. A screen having a diameter of 25mm was provided at the bottom of the grinding machine, which was operated at 30 h.p. for one hour, thereby producing 120kg of bamboo fibers having a fiber length of 25mm. At this stage, the inner thin skin portion of bamboo was separated from and mixed in the bamboo fibers.

(3) Third step for separating the inner thin skin portion from the bamboo fibers:

① Mechanical separation

The drum 2 was rotated at a speed of approximately 1000 r.p.m., using an IM-34-type opening machine manufactured by Izuminami Seishinjo to effect separation. Assuming that the weight of the bamboo subjected to the first step when in the dry condition was 100%, the yield of bamboo fibers was: 97%, after the first step; 80%, after the second step; and 75%, after

the third step, with no thin skin portion existing in the bamboo fibers finally obtained.

② Separation by immersion in water

The bamboo fibers obtained in the second step were immersed in water, and the thin skin portion, floating on the surface of the water as fragments, was removed.

Upon visual inspection, practically no thin skin portion was found in the bamboo fibers processed by either method ① or ②.

Thus, the bamboo fiber producing method of this invention makes it possible to obtain bamboo fibers in which the inner thin skin portion of bamboo has been removed.



# CLAIMS

1. A method for producing bamboo fibers comprising:  
a first step of crushing bamboo in the direction of growth thereof by a rolling machine;  
a second step of fiberizing the crushed bamboo, obtained in the first step, by a hammer-mill-type grinding machine; and  
a third step of separating an inner thin skin portion of the bamboo, mixed in with the bamboo fibers obtained in the second step, from the bamboo fibers.
2. A method according to claim 1 wherein the rolling machine used in the first step is a roll-type rolling machine or a stamping-type rolling machine.
3. A method according to claim 1 wherein the third step is performed by mechanically process or immersion process in water.
4. A method for producing bamboo fibres, the method being substantially as hereinbefore described with reference to the accompanying drawing.