

#### Abstract

An Ni-based alloy powder containing, in mass%, 3.5-4.5% of Al, 0.8-4.0% of Cr, not more than 0.0100% of C, 0.001-0.050% of O, and 0.0001-0.0150% of N, the remaining portion being Ni and unavoidable impurities.

FIG. 1