

SPECIFICATION**Improvements in or relating to method and apparatus for manufacturing girdles****Background of the invention****5 I. Field of the invention**

This invention relates to the field of manufacturing girdles, and in particular, to a method and apparatus for applying stretch fabric liners to latex sheath girdles.

10 II. Prior art

It is known in the prior art to attach fabric liners to latex sheath girdles by means of cylindrical elements. The form on which the fabric element is stretched is a uniform or perfect cylinder. The form on which the latex film is applied is a cylinder which decreases in diameter, with its narrower end being first inserted into the uniform cylinder and first engaging the fabric element. It may be appreciated that an annular space is created between the outer surface of the form and the inner surface of the edge of this uniform cylinder on which the fabric element is mounted. It may also be appreciated that, as the cylindrical form is further inserted into the uniform cylindrical element, the annular space therebetween decreases because the diameter of the cylindrical form increases. This creates an everchanging annular space, which results in non-uniformity and lack of control over the interpenetration of the fabric element and the latex film. In the apparatus according to the present invention, the form is substantially flat. The only variations in shape are the substantially curved edges, which result in the form being widest in the middle, and narrowest at the ends. By way of further contrast, the uniform cylinder known in the prior art is replaced in the present invention with an annular rectangular frame. The dimensions of the frame and the form are such that in a preferred embodiment there are very close tolerances therebetween which just permit the form to be inserted through the frame, and then withdrawn. It may therefore be appreciated that the only space between the form and the frame which changes in any appreciable fashion is that between each side edge of the form and each edge of the frame. Due to the close tolerances, the longer sides of the form and the longer sides of the frame are substantially co-extensive. In fact, the circumferential interface between form and frame is constant over approximately 93% as the form travels through the frame since the sides are flat and only the edges are variable. The fabric liner, which is sewn or otherwise fastened so as to be closed at one end and slipped over the frame, is attached to the form as it is moved through the frame. The close tolerance between the form and the frame controls the depth to which the fabric liner is embedded into the latex film covering the form. It is therefore easier to control the uniform application of the fabric element to the latex sheath because the variable of the changing space described above is practically eliminated.

Summary of the invention

65 It is an object of the present invention to provide a greatly simplified method and apparatus for applying the fabric liners to latex sheath girdles.

It is another object of the present invention to provide a simplified method and apparatus for attaching a fabric liner to a latex sheath girdle, which application can be accomplished in a "one-step" operation.

70 It is still another object of the present invention to provide a latex sheath girdle, with a stretch fabric lining, which has desirable horizontal and vertical stretch characteristics.

It is yet another object of the present invention to provide a lined, latex sheath girdle having increased horizontal stretchability in the waist area and increased vertical stretchability in the lower back and buttocks area.

80 It is yet another object of the present invention to provide a simplified method and apparatus for manufacturing lined latex sheath girdles wherein the interpenetration of the fabric liner and the latex of the sheath is easily and uniformly controlled.

85 According to one aspect of the present invention, an apparatus for manufacturing girdles comprises:

a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath said form being without fabric securing means, and

95 a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages, without securing, the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

100 According to another aspect of the present invention, an apparatus for manufacturing girdles comprises:

a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath, and

105 a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the form having a non-conical shape, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

120 According to still another aspect of the present invention, an apparatus for manufacturing girdles comprises:

125 a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath, and a frame including structure defining an open

space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the form being movable through the frame along an axis, the form having a non-circular cross-section taken normal to the axis, which is of relatively small thickness and of relatively large width, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

According to yet another aspect of the present invention, an apparatus for manufacturing girdles comprises:

a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath, and a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the form being movable through the frame along an axis, the form having a non-circular cross-section taken normal to the axis, which has a large width to thickness ratio, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

According to yet another aspect of the present invention, an apparatus for manufacturing girdles comprises:

a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath, and a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the form being movable through the frame along an axis, the form having a non-circular cross-section taken normal to the axis, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

Preferably the form is substantially flat and has rounded edges.

The frame preferably comprises at least one roller member and means for mounting the roller member.

At least one brush member may be mounted on said frame.

The frame preferably comprises structure of two parallel sides and two joining ends.

According to yet another aspect of the present invention, a method of manufacturing girdles comprises the steps of:

forming an adherable latex sheath on a form having curved edges;

placing a fabric liner having a substantially

closed end over a frame, the frame having an opening comprising structure of two parallel sides and two joining ends and being of sufficient size to receive the form which has two parallel sides;

moving the form through the opening in the frame, so as to engage the closed end of the liner into contact with the coated form, whereby the fabric liner is transferred from the frame to the coated form.

Preferably, the form is substantially flat and has rounded edges.

The step of moving the form through the opening in the frame may comprise a controlled movement wherein the circumferential interface between the form and the frame remains substantially constant for approximately 93% of the total interface.

Preferably, the frame and form have relatively close tolerances in dimension, thereby controlling the interpenetration of the fabric liner and the latex sheath.

The method may further comprise the step of moving the form back out through the frame.

Briefly, the subject invention utilizes a flat form to which latex is applied in forming the latex sheath. The only variations in shape are the substantially curved edges, which result in the form being widest in the middle, and narrowest at the ends. An annular rectangular frame is utilized for holding the fabric liner, which is preferably a seamless sheath or sleeve, one end of which has been sewn or otherwise held together. The fabric liner is slipped over the frame, with the seamed end in the middle thereof. While the latex on the form is still tacky, the form is inserted through the frame, engaging the fabric liner at the sewn seam. As the form moves through the frame, the fabric liner slides over the edges of the frame and contacts the sides of the form. When the form has been fully inserted through the frame, the liner has been completely transferred onto the form. Close tolerance between the form and the frame just permit the form to be inserted therethrough and, at the same time, provide a means for automatically controlling the interpenetration of the fabric liner and the tacky latex film. In alternative embodiments, the frame is provided with either inwardly directed rollers or brushes, which provide the close tolerances with the form.

Brief description of the preferred embodiments

A girdle forming apparatus according to one of the presently preferred embodiments of the present invention is shown in Figure 1, and generally designated by numeral 10. The apparatus 10 is basically comprised of a form member generally designated 14 and a lower section generally designated by numeral 16.

The girdle form 14 has a non-conical shape and is preferably flat. It may be made from metal or plastic. The girdle form 14 has rounded edges, being widest near the middle thereof, at the place indicated by numeral 18. The form is substantially curved toward its top and bottom, to narrower end portions shown by numerals 20 and 22. The

numeral 22 corresponds to that part of the girdle form 14 on which the waist portion of the girdle is formed. The form 14, which is without fabric securing means, is provided with an elongate attachment member 24, by means of which the form 14 may be supported and thereby transported during the various phases of the girdle manufacture. During the course of girdle manufacture, the substantially flat form 14 has deposited upon it a latex film, preferably by dipping or spraying, which layer of latex film is designated by numeral 26. The film is on the front, back, side edges and bottom edge of the form. The latex film 26 may also be on the upper edge of the form, with respect to the orientation of Figure 1, but this is of no consequence in the girdle making process.

The lower section 16 of the apparatus 10 has an annular, rectangular, tubular frame member 28, best described as a squashed hoop 28. Frame 28 is supported by support members 30. When two support members 30 are utilized, as shown in Figure 1, they may be attached to an H-shaped base 32 or other suitable support. The seamless fabric element 34, which is to become the fabric lining of a seamless latex girdle, and is preferably a two-way stretch fabric, has one of its ends stitched or otherwise held closed, as shown by numeral 36. The "bag" then formed by the fabric element is slipped over the frame 28, until the seam or connections 36 are substantially centered within the squashed hoop 28, as shown in Figure 1.

The dimensions of the form 14 and frame 28 are such that the frame defines an open space of dimensional compatibility to the form, whereby there may be close tolerance which just permits the form 14 to be inserted through the frame 28, along the axis of attachment member 24, and then withdrawn. This close tolerance, along with uniformity of annular space, helps to control the depth to which the fabric element 34 is embedded into the latex film covering the form 14. As is known in the art, the extent to which the latex film seeps or is pushed into the fabric element, or conversely, the extent to which the fabric element is embedded into the latex film, determines the overall stretch characteristics of the complete girdle laminae.

In addition to being non-conical, the shape of the form 14, taken normal to the axis of attachment member 24, i.e. the axis of movement of the form through the open space defined by frame 28 can be viewed as:—

- (a) having a large width to thickness ratio, and
- (b) non-circular.

In order to produce a body-conforming garment, the form 14 is firstly covered with a latex film, preferably by dipping same into a vat. This forms the base latex sheath. At the same time, the fabric element 34, which is to become the inner cloth lining for the girdle, is also prepared. Preferably, the fabric element 34 is a seamless two-way stretch knitted sheath. One end of the sheath is closed on itself, such as by

the basting stitches shown as numeral 36. The sheath, which is then in the form of a bag, is slipped over the frame of the lower section. With the latex film still wet or tacky, either from dipping or from the application of heat at a time subsequent to dipping, the form 14, by means of member 24, is pushed downward substantially through the center of the frame 28 along the axis of member 24. As the form travels through the frame, the seam formed by connections 36 will be engaged by the lower edge of the form, and will be pushed downwardly with the form. As the form moves further downward, the fabric element 34 is engaged by the form so as to pull the fabric element over the edges of the frame. At the same time, and at a point adjacent or close to the level of the frame, the fabric element 34 will be brought into substantial contact with the sides and edges of the form 14. By the time the form 14 has been pushed completely through the frame, the fabric element 34 will be completely attached to the form, and will be completely free of the elements of the lower section 16. The form, with the fabric lining then attached, may then be easily withdrawn from the lower section, and may be moved to the final processing operations. If necessary, the fabric may be rolled or brushed against the latex by mechanical or hand operated means to obtain a better bond and remove any wrinkles, creases or other irregularities. This final operation further entails, basically, removing the latex and fabric element from the form so that the garment may then be trimmed and finished, which operations would include removing the connection means 36 and trimming the excess latex and fabric.

The ease in quality maintenance with respect to the depth of interpenetration between the fabric element and the latex film on the form and control of prestressing may be appreciated by a comparison of the present apparatus with the cylindrical apparatus known in the prior art. In such prior art apparatus, the form on which the fabric element was first stretched was a perfect cylinder. The form on which the latex film was applied was a cylinder which decreased in diameter, with the narrower end of the form being first inserted into the cylinder and first engaging the fabric element. It may be appreciated that an annular space is created between the outer surface of the form and the inner surface of the edge of the cylinder mounting the fabric element. It may also be appreciated that as the cylindrical form is further inserted into the uniform cylindrical element, the annular space therebetween decreases because the diameter of the cylindrical form increases. This creates an everchanging annular space, which as an added variable makes uniformity and control over the interpenetration of the fabric element and the latex film and control over prestressing characteristics of the fabric more difficult. In the apparatus according to the present invention, the form is flat. The only variations in shape are the regularly curved edges, causing the form to be widest in the middle and

narrowest at the ends, as noted hereinbefore. It may be appreciated that the only space between the form and the frame which changes in any appreciable fashion is that between each side edge of the form and each edge of the frame. Due to the close tolerances, the longer sides of the form and the longer sides of the frame are substantially co-extensive. In fact, the circumferential interface between the form and the frame is constant over approximately 93% of the total interface. It is therefore easier to control the uniform application of the fabric element to the latex sheath because the variable of the changing space described above is practically eliminated.

The present method also provides significant advantages in that it is easier to remove vertical stretch from areas of the finished girdle where such stretch is undesirable, and it is easier to increase horizontal stretch in areas where horizontal stretch is desirable, such as in the waist portion. As noted hereinbefore, the lower end of the form, which is one of the two narrower ends thereof, corresponds to the waist portion. In use, this narrower portion must be easily pulled over the hips of the user. As is known, the stretchability of the fabric, as applied to the latex, is affected by the extent to which the fabric is stretched when applied. The unique method according to the present invention takes advantage of this characteristic, and obviates the difficulty of pulling the narrower waist portion over the hips.

The foregoing is demonstrated in the following tables. Table 1 has listed therein the % vertical and horizontal stretch produced in the fabric lining when applied in accordance with the present invention. The data is listed beginning from the waist portion of the girdle, with substantially even increments moving towards the bottom section of the girdle.

Table 1

	Vertical stretch	Horizontal stretch
From waist	44%	10%
45	40%	20%
	30%	28%
	28%	34%
	26%	40%
50	18%	45%
	20%	45%
	15%	45%
	16%	42%
	8%	40%
55	5%	38%
	2%	36%
	0%	36%
	-12%	28%

It is known in the art that the overall stretchability of a latex sheath, without a fabric lining or stiffener is on the order of 700-800 per cent. In Table 2, there is listed the stretch characteristics of the total girdle laminae, fabric

and latex as a per cent (%) of the unstressed dimensions of the laminae.

65

Table 2

	Vertical stretch	Horizontal stretch
Waist section	77%	243%
Middle section	100%	195%
70 Bottom section	135%	175%

As noted before, the waist area is one particular area where horizontal stretch is very desirable, but vertical stretch is not nearly as desirable. Reference to Table 2 shows that the horizontal stretchability in the waist portion is 243%, as compared to only 195% and 175% in the middle and bottom sections respectively. Vertical stretch is most desirable in the middle and bottom sections of the girdle, in order to facilitate sitting down. In this respect, Table 2 shows that the vertical stretchability in the middle and bottom sections is 100% and 135% respectively, as compared to only 77% in the waist section.

It is often necessary, in prior art methods, to mechanically or hand roll or brush the fabric in order to work it into the latex film after the application of the fabric to the latex has been made. The method according to some of the embodiments of the present invention, to the contrary, provides a "one-step" operation, whether it be a hand operation or a mechanical operation.

There are two other presently preferred embodiments for performing the process according to the present invention, in addition to that shown in Figures 1 and 2. With reference to Figure 3, a lower section, generally designed by numeral 50, is provided with rollers. Rather than utilizing a frame shaped like a squashed hoop which is itself manufactured according to desired close tolerances, the close tolerances are provided by two opposing rollers 52. The rollers are provided with U-shaped roller mounting means 56, which are attached to support members 58. The support members may themselves be supported in a manner similar to lower section 16 in Figure 1.

During the method of forming a girdle according to the present invention, the fabric bag is formed so that the connection members or seam 36 is disposed between the rollers 52. Similarly, the form 14 is inserted between the rollers. Thus the need for subsequent rolling may be eliminated by this one step process.

The third of the presently preferred embodiments is shown in Figure 4, and is generally designated by numeral 70. This embodiment is similar to that shown in Figure 3, except that brush elements are used instead of rollers. Brush elements 72 are held inside a somewhat enlarged squashed hoop 74 by brush mounting means 76. The hoop and brush assembly of this embodiment may also be

120

supported in a manner similar to the first two described embodiments.

The advantages provided by the second and third embodiments are similar. Both the rollers and brushes provide a rolling, brushing or rubbing action which assures the proper interpenetration of the fiber mesh of the fabric and the latex film on the form.

The present invention may be embodied in other specific forms without departing from the essential attributes thereof, and accordingly, reference should be made to the appended claims, rather than to the foregoing specification as indicating the scope of the invention.

15 Claims

1. An apparatus, for manufacturing girdles, comprising:

a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath said form being without fabric securing means, and

a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages, without securing, the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

2. The apparatus of Claim 1, wherein said form is substantially flat.

3. The apparatus of Claim 1 or 2, wherein said form has rounded edges.

4. The apparatus of Claim 1, 2 or 3, wherein said frame comprises at least one roller member and means for mounting the roller member.

5. The apparatus claimed in any one of Claims 1, 2, 3 or 4, where at least one brush member is mounted on said frame.

6. The apparatus claimed in any one of Claims 1 to 5, wherein said frame comprises structure of two parallel sides and two joining ends.

7. A method of manufacturing girdles, comprising the steps of:

forming an adherable latex sheath on a form having curved edges;

placing a fabric liner having a substantially closed end over a frame, the frame having an opening comprising structure of two parallel sides and two joining ends and being of sufficient size to receive the form which has two parallel sides; moving the form through the opening in the frame, so as to engage the closed end of the liner into contact with the coated form, whereby the fabric liner is transferred from the frame to the coated form.

8. The method of Claim 7, wherein said form is substantially flat.

9. The method of Claim 7 or 8, wherein the step of moving the form through the opening in the frame further comprises a controlled movement wherein the circumferential interface between the

form and the frame remains substantially constant for approximately 93% of the total interface.

10. The method of Claim 7, 8 or 9, wherein the frame and form have relatively close tolerances in dimension, thereby controlling the interpenetration of the fabric liner and the latex sheath.

11. The method of any one of Claims 7 to 10, further comprising the step of moving the form back out through the frame.

12. A girdle manufactured by the method claimed in any one of Claims 7 to 11.

13. Apparatus for manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings.

14. Apparatus for manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings, modified substantially as hereinbefore described with reference to Figure 3 of said drawings.

15. Apparatus for manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings, modified substantially as hereinbefore described with reference to Figure 4 of said drawings.

16. A method of manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings.

17. A method of manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings, modified substantially as hereinbefore described with reference to Figure 3 of said drawings.

18. A method of manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings, modified substantially as hereinbefore described with reference to Figure 4 of said drawings.

19. A girdle manufactured by the method claimed in Claim 16, 17 or 18.

20. An apparatus for manufacturing girdles, comprising:

a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath, and a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the form having a non-conical shape, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

21. An apparatus for manufacturing girdles, comprising:



17

supported in a manner similar to the first two described embodiments.

The advantages provided by the second and third embodiments are similar. Both the rollers and brushes provide a rolling, brushing or rubbing action which assures the proper interpenetration of the fiber mesh of the fabric and the latex film on the form.

The present invention may be embodied in other specific forms without departing from the essential attributes thereof, and accordingly, reference should be made to the appended claims, rather than to the foregoing specification as indicating the scope of the invention.

15 Claims

1. An apparatus for manufacturing girdles, comprising:
 - a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath said form being without fabric securing means, and
 - a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages, without securing, the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.
2. The apparatus of Claim 1, wherein said form is substantially flat.
3. The apparatus of Claim 1 or 2, wherein said form has rounded edges.
4. The apparatus of Claim 1, 2 or 3, wherein said frame comprises at least one roller member and means for mounting the roller member.
5. The apparatus claimed in any one of Claims 1, 2, 3 or 4, where at least one brush member is mounted on said frame.
6. The apparatus claimed in any one of Claims 1 to 5, wherein said frame comprises structure of two parallel sides and two joining ends.
7. A method of manufacturing girdles, comprising the steps of:
 - forming an adherable latex sheath on a form having curved edges;
 - placing a fabric liner having a substantially closed end over a frame, the frame having an opening comprising structure of two parallel sides and two joining ends and being of sufficient size to receive the form which has two parallel sides;
 - moving the form through the opening in the frame, so as to engage the closed end of the liner into contact with the coated form, whereby the fabric liner is transferred from the frame to the coated form.
8. The method of Claim 7, wherein said form is substantially flat.
9. The method of Claim 7 or 8, wherein the step of moving the form through the opening in the frame further comprises a controlled movement wherein the circumferential interface between the

form and the frame remains substantially constant for approximately 93% of the total interface.

10. The method of Claim 7, 8 or 9, wherein the frame and form have relatively close tolerances in dimension, thereby controlling the interpenetration of the fabric liner and the latex sheath.

11. The method of any one of Claims 7 to 10, further comprising the step of moving the form back out through the frame.

12. A girdle manufactured by the method claimed in any one of Claims 7 to 11.

13. Apparatus for manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings.

14. Apparatus for manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings, modified substantially as hereinbefore described with reference to Figure 3 of said drawings.

15. Apparatus for manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings, modified substantially as hereinbefore described with reference to Figure 4 of said drawings.

16. A method of manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings.

17. A method of manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings, modified substantially as hereinbefore described with reference to Figure 3 of said drawings.

18. A method of manufacturing girdles, substantially as hereinbefore described, with reference to Figures 1 and 2 of the accompanying drawings, modified substantially as hereinbefore described with reference to Figure 4 of said drawings.

19. A girdle manufactured by the method claimed in Claim 16, 17 or 18.

20. An apparatus for manufacturing girdles, comprising:

- a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath, and
- a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the form having a non-conical shape, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

21. An apparatus for manufacturing girdles, comprising:



18

a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath, and

- 5 a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the form being movable through the frame along an axis, the form having a non-circular cross-section taken normal to the axis, which is of relatively small thickness and of relatively large width, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages the
- 10 liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

22. An apparatus for manufacturing girdles, comprising:

- 20 a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath, and, a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed
- 25 through said open space, the form being movable through the frame along an axis, the form having a non-circular cross-section taken normal to the axis, which has a large width to thickness ratio, the structure of the frame adapted to support a fabric liner with closed end whereby upon movement of said form through said frame opening, the coated form engages the liner, pulling the liner through the opening in the frame
- 30 and into substantial contact with the coated form.
- 35

23. An apparatus for manufacturing girdles, comprising:

- a form shaped to produce a body-conforming garment which provides a support upon which latex is deposited to form a latex sheath, said form being without fabric securing means, and,
- 40 a frame including structure defining an open space of dimensional compatibility to the form, supported to permit the form to be passed through said open space, the form being movable through the frame along an axis, the form having a non-circular cross-section taken normal to the axis, the structure of the frame adapted to support a fabric liner with closed end whereby upon
- 45 movement of said form through said frame opening, the coated form engages the liner, pulling the liner through the opening in the frame and into substantial contact with the coated form.

24. The apparatus of Claim 21, 22 or 23,

- 55 wherein said form is substantially flat.

25. The apparatus of any one of Claims 21 to 24, wherein said form has rounded edges.

26. The apparatus of any one of Claims 21 to 25, wherein said frame comprises at least one roller member and means for mounting the roller member.
- 60

27. The apparatus claimed in any one of Claims 21 to 26, where at least one brush member is mounted on said frame.

28. The apparatus claimed in any one of Claims 21 to 27, wherein said frame comprises structure of two parallel sides and two joining ends.
- 65