



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08K 5/521, C08L 69/00 // (C08L 69/00, 55:02, 25:12)	A1	(11) International Publication Number: WO 00/39210 (43) International Publication Date: 6 July 2000 (06.07.00)
(21) International Application Number: PCT/US99/30197 (22) International Filing Date: 17 December 1999 (17.12.99) (30) Priority Data: 10/366465 24 December 1998 (24.12.98) JP Not furnished 14 December 1999 (14.12.99) US (71) Applicant: GENERAL ELECTRIC COMPANY [US/US]; 1 River Road, Schenectady, NY 12345 (US). (72) Inventors: FUJIGUCHI, Tomohide; 1190-4, Inageda, Haga Town, Haga County, Tochigi Prefecture 321-3303 (JP). CHOATE, Kim; Excel #305, 6-2-3, 3-chome, Higashishukugo, Utsunomiya City, Tochigi Prefecture 321-0953 (JP). SAWANO, Yuzuru; A 101 Sun Gardenwinds, 1-2-5, Shimoguri, Utsunomiya City, Tochigi Prefecture 321-0924 (JP). SAITO, Akihiro; 301, President Building No. 8, 1-6-1 Shimoguri, Utsunomiya City, Tochigi Prefecture 321-0924 (JP). ITOI, Hideyuki; 2-19-16, Toyosatodai Voyage Drive, Utsunomiya City, Tochigi Prefecture 321-0911 (JP). (74) Agents: WINTER, Catherine, J. et al.; General Electric Company, 3135 Easton Turnpike W3C, Fairfield, CT 06431 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: POLYCARBONATE RESIN COMPOSITION (57) Abstract To provide a polycarbonate resin composition that has excellent moisture resistance, good flame resistance, and markedly superior mechanical strength. Means for Solution: A resin composition containing (A) 1 to 99 weight parts of a polycarbonate resin having a viscosity average molecular weight of 10,000 to 100,000 and (B) 1 to 99 weight parts of a styrene resin, and also containing (C) a phosphoric ester compound with an acid value of 1 or less, in an amount of 1 to 40 weight parts per combined 100 weight parts of (A) + (B), and (D) a reinforcing agent in an amount of 1 to 100 weight parts per combined 100 weight parts of (A) + (B) + (C).		