

ABSTRACT

The invention relates to a method comprising the following steps: first, mixing ground ABS and acetone, the latter varying according to the desired viscosity; second, beating the mixture; third, leaving the mixture to rest in a sealed environment; and fourth, beating the mixture again until same is homogeneous, and leaving to rest for 24 hours.