

REPLACED SHEETS		SG
☒	Description : paged to paged	
☐	Claim(s) : paged to paged	
☐	Drawing(s) : paged to paged	
☒	Abstract : paged to paged	
DATE OF RECEIPT		

Ref. 6220/125

- 5 The present invention is concerned with photo cross-linkable, optically active compounds, liquid crystalline mixtures which contain such compounds as well as their use in the cross-linked state as optical components.
- 10 Photo cross-linkable liquid crystals, which are provided with a suitable amount of a photoinitiator, can be oriented on a substrate or in a cell by suitable orienting layers or in a field and then in this state can be cross-linked by irradiation with light of a suitable wavelength. The structure thereby produced is
- 15 preserved even at high temperatures. Thus, optical components such as, for example, wave guides, optical grids and filters, piezoelectric cells and cells having non-linear optical (NLO) properties, electro-optical devices, etc. can be produced. Such optical components can be used, for example, in cells for
- 20 frequency doubling (SHG) or in colour filters.

Further properties such as, for example, the birefringence, the refractive index, the transparency, etc. must fulfil different requirements depending on the field of use. For example,

25 materials for colour filters, polarizers, $\lambda/2$ plates, etc. should produce a small pitch for circularly polarized light.

The photo cross-linkable liquid crystals must have a good chemical and thermal stability, good solubility in usual solvents

30 and a good stability towards electric fields and electromagnetic radiation. They should have a suitable mesophase in a temperature range from about 25°C to about +100°C, especially from about 25°C to about +80°C.

35 Chiral nematic (cholesteric) liquid crystals in the homogeneously orientated state (Grandjean texture) reflect light essentially only in a wavelength range which is dependent on the wavelength of the helical pitch. The spectral width of this

Hu/So 29.5.96

This Sheet Has Been Replaced




reflected light can be varied by suitable choice of the liquid crystal. The reflected light is completely circularly polarized. The direction of rotation of the reflected light depends on the direction of rotation of the cholesteric helical structure. The oppositely circularly polarized light is transmitted unimpaired. These properties can be used for the production of optical filters, polarizers, analyzers, etc. When such cholesteric mixtures contain photochemically oligomerisable or polymerisable components, then these components can be cross-linked by irradiation with light. The liquid crystalline structure of these mixtures is thereby stabilized or even frozen. Thus, colour filters, $\lambda/2$ plates, optical retarders, polarizers, etc. can be produced in the solid state.

Since liquid crystals are usually used as mixtures of several components, it is important that the components have a good miscibility with one another. Mixtures consisting of photo cross-linkable liquid crystals and non-photo cross-linkable components, which lead to optical activity in mixtures, allow the non-cross linked components to relax and thereby decrease the stability of the network. Conventional optically active photochemically oligomerizable or polymerisable additives have the centre of chirality in the spacers between the photo cross-linkable group and the core of the molecule. This requires an expensive and complicated synthesis. The twisting capacity of these compounds is relatively small.

There is accordingly the need to produce, especially for use in optical filters, photochemically oligomerisable or polymerisable optically active compounds which have a large twisting capacity. Thus, they can be admixed in liquid crystalline mixtures in small concentrations in order to produce the desired pitch without influencing the clearing point or other physical properties of the mixture too severely. Moreover, they should be readily accessible from starting materials which are known or which are commercially available. Furthermore, mixtures which contain such optically active photo cross-linkable compounds should be orientable and structurable as domain-free as possible

and should also have an excellent thermal stability and long-term stability in the cross-linked state.

The present invention now provides compounds which are
 5 outstandingly suitable as single components or as components of
 such liquid crystal mixtures. The compounds of the present
 invention have general formula I



I

10

wherein

A¹ and A² each signify a cross-linkable mesogenic
 residue; and


A³ signifies (R,R)- or (S,S)-trans-1,2-
 15 cyclohexyl-diyl.

15

Since the compounds of formula I in accordance with the
 invention or mixtures containing such compounds have a meso-
 phase, they can, prior to the cross-linking, be oriented on an
 20 orienting layer by the application of an electric or magnetic field.
 A uniform layer is produced in this manner.

Preferably, the mesogenic residues A¹ and A² each signify a
 residue of general formula II

25




II

wherein

rings C and D each independently signify pyridine-2,5-
 30 diyl, pyrimidine-2,5-diyl, trans-1,4-
 cyclohexylene, trans-1,3-dioxane-2,5-diyl
 or 1,4-phenylene optionally substituted
 with halogen, methyl and/or cyano;

Z¹ signifies $\text{---}(\text{CH}_2)_m\text{---}$, ---CO--- , $\text{---}(\text{CH}_2)_m\text{CO---}$ or
 35 $\text{---}(\text{CH}_2)_m\text{OOC---}$;

35

	Z ²	signifies a single bond, -CH ₂ CH ₂ -, -CH ₂ O-, -OCH ₂ -, -COO-, -OOC-, -(CH ₂) ₄ -, -O(CH ₂) ₃ - or -(CH ₂) ₃ O-;
5	Z ³	-(CY ₂) _m -, -O(CY ₂) _m -, -(CY ₂) _m O-, -(CY ₂) _m COO-, -(CY ₂) _m OOC-, -[Si[(CH ₃) ₂]O] _m -, -OCH ₂ [Si[(CH ₃) ₂]O] _m -, -Si[(CH ₃) ₂]CH ₂ O- or -NHCH ₂ [Si[(CH ₃) ₂]O] _m -, -Si[(CH ₃) ₂]CH ₂ NH-;
10	Y	signifies hydrogen or fluorine;
	n	signifies 0, 1 or 2;
	m	signifies a whole number of 1 to 16; and
15	R ¹	signifies a cross-linkable group of the structure CH ₂ =CH-, CH ₂ =CH-COO-, CH ₂ =C(CH ₃)-COO-, CH ₂ =C(Cl)-COO-, CH ₂ =C(Ph)-COO-, CH ₂ =CH-COO-Ph-, CH ₂ =CH-CO-NH-, CH ₂ =C(CH ₃)-CONH-, CH ₂ =C(Cl)-CONH-, CH ₂ =C(Ph)-CONH-, CH ₂ =C(COOR')-CH ₂ -COO-, CH ₂ =CH-O-, CH ₂ =CH-OOC-, Ph-CH=CH-, CH ₃ -C(=NR')-,
20		cis,trans HOO-CR'=CR'-COO-, $\text{H}_2\text{C}-\text{CH}-$ $\diagup \quad \diagdown$ O , R'  $\text{CH}=\text{CH}-$ or R''  $\text{CH}=\text{CH}-\text{COO}-$
25	Ph	signifies phenyl;
	R'	signifies lower alkyl; and
	R''	signifies methyl, methoxy, cyano or halogen;

with the proviso that R¹-Z³ contains no -O-O- or -N-O- groups.

- 30 Compounds of formula I in which the two mesogenic residues A¹ and A² have the same significance are preferred.

- 35 Residues A¹ and A² of formula II in which rings C and D each independently signify unsubstituted or fluoro-substituted 1,4-phenylene, pyridine-2,5-diyl, pyrimidine-2,5-diyl or trans-1,4-cyclohexylene, Z¹ signifies -CH₂-, -CO- or -OOC-, Z² signifies a

10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846

5



wherein R' and R'' have the significance given above.

15

$$\text{CH}_2=\text{C}(\text{CH}_3)-\text{COO}^-, \text{CH}_2=\text{CH}-\text{O}^- \text{ and } \text{H}_2\text{C}-\underset{\text{O}}{\underset{|}{\text{CH}}}-$$

The terms used above will be explained hereinafter:

25

"halogen" signifies fluorine, chlorine or bromine, especially fluorine;


"lower alkyl" signifies a straight-chain or branched alkyl group with 1 to 4 carbon atoms such as, for example, methyl,

"lower alkyl" signifies a straight-chain or branched alkyl with 1 to 4 carbon atoms such as, for example, methyl,

ethyl, propyl, butyl, i-propyl, i-butyl, tert.-butyl, but especially methyl, ethyl, propyl or butyl.

The mesophase type of the compounds in accordance with the invention can be influenced by varying the rings in the side-chains A¹ and A². Thus, aromatic rings such as phenylene have the tendency to produce smectic phases, while saturated rings such as trans-1,4-cyclohexylene or trans-1,3-dioxane-2,5-diyl rings promote nematic tendencies.

Preferably, the mesogenic residues A¹ and A² signify a residue of formula II in which n is 1, i.e. a residue of formula II-a



II-a

wherein

rings C¹ and D¹ each independently signify pyridine-2,5-diyl, pyrimidine-2,5-diyl, trans-1,4-cyclohexylene or 1,4-phenylene optionally substituted with fluorine;

Z¹¹ signifies -CH₂- or -CO-;


Z²¹ signifies a single bond, -CH₂O-, -COO- or -OOC-;

Z³¹ signifies -(CH₂)_{m'}-, -(CH₂)_{m'}O-, -(CH₂)_{m'}COO- or -(CH₂)_{m'}OOC-;


m' signifies a whole number of 3 to 12; and

R¹¹ signifies CH₂=CH-COO-, CH₂=C(CH₃)-COO-, CH₂=CH-O- or $\begin{matrix} \text{H}_2\text{C} & - & \text{CH} \\ & \diagdown & / \\ & \text{O} & \end{matrix}$.


Especially preferred are compounds of the formulae




I-A




I-B



I-C



I-D



I-E

wherein Z^{11} signifies $-CO-$ and Z^{21} signifies a single bond or $-COO-$, especially $-COO-$, and m' is a whole number of 3 to 12,

as well as the enantiomers of these compounds.

5


The compounds of formula I in which A^1 and A^2 have the same significance are very readily accessible synthetically and can be produced, for example, analogously to the methods illustrated in Schemes 1 to 5. Thus, optically active diols can be
10 reacted with (ω -acryloyloxyalkyloxy)-substituted carboxylic acids in a manner known per se. This esterification can be effected, for example, via the corresponding methylsulphonate in tetrahydrofuran or in the presence of N,N' -dicyclohexylcarbodiimide and 4-(dimethylamino)pyridine in dichloromethane or
15 another suitable solvent such as e.g. chloroform. Optically active diols can also be reacted with (ω -acryloyloxyalkyloxy)-substituted benzyl tosylates in a Williamson etherification. This etherification can be effected, for example, at room temperature in the presence of potassium tert.-butylate in dimethoxyethane or
20 another suitable solvent such as e.g. N,N' -dimethylformamide.

Compounds of formula I in which A^1 and A^2 are different can be produced by the mono-esterification of optically active diols with an (ω -acryloyloxyalkyloxy)-substituted carboxylic acid
25 and subsequent esterification with a different (ω -acryloyloxyalkyloxy)-substituted carboxylic acid. The corresponding asymmetric diethers are accessible via a similar two-stage process (described). The starting materials are known and in part are commercially available.


30

The reactions set forth in Schemes 1 to 5 are all effected in a manner known per se. In the Schemes the symbols have the aforementioned significances.


Scheme 1




Scheme 2




Scheme 3



Scheme 4



Scheme 5



A small amount of BHT (2,6-di-tert.-butyl-4-methyl-
 5 phenol/"butylhydroxytoluene") is admixed in each step in order to
 stop undesired thermal cross-linkage.


The compounds of formula I are used as chiral dopants in
 liquid crystalline mixtures. These liquid crystalline mixtures
 10 contain at least one compound of formula I.

The content of chiral compounds of formula I in the liquid
 crystalline mixtures in accordance with the invention can vary in
 a wide range and can be, for example, about 0.1-30 wt.% and is
 15 determined essentially by the twisting capacity of the compounds
 and the desired pitch.



The liquid crystalline mixtures in accordance with the invention contain at least 2 components, of which at least one component is a compound of formula I. A second component and
 5 any additional components can be further compounds of formula I or other known liquid crystalline compounds having a photo cross-linkable group. Additional chiral components can also be present in the mixture.

10 The mixtures in accordance with the invention preferably contain, in addition to one or more compounds of formula I, one or more compounds from the group of compounds of the general formulae



15



III





IV




V


15




VI




VII





VIII



IX




X



5

and



10

X

signifies hydrogen, fluorine, chlorine, bromine
or methyl;

m'

signifies a whole number of 4 to 12;

- t signifies a whole number of 2 to 12;
 Z signifies -OCH₂- or -OOC-;
 A signifies 1,4-phenylene or 2- or 3-fluoro-1,4-phenylene;
 5 S signifies -(CH₂)_m-, -(CH₂)_mO- or -O(CH₂)_m-;
 and
 R signifies CH₂=CH-COO-, CH₂=C(CH₃)-COO-,
 CH₂=CH-O- or $\text{H}_2\text{C}=\underset{\text{O}}{\text{C}}-\text{CH}-$.

- 10 The production of the compounds of formula I and of liquid crystalline mixtures containing these compounds is illustrated in more detail by the following Examples. C signifies a crystalline phase, S signifies a smectic phase, N signifies a nematic phase and I signifies the isotropic phase. Optical antipodes have in each
 15 case "mirror image properties", i.e. the same melting point etc., but lead to opposite helical rotation and opposite circular polarisation of reflected light.

Example 1

20

- 0.44 g of N,N'-dicyclohexylcarbodiimide was added with 5 minutes while stirring to a solution of 0.1 g of (1R,2R)-trans-1,2-cyclohexanediol, 0.9 g of 4-(4-[8-acryloyloxyoctyloxy]-phenylcarbonyloxy)benzoic acid and 0.05 g of 4-(dimethylamino)-
 25 pyridine in 20 ml of dichloromethane. The reaction mixture was stirred overnight, filtered and the filtrate was concentrated. Chromatography of the residue on silica gel with hexane/ethyl acetate (vol. 8:2) and recrystallization from ethyl alcohol of the fractions which were pure according to thin-layer chroma-
 30 tography gave 0.1 g of (1R,2R)-trans-1,2-bis[4-(4-[8-acryloyloxyoctyloxy]phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane; m.p. (C-I) 97°C.

- The following compounds can be prepared in an analogous
 35 manner:

(1R,2R)-trans-1,2-bis[4-(5-[4-Acryloyloxybutyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane; m.p. (C-I) 107°C;

(1R,2R)-trans-1,2-bis[2-(4-[4-acryloyloxybutyloxy]-phenyl)pyridin-5-yl)carbonyloxy]cyclohexane; m.p. (C-I) 108°C;

(1R,2R)-trans-1,2-bis[4-(4-[6-acryloyloxyhexyloxy]-phenyl)cyclohexyl-ethylcarbonyloxy]cyclohexane; m.p. (C-I) 54°C.

5

There can also be prepared:

(1R,2R)-trans-1,2-bis[4-(4-[3-Acryloyloxypropyloxy]-phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane;

10 (1R,2R)-trans-1,2-bis[4-(4-[4-acryloyloxybutoxy]-phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane;

(1R,2R)-trans-1,2-bis[4-(4-[5-acryloyloxypropyloxy]-phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane;

15 (1R,2R)-trans-1,2-bis[4-(4-[6-acryloyloxyhexyloxy]-phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane;

(1R,2R)-trans-1,2-bis[4-(4-[7-acryloyloxyheptyloxy]-phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane;

(1R,2R)-trans-1,2-bis[4-(4-[9-acryloyloxynonyloxy]-phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane;

20 (1R,2R)-trans-1,2-bis[4-(4-[10-acryloyloxydecyloxy]-phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane;

(1R,2R)-trans-1,2-bis[4-(4-[11-acryloyloxyundecyloxy]-phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane;

25 (1R,2R)-trans-1,2-bis[4-(4-[12-acryloyloxydodecyloxy]-phenylcarbonyloxy)phenylcarbonyloxy]cyclohexane;

(1R,2R)-trans-1,2-bis(4-[3-acryloyloxypropyloxy]biphenyl-4'-carbonyloxy)cyclohexane;

(1R,2R)-trans-1,2-bis(4-[4-acryloyloxybutoxy]biphenyl-4'-carbonyloxy)cyclohexane;

30 (1R,2R)-trans-1,2-bis(4-[5-acryloyloxypropyloxy]biphenyl-4'-carbonyloxy)cyclohexane;

(1R,2R)-trans-1,2-bis(4-[6-acryloyloxyhexyloxy]biphenyl-4'-carbonyloxy)cyclohexane;

35 (1R,2R)-trans-1,2-bis(4-[7-acryloyloxyheptyloxy]biphenyl-4'-carbonyloxy)cyclohexane;

(1R,2R)-trans-1,2-bis(4-[8-acryloyloxyoctyloxy]biphenyl-4'-carbonyloxy)cyclohexane;

- (1R,2R)-trans-1,2-bis(4-[9-acryloyloxyundecyloxy]biphenyl-4'-carbonyloxy)cyclohexane;
- (1R,2R)-trans-1,2-bis(4-[10-acryloyloxydodecyloxy]biphenyl-4'-carbonyloxy)cyclohexane;
- 5 (1R,2R)-trans-1,2-bis(4-[11-acryloyloxyundecyloxy]biphenyl-4'-carbonyloxy)cyclohexane;
- (1R,2R)-trans-1,2-bis(4-[12-acryloyloxydodecyloxy]biphenyl-4'-carbonyloxy)cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[3-acryloyloxypropyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane;
- 10 (1R,2R)-trans-1,2-bis[4-(5-[5-acryloyloxypropyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[6-acryloyloxyhexyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane;
- 15 (1R,2R)-trans-1,2-bis[4-(5-[7-acryloyloxyheptyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[8-acryloyloxyoctyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[9-acryloyloxyundecyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane;
- 20 (1R,2R)-trans-1,2-bis[4-(5-[10-acryloyloxydodecyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[11-acryloyloxyundecyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane;
- 25 (1R,2R)-trans-1,2-bis[4-(5-[12-acryloyloxydodecyloxy]-pyrimidin-2-yl)phenylcarbonyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[3-acryloyloxypropyloxy]-pyridin-2-yl)phenylcarbonyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[4-acryloyloxybutyloxy]pyridin-2-yl)phenylcarbonyloxy]cyclohexane;
- 30 (1R,2R)-trans-1,2-bis[4-(5-[5-acryloyloxypropyloxy]-pyridin-2-yl)phenylcarbonyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[6-acryloyloxyhexyloxy]pyridin-2-yl)phenylcarbonyloxy]cyclohexane;
- 35 (1R,2R)-trans-1,2-bis[4-(5-[7-acryloyloxyheptyloxy]-pyridin-2-yl)phenylcarbonyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[8-acryloyloxyoctyloxy]pyridin-2-yl)phenylcarbonyloxy]cyclohexane;

- (1R,2R)-trans-1,2-bis[4-(5-[9-acryloyloxynonyloxy]pyridin-2-yl)phenylcarbonyloxy]cyclohexane;
 (1R,2R)-trans-1,2-bis[4-(5-[10-acryloyloxydecyloxy]-pyridin-2-yl)phenylcarbonyloxy]cyclohexane;
 5 (1R,2R)-trans-1,2-bis[4-(5-[11-acryloyloxyundecyloxy]-pyridin-2-yl)phenylcarbonyloxy]cyclohexane;
 (1R,2R)-trans-1,2-bis[4-(5-[12-acryloyloxydodecyloxy]-pyridin-2-yl)phenylcarbonyloxy]cyclohexane;
 (1R,2R)-trans-1,2-bis[2-(4-[8-acryloyloxyoctyloxy]phenyl)-
 10 pyrimidin-5-ylcarbonyloxy]cyclohexane;
 (1R,2R)-trans-1,2-bis[2-(4-[8-acryloyloxyoctyloxy]phenyl)-pyridin-5-ylcarbonyloxy]cyclohexane;
 (1R,2R)-trans-1,2-bis[trans-4-(trans-4-[3-acryloyloxypropyl]cyclohexyl)cyclohexanecarbonyloxy]cyclohexane;
 15 (1R,2R)-trans-1,2-bis[trans-4-(2-[trans-4-(3-acryloyloxypropyl)cyclohexyl]ethyl)cyclohexanecarbonyloxy]cyclohexane;
 (1R,2R)-trans-1,2-bis[4-(trans-4-[3-acryloyloxypropyl]-cyclohexyl)phenylcarbonyloxy]cyclohexane;
 (1R,2R)-trans-1,2-bis[4-(2-[trans-4-(3-acryloyloxypropyl)cyclohexyl]ethyl)phenylcarbonyloxy]cyclohexane.
 20

Example 2

- A solution of 0.2 g of (1R,2R)-trans-1,2-cyclohexanediol,
 25 0.5 g of sodium hydride and 50 ml of tetrahydrofuran is stirred for 7 hours, treated with 1.1 g of 4-(5-[8-acryloyloxyoctyloxy]pyrimidin-2-yl)benzyl tosylate, the mixture is stirred at room temperature overnight, poured into 100 ml of water and then extracted three times with 50 ml of diethyl ether each
 30 time. The organic phases are combined, washed twice with 100 ml of water each time, dried over magnesium sulphate, filtered and the filtrate is concentrated. Chromatographic purification of the residue on silica gel with cyclohexane/ethyl acetate (vol. 8:2) and two-fold recrystallization from a
 35 cyclohexane/ethyl acetate mixture (vol. 8:2) of the fractions which are pure according to thin-layer chromatography gives 1.1 g of (1R,2R)-trans-1,2-bis[4-(5-[8-acryloyloxyoctyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane.

The following compounds can be prepared in an analogous manner:

- 5 (1R,2R)-trans-1,2-bis[4-(4-[3-Acryloyloxypropyloxy]-phenylcarbonyloxy)benzyloxy]cyclohexane;
(1R,2R)-trans-1,2-bis[4-(4-[4-acryloyloxybutoxy]phenylcarbonyloxy)benzyloxy]cyclohexane;
(1R,2R)-trans-1,2-bis[4-(4-[5-acryloyloxypentyloxy]-phenylcarbonyloxy)benzyloxy]cyclohexane;
10 (1R,2R)-trans-1,2-bis[4-(4-[6-acryloyloxyhexyloxy]phenylcarbonyloxy)benzyloxy]cyclohexane;
(1R,2R)-trans-1,2-bis[4-(4-[7-acryloyloxyheptyloxy]-phenylcarbonyloxy)benzyloxy]cyclohexane;
15 (1R,2R)-trans-1,2-bis[4-(4-[9-acryloyloxynonyloxy]phenylcarbonyloxy)benzyloxy]cyclohexane;
(1R,2R)-trans-1,2-bis[4-(4-[10-acryloyloxydecyloxy]-phenylcarbonyloxy)benzyloxy]cyclohexane;
(1R,2R)-trans-1,2-bis[4-(4-[11-acryloyloxyundecyloxy]-phenylcarbonyloxy)benzyloxy]cyclohexane;
20 (1R,2R)-trans-1,2-bis[4-(4-[12-acryloyloxydodecyloxy]-phenylcarbonyloxy)benzyloxy]cyclohexane;
(1R,2R)-trans-1,2-bis(4-[3-acryloyloxypropyloxy]biphenyl-4'-methoxy)cyclohexane;
25 (1R,2R)-trans-1,2-bis(4-[4-acryloyloxybutoxy]biphenyl-4'-methoxy)cyclohexane;
(1R,2R)-trans-1,2-bis(4-[5-acryloyloxypentyloxy]biphenyl-4'-methoxy)cyclohexane;
(1R,2R)-trans-1,2-bis(4-[6-acryloyloxyhexyloxy]biphenyl-4'-methoxy)cyclohexane;
30 (1R,2R)-trans-1,2-bis(4-[7-acryloyloxyheptyloxy]biphenyl-4'-methoxy)cyclohexane;
(1R,2R)-trans-1,2-bis(4-[9-acryloyloxynonyloxy]biphenyl-4'-methoxy)cyclohexane;
35 (1R,2R)-trans-1,2-bis(4-[10-acryloyloxydecyloxy]biphenyl-4'-methoxy)cyclohexane;
(1R,2R)-trans-1,2-bis(4-[11-acryloyloxyundecyloxy]biphenyl-4'-methoxy)cyclohexane;

- (1R,2R)-trans-1,2-bis(4-[12-acryloyloxydodecyloxy]-biphenyl-4'-methoxy)cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[3-acryloyloxypropyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- 5 (1R,2R)-trans-1,2-bis[4-(5-[4-acryloyloxybutyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[5-acryloyloxypentyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[6-acryloyloxyhexyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- 10 (1R,2R)-trans-1,2-bis[4-(5-[7-acryloyloxyheptyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[8-acryloyloxyoctyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- 15 (1R,2R)-trans-1,2-bis[4-(5-[9-acryloyloxynonyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[10-acryloyloxydecyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[11-acryloyloxyundecyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- 20 (1R,2R)-trans-1,2-bis[4-(5-[12-acryloyloxydodecyloxy]-pyrimidin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[3-acryloyloxypropyloxy]-pyridin-2-yl)benzyloxy]cyclohexane;
- 25 (1R,2R)-trans-1,2-bis[4-(5-[4-acryloyloxybutyloxy]pyridin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[5-acryloyloxypentyloxy]-pyridin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[6-acryloyloxyhexyloxy]pyridin-2-yl)benzyloxy]cyclohexane;
- 30 (1R,2R)-trans-1,2-bis[4-(5-[7-acryloyloxyheptyloxy]-pyridin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[8-acryloyloxyoctyloxy]pyridin-2-yl)benzyloxy]cyclohexane;
- 35 (1R,2R)-trans-1,2-bis[4-(5-[9-acryloyloxynonyloxy]pyridin-2-yl)benzyloxy]cyclohexane;
- (1R,2R)-trans-1,2-bis[4-(5-[10-acryloyloxydecyloxy]-pyridin-2-yl)benzyloxy]cyclohexane;

(1R,2R)-trans-1,2-bis[4-(5-[11-acryloyloxyundecyloxy]-pyridin-2-yl)benzyloxy]cyclohexane;

(1R,2R)-trans-1,2-bis[4-(5-[12-acryloyloxydodecyloxy]-pyridin-2-yl)benzyloxy]cyclohexane;

5 (1R,2R)-trans-1,2-bis[(2-[4-(8-acryloyloxyoctyloxy)-phenyl]pyrimidin-5-yl)methoxy]cyclohexane;

(1R,2R)-trans-1,2-bis[(trans-4-(trans-4-[3-acryloyloxypropyl]cyclohexyl)cyclohexyl)methoxy]cyclohexane;

10 (1R,2R)-trans-1,2-bis[(trans-4-[2-(trans-4-[3-acryloyloxypropyl]cyclohexyl)ethyl]cyclohexyl)methoxy]cyclohexane;


(1R,2R)-trans-1,2-bis[4-(trans-4-[3-acryloyloxypropyl]-cyclohexyl)benzyloxy]cyclohexane;

(1R,2R)-trans-1,2-bis[4-(2-[trans-4-(3-acryloyloxypropyl)cyclohexyl]ethyl)benzyloxy]cyclohexane.



Claims

1. Compounds of the general formula



5

I

wherein

A¹ and A²

each signify a cross-linkable mesogenic residue; and


10

A³

signifies (R,R)- or (S,S)-trans-1,2-cyclohexyl-diyl.

2. Compounds according to claim 1, wherein the mesogenic residues A¹ and A² each signify a residue of general formula II

15



II

wherein

20

rings C and D

each independently signify pyridine-2,5-diyl, pyrimidine-2,5-diyl, trans-1,4-cyclohexylene, trans-1,3-dioxane-2,5-diyl or 1,4-phenylene optionally substituted with halogen, methyl and/or cyano;

25

Z¹

signifies -(CH₂)_m-, -CO-, -(CH₂)_mCO- or -(CH₂)_mOOC-;

Z²

signifies a single bond, -CH₂CH₂-, -CH₂O-, -OCH₂-, -COO-, -OOC-, -(CH₂)₄-, -O(CH₂)₃- or -(CH₂)₃O-;

30

Z³

-(CY₂)_m-, -O(CY₂)_m-, -(CY₂)_mO-, -(CY₂)_mCOO-, -(CY₂)_mOOC-, -[Si[(CH₃)₂]O]_m-, -OCH₂[Si[(CH₃)₂]O]_m-, -Si[(CH₃)₂]CH₂O- or -NHCH₂[Si[(CH₃)₂]O]_m-, -Si[(CH₃)₂]CH₂NH-;


35

Y

signifies hydrogen or fluorine;



- n signifies 0, 1 or 2;
 m signifies a whole number of 1 to 16; and
 R¹ signifies a cross-linkable group of the structure CH₂=CH-, CH₂=CH-COO-,
 5 CH₂=C(CH₃)-COO-, CH₂=C(Cl)-COO-,
 CH₂=C(Ph)-COO-, CH₂=CH-COO-Ph-,
 CH₂=CH-CO-NH-, CH₂=C(CH₃)-CONH-,
 CH₂=C(Cl)-CONH-, CH₂=C(Ph)-CONH-,
 10 CH₂=C(COOR')-CH₂-COO-, CH₂=CH-O-,
 CH₂=CH-OOC-, Ph-CH=CH-, CH₃-C(=NR')-,
 cis,trans HOO-CR'=CR'-COO-,




- 15 Ph signifies phenyl;
 R' signifies lower alkyl; and
 R'' signifies methyl, methoxy, cyano or halogen;
 with the proviso that R¹-Z³ contains no -O-O- or -N-O- groups.

20

3. Compounds according to claim 1 or 2, wherein the mesogenic residues A¹ and A² each signify a residue of general formula II



25



II

- wherein
 rings C and D each independently signify pyridine-2,5-
 30 diyl, pyrimidine-2,5-diyl, trans-1,4-
 cyclohexylene, trans-1,3-dioxane-2,5-diyl
 or 1,4-phenylene optionally substituted
 with halogen, methyl and/or cyano;
 Z¹ signifies -CH₂-, -CO-, -(CH₂)₃- or
 -(CH₂)₂CO-;



- Z^2 signifies a single bond, $-CH_2CH_2-$, $-CH_2O-$, $-OCH_2-$, $-COO-$, $-OOC-$, $-(CH_2)_4-$, $-O(CH_2)_3-$ or $-(CH_2)_3O-$;
 Z^3 $-(CY_2)_m-$, $-O(CY_2)_m-$, $-(CY_2)_mO-$,
 5 $-(CY_2)_mCOO-$, $-(CY_2)_mOOC-$,
 $-(Si[(CH_3)_2]O)_m-$, $-OCH_2(Si[(CH_3)_2]O)_m-$,
 $Si[(CH_3)_2]CH_2O-$ or $-NHCH_2(Si[(CH_3)_2]O)_m-$,
 $Si[(CH_3)_2]CH_2NH-$;
 Y signifies hydrogen or fluorine;
 10 n signifies 0 or 1;
 m signifies a whole number of 1 to 16; and
 R^1 signifies a cross-linkable group of the
 structure $CH_2=CH-$, $CH_2=CH-COO-$,
 15 $CH_2=C(CH_3)-COO-$, $CH_2=C(Cl)-COO-$,
 $CH_2=C(Ph)-COO-$, $CH_2=CH-COO-Ph-$,
 $CH_2=CH-CO-NH-$, $CH_2=C(CH_3)-CONH-$,
 $CH_2=C(Cl)-CONH-$, $CH_2=C(Ph)-CONH-$,
 $CH_2=C(COOR')-CH_2-COO-$, $CH_2=CH-O-$,
 20 $CH_2=CH-OOC-$, $Ph-CH=CH-$, $CH_3-C(=NR')-$,
 $cis,trans HOO-CR'=CR'-COO-$,
 H_2C-CH- , R'  $CH=CH-$ or
 R''  $CH=CH-COO-$;
 Ph signifies phenyl;
 25 R' signifies lower alkyl; and
 R'' signifies methyl, methoxy, cyano or
 halogen;


with the proviso that R^1-Z^3 contains no $-O-O-$ or $-N-O-$ groups.

- 30 4. Compounds according to claim 2 or 3, wherein the mesogenic residues A^1 and A^2 have the same significance.

5. Compounds according to any one of claims 1 to 4, wherein the residues A^1 and A^2 signify a residue of formula II-a



26



II-a

wherein

5 rings C¹ and D¹ each independently signify pyridine-2,5-diyl, pyrimidine-2,5-diyl, trans-1,4-cyclohexylene or 1,4-phenylene optionally substituted with fluorine;

10 Z¹¹ signifies -CH₂- or -CO-;


Z²¹ signifies a single bond, -CH₂O-, -COO- or -OOC-;

15 Z³¹ signifies -(CH₂)_{m'}-, -(CH₂)_{m'}O-, -(CH₂)_{m'}COO- or -(CH₂)_{m'}OOC-;


m' signifies a whole number of 3 to 12; and

R¹¹ signifies CH₂=CH-COO-, CH₂=C(CH₃)-COO-, CH₂=CH-O- or $\text{H}_2\text{C}-\underset{\text{O}}{\text{CH}}-$.

6. Compounds according to claim 5 of formulae IA-IE




I - A




I - B


20



I - C



I - D




I - E

5 wherein Z^{11} signifies $-\text{CO}-$ and Z^{21} signifies a single bond or $-\text{COO}-$, especially $-\text{COO}-$, and m' is a whole number of 3 to 12,


as well as the enantiomers of these compounds.

10 7. A cross-linkable liquid crystalline mixture consisting of at least 2 components, wherein at least one component is an optically active compound of the formula I defined in claim 1.


15 8. A cross-linkable liquid crystalline mixture according to claim 7, which contains, in addition to one or more compounds of formula I, one or more compound from the group of the formulae




III




IV




V



VI




VII



VIII




29



IX

and



X

5

wherein

X signifies hydrogen, fluorine, chlorine, bromine or methyl;

10 m' signifies a whole number of 3 to 12;

t signifies a whole number of 2 to 12;

Z signifies -OCH₂- or -OOC-;

A signifies 1,4-phenylene or 2- or 3-fluoro-1,4-phenylene;

15 S signifies -(CH₂)_{m'}-; -(CH₂)_{m'}O- or -O(CH₂)_{m'}-; and


R signifies CH₂=CH-COO-, CH₂=C(CH₃)-COO-,
CH₂=CH-O- or $\text{H}_2\text{C} \begin{array}{c} \diagup \text{CH-} \\ \diagdown \text{O} \end{array}$.

20 9. The use of compounds according to any one of claims 1 to 6 in their cross-linked state for optical components.

10. The use of cross-linkable liquid crystalline mixtures according to claim 7 or 8 in their cross-linked state for optical
25 components.

Abstract

- 5 The present invention is concerned with photo cross-linkable liquid crystalline compounds of the general formula



- 10 wherein
 A¹ and A² each signify a cross-linkable mesogenic residue; and
 A³ signifies (R,R)- or (S,S)-trans-1,2-cyclohexyl-diyl,
- 15 liquid crystalline mixtures which contain such compounds and their use in the cross-linked state as optical components.

This Sheet Has Been Replaced



8-22601-22

12 DEC 1996

9410366-8 1995

☒ Description : paged ... to paged ...
☐ Claim(s) : paged ... to paged ...
☐ Drawing(s) : paged ... to paged ...
☒ Abstract : paged 30 to paged ...

PHOTO-CROSS-LINKABLE OPTICALLY ACTIVE COMPOUNDS OF RECEIPT 12/12/96


- 5 The present invention is concerned with photo cross-linkable, optically active compounds, liquid crystalline mixtures which contain such compounds as well as their use in the cross-linked state as optical components.
- 10 Photo cross-linkable liquid crystals, which are provided with a suitable amount of a photoinitiator, can be oriented on a substrate or in a cell by suitable orienting layers or in a field and then in this state can be cross-linked by irradiation with light of a suitable wavelength. The structure thereby produced is
- 15 preserved even at high temperatures. Thus, optical components such as, for example, wave guides, optical grids and filters, piezoelectric cells and cells having non-linear optical (NLO) properties, electro-optical devices, etc. can be produced. Such optical components can be used, for example, in cells for
- 20 frequency doubling (SHG) or in colour filters.

- Further properties such as, for example, the birefringence, the refractive index, the transparency, etc. must fulfil different requirements depending on the field of use. For example,
- 25 materials for colour filters, polarizers, $\lambda/2$ plates, etc. should produce a small pitch for circularly polarized light.

- The photo cross-linkable liquid crystals must have a good chemical and thermal stability, good solubility in usual solvents
- 30 and a good stability towards electric fields and electromagnetic radiation. They should have a suitable mesophase in a temperature range from about 25°C to about +100°C, especially from about 25°C to about +80°C.

- 35 Chiral nematic (cholesteric) liquid crystals in the homogeneously orientated state (Grandjean texture) reflect light essentially only in a wavelength range which is dependent on the wavelength of the helical pitch. The spectral width of this

5 The present invention is concerned with photo cross-linkable liquid crystalline compounds of the general formula



10 wherein
 A¹ and A² each signify a cross-linkable mesogenic
 residue; and
 A³ signifies (R,R)- or (S,S)-trans-1,2-
 cyclohexyl-diyl,
 15 liquid crystalline mixtures which contain such compounds and their
 use in the cross-linked state as optical components.

REPLACEMENT SHEET

12 DEC 1996

8-223013