

TITLE: Transition Metal Bis(Phenolate) Complexes and Their Use as Catalysts for Olefin Polymerization

Inventors: Georgy P. Goryunov, Mikhail I. Sharikov, Vladislav A. Popov, Dmitry V. Uborsky, Alexander Z. Voskoboynikov, John R. Hagadorn, Michelle E. Titone, Alex E. Carpenter, Catherine A. Faler, Jo Ann M. Canich

PRIORITY

[0001] This invention claims the benefit of and priority to USSN 62/804,372, filed February 12, 2019 and EP Search Report Application No. 19179811.5 filed June 12, 2019, the disclosures of which are incorporated in their entirety.

FIELD OF THE INVENTION

[0002] This invention relates to novel catalyst compounds comprising group 4 bis(phenolate) complexes, catalyst systems comprising such, and uses thereof.

BACKGROUND OF THE INVENTION

[0003] Olefin polymerization catalysts are of great use in industry. Hence there is interest in finding new catalyst systems that increase the commercial usefulness of the catalyst and allow the production of polymers having improved properties.

[0004] Catalysts for olefin polymerization can be based on bis(phenolate) complexes as catalyst precursors, which are activated typically by an alumoxane or an activator containing a non-coordinating anion.

[0005] KR 2018022137 (LG Chem.) describes transition metal complexes of bis(methylphenyl phenolate)pyridine.

[0006] US 7,030,256 B2 (Symyx Technologies, Inc.) describes bridged bi-aromatic ligands, catalysts, processes for polymerizing and polymers therefrom.

[0007] US 6,825,296 (University of Hong Kong) describes transition metal complexes of bis(phenolate) ligands that coordinate to metal with two 6-membered rings.

[0008] US 7,847,099 (California Institute of Technology) describes transition metal complexes of bis(phenolate) ligands that coordinate to metal with two 6-membered rings.

[0009] WO 2016/172110 – (Univation Technologies) describes complexes of tridentate bis(phenolate) ligands that feature a non-cyclic ether or thioether donor.

[0010] Other references of interest include: Baier, M. C. (2014) “Post-Metallocenes in the Industrial Production of Polyolefins,” *Angew. Chem. Int. Ed.* 2014, v.53, pp. 9722-9744; and

Golisz, S. et al. (2009) "Synthesis of Early Transition Metal Bisphenolate Complexes and Their Use as Olefin Polymerization Catalysts," *Macromolecules*, v.42(22), pp. 8751-8762.


[0011] New catalysts capable of polymerizing olefins to yield high molecular weight and/or high tacticity polymers at high process temperatures are desirable for the industrial production of polyolefins. There is still a need in the art for new and improved catalyst systems for the polymerization of olefins, in order to achieve specific polymer properties, such as high molecular weight and/or high tacticity polymers, preferably at high process temperatures.

[0012] It is therefore an object of the present invention to provide novel catalyst compounds, catalyst systems comprising such compounds, and processes for the polymerization of olefins using such compounds and systems.

SUMMARY OF THE INVENTION.

[0013] This invention relates to transition metal complexes of a dianionic, tridentate ligand that features a central neutral heterocyclic Lewis base and two phenolate donors, where the tridentate ligand coordinates to the metal center to form two eight-membered rings.

[0014] This invention relates to bis(phenolate) complexes represented by Formula (I):



wherein:

M is a group 3-6 transition metal or Lanthanide;

E and E' are each independently O, S, or NR⁹, where R⁹ is independently hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, or a heteroatom-containing group;

Q is group 14, 15, or 16 atom that forms a dative bond to metal M;

A¹QA^{1'} are part of a heterocyclic Lewis base containing 4 to 40 non-hydrogen atoms that links A² to A^{2'} via a 3-atom bridge with Q being the central atom of the 3-atom bridge, A¹ and A^{1'} are independently C, N, or C(R²²), where R²² is selected from hydrogen, C₁-C₂₀ hydrocarbyl, C₁-C₂₀ substituted hydrocarbyl;

A³---A² is a divalent group containing 2 to 40 non-hydrogen atoms that links A¹ to the E-bonded aryl group via a 2-atom bridge;

$A^{2'} \equiv A^{3'}$ is a divalent group containing 2 to 40 non-hydrogen atoms that links $A^{1'}$ to the E'-bonded aryl group via a 2-atom bridge;

L is a neutral Lewis base;

X is an anionic ligand;

5 n is 1, 2 or 3;

m is 0, 1, or 2;

n+m is not greater than 4;

each of R^1 , R^2 , R^3 , R^4 , $R^{1'}$, $R^{2'}$, $R^{3'}$, and $R^{4'}$ is independently hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or
 10 one or more of R^1 and R^2 , R^2 and R^3 , R^3 and R^4 , $R^{1'}$ and $R^{2'}$, $R^{2'}$ and $R^{3'}$, $R^{3'}$ and $R^{4'}$ may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings;

any two L groups may be joined together to form a bidentate Lewis base;

15 an X group may be joined to an L group to form a monoanionic bidentate group;

any two X groups may be joined together to form a dianionic ligand group.

[0015] This invention also relates to a method to polymerize olefins comprising contacting a catalyst compound as described herein with an activator and one or more monomers. This invention further relates to polymer compositions produced by the methods described herein.

20 Definitions

[0016] For the purposes of this invention and the claims thereto, the following definitions shall be used.

[0017] The new numbering scheme for the Periodic Table Groups is used as described in *Chemical and Engineering News*, v.63(5), pg. 27 (1985). Therefore, a "group 4 metal" is an
 25 element from group 4 of the Periodic Table, e.g. Hf, Ti, or Zr.

[0018] "Catalyst productivity" is a measure of the mass of polymer produced using a known quantity of polymerization catalyst. Typically, "catalyst productivity" is expressed in units of (g of polymer)/(g of catalyst) or (g of polymer)/(mmols of catalyst) or the like. If units are not specified then the "catalyst productivity" is in units of (g of polymer)/(grams of catalyst). For
 30 calculating catalyst productivity only the weight of the transition metal component of the catalyst is used (i.e. the activator and/or co-catalyst is omitted). "Catalyst activity" is a measure of the mass of polymer produced using a known quantity of polymerization catalyst per unit time for batch and semi-batch polymerizations. For calculating catalyst productivity only the weight of

the transition metal component of the catalyst is used (i.e. the activator and/or co-catalyst is omitted). Typically, "catalyst activity" is expressed in units of (g of polymer)/(mmol of catalyst)/hour or (kg of polymer)/(mmols of catalyst)/hour or the like. If units are not specified then the "catalyst activity" is in units of (g of polymer)/(mmol of catalyst)/hour.

5 **[0019]** "Conversion" is the percentage of a monomer that is converted to polymer product in a polymerization, and is reported as % and is calculated based on the polymer yield, the polymer composition, and the amount of monomer fed into the reactor.

10 **[0020]** An "olefin," alternatively referred to as "alkene," is a linear, branched, or cyclic compound of carbon and hydrogen having at least one double bond. For purposes of this specification and the claims appended thereto, when a polymer or copolymer is referred to as comprising an olefin, the olefin present in such polymer or copolymer is the polymerized form of the olefin. For example, when a copolymer is said to have an "ethylene" content of 35 wt% to 55 wt%, it is understood that the mer unit in the copolymer is derived from ethylene in the polymerization reaction and said derived units are present at 35 wt% to 55 wt%, based upon the weight of the copolymer. A "polymer" has two or more of the same or different mer units. A "homopolymer" is a polymer having mer units that are the same. A "copolymer" is a polymer having two or more mer units that are different from each other. A "terpolymer" is a polymer having three mer units that are different from each other. Accordingly, the definition of copolymer, as used herein, includes terpolymers and the like. "Different" as used to refer to mer units indicates that the mer units differ from each other by at least one atom or are different isomerically. An "ethylene polymer" or "ethylene copolymer" is a polymer or copolymer comprising at least 50 mole% ethylene derived units, a "propylene polymer" or "propylene copolymer" is a polymer or copolymer comprising at least 50 mole% propylene derived units, and so on.

25 **[0021]** Ethylene shall be considered an α -olefin.

[0022] Unless otherwise specified, the term " C_n " means hydrocarbon(s) having n carbon atom(s) per molecule, wherein n is a positive integer.

30 **[0023]** The term "hydrocarbon" means a class of compounds containing hydrogen bound to carbon, and encompasses (i) saturated hydrocarbon compounds, (ii) unsaturated hydrocarbon compounds, and (iii) mixtures of hydrocarbon compounds (saturated and/or unsaturated), including mixtures of hydrocarbon compounds having different values of n. Likewise, a " C_m - C_y " group or compound refers to a group or compound comprising carbon atoms at a total number thereof in the range from m to y. Thus, a C_1 - C_{50} alkyl group refers to an alkyl group comprising carbon atoms at a total number thereof in the range from 1 to 50.

[0024] The terms “group,” “radical,” and “substituent” may be used interchangeably.

[0025] The terms “hydrocarbyl radical,” “hydrocarbyl group,” or “hydrocarbyl” may be used interchangeably and are defined to mean a group consisting of hydrogen and carbon atoms only. Preferred hydrocarbyls are C₁-C₁₀₀ radicals that may be linear, branched, or cyclic, and when
5 cyclic, aromatic or non-aromatic. Examples of such radicals include, but are not limited to, alkyl groups such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, pentyl, iso-amyl, hexyl, octyl cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cyclooctyl, and the like, aryl groups, such as phenyl, benzyl naphthalenyl, and the like.


[0026] Unless otherwise indicated, (e.g., the definition of “substituted hydrocarbyl”, etc.),
10 the term “substituted” means that at least one hydrogen atom has been replaced with at least one non-hydrogen group, such as a hydrocarbyl group, a heteroatom or heteroatom-containing group, such as halogen (such as Br, Cl, F or I) or at least one functional group such as -NR*₂, -OR*, -SeR*, -TeR*, -PR*₂, -AsR*₂, -SbR*₂, -SR*, -BR*₂, -SiR*₃, -GeR*₃, -SnR*₃, -PbR*₃, -(CH₂)_q-SiR*₃, and the like, where q is 1 to 10 and each R* is independently hydrogen, a
15 hydrocarbyl or halocarbyl radical, and two or more R* may join together to form a substituted or unsubstituted completely saturated, partially unsaturated, or aromatic cyclic or polycyclic ring structure), or where at least one heteroatom has been inserted within a hydrocarbyl ring.

[0027] The term “substituted hydrocarbyl” means a hydrocarbyl radical in which at least one hydrogen atom of the hydrocarbyl radical has been substituted with at least one heteroatom (such
20 as halogen, e.g., Br, Cl, F or I) or heteroatom-containing group (such as a functional group, e.g., -NR*₂, -OR*, -SeR*, -TeR*, -PR*₂, -AsR*₂, -SbR*₂, -SR*, -BR*₂, -SiR*₃, -GeR*₃, -SnR*₃, -PbR*₃, -(CH₂)_q-SiR*₃, and the like, where q is 1 to 10 and each R* is independently hydrogen, a hydrocarbyl or halocarbyl radical, and two or more R* may join together to form a substituted or unsubstituted completely saturated, partially unsaturated, or aromatic cyclic or polycyclic ring
25 structure), or where at least one heteroatom has been inserted within a hydrocarbyl ring.

[0028] The term “aryl” or “aryl group” means an aromatic ring (typically made of 6 carbon atoms) and the substituted variants thereof, such as phenyl, 2-methyl-phenyl, xylyl, 4-bromo-xylyl. Likewise, heteroaryl means an aryl group where a ring carbon atom (or two or three ring carbon atoms) has been replaced with a heteroatom, such as N, O, or S. As used herein, the term
30 “aromatic” also refers to pseudoaromatic heterocycles which are heterocyclic substituents that have similar properties and structures (nearly planar) to aromatic heterocyclic ligands, but are not by definition aromatic.

[0029] The term "substituted aromatic," means an aromatic group having 1 or more hydrogen groups replaced by a hydrocarbyl, substituted hydrocarbyl, heteroatom or heteroatom containing group.

[0030] A "substituted phenolate" is a phenolate group where at least one, two, three, four or five hydrogen atoms in the 2, 3, 4, 5, and/or 6 positions has been replaced with at least one non-hydrogen group, such as a hydrocarbyl group, a heteroatom or heteroatom-containing group, such as halogen (such as Br, Cl, F or I) or at least one functional group such as $-\text{NR}^*_2$, $-\text{OR}^*$, $-\text{SeR}^*$, $-\text{TeR}^*$, $-\text{PR}^*_2$, $-\text{AsR}^*_2$, $-\text{SbR}^*_2$, $-\text{SR}^*$, $-\text{BR}^*_2$, $-\text{SiR}^*_3$, $-\text{GeR}^*_3$, $-\text{SnR}^*_3$, $-\text{PbR}^*_3$, $-(\text{CH}_2)_q\text{-SiR}^*_3$, and the like, where q is 1 to 10 and each R^* is independently hydrogen, a hydrocarbyl or halocarbyl radical, and two or more R^* may join together to form a substituted or unsubstituted completely saturated, partially unsaturated, or aromatic cyclic or polycyclic ring structure), where the 1 position is the phenolate group (Ph-O- , Ph-S- , and $\text{Ph-N(R}^\wedge\text{)-}$ groups, where $\text{R}^\wedge$ is hydrogen, $\text{C}_1\text{-C}_{40}$ hydrocarbyl, $\text{C}_1\text{-C}_{40}$ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group). Preferably, a "substituted phenolate" group in the catalyst compounds described herein is represented by the formula:



where R^{18} is hydrogen, $\text{C}_1\text{-C}_{40}$ hydrocarbyl (such as $\text{C}_1\text{-C}_{40}$ alkyl) or $\text{C}_1\text{-C}_{40}$ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, E^{17} is oxygen, sulfur, or NR^{17} , and each of R^{17} , R^{18} , R^{19} , R^{20} , and R^{21} is independently selected from hydrogen, $\text{C}_1\text{-C}_{40}$ hydrocarbyl (such as $\text{C}_1\text{-C}_{40}$ alkyl) or $\text{C}_1\text{-C}_{40}$ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or two or more of R^{18} , R^{19} , R^{20} , and R^{21} are joined together to form a $\text{C}_4\text{-C}_{62}$ cyclic or polycyclic ring structure, or a combination thereof, and the wavy lines show where the substituted phenoate group forms bonds to the rest of the catalyst compound.

[0031] An "alkyl substituted phenolate" is a phenolate group where at least one, two, three, four or five hydrogen atoms in the 2, 3, 4, 5, and/or 6 positions has been replaced with at least one alkyl group, such as a C_1 to C_{40} , alternately C_2 to C_{20} , alternately C_3 to C_{12} alkyl, such as methyl, ethyl, methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, pentyl, iso-amyl, hexyl, octyl cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cyclooctyl, adamantanyl and the like including their substituted analogues.

[0032] An "aryl substituted phenolate" is a phenolate group where at least one, two, three, four or five hydrogen atoms in the 2, 3, 4, 5, and/or 6 positions has been replaced with at least one aryl group, such as a C₁ to C₄₀, alternately C₂ to C₂₀, alternately C₃ to C₁₂ aryl group, such as phenyl, 4-fluorophenyl, 2-methylphenyl, 2-propylphenyl, 2,6-dimethylphenyl, mesityl, 2-ethylphenyl, naphthalenyl and the like including their substituted analogues.


[0033] The term "ring atom" means an atom that is part of a cyclic ring structure. By this definition, a benzyl group has six ring atoms and tetrahydrofuran has 5 ring atoms.

[0034] A heterocyclic ring, also referred to as a heterocyclic, is a ring having a heteroatom in the ring structure as opposed to a "heteroatom-substituted ring" where a hydrogen on a ring atom is replaced with a heteroatom. For example, tetrahydrofuran is a heterocyclic ring and 4-N,N-dimethylamino-phenyl is a heteroatom substituted ring. A substituted heterocyclic ring means a heterocyclic ring having 1 or more hydrogen groups replaced by a hydrocarbyl, substituted hydrocarbyl, heteroatom or heteroatom containing group.

[0035] A substituted hydrocarbyl ring means a ring comprised of carbon and hydrogen atoms having 1 or more hydrogen groups replaced by a hydrocarbyl, substituted hydrocarbyl, heteroatom or heteroatom containing group.


[0036] For purposes of the present disclosure, in relation to catalyst compounds (e.g., substituted bis(phenolate) catalyst compounds), the term "substituted" means that a hydrogen group has been replaced with a hydrocarbyl group, a heteroatom or heteroatom-containing group, such as halogen (such as Br, Cl, F or I) or at least one functional group such as -NR*₂, -OR*, -SeR*, -TeR*, -PR*₂, -AsR*₂, -SbR*₂, -SR*, -BR*₂, -SiR*₃, -GeR*₃, -SnR*₃, -PbR*₃, -(CH₂)_q-SiR*₃, and the like, where q is 1 to 10 and each R* is independently hydrogen, a hydrocarbyl or halocarbyl radical, and two or more R* may join together to form a substituted or unsubstituted completely saturated, partially unsaturated, or aromatic cyclic or polycyclic ring structure), or where at least one heteroatom has been inserted within a hydrocarbyl ring.

[0037] A tertiary hydrocarbyl group possesses a carbon atom bonded to three other carbon atoms. When the hydrocarbyl group is an alkyl group, tertiary hydrocarbyl groups are also referred to as tertiary alkyl groups. Examples of tertiary hydrocarbyl groups include tert-butyl, 2-methylbutan-2-yl, 2-methylhexan-2-yl, 2-phenylpropan-2-yl, 2-cyclohexylpropan-2-yl, 1-methylcyclohexyl, 1-adamantyl, bicyclo[2.2.1]heptan-1-yl and the like. Tertiary hydrocarbyl groups can be illustrated by Formula A:



, wherein R^A , R^B and R^C are hydrocarbyl groups or substituted hydrocarbyl groups that may optionally be bonded to one another, and the wavy line shows where the tertiary hydrocarbyl group forms bonds to other groups.

- [0038]** A cyclic tertiary hydrocarbyl group is defined as a tertiary hydrocarbyl group that forms at least one alicyclic (non-aromatic) ring. Cyclic tertiary hydrocarbyl groups are also referred to as alicyclic tertiary hydrocarbyl groups. When the hydrocarbyl group is an alkyl group, cyclic tertiary hydrocarbyl groups are also referred to as cyclic tertiary alkyl groups or alicyclic tertiary alkyl groups. Examples of cyclic tertiary hydrocarbyl groups include 1-adamantanyl, 1-methylcyclohexyl, 1-methylcyclopentyl, 1-methylcyclooctyl, 1-methylcyclodecyl, 1-methylcyclododecyl, bicyclo[3.3.1]nonan-1-yl, bicyclo[2.2.1]heptan-1-yl, bicyclo[2.3.3]hexan-1-yl, bicycle[1.1.1]pentan-1-yl, bicycle[2.2.2]octan-1-yl, and the like. Cyclic tertiary hydrocarbyl groups can be illustrated by Formula B:



- , wherein R^A is a hydrocarbyl group or substituted hydrocarbyl group, each R^D is independently hydrogen or a hydrocarbyl group or substituted hydrocarbyl group, w is an integer from 1 to about 30, and R^A , and one or more R^D , and or two or more R^D may optionally be bonded to one another to form additional rings.

- [0039]** When a cyclic tertiary hydrocarbyl group contains more than one alicyclic ring, it can be referred to as polycyclic tertiary hydrocarbyl group or if the hydrocarbyl group is an alkyl group, it may be referred to as a polycyclic tertiary alkyl group.
- [0040]** The terms “alkyl radical,” and “alkyl” are used interchangeably throughout this disclosure. For purposes of this disclosure, “alkyl radical” is defined to be C_1 - C_{100} alkyls that may be linear, branched, or cyclic. Examples of such radicals can include methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, pentyl, iso-amyl, hexyl, octyl, cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cyclooctyl, and the like including their substituted analogues. Substituted alkyl radicals are radicals in which at least one hydrogen atom of the alkyl radical has been substituted with at least a non-hydrogen group, such as a

hydrocarbyl group, a heteroatom or heteroatom-containing group, such as halogen (such as Br, Cl, F or I) or at least one functional group such as -NR*₂, -OR*, -SeR*, -TeR*, -PR*₂, -AsR*₂, -SbR*₂, -SR*, -BR*₂, -SiR*₃, -GeR*₃, -SnR*₃, -PbR*₃, -(CH₂)_q-SiR*₃, and the like, where q is 1 to 10 and each R* is independently hydrogen, a hydrocarbyl or halocarbyl radical, and two or more R* may join together to form a substituted or unsubstituted completely saturated, partially unsaturated, or aromatic cyclic or polycyclic ring structure), or where at least one heteroatom has been inserted within a hydrocarbyl ring.

[0041] Where isomers of a named alkyl, alkenyl, alkoxide, or aryl group exist (e.g., n-butyl, iso-butyl, sec-butyl, and tert-butyl) reference to one member of the group (e.g., n-butyl) shall expressly disclose the remaining isomers (e.g., iso-butyl, sec-butyl, and tert-butyl) in the family. Likewise, reference to an alkyl, alkenyl, alkoxide, or aryl group without specifying a particular isomer (e.g., butyl) expressly discloses all isomers (e.g., n-butyl, iso-butyl, sec-butyl, and tertbutyl).

[0042] As used herein, Mn is number average molecular weight, Mw is weight average molecular weight, and Mz is z average molecular weight, wt% is weight percent, and mol% is mole percent. Molecular weight distribution (MWD), also referred to as polydispersity index (PDI), is defined to be Mw divided by Mn. Unless otherwise noted, all molecular weight units (e.g., Mw, Mn, Mz) are g/mol (g mol⁻¹).

[0043] The following abbreviations may be used herein: Me is methyl, Et is ethyl, Pr is propyl, cPr is cyclopropyl, nPr is n-propyl, iPr is isopropyl, Bu is butyl, nBu is normal butyl, iBu is isobutyl, sBu is sec-butyl, tBu is tert-butyl, Oct is octyl, Ph is phenyl, MAO is methylalumoxane, dme is 1,2-dimethoxyethane, p-tBu is para-tertiary butyl, TMS is trimethylsilyl, TIBAL is triisobutylaluminum, TNOA and TNOAL are tri(n-octyl)aluminum, p-Me is para-methyl, Bn is benzyl (i.e., CH₂Ph), THF (also referred to as thf) is tetrahydrofuran, RT is room temperature (and is 23°C unless otherwise indicated), tol is toluene, EtOAc is ethyl acetate, Cbz is Carbazole, and Cy is cyclohexyl.

[0044] A "catalyst system" is a combination comprising at least one catalyst compound and at least one activator. When "catalyst system" is used to describe such a pair before activation, it means the unactivated catalyst complex (precatalyst) together with an activator and, optionally, a co-activator. When it is used to describe such a pair after activation, it means the activated complex and the activator or other charge-balancing moiety. The transition metal compound may be neutral as in a precatalyst, or a charged species with a counter ion as in an activated catalyst system. For the purposes of this invention and the claims thereto, when catalyst systems

are described as comprising neutral stable forms of the components, it is well understood by one of ordinary skill in the art, that the ionic form of the component is the form that reacts with the monomers to produce polymers. A polymerization catalyst system is a catalyst system that can polymerize monomers to polymer.

5 [0045] In the description herein, the catalyst may be described as a catalyst, a catalyst precursor, a pre-catalyst compound, catalyst compound or a transition metal compound, and these terms are used interchangeably.

[0046] An “anionic ligand” is a negatively charged ligand which donates one or more pairs of electrons to a metal ion. The term “anionic donor” is used interchangeably with “anionic
10 ligand”. Examples of anionic donors in the context of the present invention include, but are not limited to, methyl, chloride, fluoride, alkoxide, aryloxy, alkyl, alkenyl, thiolate, carboxylate, amido, methyl, benzyl, hydrido, amidinate, amidate, and phenyl. Two anionic donors may be joined to form a dianionic group.

[0047] A “neutral Lewis base or “neutral donor group” is an uncharged (i.e. neutral) group
15 which donates one or more pairs of electrons to a metal ion. Non-limiting examples of neutral Lewis bases include ethers, thioethers, amines, phosphines, ethyl ether, tetrahydrofuran, dimethylsulfide, triethylamine, pyridine, alkenes, alkynes, alenes, and carbenes. Lewis bases may be joined together to form bidentate or tridentate Lewis bases.

[0048] For purposes of this invention and the claims thereto, phenolate donors include
20 Ph-O-, Ph-S-, and Ph-N(R[^])- groups, where R[^] is hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, and Ph is optionally substituted phenyl.

DETAILED DESCRIPTION

[0049] This invention relates to a new catalyst family comprising transition metal complexes
25 of a dianionic, tridentate ligand that features a central neutral donor group and two phenolate donors, where the tridentate ligands coordinate to the metal center to form two eight-membered rings. In complexes of this type it is advantageous for the central neutral donor to be a heterocyclic group. It is particularly advantageous for the heterocyclic group to lack hydrogens in the position alpha to the heteroatom. In complexes of this type it is also advantageous for the
30 phenolates to be substituted with one or more cyclic tertiary alkyl substituents. The use of cyclic tertiary alkyl substituted phenolates is demonstrated to improve the ability of these catalysts to produce high molecular weight polymer.

[0050] Complexes of substituted bis(phenolate) ligands (such as adamantanyl-substituted bis(phenolate) ligands) have been prepared and characterized herein. These complexes form

active olefin polymerization catalysts when combined with activators, such as non-coordinating anion or alumoxane activators. Useful bis(aryl phenolate)pyridine complexes comprise a tridentate bis(aryl phenolate)pyridine ligand that is coordinated to a group 4 transition metal with the formation of two eight-membered rings.

5 **[0051]** This invention also relates to a metal complex comprising: a metal selected from groups 3-6 or Lanthanide metals, and a tridentate, dianionic ligand containing two anionic donor groups and a neutral Lewis base donor, wherein the neutral Lewis base donor is covalently bonded between the two anionic donors, and wherein the metal-ligand complex features a pair of 8-membered metallocycle rings.

10 **[0052]** This invention relates to catalyst systems comprising activator and one or more catalyst compounds as described herein.

[0053] This invention also relates to process to polymerize olefins using the catalyst compounds described herein comprising contacting one or more olefins with a catalyst system comprising an activator and a catalyst compound described herein.

15 **[0054]** The present disclosure also relates to a catalyst system comprising a transition metal compound and an activator compound as described herein, to the use of such activator compounds for activating a transition metal compound in a catalyst system for polymerizing olefins, and to processes for polymerizing olefins, the process comprising contacting under polymerization conditions one or more olefins with a catalyst system comprising a transition
20 metal compound and activator compounds, where aromatic solvents, such as toluene, are absent (e.g. present at zero mol% relative to the moles of activator, alternately present at less than 1 mol%, preferably the catalyst system, the polymerization reaction and/or the polymer produced are free of “detectable aromatic hydrocarbon solvent,” such as toluene). For purposes of the present disclosure, “detectable aromatic hydrocarbon solvent” means 0.1 mg/m² or more as
25 determined by gas phase chromatography. For purposes of the present disclosure, “detectable toluene” means 0.1 mg/m² or more as determined by gas phase chromatography.

[0055] The polyalpha-olefins produced herein preferably contain 0 ppm (alternately less than 1 ppm, alternately less than 2 ppm, alternately less than 5 ppm) of residual aromatic hydrocarbon. Preferably, the polyalpha-olefins produced herein contain 0 ppm (alternately less
30 than 1 ppm) of residual toluene.

[0056] The catalyst systems used herein preferably contain 0 ppm (alternately less than 1 ppm) of residual aromatic hydrocarbon. Preferably, the catalyst systems used herein contain 0 ppm (alternately less than 1 ppm) of residual toluene.

[0057] The polyalpha-olefins produced herein preferably contain 5 wt% or less of aromatic hydrocarbon, such as toluene, (alternately 4 wt% or less, alternately 3 wt% or less, alternately 2 wt% or less, alternately 1 wt% or less, alternately 0.5 wt% or less, alternately less than 50 ppm, alternately less than 5 ppm) of residual aromatic hydrocarbon, such as toluene.

5 Catalyst Compounds

[0058] The terms “catalyst”, “compound”, “catalyst compound”, and “complex” may be used interchangeably to describe a transition metal or Lanthanide metal complex that forms an olefin polymerization catalyst when combined with a suitable activator.

[0059] The catalyst complexes of the present invention comprise a metal selected from
10 groups 3, 4, 5 or 6 or Lanthanide metals of the Periodic Table of the Elements, a tridentate dianionic ligand containing two anionic donor groups and a neutral heterocyclic Lewis base donor, wherein the heterocyclic donor is covalently bonded between the two anionic donors. Preferably the dianionic, tridentate ligand features a central heterocyclic donor group and two phenolate donors and the tridentate ligand coordinates to the metal center to form two eight-
15 membered rings.

[0060] The metal is preferably selected from group 3, 4, 5, or 6 elements. Preferably the metal, M, is a group 4 metal. Most preferably the metal, M, is zirconium or hafnium.

[0061] Preferably the heterocyclic Lewis base donor features a nitrogen or oxygen donor atom. Preferred heterocyclic groups include derivatives of pyridine, pyrazine, pyrimidine,
20 triazine, thiazole, imidazole, thiophene, oxazole, thiazole, furan, and substituted variants of thereof. Preferably the heterocyclic Lewis base lacks hydrogen(s) in the position alpha to the donor atom. Particularly preferred heterocyclic Lewis base donors include pyridine, 3-substituted pyridines, and 4-substituted pyridines.

[0062] The anionic donors of the tridentate dianionic ligand may be arylthiolates, phenolates,
25 or anilides. Preferred anionic donors are phenolates. It is preferred that the tridentate dianionic ligand coordinates to the metal center to form a complex that lacks a mirror plane of symmetry. It is preferred that the tridentate dianionic ligand coordinates to the metal center to form a complex that has a two-fold rotation axis of symmetry; when determining the symmetry of the bis(phenolate) complexes only the metal and dianionic tridentate ligand are considered (i.e.
30 ignore remaining ligands).

[0063] The bis(phenolate) ligands useful in the present invention are preferably tridentate dianionic ligands that coordinate to the metal M in such a fashion that a pair of 8-membered metallocycle rings are formed. The bis(phenolate) ligands wrap around the metal to form a complex with a 2-fold rotation axis, thus giving the complexes C_2 symmetry. The C_2 geometry

and the 8-membered metallocycle rings are features of these complexes that make them effective catalyst components for the production of polyolefins, particularly isotactic poly(alpha olefins). If the ligands were coordinated to the metal in such a manner that the complex had mirror-plane (C_s) symmetry, then the catalyst would be expected to produce only atactic poly(alpha olefins);

5 these symmetry-reactivity rules are summarized by Bercaw, J. E. (2009) in *Macromolecules*, v.42, pp. 8751-8762. The pair of 8-membered metallocycle rings of the inventive complexes is also a notable feature that is advantageous for catalyst activity, temperature stability, and isoselectivity of monomer enchainment. Related group 4 complexes featuring smaller 6-

10 membered metallocycle rings are known (*Macromolecules* **2009**, 42, 8751-8762) to form mixtures of C_2 and C_s symmetric complexes when used in olefin polymerizations and are thus not well suited to the production of highly isotactic poly(alpha olefins).

[0064] Bis(phenolate) ligands that contain oxygen donor groups (i.e. $E = E' = \text{oxygen}$ in Formula (I)) in the present invention are preferably substituted with alkyl, substituted alkyl, aryl, or other groups. It is advantageous that each phenolate group be substituted in the ring position

15 that is adjacent to the oxygen donor atom. It is preferred that substitution at the position adjacent to the oxygen donor atom be an alkyl group containing 1-20 carbon atoms. It is preferred that substitution at the position next to the oxygen donor atom be a non-aromatic cyclic alkyl group with one or more five- or six-membered rings. It is preferred that substitution at the position next to the oxygen donor atom be a cyclic tertiary alkyl group. It is highly preferred that


20 substitution at the position next to the oxygen donor atom be adamantan-1-yl or substituted adamantan-1-yl.

[0065] The neutral heterocyclic Lewis base donor is covalently bonded between the two anionic donors via "linker groups" that join the heterocyclic Lewis base to the phenolate groups. The "linker groups" are indicated by (A^3A^2) and ($A^{2'}A^{3'}$) in Formula (I). The choice of each

25 linker group may affect the catalyst performance, such as the tacticity of the poly(alpha olefin) produced. Each linker group is typically a C_2 - C_{40} divalent group that is two-atoms in length. One or both linker groups may independently be phenylene, substituted phenylene, heteroaryl, vinylene, or a non-cyclic two-carbon long linker group. When one or both linker groups are phenylene, the alkyl substituents on the phenylene group may be chosen to optimize catalyst

30 performance. Typically, one or both phenylenes may be unsubstituted or may be independently substituted with C_1 to C_{20} alkyl, such as methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl, or an isomer thereof, such as isopropyl, etc.

[0066] This invention further relates to catalyst compounds, and catalyst systems comprising such compounds, represented by the Formula (I):



wherein:

5 M is a group 3, 4, 5, or 6 transition metal or a Lanthanide (such as Hf, Zr or Ti);

E and E' are each independently O, S, or NR⁹, where R⁹ is independently hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, or a heteroatom-containing group, preferably O, preferably both E and E' are O;

Q is group 14, 15, or 16 atom that forms a dative bond to metal M, preferably Q is C, O, S or N, more preferably Q is C, N or O, most preferably Q is N;

A¹QA^{1'} are part of a heterocyclic Lewis base containing 4 to 40 non-hydrogen atoms that links A² to A^{2'} via a 3-atom bridge with Q being the central atom of the 3-atom bridge (A¹QA^{1'} combined with the curved line joining A¹ and A^{1'} represents the heterocyclic Lewis base), A¹ and A^{1'} are independently C, N, or C(R²²), where R²² is selected from hydrogen, C₁-C₂₀ hydrocarbyl, and C₁-C₂₀ substituted hydrocarbyl. Preferably A¹ and A^{1'} are C;

$A^{3---}A^2$ is a divalent group containing 2 to 40 non-hydrogen atoms that links A^1 to the E-bonded aryl group via a 2-atom bridge, such as ortho-phenylene, substituted ortho-phenylene, ortho-arene, indolene, substituted indolene, benzothiophene, substituted benzothiophene, pyrrolene, substituted pyrrolene, thiophene, substituted thiophene, 1,2-ethylene (-CH₂CH₂-), substituted 1,2-ethylene, 1,2-vinylene (-HC=CH-), or substituted 1,2-vinylene, preferably $A^{3---}A^2$ is a divalent hydrocarbyl group;

$A^{2'} \equiv A^{3'}$ is a divalent group containing 2 to 40 non-hydrogen atoms that links $A^{1'}$ to the E'-bonded aryl group via a 2-atom bridge such as ortho-phenylene, substituted ortho-phenylene, ortho-arene, indolene, substituted indolene, benzothiophene, substituted benzothiophene, pyrrolene, substituted pyrrolene, thiophene, substituted thiophene, 1,2-ethylene (-CH₂CH₂-), substituted 1,2-ethylene, 1,2-vinylene (-HC=CH-), or substituted 1,2-vinylene,

preferably $A^{2'} \equiv A^{3'}$ is a divalent hydrocarbyl group;

each L is independently a Lewis base;

each X is independently an anionic ligand;

n is 1, 2 or 3;

5 m is 0, 1, or 2;

n+m is not greater than 4;


each of R^1 , R^2 , R^3 , R^4 , $R^{1'}$, $R^{2'}$, $R^{3'}$, and $R^{4'}$ is independently hydrogen, C_1 - C_{40} hydrocarbyl, C_1 - C_{40} substituted hydrocarbyl, a heteroatom or a heteroatom-containing group (preferably $R^{1'}$ and R^1 are independently a cyclic group, such as a cyclic tertiary alkyl group), or
 10 one or more of R^1 and R^2 , R^2 and R^3 , R^3 and R^4 , $R^{1'}$ and $R^{2'}$, $R^{2'}$ and $R^{3'}$, $R^{3'}$ and $R^{4'}$ may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings;

any two L groups may be joined together to form a bidentate Lewis base;

15 an X group may be joined to an L group to form a monoanionic bidentate group;

any two X groups may be joined together to form a dianionic ligand group.

[0067] This invention is further related to catalyst compounds, and catalyst systems comprising such compounds, represented by the Formula (II):



20 wherein:

M is a group 3, 4, 5, or 6 transition metal or a Lanthanide (such as Hf, Zr or Ti);

E and E' are each independently O, S, or NR^9 , where R^9 is independently hydrogen, C_1 - C_{40} hydrocarbyl, C_1 - C_{40} substituted hydrocarbyl, or a heteroatom-containing group, preferably O, preferably both E and E' are O;

25 each L is independently a Lewis base;

each X is independently an anionic ligand;

n is 1, 2 or 3;

m is 0, 1, or 2;

n+m is not greater than 4;

each of R¹, R², R³, R⁴, R^{1'}, R^{2'}, R^{3'}, and R^{4'} is independently hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or
 5 one or more of R¹ and R², R² and R³, R³ and R⁴, R^{1'} and R^{2'}, R^{2'} and R^{3'}, R^{3'} and R^{4'} may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings;

any two L groups may be joined together to form a bidentate Lewis base;

10 any X group may be joined to an L group to form a monoanionic bidentate group;

any two X groups may be joined together to form a dianionic ligand group;

each of R⁵, R⁶, R⁷, R⁸, R^{5'}, R^{6'}, R^{7'}, R^{8'}, R¹⁰, R¹¹, and R¹² is independently hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more of R⁵ and R⁶, R⁶ and R⁷, R⁷ and R⁸, R^{5'} and R^{6'}, R^{6'} and R^{7'}, R^{7'} and R^{8'},
 15 R¹⁰ and R¹¹, or R¹¹ and R¹² may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings.

[0068] The metal, M, is preferably selected from group 3, 4, 5, or 6 elements, more
 20 preferably group 4. Most preferably the metal, M, is zirconium or hafnium.


[0069] The donor atom Q of the neutral heterocyclic Lewis base (in Formula (I)) is preferably nitrogen, carbon, or oxygen. Preferred Q is nitrogen.

[0070] Non-limiting examples of neutral heterocyclic Lewis base groups include derivatives of pyridine, pyrazine, pyrimidine, triazine, thiazole, imidazole, thiophene, oxazole, thiazole,
 25 furan, and substituted variants of thereof. Preferred heterocyclic Lewis base groups include derivatives of pyridine, pyrazine, thiazole, and imidazole.

[0071] Each A¹ and A^{1'} of the heterocyclic Lewis base (in formula I) are independently C, N, or C(R²²), where R²² is selected from hydrogen, C₁-C₂₀ hydrocarbyl, and C₁-C₂₀ substituted hydrocarbyl. Preferably A¹ and A^{1'} are carbon. When Q is carbon, it is preferred that A¹ and
 30 A^{1'} be selected from nitrogen and C(R²²). When Q is nitrogen, it is preferred that A¹ and A^{1'} be carbon. It is preferred that Q = nitrogen, and A¹ = A^{1'} = carbon. When Q is nitrogen or oxygen, is preferred that the heterocyclic Lewis base in Formula (I) not have any hydrogen atoms bound to the A¹ or A^{1'} atoms. This is preferred because it is thought that hydrogens in those positions

may undergo unwanted decomposition reactions that reduce the stability of the catalytically active species.

- [0072] The heterocyclic Lewis base (of formula I) represented by A^1QA^1 combined with the curved line joining A^1 and A^1 is preferably selected from the following, with each R^{23} group selected from hydrogen, heteroatoms, C_1 - C_{20} alkyls, C_1 - C_{20} alkoxides, C_1 - C_{20} amides, and C_1 - C_{20} substituted alkyls.



- [0073] In some embodiments, the heterocyclic Lewis base (of Formula (I)) represented by A^1QA^1 combined with the curved line joining A^1 and A^1 is a six membered ring containing one ring heteroatom with Q being the ring heteroatom, or a five membered ring containing one or two ring heteroatoms but with Q being a ring carbon. Alternately, the heterocyclic Lewis base (of Formula (I)) represented by A^1QA^1 combined with the curved line joining A^1 and A^1 is not a five membered ring containing one or more ring heteroatoms with Q being a ring heteroatom.

- [0074] In Formula (I) or (II), E and E' are each selected from oxygen or NR^9 , where R^9 is independently hydrogen, C_1 - C_{40} hydrocarbyl, C_1 - C_{40} substituted hydrocarbyl, or a heteroatom-containing group. It is preferred that E and E' are oxygen. When E and/or E' are NR^9 it is preferred that R^9 be selected from C_1 to C_{20} hydrocarbyls, alkyls, or aryls. In one embodiment E and E' are each selected from O, S, or N(alkyl) or N(aryl), where the alkyl is preferably a C_1 to C_{20} alkyl, such as methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, nonyl, decyl, undecyl, dodecyl and the like, and aryl is a C_6 to C_{40} aryl group, such as phenyl, naphthalenyl, benzyl, methylphenyl, and the like.

[0075] In embodiments, $A^3\text{---}A^2$ and $A^{2'}\text{---}A^{3'}$ are independently a divalent hydrocarbyl group, such as C_1 to C_{12} hydrocarbyl group.

[0076] In complexes of Formula (I) or (II), when E and E' are oxygen it is advantageous that each phenolate group be substituted in the position that is next to the oxygen atom (i.e. R^1 and $R^{1'}$ in Formula (I) or (II)). Thus, when E and E' are oxygen it is preferred that each of R^1 and $R^{1'}$ is independently a C_1 - C_{40} hydrocarbyl, a C_1 - C_{40} substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, more preferably, each of R^1 and $R^{1'}$ is independently a non-aromatic cyclic alkyl group with one or more five- or six-membered rings (such as cyclohexyl, cyclooctyl, adamantanyl, or 1-methylcyclohexyl, or substituted adamantanyl), most preferably a non-aromatic cyclic tertiary alkyl group (such as 1-methylcyclohexyl, adamantanyl, or substituted adamantanyl).

[0077] In some embodiments of the invention of Formula (I) or (II), each of R^1 and $R^{1'}$ is independently a tertiary hydrocarbyl group. In other embodiments of the invention of Formula (I) or (II), each of R^1 and $R^{1'}$ is independently a cyclic tertiary hydrocarbyl group. In other embodiments of the invention of Formula (I) or (II), each of R^1 and $R^{1'}$ is independently a polycyclic tertiary hydrocarbyl group.

[0078] In some embodiments of the invention of Formula (I) or (II), each of R^1 and $R^{1'}$ is independently a tertiary hydrocarbyl group. In other embodiments of the invention of Formula (I) or (II), each of R^1 and $R^{1'}$ is independently a cyclic tertiary hydrocarbyl group. In other embodiments of the invention of Formula (I) or (II), each of R^1 and $R^{1'}$ is independently a polycyclic tertiary hydrocarbyl group.

[0079] The linker groups (i.e. $A^3\text{---}A^2$ and $A^{2'}\text{---}A^{3'}$ in Formula (I)) are each preferably part of an ortho-phenylene group, preferably a substituted ortho-phenylene group. It is preferred for the R^7 and $R^{7'}$ positions of Formula (II) to be hydrogen, or C_1 to C_{20} alkyl, such as methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl, or an isomer thereof, such as isopropyl, etc. For applications targeting polymers with high tacticity it is preferred for the R^7 and $R^{7'}$ positions of Formula (II) to be a C_1 to C_{20} alkyl, most preferred for both R^7 and $R^{7'}$ to be a C_1 to C_3 alkyl.

[0080] In embodiments of Formula (I) herein, Q is C, N or O, preferably Q is N.

[0081] In embodiments of Formula (I) herein, A^1 and $A^{1'}$ are independently carbon, nitrogen, or $C(R^{22})$, with R^{22} selected from hydrogen, C_1 - C_{20} hydrocarbyl, C_1 - C_{20} substituted hydrocarbyl. Preferably A^1 and $A^{1'}$ are carbon.

[0082] In embodiments of Formula (I) herein, $A^1QA^{1'}$ in Formula (I) is part of a heterocyclic Lewis base, such as a pyridine, pyrazine, pyrimidine, triazine, thiazole, imidazole, thiophene, oxazole, thiazole, furan, or a substituted variant of thereof.

[0083] In embodiments of Formula (I) herein, $A^1QA^{1'}$ are part of a heterocyclic Lewis base containing 2 to 20 non-hydrogen atoms that links A^2 to $A^{2'}$ via a 3-atom bridge with Q being the central atom of the 3-atom bridge. Preferably each A^1 and $A^{1'}$ is a carbon atom and the $A^1QA^{1'}$ fragment forms part of a pyridine, pyrazine, pyrimidine, triazine, thiazole, imidazole, thiophene, oxazole, thiazole, furan, or a substituted variant of thereof group, or a substituted variant thereof.

[0084] In one embodiment of Formula (I) herein, Q is carbon, and each A^1 and $A^{1'}$ is N or C(R^{22}), where R^{22} is selected from hydrogen, C_1 - C_{20} hydrocarbyl, C_1 - C_{20} substituted hydrocarbyl, a heteroatom or a heteroatom-containing group. In this embodiment, the $A^1QA^{1'}$ fragment forms part of a cyclic carbene, N-heterocyclic carbene, cyclic amino alkyl carbene, or a substituted variant of thereof group, or a substituted variant thereof.

[0085] In embodiments of Formula (I) herein, $A^3\text{---}A^2$ is a divalent group containing 2 to 20 non-hydrogen atoms that links A^1 to the E-bonded aryl group via a 2-atom bridge, where the $A^3\text{---}A^2$ is a linear alkyl or forms part of a cyclic group (such as an optionally substituted ortho-phenylene group, or ortho-arylene group) or a substituted variant thereof.

[0086] $A^{2'}\text{---}A^{3'}$ is a divalent group containing 2 to 20 non-hydrogen atoms that links $A^{1'}$ to the E'-bonded aryl group via a 2-atom bridge, where the $A^{2'}\text{---}A^{3'}$ is a linear alkyl or forms part of a cyclic group (such as an optionally substituted ortho-phenylene group, or ortho-arylene group or, or a substituted variant thereof).

[0087] In embodiments of the invention herein, in Formula (I) and (II), M is a group 4 metal, such as Hf or Zr.

[0088] In embodiments of the invention herein, in Formula (I) and (II), E and E' are O.

[0089] In embodiments of the invention herein, in Formula (I) and (II), R^1 , R^2 , R^3 , R^4 , $R^{1'}$, $R^{2'}$, $R^{3'}$, and $R^{4'}$ is independently hydrogen, C_1 - C_{40} hydrocarbyl, C_1 - C_{40} substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more of R^1 and R^2 , R^2 and R^3 , R^3 and R^4 , $R^{1'}$ and $R^{2'}$, $R^{2'}$ and $R^{3'}$, $R^{3'}$ and $R^{4'}$ may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can

join to form additional rings, preferably hydrogen, methyl, ethyl, propyl, butyl, pentyl, hexyl, or an isomer thereof.

[0090] In embodiments of the invention herein, in Formula (I) and (II), R¹, R², R³, R⁴, R^{1'}, R^{2'}, R^{3'}, R^{4'}, and R⁹ are independently selected from methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl, heneicosyl, docosyl, tricosyl, tetracosyl, pentacosyl, hexacosyl, heptacosyl, octacosyl, nonacosyl, triacontyl, phenyl, substituted phenyl (such as methylphenyl and dimethylphenyl), benzyl, substituted benzyl (such as methylbenzyl), naphthalenyl, cyclohexyl, cyclohexenyl, methylcyclohexyl, and isomers thereof.

[0091] In embodiments of the invention herein, in Formula (I) and (II), R⁴ and R^{4'} is independently hydrogen or a C₁ to C₃ hydrocarbyl, such as methyl, ethyl or propyl.

[0092] In embodiments of the invention herein, in Formula (I) and (II), R⁹ is hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, or a heteroatom-containing group, preferably hydrogen, methyl, ethyl, propyl, butyl, pentyl, hexyl, or an isomer thereof. Preferably R⁹ is methyl, ethyl, propyl, butyl, C₁ to C₆ alkyl, phenyl, 2-methylphenyl, 2,6-dimethylphenyl, or 2,4,6-trimethylphenyl.

[0093] In embodiments of the invention herein, in Formula (I) and (II), each X is, independently, selected from the group consisting of hydrocarbyl radicals having from 1 to 20 carbon atoms (such as alkyls or aryls), hydrides, amides, alkoxides, sulfides, phosphides, halides, alkyl sulfonates, and a combination thereof, (two or more X's may form a part of a fused ring or a ring system), preferably each X is independently selected from halides, aryls, and C₁ to C₅ alkyl groups, preferably each X is independently a hydrido, dimethylamido, diethylamido, methyltrimethylsilyl, neopentyl, phenyl, benzyl, methyl, ethyl, propyl, butyl, pentyl, fluoro, iodo, bromo, or chloro group.

[0094] Alternatively, each X may be, independently, a halide, a hydride, an alkyl group, an alkenyl group or an arylalkyl group.

[0095] In embodiments of the invention herein, in Formula (I) and (II), each L is a Lewis base, independently, selected from the group consisting of ethers, thio-ethers, amines, nitriles, imines, pyridines, halocarbons, and phosphines, preferably ethers and thioethers, and a combination thereof, optionally two or more L's may form a part of a fused ring or a ring system, preferably each L is independently selected from ether and thioether groups, preferably each L is a ethyl ether, tetrahydrofuran, dibutyl ether, or dimethylsulfide group.

[0096] In embodiments of the invention herein, in Formula (I) and (II), R¹ and R^{1'} are independently cyclic tertiary alkyl groups.

[0097] In embodiments of the invention herein, in Formula (I) and (II), n is 1, 2 or 3, typically 2.

[0098] In embodiments of the invention herein, in Formula (I) and (II), m is 0, 1 or 2, typically 0.

5 [0099] In embodiments of the invention herein, in Formula (I) and (II), R¹ and R^{1'} are not hydrogen.

[0100] In embodiments of the invention herein, in Formula (I) and (II), M is Hf or Zr, E and E' are O; each of R¹ and R^{1'} is independently a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, each R², R³, R⁴, R^{2'}, R^{3'}, and R^{4'} is
10 independently hydrogen, C₁-C₂₀ hydrocarbyl, C₁-C₂₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more of R¹ and R², R² and R³, R³ and R⁴, R^{1'} and R^{2'}, R^{2'} and R^{3'}, R^{3'} and R^{4'} may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form
15 additional rings; each X is, independently, selected from the group consisting of hydrocarbyl radicals having from 1 to 20 carbon atoms (such as alkyls or aryls), hydrides, amides, alkoxides, sulfides, phosphides, halides, and a combination thereof, (two or more X's may form a part of a fused ring or a ring system); each L is, independently, selected from the group consisting of ethers, thioethers, and halo carbons (two or more L's may form a part of a fused ring or a ring
20 system).

[0101] In embodiments of the invention herein, in Formula (II), each of R⁵, R⁶, R⁷, R⁸, R^{5'}, R^{6'}, R^{7'}, R^{8'}, R¹⁰, R¹¹ and R¹² is independently hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more adjacent R groups may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl
25 rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings.

[0102] In embodiments of the invention herein, in Formula (II), each of R⁵, R⁶, R⁷, R⁸, R^{5'}, R^{6'}, R^{7'}, R^{8'}, R¹⁰, R¹¹ and R¹² is independently hydrogen, methyl, ethyl, propyl, butyl, pentyl, hexyl, or an isomer thereof.

30 [0103] In embodiments of the invention herein, in Formula (II), each of R⁵, R⁶, R⁷, R⁸, R^{5'}, R^{6'}, R^{7'}, R^{8'}, R¹⁰, R¹¹ and R¹² is are independently selected from methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl, heneicosyl, docosyl, tricosyl, tetracosyl, pentacosyl, hexacosyl, heptacosyl, octacosyl, nonacosyl, triacontyl, phenyl, substituted phenyl

(such as methylphenyl and dimethylphenyl), benzyl, substituted benzyl (such as methylbenzyl), naphthalenyl, cyclohexyl, cyclohexenyl, methylcyclohexyl, and isomers thereof.

[0104] In embodiments of the invention herein, in Formula (II), M is Hf or Zr, E and E' are O; each of R¹ and R^{1'} is independently a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group,

each R¹, R², R³, R⁴, R^{1'}, R^{2'}, R^{3'}, and R^{4'} is independently hydrogen, C₁-C₂₀ hydrocarbyl, C₁-C₂₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more of R¹ and R², R² and R³, R³ and R⁴, R^{1'} and R^{2'}, R^{2'} and R^{3'}, R^{3'} and R^{4'} may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings; R⁹ is hydrogen, C₁-C₂₀ hydrocarbyl, C₁-C₂₀ substituted hydrocarbyl, or a heteroatom-containing group, such as hydrogen, methyl, ethyl, propyl, butyl, pentyl, hexyl, or an isomer thereof;

each X is, independently, selected from the group consisting of hydrocarbyl radicals having from 1 to 20 carbon atoms (such as alkyls or aryls), hydrides, amides, alkoxides, sulfides, phosphides, halides, dienes, amines, phosphines, ethers, and a combination thereof, (two or more X's may form a part of a fused ring or a ring system); n is 2; m is 0; and each of R⁵, R⁶, R⁷, R⁸, R^{5'}, R^{6'}, R^{7'}, R^{8'}, R¹⁰, R¹¹ and R¹² is independently hydrogen, C₁-C₂₀ hydrocarbyl, C₁-C₂₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more adjacent R groups may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings, such as each of R⁵, R⁶, R⁷, R⁸, R^{5'}, R^{6'}, R^{7'}, R^{8'}, R¹⁰, R¹¹ and R¹² is are independently selected from methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl, heneicosyl, docosyl, tricosyl, tetracosyl, pentacosyl, hexacosyl, heptacosyl, octacosyl, nonacosyl, triacontyl, phenyl, substituted phenyl (such as methylphenyl and dimethylphenyl), benzyl, substituted benzyl (such as methylbenzyl), naphthyl, cyclohexyl, cyclohexenyl, methylcyclohexyl, and isomers thereof.

[0105] Preferred embodiment of Formula (I) is M is Zr or Hf, Q is nitrogen, both A¹ and A^{1'} are carbon, both E and E' are oxygen, and both R¹ and R^{1'} are C₄-C₂₀ cyclic tertiary alkyls.

[0106] Preferred embodiment of Formula (I) is M is Zr or Hf, Q is nitrogen, both A¹ and A^{1'} are carbon, both E and E' are oxygen, and both R¹ and R^{1'} are adamantan-1-yl or substituted adamantan-1-yl.

[0107] Preferred embodiment of Formula (I) is M is Zr or Hf, Q is nitrogen, both A¹ and A^{1'} are carbon, both E and E' are oxygen, and both R¹ and R^{1'} are C₆-C₂₀ aryls.

[0108] Preferred embodiment of Formula (II) is M is Zr or Hf, both E and E' are oxygen, and both R¹ and R^{1'} are C₄-C₂₀ cyclic tertiary alkyls.

5 [0109] Preferred embodiment of Formula (II) is M is Zr or Hf, both E and E' are oxygen, and both R¹ and R^{1'} are adamantan-1-yl or substituted adamantan-1-yl.


[0110] Preferred embodiment of Formula (II) is M is Zr or Hf, both E and E' are oxygen, and each of R¹, R^{1'}, R³ and R^{3'} are adamantan-1-yl or substituted adamantan-1-yl.

10 [0111] Preferred embodiment of Formula (II) is M is Zr or Hf, both E and E' are oxygen, both R¹ and R^{1'} are C₄-C₂₀ cyclic tertiary alkyls, and both R⁷ and R^{7'} are C₁-C₂₀ alkyls.


[0112] Catalyst compounds that are particularly useful in this invention include one or more of: dimethylzirconium[2',2'''-(pyridine-2,6-diyl)bis(3-adamantan-1-yl)-5-(tert-butyl)-[1,1'-biphenyl]-2-olate)], dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-adamantan-1-yl)-5-(tert-butyl)-[1,1'-biphenyl]-2-olate)], dimethylzirconium[6,6'-(pyridine-2,6-diylbis(benzo[b]thiophene-3,2-diyl))bis(2-adamantan-1-yl)-4-methylphenolate)], dimethylhafnium[6,6'-(pyridine-2,6-diylbis(benzo[b]thiophene-3,2-diyl))bis(2-adamantan-1-yl)-4-methylphenolate)], dimethylzirconium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-methyl-[1,1'-biphenyl]-2-olate)], dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-methyl-[1,1'-biphenyl]-2-olate)], dimethylzirconium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-4',5-dimethyl-[1,1'-biphenyl]-2-olate)], dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-4',5-dimethyl-[1,1'-biphenyl]-2-olate)].

15
20


[0113] Catalyst compounds that are particularly useful in this invention include those represented by one or more of the formulas:




Complex 1




Complex 2




Complex 3




Complex 4




Complex 5




Complex 6




Complex 7




Complex 8




Complex 9




Complex 10




Complex 11




Complex 12




Complex 13




Complex 14




Complex 15




Complex 16




Complex 17




Complex 18




Complex 19




Complex 20




Complex 21




Complex 22




Complex 23




Complex 24




Complex 25




Complex 26




Complex 27




Complex 29



Complex 30



Complex 31



Complex 32

[0114] In some embodiments, two or more different catalyst compounds are present in the catalyst system used herein. In some embodiments, two or more different catalyst compounds are present in the reaction zone where the process(es) described herein occur. When two transition metal compound based catalysts are used in one reactor as a mixed catalyst system, the two transition metal compounds are preferably chosen such that the two are compatible. A simple screening method such as by ^1H or ^{13}C NMR, known to those of ordinary skill in the art, can be used to determine which transition metal compounds are compatible. It is preferable to use the same activator for the transition metal compounds, however, two different activators, such as a non-coordinating anion activator and an alumoxane, can be used in combination. If one or more transition metal compounds contain an X group which is not a hydride, hydrocarbyl, or substituted hydrocarbyl, then the alumoxane can be contacted with the transition metal compounds prior to addition of the non-coordinating anion activator.

[0115] The two transition metal compounds (pre-catalysts) may be used in any ratio. Preferred molar ratios of (A) transition metal compound to (B) transition metal compound fall within the range of (A:B) 1:1000 to 1000:1, alternatively 1:100 to 500:1, alternatively 1:10 to 200:1, alternatively 1:1 to 100:1, and alternatively 1:1 to 75:1, and alternatively 5:1 to 50:1. The particular ratio chosen will depend on the exact pre-catalysts chosen, the method of activation, and the end product desired. In a particular embodiment, when using the two pre-catalysts, where both are activated with the same activator, useful mole percents, based upon the molecular weight of the pre-catalysts, are 10 to 99.9% A to 0.1 to 90%B, alternatively 25 to 99% A to 0.5 to 50% B, alternatively 50 to 99% A to 1 to 25% B, and alternatively 75 to 99% A to 1 to 10%B.


Methods to Prepare the Catalyst Compounds

Ligand synthesis

[0116] The bis(phenol) ligands may be prepared using the general methods shown in Scheme 1. The formation of the bis(phenol) ligand by the coupling of compound A with compound B (method 1) may be accomplished by known Pd- and Ni-catalyzed couplings, such as Negishi, Suzuki, or Kumada couplings. The formation of the bis(phenol) ligand by the coupling of compound C with compound D (method 2) may also be accomplished by known Pd- and Ni-catalyzed couplings, such as Negishi, Suzuki, or Kumada couplings. Compound D may be prepared from compound E by reaction of compound E with either an organolithium reagent or magnesium metal, followed by optional reaction with a main-group metal halide (e.g. ZnCl_2) or boron-based reagent (e.g. $\text{B}(\text{O}^i\text{Pr})_3$, $^i\text{PrOB}(\text{pin})$). Compound E may be prepared in a non-catalyzed reaction from by the reaction of an aryllithium or aryl Grignard reagent (compound F) with a dihalogenated arene (compound G), such as 1-bromo-2-chlorobenzene.

Compound E may also be prepared in a Pd- or Ni-catalyzed reaction by reaction of an arylzinc or aryl-boron reagent (compound F) with a dihalogenated arene (compound G).

Scheme 1



- 5 where M' is a group 1, 2, 12, or 13 element or substituted element such as Li, MgCl, MgBr, ZnCl, B(OH)₂, B(pinacolate), P is a protective group such as methoxymethyl (MOM), tetrahydropyranyl (THP), t-butyl, allyl, ethoxymethyl, trialkylsilyl, t-butyldimethylsilyl, or benzyl, R is a C₁-C₄₀ alkyl, substituted alkyl, aryl, tertiary alkyl, cyclic tertiary alkyl, adamantanyl, or substituted adamantanyl and each X' and X is halogen, such as Cl, Br, F or I.
- 10 It is preferred that the bis(phenol) ligand and intermediates used for the preparation of the

bis(phenol) ligand are prepared and purified without the use of column chromatography. This may be accomplished by a variety of methods that include distillation, precipitation and washing, formation of insoluble salts (such as by reaction of a pyridine derivative with an organic acid), and liquid-liquid extraction. Preferred methods include those described in Practical Process

5 Research and Development – A Guide for Organic Chemists by Neal C. Anderson (ISBN: 1493300125X).


Synthesis of carbene bis(phenol) ligands

[0117] The general synthetic method to produce carbene bis(phenol) ligands is shown in Scheme 2. A substituted phenol can be ortho-brominated then protected by a known phenol

10 protecting group, such as MOM, THP, t-butyldimethylsilyl (TBDMS), benzyl (Bn), etc. The bromide is then converted to a boronic ester (compound I) or boronic acid which can be used in a Suzuki coupling with bromoaniline. The biphenylaniline (compound J) can be bridged by reaction with dibromoethane or condensation with oxalaldehyde, then deprotected (compound K). Reaction with triethyl orthoformate forms an iminium salt that is deprotonated to a carbene.

15

Scheme 2



[0118] The substituted phenol (compound H) dissolved in methylene chloride, is added an equivalent of N-bromosuccinimide and 0.1 equivalent of diisopropylamine. After stirring at ambient temperature until completion, the reaction is quenched with a 10% solution of HCl. The organic portion is washed with brine, dried over magnesium sulfate, filtered, and concentrated under reduced pressure to give a bromophenol, typically as a solid. The substituted bromophenol, methoxymethylchloride, and potassium carbonate are dissolved in dry acetone and stirred at ambient temperature until completion of the reaction. The solution is filtered and the filtrate concentrated to give protected phenol (compound I). Alternatively, the substituted bromophenol and an equivalent of dihydropyran is dissolved in methylene chloride and cooled to 0°C. A catalytic amount of para-toluenesulfonic acid is added and the reaction stirred for 10 minutes, then quenched with trimethylamine. The mixture is washed with water and brine, then dried over magnesium sulfate, filtered, and concentrated under reduced pressure to give a tetrahydropyran-protected phenol.

[0119] Aryl bromide (compound I) is dissolved in THF and cooled to -78°C. n-Butyllithium is added slowly, followed by trimethoxy borate. The reaction is allowed to stir at ambient temperature until completion. The solvent is removed and the solid boronic ester washed with pentane. A boronic acid can be made from the boronic ester by treatment with HCl. The boronic ester or acid is dissolved in toluene with an equivalent of ortho-bromoaniline and a catalytic amount of palladium tetrakis(triphenyl)phosphine. An aqueous solution of sodium carbonate is added and the reaction heated at reflux overnight. Upon cooling, the layers are separated and the aqueous layer extracted with ethyl acetate. The combined organic portions are washed with brine, dried (MgSO₄), filtered, and concentrated under reduced pressure. Column chromatography is typically used to purify the coupled product (compound J).

[0120] The aniline (compound J) and dibromoethane (0.5 equiv.) are dissolved in acetonitrile and heated at 60°C overnight. The reaction is filtered and concentrated to give an ethylene bridged dianiline. The protected phenol is deprotected by reaction with HCl to give a bridged bisamino(biphenyl)ol (compound K).

[0121] The diamine (compound K) is dissolved in triethylorthoformate. Ammonium chloride is added and the reaction heated at reflux overnight. A precipitate is formed which is collected by filtration and washed with ether to give the iminium salt. The iminium chloride is suspended in THF and treated with lithium or sodium hexamethyldisilylamide. Upon completion, the reaction is filtered and the filtrate concentrated to give the carbene ligand.

Preparation of bis(phenolate) complexes

[0122] Transition metal or Lanthanide metal bis(phenolate) complexes are used as catalyst components for olefin polymerization in the present invention. The terms “catalyst” and “catalyst complex” are used interchangeably. The preparation of transition metal or Lanthanide metal bis(phenolate) complexes may be accomplished by reaction of the bis(phenol) ligand with a metal reactant containing anionic basic leaving groups. Typical anionic basic leaving groups include dialkylamido, benzyl, phenyl, hydrido, and methyl. In this reaction, the role of the basic leaving group is to deprotonate the bis(phenol) ligand. Suitable metal reactants for this type of reaction include, but are not limited to, HfBn₄ (Bn = CH₂Ph), ZrBn₄, TiBn₄, ZrBn₂Cl₂(OEt₂), HfBn₂Cl₂(OEt₂)₂, Zr(NMe₂)₂Cl₂(dimethoxyethane), Hf(NMe₂)₂Cl₂(dimethoxyethane), Hf(NMe₂)₄, Zr(NMe₂)₄, and Hf(NEt₂)₄. Suitable metal reagents also include ZrMe₄, HfMe₄, and other group 4 alkyls that may be formed *in situ* and used without isolation.

[0123] A second method for the preparation of transition metal or Lanthanide bis(phenolate) complexes is by reaction of the bis(phenol) ligand with an alkali metal or alkaline earth metal base (e.g., Na, BuLi, ⁱPrMgBr) to generate deprotonated ligand, followed by reaction with a metal halide (e.g., HfCl₄, ZrCl₄) to form a bis(phenolate) complex. Bis(phenolate) metal complexes that contain metal-halide, alkoxide, or amido leaving groups may be alkylated by reaction with organolithium, Grignard, and organoaluminum reagents. In the alkylation reaction the alkyl groups are transferred to the bis(phenolate) metal center and the leaving groups are removed. Reagents typically used for the alkylation reaction include, but are not limited to, MeLi, MeMgBr, AlMe₃, Al(ⁱBu)₃, AlOct₃, and PhCH₂MgCl. Typically 2 to 20 molar equivalents of the alkylating reagent are added to the bis(phenolate) complex. The alkylations are generally performed in etherial or hydrocarbon solvents or solvent mixtures at temperatures typically ranging from -80°C to 120°C.

Activators

[0124] The terms “cocatalyst” and “activator” are used herein interchangeably.

[0125] The catalyst systems described herein typically comprises a catalyst complex, such as the transition metal or Lanthanide bis(phenolate) complexes described above, and an activator such as alumoxane or a non-coordinating anion. These catalyst systems may be formed by combining the catalyst components described herein with activators in any manner known from the literature. The catalyst systems may also be added to or generated in solution polymerization or bulk polymerization (in the monomer). Catalyst systems of the present disclosure may have one or more activators and one, two or more catalyst components. Activators are defined to be any compound which can activate any one of the catalyst compounds described above by

converting the neutral metal compound to a catalytically active metal compound cation. Non-limiting activators, for example, include alumoxanes, ionizing activators, which may be neutral or ionic, and conventional-type cocatalysts. Preferred activators typically include alumoxane compounds, modified alumoxane compounds, and ionizing anion precursor compounds that abstract a reactive metal ligand making the metal compound cationic and providing a charge-balancing non-coordinating or weakly coordinating anion, e.g. a non-coordinating anion.

Alumoxane Activators

[0126] Alumoxane activators are utilized as activators in the catalyst systems described herein. Alumoxanes are generally oligomeric compounds containing $-Al(R^1)-O-$ sub-units, where R^1 is an alkyl group. Examples of alumoxanes include methylalumoxane (MAO), modified methylalumoxane (MMAO), ethylalumoxane and isobutylalumoxane. Alkylalumoxanes and modified alkylalumoxanes are suitable as catalyst activators, particularly when the abstractable ligand is an alkyl, halide, alkoxide or amide. Mixtures of different alumoxanes and modified alumoxanes may also be used. It may be preferable to use a visually clear methylalumoxane. A cloudy or gelled alumoxane can be filtered to produce a clear solution or clear alumoxane can be decanted from the cloudy solution. A useful alumoxane is a modified methyl alumoxane (MMAO) cocatalyst type 3A (commercially available from Akzo Chemicals, Inc. under the trade name Modified Methylalumoxane type 3A, covered under patent number U.S. Patent No. 5,041,584). Another useful alumoxane is solid polymethylaluminumoxane as described in US 9,340,630; US 8,404,880; and US 8,975,209.

[0127] When the activator is an alumoxane (modified or unmodified), typically the maximum amount of activator is at up to a 5,000-fold molar excess Al/M over the catalyst compound (per metal catalytic site). The minimum activator-to-catalyst-compound is a 1:1 molar ratio. Alternate preferred ranges include from 1:1 to 500:1, alternately from 1:1 to 200:1, alternately from 1:1 to 100:1, or alternately from 1:1 to 50:1.

[0128] In an alternate embodiment, little or no alumoxane is used in the polymerization processes described herein. Preferably, alumoxane is present at zero mole %, alternately the alumoxane is present at a molar ratio of aluminum to catalyst compound transition metal less than 500:1, preferably less than 300:1, preferably less than 100:1, preferably less than 1:1.

Ionizing/Non Coordinating Anion Activators

[0129] The term "non-coordinating anion" (NCA) means an anion which either does not coordinate to a cation or which is only weakly coordinated to a cation thereby remaining sufficiently labile to be displaced by a neutral Lewis base. Further, the anion will not transfer an anionic substituent or fragment to the cation so as to cause it to form a neutral transition metal

compound and a neutral by-product from the anion. Non-coordinating anions useful in accordance with this invention are those that are compatible, stabilize the transition metal cation in the sense of balancing its ionic charge at +1, and yet retain sufficient lability to permit displacement during polymerization. The term NCA is also defined to include multicomponent NCA-containing activators, such as N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate, that contain an acidic cationic group and the non-coordinating anion. The term NCA is also defined to include neutral Lewis acids, such as tris(pentafluorophenyl)boron, that can react with a catalyst to form an activated species by abstraction of an anionic group. Any metal or metalloid that can form a compatible, weakly coordinating complex may be used or contained in the non-coordinating anion. Suitable metals include, but are not limited to, aluminum, gold, and platinum. Suitable metalloids include, but are not limited to, boron, aluminum, phosphorus, and silicon.

[0130] It is within the scope of this invention to use an ionizing activator, neutral or ionic. It is also within the scope of this invention to use neutral or ionic activators alone or in combination with alumoxane or modified alumoxane activators.

[0131] In embodiments of the invention, the activator is represented by the Formula (III):



wherein Z is (L-H) or a reducible Lewis Acid, L is an neutral Lewis base; H is hydrogen; (L-H)⁺ is a Bronsted acid; A^{d-} is a non-coordinating anion having the charge d-; and d is an integer from 1 to 3 (such as 1, 2 or 3), preferably Z is (Ar₃C⁺), where Ar is aryl or aryl substituted with a heteroatom, a C₁ to C₄₀ hydrocarbyl, or a substituted C₁ to C₄₀ hydrocarbyl. The anion component A^{d-} includes those having the formula [M^{k+}Q_n]^{d-} wherein k is 1, 2, or 3; n is 1, 2, 3, 4, 5, or 6 (preferably 1, 2, 3, or 4); n - k = d; M is an element selected from Group 13 of the Periodic Table of the Elements, preferably boron or aluminum, and Q is independently a hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, and halosubstituted-hydrocarbyl radicals, said Q having up to 40 carbon atoms (optionally with the proviso that in not more than 1 occurrence is Q a halide). Preferably, each Q is a fluorinated hydrocarbyl group having 1 to 40 (such as 1 to 20) carbon atoms, more preferably each Q is a fluorinated aryl group, such as a perfluorinated aryl group and most preferably each Q is a pentafluoryl aryl group or perfluoronaphthalenyl group. Examples of suitable A^{d-} also include diboron compounds as disclosed in U.S. Patent No. 5,447,895, which is fully incorporated herein by reference.

[0132] When Z is the activating cation (L-H), it can be a Bronsted acid, capable of donating

a proton to the transition metal catalytic precursor resulting in a transition metal cation, including ammoniums, oxoniums, phosphoniums, sulfoniums, and mixtures thereof, such as ammoniums of methylamine, aniline, dimethylamine, diethylamine, N-methylaniline, N-methyl-4-nonadecyl-N-octadecylaniline, N-methyl-4-octadecyl-N-octadecylaniline, diphenylamine, 5 trimethylamine, triethylamine, N,N-dimethylaniline, methyldiphenylamine, pyridine, p-bromo N,N-dimethylaniline, p-nitro-N,N-dimethylaniline, dioctadecylmethylamine, phosphoniums from triethylphosphine, triphenylphosphine, and diphenylphosphine, oxoniums from ethers such as dimethyl ether, diethyl ether, tetrahydrofuran and dioxane, sulfoniums from thioethers, such as diethyl thioethers, tetrahydrothiophene, and mixtures thereof.

10 **[0133]** In particularly useful embodiments of the invention, the activator is soluble in non-aromatic-hydrocarbon solvents, such as aliphatic solvents.

[0134] In one or more embodiments, a 20 wt% mixture of the activator compound in n-hexane, isohexane, cyclohexane, methylcyclohexane, or a combination thereof, forms a clear homogeneous solution at 25°C, preferably a 30 wt% mixture of the activator compound in 15 n-hexane, isohexane, cyclohexane, methylcyclohexane, or a combination thereof, forms a clear homogeneous solution at 25°C.

[0135] In embodiments of the invention, the activators described herein have a solubility of more than 10 mM (or more than 20 mM, or more than 50 mM) at 25°C (stirred 2 hours) in methylcyclohexane.

20 **[0136]** In embodiments of the invention, the activators described herein have a solubility of more than 1 mM (or more than 10 mM, or more than 20 mM) at 25°C (stirred 2 hours) in isohexane.

[0137] In embodiments of the invention, the activators described herein have a solubility of more than 10 mM (or more than 20 mM, or more than 50 mM) at 25°C (stirred 2 hours) in 25 methylcyclohexane and a solubility of more than 1 mM (or more than 10 mM, or more than 20 mM) at 25°C (stirred 2 hours) in isohexane.

[0138] In a preferred embodiment, the activator is a non-aromatic-hydrocarbon soluble activator compound.

[0139] Non-aromatic-hydrocarbon soluble activator compounds useful herein include those 30 represented by the Formula (V):



wherein:

E is nitrogen or phosphorous;

d is 1, 2 or 3; *k* is 1, 2, or 3; *n* is 1, 2, 3, 4, 5, or 6; *n* − *k* = *d* (preferably *d* is 1, 2 or

3; k is 3; n is 4, 5, or 6);


$R^{1'}$, $R^{2'}$, and $R^{3'}$ are independently a C_1 to C_{50} hydrocarbyl group optionally substituted with one or more alkoxy groups, silyl groups, a halogen atoms, or halogen containing groups,

wherein $R^{1'}$, $R^{2'}$, and $R^{3'}$ together comprise 15 or more carbon atoms;

5 Mt is an element selected from group 13 of the Periodic Table of the Elements, such as B or Al; and

each Q is independently a hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxide, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, or halosubstituted-hydrocarbyl radical.


10 **[0140]** Non-aromatic-hydrocarbon soluble activator compounds useful herein include those represented by the Formula (VI):




wherein: E is nitrogen or phosphorous; $R^{1'}$ is a methyl group; $R^{2'}$ and $R^{3'}$ are independently is C_4 - C_{50} hydrocarbyl group optionally substituted with one or more alkoxy groups, silyl groups, a

15 halogen atoms, or halogen containing groups wherein $R^{2'}$ and $R^{3'}$ together comprise 14 or more carbon atoms; B is boron; and $R^{4'}$, $R^{5'}$, $R^{6'}$, and $R^{7'}$ are independently hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxide, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, or halosubstituted-hydrocarbyl radical.

[0141] Non-aromatic-hydrocarbon soluble activator compounds useful herein include those represented by the Formula (VII) or Formula (VIII):



and



wherein:

25 N is nitrogen;

$R^{2'}$ and $R^{3'}$ are independently is C_6 - C_{40} hydrocarbyl group optionally substituted with one or more alkoxy groups, silyl groups, a halogen atoms, or halogen containing groups wherein

$R^{2'}$ and $R^{3'}$ (if present) together comprise 14 or more carbon atoms;

$R^{8'}$, $R^{9'}$, and $R^{10'}$ are independently a C₄-C₃₀ hydrocarbyl or substituted C₄-C₃₀ hydrocarbyl group;

B is boron;

- 5 and $R^{4'}$, $R^{5'}$, $R^{6'}$, and $R^{7'}$ are independently hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, or halosubstituted-hydrocarbyl radical.

[0142] Optionally, in any of Formulas (V), (VI), (VII), or (VIII) herein, $R^{4'}$, $R^{5'}$, $R^{6'}$, and $R^{7'}$ are pentafluorophenyl.

- 10 [0143] Optionally, in any of Formulas (V), (VI), (VII), or (VIII) herein, $R^{4'}$, $R^{5'}$, $R^{6'}$, and $R^{7'}$ are pentafluoronaphthalenyl.

[0144] Optionally, in any embodiment of Formula (VIII) herein, $R^{8'}$ and $R^{10'}$ are hydrogen atoms and $R^{9'}$ is a C₄-C₃₀ hydrocarbyl group which is optionally substituted with one or more alkoxy groups, silyl groups, a halogen atoms, or halogen containing groups.

- 15 [0145] Optionally, in any embodiment of Formula (VIII) herein, $R^{9'}$ is a C₈-C₂₂ hydrocarbyl group which is optionally substituted with one or more alkoxy groups, silyl groups, a halogen atoms, or halogen containing groups.

[0146] Optionally, in any embodiment of Formula (VII) or (VIII) herein, $R^{2'}$ and $R^{3'}$ are independently a C₁₂-C₂₂ hydrocarbyl group.

- 20 [0147] Optionally, $R^{1'}$, $R^{2'}$ and $R^{3'}$ together comprise 15 or more carbon atoms (such as 18 or more carbon atoms, such as 20 or more carbon atoms, such as 22 or more carbon atoms, such as 25 or more carbon atoms, such as 30 or more carbon atoms, such as 35 or more carbon atoms, such as 38 or more carbon atoms, such as 40 or more carbon atoms, such as 15 to 100 carbon atoms, such as 25 to 75 carbon atoms).

- 25 [0148] Optionally, $R^{2'}$ and $R^{3'}$ together comprise 15 or more carbon atoms (such as 18 or more carbon atoms, such as 20 or more carbon atoms, such as 22 or more carbon atoms, such as 25 or more carbon atoms, such as 30 or more carbon atoms, such as 35 or more carbon atoms, such as 38 or more carbon atoms, such as 40 or more carbon atoms, such as 15 to 100 carbon atoms, such as 25 to 75 carbon atoms).

- 30 [0149] Optionally, $R^{8'}$, $R^{9'}$, and $R^{10'}$ together comprise 15 or more carbon atoms (such as 18 or more carbon atoms, such as 20 or more carbon atoms, such as 22 or more carbon atoms, such as 25 or more carbon atoms, such as 30 or more carbon atoms, such as 35 or more carbon

atoms, such as 38 or more carbon atoms, such as 40 or more carbon atoms, such as 15 to 100 carbon atoms, such as 25 to 75 carbon atoms).

[0150] Optionally, when Q is a fluorophenyl group, then $R^{2'}$ is not a C₁-C₄₀ linear alkyl group (alternately $R^{2'}$ is not an optionally substituted C₁-C₄₀ linear alkyl group).

5 [0151] Optionally, each of $R^{4'}$, $R^{5'}$, $R^{6'}$, and $R^{7'}$ is an aryl group (such as phenyl or naphthalenyl), wherein at least one of $R^{4'}$, $R^{5'}$, $R^{6'}$, and $R^{7'}$ is substituted with at least one fluorine atom, preferably each of $R^{4'}$, $R^{5'}$, $R^{6'}$, and $R^{7'}$ is a perfluoroaryl group (such as perfluorophenyl or perfluoronaphthalenyl).

[0152] Optionally, each Q is an aryl group (such as phenyl or naphthalenyl), wherein at least
10 one Q is substituted with at least one fluorine atom, preferably each Q is a perfluoroaryl group (such as perfluorophenyl or perfluoronaphthalenyl).

[0153] Optionally, $R^{1'}$ is a methyl group; $R^{2'}$ is C₆-C₅₀ aryl group; and $R^{3'}$ is independently C₁-C₄₀ linear alkyl or C₅-C₅₀-aryl group.






















[0154] Optionally, each of $R^{2'}$ and $R^{3'}$ is independently unsubstituted or substituted with at
15 least one of halide, C₁-C₃₅ alkyl, C₅-C₁₅ aryl, C₆-C₃₅ arylalkyl, C₆-C₃₅ alkylaryl, wherein R^2 , and R^3 together comprise 20 or more carbon atoms.

[0155] Optionally, each Q is independently a hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, or halosubstituted-hydrocarbyl radical, provided that when Q is a fluorophenyl
20 group, then $R^{2'}$ is not a C₁-C₄₀ linear alkyl group, preferably $R^{2'}$ is not an optionally substituted C₁-C₄₀ linear alkyl group (alternately when Q is a substituted phenyl group, then $R^{2'}$ is not a C₁-C₄₀ linear alkyl group, preferably $R^{2'}$ is not an optionally substituted C₁-C₄₀ linear alkyl group). Optionally, when Q is a fluorophenyl group (alternately when Q is a substituted phenyl group), then $R^{2'}$ is a meta- and/or para-substituted phenyl group, where the meta and para
25 substituents are, independently, an optionally substituted C₁ to C₄₀ hydrocarbyl group (such as a C₆ to C₄₀ aryl group or linear alkyl group, a C₁₂ to C₃₀ aryl group or linear alkyl group, or a C₁₀ to C₂₀ aryl group or linear alkyl group), an optionally substituted alkoxy group, or an optionally substituted silyl group. Optionally, each Q is a fluorinated hydrocarbyl group having 1 to 30 carbon atoms, more preferably each Q is a fluorinated aryl (such as phenyl or naphthalenyl)
30 group, and most preferably each Q is a perfluorinated aryl (such as phenyl or naphthalenyl) group. Examples of suitable $[Mt^{k+}Q_n]^{d-}$ also include diboron compounds as disclosed in US Patent No. 5,447,895, which is fully incorporated herein by reference. Optionally, at least one

Q is not substituted phenyl. Optionally all Q are not substituted phenyl. Optionally at least one Q is not perfluorophenyl. Optionally all Q are not perfluorophenyl.


- [0156] In some embodiments of the invention, $R^{1'}$ is not methyl, $R^{2'}$ is not C_{18} alkyl and $R^{3'}$ is not C_{18} alkyl, alternately $R^{1'}$ is not methyl, $R^{2'}$ is not C_{18} alkyl and $R^{3'}$ is not C_{18} alkyl and at least one Q is not substituted phenyl, optionally all Q are not substituted phenyl.

[0157] Useful cation components in Formulas (III) and (V) to (VIII) include those represented by the formula:

10		11		12	
13		14		15	
16		17		18	
19		20		21	
22		23		24	
25		26		27	
29		28		30	

tetrakis(pentafluorophenyl)borate.

[0162] Anions for use in the non-coordinating anion activators described herein also include those represented by formula 7, below:



Formula 7

5 wherein:

M^* is a group 13 atom, preferably B or Al, preferably B;

each R^{11} is, independently, a halide, preferably a fluoride;

each R^{12} is, independently, a halide, a C_6 to C_{20} substituted aromatic hydrocarbyl group or a siloxy group of the formula $-O-Si-R^a$, where R^a is a C_1 to C_{20} hydrocarbyl or hydrocarbylsilyl group, preferably R^{12} is a fluoride or a perfluorinated phenyl group;

each R^{13} is a halide, a C_6 to C_{20} substituted aromatic hydrocarbyl group or a siloxy group of the formula $-O-Si-R^a$, where R^a is a C_1 to C_{20} hydrocarbyl or hydrocarbylsilyl group, preferably R^{13} is a fluoride or a C_6 perfluorinated aromatic hydrocarbyl group;

wherein R^{12} and R^{13} can form one or more saturated or unsaturated, substituted or unsubstituted rings, preferably R^{12} and R^{13} form a perfluorinated phenyl ring. Preferably the anion has a molecular weight of greater than 700 g/mol, and, preferably, at least three of the substituents on the M^* atom each have a molecular volume of greater than 180 cubic Å.

[0163] "Molecular volume" is used herein as an approximation of spatial steric bulk of an activator molecule in solution. Comparison of substituents with differing molecular volumes allows the substituent with the smaller molecular volume to be considered "less bulky" in comparison to the substituent with the larger molecular volume. Conversely, a substituent with a larger molecular volume may be considered "more bulky" than a substituent with a smaller

molecular volume.

- [0164] Molecular volume may be calculated as reported in "A Simple "Back of the Envelope" Method for Estimating the Densities and Molecular Volumes of Liquids and Solids," *Journal of Chemical Education*, v.71(11), November 1994, pp. 962-964. Molecular volume (MV), in units of cubic Å, is calculated using the formula: $MV = 8.3V_S$, where V_S is the scaled volume. V_S is the sum of the relative volumes of the constituent atoms, and is calculated from the molecular formula of the substituent using Table A below of relative volumes. For fused rings, the V_S is decreased by 7.5% per fused ring. The Calculated Total MV of the anion is the sum of the MV per substituent, for example, the MV of perfluorophenyl is 183 Å^3 , and the
- 5
- 10 Calculated Total MV for tetrakis(perfluorophenyl)borate is four times 183 Å^3 , or 732 Å^3 .







Table A

Element	Relative Volume
H	1
1 st short period, Li to F	2
2 nd short period, Na to Cl	4
1 st long period, K to Br	5
2 nd long period, Rb to I	7.5
3 rd long period, Cs to Bi	9

- [0165] Exemplary anions useful herein and their respective scaled volumes and molecular volumes are shown in Table B below. The dashed bonds indicate bonding to boron.

15

Table B

Ion	Structure of Boron Substituents	Molecular Formula of Each Substituent	V_s	MV Per subst. ($\text{\AA}^3$)	Calculated Total MV ($\text{\AA}^3$)
tetrakis(perfluorophenyl)borate		C_6F_5	22	183	732
tris(perfluorophenyl)-(perfluoronaphthalenyl)borate		C_6F_5 $C_{10}F_7$	22 34	183 261	810
(perfluorophenyl)tris-(perfluoronaphthalenyl)borate		C_6F_5 $C_{10}F_7$	22 34	183 261	966
tetrakis(perfluoronaphthalenyl)borate		$C_{10}F_7$	34	261	1044
tetrakis(perfluorobiphenyl)borate		$C_{12}F_9$	42	349	1396
$[(C_6F_3(C_6F_5)_2)_4B]$		$C_{18}F_{13}$	62	515	2060

[0166] The activators may be added to a polymerization in the form of an ion pair using, for example, [M2HTH]⁺ [NCA]⁻ in which the di(hydrogenated tallow)methylamine (“M2HTH”) cation reacts with a basic leaving group on the transition metal complex to form a transition metal complex cation and [NCA]⁻. Alternatively, the transition metal complex may be reacted with a neutral NCA precursor, such as B(C₆F₅)₃, which abstracts an anionic group from the complex to form an activated species. Useful activators include di(hydrogenated tallow)methylammonium[tetrakis(pentafluorophenyl)borate] (i.e., [M2HTH]B(C₆F₅)₄) and di(octadecyl)tolylammonium [tetrakis(pentafluorophenyl)borate] (i.e., [DODTH]B(C₆F₅)₄).

[0167] Activator compounds that are particularly useful in this invention include one or more of:

- N,N*-di(hydrogenated tallow)methylammonium [tetrakis(perfluorophenyl) borate],
- N*-methyl-4-nonadecyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-hexadecyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-tetradecyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-dodecyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-decyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-octyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-hexyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-butyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-octadecyl-*N*-decylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-nonadecyl-*N*-dodecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-nonadecyl-*N*-tetradecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-4-nonadecyl-*N*-hexadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-ethyl-4-nonadecyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
- N*-methyl-*N,N*-dioctadecylammonium [tetrakis(perfluorophenyl)borate],
- N*-methyl-*N,N*-dihexadecylammonium [tetrakis(perfluorophenyl)borate],
- N*-methyl-*N,N*-ditetradecylammonium [tetrakis(perfluorophenyl)borate],
- N*-methyl-*N,N*-didodecylammonium [tetrakis(perfluorophenyl)borate],
- N*-methyl-*N,N*-didecylammonium [tetrakis(perfluorophenyl)borate],
- N*-methyl-*N,N*-dioctylammonium [tetrakis(perfluorophenyl)borate],
- N*-ethyl-*N,N*-dioctadecylammonium [tetrakis(perfluorophenyl)borate],
- N,N*-di(octadecyl)tolylammonium [tetrakis(perfluorophenyl)borate],
- N,N*-di(hexadecyl)tolylammonium [tetrakis(perfluorophenyl)borate],
- N,N*-di(tetradecyl)tolylammonium [tetrakis(perfluorophenyl)borate],

- N,N*-di(dodecyl)tolylammonium [tetrakis(perfluorophenyl)borate],
N-octadecyl-*N*-hexadecyl-tolylammonium [tetrakis(perfluorophenyl)borate],
N-octadecyl-*N*-hexadecyl-tolylammonium [tetrakis(perfluorophenyl)borate],
N-octadecyl-*N*-tetradecyl-tolylammonium [tetrakis(perfluorophenyl)borate],
5 *N*-octadecyl-*N*-dodecyl-tolylammonium [tetrakis(perfluorophenyl)borate],
N-octadecyl-*N*-decyl-tolylammonium [tetrakis(perfluorophenyl)borate],
N-hexadecyl-*N*-tetradecyl-tolylammonium [tetrakis(perfluorophenyl)borate],
N-hexadecyl-*N*-dodecyl-tolylammonium [tetrakis(perfluorophenyl)borate],
N-hexadecyl-*N*-decyl-tolylammonium [tetrakis(perfluorophenyl)borate],
10 *N*-tetradecyl-*N*-dodecyl-tolylammonium [tetrakis(perfluorophenyl)borate],
N-tetradecyl-*N*-decyl-tolylammonium [tetrakis(perfluorophenyl)borate],
N-dodecyl-*N*-decyl-tolylammonium [tetrakis(perfluorophenyl)borate],
N-methyl-*N*-octadecylanilinium [tetrakis(perfluorophenyl)borate],
N-methyl-*N*-hexadecylanilinium [tetrakis(perfluorophenyl)borate],
15 *N*-methyl-*N*-tetradecylanilinium [tetrakis(perfluorophenyl)borate],
N-methyl-*N*-dodecylanilinium [tetrakis(perfluorophenyl)borate],
N-methyl-*N*-decylanilinium [tetrakis(perfluorophenyl)borate], and
N-methyl-*N*-octylanilinium [tetrakis(perfluorophenyl)borate].
- [0168]** Additional useful activators and the synthesis non-aromatic-hydrocarbon soluble
20 activators, are described in USSN 16/394,166 filed April 25, 2019, USSN 16/394,186, filed April
25, 2019, and USSN 16/394,197, filed April 25, 2019, which are incorporated by reference
herein.
- [0169]** Likewise, particularly useful activators also include dimethylaniliniumtetrakis
(pentafluorophenyl) borate and dimethyl anilinium tetrakis(heptafluoro-2-naphthalenyl) borate.
25 For a more detailed description of useful activators please see WO 2004/026921 page 72,
paragraph [00119] to page 81 paragraph [00151]. A list of additionally particularly useful
activators that can be used in the practice of this invention may be found at page 72, paragraph
[00177] to page 74, paragraph [00178] of WO 2004/046214.
- [0170]** For descriptions of useful activators please see US 8,658,556 and US 6,211,105.
- 30 **[0171]** Preferred activators for use herein also include *N*-methyl-4-nonadecyl-*N*-
octadecylbenzenaminium tetrakis(pentafluorophenyl)borate, *N*-methyl-4-nonadecyl-*N*-
octadecylbenzenaminium tetrakis(perfluoronaphthalenyl)borate, *N,N*-dimethylanilinium
tetrakis(perfluoronaphthalenyl)borate, *N,N*-dimethylanilinium
tetrakis(perfluorobiphenyl)borate, *N,N*-dimethylanilinium tetrakis(perfluorophenyl)borate,

N,N-dimethylanilinium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, triphenylcarbenium tetrakis(perfluoronaphthalenyl)borate, triphenylcarbenium tetrakis(perfluorobiphenyl)borate, triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, triphenylcarbenium tetrakis(perfluorophenyl)borate, $[\text{Me}_3\text{NH}^+][\text{B}(\text{C}_6\text{F}_5)_4^-]$; 1-(4-(tris(pentafluorophenyl)borate)-2,3,5,6-tetrafluorophenyl)pyrrolidinium; and tetrakis(pentafluorophenyl)borate, 4-(tris(pentafluorophenyl)borate)-2,3,5,6-tetrafluoropyridine.

[0172] In a preferred embodiment, the activator comprises a triaryl carbenium (such as triphenylcarbenium tetraphenylborate, triphenylcarbenium tetrakis(pentafluorophenyl)borate, triphenylcarbenium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, triphenylcarbenium tetrakis(perfluoronaphthalenyl)borate, triphenylcarbenium tetrakis(perfluorobiphenyl)borate, triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate).

[0173] In another embodiment, the activator comprises one or more of trialkylammonium tetrakis(pentafluorophenyl)borate, N,N-dialkylanilinium tetrakis(pentafluorophenyl)borate, dioctadecylmethylammonium tetrakis(pentafluorophenyl)borate, dioctadecylmethylammonium tetrakis(perfluoronaphthalenyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl)borate, trialkylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, N,N-dialkylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, trialkylammonium tetrakis(perfluoronaphthalenyl)borate, N,N-dialkylanilinium tetrakis(perfluoronaphthalenyl)borate, trialkylammonium tetrakis(perfluorobiphenyl)borate, N,N-dialkylanilinium tetrakis(perfluorobiphenyl)borate, trialkylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, N,N-dialkylanilinium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, N,N-dialkyl-(2,4,6-trimethylanilinium) tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, di-(i-propyl)ammonium tetrakis(pentafluorophenyl)borate, (where alkyl is methyl, ethyl, propyl, n-butyl, sec-butyl, or t-butyl).

[0174] The typical activator-to-catalyst ratio, e.g., all NCA activators-to-catalyst ratio is about a 1:1 molar ratio. Alternate preferred ranges include from 0.1:1 to 100:1, alternately from 0.5:1 to 200:1, alternately from 1:1 to 500:1 alternately from 1:1 to 1000:1. A particularly useful range is from 0.5:1 to 10:1, preferably 1:1 to 5:1.

[0175] It is also within the scope of the present disclosure that the catalyst compounds can be combined with combinations of alumoxanes and NCA's (see for example, US 5,153,157; US 5,453,410; EP 0 573 120 B1; WO 1994/007928; and WO 1995/014044 (the disclosures of which are incorporated herein by reference in their entirety) which discuss the use of an alumoxane in combination with an ionizing activator).

Optional Scavengers, Co-Activators, Chain Transfer Agents

[0176] In addition to activator compounds, scavengers or co-activators may be used. A scavenger is a compound that is typically added to facilitate polymerization by scavenging impurities. Some scavengers may also act as activators and may be referred to as co-activators.

- 5 A co-activator, that is not a scavenger, may also be used in conjunction with an activator in order to form an active catalyst. In some embodiments a co-activator can be pre-mixed with the transition metal compound to form an alkylated transition metal compound.

[0177] Co-activators can include alumoxanes such as methylalumoxane, modified alumoxanes such as modified methylalumoxane, and aluminum alkyls such trimethylaluminum, tri-isobutylaluminum, triethylaluminum, and tri-isopropylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum, tri-n-decylaluminum or tri-n-dodecylaluminum. Co-activators are typically used in combination with Lewis acid activators and ionic activators when the pre-catalyst is not a dihydrocarbyl or dihydride complex. Sometimes co-activators are also used as scavengers to deactivate impurities in feed or reactors.

- 15 [0178] Aluminum alkyl or organoaluminum compounds which may be utilized as scavengers or co-activators include, for example, trimethylaluminum, triethylaluminum, triisobutylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum, and dialkyl zinc, such as diethyl zinc.

[0179] Chain transfer agents may be used in the compositions and or processes described herein. Useful chain transfer agents are typically hydrogen, alkylalumoxanes, a compound represented by the formula AlR_3 , ZnR_2 (where each R is, independently, a C_1 - C_8 aliphatic radical, preferably methyl, ethyl, propyl, butyl, penyl, hexyl octyl or an isomer thereof) or a combination thereof, such as diethyl zinc, trimethylaluminum, triisobutylaluminum, trioctylaluminum, or a combination thereof.

25 ***Polymerization Processes***

[0180] For the polymerization processes described herein, the term "continuous" means a system that operates without interruption or cessation. For example a continuous process to produce a polymer would be one where the reactants are continually introduced into one or more reactors and polymer product is continually withdrawn.

- 30 [0181] A solution polymerization means a polymerization process in which the polymer is dissolved in a liquid polymerization medium, such as an inert solvent or monomer(s) or their blends. A solution polymerization is typically homogeneous. A homogeneous polymerization is one where the polymer product is dissolved in the polymerization medium. Such systems are preferably not turbid as described in J. Vladimir Oliveira et al. (2000) *Ind. Eng. Chem. Res.*,

v.29, page 4627.

[0182] A bulk polymerization means a polymerization process in which the monomers and/or comonomers being polymerized are used as a solvent or diluent using little or no inert solvent as a solvent or diluent. A small fraction of inert solvent might be used as a carrier for catalyst and scavenger. A bulk polymerization system contains less than 25 wt% of inert solvent or diluent, preferably less than 10 wt%, preferably less than 1 wt%, preferably 0 wt%.

[0183] In embodiments herein, the invention relates to polymerization processes where monomer (such as propylene), and optionally comonomer, are contacted with a catalyst system comprising an activator and at least one catalyst compound, as described above. The catalyst compound and activator may be combined in any order, and are combined typically prior to contacting with the monomer.

[0184] Monomers useful herein include substituted or unsubstituted C₂ to C₄₀ alpha olefins, preferably C₂ to C₂₀ alpha olefins, preferably C₂ to C₁₂ alpha olefins, preferably ethylene, propylene, butene, pentene, hexene, heptene, octene, nonene, decene, undecene, dodecene and isomers thereof. In a preferred embodiment of the invention, the monomer comprises propylene and an optional comonomers comprising one or more ethylene or C₄ to C₄₀ olefins, preferably C₄ to C₂₀ olefins, or preferably C₆ to C₁₂ olefins. The C₄ to C₄₀ olefin monomers may be linear, branched, or cyclic. The C₄ to C₄₀ cyclic olefins may be strained or unstrained, monocyclic or polycyclic, and may optionally include heteroatoms and/or one or more functional groups. In another preferred embodiment, the monomer comprises ethylene and an optional comonomers comprising one or more C₃ to C₄₀ olefins, preferably C₄ to C₂₀ olefins, or preferably C₆ to C₁₂ olefins. The C₃ to C₄₀ olefin monomers may be linear, branched, or cyclic. The C₃ to C₄₀ cyclic olefins may be strained or unstrained, monocyclic or polycyclic, and may optionally include heteroatoms and/or one or more functional groups.

[0185] Exemplary C₂ to C₄₀ olefin monomers and optional comonomers include ethylene, propylene, butene, pentene, hexene, heptene, octene, nonene, decene, undecene, dodecene, norbornene, cyclopentene, cycloheptene, cyclooctene, cyclododecene, substituted derivatives thereof, and isomers thereof, preferably hexene, heptene, octene, nonene, decene, dodecene, cyclooctene, 5-methylcyclopentene, cyclopentene, norbornene, 5-ethylidene-2-norbornene, and their respective homologs and derivatives.

[0186] In a preferred embodiment one or more dienes are present in the polymer produced herein at up to 10 weight %, preferably at 0.00001 to 1.0 weight %, preferably 0.002 to 0.5 weight %, even more preferably 0.003 to 0.2 weight %, based upon the total weight of the

composition. In some embodiments 500 ppm or less of diene is added to the polymerization, preferably 400 ppm or less, preferably or 300 ppm or less. In other embodiments at least 50 ppm of diene is added to the polymerization, or 100 ppm or more, or 150 ppm or more.

[0187] Preferred diolefin monomers useful in this invention include any hydrocarbon structure, preferably C₅ to C₃₀, having at least two unsaturated bonds, wherein at least two of the unsaturated bonds are readily incorporated into a polymer by either a stereospecific or a non-stereospecific catalyst(s). It is further preferred that the diolefin monomers be selected from non-conjugated diene monomers. More preferably, the diolefin monomers are linear di-vinyl monomers, most preferably those containing from 5 to 30 carbon atoms. Examples of preferred dienes include pentadiene, hexadiene, heptadiene, octadiene, nonadiene, decadiene, undecadiene, dodecadiene, tridecadiene, tetradecadiene, pentadecadiene, hexadecadiene, heptadecadiene, octadecadiene, nonadecadiene, icosadiene, heneicosadiene, docosadiene, tricosadiene, tetracosadiene, pentacosadiene, hexacosadiene, heptacosadiene, octacosadiene, nonacosadiene, triacontadiene, particularly preferred dienes include 1,6-heptadiene, 1,7-octadiene, 1,8-nonadiene, 1,9-decadiene, 1,10-undecadiene, 1,11-dodecadiene, 1,12-tridecadiene, 1,13-tetradecadiene, divinylbenzene, and low molecular weight polybutadienes (M_w less than 1000 g/mol). Preferred cyclic dienes include cyclopentadiene, vinyl norbornene, norbornadiene, and dicyclopentadiene.

[0188] Polymerization processes of this invention can be carried out in any manner known in the art. Any suspension, homogeneous, bulk, solution, slurry, or gas phase polymerization process known in the art can be used. Such processes can be run in a batch, semi-batch, or continuous mode. Homogeneous polymerization processes and slurry processes are preferred. (A homogeneous polymerization process is preferably a process where at least 90 wt% of the product is soluble in the reaction media.) A bulk homogeneous process is particularly preferred. (A bulk process is preferably a process where monomer concentration in all feeds to the reactor is 70 volume % or more.) Alternately, no solvent or diluent is present or added in the reaction medium, (except for the small amounts used as the carrier for the catalyst system or other additives, or amounts typically found with the monomer; e.g., propane in propylene). In another embodiment, the process is a slurry process. As used herein the term "slurry polymerization process" means a polymerization process where a supported catalyst is employed and monomers are polymerized on the supported catalyst particles. At least 95 wt% of polymer products derived from the supported catalyst are in granular form as solid particles (not dissolved in the diluent).

[0189] Suitable diluents/solvents for polymerization include non-coordinating, inert liquids. Examples include straight and branched-chain hydrocarbons, such as isobutane, butane, pentane,

- isopentane, hexanes, isohexane, heptane, octane, dodecane, and mixtures thereof; cyclic and alicyclic hydrocarbons, such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane, and mixtures thereof, such as can be found commercially (Isopar™ fluids); perhalogenated hydrocarbons, such as perfluorinated C₄₋₁₀ alkanes, chlorobenzene, and
- 5 aromatic and alkylsubstituted aromatic compounds, such as benzene, toluene, mesitylene, and xylene. Suitable solvents also include liquid olefins which may act as monomers or comonomers including ethylene, propylene, 1-butene, 1-hexene, 1-pentene, 3-methyl-1-pentene, 4-methyl-1-pentene, 1-octene, 1-decene, and mixtures thereof. In a preferred embodiment, aliphatic hydrocarbon solvents are used as the solvent, such as isobutane, butane, pentane, isopentane,
- 10 hexanes, isohexane, heptane, octane, dodecane, and mixtures thereof; cyclic and alicyclic hydrocarbons, such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane, and mixtures thereof. In another embodiment, the solvent is not aromatic, preferably aromatics are present in the solvent at less than 1 wt%, preferably less than 0.5 wt%, preferably less than 0 wt% based upon the weight of the solvents.
- 15 **[0190]** In a preferred embodiment, the feed concentration of the monomers and comonomers for the polymerization is 60 vol% solvent or less, preferably 40 vol% or less, or preferably 20 vol% or less, based on the total volume of the feedstream. Preferably the polymerization is run in a bulk process.
- [0191]** Preferred polymerizations can be run at any temperature and/or pressure suitable to
- 20 obtain the desired ethylene polymers. Typical temperatures and/or pressures include a temperature in the range of from about 0°C to about 300°C, preferably about 20°C to about 200°C, preferably about 35°C to about 150°C, preferably from about 40°C to about 120°C, preferably from about 45°C to about 80°C; and at a pressure in the range of from about 0.35 MPa to about 10 MPa, preferably from about 0.45 MPa to about 6 MPa, or preferably from about 0.5
- 25 MPa to about 4 MPa.
- [0192]** In a typical polymerization, the run time of the reaction is up to 300 minutes, preferably in the range of from about 5 to 250 minutes, or preferably from about 10 to 120 minutes.
- [0193]** In some embodiments hydrogen is present in the polymerization reactor at a partial
- 30 pressure of 0.001 to 50 psig (0.007 to 345 kPa), preferably from 0.01 to 25 psig (0.07 to 172 kPa), more preferably 0.1 to 10 psig (0.7 to 70 kPa).
- [0194]** In an alternate embodiment, the catalyst activity is at least 10,000 g/mmol/hour, preferably 100,000 or more g/mmol/hour, preferably 500,000 or more g/mmol/hr, preferably 1,000,000 or more g/mmol/hr, preferably 2,000,000 or more g/mmol/hr, preferably 5,000,000 or

more g/mmol/hr. In an alternate embodiment, the conversion of olefin monomer is at least 10%, based upon polymer yield and the weight of the monomer entering the reaction zone, preferably 20% or more, preferably 30% or more, preferably 50% or more, preferably 80% or more.

[0195] In a preferred embodiment, little or no alumoxane is used in the process to produce the polymers. Preferably, alumoxane is present at zero mol%, alternately the alumoxane is present at a molar ratio of aluminum to transition metal less than 500:1, preferably less than 300:1, preferably less than 100:1, preferably less than 1:1.

[0196] In a preferred embodiment, little or no scavenger is used in the process to produce the ethylene polymer. Preferably, scavenger (such as tri alkyl aluminum) is present at zero mol%, alternately the scavenger is present at a molar ratio of scavenger metal to transition metal of less than 100:1, preferably less than 50:1, preferably less than 15:1, preferably less than 10:1.

[0197] In a preferred embodiment, the polymerization: 1) is conducted at temperatures of 0 to 300°C (preferably 25 to 150°C, preferably 40 to 120°C, preferably 45 to 80°C, preferably 60 to 160°C); 2) is conducted at a pressure of atmospheric pressure to 10 MPa (preferably 0.35 to 10 MPa, preferably from 0.45 to 6 MPa, preferably from 0.5 to 4 MPa); 3) is conducted in an aliphatic hydrocarbon solvent (such as isobutane, butane, pentane, isopentane, hexanes, isohexane, heptane, octane, dodecane, and mixtures thereof; cyclic and alicyclic hydrocarbons, such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane, and mixtures thereof; preferably where aromatics are preferably present in the solvent at less than 1 wt%, preferably less than 0.5 wt%, preferably at 0 wt% based upon the weight of the solvents); 4) wherein the catalyst system used in the polymerization comprises less than 0.5 mol%, preferably 0 mol% alumoxane, alternately the alumoxane is present at a molar ratio of aluminum to transition metal less than 500:1, preferably less than 300:1, preferably less than 100:1, preferably less than 1:1; 5) the polymerization preferably occurs in one reaction zone; 6) the catalyst activity is at least 10,000 g/mmol/hr (preferably at least 100,000 g/mmol/hr, preferably at least 200,000 g/mmol/hr, preferably at least 500,000 g/mmol/hr, preferably at least 1,000,000 g/mmol/hr, preferably at least 2,000,000 g/mmol/hr, preferably at least 5,000,000 g/mmol/hr); 7) optionally scavengers (such as trialkyl aluminum compounds) are absent (e.g. present at zero mol%, alternately the scavenger is present at a molar ratio of scavenger metal to transition metal of less than 100:1, preferably less than 50:1, preferably less than 15:1, preferably less than 10:1); and 8) optionally hydrogen is present in the polymerization reactor at a partial pressure of 0.001 to 50 psig (0.007 to 345 kPa) (preferably from 0.01 to 25 psig (0.07 to 172 kPa), more preferably 0.1 to 10 psig (0.7 to 70 kPa)). In a preferred embodiment, the catalyst system used in the polymerization comprises no more than one catalyst compound. A "reaction zone" also referred

to as a "polymerization zone" is a vessel where polymerization takes place, for example a batch reactor. When multiple reactors are used in either series or parallel configuration, each reactor is considered as a separate polymerization zone. For a multi-stage polymerization in both a batch reactor and a continuous reactor, each polymerization stage is considered as a separate
5 polymerization zone. In a preferred embodiment, the polymerization occurs in one reaction zone. Room temperature is 23°C unless otherwise noted.

[0198] Other additives may also be used in the polymerization, as desired, such as one or more scavengers, hydrogen, aluminum alkyls, silanes, or chain transfer agents (such as alkylalumoxanes, a compound represented by the formula AlR_3 or ZnR_2 (where each R is,
10 independently, a C₁-C₈ aliphatic radical, preferably methyl, ethyl, propyl, butyl, penyl, hexyl octyl or an isomer thereof) or a combination thereof, such as diethyl zinc, methylalumoxane, trimethylaluminum, triisobutylaluminum, trioctylaluminum, or a combination thereof).

Polyolefin Products

[0199] This invention also relates to compositions of matter produced by the methods
15 described herein. The processes described herein may be used to produce polymers of olefins or mixtures of olefins. Polymers that may be prepared include polyethylene, polypropylene, homopolymers of C₄-C₂₀ olefins, copolymers of C₄-C₂₀ olefins, copolymers of ethylene with C₃-C₂₀ olefins, copolymers of propylene with C₄-C₂₀ olefins, terpolymers of C₄-C₂₀ olefins, terpolymers of ethylene and propylene with C₄-C₂₀ olefins, and terpolymers of ethylene and
20 propylene with 5-ethylidene-2-norbornene.

[0200] In a preferred embodiment, the process described herein produces propylene homopolymers or propylene copolymers, such as propylene-ethylene and / or propylene-alphaolefin (preferably C₄ to C₂₀) copolymers (such as propylene-hexene copolymers or propylene-octene copolymers) having a Mw/Mn of between 1 to 10 (preferably 2-5, preferably
25 2-4, preferably 2-3).

[0201] In a preferred embodiment, the polymers produced herein are copolymers of ethylene preferably having from 0 to 25 mole% (alternately from 0.5 to 20 mole%, alternately from 1 to 15 mole%, preferably from 3 to 10 mole%) of one or more C₃ to C₂₀ olefin comonomer (preferably C₃ to C₁₂ alpha-olefin, preferably propylene, butene, hexene, octene, decene,
30 dodecene, preferably propylene, butene, hexene, octene), or are copolymers of propylene preferably having from 0 to 25 mole% (alternately from 0.5 to 20 mole%, alternately from 1 to 15 mole%, preferably from 3 to 10 mole%) of one or more of C₂ or C₄ to C₂₀ olefin comonomer (preferably ethylene or C₄ to C₁₂ alpha-olefin, preferably ethylene, butene, hexene, octene, decene, dodecene, preferably ethylene, butene, hexene, octene).

[0202] In a preferred embodiment, the monomer is ethylene and the comonomer is hexene, preferably from 1 to 15 mole% hexene, alternately 1 to 10 mole%.

[0203] Typically, the polymers produced herein have an Mw of 5,000 to 1,000,000 g/mol (preferably 25,000 to 750,000 g/mol, preferably 50,000 to 500,000 g/mol), and/or an Mw/Mn of
5 greater than 1 to 40 (alternately 1.2 to 20, alternately 1.3 to 10, alternately 1.4 to 5, 1.5 to 4, alternately 1.5 to 3).

[0204] In a preferred embodiment the polymer produced herein has a unimodal or multimodal molecular weight distribution as determined by Gel Permeation Chromatography (GPC). By "unimodal" is meant that the GPC trace has one peak or inflection point. By
10 "multimodal" is meant that the GPC trace has at least two peaks or inflection points. An inflection point is that point where the second derivative of the curve changes in sign (e.g., from negative to positive or vice versa).

Blends

[0205] In another embodiment, the polymer (preferably the polyethylene or polypropylene)
15 produced herein is combined with one or more additional polymers prior to being formed into a film, molded part or other article. Other useful polymers include polyethylene, isotactic polypropylene, highly isotactic polypropylene, syndiotactic polypropylene, random copolymer of propylene and ethylene, and/or butene, and/or hexene, polybutene, ethylene vinyl acetate, LDPE, LLDPE, HDPE, ethylene vinyl acetate, ethylene methyl acrylate, copolymers of acrylic
20 acid, polymethylmethacrylate or any other polymers polymerizable by a high-pressure free radical process, polyvinylchloride, polybutene-1, isotactic polybutene, ABS resins, ethylene-propylene rubber (EPR), vulcanized EPR, EPDM, block copolymer, styrenic block copolymers, polyamides, polycarbonates, PET resins, cross linked polyethylene, copolymers of ethylene and vinyl alcohol (EVOH), polymers of aromatic monomers such as polystyrene, poly-1 esters,
25 polyacetal, polyvinylidene fluoride, polyethylene glycols, and/or polyisobutylene.

[0206] In a preferred embodiment, the polymer (preferably the polyethylene or polypropylene) is present in the above blends, at from 10 to 99 wt%, based upon the weight of the polymers in the blend, preferably 20 to 95 wt%, even more preferably at least 30 to 90 wt%, even more preferably at least 40 to 90 wt%, even more preferably at least 50 to 90 wt%, even
30 more preferably at least 60 to 90 wt%, even more preferably at least 70 to 90 wt%.

[0207] The blends described above may be produced by mixing the polymers of the invention with one or more polymers (as described above), by connecting reactors together in series to make reactor blends or by using more than one catalyst in the same reactor to produce multiple species of polymer. The polymers can be mixed together prior to being put into the

extruder or may be mixed in an extruder.

[0208] The blends may be formed using conventional equipment and methods, such as by dry blending the individual components and subsequently melt mixing in a mixer, or by mixing the components together directly in a mixer, such as, for example, a Banbury mixer, a Haake mixer, a Brabender internal mixer, or a single or twin-screw extruder, which may include a compounding extruder and a side-arm extruder used directly downstream of a polymerization process, which may include blending powders or pellets of the resins at the hopper of the film extruder. Additionally, additives may be included in the blend, in one or more components of the blend, and/or in a product formed from the blend, such as a film, as desired. Such additives are well known in the art, and can include, for example: fillers; antioxidants (e.g., hindered phenolics such as IRGANOX™ 1010 or IRGANOX™ 1076 available from Ciba-Geigy); phosphites (e.g., IRGAFOS™ 168 available from Ciba-Geigy); anti-cling additives; tackifiers, such as polybutenes, terpene resins, aliphatic and aromatic hydrocarbon resins, alkali metal and glycerol stearates, and hydrogenated rosins; UV stabilizers; heat stabilizers; anti-blocking agents; release agents; anti-static agents; pigments; colorants; dyes; waxes; silica; fillers; talc; and the like.

[0209] Any of the foregoing polymers and compositions in combination with optional additives (*see, for example*, U.S. Patent Application Publication No. 2016/0060430, paragraphs [0082]-[0093]) may be used in a variety of end-use applications. Such end uses may be produced by methods known in the art. End uses include polymer products and products having specific end-uses. Exemplary end uses are films, film-based products, diaper backsheets, housewrap, wire and cable coating compositions, articles formed by molding techniques, e.g., injection or blow molding, extrusion coating, foaming, casting, and combinations thereof. End uses also include products made from films, e.g., bags, packaging, and personal care films, pouches, medical products, such as for example, medical films and intravenous (IV) bags.

Films

[0210] Specifically, any of the foregoing polymers, such as the foregoing polypropylenes or blends thereof, may be used in a variety of end-use applications. Such applications include, for example, mono- or multi-layer blown, extruded, and/or shrink films. These films may be formed by any number of well-known extrusion or coextrusion techniques, such as a blown bubble film processing technique, wherein the composition can be extruded in a molten state through an annular die and then expanded to form a uni-axial or biaxial orientation melt prior to being cooled to form a tubular, blown film, which can then be axially slit and unfolded to form a flat film. Films may be subsequently unoriented, uniaxially oriented, or biaxially oriented to the same or

different extents. One or more of the layers of the film may be oriented in the transverse and/or longitudinal directions to the same or different extents. The uniaxially orientation can be accomplished using typical cold drawing or hot drawing methods. Biaxial orientation can be accomplished using tenter frame equipment or a double bubble processes and may occur before or after the individual layers are brought together. For example, a polyethylene layer can be extrusion coated or laminated onto an oriented polypropylene layer or the polyethylene and polypropylene can be coextruded together into a film then oriented. Likewise, oriented polypropylene could be laminated to oriented polyethylene or oriented polyethylene could be coated onto polypropylene then optionally the combination could be oriented even further.


Typically the films are oriented in the Machine Direction (MD) at a ratio of up to 15, preferably between 5 and 7, and in the Transverse Direction (TD) at a ratio of up to 15, preferably 7 to 9. However, in another embodiment the film is oriented to the same extent in both the MD and TD directions.

[0211] The films may vary in thickness depending on the intended application; however, films of a thickness from 1 to 50 μm are usually suitable. Films intended for packaging are usually from 10 to 50 μm thick. The thickness of the sealing layer is typically 0.2 to 50 μm . There may be a sealing layer on both the inner and outer surfaces of the film or the sealing layer may be present on only the inner or the outer surface.

[0212] In another embodiment, one or more layers may be modified by corona treatment, electron beam irradiation, gamma irradiation, flame treatment, or microwave. In a preferred embodiment, one or both of the surface layers is modified by corona treatment.

[0213] In another embodiment, this invention relates to:

1. A catalyst compound represented by the Formula (I):



wherein:

M is a group 3, 4, 5, or 6 transition metal or a Lanthanide;

E and E' are each independently O, S, or NR^9 where R^9 is independently hydrogen, a $\text{C}_1\text{-C}_{40}$ hydrocarbyl, a $\text{C}_1\text{-C}_{40}$ substituted hydrocarbyl or a heteroatom-containing group;

Q is group 14, 15, or 16 atom that forms a dative bond to metal M;

- $A^1QA^{1'}$ are part of a heterocyclic Lewis base containing 4 to 40 non-hydrogen atoms that links A^2 to $A^{2'}$ via a 3-atom bridge with Q being the central atom of the 3-atom bridge, A^1 and $A^{1'}$ are independently C, N, or $C(R^{22})$, where R^{22} is selected from hydrogen, C_1 - C_{20} hydrocarbyl, C_1 - C_{20} substituted hydrocarbyl;

$A^3 \text{---} A^2$ is a divalent group containing 2 to 40 non-hydrogen atoms that links A^1 to the E-bonded aryl group via a 2-atom bridge;

$A^{2'} \text{---} A^{3'}$ is a divalent group containing 2 to 40 non-hydrogen atoms that links $A^{1'}$ to the E'-bonded aryl group via a 2-atom bridge;

- L is a Lewis base;

X is an anionic ligand;

n is 1, 2 or 3;

m is 0, 1, or 2;

n+m is not greater than 4;


- each of R^1 , R^2 , R^3 , R^4 , $R^{1'}$, $R^{2'}$, $R^{3'}$, and $R^{4'}$ is independently hydrogen, a C_1 - C_{40} hydrocarbyl, a C_1 - C_{40} substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, and one or more of R^1 and R^2 , R^2 and R^3 , R^3 and R^4 , $R^{1'}$ and $R^{2'}$, $R^{2'}$ and $R^{3'}$, $R^{3'}$ and $R^{4'}$ may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings;

any two L groups may be joined together to form a bidentate Lewis base;

an X group may be joined to an L group to form a monoanionic bidentate group;

any two X groups may be joined together to form a dianionic ligand group.

2. The catalyst compound of formula 1 where the catalyst compound represented by the Formula (II):



wherein:

M is a group 3, 4, 5, or 6 transition metal or a Lanthanide;

E and E' are each independently O, S, or NR⁹, where R⁹ is independently hydrogen, a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl, or a heteroatom-containing group;

5 each L is independently a Lewis base;

each X is independently an anionic ligand;

n is 1, 2 or 3;

m is 0, 1, or 2;

n+m is not greater than 4;

10 each of R¹, R², R³, R⁴, R^{1'}, R^{2'}, R^{3'}, and R^{4'} is independently hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more of R¹ and R², R² and R³, R³ and R⁴, R^{1'} and R^{2'}, R^{2'} and R^{3'}, R^{3'} and R^{4'} may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and
15 where substitutions on the ring can join to form additional rings; any two L groups may be joined together to form a bidentate Lewis base;

an X group may be joined to an L group to form a monoanionic bidentate group;

any two X groups may be joined together to form a dianionic ligand group;

20 each of R⁵, R⁶, R⁷, R⁸, R^{5'}, R^{6'}, R^{7'}, R^{8'}, R¹⁰, R¹¹, and R¹² is independently hydrogen, a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more of R⁵ and R⁶, R⁶ and R⁷, R⁷ and R⁸, R^{5'} and R^{6'}, R^{6'} and R^{7'}, R^{7'} and R^{8'}, R¹⁰ and R¹¹, or R¹¹ and R¹² may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form
25 additional rings.

3. The catalyst compound of paragraph 1 or 2 wherein the M is Hf, Zr or Ti.


4. The catalyst compound of paragraph 1, 2, or 3 wherein E and E' are each O.

5. The catalyst compound of paragraph 1, 2, 3, or 4 wherein R¹ and R^{1'} is independently a C₄-C₄₀ tertiary hydrocarbyl group.

30 6. The catalyst compound of paragraph 1, 2, 3, 4, or 5 wherein R¹ and R^{1'} is independently a C₄-C₄₀ cyclic tertiary hydrocarbyl group.


7. The catalyst compound of paragraph 1, 2, 3, 4, 5, or 6 wherein R¹ and R^{1'} is independently a C₄-C₄₀ polycyclic tertiary hydrocarbyl group.

8. The catalyst compound any of paragraphs 1 to 7 wherein each X is, independently, selected from the group consisting of substituted or unsubstituted hydrocarbyl radicals having from 1 to 20 carbon atoms, hydrides, amides, alkoxides, sulfides, phosphides, halides, and a combination thereof, (two X's may form a part of a fused ring or a ring system).
- 5 9. The catalyst compound any of paragraphs 1 to 8 wherein each L is, independently, selected from the group consisting of: ethers, thioethers, amines, phosphines, ethyl ether, tetrahydrofuran, dimethylsulfide, triethylamine, pyridine, alkenes, alkynes, alenes, and carbenes and a combinations thereof, optionally two or more L's may form a part of a fused ring or a ring system).
- 10 10. The catalyst compound of paragraph 1, wherein M is Zr or Hf, Q is nitrogen, both A¹ and A^{1'} are carbon, both E and E' are oxygen, and both R¹ and R^{1'} are C₄-C₂₀ cyclic tertiary alkyls.
11. The catalyst compound of paragraph 1, wherein M is Zr or Hf, Q is nitrogen, both A¹ and A^{1'} are carbon, both E and E' are oxygen, and both R¹ and R^{1'} are adamantan-1-yl or substituted adamantan-1-yl.
- 15 12. The catalyst compound of paragraph 1, wherein M is Zr or Hf, Q is nitrogen, both A¹ and A^{1'} are carbon, both E and E' are oxygen, and both R¹ and R^{1'} are C₆-C₂₀ aryls.
13. The catalyst compound of paragraph 1, wherein Q is nitrogen, A¹ and A^{1'} are both carbon, both R¹ and R^{1'} are hydrogen, both E and E' are NR⁹, where R⁹ is selected from a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl, or a heteroatom-containing group.
- 20 14. The catalyst compound of paragraph 1, wherein Q is carbon, A¹ and A^{1'} are both nitrogen, and both E and E' are oxygen.
15. The catalyst compound of paragraph 1, wherein Q is carbon, A¹ is nitrogen, A^{1'} is C(R²²), and both E and E' are oxygen, where R²² is selected from hydrogen, C₁-C₂₀ hydrocarbyl, C₁-C₂₀ substituted hydrocarbyl.
- 25 16. The catalyst compound of paragraph 1, wherein the heterocyclic Lewis base is selected from the groups represented by the following formulas:




where each R^{23} is independently selected from hydrogen, C_1 - C_{20} alkyls, and C_1 - C_{20} substituted alkyls.


17. The catalyst compound of paragraph 2, wherein M is Zr or Hf, both E and E' are oxygen, and both R^1 and $R^{1'}$ are C_4 - C_{20} cyclic tertiary alkyls.
18. The catalyst compound of paragraph 2, wherein M is Zr or Hf, both E and E' are oxygen, and both R^1 and $R^{1'}$ are adamantan-1-yl or substituted adamantan-1-yl.
19. The catalyst compound of paragraph 2, wherein M is Zr or Hf, both E and E' are oxygen, and each of R^1 , $R^{1'}$, R^3 and $R^{3'}$ are adamantan-1-yl or substituted adamantan-1-yl.
20. The catalyst compound of paragraph 2, wherein M is Zr or Hf, both E and E' are oxygen, both R^1 and $R^{1'}$ are C_4 - C_{20} cyclic tertiary alkyls, and both R^7 and $R^{7'}$ are C_1 - C_{20} alkyls.
21. The catalyst compound of paragraph 2, wherein M is Zr or Hf, both E and E' are O, both R^1 and $R^{1'}$ are C_4 - C_{20} cyclic tertiary alkyls, and both R^7 and $R^{7'}$ are C_1 - C_{20} alkyls.
22. The catalyst compound of paragraph 2, wherein M is Zr or Hf, both E and E' are O, both R^1 and $R^{1'}$ are C_4 - C_{20} cyclic tertiary alkyls, and both R^7 and $R^{7'}$ are C_1 - C_3 alkyls.
23. The catalyst compound of paragraph 1 wherein the catalyst compound is represented by one or more of the following formulas:




Complex 1




Complex 2




Complex 3




Complex 4




Complex 5




Complex 6




Complex 7




Complex 8




Complex 9




Complex 10




Complex 11




Complex 12




Complex 13




Complex 14




Complex 15




Complex 16




Complex 17




Complex 18




Complex 19




Complex 20




Complex 21




Complex 22




Complex 23




Complex 24




Complex 25




Complex 26




Complex 27




Complex 29



Complex 30




Complex 31



Complex 32

24. A catalyst system comprising activator and the catalyst compound of any of paragraphs 1 to 23.
25. The catalyst system of paragraph 24, wherein the activator comprises an alumoxane or a non-coordinating anion.
26. The catalyst system of paragraph 24, wherein the activator is soluble in non-aromatic-hydrocarbon solvent.
27. The catalyst system of paragraph 24, wherein the catalyst system is free of aromatic solvent.

28. The catalyst system of paragraph 24, wherein the activator is represented by the formula:




wherein Z is (L-H) or a reducible Lewis Acid, L is an neutral Lewis base; H is hydrogen; (L-H)⁺ is a Bronsted acid; A^{d-} is a non-coordinating anion having the charge d-; and d is an integer from 1 to 3.

29. The catalyst system of paragraph 24, wherein the activator is represented by the formula:












wherein: E is nitrogen or phosphorous; d is 1, 2 or 3; k is 1, 2, or 3; n is 1, 2, 3, 4, 5, or 6; n - k = d; R^{1'}, R^{2'}, and R^{3'} are independently a C₁ to C₅₀ hydrocarbyl group optionally substituted with one or more alkoxy groups, silyl groups, a halogen atoms, or halogen containing groups, wherein R^{1'}, R^{2'}, and R^{3'} together comprise 15 or more carbon atoms; Mt is an element selected from group 13 of the Periodic Table of the Elements; and each Q is independently a hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, or halosubstituted-hydrocarbyl radical.

30. The catalyst system of paragraph 24, wherein the activator is represented by the formula:



wherein A^{d-} is a non-coordinating anion having the charge d-; and d is an integer from 1 to 3 and (Z)_d⁺ is represented by one or more of:

10		11		12	
13		14		15	
16		17		18	

19		20		21	
22		23		24	
25		26		27	
29		28		30	
31		32		33	
34		35		36	

31. The catalyst system of paragraph 24, wherein the activator is one or more of:
- N-methyl-4-nonadecyl-N-octadecylbenzenaminium tetrakis(pentafluorophenyl)borate,
 - N-methyl-4-nonadecyl-N-octadecylbenzenaminium tetrakis(perfluoronaphthalenyl)borate,
 - 5 dioctadecylmethyllummonium tetrakis(pentafluorophenyl)borate,
 - dioctadecylmethyllummonium tetrakis(perfluoronaphthalenyl)borate,
 - N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate,
 - triphenylcarbenium tetrakis(pentafluorophenyl)borate,
 - trimethyllummonium tetrakis(perfluoronaphthalenyl)borate,
 - 10 triethyllummonium tetrakis(perfluoronaphthalenyl)borate,
 - tripropyllummonium tetrakis(perfluoronaphthalenyl)borate,
 - tri(n-butyl)ammonium tetrakis(perfluoronaphthalenyl)borate,

- tri(t-butyl)ammonium tetrakis(perfluoronaphthalenyl)borate,
 N,N-dimethylanilinium tetrakis(perfluoronaphthalenyl)borate,
 N,N-diethylanilinium tetrakis(perfluoronaphthalenyl)borate,
 N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(perfluoronaphthalenyl)borate,
- 5 tropillium tetrakis(perfluoronaphthalenyl)borate,
 triphenylcarbenium tetrakis(perfluoronaphthalenyl)borate,
 triphenylphosphonium tetrakis(perfluoronaphthalenyl)borate,
 triethylsilylium tetrakis(perfluoronaphthalenyl)borate,
 benzene(diazonium) tetrakis(perfluoronaphthalenyl)borate,
- 10 trimethylammonium tetrakis(perfluorobiphenyl)borate,
 triethylammonium tetrakis(perfluorobiphenyl)borate,
 tripropylammonium tetrakis(perfluorobiphenyl)borate,
 tri(n-butyl)ammonium tetrakis(perfluorobiphenyl)borate,
 tri(t-butyl)ammonium tetrakis(perfluorobiphenyl)borate,
- 15 N,N-dimethylanilinium tetrakis(perfluorobiphenyl)borate,
 N,N-diethylanilinium tetrakis(perfluorobiphenyl)borate,
 N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(perfluorobiphenyl)borate,
 tropillium tetrakis(perfluorobiphenyl)borate,
 triphenylcarbenium tetrakis(perfluorobiphenyl)borate,
- 20 triphenylphosphonium tetrakis(perfluorobiphenyl)borate,
 triethylsilylium tetrakis(perfluorobiphenyl)borate,
 benzene(diazonium) tetrakis(perfluorobiphenyl)borate,
 [4-t-butyl-PhNMe₂H][(C₆F₃(C₆F₅)₂)₄B],
 trimethylammonium tetraphenylborate,
- 25 triethylammonium tetraphenylborate,
 tripropylammonium tetraphenylborate,
 tri(n-butyl)ammonium tetraphenylborate,
 tri(t-butyl)ammonium tetraphenylborate,
 N,N-dimethylanilinium tetraphenylborate,
- 30 N,N-diethylanilinium tetraphenylborate,
 N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,
 tropillium tetraphenylborate,
 triphenylcarbenium tetraphenylborate,
 triphenylphosphonium tetraphenylborate,

- triethylsilylium tetraphenylborate,
benzene(diazonium)tetraphenylborate,
trimethylammonium tetrakis(pentafluorophenyl)borate,
triethylammonium tetrakis(pentafluorophenyl)borate,
5 tripropylammonium tetrakis(pentafluorophenyl)borate,
tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl)borate,
N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate,
N,N-diethylanilinium tetrakis(pentafluorophenyl)borate,
10 N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl)borate,
tropillium tetrakis(pentafluorophenyl)borate,
triphenylcarbenium tetrakis(pentafluorophenyl)borate,
triphenylphosphonium tetrakis(pentafluorophenyl)borate,
triethylsilylium tetrakis(pentafluorophenyl)borate,
15 benzene(diazonium) tetrakis(pentafluorophenyl)borate,
trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl)borate,
20 dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
tropillium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
25 triphenylcarbenium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
triphenylphosphonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
triethylsilylium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
benzene(diazonium) tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
trimethylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
30 triethylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
tripropylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
tri(n-butyl)ammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
tri(t-butyl)ammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
N,N-dimethylanilinium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,

- N,N-diethylanilinium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 tropillium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 5 triphenylphosphonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 triethylsilylium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 benzene(diazonium) tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 di-(i-propyl)ammonium tetrakis(pentafluorophenyl)borate,
 dicyclohexylammonium tetrakis(pentafluorophenyl)borate,
 10 tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl)borate,
 tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl)borate,
 triphenylcarbenium tetrakis(perfluorophenyl)borate,
 1-(4-(tris(pentafluorophenyl)borate)-2,3,5,6-tetrafluorophenyl)pyrrolidinium,
 tetrakis(pentafluorophenyl)borate,
 15 4-(tris(pentafluorophenyl)borate)-2,3,5,6-tetrafluoropyridine, and
 triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate).

32. A process to polymerize olefins comprising contacting one or more olefins with the catalyst system of any of paragraphs 23 to 31.

33. The process of paragraph 32 wherein the process occurs at a temperature of from about
 20 0°C to about 300°C, at a pressure in the range of from about 0.35 MPa to about 10 MPa, and at a time up to 300 minutes.


34. The process of paragraph 32 further comprising obtaining polymer.

35. The process of paragraph 32 wherein the olefins comprise one or more substituted or unsubstituted C₂ to C₄₀ alpha olefins.


25 **Experimental**

[0214] Shown in Scheme 3 are drawings of catalyst complexes **1-32**. Complexes **26** and **27** were prepared as described in concurrently filed US Patent Application Serial No. _____, entitled "*Lewis Base Catalysts and Methods Thereof*" (attorney docket number 2019EM043) which claims priority to and the benefit of 62/804,372, filed February 12, 2019. Complex **28**
 30 (comparative) was prepared as described by Golisz et al. (2009) *Macromolecules*, v.42, pp. 8751-8762 and is a comparative complex. Complexes **31** and **32** were prepared using procedures analogous to that described for complex **29**. 2-(Adamantan-1-yl)-4-(tert-butyl)phenol was prepared from 4-tert-butylphenol (Merck) and adamantanol-1 (Aldrich) as described in *Organic Letters* **2015**, v.17, pp. 2242-2245.


Scheme 3




Scheme 3 (continued)




Scheme 3 (continued)




Complex 21




Complex 22




Complex 23




Complex 24





Complex 25




Complex 26



Complex 27



Complex 28
comparative

Complex 29




Complex 30

Scheme 3 (continued)

**[0215] 2-(Adamantan-1-yl)-6-bromo-4-(tert-butyl)phenol**

- 5 To a solution of 57.6 g (203 mmol) of 2-(adamantan-1-yl)-4-(tert-butyl)phenol in 400 ml of chloroform a solution of 10.4 ml (203 mmol) of bromine in 200 ml of chloroform was added dropwise for 30 minutes at room temperature. The resulting mixture was diluted with 400 ml of water. The obtained mixture was extracted with dichloromethane (3 x 100 ml), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. Yield 71.6 g (97%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.32 (d, J = 2.3 Hz, 1 H), 7.19 (d, J = 2.3 Hz, 1 H), 5.65 (s, 1 H), 2.18 - 2.03 (m, 9 H), 1.78 (m, 6 H), 1.29 (s, 9 H). ¹³C NMR (CDCl₃, 100 MHz): δ 148.07, 143.75, 137.00, 126.04, 123.62, 112.11, 40.24, 37.67, 37.01, 34.46, 31.47, 29.03.
- 10


[0216] (1-(3-Bromo-5-(tert-butyl)-2-(methoxymethoxy)phenyl)adamantine

15

- To a solution of 71.6 g (197 mmol) of 2-(adamantan-1-yl)-6-bromo-4-(tert-butyl)phenol in 1,000 ml of THF 8.28 g (207 mmol, 60% wt. in mineral oil) of sodium hydride was added portionwise at room temperature. To the resulting suspension 16.5 ml (217 mmol) of methoxymethyl chloride was added dropwise for 10 minutes at room temperature. The obtained mixture was stirred overnight, then poured into 1,000 ml of water. The obtained mixture was extracted with dichloromethane (3 x 300 ml), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄ and then evaporated to dryness. Yield 80.3 g (~quant.) of a white
- 20


solid. ^1H NMR (CDCl_3 , 400 MHz): δ 7.39 (d, $J = 2.4$ Hz, 1 H), 7.27 (d, $J = 2.4$ Hz, 1 H), 5.23 (s, 2 H), 3.71 (s, 3 H), 2.20 - 2.04 (m, 9 H), 1.82 - 1.74 (m, 6 H), 1.29 (s, 9 H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 150.88, 147.47, 144.42, 128.46, 123.72, 117.46, 99.53, 57.74, 41.31, 38.05, 36.85, 34.58, 31.30, 29.08.

5 [0217] **2-(3-Adamantan-1-yl)-5-(*tert*-butyl)-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane**



To a solution of 22.5 g (55.0 mmol) of (1-(3-bromo-5-(*tert*-butyl)-2-(methoxymethoxy)phenyl)adamantine in 300 ml of dry THF 23.2 ml (57.9 mmol, 2.5 M) of
 10 $n\text{BuLi}$ in hexanes was added dropwise for 20 minutes at -80°C . The reaction mixture was stirred at this temperature for 1 hour followed by addition of 14.5 ml (71.7 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 300 ml of water. The obtained mixture was extracted with dichloromethane (3 x 300 ml), the combined organic extract was dried over Na_2SO_4 , and
 15 then evaporated to dryness. Yield 25.0 g (~quant.) of a colorless viscous oil. ^1H NMR (CDCl_3 , 400 MHz): δ 7.54 (d, $J = 2.5$ Hz, 1 H), 7.43 (d, $J = 2.6$ Hz, 1 H), 5.18 (s, 2 H), 3.60 (s, 3 H), 2.24 - 2.13 (m, 6 H), 2.09 (br. s., 3 H), 1.85 - 1.75 (m, 6 H), 1.37 (s, 12 H), 1.33 (s, 9 H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 159.64, 144.48, 140.55, 130.58, 127.47, 100.81, 83.48, 57.63, 41.24, 37.29, 37.05, 34.40, 31.50, 29.16, 24.79.


20 [0218] **1-(2'-Bromo-5-(*tert*-butyl)-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine**



To a solution of 25.0 g (55.0 mmol) of 2-(3-adamantan-1-yl)-5-(*tert*-butyl)-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 200 ml of dioxane 15.6 g
 25 (55.0 mmol) of 2-bromiodobenzene, 19.0 g (137 mmol) of potassium carbonate, and 100 ml of water were subsequently added. The mixture obtained was purged with argon for 10 min


followed by addition of 3.20 g (2.75 mmol) of Pd(PPh₃)₄. Thus obtained mixture was stirred for 12 hours at 100°C, then cooled to room temperature and diluted with 100 ml of water. The obtained mixture was extracted with dichloromethane (3 x 100 ml), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 um, eluent: hexane-dichloromethane = 10:1, vol.). Yield 23.5 g (88%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.68 (dd, J = 1.0, 8.0 Hz, 1 H), 7.42 (dd, J = 1.7, 7.6 Hz, 1 H), 7.37 - 7.32 (m, 2 H), 7.20 (dt, J = 1.8, 7.7 Hz, 1 H), 7.08 (d, J = 2.5 Hz, 1 H), 4.53 (d, J = 4.6 Hz, 1 H), 4.40 (d, J = 4.6 Hz, 1 H), 3.20 (s, 3 H), 2.23 - 2.14 (m, 6 H), 2.10 (br. s., 3 H), 1.86 - 1.70 (m, 6 H), 1.33 (s, 9 H). ¹³C NMR (CDCl₃, 100 MHz): δ 151.28, 145.09, 142.09, 141.47, 133.90, 132.93, 132.41, 128.55, 127.06, 126.81, 124.18, 123.87, 98.83, 57.07, 41.31, 37.55, 37.01, 34.60, 31.49, 29.17.

[0219] 2-(3'-(Adamantan-1-yl)-5'-(*tert*-butyl)-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane




To a solution of 30.0 g (62.1 mmol) of 1-(2'-bromo-5-(*tert*-butyl)-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine in 500 ml of dry THF 25.6 ml (63.9 mmol, 2.5 M) of ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred at this temperature for 1 hour followed by addition of 16.5 ml (80.7 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 300 ml of water. The obtained mixture was extracted with dichloromethane (3 x 300 ml), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. Yield 32.9 g (~quant.) of a colorless glassy solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.75 (d, J = 7.3 Hz, 1 H), 7.44 - 7.36 (m, 1 H), 7.36 - 7.30 (m, 2 H), 7.30 - 7.26 (m, 1 H), 6.96 (d, J = 2.4 Hz, 1 H), 4.53 (d, J = 4.7 Hz, 1 H), 4.37 (d, J = 4.7 Hz, 1 H), 3.22 (s, 3 H), 2.26 - 2.14 (m, 6 H), 2.09 (br. s., 3 H), 1.85 - 1.71 (m, 6 H), 1.30 (s, 9 H), 1.15 (s, 6 H), 1.10 (s, 6 H). ¹³C NMR (CDCl₃, 100 MHz): δ 151.35, 146.48, 144.32, 141.26, 136.15, 134.38, 130.44, 129.78, 126.75, 126.04, 123.13, 98.60, 83.32, 57.08, 41.50, 37.51, 37.09, 34.49, 31.57, 29.26, 24.92, 24.21.

[0220] 2',2'''-(Pyridine-2,6-diyl)bis(3-adamantan-1-yl)-5-(*tert*-butyl)-[1,1'-biphenyl]-2-ol




- To a solution of 32.9 g (62.0 mmol) of 2-(3'-(adamantan-1-yl)-5'-(*tert*-butyl)-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 140 ml of dioxane 7.35 g (31.0 mmol) of 2,6-dibromopyridine, 50.5 g (155 mmol) of cesium carbonate and 70 ml of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 3.50 g (3.10 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature and diluted with 50 ml of water. The obtained mixture was extracted with dichloromethane (3 x 50 ml), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 300 ml of THF, 300 ml of methanol, and 21 ml of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 500 ml of water. The obtained mixture was extracted with dichloromethane (3 x 350 ml), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). The obtained glassy solid was triturated with 70 ml of n-pentane, the precipitate obtained was filtered off, washed with 2 x 20 ml of n-pentane, and dried in vacuo. Yield 21.5 g (87%) of a mixture of two isomers as a white powder. ¹H NMR (CDCl₃, 400 MHz): δ 8.10 + 6.59 (2s, 2H), 7.53 – 7.38 (m, 10H), 7.09 + 7.08 (2d, J = 2.4 Hz, 2H), 7.04 + 6.97 (2d, J = 7.8 Hz, 2H), 6.95 + 6.54 (2d, J = 2.4 Hz), 2.03 – 1.79 (m, 18H), 1.74 – 1.59 (m, 12H), 1.16 + 1.01 (2s, 18H).
- ¹³C NMR (CDCl₃, 100 MHz, minor isomer shifts labeled with *): δ 157.86, 157.72*, 150.01, 149.23*, 141.82*, 141.77, 139.65*, 139.42, 137.92, 137.43, 137.32*, 136.80, 136.67*, 136.29*, 131.98*, 131.72, 130.81, 130.37*, 129.80, 129.09*, 128.91, 128.81*, 127.82*, 127.67, 126.40, 125.65*, 122.99*, 122.78, 122.47, 122.07*, 40.48, 40.37*, 37.04, 36.89*, 34.19*, 34.01, 31.47, 29.12, 29.07*.
- [0221] Dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-adamantan-1-yl)-5-(*tert*-butyl)-[1,1'-biphenyl]-2-olate] (Complex 5)**




To a suspension of 3.22 g (10.05 mmol) of hafnium tetrachloride (<0.05% Zr) in 250 ml of dry toluene 14.6 ml (42.2 mmol, 2.9 M) of MeMgBr in diethyl ether was added in one portion via syringe at 0°C. The resulting suspension was stirred for 1 min, and 8.00 g (10.05 mmol) of 2',2'''-(pyridine-2,6-diyl)bis(3-adamantan-1-yl)-5-(*tert*-butyl)-[1,1'-biphenyl]-2-ol) was added portionwise for 1 minute. The reaction mixture was stirred for 36 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 100 ml of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 50 ml of n-hexane, the obtained precipitate was filtered off (G3), washed with 20 ml of n-hexane (2 x 20 ml), and then dried in vacuo. Yield 6.66 g (61%, ~1:1 solvate with n-hexane) of a light-beige solid. Anal. Calc. for C₅₉H₆₉HfNO₂×1.0(C₆H₁₄): C, 71.70; H, 7.68; N, 1.29. Found: C 71.95; H, 7.83; N 1.18. ¹H NMR (C₆D₆, 400 MHz): δ 7.58 (d, J = 2.6 Hz, 2 H), 7.22 - 7.17 (m, 2 H), 7.14 - 7.08 (m, 4 H), 7.07 (d, J = 2.5 Hz, 2 H), 7.00 - 6.96 (m, 2 H), 6.48 - 6.33 (m, 3 H), 2.62 - 2.51 (m, 6H), 2.47 - 2.35 (m, 6H), 2.19 (br.s, 6H), 2.06 - 1.95 (m, 6H), 1.92 - 1.78 (m, 6H), 1.34 (s, 18 H), -0.12 (s, 6 H). ¹³C NMR (C₆D₆, 100 MHz): δ 159.74, 157.86, 143.93, 140.49, 139.57, 138.58, 133.87, 133.00, 132.61, 131.60, 131.44, 127.98, 125.71, 124.99, 124.73, 51.09, 41.95, 38.49, 37.86, 34.79, 32.35, 30.03.

[0222] Dimethylzirconium[2',2'''-(pyridine-2,6-diyl)bis(3-adamantan-1-yl)-5-(*tert*-butyl)-[1,1'-biphenyl]-2-olate] (Complex 6)




To a suspension of 2.92 g (12.56 mmol) of zirconium tetrachloride in 300 ml of dry toluene 18.2 ml (52.7 mmol, 2.9 M) of MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 10.00 g (12.56 mmol) of 2',2'''-(pyridine-2,6-diyl)bis(3-adamantan-1-yl)-5-(*tert*-butyl)-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The

reaction mixture was stirred for 2 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 100 ml of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 50 ml of n-hexane, the obtained precipitate was filtered off (G3), washed with n-hexane (2 x 20 ml), and then dried in vacuo. Yield 8.95 g (74%, ~1:0.5 solvate with n-hexane) of a beige solid. Anal. Calc. for $C_{59}H_{69}ZrNO_2 \times 0.5(C_6H_{14})$: C, 77.69; H, 7.99; N, 1.46. Found: C 77.90; H, 8.15; N 1.36. 1H NMR (C_6D_6 , 400 MHz): δ 7.56 (d, J = 2.6 Hz, 2 H), 7.20 - 7.17 (m, 2 H), 7.14 - 7.07 (m, 4 H), 7.07 (d, J = 2.5 Hz, 2 H), 6.98 - 6.94 (m, 2 H), 6.52 - 6.34 (m, 3 H), 2.65 - 2.51 (m, 6H), 2.49 - 2.36 (m, 6H), 2.19 (br.s., 6H), 2.07 - 1.93 (m, 6H), 1.92 - 1.78 (m, 6H), 1.34 (s, 18 H), 0.09 (s, 6 H). ^{13}C NMR (C_6D_6 , 100 MHz): δ 159.20, 158.22, 143.79, 140.60, 139.55, 138.05, 133.77, 133.38, 133.04, 131.49, 131.32, 127.94, 125.78, 124.65, 124.52, 42.87, 41.99, 38.58, 37.86, 34.82, 32.34, 30.04.

[0223] 1-adamantanol


To a stirring solution of 1-bromoadamantane (5.00g, 23.242mmol) in dimethylformamide (25mL) was added hydrochloric acid (8.7mL of 0.67M HCl) followed by water (15mL). The mixture was brought to 105°C and stirred for 1 hour. After cooling to room temperature, water (150mL) was added and the resulting precipitate was collected via vacuum filtration. The solid was taken up in dichloromethane (200mL) and washed with water (3x100mL). The organic layers were dried ($MgSO_4$), filtered and concentrated under vacuum giving 3.512g (23.069mmol, 99% yield).

[0224] 2,4-di(adamant-1-yl)phenol

To a mixture of phenol (2.00g, 21.252mmol) and 1-adamantanol (6.794g, 44.629mmol, 2.10eq) in dichloromethane (20mL) was added concentrated sulfuric acid (2.5mL), dropwise (over 10 minutes) at room temperature. This was stirred overnight at room temperature. Water (15mL) was added to the reaction mixture and the pH was brought to 9-10 (2M aq. NaOH). Organics were extracted with dichloromethane (3x20mL), washed with brine, dried ($MgSO_4$), filtered and


concentrated under vacuum. The residue was purified via column chromatography (5-10% ethyl acetate/hexane) giving 1.29g (17% yield) of white solid.

[0225] 1,1'-(4-(methoxymethoxy)-1,3-phenylene)bis(adamantane)




- 5 To a mixture of 2,4-di(adamantyl)phenol (1.29g, 3.558mmol) in tetrahydrofuran (3mL) was slowly added sodium hydride, 60% in mineral oil (0.185g, 4.625mmol, 1.30eq). This was stirred for 30 minutes at room temperature at which point chloromethyl methyl ether (0.459mL, 6.049mmol, 1.70eq) was added incrementally. The reaction was allowed to stir at room temperature overnight. The reaction mixture was quenched with water (20mL) and the pH was
- 10 adjusted to 8-10 using potassium hydroxide. The product was extracted with diethyl ether (3x30mL), dried (MgSO₄), filtered and concentrated in vacuo giving 1.330g (3.275mmol, 92% yield).

[0226] (3,5-diadamantan-1-yl)-2-(methoxymethoxy)phenyl)lithium · (1,2-dimethoxyethane)




- 15 Pentane (20 mL) was added to 1,1'-(4-(methoxymethoxy)-1,3-phenylene)bis(adamantane) (1.38 g, 3.40 mmol) to form a solution. A 1.6 M hexane solution of BuLi (2.13 mL, 3.40 mmol) was added dropwise. 1,2-Dimethoxyethane (DME) was then added dropwise. Within a couple of minutes the yellow solution became murky, then precipitate began to form. The mixture was allowed to stir for 1.5 hours then the precipitate was isolated on a fritted disk, washed with
- 20 pentane (3 x 15 mL), and dried under reduced pressure. Product was isolated as an off-white solid. Yield: 1.15 g, 67.2%.

[0227] 1,1'-(2'-bromo-2-(methoxymethoxy)-[1,1'-biphenyl]-3,5-diyl)bis(adamantane)



Toluene (20 mL) was added to (3,5-diadamantan-1-yl)-2-(methoxymethoxy)phenyl lithium · (1,2-dimethoxyethane) (1.15 g, 2.29 mmol) to form a suspension. A toluene solution (10 mL) of 1-bromo-2-chlorobenzene (0.482 g, 2.52 mmol) was added dropwise over 1 hour to form a cloudy solution. The mixture was stirred for an additional hour then the volatiles were removed under reduced pressure. The residue was extracted with CH₂Cl₂ (8 mL) and filtered through Celite 503 on a Teflon filter. The volatiles were evaporated and pentane (3 mL) was added to the residue. The mixture was cooled to -20°C overnight. Nothing crystallized so the volatiles were evaporated and the residue was dried under reduced pressure at 60°C. Yield: 1.32 g, 98.9%.

[0228] 2',2'''-(pyridine-2,6-diyl)bis((3,5-diadamantan-1-yl)-[1,1'-biphenyl]-2-ol)




Tetrahydrofuran (15 mL) was added to 1,1'-(2'-bromo-2-(methoxymethoxy)-[1,1'-biphenyl]-3,5-diyl)bis(adamantane) (1.32 g, 2.26 mmol) to form a solution. The mixture was cooled to -45°C and a 1.6 M solution of BuLi in hexanes (1.46 mL, 2.33 mmol) was added dropwise over a minute. The mixture was allowed to slowly warm to -25°C over 45 minutes. Solid ZnCl₂ (0.216 g, 1.58 mmol) was added to the clear solution. The mixture was allowed to warm slowly to ambient temperature over 30 minutes. After 30 minutes at ambient temperature 2,6-dibromopyridine (0.260 g, 1.10 mmol) and Pd(P(tBu)₃)₂ (0.023 g, 0.045 mmol) were added to the clear colorless solution. The mixture was heated overnight on a metal block kept at 65°C. After stirring overnight the volatiles were evaporated with a rotary evaporator. To the residue were added methanol (20 mL), thf (20 mL), and concentrated HCl (1 mL). The mixture was heated to 60°C for 5 hours. The volatiles were then evaporated with a rotary evaporator and the residue was extracted with CH₂Cl₂ (60 mL). The organics were washed with water (3 x 50 mL),

and dilute NaHCO_3 to adjust pH to 7 (1 x 50 mL), then dried with brine (40 mL), and over MgSO_4 . Filtration and removal of the volatiles afforded 1.2 g of crude product. Purified on silica gel by column chromatography using 2-8% EtOAc in isohexane. Evaporation of the isohexane-EtOAc afforded a white residue that contained some material that was insoluble in CH_2Cl_2 . The solid was extracted with benzene (10 mL), filtered, and evaporated. The residue was dried at 60°C under reduced pressure to afford a foamy solid. Yield: 0.322 g, 30.8%.

[0229] Dibenzylzirconium[2',2'''-(pyridine-2,6-diyl)bis(3,5-diadamantan-1-yl)-[1,1'-biphenyl]-2-olate] (Complex 22). Benzene (15 mL) was added to 2',2'''-(pyridine-2,6-diyl)bis((3,5-diadamantan-1-yl)-[1,1'-biphenyl]-2-ol) (0.315 g, 0.331 mmol) to form a solution. ZrBn_4 (0.151 g, 0.331 mmol) and benzene (2 mL) were added. The mixture was shaken to form a yellow-orange solution. After 30 minutes the mixture was filtered and evaporated to 1 mL. Hexane (3 mL) was added to form a murky mixture. The volatiles were evaporated to dryness. The yellow-orange solid was washed thoroughly with pentane (5 mL). The pentane extract was filtered and cooled to -20°C for a couple hours. Some yellow solid was isolated from the pentane solution. The sample that had been washed with pentane was combined with methylcyclohexane (10 mL) and the mixture was heated to near boiling for a few minutes. Some crystalline solid separated from the orange solution. The mixture was allowed to sit at ambient temperature for 2 hours, then the colorless solid was isolated and dried under reduced pressure. HNMR spectroscopy indicated that the product cocrystallized with 1 equiv of methylcyclohexane. Yield: 0.092 g, 21%.


[0230] 1-(3-Bromo-2-(methoxymethoxy)-5-methylphenyl)adamantine



To a solution of 21.3 g (66.4 mmol) of 2-bromo-6-adamantyl-4-methylphenol in 300 mL of dry THF 2.79 g (69.7 mmol, 60% wt. in mineral oil) of sodium hydride was added portionwise at room temperature. After that, 5.55 mL (73.0 mmol) of MOMCl was added dropwise for 1 hour. The reaction mixture was heated at 60°C for 24 hours and then poured into 300 mL of cold water. The crude product was extracted with 3 x 200 mL of dichloromethane. The combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. Yield 24.3 g (quant.) of a colorless oil. ^1H NMR (CDCl_3 , 400 MHz): δ 7.24 (d, $J = 1.5$ Hz, 1H), 7.05 (d, $J = 1.8$ Hz, 1H), 5.22 (s, 2H), 3.71 (s, 3H), 2.27 (s, 3H), 2.07 – 2.15 (m, 9H), 1.78 (m, 6H). ^{13}C NMR


(CDCl₃, 100 MHz): δ 151.01, 144.92, 134.34, 131.80, 127.44, 117.57, 99.56, 57.75, 41.27, 37.71, 36.82, 29.03, 20.68.

[0231] 2-(3-Adamantan-1-yl)-2-(methoxymethoxy)-5-methylphenylbenzo[*b*]thiophene



- 5 To a solution of 10.0 g (74.5 mmol) of benzo[*b*]thiophene in 250 ml of dry THF 29.8 ml (74.5 mmol, 2.5 M) of ⁿBuLi in hexanes was added dropwise at -10°C. The reaction mixture was stirred for 1 hour at 0°C, followed by an addition of 11.2 g (82.0 mmol) of ZnCl₂. Next, the obtained solution was warmed to room temperature, 13.6 g (37.3 mmol) of 1-(3-bromo-2-(methoxymethoxy)-5-methylphenyl)adamantine and 1.52 g (2.98 mmol) of Pd[P^tBu₃]₂ were
- 10 subsequently added. The resulting mixture was stirred overnight at 60°C, then poured into 250 ml of water. The crude product was extracted with 3 x 150 ml of dichloromethane. The combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m; eluent: hexane-ethyl acetate = 10:1, vol.). Yield 5.31 g (34%) of a light-yellow solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.88
- 15 (d, J = 7.7 Hz, 1H), 7.81 (d, J = 7.4 Hz, 1H), 7.54 (s, 1H), 7.32 – 7.42 (m, 2H), 7.18 – 7.23 (m, 2H), 4.79 (s, 2H), 3.49 (s, 3H), 2.38 (s, 3H), 2.24 (m, 6H), 2.16 (m, 3H), 1.85 (m, 6H).


[0232] 3-Bromo-2-(3-adamantan-1-yl)-2-(methoxymethoxy)-5-methylphenylbenzo[*b*]thiophene



- 20 To a solution of 5.31 g (12.7 mmol) of 2-(3-adamantan-1-yl)-2-(methoxymethoxy)-5-methylphenylbenzo[*b*]thiophene in 150 ml of chloroform 2.26 g (12.7 mmol) of N-bromosuccinimide was added at room temperature. The reaction mixture was stirred for 2 hours at this temperature, then poured into 100 ml of water. The crude product was extracted with 3 x 50 ml of dichloromethane. The combined organic extract was dried over Na₂SO₄ and
- 25 then evaporated to dryness. The residue was recrystallized from 90 ml of n-hexane at -30°C. Yield 6.25 g (98%) of a light-yellow solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.90 (d, J = 7.8 Hz, 1H), 7.84 (d, J = 7.9 Hz, 1H), 7.49 (dt, J = 0.9, 7.1 Hz, 1H), 7.43 (dt, J = 1.2, 8.1 Hz, 1H), 7.24

(d, $J = 2.0$ Hz, 1H), 7.12 (d, $J = 1.7$ Hz, 1H), 4.66 (s, 2H), 3.33 (s, 3H), 2.38 (s, 3H), 2.22 (m, 6H), 2.14 (br.s, 3H), 1.83 (m, 6H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 153.19, 143.13, 138.54, 138.19, 137.38, 132.48, 130.68, 129.30, 126.06, 125.38, 125.03, 123.42, 122.19, 107.76, 99.33, 57.38, 41.17, 37.30, 36.97, 29.10, 20.98.

5 **[0233] 6,6'-(Pyridine-2,6-diylbis(benzo[*b*]thiophene-3,2-diyl))bis(2-adamantan-1-yl)-4-methylphenol)**



To a solution of 3.00 g (6.03 mmol) of 3-bromo-2-(3-adamantan-1-yl)-2-(methoxymethoxy)-5-methylphenylbenzo[*b*]thiophene in 120 ml of dry THF 2.41 ml (6.03 mmol, 2.5 M) of $n\text{BuLi}$ in
 10 hexanes was added dropwise at -80°C . The reaction mixture was stirred for 30 minutes at this temperature, then 2.32 g (17.1 mmol) of ZnCl_2 was added. The obtained mixture was warmed to room temperature, then 0.72 g (3.02 mmol) of 2,6-dibromopyridine and 245 mg (0.48 mmol) of $\text{Pd}[\text{P}^t\text{Bu}_3]_2$ were subsequently added. The obtained mixture was stirred overnight at 60°C , poured into 100 ml of water, and the crude product was extracted with dichloromethane
 15 (3 x 50 ml). The combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. To the resulting oil 50 ml of THF, 50 ml of methanol, and 1 ml of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 ml of water. The obtained mixture was extracted with dichloromethane (3 x 50 ml), the combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. The residue
 20 was purified by flash chromatography on silica gel 60 (40-63 μm ; eluent: hexane-ethyl acetate-triethylamine = 100:10:1, vol.). Yield 0.78 g (31%) of a white foam. ^1H NMR (CDCl_3 , 400 MHz): δ 7.87 – 7.94 (m, 4H), 7.67 (t, $J = 7.8$ Hz, 1H), 7.38 – 7.48 (m, 4H), 7.28 (d, $J = 7.8$ Hz, 2H), 6.91 – 6.99 (m, 4H), 2.23 (s, 6H), 1.82 (br.s, 6H), 1.67 (br.s, 9H), 1.57 – 1.62 (m, 6H), 1.42 – 1.50 (m, 6H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 153.56, 150.70, 140.51, 139.91, 138.86, 138.50, 137.87, 131.91, 129.49, 128.68, 128.49, 124.92, 124.77, 123.71, 122.82, 122.00, 40.02, 36.81, 36.60, 28.98, 20.73.


[0234] Dimethylhafnium[6,6'-(pyridine-2,6-diylbis(benzo[*b*]thiophene-3,2-diyl))bis(2-adamantan-1-yl)-4-methylphenolate)] (Complex 23). To a suspension of 155 mg (0.485 mmol) of hafnium tetrachloride in 50 ml of dry toluene 0.75 ml (2.20 mmol, 2.9 M) of MeMgBr

in diethyl ether was added in one portion at room temperature. The resulting suspension was stirred for 1 minute, and a solution of 400 mg (0.485 mmol) of 6,6'-(pyridine-2,6-diylbis(benzo[*b*]thiophene-3,2-diyl))bis(2-adamantan-1-yl)-4-methylphenol) in 10 ml of dry toluene was added dropwise for 1 minute. The reaction mixture was stirred overnight at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 ml of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The resulting solid was washed with 5 ml of n-hexane and dried in vacuo. Yield 303 mg (60%) of a beige solid as a hexane solvate. Anal. Calc. for $C_{57}H_{57}HfNO_2S_2 \times 2(C_6H_{14})$: C, 68.89; H, 7.12; N, 1.16. Found: C 69.07; H 7.33; N 1.11. 1H NMR (C_6D_6 , 400 MHz): δ 7.35 (dd, *J* = 1.9, 6.9 Hz, 2H), 7.21 (d, *J* = 2.1 Hz, 2H), 7.12 (d, *J* = 2.1 Hz, 2H), 7.05 – 7.12 (m, 4H), 6.92 (dd, *J* = 2.0, 6.5 Hz, 2H), 6.69 (t, *J* = 7.8 Hz, 1H), 6.46 (d, *J* = 7.8 Hz, 2H), 2.20 (s, 6H), 2.11 – 2.17 (m, 6H), 1.99 – 2.07 (m, 6H), 1.75 – 1.87 (m, 12H), 1.63 – 1.70 (m, 6H), 0.18 (s, 6H). ^{13}C NMR (C_6D_6 , 100 MHz): δ 160.12, 154.44, 150.43, 149.60, 147.46, 143.70, 141.40, 140.26, 134.21, 131.01, 130.32, 129.66, 127.31, 126.59, 125.59, 125.45, 124.83, 124.64, 122.98, 122.68, 114.02, 52.62, 41.19, 38.05, 37.67, 32.30, 29.73, 23.39, 14.69.

[0235] Dimethylzirconium[6,6'-(pyridine-2,6-diylbis(benzo[*b*]thiophene-3,2-diyl))bis(2-adamantan-1-yl)-4-methylphenolate)] (Complex 24). To a suspension of 58 mg (0.247 mmol) of zirconium tetrachloride in 30 ml of dry toluene 0.38 ml (1.11 mmol, 2.9 M) of MeMgBr in diethyl ether was added in one portion at room temperature. The resulting suspension was stirred for 10 seconds, and a solution of 204 mg (0.247 mmol) of 6,6'-(pyridine-2,6-diylbis(benzo[*b*]thiophene-3,2-diyl))bis(2-adamantan-1-yl)-4-methylphenol) in 10 ml of dry toluene was added dropwise for 30 seconds. The reaction mixture was stirred overnight at room temperature and then evaporated to near dryness. The solids obtained were extracted with 2 x 20 ml of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The resulting solid was washed with 5 ml of n-hexane and then dried in vacuum. Yield 140 mg (60%) of a beige solid. Anal. Calc. for $C_{57}H_{57}ZrNO_2S_2$: C, 72.57; H, 6.09; N, 1.48. Found: C 72.78; H 6.29; N 1.31. 1H NMR (C_6D_6 , 400 MHz): δ 7.34 (dd, *J* = 1.9, 6.7 Hz, 2H), 7.20 (d, *J* = 2.2 Hz, 2H), 7.12 (d, *J* = 2.5 Hz, 2H), 7.08 (m, 4H), 7.02 (m, 2H), 6.91 (dd, *J* = 1.8, 6.4 Hz, 2H), 6.69 (t, *J* = 7.6 Hz, 1H), 6.45 (d, *J* = 7.8 Hz, 2H), 2.20 (s, 6H), 2.15 – 2.21 (m, 6H), 2.02 – 2.09 (m, 6H), 1.75 – 1.85 (m, 12H), 1.64 – 1.72 (m, 6H), 0.40 (s, 6H). ^{13}C NMR (C_6D_6 , 100 MHz): δ 160.18, 155.17, 149.57, 141.60, 140.66, 140.29, 139.81, 130.94, 130.24, 129.66, 128.88, 127.40, 126.54, 126.12, 126.02, 125.72,


125.45, 125.07, 122.93, 122.73, 44.72, 41.44, 38.36, 37.83, 29.99, 21.65, 21.18.

[0236] 2-(3,5-Dimethyladamantan-1-yl)-4-fluorophenol




To a solution of 8.40 g (75.0 mmol) of 4-fluorophenol and 13.5 g (75.0 mmol) of 3,5-dimethyladamantan-1-ol in 150 ml of dichloromethane a solution of 4.90 ml (75.0 mmol) of methanesulfonic acid and 5 ml of acetic acid in 100 ml of dichloromethane was added dropwise for 1 hour at room temperature. The resulting mixture was stirred at room temperature for 48 hours and then carefully poured into 300 ml of 5% NaHCO₃. The obtained mixture was extracted with dichloromethane (3 x 50 ml), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified using Kugelrohr apparatus (1 mbar, 70°C) yielding 14.2 g (68%) of the title product as a light-yellow oil. ¹H NMR (CDCl₃, 400 MHz): δ 6.93 (dd, J = 3.1, 11.2 Hz, 1H), 6.73 (ddd, J = 3.1, 7.4, 8.6 Hz, 1H), 6.55 (dd, J = 4.9, 8.6 Hz), 4.62 (s, 1H), 2.16 (dt, J = 3.1, 6.3 Hz, 1H), 1.91 (m, 2H), 1.64 – 1.74 (m, 4H), 1.35 – 1.45 (m, 4H), 1.20 (br.s, 2H), 0.87 (s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 158.49 (J_F = 236 Hz), 150.19 (J_F = 2.0 Hz), 137.69 (J_F = 5.9 Hz), 117.12 (J_F = 8.1 Hz), 114.13 (J_F = 24.0 Hz), 112.57 (J_F = 22.9 Hz), 50.92, 46.44, 43.05, 38.70, 38.48, 31.38, 30.84, 29.90.


[0237] 2-Bromo-6-(3,5-dimethyladamantan-1-yl)-4-fluorophenol



To a solution of 14.2 g (51.7 mmol) of 2-(3,5-dimethyladamantan-1-yl)-4-fluorophenol in 200 ml of dichloromethane a solution of 2.67 ml (51.7 mmol) of bromine in 100 ml of dichloromethane was added dropwise for 1 hour at room temperature. The resulting mixture was stirred at room temperature for 48 hours and then carefully poured into 200 ml of 5% NaHCO₃. The obtained mixture was extracted with dichloromethane (3 x 50 ml), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. Yield 17.5 g (96%) of a light-yellow solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.06 (dd, J = 3.0, 7.0 Hz, 1H), 6.93 (dd, J = 2.9, 10.8 Hz, 1H), 5.59 (s, 1H), 2.16 (m, 1H), 1.89 (br.s, 2H), 1.63 – 1.73 (m, 4H), 1.34 – 1.44 (m, 4H), 1.19 (br.s, 2H), 0.86 (s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 157.21 (J_F = 241 Hz), 146.61 (J_F = 2.8 Hz), 137.97 (J_F = 6.1 Hz), 115.34 (J_F = 25.8 Hz), 113.64 (J_F = 23.6 Hz), 110.83 (J_F = 10.9 Hz), 54.77, 50.48, 45.71, 42.61, 38.96, 38.03, 31.02, 30.42, 29.49.

[0238] 1-(3-Bromo-5-fluoro-2-(methoxymethoxy)phenyl)-3,5-dimethyladamantane


To a solution of 17.5 g (49.5 mmol) of 2-bromo-6-(3,5-dimethyladamantan-1-yl)-4-fluorophenol in 200 ml of dry THF 2.17 g (54.4 mmol, 60% wt. in mineral oil) of sodium hydride was added portionwise at room temperature. After that, 4.53 ml (60.0 mmol) of MOMCl was added dropwise for 1 hour. The reaction mixture was heated at 60°C for 24 hours and then poured into 300 ml of cold water. The crude product was extracted with 3 x 200 ml of dichloromethane. The combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. Yield 19.6 g (quant.) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.13 (dd, J = 3.1, 6.8 Hz, 1H), 6.98 (dd, J = 3.1, 10.9 Hz, 1H), 5.19 (s, 2H), 3.68 (s, 3H), 2.16 (m, 1H), 1.89 (br.s, 2H), 1.64 – 1.74 (m, 4H), 1.34 – 1.44 (m, 4H), 1.19 (br.s, 2H), 0.87 (s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.47 (J_F = 245 Hz), 150.08 (J_F = 3.3 Hz), 146.34 (J_F = 6.4 Hz), 118.13 (J_F = 25.4 Hz), 117.65 (J_F = 10.7 Hz), 114.01 (J_F = 23.4 Hz), 99.95, 57.89, 50.69, 47.13, 42.84, 39.78, 39.55, 31.50, 30.84, 29.94.

[0239] 2-(3-(3,5-Dimethyladamantan-1-yl)-5-fluoro-2-(methoxymethoxy)phenyl)benzo[b]thiophene

To a solution of 3.38 g (25.2 mmol) of benzo[b]thiophene in 200 ml of dry THF 9.50 ml (23.9 mmol, 2.5 M) of ⁿBuLi in hexanes was added dropwise at -10°C. The reaction mixture was stirred for 2 hours at 0°C, followed by an addition of 3.30 g (23.9 mmol) of ZnCl₂. Next, the obtained solution was warmed to room temperature, 5.00 g (12.6 mmol) of 1-(3-bromo-5-fluoro-2-(methoxymethoxy)phenyl)-3,5-dimethyladamantane and 643 mg (1.26 mmol) of Pd[P^tBu₃]₂ were subsequently added. The resulting mixture was stirred overnight at 60°C, then poured into 250 ml of water. The crude product was extracted with 3 x 150 ml of dichloromethane. The combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μm; eluent:


hexane-ethyl acetate = 10:1, vol.). Yield 4.52 g (80%) of a light-yellow oil. ¹H NMR (CDCl₃, 400 MHz): δ 7.85 (dd, J = 1.1, 7.3 Hz, 1H), 7.79 (dd, J = 1.5, 7.0 Hz, 1H), 7.51 (s, 1H), 7.35 (qd, J = 5.7, 7.2, 7.2, 7.2, 2H), 7.06 (s, 1H), 7.04 (m, 1H), 4.72 (s, 2H), 3.45 (s, 3H), 2.20 (m, 1H), 1.98 (br.s, 2H), 1.71 – 1.83 (m, 4H), 1.37 – 1.47 (m, 4H), 1.22 (br.s, 2H), 0.90 (s, 6H).
 5 ¹³C NMR (CDCl₃, 100 MHz): δ 159.72 (J_F = 241 Hz), 150.30, 150.28, 145.71, 140.51 (J_F = 2.0 Hz), 140.29, 139.92, 129.86, 129.78, 124.51 (J_F = 3.5 Hz), 123.64 (J_F = 3.5 Hz), 122.15, 115.46 (J_F = 23.7 Hz), 114.68 (J_F = 23.6 Hz), 99.29, 57.73, 50.84, 47.25, 42.97, 39.59, 39.47, 31.54, 30.92, 30.03.

[0240] 3-Bromo-2-(3-(3,5-dimethyladamantan-1-yl)-5-fluoro-2-(methoxymethoxy)phenyl)benzo[b]thiophene



To a solution of 4.50 g (10.0 mmol) of 2-(3-(3,5-dimethyladamantan-1-yl)-5-fluoro-2-(methoxymethoxy)phenyl)benzo[b]thiophene in 150 ml of chloroform 1.82 g (10.2 mmol) of N-bromosuccinimide was added at room temperature. The reaction mixture was stirred for 12
 15 hours at this temperature, then poured into 100 ml of water. The crude product was extracted with 3 x 50 ml of dichloromethane. The combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was recrystallized from 110 ml of n-hexane. Yield 4.88 g (92%) of a beige solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.87 (d, J = 7.4 Hz, 1H), 7.83 (d, J = 8.0 Hz, 1H), 7.49 (dt, J = 1.1, 7.1 Hz, 1H), 7.43 (dt, J = 1.3, 7.3 Hz, 1H), 7.11 (dd, J = 3.2, 10.9 Hz, 1H), 6.99 (dd, J = 3.2, 7.6 Hz, 1H), 4.59 (s, 2H), 3.31 (s, 3H), 2.19 (m, 1H), 1.98 (br.s, 2H), 1.70 – 1.83 (m, 4H), 1.36 – 1.46 (m, 4H), 1.21 (br.s, 2H), 0.89 (s, 6H).
 20 ¹³C NMR (CDCl₃, 100 MHz): δ 159.24 (J_F = 242 Hz), 151.76 (J_F = 2.9 Hz), 145.29 (J_F = 6.4 Hz), 138.60, 138.01, 135.93, 127.35 (J_F = 9.0 Hz), 125.76, 125.22, 123.64, 122.29, 116.40 (J_F = 23.4 Hz), 115.67 (J_F = 23.6 Hz), 108.29, 99.65, 57.51, 50.86, 47.09, 42.98, 39.41, 39.36,
 25 31.51, 30.92, 29.99.

[0241] 6,6'-(Pyridine-2,6-diylbis(benzo[b]thiophene-3,2-diyl))bis(2-(3,5-dimethyladamantan-1-yl)-4-fluorophenol)




To a solution of 4.00 g (7.55 mmol) of 3-bromo-2-(3-(3,5-dimethyladamantan-1-yl)-5-fluoro-2-(methoxymethoxy)phenyl)benzo[*b*]thiophene in 50 ml of dry THF 3.08 ml (7.70 mmol, 2.5 M) of ⁿBuLi in hexanes was added dropwise at -80°C. The reaction mixture was stirred for 30 minutes at this temperature, then 1.02 g (7.70 mmol) of ZnCl₂ was added. The obtained mixture was warmed to room temperature, then 0.86 g (3.63 mmol) of 2,6-dibromopyridine and 194 mg (0.38 mmol) of Pd[P^tBu₃]₂ were subsequently added. The obtained mixture was stirred overnight at 60°C, poured into 100 ml of water, and the crude product was extracted with dichloromethane (3 x 50 ml). The combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 ml of THF, 50 ml of methanol, and 2 ml of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 ml of water. The obtained mixture was extracted with dichloromethane (3 x 50 ml), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μm; eluent: hexane-ethyl acetate-triethylamine = 100:10:1, vol.). Yield 1.80 g (56%, as a mixture of rotamers) of a light-yellow foam. ¹H NMR (CDCl₃, 400 MHz): δ 7.85 – 7.91 (m, 4H), 7.71 (t, *J* = 7.8 Hz, 1H), 7.43 (m, 4H), 7.27 (m, 2H), 6.82 – 6.87 (m, 4H), 0.91 – 2.15 (m, 26H), 0.69 – 0.87 (m, 12H). ¹³C NMR (CDCl₃, 100 MHz): δ 157.34, 154.97, 153.27, 148.98, 140.47 (*J_F* = 5.9 Hz), 140.03, 138.96, 138.56, 138.09, 132.36, 125.19, 124.00, 122.91, 122.19, 119.08, 115.02 (*J_F* = 11.0 Hz), 114.79 (*J_F* = 10.7 Hz), 50.73, 46.35, 46.14, 43.07, 42.71, 38.59, 37.57, 31.39, 31.15, 30.87, 30.74, 30.03, 29.93.

[0242] Dimethylhafnium[6,6'-(pyridine-2,6-diylbis(benzo[*b*]thiophene-3,2-diyl))bis(2-(3,5-dimethyladamantan-1-yl)-4-fluorophenolate)] (Complex 25). To a suspension of 623 mg (1.94 mmol) of hafnium tetrachloride (<0.05% Zr) in 70 ml of dry toluene 3.01 ml (8.73 mmol, 2.9 M) of MeMgBr in diethyl ether was added in one portion at room temperature. The resulting suspension was stirred for 1 minute, and a solution of 1.73 g (1.94 mmol) of 6,6'-(pyridine-2,6-diylbis(benzo[*b*]thiophene-3,2-diyl))bis(2-(3,5-dimethyladamantan-1-yl)-4-fluorophenol) in 20 ml of dry toluene was added dropwise for 1 minute. The reaction mixture was stirred overnight at room temperature and then evaporated to near dryness. The solid obtained was


- extracted with 2 x 50 ml of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The resulting solid was washed with 15 ml of n-hexane and then dried in vacuo. Yield 1.40 g (66%) of a beige solid as a hexane solvate. Anal. Calc. for $C_{59}H_{59}F_2HfNO_2S_2 \times 0.5(C_6H_{14})$: C, 65.45; H, 5.85; N, 1.23.
- 5 Found: C 65.68; H 6.07; N 1.14. 1H NMR (C_6D_6 , 400 MHz): δ 7.31 (m, 2H), 7.23 (dd, J = 3.3, 11.1 Hz, 2H), 7.09 (dd, J = 3.2, 7.7 Hz, 2H), 7.04 (m, 4H), 6.83 (m, 2H), 6.74 (t, J = 7.8 Hz, 1H), 6.35 (d, J = 7.8 Hz, 2H), 2.33 (d, J = 12.1 Hz, 2H), 2.05 (d, J = 11.7 Hz, 2H), 1.66 (br.s, 2H), 1.03 – 1.50 (m, 20H), 0.83 (s, 6H), 0.76 (s, 6H), -0.10 (s, 6H). ^{13}C NMR (CD_2Cl_2 , 100 MHz): δ 158.62, 156.35 (J_F = 234 Hz), 154.17, 147.34 (J_F = 1.8 Hz), 141.61, 141.52 (J_F = 6.1 Hz), 141.02,
- 10 139.98, 127.11, 126.43, 126.18, 126.01, 124.23 (J_F = 8.8 Hz), 122.81, 115.91 (J_F = 16.8 Hz), 115.68 (J_F = 16.8 Hz), 52.36, 51.64, 48.47, 45.29, 43.61, 42.34, 39.67, 37.98, 31.91, 31.44, 31.38, 30.79, 29.98, 27.47.

[0243] 2,6-bis(2-Bromophenyl)pyridine



- 15 2,6-Dibromopyridine (3.73 g, 15.7 mmol), 2-bromophenylboronic acid (6.26 g, 31.4 mmol), sodium carbonate (8.33 g, 78.6 mmol), dioxane (66 mL), and water (33 mL) were combined in a round-bottomed flask. The mixture was sparged with nitrogen for 1 hour then the $Pd(PPh_3)_4$ (1.82 g, 1.57 mmol) was quickly added. The mixture was sparged for 30 minutes, then heated to 100°C overnight. The next day the mixture was poured into water (200 mL) and extracted
- 20 with dichloromethane (4 x 60 mL). The combined organics were dried with brine, then Na_2SO_4 . Evaporation afforded crude product as a yellow-orange oily solid that is purified by crystallization from hot toluene. Yield 3.42 g, 55.9%.

[0244] 2-(3-(2,3-dimethylbutan-2-yl)-2-(methoxymethoxy)-5-methylphenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane




25

Tetrahydrofuran (20 mL) was added to 1-bromo-3-(2,3-dimethylbutan-2-yl)-2-(methoxymethoxy)-5-methylbenzene (2.89 g, 9.17 mmol) to form a pale brown solution. At -50°C a hexane solution of BuLi (6.30 mL, 10.1 mmol) was added dropwise over 5 minutes to

form a brown suspension. The mixture was stirred for 45 minutes then the 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane (2.22 g, 11.9 mmol) was added to form a clear brown solution. The mixture was allowed to slowly warm to ambient temperature. After stirring overnight the mixture was poured into water (100 mL) and shaken. The mixture was extracted with dichloromethane (5 x 50 mL). The combined organics were washed with water, brine, then dried over MgSO₄. Removal of volatiles afforded the product as a brown oil. Yield: 2.45 g, 73.7%.

[0245] 2',2'''-(pyridine-2,6-diyl)bis(3-(2,3-dimethylbutan-2-yl)-5-methyl-[1,1'-biphenyl]-2-ol)




A 100 mL round-bottomed flask was loaded with 1-bromo-3-(2,3-dimethylbutan-2-yl)-2-(methoxymethoxy)-5-methylbenzene (2.45 g, 6.76 mmol), 2,6-bis(2-bromophenyl)pyridine (1.32 g, 3.38 mmol), Na₂CO₃ (1.79 g, 16.9 mmol), dioxane (20 mL) and water (10 mL). The mixture was sparged with nitrogen for 30 minutes then solid Pd(PPh₃)₄ (0.391 g, 0.340 mmol) was added. The mixture was sparged for an additional 15 minutes, then stirred and heated in an oil bath maintained at 100°C. After 17 hours the brown mixture was combined with water (100 mL) in a separatory funnel. The mixture was extracted with CH₂Cl₂ (6 x 25 mL). The combined organics were dried over brine, then MgSO₄. Removal of the volatiles afforded 3.1 g of brown oil that was combined with tetrahydrofuran (20 mL), methanol (20 mL), and concentrated HCl (1.0 mL). The mixture was stirred and heated to 60°C for 4 hours. The volatiles were then evaporated and the residue was extracted with CH₂Cl₂ (100 mL), washed with water (3 x 50 mL), and dried with brine (20 mL). The mixture was dried over MgSO₄, filtered, then evaporated to afford crude product that was purified on by column chromatography on silica gel, eluted with 2-8% ethyl acetate in hexanes. Yield: 0.87 g, 42%.

[0246] Dibenzylzirconium[2',2'''-(pyridine-2,6-diyl)bis(3-(2,3-dimethylbutan-2-yl)-5-methyl-[1,1'-biphenyl]-2-olate)] (Complex 29). Toluene (5 mL) was added to 2',2'''-(pyridine-2,6-diyl)bis(3-(2,3-dimethylbutan-2-yl)-5-methyl-[1,1'-biphenyl]-2-ol) (0.260 g, 0.425 mmol) and tetrabenzylzirconium (0.194 g, 0.425 mmol) to form a slightly cloudy orange solution. After stirring overnight the mixture was evaporated and the residue was extracted with methylcyclohexane (5 mL). The cloudy orange solution was filtered and evaporated to a residue and pentane (4 mL) was added. The mixture was triturated to form a divided yellow-orange solid. The mixture was cooled to -15°C for 1 hour then the solid was collected on a fritted disk.

The solid was washed with cold pentane (2 x 5 mL) and dried under reduced pressure. Product co-crystallized with 1 equiv. hexane. Yield: 0.233 g, 56.5%.


[0247] Dibenzylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-(2,3-dimethylbutan-2-yl)-5-methyl-[1,1'-biphenyl]-2-olate)] (Complex 30). Toluene (5 mL) was added to 2',2'''-(pyridine-2,6-diyl)bis(3-(2,3-dimethylbutan-2-yl)-5-methyl-[1,1'-biphenyl]-2-ol) (0.208 g, 0.340 mmol) and tetrabenzylhafnium (0.185 g, 0.340 mmol) to form a clear yellow-orange solution. The mixture was stirred overnight. The mixture was filtered and evaporated to a residue. Pentane (3 mL) was added and the mixture was triturated until a divided solid formed. The mixture was cooled to -15°C for 1 hour. Yellow solid was then collected on a fritted disk, washed with cold pentane (2 x 5 mL) and dried under reduced pressure. Product is co-crystallized with 1 equiv. of hexane. Yield: 0.160 g, 44.5%.

[0248] 2-(Adamantan-1-yl)-6-bromo-4-methylphenol



To a solution of 21.2 g (87.0 mmol) of 2-(adamantan-1-yl)-4-methylphenol in 200 mL of dichloromethane a solution of 4.50 mL (87.0 mmol) of bromine in 100 mL of dichloromethane was added dropwise for 10 minutes at room temperature. The resulting mixture was diluted with 400 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄ and then evaporated to dryness. Yield 21.5 g (77%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.17 (s, 1H), 6.98 (s, 1H), 5.65 (s, 1H), 2.27 (s, 3H), 2.10 – 2.13 (m, 9H), 1.80 (m, 6H), ¹³C NMR (CDCl₃, 100 MHz): δ 148.18, 137.38, 130.24, 129.32, 127.26, 112.08, 40.18, 37.32, 36.98, 28.99, 20.55.


[0249] (1-(3-Bromo-5-methyl-2-(methoxymethoxy)phenyl)adamantine



To a solution of 21.3 g (66.4 mmol) of 2-(adamantan-1-yl)-6-bromo-4-methylphenol in 400 mL of THF 2.79 g (69.7 mmol, 60% wt. in mineral oil) of sodium hydride was added portionwise at room temperature. To the resulting suspension 5.55 mL (73.0 mmol) of methoxymethyl chloride was added dropwise for 10 minutes at room temperature. The obtained mixture was stirred


overnight, then poured into 200 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 200 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. Yield 24.3 g (quant.) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.24 (d, J = 1.5 Hz, 1H), 7.05 (d, J = 1.8 Hz, 1H), 5.22 (s, 2H), 3.71 (s, 3H), 2.27 (s, 3H), 2.05 – 2.12 (m, 9H), 1.78 (m, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 151.01, 144.92, 134.34, 131.80, 127.44, 117.57, 99.56, 57.75, 41.27, 37.71, 36.82, 29.03, 20.68.

[0250] 2-(3-Adamantan-1-yl)-5-methyl-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



To a solution of 20.0 g (55.0 mmol) of (1-(3-bromo-5-methyl-2-(methoxymethoxy)phenyl)adamantine in 400 mL of dry THF 22.5 mL (56.4 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred at this temperature for 1 hour followed by addition of 16.7 mL (82.2 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred for 1 hour at room temperature, then poured into 300 mL of water. The crude product was extracted with dichloromethane (3 x 300 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. Yield 22.4 g (99%) of a colorless viscous oil. ¹H NMR (CDCl₃, 400 MHz): δ 7.35 (d, J = 2.3 Hz, 1H), 7.18 (d, J = 2.3 Hz, 1H), 5.14 (s, 2H), 3.58 (s, 3H), 2.28 (s, 3H), 2.14 (m, 6H), 2.06 (m, 3H), 1.76 (m, 6H), 1.35 (s, 12H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.68, 141.34, 134.58, 131.69, 131.14, 100.96, 83.61, 57.75, 41.25, 37.04, 29.14, 24.79, 20.83.


[0251] 1-(2'-Bromo-5-methyl-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine



To a solution of 10.0 g (24.3 mmol) of 2-(3-adamantan-1-yl)-5-methyl-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 100 mL of 1,4-dioxane 7.22 g (25.5 mmol) of 2-bromoiodobenzene, 8.38 g (60.6 mmol) of potassium carbonate, and 50 mL of water were subsequently added. The mixture obtained was purged with argon for 10


minutes followed by addition of 1.40 g (1.21 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 100 mL of water. The crude product was extracted with dichloromethane (3 x 150 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 um, eluent: hexane-dichloromethane = 10:1, vol.). Yield 10.7 g (quant.) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.72 (d, J = 7.9 Hz, 1H), 7.35 – 7.44 (m, 3H), 7.19 – 7.26 (m, 1H), 6.94 (m, 1H), 4.53 (dd, J = 20.0, 4.6 Hz, 2H), 3.24 (s, 3H), 2.38 (s, 3H), 2.23 (m, 6H), 2.15 (m, 3H), 1.84 (m, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 151.51, 142.78, 141.11, 134.63, 132.76, 132.16, 132.13, 129.83, 128.57, 127.76, 127.03, 124.05, 98.85, 56.95, 41.21, 37.18, 36.94, 29.07, 21.00.

[0252] 2-(3'-(Adamantan-1-yl)-5'-methyl-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane




To a solution of 10.7 g (24.3 mmol) of 1-(2'-bromo-5-methyl-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine in 250 mL of dry THF 11.6 mL (29.1 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred for 1 hour at this temperature followed by addition of 8.43 mL (41.3 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 300 mL of water. The crude product was extracted with dichloromethane (3 x 300 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 um, eluent: hexane-diethyl ether = 10:1, vol.). Yield 8.60 g (72%) of a colorless glassy solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.75 (d, J = 7.4 Hz, 1H), 7.33 – 7.44 (m, 2H), 7.29 – 7.33 (m, 1H), 7.07 (br.s, 1H), 6.84 (br.s, 1H), 4.50 (d, J = 4.4 Hz, 1H), 4.40 (d, J = 4.4 Hz, 1H), 3.27 (s, 3H), 2.30 (s, 3H), 2.21 (br.s, 6H), 2.11 (m, 3H), 1.80 (m, 6H), 1.21 (s, 6H), 1.15 (s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 151.52, 145.68, 142.04, 136.74, 134.30, 131.47, 130.51, 130.23, 129.79, 126.69, 126.06, 98.73, 83.39, 57.22, 41.47, 37.20, 37.04, 29.19, 25.00, 24.16, 20.97.

[0253] 2',2'''-(Pyridine-2,6-diyl)bis(3-adamantan-1-yl)-5-methyl-[1,1'-biphenyl]-2-ol




To a solution of 4.00 g (8.19 mmol) of 2-(3'-(adamantan-1-yl)-5'-methyl-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of 1,4-dioxane, 969 mg (4.09 mmol) of 2,6-dibromopyridine, 6.68 g (20.5 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 470 mg (0.41 mmol) of $\text{Pd(PPh}_3)_4$. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO_3 , dried over Na_2SO_4 , and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μm , eluent: hexane-ethyl acetate = 10:1, vol.). The obtained glassy solid was triturated with 30 mL of n-pentane, the precipitate thus obtained was filtered off (G3), washed with 2 x 10 mL of n-pentane, and dried in vacuo. Yield 2.10 g (72%) of a mixture of two isomers as a white powder. ^1H NMR (CDCl_3 , 400 MHz): δ 7.64 (s, 1H), 7.41 – 7.59 (m, 7H), 7.33 – 7.38 (m, 2H), 7.27 (br.s, 1H), 7.02 (d, J = 7.9 Hz, 1H), 7.00 (d, J = 7.8 Hz, 1H), 6.87 – 6.92 (m, 3H), 6.21 (d, J = 1.7 Hz, 1H), 2.26 (s, 3H), 1.55 – 1.98 (m, 33H). ^{13}C NMR (CDCl_3 , 100 MHz) δ 157.91, 157.89, 150.24, 149.65, 139.70, 138.49, 137.93, 137.58, 137.54, 137.44, 137.06, 136.80, 132.39, 131.36, 130.48, 130.34, 130.17, 129.97, 129.36, 129.09, 128.90, 128.82, 128.70, 128.45, 127.78, 127.71, 126.90, 126.54, 122.30, 122.02, 40.35, 40.17, 37.00, 36.78, 36.66, 36.46, 29.09, 28.96, 20.85, 20.52.

[0254] (3r,5r,7r)-1-(2'-Bromo-2-(methoxymethoxy)-4',5-dimethyl-[1,1'-biphenyl]-3-yl)adamantine



To a solution of 6.11 g (14.8 mmol) of 2-(3-adamantan-1-yl)-5-methyl-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 100 mL of 1,4-dioxane 4.62 g (15.6 mmol) of 2-bromo-4-methyliodobenzene, 5.12 g (37.0 mmol) of potassium carbonate, and 50 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 850 mg (0.741 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 100 mL of water. The crude product was extracted with dichloromethane (3 x 150 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 um, eluent: hexane-dichloromethane = 10:1, vol.). Yield 4.88 g (73%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.53 (s, 1H), 7.27 (d, J = 7.8 Hz, 1H), 7.16 – 7.19 (m, 2H), 6.90 (d, J = 1.7 Hz, 1H), 4.40 (m, 2H), 3.27 (s, 3H), 2.40 (s, 3H), 2.35 (s, 3H), 2.20 (m, 6H), 2.12 (m, 3H), 1.81 (m, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 151.72, 142.67, 138.73, 138.09, 134.43, 133.20, 132.02, 131.82, 130.08, 127.94, 127.61, 123.70, 98.79, 57.06, 41.21, 37.19, 36.98, 29.11, 21.03, 20.75.


[0255] 2-(3'-((3r,5r,7r)-Adamantan-1-yl)-2'-(methoxymethoxy)-4,5'-dimethyl-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



To a solution of 4.88 g (10.7 mmol) of (3r,5r,7r)-1-(2'-bromo-2-(methoxymethoxy)-4',5'-dimethyl-[1,1'-biphenyl]-3-yl)adamantine in 120 mL of dry THF 5.20 mL (12.8 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred for 1 hour at this temperature followed by addition of 4.43 mL (21.4 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 300 mL of water. The crude product was extracted with dichloromethane (3 x 300 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 um, eluent: hexane-diethyl ether = 10:1, vol.). Yield 3.04 g (57%) of a colorless glassy solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.53 (s, 1H), 7.19 – 7.23 (m, 2H), 7.02 (d, J = 2.1 Hz, 1H), 6.79 (d, J = 1.7 Hz, 1H), 4.43 (m, 2H), 3.27 (s, 3H), 2.37 (s, 3H), 2.26 (s, 3H), 2.17 (m, 6H), 2.08 (m, 6H), 1.77 (m, 6H), 1.18 (s, 6H), 1.13 (s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 151.71,

142.84, 141.95, 136.61, 135.53, 134.91, 131.41, 130.65, 130.63, 130.21, 126.52, 98.73, 83.38, 57.28, 41.49, 37.20, 37.07, 29.22, 25.02, 24.20, 21.03, 20.99.


[0256] 2',2'''-(Pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-4',5-dimethyl-[1,1'-biphenyl]-2-ol)



5


To a solution of 3.04 g (6.05 mmol) of 2-(3'-((3*r*,5*r*,7*r*)-adamantan-1-yl)-2'-(methoxymethoxy)-4,5'-dimethyl-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of 1,4-dioxane, 716 mg (3.02 mmol) of 2,6-dibromopyridine, 4.92 g (15.1 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 350 mg (0.30 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μm, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 0.74 g (33%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 7.66 (s, 1H), 7.39 – 7.42 (m, 3H), 7.22 – 7.35 (m, 5H), 6.96 – 7.01 (m, 2H), 6.85 – 6.91 (m, 3H), 6.16 (d, J = 1.5 Hz, 1H), 2.49 (s, 3H), 2.47 (s, 3H), 2.26 (s, 3H), 1.58 – 2.04 (m, 33H). ¹³C NMR (CDCl₃, 100 MHz) δ 158.05, 157.98, 150.39, 149.80, 139.62, 138.29, 137.77, 137.61, 137.55, 136.94, 136.62, 134.64, 134.44, 132.31, 131.18, 130.90, 130.77, 130.39, 130.15, 129.95, 129.55, 129.13, 128.99, 128.62, 128.34, 126.74, 126.34, 122.22, 121.95, 40.35, 40.21, 37.07, 36.88, 36.65, 36.46, 29.15, 29.04, 21.09, 21.06, 20.86, 20.51.

[0257] (3*r*,5*r*,7*r*)-1-(2'-Bromo-4'-(*tert*-butyl)-2-(methoxymethoxy)-5-methyl-[1,1'-biphenyl]-3-yl)adamantine



To a solution of 8.00 g (19.4 mmol) of 2-(3-adamantan-1-yl)-5-methyl-2-(methoxymethoxy)phenyl-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 50 mL of 1,4-dioxane 7.22 g (21.3 mmol) of 2-bromo-4-(*tert*-butyl)iodobenzene, 6.70 g (48.5 mmol) of potassium carbonate, and 25 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 2.20 g (1.90 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 100 mL of water. The crude product was extracted with dichloromethane (3 x 150 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 um, eluent: hexane-dichloromethane = 10:1, vol.). Yield 5.20 g (54%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.68 (s, 1H), 7.30 – 7.38 (m, 2H), 7.16 (s, 1H), 6.92 (s, 1H), 4.49 (m, 2H), 3.18 (s, 3H), 2.35 (s, 3H), 2.19 (m, 6H), 2.12 (m, 3H), 1.81 (m, 6H), 1.37 (s, 9H). ¹³C NMR (CDCl₃, 100 MHz): δ 152.30, 151.61, 142.80, 138.05, 134.67, 132.11, 131.74, 130.01, 129.70, 127.66, 124.22, 123.89, 98.83, 56.93, 41.29, 37.24, 37.00, 34.60, 31.22, 29.14, 21.05.


[0258] 2-(3'-((3*r*,5*r*,7*r*)-Adamantan-1-yl)-4-(*tert*-butyl)-2'-(methoxymethoxy)-5'-methyl-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



To a solution of 5.12 g (10.3 mmol) of (3*r*,5*r*,7*r*)-1-(2'-bromo-4'-(*tert*-butyl)-2-(methoxymethoxy)-5-methyl-[1,1'-biphenyl]-3-yl)adamantine in 120 mL of dry THF 6.20 mL (15.4 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred for 1 hour at this temperature followed by addition of 5.23 mL (25.6 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 300 mL of water. The crude product was extracted with dichloromethane (3 x 300 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash

chromatography on silica gel 60 (40-63 μ m, eluent: hexane-diethyl ether = 10:1, vol.). Yield 3.30 g (59%) of a colorless glassy solid. ^1H NMR (CDCl_3 , 400 MHz): δ 7.72 (d, J = 2.1 Hz, 1H), 7.44 (dd, J = 8.1, 2.2 Hz, 1H), 7.29 (d, J = 8.1 Hz, 1H), 7.05 (d, J = 2.0 Hz, 1H), 6.83 (d, J = 1.7 Hz, 1H), 4.45 (m, 2H), 3.24 (s, 3H), 2.28 (s, 3H), 2.20 (m, 6H), 2.10 (m, 3H), 1.79 (m, 6H), 1.37 (s, 9H), 1.20 (br.s, 6H), 1.14 (br.s, 6H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 151.61, 148.72, 142.79, 141.98, 136.75, 131.35, 130.67, 130.64, 129.95, 126.89, 126.48, 98.70, 83.33, 57.20, 41.51, 37.22, 37.08, 34.45, 31.41, 29.22, 25.03, 24.22, 20.96.

[0259] 2',2'''-(Pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-4'-(tert-butyl)-5-methyl-[1,1'-biphenyl]-2-ol)




10

To a solution of 1.75 g (3.21 mmol) of 2-(3'-((3*r*,5*r*,7*r*)-adamantan-1-yl)-4-(tert-butyl)-2'-(methoxymethoxy)-5'-methyl-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of 1,4-dioxane, 381 mg (1.61 mmol) of 2,6-dibromopyridine, 2.62 g (8.03 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 180 mg (0.16 mmol) of $\text{Pd}(\text{PPh}_3)_4$. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO_3 , dried over Na_2SO_4 , and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 0.60 g (45%) of a mixture of two isomers as a white foam. ^1H NMR (CDCl_3 , 400 MHz): δ 7.72 and 7.08 (2s, 2H), 7.40 – 7.53 (m, 5H), 7.21 – 7.26 (m, 2H), 6.94 – 7.00 (m, 2H), 6.80 – 6.86 and 6.09 (2m, 4H), 1.53 – 1.95 (m, 30H), 1.39 and 1.40 (2s, 18H). ^{13}C NMR (CDCl_3 , 100 MHz) δ 158.53, 150.71, 150.54, 149.85, 139.47, 137.94, 137.52, 136.66, 134.45, 132.05, 130.80, 130.68, 129.49, 129.04, 128.58, 128.41, 127.40, 127.24, 126.78, 126.36, 125.72,

25

122.26, 122.02, 40.38, 40.28, 37.05, 36.87, 36.70, 36.52, 34.67, 31.58, 31.39, 29.11, 28.98, 20.87, 20.52.


[0260] 2',2'''-(4-Methoxypyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-4'-(*tert*-butyl)-5-methyl-[1,1'-biphenyl]-2-ol)



5


To a solution of 1.50 g (2.75 mmol) of 2-(3'-((3*r*,5*r*,7*r*)-adamantan-1-yl)-4-(*tert*-butyl)-2'-(methoxymethoxy)-5'-methyl-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of 1,4-dioxane, 367 mg (1.38 mmol) of 2,6-dibromo-4-methoxypyridine, 2.25 g (6.90 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained
 10 was purged with argon for 10 minutes followed by addition of 160 mg (0.138 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were
 15 subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μm, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 1.04 g (89%) of a mixture of two
 20 isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 7.88 and 7.31 (2s, 2H), 7.46 – 7.57 (m, 4H), 7.21 – 7.27 (m, 2H), 6.83 (m, 2H), 6.46 – 6.48 (m, 2H), 6.12 and 6.88 (2m, 2H), 3.50 and 3.41 (2s, 3H), 1.57 – 1.95 (m, 30H), 1.40 and 1.41 (2s, 18H). ¹³C NMR (CDCl₃, 100 MHz) δ 160.07, 150.75, 150.50, 139.59, 137.92, 134.48, 131.99, 130.84, 130.77, 129.49, 129.11, 128.53, 127.13, 126.42, 125.79, 108.64, 108.33, 55.22, 40.54, 40.29, 37.08, 36.92, 36.77, 34.69,
 25 31.46, 31.42, 29.17, 29.06, 20.57.

[0261] 2-(Adamantan-1-yl)-6-bromo-4-(*tert*-butyl)phenol




To a solution of 236 g (830 mmol) of 2-(adamantan-1-yl)-4-(*tert*-butyl)phenol in 2000 mL of dichloromethane a solution of 132 g (830 mmol) of bromine in 400 mL of dichloromethane was added dropwise for 1 hour at room temperature. The resulting mixture was diluted with 2,000 mL of water. The obtained mixture was extracted with dichloromethane (3 x 500 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. Yield 299 g (99%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.32 (d, J = 2.3 Hz, 1 H), 7.19 (d, J = 2.3 Hz, 1 H), 5.65 (s, 1 H), 2.18 - 2.03 (m, 9 H), 1.78 (m, 6 H), 1.29 (s, 9 H). ¹³C NMR (CDCl₃, 100 MHz): δ 148.07, 143.75, 137.00, 126.04, 123.62, 112.11, 40.24, 37.67, 37.01, 34.46, 31.47, 29.03.

[0262] (1-(3-Bromo-5-(*tert*-butyl)-2-(methoxymethoxy)phenyl)adamantine




To a solution of 330 g (910 mmol) of 2-(adamantan-1-yl)-6-bromo-4-(*tert*-butyl)phenol in 3,000 mL of THF 40.0 g (1.00 mol, 60% wt. in mineral oil) of sodium hydride was added portionwise at room temperature. To the resulting suspension 76.0 mL (1.00 mol) of methoxymethyl chloride was added dropwise for 40 minutes at room temperature. The obtained mixture was stirred overnight, then poured into 2,000 mL of water. The desired product was extracted with dichloromethane (3 x 900 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. Yield 367 g (99%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.39 (d, J = 2.4 Hz, 1 H), 7.27 (d, J = 2.4 Hz, 1 H), 5.23 (s, 2 H), 3.71 (s, 3 H), 2.20 - 2.04 (m, 9 H), 1.82 - 1.74 (m, 6 H), 1.29 (s, 9 H). ¹³C NMR (CDCl₃, 100 MHz): δ 150.88, 147.47, 144.42, 128.46, 123.72, 117.46, 99.53, 57.74, 41.31, 38.05, 36.85, 34.58, 31.30, 29.08.

[0263] 2-(3-Adamantan-1-yl)-5-(*tert*-butyl)-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



To a solution of 183.5 g (450 mmol) of 1-(3-bromo-5-(*tert*-butyl)-2-(methoxymethoxy)phenyl)adamantine in 2,500 mL of dry THF 190 mL (473 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred
 5 at this temperature for 1 hour, followed by addition of 120 mL (585 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred for 1 hour at room temperature, then poured into 300 mL of water. The obtained mixture was evaporated to ca. 1 liter, the crude product was extracted with dichloromethane (3 x 800 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. Yield 204.7 g (quant.)
 10 of a colorless solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.54 (d, J = 2.5 Hz, 1 H), 7.43 (d, J = 2.6 Hz, 1 H), 5.18 (s, 2 H), 3.60 (s, 3 H), 2.24 - 2.13 (m, 6 H), 2.09 (br. s., 3 H), 1.85 - 1.75 (m, 6 H), 1.37 (s, 12 H), 1.33 (s, 9 H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.64, 144.48, 140.55, 130.58, 127.47, 100.81, 83.48, 57.63, 41.24, 37.29, 37.05, 34.40, 31.50, 29.16, 24.79.


[0264] 1-(2'-Bromo-5-(*tert*-butyl)-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine
 15



In a 2 l pressure vessel, 150 g (330 mmol) of 2-(3-adamantan-1-yl)-5-(*tert*-butyl)-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane, 1000 mL of dioxane, 93.4 g (330 mmol) of 2-bromiodobenzene, 114 g (825 mmol) of potassium carbonate, and
 20 500 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 19.1 g (17.0 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 115°C, then cooled to room temperature, and diluted with 500 mL of water. The crude product was extracted with dichloromethane (3 x 700 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash
 25 chromatography on silica gel 60 (40-63 um, eluent: hexane-dichloromethane = 10:1, vol.). Yield 112 g (70%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.68 (dd, J = 1.0, 8.0 Hz, 1 H),


7.42 (dd, $J = 1.7, 7.6$ Hz, 1 H), 7.37 - 7.32 (m, 2 H), 7.20 (dt, $J = 1.8, 7.7$ Hz, 1 H), 7.08 (d, $J = 2.5$ Hz, 1 H), 4.53 (d, $J = 4.6$ Hz, 1 H), 4.40 (d, $J = 4.6$ Hz, 1 H), 3.20 (s, 3 H), 2.23 - 2.14 (m, 6 H), 2.10 (br. s., 3 H), 1.86 - 1.70 (m, 6 H), 1.33 (s, 9 H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 151.28, 145.09, 142.09, 141.47, 133.90, 132.93, 132.41, 128.55, 127.06, 126.81, 124.18, 123.87, 98.83, 57.07, 41.31, 37.55, 37.01, 34.60, 31.49, 29.17.

[0265] 2-(3'-(Adamantan-1-yl)-5'-(*tert*-butyl)-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane




To a solution of 223 g (462 mmol) of 1-(2'-bromo-5-(*tert*-butyl)-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine in 3,000 mL of dry THF 194 mL (485 mmol) of 2.5 M $^n\text{BuLi}$ in hexanes was added dropwise for 20 minutes at -80°C . The reaction mixture was stirred at this temperature for 1 hour, followed by addition of 122 mL (600 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 300 mL of water. The obtained mixture was evaporated to ca. 1 liter, the crude product was extracted with dichloromethane (3 x 300 mL), the combined organic extract was dried over Na_2SO_4 , and then evaporated to dryness. Yield 240.9 g (quant.) of a white solid. ^1H NMR (CDCl_3 , 400 MHz): δ 7.75 (d, $J = 7.3$ Hz, 1 H), 7.44 - 7.36 (m, 1 H), 7.36 - 7.30 (m, 2 H), 7.30 - 7.26 (m, 1 H), 6.96 (d, $J = 2.4$ Hz, 1 H), 4.53 (d, $J = 4.7$ Hz, 1 H), 4.37 (d, $J = 4.7$ Hz, 1 H), 3.22 (s, 3 H), 2.26 - 2.14 (m, 6 H), 2.09 (br. s., 3 H), 1.85 - 1.71 (m, 6 H), 1.30 (s, 9 H), 1.15 (s, 6 H), 1.10 (s, 6 H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 151.35, 146.48, 144.32, 141.26, 136.15, 134.38, 130.44, 129.78, 126.75, 126.04, 123.13, 98.60, 83.32, 57.08, 41.50, 37.51, 37.09, 34.49, 31.57, 29.26, 24.92, 24.21.

[0266] 2',2'''-(4-Methoxypyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(*tert*-butyl)-[1,1'-biphenyl]-2-ol)



To a solution of 2.00 g (3.77 mmol) of 2-(3'-(adamantan-1-yl)-5'-(*tert*-butyl)-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of dioxane, 503 mg (1.88 mmol) of 2,6-dibromo-4-methoxypyridine, 3.07 g (9.42 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 min followed by addition of 440 mg (0.380 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 h at 100°C, then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 1.33 g (86%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 8.31 and 7.13 (2s, 2H), 7.37 – 7.60 (m, 8H), 7.09 – 7.11 (m, 2H), 6.55 and 6.98 (2m, 2H), 6.50 and 6.42 (2s, 2H), 3.37 and 3.36 (2s, 3H), 1.87 – 2.00 (m, 18H), 1.60 – 1.69 (m, 12H), 1.21 and 1.00 (2s, 18H). ¹³C NMR (CDCl₃, 100 MHz) δ 165.87, 159.18, 149.98, 141.89, 139.42, 137.80, 137.42, 131.50, 130.81, 129.86, 129.05, 127.75, 126.53, 122.80, 108.97, 55.12, 40.57, 40.32, 37.07, 37.01, 34.02, 31.58, 31.46, 29.11, 29.02.


[0267] 2',2'''-(4-(Trifluoromethyl)pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(*tert*-butyl)-[1,1'-biphenyl]-2-ol)



To a solution of 2.00 g (3.77 mmol) of 2-(3'-(adamantan-1-yl)-5'-(*tert*-butyl)-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of dioxane, 406 mg (1.88 mmol) of 2,6-dichloro-4-trifluoromethylpyridine, 3.07 g (9.42 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 440 mg (0.380 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted

with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 1.31 g (83%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 7.40 – 7.55 (m, 8H), 7.04 – 7.14 + 5.62 (2m, 6H), 6.86 + 6.56 (2d, J = 2.4 Hz, 2H), 1.90 – 2.02 (m, 18H), 1.60 – 1.74 (m, 12H), 1.16 + 1.01 (2s, 18H). ¹³C NMR (CDCl₃, 100 MHz) δ 159.29, 159.09, 149.57, 148.84, 142.43, 142.33, 139.45, 138.78, 138.45, 137.60, 137.22, 136.72, 136.24, 131.62, 131.51, 130.76, 130.52, 129.76, 129.71, 128.53, 128.39, 128.16, 127.42, 126.03, 125.28, 123.46, 123.34, 118.20 (q, J_{C,F} = 3.5 Hz), 40.45, 40.34, 37.07, 37.03, 34.21, 34.06, 31.45, 31.42, 29.11, 29.06.


[0268] (3r,5r,7r)-1-(2'-Bromo-5-(*tert*-butyl)-2-(methoxymethoxy)-4'-methyl-[1,1'-biphenyl]-3-yl)adamantane



To a solution of 10.0 g (22.0 mmol) of 2-(3-adamantan-1-yl)-5-(*tert*-butyl)-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 100 mL of 1,4-dioxane 6.83 g (23.0 mmol) of 2-bromo-4-methyliodobenzene, 7.60 g (55.0 mmol) of potassium carbonate, and 50 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 1.27 g (1.10 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 100 mL of water. The crude product was extracted with dichloromethane (3 x 150 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-dichloromethane = 10:1, vol.). Yield 8.77 g (80%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.56 (m, 1H), 7.32 – 7.39 (m, 2H), 7.19 (d, J = 7.8 Hz, 1H), 7.11 (d, J = 2.5 Hz, 1H), 4.59 (m, 1H), 4.47 (m, 1H), 3.29 (s, 3H), 2.41 (s, 3H), 2.25 (m, 6H), 2.15 (m, 3H), 1.84 (m, 6H), 1.37 (s, 9H).

^{13}C NMR (CDCl_3 , 100 MHz): δ 151.48, 144.93, 141.94, 138.66, 138.46, 133.66, 133.32, 132.02, 127.90, 127.02, 123.82, 123.66, 98.75, 57.09, 41.30, 37.53, 37.04, 34.56, 31.48, 29.19, 20.76.

[0269] 4-((3*r*,5*r*,7*r*)-Adamantan-1-yl)-2-(*tert*-butyl)-6-isopropoxy-8-methyl-6*H*-dibenzo[*c,e*][1,2]oxaborinine




5

To a solution of 8.75 g (17.6 mmol) of (3*r*,5*r*,7*r*)-1-(2'-bromo-5-(*tert*-butyl)-2-(methoxymethoxy)-4'-methyl-[1,1'-biphenyl]-3-yl)adamantane in 120 mL of dry THF 8.44 mL (21.1 mmol) of 2.5 M $^n\text{BuLi}$ in hexanes was added dropwise for 20 minutes at -80°C . The reaction mixture was stirred for 1 hour at this temperature followed by addition of 6.12 mL (30.0 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 300 mL of water. The crude product was extracted with dichloromethane (3 x 300 mL), the combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. The residue was recrystallized from 20 mL of hot isopropanol, the obtained crystalline material was filtered off (G3), washed with 5 mL of cold isopropanol, and dried in vacuo. Yield 4.90 g (51%) of a white crystals. ^1H NMR (CDCl_3 , 400 MHz): δ 8.07 (d, J = 8.3 Hz, 1H), 8.03 (d, J = 2.0 Hz, 1H), 7.87 (m, 1H), 7.46 (d, J = 8.2 Hz, 1H), 7.40 (d, J = 2.0 Hz, 1H), 5.25 (sept, J = 6.1 Hz, 1H), 2.46 (s, 3H), 2.30 (m, 6H), 2.16 (m, 3H), 1.85 (m, 6H), 1.42 (s, 9H), 1.42 (d, J = 6.0 Hz, 6H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 147.99, 143.84, 138.75, 138.38, 136.14, 133.08, 132.97, 123.55, 122.32, 121.59, 117.90, 65.66, 40.77, 37.45, 37.19, 34.75, 31.67, 29.17, 24.74, 21.21.

10
15
20

[0270] 2',2'''-(Pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(*tert*-butyl)-4'-methyl-[1,1'-biphenyl]-2-ol)




To a solution of 1.60 g (3.62 mmol) of 4-((3*r*,5*r*,7*r*)-adamantan-1-yl)-2-(*tert*-butyl)-6-isopropoxy-8-methyl-6*H*-dibenzo[*c,e*][1,2]oxaborinine in 40 mL of 1,4-dioxane, 429 mg

25

(1.81 mmol) of 2,6-dibromopyridine, 2.95 g (9.10 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 210 mg (0.180 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. The crude product was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 1.11 g (74%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 8.15 + 6.81 (2s, 2H), 7.31 – 7.40 (m, 3H), 7.21 – 7.24 (m, 2H), 6.90 – 7.03 + 6.49 (2m, 6H), 2.42 + 2.41 (2s, 6H), 1.73 – 2.06 (m, 18H), 1.60 – 1.67 (m, 12H), 1.13 + 0.97 (2s, 18H). ¹³C NMR (CDCl₃, 100 MHz) δ 157.96, 157.77, 150.22, 149.45, 141.67, 139.30, 137.45, 137.40, 136.71, 135.04, 131.60, 131.43, 130.82, 129.84, 129.64, 126.50, 125.77, 122.58, 122.42, 40.52, 40.39, 37.11, 37.03, 36.85, 33.99, 31.48, 29.19, 29.11, 21.14.


[0271] 2',2'''-(4-(Trifluoromethyl)pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(*tert*-butyl)-4'-methyl-[1,1'-biphenyl]-2-ol)



To a solution of 1.60 g (3.62 mmol) of 4-((3*r*,5*r*,7*r*)-adamantan-1-yl)-2-(*tert*-butyl)-6-isopropoxy-8-methyl-6*H*-dibenzo[*c,e*][1,2]oxaborinine in 40 mL of 1,4-dioxane, 391 mg (1.81 mmol) of 2,6-dichloro-4-trifluoromethylpyridine, 2.95 g (9.10 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 210 mg (0.180 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. The crude product was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 1.01 g (62%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 7.44 and 5.97 (2s, 2H), 7.34 – 7.38 (m, 6H), 7.12 (d, *J* = 2.4 Hz, 2H), 7.07 (s, 2H), 6.92 and 6.56 (2m, 2H), 2.49 and 2.48 (2s, 6H), 1.85 – 2.04 (m, 18H), 1.65 – 1.75 (m, 12H), 1.18 and 1.03 (s, 18H). ¹³C NMR (CDCl₃, 100 MHz) δ 159.41, 159.19, 149.81, 149.80, 149.05, 142.20, 142.16,


139.08, 138.70, 138.57, 138.37, 138.10, 138.01, 137.26, 136.25, 134.77, 134.03, 131.51, 131.27, 130.91, 130.49, 130.41, 128.66, 127.64, 126.17, 125.43, 123.69, 123.31, 123.12, 118.23 (q, $J_{C,F}$ = 3.8 Hz), 117.88 (q, $J_{C,F}$ = 3.8 Hz), 40.47, 40.34, 37.08, 37.06, 34.02, 31.42, 29.17, 29.08, 26.91, 21.14.

- 5 **[0272] 2',2'''-(4-Methoxypyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(*tert*-butyl)-4'-methyl-[1,1'-biphenyl]-2-ol)**




To a solution of 1.60 g (3.62 mmol) of 4-((3*r*,5*r*,7*r*)-adamantan-1-yl)-2-(*tert*-butyl)-6-isopropoxy-8-methyl-6*H*-dibenzo[*c,e*][1,2]oxaborinine in 40 mL of 1,4-dioxane, 483 mg
 10 (1.81 mmol) of 2,6-dibromo-4-methoxypyridine, 2.95 g (9.10 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 210 mg (0.180 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. The crude product was extracted with dichloromethane (3 x 50 mL), the combined organic extract
 15 was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μm, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 910 mg (58%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 8.39 + 6.52 (2s, 2H), 7.25 – 7.45 (m, 7H), 7.00 – 7.12 (m, 2H), 6.42 – 6.56 (m, 3H), 3.41 + 3.38 (2s, 3H), 2.47 (s, 6H), 1.87 – 2.02 (m, 18H), 1.62 – 1.75 (m, 12H), 1.24 + 1.02 (2s, 18H).
 20 ¹³C NMR (CDCl₃, 100 MHz) δ 165.79, 159.28, 159.22, 150.13, 149.66, 141.90, 141.78, 139.28, 138.72, 137.54, 137.36, 136.77, 134.89, 134.80, 132.26, 131.39, 131.37, 130.94, 130.08, 129.87, 129.75, 129.34, 126.60, 125.60, 123.01, 122.58, 108.92, 108.34, 55.09, 54.73, 40.61, 40.35, 37.08, 37.07, 36.87, 34.22, 33.99, 31.56, 31.46, 29.19, 29.07, 26.90, 22.65, 21.15.

- 25 **[0273] (3*r*,5*r*,7*r*)-1-(2'-Bromo-5-(*tert*-butyl)-4'-isopropyl-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine**



To a solution of 10.0 g (22.0 mmol) of 2-(3-(adamantan-1-yl)-5-(*tert*-butyl)-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 100 mL of 1,4-dioxane 6.83 g (23.0 mmol) of 2-bromo-4-isopropyl iodobenzene, 7.60 g (55.0 mmol) of potassium carbonate, and 50 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 1.27 g (1.10 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 100 mL of water. The crude product was extracted with dichloromethane (3 x 150 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-dichloromethane = 10:1, vol.). Yield 11.5 g (95%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.53 (d, J = 1.7 Hz, 1H), 7.30 – 7.33 (m, 2H), 7.19 (dd, J = 8.0, 1.7 Hz, 1H), 7.08 (d, J = 2.5 Hz, 1H), 4.52 (m, 1H), 4.39 (m, 1H), 3.18 (s, 3H), 2.92 (sept, J = 6.9 Hz, 1H), 2.14 – 2.20 (m, 6H), 2.10 (br.s, 3H), 1.74 – 1.84 (m, 6H), 1.32 (s, 9H), 1.28 (d, J = 6.9 Hz, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 151.35, 149.85, 145.03, 142.04, 138.73, 133.91, 132.21, 130.79, 126.96, 125.33, 124.02, 123.71, 98.76, 57.03, 41.35, 37.57, 37.04, 33.63, 31.50, 29.20, 24.83, 23.90.


[0274] 2-(3'-((3r,5r,7r)-Adamantan-1-yl)-5'-(*tert*-butyl)-4-isopropyl-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



To a solution of 11.3 g (21.5 mmol) of (3r,5r,7r)-1-(2'-bromo-5-(*tert*-butyl)-4'-isopropyl-2'-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine in 200 mL of dry THF 9.00 mL (22.6 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred at this temperature for 1 hour, followed by an addition of 6.98 mL (32.2 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 100 mL of water. The obtained mixture was evaporated to ca. 150 mL, then the crude product was extracted with

dichloromethane (3 x 100 mL). The combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-diethyl ether = 10:1, vol.). Yield 6.80 g (56%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.57 (s, 1H), 7.24 – 7.28 (m, 3H), 6.97 (d, J = 2.4 Hz, 1H), 4.52 (m, 1H), 4.37 (m, 1H), 3.20 (s, 3H), 2.95 (sept, J = 6.9 Hz, 1H), 2.17 – 2.21 (m, 6H), 2.09 (br.s, 3H), 1.73 – 1.84 (m, 6H), 1.29 (s, 9H), 1.28 (d, J = 6.9 Hz, 6H), 1.15 (s, 6H), 1.10 (s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 151.43, 146.50, 144.22, 143.92, 141.17, 136.17, 132.40, 130.45, 127.73, 126.84, 122.94, 98.52, 83.26, 57.06, 41.50, 37.49, 37.10, 34.48, 33.86, 31.58, 29.26, 24.94, 24.41, 24.13, 24.07.


10 **[0275] 2',2'''-(Pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(*tert*-butyl)-4'-isopropyl-[1,1'-biphenyl]-2-ol)**



To a solution of 3.20 g (5.66 mmol) of 2-(3'-(adamantan-1-yl)-5'-(*tert*-butyl)-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of 1,4-dioxane, 609 mg (2.83 mmol) of 2,6-dibromopyridine, 5.00 g (14.2 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 300 mg (0.260 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 1.34 g (54%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 8.26 + 6.83 (2s, 2H), 6.95 – 7.58 + 6.52 (2m, 13H), 3.01 (sept, J = 6.9 Hz, 2H), 1.85 – 2.02 (m, 18H), 1.62 – 1.68 (m, 12H), 1.33 (d, J = 6.9 Hz, 6H), 1.32 (d, J = 6.9 Hz, 6H), 1.13 + 1.00 (2s, 18H). ¹³C NMR (CDCl₃, 100 MHz) δ 158.28, 157.98, 150.28, 149.48, 148.14,


148.02, 141.61, 141.46, 139.28, 137.50, 136.74, 136.20, 135.43, 135.13, 132.10, 131.67, 130.07, 129.29, 128.97, 128.07, 127.18, 126.90, 126.58, 125.77, 122.74, 122.50, 122.44, 122.20, 40.51, 40.30, 37.08, 37.05, 36.81, 34.17, 34.00, 33.84, 33.78, 31.50, 31.40, 29.15, 29.10, 24.14, 23.81.

[0276] **2',2'''-(4-(Trifluoromethyl)pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(*tert*-butyl)-4'-isopropyl-[1,1'-biphenyl]-2-ol)**




To a solution of 1.77 g (3.09 mmol) of 2-(3'-(adamantan-1-yl)-5'-(*tert*-butyl)-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of dioxane, 325 mg (1.51 mmol) of 2,6-dichloro-4-trifluoromethylpyridine, 3.00 g (9.04 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 200 mg (0.190 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μm, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 1.17 g (82%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 7.35 – 7.46 and 5.99 (2m, 8H), 7.06 – 7.13 (m, 4H), 6.95 and 6.56 (2m, 2H), 3.05 (sept, J = 6.9 Hz, 2H), 1.86 – 2.04 (m, 18H), 1.63 – 1.71 (m, 12H), 1.36 (d, J = 6.9 Hz, 6H), 1.34 (d, J = 6.9 Hz, 6H), 1.15 and 1.01 (2s, 18H). ¹³C NMR (CDCl₃, 100 MHz) δ 159.68, 149.86, 149.11, 148.81, 142.12, 138.59, 137.29, 136.18, 135.10, 131.67, 131.57, 128.98, 128.81, 127.66, 126.29, 125.43, 123.10, 118.27 (q, J_{C,F} = 3.5 Hz), 40.48, 40.28, 37.06, 36.87, 34.02, 33.84, 31.43, 31.39, 29.12, 29.07, 24.07, 23.86.

[0277] **2',2'''-(4-Methoxypyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(*tert*-butyl)-4'-isopropyl-[1,1'-biphenyl]-2-ol)**



To a solution of 1.77 g (3.09 mmol) of 2-(3'-(adamantan-1-yl)-5'-(*tert*-butyl)-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of dioxane, 400 mg (1.51 mmol) of 2,6-dibromo-4-methoxypyridine, 3.00 g (9.04 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 200 mg (0.190 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 1.01 g (74%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 8.40 and 7.02 (2s, 2H), 7.23 – 7.44 (m, 6H), 7.07 (m, 2H), 6.56 – 6.58 (m, 2H), 6.41 (m, 2H), 3.50 and 3.37 (2s, 3H), 3.02 (sept, J = 6.9 Hz, 2H), 1.85 – 2.02 (m, 18H), 1.62 – 1.70 (m, 12H), 1.34 (d, J = 6.9 Hz, 12H), 1.19 + 1.00 (2s, 18H). ¹³C NMR (CDCl₃, 100 MHz) δ 165.74, 159.62, 150.20, 148.30, 141.73, 139.35, 137.37, 135.18, 131.38, 129.99, 129.03, 127.34, 127.03, 126.71, 125.71, 122.56, 108.94, 55.12, 40.61, 37.08, 37.06, 34.01, 33.76, 31.48, 29.13, 24.12, 23.83.


[0278] 2-(Adamantan-1-yl)-4-fluorophenol



To a solution of 30.0 g (268 mmol) of 4-fluorophenol and 40.8 g (268 mmol) of adamantan-1-ol in 300 mL of dichloromethane a solution of 17.4 mL (268 mmol) of methanesulfonic acid and 20 mL of acetic acid in 100 mL of dichloromethane was added dropwise for 1 hour at room


temperature. The resulting mixture was stirred for 48 hours at room temperature and then carefully poured into 300 mL of 5% NaHCO₃. The crude product was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified using Kugelrohr apparatus (0.3 mbar, 95°C) yielding 49.3 g (75%) of the title product as a light-yellow oil. ¹H NMR (CDCl₃, 400 MHz): δ 6.92 (dd, J = 11.2, 3.1 Hz, 1H), 6.73 (ddd, J = 8.7, 7.4, 3.1 Hz, 1H), 6.60 (dd, J = 8.7, 5.0 Hz, 1H), 4.34 (br.s, 1H), 2.08 – 2.11 (m, 9H), 1.75 – 1.80 (m, 9H), 1.58 – 1.67 (m, 3H), ¹³C NMR (CDCl₃, 100 MHz): δ 158.28 (d, J_{C,F} = 236 Hz), 150.60 (d, J_{C,F} = 2.0 Hz), 138.27 (d, J_{C,F} = 5.9 Hz), 117.07 (d, J_{C,F} = 8.1 Hz), 113.88 (d, J_{C,F} = 23.9 Hz), 112.36 (d, J_{C,F} = 23.0 Hz), 45.05, 40.13, 36.88, 35.90, 30.65, 28.88.

[0279] 2-Bromo-6-(adamantan-1-yl)-4-fluorophenol



To a solution of 49.3 g (200 mmol) of 2-(adamantan-1-yl)-4-fluorophenol in 500 mL of dichloromethane a solution of 10.3 mL (200 mmol) of bromine in 100 mL of dichloromethane was added dropwise for 1 hour at room temperature. The resulting mixture was stirred for 48 hours at room temperature and then carefully poured into 200 mL of 5% NaHCO₃. The crude product was extracted with dichloromethane (3 x 150 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. Yield 65.0 g (quant.) of a light-yellow solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.07 (dd, J = 7.0, 3.0 Hz, 1H), 6.92 (dd, J = 10.8, 3.0 Hz, 1H), 5.60 (s, 1H), 2.07 (br.s, 9H), 1.77 (br.s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 157.21 (d, J_{C,F} = 241 Hz), 147.03 (d, J_{C,F} = 3.0 Hz), 138.91 (d, J_{C,F} = 5.9 Hz), 115.66 (d, J_{C,F} = 25.8 Hz), 113.97 (d, J_{C,F} = 23.6 Hz), 111.21 (d, J_{C,F} = 10.9 Hz), 39.88, 37.60, 36.82, 28.86.


[0280] (3r,5r,7r)-1-(3-Bromo-5-fluoro-2-(methoxymethoxy)phenyl)adamantine



To a solution of 48.4 g (150 mmol) of 2-bromo-6-(adamantan-1-yl)-4-fluorophenol in 500 mL of dry THF 6.30 g (155 mmol, 60% wt. in mineral oil) of sodium hydride was added portionwise at room temperature. After that, 13.7 mL (180 mmol) of MOMCl was added dropwise for 1 hour. The reaction mixture was heated for 24 hours at 60°C and then poured into 300 mL of

cold water. The crude product was extracted with 3 x 200 mL of dichloromethane. The combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. Yield 56.0 g (quant.) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.12 (dd, J = 6.9, 3.1 Hz, 1H), 6.98 (dd, J = 10.9, 3.1 Hz, 1H), 5.20 (s, 2H), 3.69 (s, 3H), 2.07 (br.s, 9H), 1.76 (br.s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.51 (d, $J_{C,F}$ = 245 Hz), 149.86 (d, $J_{C,F}$ = 3.3 Hz), 146.93 (d, $J_{C,F}$ = 6.5 Hz), 118.09 (d, $J_{C,F}$ = 25.4 Hz), 117.67 (d, $J_{C,F}$ = 10.5 Hz), 113.99 (d, $J_{C,F}$ = 23.6 Hz), 99.72, 57.83, 40.99, 38.06, 36.67, 28.92.


[0281] 2-((3r,5r,7r)-3-Adamantan-1-yl)-5-fluoro-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



10


To a solution of 28.0 g (75.8 mmol) of (1-(3-bromo-5-fluoro-2-(methoxymethoxy)phenyl)adamantine in 400 mL of dry THF 30.3 mL (75.8 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred for 1 hour at this temperature followed by addition of 20.1 mL (98.5 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred for 1 hour at room temperature, then poured into 300 mL of water. The crude product was extracted with dichloromethane (3 x 300 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was recrystallized from isopropanol. Yield 27.8 g (88%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.19 (dd, J = 7.7, 3.3 Hz, 1H), 7.06 (dd, J = 10.9, 3.3 Hz, 1H), 5.12 (s, 2H), 3.57 (s, 3H), 2.10 (br.s, 6H), 2.06 (br.s, 3H), 1.75 (br.s, 6H), 1.34 (s, 12H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.46 (d, $J_{C,F}$ = 241 Hz), 157.48 (d, $J_{C,F}$ = 2.0 Hz), 144.23 (d, $J_{C,F}$ = 5.7 Hz), 119.42 (d, $J_{C,F}$ = 21.0 Hz), 117.35 (d, $J_{C,F}$ = 24.0 Hz), 100.98, 83.96, 57.73, 40.97, 37.29, 36.87, 28.99, 24.79.

[0282] (3r,5r,7r)-1-(2'-Bromo-5-fluoro-4'-isopropyl-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine



To a solution of 8.00 g (19.21 mmol) of 2-((3*r*,5*r*,7*r*)-3-adamantan-1-yl)-5-fluoro-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 60 mL of 1,4-dioxane 6.24 g (19.2 mmol) of 2-bromo-4-isopropylidobenzene, 6.63 g (48.0 mmol) of potassium carbonate, and 50 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 1.10 g (0.96 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 100 mL of water. The crude product was extracted with dichloromethane (3 x 150 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-dichloromethane = 10:1, vol.). Yield 4.70 g (50%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.53 (d, J = 1.6 Hz, 1H), 7.27 (d, J = 7.9 Hz, 1H), 7.20 (dd, J = 7.9, 1.6 Hz, 1H), 7.03 (dd, J = 11.0, 3.2 Hz, 1H), 6.79 (dd, J = 7.9, 3.2 Hz, 1H), 4.48 (m, 1H), 4.40 (m, 1H), 3.16 (s, 3H), 2.93 (sept, J = 6.9 Hz, 1H), 2.13 (br.s, 6H), 2.10 (br.s, 3H), 1.78 (br.s, 6H), 1.28 (d, J = 6.9 Hz, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.33 (d, J_{C,F} = 240 Hz), 150.47, 145.50 (d, J_{C,F} = 5.9 Hz), 137.28, 136.00 (d, J_{C,F} = 8.8 Hz), 131.87, 130.86, 125.47, 123.65, 115.67 (d, J_{C,F} = 23.6 Hz), 113.95 (d, J_{C,F} = 23.6 Hz), 98.98, 57.03, 41.03, 37.57, 36.85, 33.66, 29.03, 23.84.


[0283] 2-(3'-((3*r*,5*r*,7*r*)-Adamantan-1-yl)-5'-fluoro-4'-isopropyl-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



To a solution of 4.70 g (9.64 mmol) of (3*r*,5*r*,7*r*)-1-(2'-(2-bromo-5-fluoro-4'-isopropyl-2'-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)adamantine in 100 mL of dry THF 3.86 mL (9.64 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred for 1 hour at this temperature followed by addition of 2.33 mL (12.5 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 300 mL of water. The crude product was extracted with dichloromethane (3 x 300 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-diethyl ether = 10:1, vol.). Yield 5.10 g (99%) of a colorless glassy solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.59 (d, J = 1.9 Hz), 7.29 (dd, J = 7.9, 1.9 Hz, 1H), 7.24 (d, J = 7.9 Hz), 6.95 (dd, J = 11.2, 3.2 Hz, 1H), 6.71 (dd, J = 8.0, 3.2 Hz, 1H), 4.30

– 4.42 (m, 2H), 3.20 (s, 3H), 2.95 (sept, $J = 6.9$ Hz, 1H), 2.14 (br.s, 6H), 2.08 (br.s, 6H), 1.74 – 1.80 (m, 6H), 1.28 (d, $J = 6.9$ Hz, 6H), 1.17 (br.s, 12H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 159.31 (d, $J_{\text{C,F}} = 240$ Hz), 149.77 (d, $J_{\text{C,F}} = 2.4$ Hz), 147.17, 144.55 (d, $J_{\text{C,F}} = 6.6$ Hz), 142.17, 138.49 (d, $J_{\text{C,F}} = 8.1$ Hz), 132.80, 130.14, 128.01, 115.90 (d, $J_{\text{C,F}} = 22.5$ Hz), 112.61 (d, $J_{\text{C,F}} = 23.6$ Hz), 98.69, 83.48, 57.23, 41.26, 37.52, 36.91, 33.86, 29.09, 25.07 (broad), 24.26 (broad), 24.04.


[0284] 2',2'''-(4-Methoxypyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-fluoro-4'-isopropyl-[1,1'-biphenyl]-2-ol)



- 10 To a solution of 2.00 g (3.74 mmol) of 2-(3'-((3r,5r,7r)-adamantan-1-yl)-5'-fluoro-4-isopropyl-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of 1,4-dioxane, 500 mg (1.87 mmol) of 2,6-dibromo-4-methoxypyridine, 3.04 g (9.35 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 216 mg (0.187 mmol) of $\text{Pd}(\text{PPh}_3)_4$.
- 15 This mixture was stirred for 12 hours at 100°C , then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The
- 20 crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO_3 , dried over Na_2SO_4 , and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μm , eluent: hexane-ethyl acetate = 10:1, vol.). Yield 1.31 g (83%) of a mixture of two isomers as a white foam. ^1H NMR (CDCl_3 , 400 MHz): δ 7.95 (s, 1H), 7.20 – 7.46 (m, 8H), 6.73 – 6.84 and 6.06 – 6.09 (2m, 3H), 6.59 and 6.51 (2s, 2H), 3.63 and 3.46 (2s, 3H), 2.95 – 3.10 (2sept, 2H), 1.57 – 2.15 (m, 30H), 1.28 – 1.37 (m, 12H). ^{13}C NMR (CDCl_3 , 100 MHz) δ 166.41, 166.10, 159.62, 159.46, 157.73 (d, $J_{\text{C,F}} = 237$ Hz), 157.62 (d, $J_{\text{C,F}} = 237$ Hz), 148.99, 148.74, 148.66, 148.29, 139.95, 139.89, 139.39, 138.30, 133.96, 131.90, 131.14, 129.34, 128.13, 128.03, 127.84, 127.59, 127.03, 114.54 (d, $J_{\text{C,F}} = 22.7$ Hz), 114.19 (d, $J_{\text{C,F}} = 22.9$ Hz), 113.01 (d, $J_{\text{C,F}} = 23.2$ Hz), 112.70 (d, $J_{\text{C,F}} = 24.1$ Hz), 108.57,


108.45, 55.25, 54.97, 40.16, 39.96, 37.00, 36.93, 36.89, 36.83, 36.68, 33.83, 33.65, 28.99, 28.90, 23.99, 23.93, 23.76.

[0285] 2-(3,5-Dimethyladamantan-1-yl)-4-fluorophenol



- 5 To a solution of 8.40 g (75.0 mmol) of 4-fluorophenol and 13.5 g (75.0 mmol) of 3,5-dimethyladamantan-1-ol in 150 mL of dichloromethane a solution of 4.90 mL (75.0 mmol) of methanesulfonic acid and 5 mL of acetic acid in 100 mL of dichloromethane was added dropwise for 1 hour at room temperature. The resulting mixture was stirred for 48 hours at room temperature and then carefully poured into 300 mL of 5% NaHCO₃. The crude product was
- 10 extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified using Kugelrohr apparatus (1 mbar, 70°C) yielding 14.2 g (68%) of the title product as a light-yellow oil. ¹H NMR (CDCl₃, 400 MHz): δ 6.93 (dd, J = 3.1, 11.2 Hz, 1H), 6.73 (ddd, J = 3.1, 7.4, 8.6 Hz, 1H), 6.55 (dd, J = 4.9, 8.6 Hz, 1H), 4.62 (s, 1H), 2.16 (dt, J = 3.1, 6.3 Hz, 1H), 1.91 (m, 2H), 1.64 – 1.74
- 15 (m, 4H), 1.35 – 1.45 (m, 4H), 1.20 (br.s, 2H), 0.87 (s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 158.49 (J_F = 236 Hz), 150.19 (J_F = 2.0 Hz), 137.69 (J_F = 5.9 Hz), 117.12 (J_F = 8.1 Hz), 114.13 (J_F = 24.0 Hz), 112.57 (J_F = 22.9 Hz), 50.92, 46.44, 43.05, 38.70, 38.48, 31.38, 30.84, 29.90.


[0286] 2-Bromo-6-(3,5-dimethyladamantan-1-yl)-4-fluorophenol



- 20 To a solution of 14.2 g (51.7 mmol) of 2-(3,5-dimethyladamantan-1-yl)-4-fluorophenol in 200 mL of dichloromethane a solution of 2.67 mL (51.7 mmol) of bromine in 100 mL of dichloromethane was added dropwise for 1 hour at room temperature. The resulting mixture was stirred for 48 hours at room temperature and then carefully poured into 200 mL of 5% NaHCO₃. The crude product was extracted with dichloromethane (3 x 50 mL), the combined
- 25 organic extract was dried over Na₂SO₄ and then evaporated to dryness. Yield 17.5 g (96%) of a light-yellow solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.06 (dd, J = 3.0, 7.0 Hz, 1H), 6.93 (dd, J = 2.9, 10.8 Hz, 1H), 5.59 (s, 1H), 2.16 (m, 1H), 1.89 (br.s, 2H), 1.63 – 1.73 (m, 4H), 1.34 – 1.44 (m, 4H), 1.19 (br.s, 2H), 0.86 (s, 6H). ¹³C NMR (CDCl₃, 100 MHz): δ 157.21


($J_F = 241$ Hz), 146.61 ($J_F = 2.8$ Hz), 137.97 ($J_F = 6.1$ Hz), 115.34 ($J_F = 25.8$ Hz), 113.64 ($J_F = 23.6$ Hz), 110.83 ($J_F = 10.9$ Hz), 54.77, 50.48, 45.71, 42.61, 38.96, 38.03, 31.02, 30.42, 29.49.

[0287] 1-(3-Bromo-5-fluoro-2-(methoxymethoxy)phenyl)-3,5-dimethyladamantane



- 5 To a solution of 17.5 g (49.5 mmol) of 2-bromo-6-(3,5-dimethyladamantan-1-yl)-4-fluorophenol in 200 mL of dry THF 2.17 g (54.4 mmol, 60% wt. in mineral oil) of sodium hydride was added portionwise at room temperature. After that, 4.53 mL (60.0 mmol) of MOMCl was added dropwise for 1 hour. The reaction mixture was heated for 24 hours at 60°C and then poured into 300 mL of cold water. The crude product was extracted with 3 x 200 mL of dichloromethane.
- 10 The combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. Yield 19.6 g (quant.) of a white solid. ^1H NMR (CDCl_3 , 400 MHz): δ 7.13 (dd, $J = 3.1, 6.8$ Hz, 1H), 6.98 (dd, $J = 3.1, 10.9$ Hz, 1H), 5.19 (s, 2H), 3.68 (s, 3H), 2.16 (m, 1H), 1.89 (br.s, 2H), 1.64 – 1.74 (m, 4H), 1.34 – 1.44 (m, 4H), 1.19 (br.s, 2H), 0.87 (s, 6H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 159.47 ($J_F = 245$ Hz), 150.08 ($J_F = 3.3$ Hz), 146.34 ($J_F = 6.4$ Hz), 118.13 ($J_F = 25.4$ Hz),
- 15 117.65 ($J_F = 10.7$ Hz), 114.01 ($J_F = 23.4$ Hz), 99.95, 57.89, 50.69, 47.13, 42.84, 39.78, 39.55, 31.50, 30.84, 29.94.


[0288] 2-(3-((1r,3R,5S,7r)-3,5-dimethyladamantan-1-yl)-5-fluoro-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



- 20 To a solution of 14.0 g (35.3 mmol) of 1-(3-bromo-5-fluoro-2-(methoxymethoxy)phenyl)-3,5-dimethyladamantane in 250 mL of dry THF 16.9 mL (42.3 mmol) of 2.5 M $n\text{BuLi}$ in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred at this temperature for 1 hour followed by addition of 11.0 mL (52.9 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred for 1 hour at room
- 25 temperature, then poured into 300 mL of water. The crude product was extracted with dichloromethane (3 x 100 mL), the combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. The residue was recrystallized from isopropanol. Yield 9.65 g (62%) of


a white solid. ^1H NMR (CDCl_3 , 400 MHz): δ 7.19 (dd, $J = 7.7, 3.3$ Hz, 1H), 7.08 (dd, $J = 11.0, 3.3$ Hz, 1H), 5.11 (s, 2H), 3.57 (s, 3H), 2.13 – 2.16 (m, 1H), 1.92 (br.s, 2H), 1.66 – 1.77 (m, 4H), 1.34 (s, 12H), 1.33 – 1.44 (m, 4H), 1.18 (br.s, 2H), 0.85 (s, 6H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 159.41 (d, $J_{\text{C,F}} = 240$ Hz), 157.64, 143.65 (d, $J_{\text{C,F}} = 5.5$ Hz), 119.53 (d, $J_{\text{C,F}} = 21.0$ Hz), 117.42 (d, $J_{\text{C,F}} = 24.0$ Hz), 101.19, 84.00, 57.86, 50.91, 47.15, 43.03, 39.51, 39.03, 31.48, 30.90, 30.00, 24.78.

[0289] (1r,3R,5S,7r)-1-(2'-Bromo-5-fluoro-4'-isopropyl-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)-3,5-dimethyladamantane




To a solution of 4.02 g (9.09 mmol) of 2-((3r,5r,7r)-3-adamantan-1-yl)-5-fluoro-2-(methoxymethoxy)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 20 mL of 1,4-dioxane 3.55 g (10.9 mmol) of 2-bromo-4-isopropylidobenzene, 7.40 g (22.7 mmol) of caesium carbonate, and 10 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 525 mg (0.48 mmol) of $\text{Pd}(\text{PPh}_3)_4$. This mixture was stirred for 12 hours at 100°C , then cooled to room temperature, and diluted with 100 mL of water. The crude product was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na_2SO_4 and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μm , eluent: hexane-dichloromethane = 10:1, vol.). Yield 4.00 g (86%) of a white solid. ^1H NMR (CDCl_3 , 400 MHz): δ 7.52 (d, $J = 1.5$ Hz, 1H), 7.26 (d, $J = 7.7$ Hz, 1H), 7.20 (dd, $J = 7.8, 1.6$ Hz, 1H), 7.03 (dd, $J = 11.1, 3.2$ Hz, 1H), 6.78 (dd, $J = 7.9, 3.2$ Hz, 1H), 4.47 (m, 1H), 4.36 (m, 1H), 3.18 (s, 3H), 2.92 (sept, $J = 6.9$ Hz, 1H), 2.15 – 2.20 (m, 1H), 1.92 – 1.99 (m, 2H), 1.77 – 1.83 (m, 2H), 1.65 – 1.71 (m, 2H), 1.34 – 1.47 (m, 4H), 1.27 (d, $J = 6.9$ Hz, 6H), 1.20 (br.s, 2H), 0.88 (s, 6H). ^{13}C NMR (CDCl_3 , 100 MHz): δ 159.24 (d, $J_{\text{C,F}} = 240$ Hz), 150.45, 150.18 (d, $J_{\text{C,F}} = 2.6$ Hz), 144.82 (d, $J_{\text{C,F}} = 6.5$ Hz), 137.25, 135.86 (d, $J_{\text{C,F}} = 8.7$ Hz), 131.90, 130.88, 125.50, 123.59, 115.76 (d, $J_{\text{C,F}} = 22.9$ Hz), 113.96 (d, $J_{\text{C,F}} = 23.8$ Hz), 99.13, 57.10, 50.89, 47.25, 47.20, 43.01, 39.47, 39.28, 33.65, 31.50, 30.95, 30.02, 23.86, 23.84.

[0290] 2-(3'-((1r,3R,5S,7r)-3,5-Dimethyladamantan-1-yl)-5'-fluoro-4-isopropyl-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



To a solution of 4.00 g (7.76 mmol) of (1r,3R,5S,7r)-1-(2'-bromo-5-fluoro-4'-isopropyl-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)-3,5-dimethyladamantane in 50 mL of dry THF 3.17 mL (7.91 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred for 1 hour at this temperature followed by an addition of 2.35 mL (11.6 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred at room temperature for 1 hour, then poured into 300 mL of water. The crude product was extracted with dichloromethane (3 x 100 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 um, eluent: hexane-diethyl ether = 10:1, vol.). Yield 3.97 g (91%) of a colorless glassy solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.59 (d, J = 1.8 Hz, 1H), 7.29 (dd, J = 7.9, 1.9 Hz, 1H), 7.24 (d, J = 7.9 Hz, 1H), 6.95 (dd, J = 11.2, 3.2 Hz, 1H), 6.72 (dd, J = 8.1, 3.2 Hz, 1H), 4.34 (s, 2H), 3.22 (s, 3H), 2.95 (sept, J = 6.9 Hz, 1H), 2.14- 2.19 (m, 1H), 1.72 – 1.98 (m, 6H), 1.31 – 1.45 (m, 4H), 1.28 (d, J = 6.9 Hz, 6H), 1.13 – 1.22 (m, 14H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.29 (d, J_{C,F} = 240 Hz), 150.01 (d, J_{C,F} = 2.6 Hz), 147.15, 143.88 (d, J_{C,F} = 6.5 Hz), 142.10 (d, J_{C,F} = 1.7 Hz), 132.85, 130.16, 128.06, 115.85 (d, J_{C,F} = 22.7 Hz), 112.63 (d, J_{C,F} = 23.6 Hz), 98.83, 83.46, 57.24, 50.90, 47.44 (broad), 43.04, 39.69, 39.20, 33.85, 31.52, 30.94, 30.08, 25.20 (broad), 24.17 (broad), 24.04.


[0291] 2',2'''-(Pyridine-2,6-diyl)bis(3-((1r,3R,5S,7r)-3,5-dimethyladamantan-1-yl)-5-fluoro-4'-isopropyl-[1,1'-biphenyl]-2-ol)



To a solution of 3.97 g (7.76 mmol) of 2-(3'-((1r,3R,5S,7r)-3,5-dimethyladamantan-1-yl)-5'-fluoro-4-isopropyl-2'-(methoxymethoxy)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 40 mL of 1,4-dioxane, 880 mg (3.72 mmol) of 2,6-dibromopyridine, 6.40 g (19.4 mmol) of cesium carbonate, and 20 mL of water were subsequently added. The mixture

obtained was purged with argon for 10 minutes followed by addition of 400 mg (0.380 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. Thus obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 2.11 g (66%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 7.87 and 7.04 (2s, 2H), 7.63 and 7.42 (2t, 1H), 7.21 – 7.38 (m, 7H), 7.15 and 6.98 (2d, J = 7.8 Hz, 2H), 6.80 (dd, J = 11.0, 3.0 Hz, 1H), 6.74 (dd, J = 8.0, 3.0 Hz, 1H), 6.69 (dd, J = 11.1, 3.0 Hz, 1H), 6.11 (dd, J = 8.1, 3.1 Hz, 1H), 2.94 – 3.06 (2sept, 2H), 1.41 – 1.85 (m, 12H), 0.96 – 1.35 (m, 24H), 0.78 (s, 3H), 0.77 (s, 3H), 0.72 (s, 3H), 0.69 (s, 3H). ¹³C NMR (CDCl₃, 100 MHz) δ 157.65 (d, J_{C,F} = 238 Hz), 149.11, 148.67, 148.01, 140.28, 139.20, 138.29, 137.09, 134.11, 133.64, 132.05, 131.61, 128.58, 127.93, 122.28, 114.60 (d, J_{C,F} = 22.3 Hz), 114.13 (d, J_{C,F} = 23.0 Hz), 113.22 (d, J_{C,F} = 23.4 Hz), 51.07, 50.72, 47.18, 46.97, 46.09, 46.03, 43.18, 42.89, 42.68, 42.63, 38.59, 38.47, 37.89, 33.85, 33.73, 31.45, 31.27, 31.20, 31.09, 31.01, 30.89, 30.82, 30.70, 30.01, 29.96.


[0292] 4-Fluoro-2-((3*r*,5*r*,7*r*)-3,5,7-trimethyladamantan-1-yl)phenol



To a solution of 2.80 g (25.0 mmol) of 4-fluorophenol and 4.40 g (22.7 mmol) of 3,5,7-trimethyladamantan-1-ol in 30 mL of dichloromethane a solution of 1.60 mL (25.0 mmol) of methanesulfonic acid and 2 mL of acetic acid in 30 mL of dichloromethane was added dropwise for 1 hour at room temperature. The resulting mixture was stirred for 48 hours at room temperature and then carefully poured into 300 mL of 5% NaHCO₃. The crude product was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified using Kugelrohr apparatus (1 mbar, 80°C) yielding 3.9 g (60%) of the title product as a light-yellow oil. ¹H NMR (CDCl₃, 400 MHz): δ 6.93 (dd, J = 11.3, 3.1 Hz, 1H), 6.70 – 6.74 (m, 1H), 6.55 (dd, J = 8.6, 5.0 Hz, 1H), 4.87 (br.s, 1H), 1.62 (br.s, 6H), 1.00 – 1.18 (m, 6H), 0.87 (s, 9H). ¹³C NMR (CDCl₃, 100 MHz):


δ 158.44 (d, $J_{C,F}$ = 237 Hz), 150.28 (d, $J_{C,F}$ = 2.0 Hz), 137.44 (d, $J_{C,F}$ = 5.9 Hz), 117.10 (d, $J_{C,F}$ = 8.3 Hz), 114.13 (d, $J_{C,F}$ = 24.0 Hz), 112.56 (d, $J_{C,F}$ = 23.0 Hz), 50.28, 45.77, 39.34, 32.12, 30.46.

[0293] 2-Bromo-4-fluoro-6-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)phenol



- 5 To a solution of 3.60 g (12.5 mmol) of 4-fluoro-2-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)phenol in 20 mL of DMF 2.22 g (12.5 mmol) of NBS was added in one portion at room temperature. The resulting mixture was stirred for 48 hours at room temperature and then carefully poured into 200 mL of 5% NaHCO₃. The crude product was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then
- 10 evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-dichloromethane = 10:1, vol.). Yield 3.00 g (65%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.06 (dd, J = 6.9, 3.0 Hz, 1H), 6.94 (dd, J = 10.8, 3.0 Hz, 1H), 5.60 (s, 1H), 1.61 (br.s, 6H), 1.06 – 1.18 (m, 6H), 0.87 (s, 9H). ¹³C NMR (CDCl₃, 100 MHz): δ 157.20 (d, $J_{C,F}$ = 241 Hz), 146.99 (d, $J_{C,F}$ = 3.0 Hz), 138.10 (d, $J_{C,F}$ = 6.0 Hz), 115.76 (d, $J_{C,F}$ = 26.0 Hz), 114.06 (d, $J_{C,F}$ = 23.6 Hz), 111.22 (d, $J_{C,F}$ = 10.9 Hz), 50.20, 45.45, 40.19, 32.14, 30.42.
- 15


[0294] (3r,5r,7r)-1-(3-Bromo-5-fluoro-2-(methoxymethoxy)phenyl)-3,5,7-trimethyladamantane



- To a solution of 2.20 g (6.00 mmol) of 2-bromo-4-fluoro-6-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)phenol in 20 mL of dry THF 270 mg (6.60 mmol, 60% wt. in mineral oil) of sodium hydride was added at room temperature. After that, 630 μ l (7.80 mmol) of MOMCl was added in one portion. The reaction mixture was heated for 24 hours at 60°C and then poured into 30 mL of cold water. The crude product was extracted with 3 x 20 mL of dichloromethane. The combined organic extract was dried over Na₂SO₄ and then evaporated to
- 20 dryness. Yield 2.50 g (97%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.14 (dd, J = 6.9, 3.1 Hz, 1H), 6.99 (dd, J = 10.9, 3.1 Hz, 1H), 5.19 (s, 2H), 3.67 (s, 3H), 1.62 (br.s, 6H), 1.06 – 1.17 (m, 6H), 0.88 (s, 9H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.50 (d, $J_{C,F}$ = 245 Hz),
- 25

150.15, 146.11 (d, $J_{C,F}$ = 6.4 Hz), 118.17 (d, $J_{C,F}$ = 25.4 Hz), 117.67 (d, $J_{C,F}$ = 10.5 Hz), 114.05 (d, $J_{C,F}$ = 23.6 Hz), 100.08, 57.93, 50.07, 46.53, 40.65, 32.25, 30.46.


[0295] 2-(5-Fluoro-2-(methoxymethoxy)-3-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane



5

To a solution of 2.50 g (5.89 mmol) of (3r,5r,7r)-1-(3-bromo-5-fluoro-2-(methoxymethoxy)phenyl)-3,5,7-trimethyladamantane in 30 mL of dry THF 2.68 mL (6.70 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred at this temperature for 1 hour followed by addition of 1.84 mL (7.12 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred for 1 hour at room temperature, then poured into 30 mL of water. The crude product was extracted with dichloromethane (3 x 40 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. Yield 2.70 g (96%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.20 (dd, J = 7.6, 3.2 Hz, 1H), 7.08 (dd, J = 10.9, 3.3 Hz, 1H), 5.11 (s, 2H), 3.57 (s, 3H), 1.65 (br.s, 6H), 1.34 (s, 12H), 1.06 – 1.17 (m, 6H), 0.86 (s, 9H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.39 (d, $J_{C,F}$ = 240 Hz), 157.71 (d, $J_{C,F}$ = 2.0 Hz), 143.38 (d, $J_{C,F}$ = 5.7 Hz), 119.59 (d, $J_{C,F}$ = 21.0 Hz), 117.46 (d, $J_{C,F}$ = 24.0 Hz), 101.29, 84.01, 57.92, 50.24, 46.51, 39.88, 32.20, 30.52, 24.77.

[0296] (3r,5r,7r)-1-(2'-Bromo-5-fluoro-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)-3,5,7-trimethyladamantane




To a solution of 2.70 g (5.89 mmol) of 2-(5-fluoro-2-(methoxymethoxy)-3-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)phenyl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 20 mL of 1,4-dioxane 2.24 g (7.90 mmol) of 2-bromiodobenzene, 5.00 g (15.2 mmol) of cesium carbonate, and 10 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 350 mg (0.30 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 100 mL of

25


water. The crude product was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-dichloromethane = 10:1, vol.). Yield 2.50 g (85%) of a white solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.73 (d, J = 7.9 Hz, 1H), 7.40 – 7.42 (m, 2H), 7.26 – 7.30 (m, 1H), 7.10 (dd, J = 11.1, 3.2 Hz, 1H), 6.83 (dd, J = 7.8, 3.2 Hz, 1H), 4.53 (m, 1H), 4.42 (m, 1H), 3.27 (s, 3H), 1.73 (s, 6H), 1.14 – 1.25 (m, 6H), 0.95 (s, 9H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.22 (d, $J_{C,F}$ = 241 Hz), 150.23 (d, $J_{C,F}$ = 2.7 Hz), 140.01 (d, $J_{C,F}$ = 1.84 Hz), 135.75 (d, $J_{C,F}$ = 8.5 Hz), 133.03, 132.12, 129.11, 127.24, 123.75, 115.69 (d, $J_{C,F}$ = 23.2 Hz), 114.14 (d, $J_{C,F}$ = 23.8 Hz), 99.24, 57.16, 50.21, 46.52, 40.13, 32.21, 30.55.

[0297] 2-(5'-Fluoro-2'-(methoxymethoxy)-3'-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane




To a solution of 2.34 g (4.80 mmol) of (3r,5r,7r)-1-(2'-bromo-5-fluoro-2-(methoxymethoxy)-[1,1'-biphenyl]-3-yl)-3,5,7-trimethyladamantane in 20 mL of dry THF 2.00 mL (5.04 mmol) of 2.5 M ⁿBuLi in hexanes was added dropwise for 20 minutes at -80°C. The reaction mixture was stirred for 1 hour at this temperature followed by an addition of 1.34 mL (7.21 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane. The obtained suspension was stirred for 1 hour at room temperature, then poured into 100 mL of water. The crude product was extracted with dichloromethane (3 x 100 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-diethyl ether = 10:1, vol.). Yield 2.50 g (97%) of a colorless glassy solid. ¹H NMR (CDCl₃, 400 MHz): δ 7.76 (d, J = 7.6 Hz, 1H), 7.43 (td, J = 7.5, 1.5 Hz, 1H), 7.31 – 7.35 (m, 2H), 6.98 (dd, J = 11.2, 3.2 Hz, 1H), 6.73 (dd, J = 8.0, 3.2 Hz, 1H), 4.33 (s, 2H), 3.25 (s, 3H), 1.70 (br.s, 6H), 1.08 – 1.21 (m, 18H), 0.88 (s, 9H). ¹³C NMR (CDCl₃, 100 MHz): δ 159.30 (d, $J_{C,F}$ = 240 Hz), 150.06 (d, $J_{C,F}$ = 2.4 Hz), 144.58, 143.70 (d, $J_{C,F}$ = 6.6 Hz), 138.28 (d, $J_{C,F}$ = 8.3 Hz), 134.75, 130.20, 130.11, 126.61, 115.78 (d, $J_{C,F}$ = 22.7 Hz), 112.86 (d, $J_{C,F}$ = 23.6 Hz), 98.97, 83.53, 57.26, 50.22, 46.71, 40.02, 32.24, 30.55, 25.20 (broad), 24.12 (broad).

[0298] 2',2'''-(Pyridine-2,6-diyl)bis(5-fluoro-3'-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)-[1,1'-biphenyl]-2-ol)




To a solution of 2.50 g (4.80 mmol) of 2-(5'-fluoro-2'-(methoxymethoxy)-3'-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)-[1,1'-biphenyl]-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane in 20 mL of 1,4-dioxane, 546 mg (2.30 mmol) of 2,6-dibromopyridine, 4.02 g (12.0 mmol) of cesium carbonate, and 10 mL of water were subsequently added. The mixture obtained was purged with argon for 10 minutes followed by addition of 304 mg (0.240 mmol) of Pd(PPh₃)₄. This mixture was stirred for 12 hours at 100°C, then cooled to room temperature, and diluted with 50 mL of water. The obtained mixture was extracted with dichloromethane (3 x 50 mL), the combined organic extract was dried over Na₂SO₄ and then evaporated to dryness. To the resulting oil 50 mL of THF, 50 mL of methanol, and 3 mL of 12 N HCl were subsequently added. The reaction mixture was stirred overnight at 60°C and then poured into 200 mL of water. The crude product was extracted with dichloromethane (3 x 70 mL), the combined organic extract was washed with 5% NaHCO₃, dried over Na₂SO₄, and then evaporated to dryness. The residue was purified by flash chromatography on silica gel 60 (40-63 μ m, eluent: hexane-ethyl acetate = 10:1, vol.). Yield 690 mg (37%) of a mixture of two isomers as a white foam. ¹H NMR (CDCl₃, 400 MHz): δ 7.37 – 7.54 (m, 8H), 6.65 – 7.04 and 6.29 – 6.32 (m, 9H), 1.43 (s, 6H), 1.22 – 1.40 (m, 6H), 0.95 – 1.15 (m, 12H), 0.78 (s, 9H), 0.72 (s, 9H). ¹³C NMR (CDCl₃, 100 MHz) δ 157.71 (d, $J_{C,F}$ = 240 Hz), 157.68 (d, $J_{C,F}$ = 240 Hz), 148.03, 147.62 (d, $J_{C,F}$ = 2.0 Hz), 139.79, 138.99, 138.91, 138.70, 138.64, 136.92, 136.82, 135.82, 135.67, 132.05, 131.43, 130.60, 130.00, 129.82, 129.20, 128.57, 128.44, 122.41, 122.18, 114.26 (d, $J_{C,F}$ = 22.7 Hz), 113.84 (d, $J_{C,F}$ = 23.0 Hz), 113.51 (d, $J_{C,F}$ = 23.4 Hz), 113.12 (d, $J_{C,F}$ = 23.7 Hz), 50.30, 50.05, 45.71, 39.55, 39.49, 32.17, 32.00, 31.89, 30.60, 30.44.

[0299] Dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-methyl-[1,1'-biphenyl]-2-olate)] (Complex 1)



- To a suspension of 225 mg (0.702 mmol) of hafnium tetrachloride (<0.5% Zr) in 50 mL of dry toluene 1.10 mL (3.16 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 500 mg (0.702 mmol) of 2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-methyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo.
- Yield 473 mg (73%) of a white-beige solid. Anal. Calc. for $C_{53}H_{57}HfNO_2$: C, 69.30; H, 6.26; N, 1.52. Found: C 69.58; H, 6.39; N 1.40. 1H NMR ($CDCl_3$, 400 MHz): δ 7.69 (t, J = 7.8 Hz, 1H), 7.54 (td, J = 7.6, 1.4 Hz, 2H), 7.35 (td, J = 7.5, 1.3 Hz, 2H), 7.30 (dd, J = 7.8, 1.2 Hz, 2H), 7.10 – 7.14 (m, 4H), 7.02 (d, J = 2.3 Hz, 2H), 6.69 (dd, J = 2.3, 0.6 Hz, 2H), 2.23 (s, 6H), 2.18 – 2.24 (m, 6H), 2.04 – 2.14 (m, 12H), 1.68 – 1.85 (m, 12H), -0.78 (s, 6H). ^{13}C NMR ($CDCl_3$, 100 MHz) δ 158.78, 157.35, 142.53, 139.60, 138.26, 132.88, 132.34, 131.79, 130.83, 130.69, 128.66, 127.52, 127.40, 126.22, 124.77, 49.51, 40.85, 37.15, 37.00, 29.06, 20.76.


[0300] Dimethylzirconium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-methyl-[1,1'-biphenyl]-2-olate)] (Complex 3)



- To a suspension of 131 mg (0.562 mmol) of zirconium tetrachloride in 50 mL of dry toluene 870 μ L (2.53 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at -30°C. To the resulting suspension 400 mg (0.562 mmol) of 2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-methyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 318 mg (68%) of a beige solid. Anal. Calc. for $C_{53}H_{57}ZrNO_2$: C, 76.58; H, 6.91; N, 1.69.


Found: C 76.89; H, 7.06; N 1.52. ^1H NMR (C_6D_6 , 400 MHz): 7.11 – 7.20 (m, 8H), 7.02 – 7.04 (m, 2H), 6.76 (d, $J = 2.2$ Hz, 2H), 6.39 – 6.50 (m, 3H), 2.45 – 2.54 (m, 6H), 2.32 – 2.37 (m, 6H), 2.23 (s, 6H), 2.17 (br.s, 6H), 1.94 – 2.03 (m, 6H), 1.80 – 1.89 (m, 6H), -0.10 (s, 6H). ^{13}C NMR (CDCl_3 , 100 MHz) δ 159.31, 158.31, 143.44, 139.58, 138.60, 133.65, 133.59, 133.18, 131.42, 131.13, 129.36, 128.54, 128.06, 127.20, 124.43, 42.89, 41.95, 38.18, 37.85, 30.01, 21.41.

[0301] Dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-4',5-dimethyl-[1,1'-biphenyl]-2-olate)] (Complex 2)




To a suspension of 118 mg (0.369 mmol) of hafnium tetrachloride (<0.5% Zr) in 50 mL of dry toluene 570 μL (1.66 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C . To the resulting suspension 273 mg (0.369 mmol) of 2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-4',5-dimethyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 240 mg (69%) of a white-beige solid. Anal. Calc. for $\text{C}_{55}\text{H}_{61}\text{HfNO}_2$: C, 69.79; H, 6.50; N, 1.48. Found: C 70.08; H, 6.73; N 1.35. ^1H NMR (C_6D_6 , 400 MHz): δ 7.20 (d, $J = 2.4$ Hz, 2H), 7.12 (d, $J = 8.0$ Hz, 2H), 6.97 (dd, $J = 7.8, 1.8$ Hz, 2H), 6.84 (m, 2H), 6.74 – 6.76 (m, 2H), 6.43 – 6.56 (m, 3H), 2.45 – 2.53 (m, 6H), 2.30 – 2.38 (m, 6H), 2.23 (s, 6H), 2.21 (s, 6H), 2.15 (br.s, 6H), 1.94 – 2.03 (m, 6H), 1.76 – 1.84 (m, 6H), -0.03 (s, 6H). ^{13}C NMR (C_6D_6 , 100 MHz) δ 159.99, 158.16, 140.99, 139.42, 139.03, 137.75, 133.71, 133.23, 133.14, 132.44, 131.03, 129.60, 128.29, 126.99, 125.20, 51.24, 41.67, 38.04, 37.81, 30.04, 21.41, 21.39.

[0302] Dimethylzirconium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-4',5-dimethyl-[1,1'-biphenyl]-2-olate)] (Complex 4)



To a suspension of 83 mg (0.354 mmol) of zirconium tetrachloride in 30 mL of dry toluene 540 μ l (1.59 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at -30°C . To the resulting suspension 262 mg (0.354 mmol) of 2',2'''-(pyridine-2,6-diyl)bis(3-
 5 ((3r,5r,7r)-adamantan-1-yl)-4',5-dimethyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained
 10 precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 193 mg (63%) of a beige solid. Anal. Calc. for $\text{C}_{55}\text{H}_{61}\text{ZrNO}_2$: C, 76.88; H, 7.16; N, 1.63. Found: C 77.06; H, 7.43; N 1.51. ^1H NMR (C_6D_6 , 400 MHz): δ 7.19 (d, $J = 1.8$ Hz, 2H), 7.13 (d, $J = 7.8$ Hz, 2H), 6.96 (ddd, $J = 7.8, 1.8, 0.6$ Hz, 2H), 6.82 (dd, $J = 1.2, 0.6$ Hz, 2H), 6.76 (dd, $J = 2.4, 0.6$ Hz, 2H), 6.42 – 6.57 (m, 3H), 2.48 – 2.55 (m, 6H), 2.34 – 2.42 (m, 6H), 2.22 (s, 6H),
 15 2.20 (s, 6H), 2.15 (br.s, 6H), 1.95 – 2.02 (m, 6H), 1.77 – 1.84 (m, 6H), -0.20 (s, 6H). ^{13}C NMR (C_6D_6 , 100 MHz) δ 159.46, 158.49, 140.84, 139.40, 138.49, 137.69, 133.62, 133.59, 133.51, 132.31, 130.93, 129.66, 128.89, 128.22, 127.09, 126.03, 124.74, 42.91, 41.72, 38.14, 37.80, 30.04, 21.42, 21.38.


[0303] **Dimethylhafnium[2',2'''-(4-methoxypyridine-2,6-diyl)bis(3-((3r,5r,7r)-
 20 adamantan-1-yl)-5-(tert-butyl)-[1,1'-biphenyl]-2-olate)] (Complex 7)**



To a suspension of 155 mg (0.484 mmol) of hafnium tetrachloride ($<0.5\%$ Zr) in 50 mL of dry toluene 750 μ l (2.18 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C . To the resulting suspension 400 mg (0.484 mmol) of 2',2'''-(4-methoxypyridine-

2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-(tert-butyl)-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 338 mg (68%) of a white-beige solid. Anal. Calc. for $C_{60}H_{71}HfNO_3$: C, 69.78; H, 6.93; N, 1.36. Found: C 70.04; H, 7.16; N 1.24. 1H NMR (C_6D_6 , 400 MHz): δ 7.59 (d, J = 2.6 Hz, 2H), 7.19 – 7.21 (m, 2H), 7.09 – 7.16 (m, 8H), 6.08 (s, 2H), 2.57 – 2.63 (m, 6H), 2.55 (s, 3H), 2.43 – 2.49 (m, 6H), 2.21 (br.s, 6H), 1.99 – 2.06 (m, 6H), 1.83 – 1.90 (m, 6H), 1.33 (s, 18H), -0.10 (s, 6H). ^{13}C NMR (C_6D_6 , 100 MHz) δ 167.56, 159.92, 159.70, 143.99, 140.37, 138.65, 133.99, 133.04, 132.78, 131.59, 131.32, 129.66, 128.90, 127.90, 125.85, 124.81, 111.17, 55.17, 50.99, 41.98, 38.57, 37.89, 34.79, 32.36, 30.08.


[0304] Dimethylhafnium[2',2'''-(4-(trifluoromethyl)pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-(tert-butyl)-[1,1'-biphenyl]-2-olate)] (Complex 8)



To a suspension of 148 mg (0.463 mmol) of hafnium tetrachloride (<0.5% Zr) in 50 mL of dry toluene 720 μ L (2.10 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 400 mg (0.463 mmol) of 2',2'''-(4-(trifluoromethyl)pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-(tert-butyl)-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 342 mg (69%) of a yellow solid. Anal. Calc. for $C_{60}H_{68}F_3HfNO_2$: C, 67.31; H, 6.40; N, 1.31. Found: C 67.65; H, 6.66; N 1.20. 1H NMR (C_6D_6 , 400 MHz): δ 7.55 (d, J = 2.6 Hz, 2H), 7.07 – 7.18 (m, 4H), 7.03 (td, J = 7.4, 1.6 Hz, 2H), 6.99 (d, J = 2.5 Hz, 2H),


6.91 (dd, $J = 7.4, 1.1$ Hz, 2H), 6.82 (s, 2H), 2.47 – 2.53 (m, 6H), 2.32 – 2.39 (m, 6H), 2.17 (br.s, 6H), 1.94 – 2.01 (m, 6H), 1.80 – 1.89 (m, 6H), 1.30 (s, 18H), -0.13 (s, 6H). ^{13}C NMR (C_6D_6 , 100 MHz) δ 160.03, 159.46, 143.80, 141.05, 138.65, 133.82, 132.47, 132.08, 131.72, 131.25, 125.67, 124.93, 121.29 (q, $J_{\text{C},\text{F}} = 3.1$ Hz), 51.49, 41.94, 38.49, 37.79, 34.78, 32.23, 29.98.

- 5 **[0305] Dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(tert-butyl)-4'-methyl-[1,1'-biphenyl]-2-olate)] (Complex 9)**




- To a suspension of 155 mg (0.485 mmol) of hafnium tetrachloride (<0.5% Zr) in 50 mL of dry toluene 750 μL (2.20 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 400 mg (0.485 mmol) of 2',2'''-(pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(tert-butyl)-4'-methyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 287 mg (57%) of a white-beige solid. Anal. Calc. for $\text{C}_{61}\text{H}_{73}\text{HfNO}_2$: C, 71.08; H, 7.14; N, 1.36. Found: C 71.31; H, 7.32; N 1.24. ^1H NMR (C_6D_6 , 400 MHz): δ 7.58 (d, $J = 2.6$ Hz, 2H), 7.12 (d, $J = 7.8$ Hz, 2H), 7.03 (d, $J = 2.6$ Hz, 2H), 6.95 (dd, $J = 7.9, 1.3$ Hz, 2H), 6.75 (d, $J = 0.7$ Hz, 2H), 6.39 – 6.52 (m, 3H), 2.55 – 2.62 (m, 6H), 2.40 – 2.48 (m, 6H), 2.19 (s, 6H), 2.19 (br.s, 6H), 1.98 – 2.05 (m, 6H), 1.78 – 1.86 (m, 6H), 1.33 (s, 18H), -0.02 (s, 6H). ^{13}C NMR (C_6D_6 , 100 MHz) δ 159.90, 158.06, 141.34, 140.38, 139.30, 138.47, 137.64, 133.82, 133.12, 132.86, 132.49, 131.21, 129.66, 128.90, 126.00, 125.32, 124.41, 51.20, 41.77, 38.48, 37.81, 34.76, 32.35, 30.07, 21.31.

- 25 **[0306] Dimethylhafnium[2',2'''-(4-(trifluoromethyl)pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(tert-butyl)-4'-isopropyl-[1,1'-biphenyl]-2-olate)] (Complex 10)**



To a suspension of 135 mg (0.421 mmol) of hafnium tetrachloride (<0.5% Zr) in 50 mL of dry toluene 650 μ L (1.89 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 400 mg (0.421 mmol) of 2',2'''-(4-(trifluoromethyl)pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-(tert-butyl)-4'-isopropyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 356 mg (73%) of a yellow solid. Anal. Calc. for C₆₆H₈₀F₃HfNO₂: C, 68.64; H, 6.98; N, 1.21. Found: C 68.88; H, 7.16; N 1.13. ¹H NMR (C₆D₆, 400 MHz): δ 7.57 (d, J = 2.6 Hz, 2H), 7.19 – 7.22 (m, 4H), 7.02 (s, 2H), 6.98 (d, J = 2.5 Hz, 2H), 6.93 (d, J = 1.7 Hz, 2H), 2.91 (sept, J = 6.9 Hz, 2H), 2.53 – 2.60 (m, 6H), 2.40 – 2.47 (m, 6H), 2.15 (br.s, 6H), 1.96 – 2.03 (m, 6H), 1.77 – 1.85 (m, 6H), 1.28 (s, 18H), 1.23 (d, J = 6.9 Hz, 6H), 1.07 (d, J = 6.9 Hz, 6H), 0.00 (s, 6H). ¹³C NMR (C₆D₆, 100 MHz) δ 160.39, 159.75, 149.13, 141.82, 140.98, 138.51, 134.19, 132.28, 129.29, 125.96, 124.61, 121.84 (q, J_{C,F} = 3.0 Hz), 51.54, 41.81, 38.53, 37.78, 34.77, 33.85, 32.24, 29.95, 26.57, 22.32.


[0307] **Dimethylhafnium[2',2'''-(4-methoxypyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-(tert-butyl)-4'-isopropyl-[1,1'-biphenyl]-2-olate)] (Complex 11)**



To a suspension of 140 mg (0.440 mmol) of hafnium tetrachloride (<0.5% Zr) in 50 mL of dry toluene 680 μ L (1.98 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 400 mg (0.440 mmol) of 2',2'''-(4-methoxypyridine-

2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(tert-butyl)-4'-isopropyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 310 mg (63%) of a white solid. Anal. Calc. for C₆₆H₈₃HfNO₃: C, 70.98; H, 7.49; N, 1.25. Found: C 71.24; H, 7.52; N 1.14. ¹H NMR (C₆D₆, 400 MHz): δ 7.60 (d, J = 2.6 Hz, 2H), 7.25 (d, J = 8.1 Hz, 2H), 7.18 (m, 2H), 7.07 (d, J = 2.5 Hz, 2H), 7.02 (d, J = 1.8 Hz, 2H), 6.21 (s, 2H), 2.98 (sept, J = 6.8 Hz, 2H), 2.60 – 2.67 (m, 6H), 2.61 (s, 3H), 2.48 – 2.56 (m, 6H), 2.18 (br.s, 6H), 2.01 – 2.08 (m, 6H), 1.80 – 1.87 (m, 6H), 1.31 (s, 18H), 1.25 (d, J = 6.8 Hz, 6H), 1.12 (d, J = 6.8 Hz, 6H), -0.02 (s, 6H). ¹³C NMR (C₆D₆, 100 MHz) δ 167.36, 160.15, 160.03, 148.56, 141.83, 140.28, 138.50, 134.24, 133.36, 132.93, 129.58, 128.24, 126.19, 124.50, 111.80, 55.16, 51.06, 41.85, 38.60, 37.87, 34.79, 33.77, 32.38, 30.03, 26.54, 22.31.


[0308] Dimethylhafnium[2',2'''-(4-(trifluoromethyl)pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(tert-butyl)-4'-methyl-[1,1'-biphenyl]-2-olate)] (Complex 12)



To a suspension of 144 mg (0.448 mmol) of hafnium tetrachloride (<0.5% Zr) in 50 mL of dry toluene 695 μ L (2.02 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 400 mg (0.448 mmol) of 2',2'''-(4-(trifluoromethyl)pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(tert-butyl)-4'-methyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 398 mg (81%) of a yellow solid. Anal. Calc. for C₆₂H₇₂F₃HfNO₂: C, 67.78; H, 6.61; N, 1.27. Found: C 68.03; H, 6.74; N 1.15. ¹H NMR

(C₆D₆, 400 MHz): δ 7.55 (d, J = 2.6 Hz, 2H), 7.07 (d, J = 7.9 Hz, 2H), 6.95 (d, J = 2.6 Hz, 2H), 6.93 (dd, J = 7.8, 1.2 Hz, 2H), 6.84 (s, 2H), 6.69 (d, J = 0.7 Hz, 2H), 2.50 – 2.57 (m, 6H), 2.37 – 2.45 (m, 6H), 2.16 (s, 6H), 2.15 (br.s, 6H), 1.96 – 2.04 (m, 6H), 1.78 – 1.86 (m, 6H), 1.30 (s, 18H), -0.03 (s, 6H). ¹³C NMR (C₆D₆, 100 MHz) δ 160.17, 159.61, 141.22, 140.90, 138.47, 137.94, 133.72, 132.95, 132.29, 132.16, 130.86, 129.66, 128.90, 126.03, 125.92, 124.58, 121.56 (q, J^F = 3.5 Hz), 51.51, 41.74, 38.48, 37.76, 34.76, 32.25, 30.04, 21.27.

[0309] Dimethylzirconium[2',2'''-(4-(trifluoromethyl)pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-(tert-butyl)-4'-methyl-[1,1'-biphenyl]-2-olate)] (Complex 13)




10

To a suspension of 105 mg (0.448 mmol) of zirconium tetrachloride in 50 mL of dry toluene 695 μ l (2.02 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at -30°C. To the resulting suspension 400 mg (0.448 mmol) of 2',2'''-(4-(trifluoromethyl)pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-(tert-butyl)-4'-methyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 330 mg (73%) of a yellow solid. Anal. Calc. for C₆₂H₇₂F₃ZrNO₂: C, 73.62; H, 7.18; N, 1.38. Found: C 73.90; H, 7.32; N 1.21. ¹H NMR (C₆D₆, 400 MHz): δ 7.54 (d, J = 2.6 Hz, 2H), 7.07 (d, J = 7.8 Hz, 2H), 6.95 (d, J = 2.5 Hz, 2H), 6.91 (dd, J = 7.8, 1.2 Hz, 2H), 6.83 (s, 2H), 6.67 (m, 2H), 2.52 – 2.59 (m, 6H), 2.39 – 2.47 (m, 6H), 2.15 (s, 6H), 2.15 (br.s, 6H), 1.96 – 2.04 (m, 6H), 1.79 – 1.86 (m, 6H), 1.30 (s, 18H), -0.20 (s, 6H). ¹³C NMR (C₆D₆, 100 MHz) δ 160.53, 159.08, 141.06, 141.00, 137.91, 137.88, 133.60, 132.81, 132.64, 132.55, 130.76, 129.66, 128.90, 125.99, 124.49, 121.05 (q, J^F = 3.0 Hz), 43.38, 41.78, 38.58, 37.75, 34.79, 32.24, 30.04, 21.25.


20
25

[0310] Dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-5-(tert-butyl)-4'-isopropyl-[1,1'-biphenyl]-2-olate)] (Complex 14)



To a suspension of 145 mg (0.454 mmol) of hafnium tetrachloride (<0.5% Zr) in 50 mL of dry toluene 704 μ L (2.04 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 400 mg (0.454 mmol) of 2',2''-(pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(tert-butyl)-4'-isopropyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 333 mg (67%) of a white solid. Anal. Calc. for C₆₅H₈₁HfNO₂: C, 71.83; H, 7.51; N, 1.29. Found: C 72.09; H, 7.67; N 1.20. ¹H NMR (C₆D₆, 400 MHz): δ 7.58 (d, J = 2.6 Hz, 2H), 7.25 (d, J = 8.1 Hz, 2H), 7.17 – 7.19 (m, 2H), 7.04 (d, J = 2.6 Hz, 2H), 6.92 (d, J = 1.8 Hz, 2H), 6.43 – 6.55 (m, 3H), 2.95 (sept, J = 6.9 Hz, 2H), 2.56 – 2.63 (m, 6H), 2.44 – 2.50 (m, 6H), 2.17 (br.s, 6H), 1.99 – 2.06 (m, 6H), 1.78 – 1.86 (m, 6H), 1.31 (s, 18H), 1.25 (d, J = 6.9 Hz, 6H), 1.10 (d, J = 6.9 Hz, 6H), 0.00 (s, 6H). ¹³C NMR (C₆D₆, 100 MHz) δ 158.67, 157.62, 147.92, 140.68, 139.28, 138.93, 137.17, 133.04, 132.32, 131.59, 128.97, 127.37, 125.20, 125.15, 123.24, 49.62, 40.65, 37.42, 37.04, 34.15, 33.03, 31.72, 29.08, 26.02, 21.86.


[0311] Dimethylhafnium[2',2''-(4-methoxypyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(tert-butyl)-4'-methyl-[1,1'-biphenyl]-2-olate)] (Complex 15)



To a suspension of 112 mg (0.351 mmol) of hafnium tetrachloride (<0.5% Zr) in 50 mL of dry toluene 544 μ L (1.56 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 300 mg (0.351 mmol) of 2',2''-(4-methoxypyridine-

2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-(tert-butyl)-4'-methyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 284 mg (76%) of a white solid. Anal. Calc. for C₆₂H₇₅HfNO₃: C, 70.20; H, 7.13; N, 1.32. Found: C 70.45; H, 7.33; N 1.23. ¹H NMR (C₆D₆, 400 MHz): δ 7.59 (d, J = 2.6 Hz, 2H), 7.12 – 7.14 (m, 2H), 7.05 (d, J = 2.6 Hz, 2H), 6.95 (dd, J = 7.9, 1.2 Hz, 2H), 6.85 (m, 2H), 6.09 (s, 2H), 2.63 (s, 3H), 2.59 – 2.65 (m, 6H), 2.44 – 2.53 (m, 6H), 2.22 (s, 6H), 2.19 (br.s, 6H), 2.01 – 2.08 (m, 6H), 1.80 – 1.87 (m, 6H), 1.33 (s, 18H), 0.00 (s, 6H). ¹³C NMR (C₆D₆, 100 MHz) δ 166.82, 159.09, 158.73, 140.36, 139.21, 137.23, 137.08, 132.94, 132.42, 131.61, 131.51, 130.47, 123.29, 110.90, 55.69, 49.23, 40.68, 37.47, 37.02, 34.15, 31.72, 29.16, 21.01.


[0312] Dimethylhafnium[2',2'''-(4-methoxypyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-fluoro-4'-isopropyl-[1,1'-biphenyl]-2-olate)] (Complex 16)



To a suspension of 153 mg (0.479 mmol) of hafnium tetrachloride (<0.05% Zr) in 50 mL of dry toluene 743 μ L (2.16 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 400 mg (0.479 mmol) of 2',2'''-(4-methoxypyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-5-fluoro-4'-isopropyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 286 mg (57%) of a white solid. Anal. Calc. for C₅₈H₆₅F₂HfNO₃: C, 66.94; H, 6.30; N, 1.35. Found: C 67.23; H, 6.51; N 1.25. ¹H NMR (C₆D₆, 400 MHz): δ 7.11 – 7.20 (m, 6H), 7.02 (m, 2H), 6.72 (dd, J = 7.8, 3.2 Hz, 2H), 6.21 (s, 2H), 2.94 (sept, J = 6.8 Hz,


2H), 2.52 (s, 3H), 2.33 – 2.42 (m, 6H), 2.20 – 2.30 (m, 6H), 2.07 (br.s, 6H), 1.87 – 1.95 (m, 6H), 1.72 – 1.80 (m, 6H), 1.24 (d, $J = 6.8$ Hz, 6H), 1.14 (d, $J = 6.8$ Hz, 6H), -0.05 (s, 6H). ^{13}C NMR (C_6D_6 , 100 MHz) δ 167.75, 159.75, 158.49, 157.28 (d, $J_{\text{C},\text{F}} = 235$ Hz), 149.31, 141.11 (d, $J_{\text{C},\text{F}} = 5.7$ Hz), 140.05 (d, $J_{\text{C},\text{F}} = 1.7$ Hz), 133.81, 133.47 (d, $J_{\text{C},\text{F}} = 7.7$ Hz), 133.28, 129.32, 128.51, 115.00 (d, $J_{\text{C},\text{F}} = 22.3$ Hz), 114.58 (d, $J_{\text{C},\text{F}} = 23.0$ Hz), 111.65, 55.26, 51.57, 41.18, 38.28, 37.59, 33.99, 29.77, 26.37, 22.34.

[0313] Dimethylhafnium[2',2'''-(4-methoxypyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-4'-(tert-butyl)-5-methyl-[1,1'-biphenyl]-2-olate)] (Complex 17)




To a suspension of 165 mg (0.515 mmol) of hafnium tetrachloride (<0.05% Zr) in 50 mL of dry toluene 800 μL (2.32 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C . To the resulting suspension 440 mg (0.515 mmol) of 2',2'''-(4-methoxypyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-4'-(tert-butyl)-5-methyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 380 mg (70%) of a white solid. Anal. Calc. for $\text{C}_{62}\text{H}_{75}\text{HfNO}_3$: C, 70.20; H, 7.13; N, 1.32. Found: C 70.46; H, 7.29; N 1.25. ^1H NMR (C_6D_6 , 400 MHz): δ 7.36 (dd, $J = 8.3, 2.0$ Hz, 2H), 7.24 (m, 4H), 7.20 (d, $J = 2.0$ Hz, 2H), 6.70 (d, $J = 2.0$ Hz, 2H), 6.26 (s, 2H), 2.52 – 2.59 (m, 6H), 2.47 (s, 3H), 2.41 – 2.48 (m, 6H), 2.19 (s, 6H), 2.17 (br.s, 6H), 1.98 – 2.06 (m, 6H), 1.76 – 1.84 (m, 6H), 1.34 (s, 18H), -0.06 (s, 6H). ^{13}C NMR (C_6D_6 , 100 MHz) δ 167.46, 160.77, 160.29, 151.37, 141.42, 139.12, 134.02, 133.98, 133.05, 129.71, 129.56, 126.86, 125.47, 112.05, 55.00, 51.36, 41.67, 38.26, 37.81, 35.15, 31.74, 29.98, 21.34.

[0314] Dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(3-((3r,5r,7r)-adamantan-1-yl)-4'-(tert-butyl)-5-methyl-[1,1'-biphenyl]-2-olate)] (Complex 18)



To a suspension of 124 mg (0.388 mmol) of hafnium tetrachloride (<0.05% Zr) in 50 mL of dry toluene 600 μ L (1.75 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 320 mg (0.388 mmol) of 2',2''-(pyridine-2,6-diyl)bis(3-((3*r*,5*r*,7*r*)-adamantan-1-yl)-4'-(tert-butyl)-5-methyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 301 mg (75%) of a white solid. Anal. Calc. for C₆₁H₇₃HfNO₂: C, 71.08; H, 7.14; N, 1.32. Found: C 71.39; H, 7.27; N 1.22. ¹H NMR (C₆D₆, 400 MHz): δ 7.35 (dd, J = 8.3, 2.0 Hz, 2H), 7.22 (d, J = 8.3 Hz, 2H), 7.19 (d, J = 2.0 Hz, 2H), 7.14 (d, J = 2.0 Hz, 2H), 6.66 (d, J = 1.7 Hz, 2H), 6.45 – 6.53 (m, 3H), 2.48 – 2.56 (m, 6H), 2.37 – 2.45 (m, 6H), 2.19 (s, 6H), 2.16 (br.s, 6H), 1.96 – 2.05 (m, 6H), 1.75 – 1.84 (m, 6H), 1.32 (s, 18H), 0.07 (s, 6H). ¹³C NMR (C₆D₆, 100 MHz) δ 160.12, 158.83, 151.36, 141.36, 139.48, 139.01, 133.84, 132.99, 129.65, 129.57, 126.93, 125.76, 125.54, 51.54, 41.59, 38.17, 37.75, 35.12, 31.69, 29.92, 21.33.


[0315] Dimethylhafnium[2',2''-(pyridine-2,6-diyl)bis(3-((1*r*,3*R*,5*S*,7*r*)-3,5-dimethyladamantan-1-yl)-5-fluoro-4'-isopropyl-[1,1'-biphenyl]-2-olate)] (Complex 19)



To a suspension of 210 mg (0.654 mmol) of hafnium tetrachloride (<0.05% Zr) in 50 mL of dry toluene 900 μ L (2.61 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 562 mg (0.654 mmol) of 2',2''-(pyridine-2,6-

diyl)bis(3-((1r,3R,5S,7r)-3,5-dimethyladamantan-1-yl)-5-fluoro-4'-isopropyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 530 mg (76%) of a white solid. Anal. Calc. for $C_{61}H_{71}F_2HfNO_2$: C, 68.68; H, 6.71; N, 1.31. Found: C 68.81; H, 6.99; N 1.23. 1H NMR (CD_2Cl_2 , 400 MHz): δ 7.77 (t, J = 7.7 Hz, 1H), 7.47 (dd, J = 8.1, 1.8 Hz, 2H), 7.18 (d, J = 8.1 Hz, 2H), 7.16 (d, J = 7.7 Hz, 2H), 6.90 – 6.94 (m, 4H), 6.49 (dd, J = 7.9, 3.2 Hz, 2H), 2.97 (sept, J = 6.9 Hz, 2H), 2.60 – 2.67 (m, 2H), 2.45 – 2.52 (m, 2H), 2.00 – 2.05 (m, 2H), 1.52 – 1.63 (m, 6H), 1.33 – 1.42 (m, 4H), 1.33 (d, J = 6.9 Hz, 6H), 1.30 – 1.34 (m, 2H), 1.22 (d, J = 6.9 Hz, 6H), 1.11 – 1.24 (m, 6H), 1.02 – 1.09 (m, 2H), 0.91 (s, 6H), 0.77 (s, 6H), -0.68 (s, 6H). ^{13}C NMR (CD_2Cl_2 , 100 MHz) δ 157.97, 157.89, 156.47 (d, $J_{C,F}$ = 234 Hz), 149.58, 140.27, 140.15 (d, $J_{C,F}$ = 6.1 Hz), 139.42 (d d, $J_{C,F}$ = 1.7 Hz), 133.12, 133.03 (d, $J_{C,F}$ = 7.9 Hz), 132.88, 129.52, 129.43, 128.70, 128.49, 125.85, 125.78, 114.45 (d, $J_{C,F}$ = 22.3 Hz), 113.65 (d, $J_{C,F}$ = 23.2 Hz), 51.75, 50.95, 49.61, 45.53, 43.87, 42.50, 39.57, 38.24, 33.76, 32.22, 31.58, 31.56, 30.92, 30.37, 25.85, 22.39.


[0316] Dimethylzirconium[2',2'''-(pyridine-2,6-diyl)bis(3-((1r,3R,5S,7r)-3,5-dimethyladamantan-1-yl)-5-fluoro-4'-isopropyl-[1,1'-biphenyl]-2-olate)] (Complex 20)



To a suspension of 135 mg (0.581 mmol) of zirconium tetrachloride in 50 mL of dry toluene 800 μ l (2.32 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at -30°C. To the resulting suspension 500 mg (0.581 mmol) of 2',2'''-(pyridine-2,6-diyl)bis(3-((1r,3R,5S,7r)-3,5-dimethyladamantan-1-yl)-5-fluoro-4'-isopropyl-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL

of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 390 mg (68%) of a white-beige solid. Anal. Calc. for $C_{61}H_{71}F_2ZrNO_2$: C, 74.80; H, 7.31; N, 1.43. Found: C 75.06; H, 7.64; N 1.19. 1H NMR (CD_2Cl_2 , 400 MHz): δ 7.76 (t, J = 7.8 Hz, 1H), 7.46 (dd, J = 8.1, 1.8 Hz, 2H), 7.19 (d, J = 8.0 Hz, 2H), 7.15 (d, J = 7.8 Hz, 2H), 6.92 (dd, J = 11.7, 3.3 Hz, 2H), 6.89 (d, J = 1.8 Hz, 2H), 6.51 (dd, J = 8.0, 3.3 Hz, 2H), 2.97 (sept, J = 6.9 Hz, 2H), 2.65 – 2.73 (m, 2H), 2.48 – 2.56 (m, 2H), 2.00 – 2.06 (m, 2H), 1.52 – 1.65 (m, 6H), 1.33 – 1.43 (m, 6H), 1.33 (d, J = 6.9 Hz, 6H), 1.22 (d, J = 6.9 Hz, 6H), 1.15 – 1.23 (m, 6H), 1.06 – 1.14 (m, 2H), 0.92 (s, 6H), 0.79 (s, 6H), -0.42 (s, 6H). ^{13}C NMR (CD_2Cl_2 , 100 MHz) δ 158.29, 157.34, 156.51 (d, $J_{C,F}$ = 235 Hz), 149.53, 140.25, 139.61 (d, $J_{C,F}$ = 6.1 Hz), 139.29 (d, $J_{C,F}$ = 1.7 Hz), 133.42 (d, $J_{C,F}$ = 7.9 Hz), 133.26, 133.03, 129.53, 129.35, 128.72, 128.37, 125.79, 125.39, 114.57 (d, $J_{C,F}$ = 22.3 Hz), 113.61 (d, $J_{C,F}$ = 23.2 Hz), 51.76, 49.61, 45.66, 43.88, 42.81, 42.52, 39.67, 38.30, 33.77, 32.23, 31.59, 31.56, 30.94, 30.39.

[0317] Dimethylhafnium[2',2'''-(pyridine-2,6-diyl)bis(5-fluoro-3-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)-[1,1'-biphenyl]-2-olate)] (Complex 21)



To a suspension of 119 mg (0.373 mmol) of hafnium tetrachloride (<0.05% Zr) in 50 mL of dry toluene 510 μ L (1.49 mmol) of 2.9 M MeMgBr in diethyl ether was added in one portion via syringe at 0°C. To the resulting suspension 300 mg (0.373 mmol) of 2',2'''-(pyridine-2,6-diyl)bis(5-fluoro-3-((3r,5r,7r)-3,5,7-trimethyladamantan-1-yl)-[1,1'-biphenyl]-2-ol) was immediately added in one portion. The reaction mixture was stirred for 4 hours at room temperature and then evaporated to near dryness. The solid obtained was extracted with 2 x 20 mL of hot toluene, and the combined organic extract was filtered through a thin pad of Celite 503. Next, the filtrate was evaporated to dryness. The residue was triturated with 5 mL of n-hexane, the obtained precipitate was filtered off (G4), washed with 2 x 5 mL of n-hexane, and then dried in vacuo. Yield 271 mg (72%) of a white solid. Anal. Calc. for $C_{57}H_{63}F_2HfNO_2$: C, 67.74; H, 6.28; N, 1.39. Found: C 67.98; H, 6.42; N 1.37. 1H NMR (CD_2Cl_2 , 400 MHz): δ 7.79 (t, J = 7.7 Hz, 1H), 7.55 (td, J = 7.5, 1.5 Hz, 2H), 7.49 (td, J = 7.4, 1.3 Hz, 2H), 7.22 (dd, J = 7.4, 0.9 Hz, 2H), 7.18 (d, J = 7.8 Hz, 2H), 7.11 (dd, J = 7.4, 0.9 Hz, 2H), 6.97

(dd, $J = 11.7, 3.3$ Hz, 2H), 6.52 (dd, $J = 7.8, 3.3$ Hz, 2H), 1.74 – 1.80 (m, 6H), 1.58 – 1.64 (m, 6H), 1.17 – 1.24 (m, 6H), 1.00 – 1.07 (m, 6H), 0.88 (s, 18H), -0.74 (s, 6H). ^{13}C NMR (CD_2Cl_2 , 100 MHz) δ 158.06, 158.04, 157.51, 156.37 (d, $J_{\text{C,F}} = 234$ Hz), 141.79 (d, $J_{\text{C,F}} = 1.7$ Hz), 140.46, 140.05 (d, $J_{\text{C,F}} = 5.9$ Hz), 139.99, 132.98, 132.90, 132.79 (d, $J_{\text{C,F}} = 7.9$ Hz), 131.28, 130.17, 130.08, 129.52, 128.71, 125.79, 125.52, 114.23 (d, $J_{\text{C,F}} = 23.2$ Hz), 114.02 (d, $J_{\text{C,F}} = 22.4$ Hz), 50.73, 46.62, 40.75, 32.64, 31.09.

Polymerization Examples.

[0318] Solvents, polymerization grade toluene and/or isohexanes were supplied by ExxonMobil Chemical Company and were purified by passing through a series of columns: two 500 cm³ Oxyclear cylinders in series from Labclear (Oakland, California), followed by two 500 cm³ columns in series packed with dried 3 Å molecular sieves (8 mesh - 12 mesh; Aldrich Chemical Company), and two 500 cm³ columns in series packed with dried 5 Å molecular sieves (8-12 mesh; Aldrich Chemical Company).

[0319] 1-Octene (98%) (Aldrich Chemical Company) was dried by stirring over Na-K alloy overnight followed by filtration through basic alumina (Aldrich Chemical Company, Brockman Basic 1). Tri-(n-octyl)aluminum (TNOA) was purchased from either Aldrich Chemical Company or Akzo Nobel and used as received.

[0320] Polymerization grade ethylene was further purified by passing it through a series of columns: 500 cm³ Oxyclear cylinder from Labclear (Oakland, California) followed by a 500 cm³ column packed with dried 3 Å molecular sieves (8 mesh - 12 mesh; Aldrich Chemical Company), and a 500 cm³ column packed with dried 5 Å molecular sieves (8 mesh - 12 mesh; Aldrich Chemical Company).

[0321] Polymerization grade propylene was further purified by passing it through a series of columns: 2,250 cm³ Oxyclear cylinder from Labclear followed by a 2,250 cm³ column packed with 3 Å molecular sieves (8 mesh - 12 mesh; Aldrich Chemical Company), then two 500 cm³ columns in series packed with 5 Å molecular sieves (8 mesh - 12 mesh; Aldrich Chemical Company), a 500 cm³ column packed with Selexsorb CD (BASF), and finally a 500 cm³ column packed with Selexsorb COS (BASF).

[0322] Methylalumoxane (MAO) was purchased from Albemarle Corporation as a 10 wt% in toluene. N,N-Dimethylanilinium tetrakis(pentafluorophenyl)borate was purchased from Albemarle Corporation. All complexes and the activators were added to the reactor as dilute solutions in toluene. The concentrations of the solutions of activator, scavenger, and complexes that were added to the reactor were chosen so that between 40 microliters - 200 microliters of

the solution were added to the reactor to ensure accurate delivery.

[0323] Reactor Description and Preparation. Polymerizations were conducted in an inert atmosphere (N₂) drybox using autoclaves equipped with an external heater for temperature control, glass inserts (internal volume of reactor = 23.5 mL for C₂ and C₂/C₈ runs; 22.5 mL for C₃ runs), septum inlets, regulated supply of nitrogen, ethylene and propylene, and equipped with disposable polyether ether ketone mechanical stirrers (800 RPM). The autoclaves were prepared by purging with dry nitrogen at 110°C or 115°C for 5 hours and then at 25°C for 5 hours.

[0324] Ethylene Polymerization (PE) or Ethylene/1-Octene Copolymerization (EO) The reactor was prepared as described above, and then purged with ethylene. Toluene (solvent unless stated otherwise), optional 1-octene (0.1 mL when used), and optional MAO were added via syringe at room temperature and atmospheric pressure. The reactor was then brought to process temperature (typically 80°C) and charged with ethylene to process pressure (typically 75 psig=618.5 kPa or 200 psig=1480.3 kPa) while stirring at 800 RPM. An optional scavenger solution (e.g., TNOA in isohexane) was then added via syringe to the reactor at process conditions. An optional non-coordinating activator (e.g., N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate) solution (in toluene) was added via syringe to the reactor at process conditions, followed by a pre-catalyst (i.e., complex or catalyst) solution (in toluene) via syringe to the reactor at process conditions. Ethylene was allowed to enter (through the use of computer controlled solenoid valves) the autoclaves during polymerization to maintain reactor gauge pressure (+/-2 psi). Reactor temperature was monitored and typically maintained within +/-1°C. Polymerizations were halted by addition of approximately 50 psi O₂/Ar (5 mol% O₂) gas mixture to the autoclaves for approximately 30 seconds. The polymerizations were quenched after a predetermined cumulative amount of ethylene had been added or for a maximum of 30 minutes polymerization time. The reactors were cooled and vented. The polymer was isolated after the solvent was removed in-vacuo. Yields reported include total weight of polymer and residual catalyst. Catalyst activity is reported as grams of polymer per mmol transition metal compound per hour of reaction time (g/mmol/hr).

[0325] Propylene Polymerization The reactor was prepared as described above, then heated to 40°C and purged with propylene gas at atmospheric pressure. Toluene (solvent unless stated otherwise), optional MAO, and liquid propylene (1.0 mL) were added via syringe. The reactor was then heated to process temperature (70°C or 100°C) while stirring at 800 RPM. Then optional scavenger solution (e.g., TNOA in isohexane) was added via syringe to the reactor at process conditions. Optional non-coordinating activator (e.g., N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate) solution (in toluene) was then added via syringe to the reactor

- at process conditions, followed by a pre-catalyst (i.e., complex or catalyst) solution (in toluene) via syringe to the reactor at process conditions. Reactor temperature was monitored and typically maintained within $\pm 1^{\circ}\text{C}$. Polymerizations were halted by addition of approximately 50 psi O_2/Ar (5 mol% O_2) gas mixture to the autoclaves for approximately 30 seconds. The polymerizations were quenched based on a predetermined pressure loss of approximately 8 psi or for a maximum of 30 minutes polymerization time. The reactors were cooled and vented. The polymer was isolated after the solvent was removed in-vacuo. Yields reported include total weight of polymer and residual catalyst. Catalyst activities are typically reported as grams of polymer per mmol transition metal compound per hour of reaction time (g/mmol/hr).
- 10 **[0326]** Polymer Characterization For analytical testing, polymer sample solutions were prepared by dissolving the polymer in 1,2,4-trichlorobenzene (TCB, 99+% purity from Sigma-Aldrich) containing 2,6-di-tert-butyl-4-methylphenol (BHT, 99% from Aldrich) at 165°C in a shaker oven for approximately 3 hours. The typical concentration of polymer in solution was between 0.1 to 0.9 mg/mL with a BHT concentration of 1.25 mg BHT/mL of TCB. Samples
- 15 were cooled to 135°C for testing.
- [0327]** High temperature size exclusion chromatography was performed using an automated "Rapid GPC" system as described in U.S. Patent Nos. 6,491,816; 6,491,823; 6,475,391; 6,461,515; 6,436,292; 6,406,632; 6,175,409; 6,454,947; 6,260,407; and 6,294,388; each of which is incorporated herein by reference. Molecular weights (weight average molecular weight
- 20 (Mw) and number average molecular weight (Mn)) and molecular weight distribution ($\text{MWD} = \text{Mw}/\text{Mn}$), which is also sometimes referred to as the polydispersity (PDI) of the polymer, were measured by Gel Permeation Chromatography using a Symyx Technology GPC equipped with evaporative light scattering detector and calibrated using polystyrene standards (Polymer Laboratories: Polystyrene Calibration Kit S-M-10: Mp (peak Mw) between 5,000 and
- 25 3,390,000). Samples (250 μL of a polymer solution in TCB were injected into the system) were run at an eluent flow rate of 2.0 mL/minute (135°C sample temperatures, 165°C oven/columns) using three Polymer Laboratories: PLgel 10 μm Mixed-B 300 x 7.5mm columns in series. No column spreading corrections were employed. Numerical analyses were performed using Epoch[®] software available from Symyx Technologies or Automation Studio software available
- 30 from Freeslate. The molecular weights obtained are relative to linear polystyrene standards.
- [0328]** Differential Scanning Calorimetry (DSC) measurements were performed on a TA-Q100 instrument to determine the melting point of the polymers. Samples were pre-annealed at 220°C for 15 minutes and then allowed to cool to room temperature overnight. The samples were then heated to 220°C at a rate of $100^{\circ}\text{C}/\text{minute}$ and then cooled at a rate of

50°C/minute. Melting points were collected during the heating period.

[0329] Table 1 illustrates ethylene polymerization results obtained using catalyst complexes **1** through **21** and **23** through **27**. *General conditions:* catalyst complex = 25 nmol, N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate activator = 1.1 equiv, 75 psig ethylene, Al(n-octyl)₃ = 500 nmol, temperature = 80°C, total volume = 5 mL.

Table 1. Ethylene polymerizations

Run	Catalyst	Quench t (s)	Yield (g)	Activity (gP.mmolcat ⁻¹ .h ⁻¹)
1	1	416	0.0769	26,619
2	1	1089	0.0781	10,327
3	1	460	0.0749	23,447
4	2	98	0.0686	100,800
5	2	263	0.0695	38,053
6	2	253	0.0724	41,208
7	3	31	0.0918	426,426
8	3	7	0.1054	2,168,229
9	3	26	0.0916	507,323
10	4	53	0.0902	245,072
11	4	54	0.0891	237,600
12	4	52	0.0889	246,185
13	5	32	0.0844	379,800
14	5	14	0.0834	857,829
15	5	24	0.0901	540,600
16	6	46	0.0869	272,035
17	6	36	0.0895	358,000
18	6	17	0.0922	780,988
19	7	82.4	0.0787	137,534
20	7	248.9	0.073	42,234
21	7	77.6	0.0879	163,113
22	8	111	0.0695	90,162
23	8	109	0.0781	103,178
24	8	115	0.0778	97,419
25	9	79.1	0.0804	146,367

26	9	95.7	0.0668	100,514
27	9	87.1	0.0729	120,524
28	10	54	0.0681	181,600
29	10	59	0.0796	194,278
30	10	49	0.0771	226,580
31	11	43.2	0.081	270,000
32	11	48.5	0.0826	245,245
33	11	46.4	0.0774	240,207
34	12	91	0.0708	112,035
35	12	78	0.0709	130,892
36	12	134	0.0665	71,463
37	13	50	0.0892	256,896
38	13	50	0.088	253,440
39	13	56	0.0879	226,029
40	14	46.9	0.0842	258,525
41	14	49.4	0.0831	242,235
42	14	46.7	0.0808	249,148
43	15	203	0.0835	59,232
44	15	147.1	0.0822	80,468
45	15	207.7	0.0794	55,049
46	16	48	0.0855	256,500
47	16	46	0.0822	257,322
48	16	50	0.0877	252,576
49	17	333	0.0327	14,141
50	17	348	0.0371	15,352
51	17	321	0.0369	16,553
52	18	200	0.0474	34,128
53	18	163	0.0412	36,398
54	18	168	0.0409	35,057
55	19	65	0.0742	164,382
56	19	64	0.074	166,500
57	19	62	0.0783	181,858
58	20	43	0.0877	293,693

59	20	59	0.0902	220,149
60	20	38	0.0607	230,021
61	21	98	0.0836	122,841
62	21	135	0.0806	85,973
63	21	48	0.0876	262,800
64	23	50	0.066	190,080
65	23	48	0.0695	208,500
66	23	39	0.0693	255,877
67	24	69	0.0953	198,887
68	24	67	0.0885	190,209
69	24	63	0.0862	197,029
70	25	71	0.0725	147,042
71	25	68	0.0716	151,624
72	25	69	0.0663	138,365
73	26	222	0.085	55,135
74	26	147	0.0843	82,580
75	26	182	0.0824	65,196
76	27	59	0.0975	237,966
77	27	61	0.0971	229,220
78	27	70	0.0928	190,903

Table 1 (*continued*)

Run	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	PDI	Tm (°C)
1	2,004,102	3,508,278	6,058,808	1.8	135
2	1,812,211	3,330,436	6,011,441	1.8	136
3	1,985,483	3,657,204	6,438,001	1.8	135
4	915,431	1,577,332	3,619,895	1.7	137
5	707,039	1,493,072	3,923,309	2.1	136
6	653,395	1,446,718	3,493,649	2.2	137
7					135
8	2,161,337	3,195,236	5,268,759	1.5	
9	879,099	2,860,284	5,513,768	3.3	135
10	943,934	1,857,405	4,176,064	2.0	136

11					136
12	739,206	1,684,302	4,499,649	2.3	137
13	1,145,262	2,917,976	5,439,049	2.6	135
14	1,021,364	2,697,262	6,248,907	2.6	135
15	1,684,279	2,897,994	5,189,147	1.7	134
16	1,102,965	2,807,009	5,465,690	2.5	136
17	18,761	2,317,736	6,752,743	123.5	136
18	27,051	2,149,810	6,142,423	79.5	136
19	1,375,402	2,733,343	5,180,063	2.0	
20	1,699,100	2,969,637	5,135,613	1.8	
21	2,067,265	3,240,013	5,277,174	1.6	
22	1,491,496	2,837,772	5,314,767	1.9	125
23	1,863,731	3,224,258	5,466,214	1.7	130
24	1,723,428	2,795,187	4,804,915	1.6	131
25	888,842	1,609,688	3,596,117	1.8	
26	821,525	1,530,616	3,585,066	1.9	
27	785,119	1,525,983	3,461,741	1.9	
28	241,214	431,495	881,437	1.8	133
29	227,326	419,407	906,656	1.8	133
30	258,136	435,592	867,799	1.7	132
31	194,980	330,811	683,995	1.7	
32	188,679	332,346	706,847	1.8	
33	181,036	314,940	649,154	1.7	
34	398,883	1,688,018	4,353,093	4.2	128
35	686,994	1,849,068	4,745,376	2.7	129
36	795,122	1,779,500	4,324,068	2.2	128
37	578,404	1,459,579	3,610,799	2.5	129
38	723,580	1,508,631	3,825,429	2.1	129
39	898,548	1,597,999	3,918,676	1.8	129
40	232,750	403,003	1,064,533	1.7	
41	192,420	372,021	873,075	1.9	
42	209,254	380,174	884,629	1.8	
43	755,505	1,287,811	2,646,678	1.7	

44	736,928	1,442,786	3,681,511	2.0	
45	706,376	1,330,185	3,103,728	1.9	
46	180,810	337,273	669,758	1.9	137
47	185,039	337,950	659,538	1.8	137
48	195,198	346,400	666,159	1.8	137
49	61,619	100,137	203,992	1.6	136
50	69,128	104,651	200,220	1.5	136
51	60,298	100,735	214,652	1.7	136
52	74,372	113,507	214,257	1.5	136
53	72,775	111,201	215,998	1.5	136
54	70,405	112,236	225,100	1.6	136
55	155,630	261,775	463,162	1.7	138
56	152,529	254,231	445,894	1.7	138
57	153,352	257,506	444,811	1.7	137
58	440,463	720,611	1,296,627	1.6	134
59	332,535	686,705	1,370,931	2.1	133
60	412,435	709,777	1,340,257	1.7	134
61	1,062,199	2,318,102	4,987,805	2.2	134
62	2,099,850	3,124,630	5,150,972	1.5	135
63	1,064,835	2,246,776	4,688,318	2.1	135
64	191,430	347,774	736,708	1.8	135
65	175,904	330,521	748,185	1.9	134
66	213,549	356,034	784,577	1.7	134
67	356,395	827,139	3,348,111	2.3	135
68	352,136	582,674	1,157,705	1.7	135
69	342,453	562,926	1,107,568	1.6	136
70	130,779	209,205	374,870	1.6	137
71	128,023	210,315	384,186	1.6	137
72	137,004	206,144	360,049	1.5	137
73	424,576	738,862	1,501,676	1.7	135
74	384,811	716,872	1,520,234	1.9	136
75	362,746	683,326	1,499,750	1.9	135
76	482,351	1,630,381	5,817,836	3.4	135

77	403,487	1,139,043	4,215,676	2.8	135
78	363,411	1,043,056	3,990,190	2.9	135

- [0330]** Table 2 illustrates ethylene-octene copolymerization results obtained using Catalysts **1** through **21** and **23** through **27**. *General conditions:* catalyst complex = 25 nmol, N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate activator = 27.5 nmol, 0.1 mL octene, 5 Al(n-octyl)₃ = 500 nmol, temperature = 80°C, total volume = 5 mL, ethylene = 75 psi.

Table 2. Ethylene-octene copolymerizations

Run	Catalyst	Quench t (s)	Yield (g)	Activity (gP.mmolcat ⁻¹ .h ⁻¹)
1	1	314	0.1376	63,103
2	1	414	0.1197	41,635
3	1	326	0.1374	60,692
4	2	443	0.0962	31,270
5	2	573	0.1069	26,865
6	2	612	0.1011	23,788
7	3	56	0.1368	351,771
8	3	50	0.1436	413,568
9	4	92	0.1285	201,130
10	4	67	0.1323	284,346
11	4	97	0.1331	197,592
12	5	368	0.135	52,826
13	5	349	0.1364	56,280
14	5	336	0.1287	55,157
15	6	60	0.1406	337,440
16	6	43	0.1331	445,730
17	6	58	0.1335	331,448
18	7	260	0.2198	121,923
19	7	294	0.1487	72,957
20	7	270	0.1482	79,040
21	8	377	0.1222	46,676
22	8	253	0.1194	67,959
23	8	379	0.1233	46,847

24	9	916	0.1276	20,068
25	9	410	0.1369	48,047
26	9	663	0.1363	29,626
27	10	41	0.1004	352,624
28	10	42	0.0935	320,571
29	10	39	0.0983	362,954
30	11	47	0.0905	276,102
31	11	47	0.086	263,489
32	11	47	0.0893	274,183
33	12	76	0.1286	243,663
34	12	75	0.1292	248,064
35	12	66	0.1212	264,436
36	13	35	0.1163	478,491
37	13	70	0.1184	243,566
38	13	47	0.1087	333,038
39	14	46	0.0963	298,862
40	14	42	0.0907	310,971
41	14	37	0.0884	346,856
42	15	313	0.1382	63,621
43	15	271	0.129	68,546
44	15	266	0.1409	76,305
45	16	45	0.0948	303,360
46	16	48	0.0957	287,100
47	16	45	0.096	307,200
48	17	320	0.034	15,300
49	17	293	0.0343	16,857
50	17	312	0.0352	16,246
51	18	139	0.0417	43,200
52	18	154	0.0397	37,122
53	18	143	0.0404	40,683
54	19	65	0.0844	186,978
55	19	63	0.088	201,143
56	19	65	0.0816	180,775

57	20	30	0.1497	718,560
58	20	29	0.1374	682,262
59	20	30	0.1489	714,720
60	21	266	0.1231	66,641
61	21	162	0.1195	106,222
62	21	149	0.117	113,074
63	23	44	0.0775	253,636
64	23	46	0.0802	251,061
65	23	41	0.0863	303,102
66	24	50	0.1387	399,456
67	24	30	0.1277	612,960
68	24	49	0.1372	403,200
69	25	55	0.0837	219,142
70	25	60	0.0806	193,440
71	25	51	0.0925	261,176
72	26	59	0.1443	352,190
73	26	78	0.1472	271,754
74	26	72	0.147	294,000
75	27	68	0.1534	324,847
76	27	64	0.1506	338,850
77	27	81	0.1522	270,578

Table 2 (*continued*)

Run	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	PDI	Tm (°C)
1	161,997	955,709	4,739,567	5.9	95
2	205,441	1,069,949	5,083,639	5.2	93
3	178,156	929,140	4,525,214	5.2	93
4	147,955	629,288	1,822,682	4.3	103
5	121,245	566,125	1,875,004	4.7	102
6	124,292	571,111	1,986,338	4.6	102
7	115,700	1,432,761	5,128,072	12.4	115
8	84,323	1,216,026	5,071,317	14.4	102
9	18,223	660,036	3,393,646	36.2	113

10	30,989	511,916	2,150,128	16.5	107
11	31,702	537,738	2,526,986	17.0	108
12	196,740	978,942	3,929,325	5.0	91
13	193,210	837,801	3,792,106	4.3	96
14	167,519	831,730	3,751,209	5.0	97
15	58,389	1,079,209	4,418,742	18.5	87
16	64,061	1,269,277	4,293,191	19.8	106
17	96,352	1,414,065	4,829,213	14.7	111
18	175,559	1,277,761	4,760,522	7.3	
19	84,777	972,681	5,032,744	11.5	
20	139,691	972,787	3,817,190	7.0	
21	315,132	707,875	2,275,848	2.3	81
22	388,155	743,414	1,960,566	1.9	78
23	315,180	737,340	1,917,913	2.3	81
24	57,426	536,839	2,961,332	9.4	
25	43,670	485,287	2,632,049	11.1	
26	78,778	691,918	2,772,687	8.8	
27	110,419	203,140	476,397	1.8	101
28	118,053	228,700	586,178	1.9	101
29	107,700	220,261	666,863	2.1	102
30	148,492	244,848	455,165	1.7	
31	166,408	264,282	493,932	1.6	
32	135,576	240,526	465,563	1.8	
33	119,414	360,282	1,208,229	3.0	49
34	108,991	337,658	1,158,756	3.1	45
35	102,449	366,502	1,335,284	3.6	91
36	30,688	500,581	2,377,430	16.3	108
37	47,228	833,946	4,010,256	17.7	116
38	109,448	3,020,935	6,325,311	27.6	121
39	141,939	262,805	632,195	1.9	
40	143,467	262,538	591,870	1.8	
41	139,164	242,256	487,647	1.7	
42	39,853	452,196	2,239,364	11.4	

43	62,919	511,848	2,143,693	8.1	
44	62,472	567,233	2,755,101	9.1	
45	82,363	253,307	629,280	3.1	111
46	149,720	281,851	608,734	1.9	112
47	118,812	261,816	607,863	2.2	111
48	58,489	96,699	201,241	1.7	120
49	49,643	90,046	178,956	1.8	119
50	51,714	88,318	172,638	1.7	119
51	52,394	95,783	190,704	1.8	119
52	57,206	102,840	248,907	1.8	120
53	58,996	99,460	200,217	1.7	118
54	147,396	233,583	411,420	1.6	108
55	141,136	228,305	411,672	1.6	107
56	137,169	226,803	402,253	1.7	108
57	53,863	147,333	365,502	2.7	112
58	73,992	165,319	363,647	2.2	111
59	50,132	143,697	359,374	2.9	112
60	183,162	789,666	3,651,129	4.3	83
61	186,080	547,667	1,609,886	2.9	89
62	164,701	487,882	1,469,224	3.0	88
63	145,719	276,681	626,677	1.9	111
64	163,495	291,028	645,864	1.8	111
65	127,438	259,144	633,339	2.0	111
66	90,341	288,725	877,502	3.2	44
67	76,149	274,100	823,697	3.6	97
68	82,908	283,065	895,391	3.4	106
69	112,353	186,608	345,162	1.7	105
70	122,869	190,423	337,086	1.6	104
71	108,022	183,870	352,966	1.7	105
72	119,232	374,399	1,040,156	3.1	109
73	106,030	351,569	1,001,951	3.3	110
74	132,265	364,947	995,808	2.8	110
75	161,484	393,868	938,443	2.4	109

76	129,637	376,574	970,116	2.9	110
77	134,847	399,368	1,112,636	3.0	110

- [0331]** Table 3 illustrates ethylene-octene copolymerization results obtained using Catalysts **1** through **21** and **23** through **27**. *General conditions:* catalyst complex = 25 nmol, N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate activator = 27.5 nmol, 0.1 mL octene, 5 Al(n-octyl)₃ = 500 nmol, temperature = 80°C, total volume = 5 mL, ethylene = 200 psi.

Table 3. Ethylene-octene copolymerizations

Run	Catalyst	Quench t (s)	Yield (g)	Activity (gP.mmolcat ⁻¹ .h ⁻¹)
1	1	63	0.2011	459,657
2	1	60	0.1906	457,440
3	1	57	0.1878	474,442
4	2	86	0.1672	279,963
5	2	92	0.1682	263,270
6	2	96	0.1761	264,150
7	3	11	0.1913	2,504,291
8	3	49	0.1835	539,265
9	3	8	0.1802	3,243,600
10	4	27	0.1824	972,800
11	4	32	0.1951	877,950
12	4	30	0.1995	957,600
13	5	12	0.1906	2,287,200
14	5	6	0.1767	4,240,800
15	5	20	0.2006	1,444,320
16	6	13	0.1896	2,100,185
17	6	10	0.2116	3,047,040
18	6	9	0.1964	3,142,400
19	7	30	0.1762	857,189
20	7	6	0.1848	4,292,129
21	7	34	0.1801	769,567
22	8	59	0.1854	452,502
23	8	40	0.1901	684,360

24	8	35	0.1859	764,846
25	9	66	0.2086	456,511
26	9	60	0.1993	475,940
27	9	59	0.1984	485,878
28	10	32	0.1749	787,050
29	10	27	0.17	906,667
30	10	30	0.1739	834,720
31	11	32	0.1542	696,075
32	11	37	0.1448	571,266
33	11	39	0.1618	592,855
34	12	107	0.1896	255,163
35	12	114	0.1882	237,726
36	12	89	0.1913	309,519
37	13	40	0.2127	765,720
38	13	24	0.2036	1,221,600
39	13	31	0.2021	938,787
40	14	48	0.1627	487,085
41	14	44	0.1646	543,633
42	14	44	0.1669	543,747
43	15	45	0.2018	644,328
44	15	47	0.1985	613,391
45	15	53	0.1897	516,386
46	16	45	0.1773	567,360
47	16	43	0.1767	591,740
48	16	41	0.1772	622,361
49	17	108	0.0323	43,067
50	17	108	0.0312	41,600
51	17	114	0.0332	41,937
52	18	61	0.0442	104,341
53	18	62	0.0432	100,335
54	18	59	0.0419	102,264
55	19	41	0.1449	508,917
56	19	38	0.1422	538,863

57	19	39	0.1364	503,631
58	20	18	0.2182	1,745,600
59	20	15	0.2093	2,009,280
60	20	15	0.211	2,025,600
61	21	64	0.1979	445,275
62	21	70	0.2044	420,480
63	21	72	0.2077	415,400
64	23	84	0.1614	276,686
65	23	50	0.1557	448,416
66	23	52	0.1529	423,415
67	24	25	0.2019	1,162,944
68	24	19	0.1909	1,446,821
69	24	18	0.1946	1,556,800
70	25	35	0.1376	566,126
71	25	32	0.1423	640,350
72	25	35	0.1512	622,080
73	26	45	0.2215	708,800
74	26	43	0.2162	724,019
75	27	23	0.2078	1,301,009
76	27	21	0.2131	1,461,257
77	27	17	0.2106	1,783,906

Table 3 (*continued*)

Run	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	PDI	Tm (°C)
1	85,401	1,485,453	6,355,326	17.4	101
2	180,860	1,668,124	5,601,126	9.2	104
3	236,581	1,637,737	5,656,677	6.9	102
4	341,563	936,687	2,901,398	2.7	114
5	376,309	941,200	2,592,050	2.5	114
6	469,738	1,075,532	2,943,419	2.3	115
7	360,049	1,593,060	4,658,669	4.4	107
8	181,413	1,818,545	5,258,186	10.0	104
9	530,776	1,946,618	5,423,261	3.7	112

10	140,030	910,929	3,364,397	6.5	117
11	44,006	580,387	2,290,085	13.2	116
12	110,628	856,406	2,725,790	7.7	118
13	185,667	1,465,572	6,887,083	7.9	105
14	203,556	1,383,705	4,746,359	6.8	103
15	369,885	1,706,602	4,840,739	4.6	100
16	173,492	1,697,638	4,780,399	9.8	118
17	274,177	1,595,198	5,114,168	5.8	116
18	277,610	1,879,652	6,137,205	6.8	109
19	500,623	1,766,457	4,640,325	3.5	
20	308,085	1,388,633	4,176,051	4.5	
21	292,254	1,485,896	4,349,242	5.1	
22	362,076	1,153,603	4,114,232	3.2	96
23	436,756	1,347,977	4,017,596	3.1	92
24	354,747	1,247,681	4,148,314	3.5	92
25	79,236	809,610	2,829,093	10.2	
26	40,170	750,673	2,900,422	18.7	
27	84,743	840,000	3,213,682	9.9	
28	132,102	251,512	578,430	1.9	116
29	134,605	245,986	546,940	1.8	117
30	124,229	237,800	524,744	1.9	116
31	151,380	283,526	670,080	1.9	
32	176,380	307,742	844,612	1.7	
33	149,502	280,963	658,141	1.9	
34	172,197	725,395	2,365,079	4.2	106
35	172,704	734,109	2,282,891	4.3	105
36	135,436	720,066	2,086,851	5.3	105
37	107,278	599,466	1,669,191	5.6	109
38	28,277	532,284	2,645,799	18.8	109
39	79,681	881,521	4,158,764	11.1	119
40	151,723	303,322	837,091	2.0	
41	148,038	276,539	580,589	1.9	
42	147,112	279,459	637,111	1.9	

43	49,484	707,025	2,599,229	14.3	
44	125,921	849,967	2,507,527	6.8	
45	59,297	695,247	2,869,724	11.7	
46	145,865	274,830	569,106	1.9	121
47	139,228	274,426	603,713	2.0	121
48	122,654	274,081	608,076	2.2	121
49	61,528	104,630	228,160	1.7	127
50	58,343	97,568	175,894	1.7	127
51	62,128	100,718	195,510	1.6	127
52	59,950	107,817	219,574	1.8	127
53	69,862	106,218	192,777	1.5	127
54	69,428	109,841	208,302	1.6	127
55	138,388	225,477	404,513	1.6	120
56	135,674	223,304	403,911	1.7	120
57	136,672	218,721	381,057	1.6	120
58	112,359	195,655	371,424	1.7	121
59	74,247	173,444	363,325	2.3	121
60	81,740	173,984	363,936	2.1	121
61	187,594	845,744	3,309,842	4.5	103
62	151,568	654,377	2,310,686	4.3	102
63	116,325	658,679	2,367,821	5.7	102
64	166,164	328,692	777,508	2.0	120
65	174,412	313,826	662,335	1.8	120
66	159,468	303,314	630,772	1.9	120
67	121,920	282,922	681,440	2.3	98
68	114,740	289,844	748,004	2.5	101
69	109,413	274,702	683,229	2.5	104
70	106,097	180,804	347,692	1.7	118
71	110,549	174,930	314,673	1.6	117
72	107,376	172,039	312,699	1.6	118
73	80,368	378,371	924,364	4.7	118
74	43,979	344,982	1,043,893	7.8	119
75	254,753	437,223	943,982	1.7	119

76	238,741	444,457	1,030,413	1.9	120
77	208,367	409,932	900,141	2.0	119

[0332] Table 4 illustrates propylene polymerization results obtained for Catalysts **1** through **28**. *General conditions:* catalyst complex = 15 nmol (exceptions are 25 nmol for catalyst **26**; 20 nmol for catalyst **22** and **28**), N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate
 5 activator = 1.1 molar equivalent relative to catalyst complex, propylene = 1 mL, Al(n-octyl)₃ = 500 nmol, total volume = 5 mL.

Table 4. Propylene polymerizations

Run	Catalyst	Temperature (°C)	Quench t (s)	Yield (g)	Activity (gP.mmolcat ⁻¹ .h ⁻¹)
1	1	70	73	0.4563	1,500,164
2	1	70	107	0.4111	922,093
3	1	70	85	0.3556	1,004,047
4	2	70	80	0.3253	975,900
5	2	70	75	0.3729	1,193,280
6	2	70	75	0.3297	1,055,040
7	3	70	15	0.3543	5,668,800
8	3	70	13	0.4127	7,619,077
9	3	70	14	0.4037	6,920,571
10	4	70	23	0.3712	3,873,391
11	4	70	24	0.4204	4,204,000
12	4	70	29	0.3914	3,239,172
13	5	70	59	0.3295	1,340,339
14	5	70	70	0.3701	1,268,914
15	5	70	58	0.3412	1,411,862
16	6	70	7	0.3795	13,011,429
17	6	70	11	0.4079	8,899,636
18	6	70	21	0.395	4,514,286
19	7	70	65	0.3707	1,368,738
20	7	70	58	0.3728	1,542,621
21	7	70	55	0.375	1,636,364
22	8	70	117	0.1833	376,000

23	8	70	69	0.1396	485,565
24	8	70	132	0.2025	368,182
25	9	70	50	0.3469	1,665,120
26	9	70	51	0.3773	1,775,529
27	9	70	60	0.4035	1,614,000
28	10	70	59	0.2298	934,780
29	10	70	56	0.2461	1,054,714
30	12	70	38	0.2896	1,829,053
31	12	70	41	0.3211	1,879,610
32	12	70	44	0.2789	1,521,273
33	13	70	16	0.3878	5,817,000
34	13	70	17	0.4334	6,118,588
35	13	70	20	0.4131	4,957,200
36	14	70	129	0.1889	351,442
37	14	70	127	0.2059	389,102
38	14	70	129	0.1976	367,628
39	15	70	74	0.3575	1,159,459
40	15	70	77	0.386	1,203,117
41	15	70	77	0.3735	1,164,156
42	16	70	168	0.1514	216,286
43	16	70	166	0.162	234,217
44	16	70	174	0.1427	196,828
45	17	70	1800	0.0075	1,000
46	17	70	1802	0.0078	1,039
47	17	70	1801	0.0056	746
48	18	70	1800	0.0277	3,693
49	18	70	1801	0.0289	3,851
50	18	70	1800	0.0194	2,587
51	19	70	197	0.1291	157,279
52	19	70	213	0.1351	152,225
53	19	70	219	0.1268	138,959
54	20	70	51	0.2961	1,393,412
55	20	70	57	0.3251	1,368,842

56	20	70	59	0.2944	1,197,559
57	21	70	103	0.2777	647,068
58	21	70	89	0.2498	673,618
59	21	70	123	0.2502	488,195
60	22	70	12	0.4126	6,087,541
61	22	70	12	0.4715	7,380,000
62	22	70	4	0.3113	15,144,324
63	23	70	131	0.155	283,969
64	23	70	104	0.1861	429,462
65	23	70	112	0.1871	400,929
66	24	70	54	0.2594	1,152,889
67	24	70	40	0.3031	1,818,600
68	24	70	68	0.2214	781,412
69	25	70	1800	0.0526	7,013
70	25	70	1803	0.0582	7,747
71	25	70	1801	0.0495	6,596
72	26	70	24	0.3654	2,192,400
73	26	70	23	0.3858	2,415,443
74	26	70	22	0.3841	2,514,109
75	27	70	23	0.6217	6,487,304
76	27	70	17	0.4999	7,057,412
77	27	70	22	0.6582	7,180,364
78	28	70	1201	-0.0003	-45
79	28	70	1201	-0.0008	-120
80	28	70	1201	-0.0013	-210

Table 4 (*continued*)

run #	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	PDI	Tm (°C)
1	114,466	489,547	1,650,145	4.3	159
2	24,847	442,963	1,925,442	17.8	159
3	140,909	430,206	1,428,541	3.1	159
4	165,597	334,380	903,938	2.0	161
5	125,777	334,087	1,073,656	2.7	161
6	114,722	316,540	1,030,692	2.8	160
7	57,753	372,797	1,464,190	6.5	148
8	64,376	502,821	2,141,863	7.8	147
9	67,290	428,075	1,753,319	6.4	148
10	17,744	126,712	777,632	7.1	150
11	27,138	162,274	909,810	6.0	151
12	18,561	174,783	1,116,895	9.4	151
13	155,932	393,075	1,312,570	2.5	159
14	115,043	360,466	1,191,971	3.1	158
15	145,110	381,122	1,231,459	2.6	158
16	118,914	474,918	1,790,054	4.0	149
17	158,183	461,138	1,272,034	2.9	148
18	103,834	456,352	1,650,050	4.4	148
19	96,491	420,800	2,185,151	4.4	160
20	104,115	408,527	2,023,472	3.9	159
21	73,631	416,915	2,300,681	5.7	159
22	219,456	388,248	912,947	1.8	153
23	221,954	414,051	948,937	1.9	153
24	217,410	410,493	969,131	1.9	153
25	124,917	330,194	1,050,495	2.6	160
26	117,874	310,304	915,337	2.6	160
27	96,278	345,774	1,434,803	3.6	159
28	84,383	132,546	247,855	1.6	160
29	71,943	126,703	289,153	1.8	160
30	139,309	282,465	778,339	2.0	158
31	115,357	249,864	664,624	2.2	158

32	146,270	290,344	703,139	2.0	159
33	49,236	161,383	648,392	3.3	146
34	40,362	150,799	619,430	3.7	145
35	45,927	159,308	617,869	3.5	146
36	167,562	276,114	554,940	1.7	161
37	180,217	294,473	612,269	1.6	161
38	135,871	278,711	597,323	2.1	162
39	119,886	290,039	942,218	2.4	162
40	107,158	320,828	1,122,488	3.0	162
41	110,748	310,245	984,005	2.8	161
42	211,948	353,711	695,938	1.7	162
43	220,371	363,530	706,255	1.7	162
44	232,443	383,689	752,363	1.7	161
45					
46					
47					
48	89,484	141,777	275,634	1.6	161
49	94,741	157,074	318,366	1.7	162
50	104,985	168,698	355,199	1.6	160
51	389,178	534,771	895,536	1.4	165
52	366,407	556,215	1,064,994	1.5	164
53	313,864	504,232	930,019	1.6	164
54	91,504	180,050	482,488	2.0	157
55	106,054	191,739	441,346	1.8	156
56	111,683	224,774	579,509	2.0	156
57	265,095	467,578	1,005,189	1.8	160
58	290,087	522,788	1,256,300	1.8	161
59	254,920	520,019	1,153,915	2.0	160
60	113,845	442,847	1,318,498	3.9	148
61	114,737	472,426	1,495,833	4.1	148
62	148,262	556,887	1,788,572	3.8	149
63	236,065	379,539	787,141	1.6	163
64	241,281	369,976	707,824	1.5	163

65	213,875	345,238	656,339	1.6	162
66	122,299	265,834	638,521	2.2	156
67	143,976	283,789	696,323	2.0	154
68	225,712	382,889	790,054	1.7	155
69	359,476	628,998	1,229,198	1.8	165
70	481,757	696,025	1,266,140	1.4	165
71	473,707	664,232	1,140,439	1.4	167
72	47,408	90,386	201,296	1.9	151
73	45,291	92,784	221,513	2.1	151
74	50,123	92,438	210,009	1.8	151
75	57,344	91,990	166,659	1.6	144
76	49,320	80,825	156,835	1.6	141
77	41,329	86,747	176,312	2.1	143

- [0333] Table 5 illustrates propylene polymerization results obtained for Catalysts **1** through **28**. *General conditions:* catalyst complex = 15 nmol (exceptions are 25 nmol for catalyst **26**; exceptions are 20 nmol for catalyst **22** and **28**), N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate activator = 1.1 molar equivalent relative to catalyst complex, propylene = 1 mL, Al(n-octyl)₃ = 500 nmol, total volume = 5 mL.

Table 5. Propylene polymerizations

Run	Catalyst	Temperature (°C)	Quench t (s)	Yield (g)	Activity (gP.mmolcat ⁻¹ .h ⁻¹)
1	1	100	46	0.2208	1,152,000
2	1	100	55	0.2204	961,745
3	1	100	44	0.2229	1,215,818
4	2	100	54	0.2062	916,444
5	2	100	59	0.2047	832,678
6	2	100	62	0.1908	738,581
7	3	100	16	0.2621	3,931,500
8	3	100	17	0.3151	4,448,471
9	3	100	20	0.2204	2,644,800
10	4	100	16	0.2991	4,486,500

11	4	100	25	0.2921	2,804,160
12	4	100	23	0.2986	3,115,826
13	5	100	33	0.2318	1,685,818
14	5	100	36	0.2135	1,423,333
15	5	100	32	0.2554	1,915,500
16	6	100	13	0.1692	3,123,692
17	6	100	19	0.3026	3,822,316
18	6	100	21	0.2996	3,424,000
19	7	100	34	0.2756	1,945,412
20	7	100	31	0.2734	2,116,645
21	7	100	29	0.2755	2,280,000
22	8	100	155	0.1025	158,710
23	8	100	102	0.1334	313,882
24	8	100	80	0.1523	456,900
25	9	100	31	0.1557	1,205,419
26	9	100	55	0.2251	982,255
27	9	100	40	0.2391	1,434,600
28	10	100	56	0.1086	465,429
29	10	100	80	0.1018	305,400
30	10	100	60	0.1099	439,600
31	12	100	38	0.1515	956,842
32	12	100	44	0.1443	787,091
33	12	100	37	0.1451	941,189
34	13	100	19	0.2893	3,654,316
35	13	100	17	0.2765	3,903,529
36	13	100	20	0.2807	3,368,400
37	14	100	116	0.1415	292,759
38	14	100	114	0.1465	308,421
39	14	100	113	0.1296	275,257
40	15	100	45	0.2523	1,345,600
41	15	100	43	0.2332	1,301,581
42	15	100	56	0.2208	946,286
43	16	100	226	0.0744	79,009

44	16	100	1801	0.037	4,931
45	16	100	1801	0.0147	1,959
46	17	100	1800	0.0002	27
47	17	100	1801	-0.0006	-80
48	17	100	1801	0.001	133
49	18	100	1801	0.0002	27
50	18	100	1800	-0.0006	-80
51	18	100	1801	-0.0006	-80
52	19	100	1800	0.0598	7,973
53	19	100	1354	0.0603	10,688
54	19	100	1800	0.0579	7,720
55	20	100	45	0.2041	1,088,533
56	20	100	49	0.2147	1,051,592
57	20	100	76	0.1811	571,895
58	21	100	75	0.1306	417,920
59	21	100	77	0.1493	465,351
60	21	100	63	0.1537	585,524
61	22	100	17	0.3162	3,328,421
62	22	100	18	0.3054	3,020,440
63	22	100	11	0.2004	3,192,212
64	23	100	148	0.0833	135,081
65	23	100	1801	0.0566	7,542
66	23	100	1105	0.0769	16,702
67	24	100	1801	0.0287	3,825
68	24	100	1801	0.0693	9,235
69	25	100	1801	0.0181	2,412
70	25	100	1801	0.0171	2,279
71	25	100	1801	0.0165	2,199
72	26	100	24	0.2007	1,204,200
73	26	100	26	0.1983	1,098,277
74	26	100	20	0.215	1,548,000
75	27	100	31	0.3777	2,924,129
76	27	100	23	0.3991	4,164,522

77	27	100	30	0.4022	3,217,600
78	28	100	1201	-0.0001	-15
79	28	100	1201	-0.0003	-45
80	28	100	1201	-0.0012	-180

Table 5 (*continued*)

run #	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	PDI	Tm (°C)
1	80,499	164,360	471,700	2.0	158
2	75,757	153,238	419,844	2.0	158
3	75,647	169,707	606,761	2.2	158
4	62,140	120,721	248,648	1.9	161
5	61,125	122,674	253,423	2.0	161
6	68,611	129,273	256,101	1.9	160
7	28,762	152,087	646,646	5.3	146
8	34,553	155,815	665,846	4.5	146
9	48,560	169,007	624,200	3.5	147
10	12,695	47,275	167,729	3.7	147
11	15,617	49,959	158,779	3.2	149
12	14,340	52,166	182,311	3.6	149
13	65,743	137,626	413,504	2.1	158
14	61,349	119,262	288,955	1.9	158
15	53,455	132,919	459,818	2.5	157
16	78,532	191,558	622,897	2.4	149
17	47,864	176,148	650,186	3.7	147
18	59,868	185,038	608,943	3.1	148
19	30,104	91,877	246,715	3.1	158
20	41,093	102,267	254,470	2.5	157
21	33,147	109,233	357,333	3.3	158
22	92,421	157,438	357,993	1.7	153
23	89,843	150,781	334,179	1.7	153
24	76,265	141,310	337,323	1.9	153
25	74,814	150,248	399,543	2.0	160
26	64,509	147,679	437,771	2.3	159


27	58,972	139,520	443,404	2.4	160
28	50,500	82,800	146,533	1.6	157
29	51,447	85,250	150,973	1.7	157
30	49,474	81,942	144,672	1.7	157
31	58,429	144,936	423,058	2.5	157
32	89,441	166,845	523,735	1.9	158
33	90,435	152,608	349,816	1.7	157
34	34,679	77,908	205,082	2.3	144
35	31,341	70,550	160,080	2.3	144
36	35,649	82,850	252,359	2.3	144
37	76,166	132,161	241,002	1.7	160
38	76,807	129,124	232,401	1.7	161
39	94,439	144,461	254,721	1.5	160
40	48,008	115,829	402,984	2.4	161
41	59,080	111,122	235,729	1.9	161
42	62,463	118,588	253,690	1.9	161
43	100,327	170,565	343,646	1.7	161
44	112,191	186,280	378,163	1.7	163
45	113,776	188,756	372,742	1.7	161
46					
47					
48					
49					
50					
51					
52	134,805	220,588	404,685	1.6	161
53	154,903	254,230	538,930	1.6	160
54	173,584	279,481	550,649	1.6	162
55	36,396	69,386	173,368	1.9	153
56	38,212	64,507	151,954	1.7	154
57	46,262	85,694	200,460	1.9	154
58	129,205	229,975	512,124	1.8	159
59	116,895	213,507	455,527	1.8	160

60	143,333	252,722	564,805	1.8	159
61	71,571	175,419	480,970	2.5	147
62	38,849	156,529	535,448	4.0	147
63	43,774	156,966	525,748	3.6	147
64	74,952	145,111	280,595	1.9	161
65	90,558	160,712	432,645	1.8	161
66	101,096	165,958	324,701	1.6	161
67	57,058	162,395	391,985	2.9	152
68	109,183	183,055	379,218	1.7	154
69	220,076	331,240	609,515	1.5	163
70	190,283	316,542	631,651	1.7	164
71	181,601	303,158	627,729	1.7	162
72	35,206	64,314	127,614	1.8	149
73	36,868	67,959	152,188	1.8	149
74	41,257	72,399	159,327	1.8	149
75	34,608	69,709	144,535	2.0	139
76	35,351	70,752	154,141	2.0	138
77	22,700	66,289	146,317	2.9	138
78					
79					
80					

[0334] All documents described herein are incorporated by reference herein, including any priority documents and/or testing procedures to the extent they are not inconsistent with this text. As is apparent from the foregoing general description and the specific embodiments, while forms of the invention have been illustrated and described, various modifications can be made without departing from the spirit and scope of the invention. Accordingly, it is not intended that the invention be limited thereby. Likewise, the term "comprising" is considered synonymous with the term "including." Likewise whenever a composition, an element or a group of elements is preceded with the transitional phrase "comprising", it is understood that we also contemplate the same composition or group of elements with transitional phrases "consisting essentially of," "consisting of", "selected from the group of consisting of," or "is" preceding the recitation of the composition, element, or elements and vice versa.

Claims

1. A catalyst compound represented by the Formula (I):



- 5 wherein:

M is a group 3, 4, 5, or 6 transition metal or a Lanthanide;

E and E' are each independently O, S, or NR⁹ where R⁹ is independently hydrogen, a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl or a heteroatom-containing group;

Q is group 14, 15, or 16 atom that forms a dative bond to metal M;

- 10 A¹QA^{1'} are part of a heterocyclic Lewis base containing 4 to 40 non-hydrogen atoms that links A² to A^{2'} via a 3-atom bridge with Q being the central atom of the 3-atom bridge, A¹ and A^{1'} are independently C, N, or C(R²²), where R²² is selected from hydrogen, C₁-C₂₀ hydrocarbyl, C₁-C₂₀ substituted hydrocarbyl;

- 15 A³---A² is a divalent group containing 2 to 40 non- hydrogen atoms that links A¹ to the E-bonded aryl group via a 2-atom bridge;

A^{2'}---A^{3'} is a divalent group containing 2 to 40 non- hydrogen atoms that links A^{1'} to the E'-bonded aryl group via a 2-atom bridge;

L is a Lewis base;

X is an anionic ligand;

- 20 n is 1, 2 or 3;

m is 0, 1, or 2;


n+m is not greater than 4;

each of R¹, R², R³, R⁴, R^{1'}, R^{2'}, R^{3'}, and R^{4'} is independently hydrogen, a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group,

- 25 and one or more of R¹ and R², R² and R³, R³ and R⁴, R^{1'} and R^{2'}, R^{2'} and R^{3'}, R^{3'} and R^{4'} may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings;

any two L groups may be joined together to form a bidentate Lewis base;
 an X group may be joined to an L group to form a monoanionic bidentate group;
 any two X groups may be joined together to form a dianionic ligand group.

- 5 2. The catalyst compound of formula 1 where the catalyst compound represented by the Formula (II):




wherein:

- M is a group 3, 4, 5, or 6 transition metal or a Lanthanide;
- 10 E and E' are each independently O, S, or NR⁹, where R⁹ is independently hydrogen, a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl, or a heteroatom-containing group;
- each L is independently a Lewis base;
- each X is independently an anionic ligand;
- n is 1, 2 or 3;
- 15 m is 0, 1, or 2;
- n+m is not greater than 4;
- each of R¹, R², R³, R⁴, R^{1'}, R^{2'}, R^{3'}, and R^{4'} is independently hydrogen, C₁-C₄₀ hydrocarbyl, C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing group, or one or more of R¹ and R², R² and R³, R³ and R⁴, R^{1'} and R^{2'}, R^{2'} and R^{3'}, R^{3'} and R^{4'} may be joined
- 20 to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form additional rings; any two L groups may be joined together to form a bidentate Lewis base;
- an X group may be joined to an L group to form a monoanionic bidentate group;
- 25 any two X groups may be joined together to form a dianionic ligand group;
- each of R⁵, R⁶, R⁷, R⁸, R^{5'}, R^{6'}, R^{7'}, R^{8'}, R¹⁰, R¹¹, and R¹² is independently hydrogen, a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl, a heteroatom or a heteroatom-containing

group, or one or more of R⁵ and R⁶, R⁶ and R⁷, R⁷ and R⁸, R^{5'} and R^{6'}, R^{6'} and R^{7'}, R^{7'} and R^{8'}, R¹⁰ and R¹¹, or R¹¹ and R¹² may be joined to form one or more substituted hydrocarbyl rings, unsubstituted hydrocarbyl rings, substituted heterocyclic rings, or unsubstituted heterocyclic rings each having 5, 6, 7, or 8 ring atoms, and where substitutions on the ring can join to form
5 additional rings.

3. The catalyst compound of claim 1 or 2 wherein the M is Hf, Zr or Ti.
4. The catalyst compound of claim 1, 2 or 3 wherein E and E' are each O.
- 10 5. The catalyst compound of claim 1, 2, 3, or 4 wherein R¹ and R^{1'} is independently a C₄-C₄₀ tertiary hydrocarbyl group.
6. The catalyst compound of claim 1, 2, 3, or 4 wherein R¹ and R^{1'} is independently a
15 C₄-C₄₀ cyclic tertiary hydrocarbyl group.
7. The catalyst compound of claim 1, 2, 3, or 4 wherein R¹ and R^{1'} is independently a C₄-C₄₀ polycyclic tertiary hydrocarbyl group.
- 20 8. The catalyst compound any of claims 1 to 7 wherein each X is, independently, selected from the group consisting of substituted or unsubstituted hydrocarbyl radicals having from 1 to 20 carbon atoms, hydrides, amides, alkoxides, sulfides, phosphides, halides, and a combination thereof, (two X's may form a part of a fused ring or a ring system).
- 25 9. The catalyst compound any of claims 1 to 8 wherein each L is, independently, selected from the group consisting of: ethers, thioethers, amines, phosphines, ethyl ether, tetrahydrofuran, dimethylsulfide, triethylamine, pyridine, alkenes, alkynes, alenes, and carbenes and a combinations thereof, optionally two or more L's may form a part of a fused ring or a ring system).
- 30 10. The catalyst compound of claim 1, wherein M is Zr or Hf, Q is nitrogen, both A¹ and A^{1'} are carbon, both E and E' are oxygen, and both R¹ and R^{1'} are C₄-C₂₀ cyclic tertiary alkyls.
11. The catalyst compound of claim 1, wherein M is Zr or Hf, Q is nitrogen, both A¹ and A^{1'}
35 are carbon, both E and E' are oxygen, and both R¹ and R^{1'} are adamantan-1-yl or substituted adamantan-1-yl.


12. The catalyst compound of claim 1, wherein M is Zr or Hf, Q is nitrogen, both A¹ and A^{1'} are carbon, both E and E' are oxygen, and both R¹ and R^{1'} are C₆-C₂₀ aryls.
13. The catalyst compound of claim 1, wherein Q is nitrogen, A¹ and A^{1'} are both carbon, both R¹ and R^{1'} are hydrogen, both E and E' are NR⁹, where R⁹ is selected from a C₁-C₄₀ hydrocarbyl, a C₁-C₄₀ substituted hydrocarbyl, or a heteroatom-containing group.
14. The catalyst compound of claim 1, wherein Q is carbon, A¹ and A^{1'} are both nitrogen, and both E and E' are oxygen.
15. The catalyst compound of claim 1, wherein Q is carbon, A¹ is nitrogen, A^{1'} is C(R²²), and both E and E' are oxygen, where R²² is selected from hydrogen, C₁-C₂₀ hydrocarbyl, C₁-C₂₀ substituted hydrocarbyl.
16. The catalyst compound of claim 1, wherein the heterocyclic Lewis base is selected from the groups represented by the following formulas:




where each R²³ is independently selected from hydrogen, C₁-C₂₀ alkyls, and C₁-C₂₀ substituted alkyls.

17. The catalyst compound of claim 2, wherein M is Zr or Hf, both E and E' are oxygen, and both R¹ and R^{1'} are C₄-C₂₀ cyclic tertiary alkyls.
18. The catalyst compound of claim 2, wherein M is Zr or Hf, both E and E' are oxygen, and both R¹ and R^{1'} are adamantan-1-yl or substituted adamantan-1-yl.


19. The catalyst compound of claim 2, wherein M is Zr or Hf, both E and E' are oxygen, and each of R¹, R^{1'}, R³ and R^{3'} are adamantan-1-yl or substituted adamantan-1-yl.
- 5 20. The catalyst compound of claim 2, wherein M is Zr or Hf, both E and E' are oxygen, both R¹ and R^{1'} are C₄-C₂₀ cyclic tertiary alkyls, and both R⁷ and R^{7'} are C₁-C₂₀ alkyls.
21. The catalyst compound of claim 2, wherein M is Zr or Hf, both E and E' are O, both R¹ and R^{1'} are C₄-C₂₀ cyclic tertiary alkyls, and both R⁷ and R^{7'} are C₁-C₂₀ alkyls.
- 10 22. The catalyst compound of claim 2, wherein M is Zr or Hf, both E and E' are O, both R¹ and R^{1'} are C₄-C₂₀ cyclic tertiary alkyls, and both R⁷ and R^{7'} are C₁-C₃ alkyls.
23. The catalyst compound of claim 1 wherein the catalyst compound is represented by one
15 or more of the following formulas:




Complex 1




Complex 2




Complex 3




Complex 4




Complex 5




Complex 6




Complex 7




Complex 8




Complex 9




Complex 10




Complex 11




Complex 12




Complex 13




Complex 14




Complex 15




Complex 16




Complex 17




Complex 18




Complex 19




Complex 20




Complex 21




Complex 22




Complex 23




Complex 24




Complex 25




Complex 26




Complex 27




Complex 29



Complex 30



Complex 31



Complex 32

24. A catalyst system comprising activator and the catalyst compound of any of claims 1 to 23.
25. The catalyst system of claim 24, wherein the activator comprises an alumoxane or a non-coordinating anion.
26. The catalyst system of claim 24, wherein the activator is soluble in non-aromatic-hydrocarbon solvent.


27. The catalyst system of claim 24, wherein the catalyst system is free of aromatic solvent.

28. The catalyst system of claim 24, wherein the activator is represented by the formula:



wherein Z is (L-H) or a reducible Lewis Acid, L is a neutral Lewis base; H is hydrogen; (L-H)⁺ is a Bronsted acid; A^{d-} is a non-coordinating anion having the charge d-; and d is an integer from 1 to 3.

10 29. The catalyst system of claim 24, wherein the activator is represented by the formula:



wherein:

E is nitrogen or phosphorous;

d is 1, 2 or 3; k is 1, 2, or 3; n is 1, 2, 3, 4, 5, or 6; n - k = d;


15 R^{1'}, R^{2'}, and R^{3'} are independently a C₁ to C₅₀ hydrocarbyl group optionally substituted with one or more alkoxy groups, silyl groups, a halogen atoms, or halogen containing groups,

wherein R^{1'}, R^{2'}, and R^{3'} together comprise 15 or more carbon atoms;

Mt is an element selected from group 13 of the Periodic Table of the Elements; and

20 each Q is independently a hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxide, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, or halosubstituted-hydrocarbyl radical.

30. The catalyst system of claim 24, wherein the activator is represented by the formula:



25 wherein A^{d-} is a non-coordinating anion having the charge d-; and d is an integer from 1 to 3 and (Z)_d⁺ is represented by one or more of:

10		11		12	
13		14		15	

16		17		18	
19		20		21	
22		23		24	
25		26		27	
29		28		30	
31		32		33	
34		35		36	

31. The catalyst system of claim 24, wherein the activator is one or more of:
- N-methyl-4-nonadecyl-N-octadecylbenzenaminium tetrakis(pentafluorophenyl)borate,
- N-methyl-4-nonadecyl-N-octadecylbenzenaminium tetrakis(perfluoronaphthalenyl)borate,
- 5 dioctadecylmethyllummonium tetrakis(pentafluorophenyl)borate,
- dioctadecylmethyllummonium tetrakis(perfluoronaphthalenyl)borate,
- N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate,
- triphenylcarbenium tetrakis(pentafluorophenyl)borate,

- trimethylammonium tetrakis(perfluoronaphthalenyl)borate,
triethylammonium tetrakis(perfluoronaphthalenyl)borate,
tripropylammonium tetrakis(perfluoronaphthalenyl)borate,
tri(n-butyl)ammonium tetrakis(perfluoronaphthalenyl)borate,
5 tri(t-butyl)ammonium tetrakis(perfluoronaphthalenyl)borate,
N,N-dimethylanilinium tetrakis(perfluoronaphthalenyl)borate,
N,N-diethylanilinium tetrakis(perfluoronaphthalenyl)borate,
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(perfluoronaphthalenyl)borate,
tropillium tetrakis(perfluoronaphthalenyl)borate,
10 triphenylcarbenium tetrakis(perfluoronaphthalenyl)borate,
triphenylphosphonium tetrakis(perfluoronaphthalenyl)borate,
triethylsilylium tetrakis(perfluoronaphthalenyl)borate,
benzene(diazonium) tetrakis(perfluoronaphthalenyl)borate,
trimethylammonium tetrakis(perfluorobiphenyl)borate,
15 triethylammonium tetrakis(perfluorobiphenyl)borate,
tripropylammonium tetrakis(perfluorobiphenyl)borate,
tri(n-butyl)ammonium tetrakis(perfluorobiphenyl)borate,
tri(t-butyl)ammonium tetrakis(perfluorobiphenyl)borate,
N,N-dimethylanilinium tetrakis(perfluorobiphenyl)borate,
20 N,N-diethylanilinium tetrakis(perfluorobiphenyl)borate,
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(perfluorobiphenyl)borate,
tropillium tetrakis(perfluorobiphenyl)borate,
triphenylcarbenium tetrakis(perfluorobiphenyl)borate,
triphenylphosphonium tetrakis(perfluorobiphenyl)borate,
25 triethylsilylium tetrakis(perfluorobiphenyl)borate,
benzene(diazonium) tetrakis(perfluorobiphenyl)borate,
[4-t-butyl-PhNMe₂H][[(C₆F₃(C₆F₅)₂)₄B],
trimethylammonium tetraphenylborate,
triethylammonium tetraphenylborate,
30 tripropylammonium tetraphenylborate,
tri(n-butyl)ammonium tetraphenylborate,
tri(t-butyl)ammonium tetraphenylborate,
N,N-dimethylanilinium tetraphenylborate,
N,N-diethylanilinium tetraphenylborate,

- N,N-dimethyl-(2,4,6-trimethylanilinium) tetraphenylborate,
tropillium tetraphenylborate,
triphenylcarbenium tetraphenylborate,
triphenylphosphonium tetraphenylborate,
5 triethylsilylium tetraphenylborate,
benzene(diazonium)tetraphenylborate,
trimethylammonium tetrakis(pentafluorophenyl)borate,
triethylammonium tetrakis(pentafluorophenyl)borate,
tripropylammonium tetrakis(pentafluorophenyl)borate,
10 tri(n-butyl)ammonium tetrakis(pentafluorophenyl)borate,
tri(sec-butyl)ammonium tetrakis(pentafluorophenyl)borate,
N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate,
N,N-diethylanilinium tetrakis(pentafluorophenyl)borate,
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl)borate,
15 tropillium tetrakis(pentafluorophenyl)borate,
triphenylcarbenium tetrakis(pentafluorophenyl)borate,
triphenylphosphonium tetrakis(pentafluorophenyl)borate,
triethylsilylium tetrakis(pentafluorophenyl)borate,
benzene(diazonium) tetrakis(pentafluorophenyl)borate,
20 trimethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate,
triethylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
tripropylammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
tri(n-butyl)ammonium tetrakis-(2,3,4,6-tetrafluoro-phenyl)borate,
dimethyl(t-butyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
25 N,N-dimethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
N,N-diethylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
tropillium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
triphenylcarbenium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
30 triphenylphosphonium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
triethylsilylium tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
benzene(diazonium) tetrakis-(2,3,4,6-tetrafluorophenyl)borate,
trimethylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
triethylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,

- tripropylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 tri(n-butyl)ammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 tri(t-butyl)ammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 N,N-dimethylanilinium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 5 N,N-diethylanilinium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 tropillium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 triphenylphosphonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 10 triethylsilylium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 benzene(diazonium) tetrakis(3,5-bis(trifluoromethyl)phenyl)borate,
 di-(i-propyl)ammonium tetrakis(pentafluorophenyl)borate,
 dicyclohexylammonium tetrakis(pentafluorophenyl)borate,
 tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl)borate,
 15 tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl)borate,
 triphenylcarbenium tetrakis(perfluorophenyl)borate,
 1-(4-(tris(pentafluorophenyl)borate)-2,3,5,6-tetrafluorophenyl)pyrrolidinium,
 tetrakis(pentafluorophenyl)borate,
 4-(tris(pentafluorophenyl)borate)-2,3,5,6-tetrafluoropyridine, and
 20 triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate).

32. A process to polymerize olefins comprising contacting one or more olefins with the catalyst system of any of claims 23 to 31.
- 25 33. The process of claim 32 wherein the process occurs at a temperature of from about 0°C to about 300°C, at a pressure in the range of from about 0.35 MPa to about 10 MPa, and at a time up to 300 minutes.
34. The process of claim 32 further comprising obtaining polymer.
- 30 35. The process of claim 32 wherein the olefins comprise one or more substituted or unsubstituted C₂ to C₄₀ alpha olefins.