

Description

The invention relates to disposable absorbent articles, particularly sanitary napkins and diapers, having a surface material comprising a non-woven fabric made solely of hot-melt fibers comprising at least partially fibers which melt at 90 to 140°C, said non-woven fabric comprising a first layer which is intended to be in contact with the skin of a user of said article and a second layer which is intended not to be in contact with the skin, said first layer having a basis weight of 5 to 15 g/m², said second layer having a basis weight of 8 to 35 g/m².

Absorbent articles of this kind are known from DE—A 3 305 406. Shortcomings of these articles are, however, that the feeling is not sufficiently good and fuzzes are coming off the surface of the articles during wearing.

In general absorbent articles such as paper diapers and sanitary napkins comprise an absorbent layer made of a cotton-like pulp or absorbent paper, a leakproof layer arranged below and around the absorbent layer and a non-woven fabric placed on the surface thereof.

The non-woven fabric forming the surface layer of the absorbent article should satisfy the following requirements: loosening of the absorbent is prevented, the flow of the liquid on the surface which invites leakage is controlled, the return of a body fluid kept in the absorbent layer toward the skin is minimized and a touch is improved.

Absorbing articles having a non-woven fabric satisfying these requirements are disclosed in JP—A—58—143 750 and JP—A—57—191 356.

The former articles are sanitary napkins characterized in that the surface material comprises 30 to 80 wt. % of hot-melt fibers and 70 to 20 wt. % of hydrophobic fibers. In these sanitary napkins having the surface made of the non-woven fabric, the blood penetrates rapidly into the napkin and is absorbed therein, the return of the blood due to a body weight of the user is minimized and a comfortable touch is obtained.

In the latter articles, the surface material is a non-woven fabric made of synthetic fibers having a relatively high fineness (6 denier or higher) and heat-bonded with hot-melt fibers to attain high compression elasticity and thickness. By using said non-woven fabric, the absorbent article which realizes a comfortable feeling upon use and in which the return is controlled can be obtained.

However, in the above-mentioned absorbent articles in which the non-woven fabric is used as the surface material, the non-woven fabric forming the surface layer is broken by vivid motions of a user such as a baby and fuzzes of mainly non-hot melt fibers come off remarkably to deteriorate the shape retention of the absorbent layer, absorbing capacity and touch seriously.

This problem is solved according to the invention by the features specified in the claim.

Thereby a surface material for the absorbent articles is provided which protects the absorbent articles from breakage or coming-off of fuzzes, which retains the shape of the absorbent layer and which maintains the absorbing capacity and comfortable touch even when the user moves vividly.

As is known, the breakage of the non-woven fabric used as the surface material and the coming-off of the fuzzes due to the vivid motion of the user can be prevented even when the non-woven fabric is made of a mixture of said hot melt fibers and non-hot melt fibers by (1) increasing the quantity of heat applied in the heat-bonding of the web, (2) increasing the basis weight of the non-woven fabric or (3) reducing the relative amount (weight) of the non-hot melt fibers. However, these processes have defects. More particularly, according to the process (1) or (2), the user's feeling is deteriorated, since the whole non-woven fabric becomes stiff and the roughness of the surface is increased. In addition, the increase of the basis weight increases the cost. The problem of the coming off of the non-hot melt fibers cannot be solved by the process (3).

When a non-woven fabric is used as the surface material as in the absorbent article of the present invention, a good touch can be realized and the breakage or coming-off of the fuzzes can be minimized substantially without necessitating an increase of the basis weight.

For example, a strength sufficient for preventing the breakage during the use and a thickness sufficient for keeping the skin from contact with the body fluid retained in the absorbent layer are required of disposable diapers. Hot-melt fibers having a three-dimensional buckled structure are recommended for improving the strength, realizing a suitable thickness and controlling the coming off of the fuzzes without increasing the basis weight while maintaining the comfortable touch.

The non-woven fabric of the present invention has preferably a strength of at least 250 g/25 mm so as to resist to the breakage due to the user's motion.

The larger the relative amount (weight) of the three-dimensionally buckled, hot-melt fibers, the thicker the non-woven fabric but the poorer the touch. Therefore, the first layer forming the surface material of the non-woven fabric to be in contact with the skin comprises at least 30 wt. % of three-dimensionally non-buckled, hot-melt fibers. The first fibers forming the first layer to be in contact with the skin are desirably as thin as about 1 to 3 denier from the viewpoint of feeling.

The second layer should contain at least 50% of three-dimensionally buckled, hot-melt second fibers so as to have a desired thickness and the fibers have a thickness higher than that of the first fibers in the first layer, i.e. 1.5 to 6 denier, preferably 2 to 6 denier.

The usable hot melt fibers are essentially those which are molten partially or wholly (preferably 30 to

70 wt. %) at a temperature of 90 to 140°C to exhibit adhesive properties. Examples of the preferred fibers include polyethylene/polypropylene, low melting polyester/polyester, low melting polyester/polypropylene and polyethylene/polyester conjugate fibers.

The first layer has a basis weight of at least about 5 g/m², since a comfortable hand is required because it is in contact with the skin. The basis weight should not exceed 15 g/m², since the layer having an excessive basis weight is stiff and has a poor feeling upon the use. The second layer is effective in mainly realizing the necessary thickness and strength. When the basis weight is less than 8 g/m², a sense of thickness is lost and the strength is lower than 250 g/25 mm. Though a high thickness can be obtained by increasing the basis weight of the second layer, an excessively high thickness causes a stiff feeling and is not preferred from economical viewpoint. Thus, the basis weight of the second layer is 8 to 35 g/m².

The following examples will further illustrate the present invention.

Examples 1, 2, 6 to 8, 10, 13 and 14 and Comparative Examples 1 to 4

Non-woven fabrics having compositions shown in Table 1 were used as the surface materials and the performances of them were examined by the following methods to obtain the results shown in Table 1.

(1) Tensile strength (CD direction, i.e. the manufacturing direction of the fabric): Test pieces having a width of 25 mm were torn at a pulling rate of 300 mm/min, the grab width being 150 mm. The tensile strength was shown in terms of the breaking strength. The direction of the tension was a CD direction of the non-woven fabric.

(2) Thickness: The thickness under a load of 1 g/m² was measured.

(3) Feeling: The softness and the touch of the non-woven fabric were examined by organoleptic tests according to the following criteria:

○: The sample was very soft and had a comfortable touch.

△: The sample was soft but the touch was comparatively poor or, alternatively, the sample had an excellent touch but was comparatively stiff.

×: The sample was stiff and had a poor touch.

(4) Coming off of fuzzes: The surface of the non-woven fabric was rubbed with a sponge roll under a load of 15 g/m² and the amount of the fibers which came off from the non-woven fabric and adhered to the sponge was examined. The results were shown according to the following criteria:

○: Substantially no fibers were observed.

△: The coming-off was remarkable but no pill (independently turned-in bundle of fibers) was observed.

×: The coming-off and the pill formation were remarkable.


In the examples and comparative examples, fibers ES and ESHB were polyethylene/polypropylene conjugate fibers of Chisso Polypro Fibers Co., Ltd. ESHB was three-dimensionally buckled one. NBF was three-dimensionally non-buckled polyethylene/polypropylene conjugate fibers of Daiwa Spinning Co., Ltd. "Melly" was three-dimensionally non-buckled low melting polyester/polyester conjugate fibers of Unitika Ltd.

It is apparent from Table 1 that when the amount of the hot-melt fibers was 100 wt. %, the coming-off of the fuzzes was scarcely observed, a sufficiently high tensile strength was obtained and that as the weight ratio of the three-dimensionally buckled fibers to said hot-melt fibers was increased, the thickness was increased. It is also suggested in Table 1 that, for maintaining the excellent feeling, the amount of the three-dimensionally non-buckled, hot-melt fibers in the first layer is at least 30 wt. %.

TABLE 1

	Basis weight		Composition								Tensile strength in CD direction g/25 mm	Thickness mm	Feeling	Coming off of fuzzes	Remarks
			1st layer			2nd layer									
	1st layer	2nd layer	fibers	fineness	ratio	fibers	fineness	ratio							
Example 1	10	25	ES ESHB	1.5d 3d	60% 40%	ES ESHB	3d 3d	30% 70%	412	1.4	○	○			
2	"	"	ES ESHB	3 3	60 40	ES ESHB	3 3	30 70	388	1.5	○	○			
6	"	"	ES ESHB	1.5 3	40 60	ES ESHB	3 3	30 70	403	1.5	○	○			
7	"	"	ES ESHB	1.5 3	80 20	ES ESHB	3 3	30 70	435	1.3	○	○			
8			ESHB	3d	40%	ESHB	6d	70%	390	1.9	○	○			
13	"	"	NBF ESHB	3 3	60 40	NBF ESHB	3 3	30 70	420	1.4	○	○			
14	"	"	Melty ESHB	3 3	40 60	Melty ESHB	3 3	30 70	439	2.0	○	○			

	Basis weight		Composition						Tensile strength in CD direction g/25 mm	Thickness mm	Feeling	Coming off of fuzzes	Remarks	
			1st layer			2nd layer								
			1st layer	2nd layer	fibers	fineness	ratio	fibers						fineness
Comparative 1			30	Rayon PET	— —	50% 50%				—	0.6	○	x	Commercially available
2			100	PP	—	100				—	0.2	○	△	"
3		10	25	ES	3	100	ES PP	3d 6d	30% 70%	203	1.2	○	x	
4		8	10	ES	1.5	100	ES PP	3 6	30 70	87	0.4	○	x	





EP 0 173 058 B1

Claim

An absorbent article having a surface material comprising a non-woven fabric made solely of hot-melt fibers comprising at least partially fibers which melt at 90 to 140°C, said non-woven fabric comprising a first layer which is intended to be in contact with the skin of a user of said article and a second layer which is intended not to be in contact with the skin, said first layer having a basis weight of 5 to 15 g/m², said second layer having a basis weight of 8 to 35 g/m², characterized in that both layers comprise first three-dimensionally non-buckled fibers and second three-dimensionally buckled fibers, the weight ratio of said first fibers and said second fibers being in the range of 100 to 30/0 to 70 in said first layer and in the range of 50 to 0/50 to 100 in said second layer.

Patentanspruch

Absorbierender Gegenstand mit einem Oberflächenmaterial, das ein Faservlies umfaßt, welches nur aus heißschmelzenden Fasern hergestellt ist, wobei zumindest ein Teil der Fasern bei 90 bis 140°C schmilzt und das Faservlies eine erste Schicht umfaßt, die in Kontakt mit der Haut des Trägers des Gegenstandes treten soll, sowie eine zweite Schicht, die nicht in Kontakt mit der Haut treten soll, wobei die erste Schicht ein Basisgewicht von 5 bis 15 g/m² und die zweite Schicht ein Basisgewicht von 8 bis 35 g/m² besitzt, dadurch gekennzeichnet, daß beide Schichten erste dreidimensional unverformte Fasern und zweite dreidimensional verformte Fasern umfassen, wobei das Gewichtsverhältnis der ersten Fasern zu den zweiten Fasern im Bereich von 100 zu 30/0 zu 70 in der ersten Schicht und im Bereich von 50 bis 0/50 bis 100 in der zweiten Schicht liegt.

Revendication

Article absorbant comportant une matière en surface qui comprend une étoffe non tissée entièrement confectionnée en fibres fondant à chaud, comprenant au moins partiellement des fibres qui fondent entre 90 et 140°C, ladite étoffe non tissée comprenant une première couche destinée à venir en contact avec la peau de l'utilisateur dudit article et une seconde couche qui n'est pas destinée à venir en contact avec la peau, ladite première couche ayant un poids par unité de surface compris entre 5 et 15 g/m², ladite seconde couche ayant un poids par unité de surface compris entre 8 et 35 g/m², caractérisé en ce que les deux couches comprennent une première série de fibres non bouclées sur le mode tridimensionnel et une seconde série de fibres bouclées sur le mode tridimensionnel, le rapport pondéral des premières fibres aux secondes fibres étant compris dans l'intervalle 100 à 30/0 à 70 dans la première couche et dans l'intervalle 50 à 0/50 à 100 dans ladite seconde couche.