

- 1 -

CYANATE RESIN COMPOSITION AND COPPER-CLAD
LAMINATE

5 The present invention relates to a cyanate
resin composition, a cyanate compound and a copper-clad
laminar produced using the same.

10 Almost all substrates for printed circuit
boards are made from adducts of bismaleimide
compounds and amine compounds or a combination of
bisphenol epoxy resins and dicyandiamide, which are
thermosetting resin compositions for electric and
15 electronic uses. The circuit boards are being
directed to multiple layered ones. A requirement
for resins to be used is that they have dielectric
constant as low as possible in order mainly to
improve signal propagation speed. One of conventional
ways to this effect is addition of thermoplastic
resins having low dielectric constant to thermo-
20 setting resins. However, this method has such
disadvantage that heat resistance of the thermosetting
resins is damaged. Demand for practically usable
resins having low dielectric constant has not yet
been sufficiently satisfied.

25 Under the circumstances, cyanate resins
have been developed (e.g. DE-A-2533122
and WO-A-88/05443). Cyanates
which are familiar at present include dicyanates of
30 bisphenol A. Although these cyanates have relatively
low dielectric constant, recent high advance of
computer techniques requires materials having
lower dielectric constant.

35

S-10000000

It is the object of the present invention to provide a cyanate


5 resin composition from which a copper-clad laminate having dielectric constant low enough and practically acceptable heat resistance without damaging properties of conventional copper-clad laminates can be produced. A further object of the present
10 invention is to provide a copper-clad laminate using said cyanate resin composition.

That is, the present invention relates to the following cyanate resin compositions (1) - (2), the
15 cyanate compound (3) and copper-clad laminates (4) using the same.

(1) A cyanate resin composition comprising (A) and (B) as essential components:


(A) a cyanate compound represented by the following formula (1):

20



30 wherein R and Q each represents a halogen atom, an alkyl group of 1-10 carbon atoms, a cycloalkyl group of 5-7 carbon atoms or a hydrocarbon group of 6-20 carbon atoms which contains a cycloalkyl group of 5-7 carbon atoms, i and j each represents an
35 integer of 0-4 with a proviso that, when i and j represent 2 or more, R and Q may be identical or

different and M represents a group shown by the following formula (2):



15 wherein T represents a halogen atom, an alkyl group of 1-10 carbon atoms, a cycloalkyl group of 5-7 carbon atoms or a hydrocarbon group of 6-20 carbon atoms which contains a cycloalkyl group of 5-7 carbon atoms, k represents an integer of 0-10 and m represents an integer of 0-8 with a proviso that, when k or m represents 2 or more, T may be identical or different


20 and

(B) a hardener.

25 (2) A cyanate resin composition comprising the above (A) and (B), and additionally (C) as essential components, said (C) being at least one of a brominated epoxy compound, a maleimide compound, a prepolymer of the brominated epoxy compound and a prepolymer of the maleimide compound.

30

(3) A cyanate compound represented by the following formula (3):




wherein R, Q, i and j are as defined in the formula
 10 (1). The compounds of formula (3) are novel compounds.

(4) A copper-clad laminate prepared by heat
 molding a copper foil and a prepreg obtained by
 impregnating a substrate with a solution of the
 cyanate resin composition of the above (1) or (2)
 15 in an organic solvent.

The present invention is explained in
 detail below.

20 The cyanate compounds of the present
 invention are obtained by subjecting a bisphenol
 represented by the following formula (4):



30 wherein R, Q, M, i and j are as defined for the
 formula (1), and a cyanogen halide such as cyanogen
 35 chloride or cyanogen bromide to dehydrohalogenation
 reaction in a suitable organic solvent in the

presence of a base.

The bisphenol may be any of those which are obtained by known processes.

5

As the processes for producing the bisphenol, mention may be made of, for example, allowing limonene, dipentene, a cyclohexanone derivative or a cyclohexenone derivative to react with a phenol in the presence of an acid catalyst. The process is not limitative.

10 The phenol used above includes compounds having one phenolic hydroxyl group. Examples of the phenol are phenol; halogenated phenols such as 2-bromophenol and 2-chlorophenol; alkyl-substituted phenols such as o-cresol, m-cresol, p-cresol, 2-ethylphenol, 2-octylphenol, 2-nonylphenol, 2,6-xylenol, 2-t-butyl-5-methylphenol, 2-t-butyl-4-methylphenol, 2,4-di(t-butyl)phenol, 2-t-butylphenol, 2-sec-butylphenol and 2-n-butylphenol or position isomers thereof; and cycloalkyl-substituted phenols such as 2-cyclohexylphenol, 4-cyclohexylphenol and 2-cyclohexyl-5-methylphenol or position isomers thereof. These are not limitative. Among these phenols, preferred are phenol, o-cresol, m-cresol, p-cresol, 2,6-xylenol, 2-t-butyl-5-methylphenol, 2-t-butyl-4-methylphenol, 2,4-di(t-butyl)phenol, 2-cyclohexyl-5-methylphenol, 2-t-butylphenol, 2-sec-butylphenol, 2-n-butylphenol, 2-cyclohexylphenol and 4-cyclohexylphenol.

As examples of the cyclohexanone derivative used here, mention may be made of cyclohexanone; halogenated cyclohexanones such as 2-bromocyclohexanone and 2-chlorocyclohexanone;

35

alkyl-substituted cyclohexanones such as 2-methyl-
cyclohexanone, 3-methylcyclohexanone, 4-methylcyclo-
hexanone, 2-isopropylcyclohexanone, 3-isopropyl-
cyclohexanone, 4-isopropylcyclohexanone, 2-n-butyl-
5 cyclohexanone, 3-n-butylcyclohexanone, 4-n-butyl-
cyclohexanone, 2-sec-butylcyclohexanone, 3-sec-
butylcyclohexanone, 4-sec-butylcyclohexanone, 2-
isobutylcyclohexanone, 3-isobutylcyclohexanone, 4-
isobutylcyclohexanone, 2-t-butylcyclohexanone, 3-t-
10 butylcyclohexanone, 4-t-butylcyclohexanone, 2,6-
dimethylcyclohexanone, 2,4-diisopropylcyclohexanone,
3,5-diisopropylcyclohexanone, 2,4-di(t-butyl)-
cyclohexanone, 3,5-di(t-butyl)cyclohexanone, 2-t-
butyl-6-methylcyclohexanone, 3,3,5-trimethylcyclo-
15 hexanone, 3,3,5,5-tetramethylcyclohexanone and
2,4,6-tri(t-butyl)cyclohexanone, or position isomers
thereof; and cycloalkyl-substituted cyclohexanones
such as 4-cyclopentylcyclohexanone, 4-cyclohexyl-
cyclohexanone and 4-cyclohexyl-2-methylcyclohexanone,
20 or position isomers. These are not limitative.
Among these cyclohexanone derivatives, preferred
are cyclohexanone, 2-sec-butylcyclohexanone,
3-sec-butylcyclohexanone, 4-sec-butylcyclohexanone,
2-isobutylcyclohexanone, 3-isobutylcyclohexanone,
25 4-isobutylcyclohexanone, 2-t-butylcyclohexanone,
3-t-butylcyclohexanone, 4-t-butylcyclohexanone,
2,6-dimethylcyclohexanone, 2,4-diisopropyl-
cyclohexanone, 3,5-diisopropylcyclohexanone,
2,4-di(t-butyl)cyclohexanone, 3,5-di(t-butyl)-
30 cyclohexanone, 2-t-butyl-6-methylcyclohexanone,
3,3,5-trimethylcyclohexanone, 3,3,5,5-tetramethyl-
cyclohexanone, 2,4,6-tri(t-butyl)cyclohexanone and
4-cyclohexylcyclohexanone.

35 As examples of the cyclohexenone
derivatives, mention may be made of 2-cyclohexenone,


3-cyclohexenone; halogenated cyclohexenones such as 6-bromo-2-cyclohexenone and 6-chloro-2-cyclohexenone; alkyl-substituted cyclohexenones such as 2-methyl-2-cyclohexenone, 6-methyl-2-cyclohexenone, 4-isopropyl-2-cyclohexenone, 4-isobutyl-2-cyclohexenone, 4-*t*-butyl-2-cyclohexenone, isophorone, 2-methyl-3-cyclohexenone, 6-methyl-3-cyclohexenone, 4-isopropyl-3-cyclohexenone, 4-isobutyl-3-cyclohexenone, 4-*t*-butyl-3-cyclohexenone and 3,3,5-trimethyl-3-cyclohexenone, or position isomers thereof; and cycloalkyl-substituted cyclohexenones such as 4-cyclohexyl-2-cyclohexenone, 4-cyclohexyl-3-cyclohexenone, 4-cyclopentyl-2-cyclohexenone and 4-cyclohexyl-6-methyl-2-cyclohexenone, and position isomers thereof. These are not limitative. Among these cyclohexenone derivatives, preferred are 2-cyclohexenone, 4-isopropyl-2-cyclohexenone, 4-isobutyl-2-cyclohexenone, 4-*t*-butyl-2-cyclohexenone, 3,3,5-trimethyl-3-cyclohexenone, 2-methyl-3-cyclohexenone, 6-methyl-3-cyclohexenone, 4-isopropyl-3-cyclohexenone, 4-isobutyl-3-cyclohexenone, 4-*t*-butyl-3-cyclohexenone, isophorone, 4-cyclohexyl-2-cyclohexenone and 4-cyclohexyl-6-methyl-2-cyclohexenone.

As the hardener for the resin composition of the present invention, there may be used known ones. Examples are protonic acids such as hydrochloric acid and phosphoric acid; Lewis acids such as aluminum chloride, boron trifluoride and zinc chloride; aromatic hydroxy compounds such as phenol, pyrocatechol and dihydroxynaphthalene; organic metal salts such as zinc naphthenate, cobalt naphthenate, tin octylate and cobalt octylate; tertiary amines such as triethylamine, tributylamine, quinoline and isoquinoline; quaternary ammonium salts

such as tetraethylammonium chloride and tetrabutyl-
 ammonium bromide; imidazoles; sodium hydroxide,
 sodium methylate, triethylamine, tributylamine,
 diazabicyclo-(2,2,2)-octane, quinoline, isoquinoline,
 5 tetraethylammonium chloride and triphenylphosphine
 and mixtures thereof. Organic metal salts such as
 zinc naphthenate, cobalt octylate and tin octylate
 are preferred from the points of dissolvability
 with resins and reactivity.

10

The maleimide compounds used in the
 present invention are those which have two or more
 N-maleimide groups in the molecule and may be
 produced by any processes. Preferred are those
 15 which are represented by the following formula (5):





25

wherein X is a group represented by the following
 formula (6), (7), (8), (9), (10) or (11):



35





15

The cyanate compounds, brominated epoxy compounds and maleimide compounds used in the present invention may be used in the form of prepolymers. The prepolymers are produced by heat-

20

ing the compounds each alone or mixtures thereof in the presence of the hardener described above.

When flame retardancy is imparted to the copper-clad laminate, for example, a brominated

25

epoxy compound is added to the composition so that bromine content is in the range of 5-25%. Considering easiness in availability and economical advantage, the brominated epoxy compounds usable include, for example, glycidyl ether of tetrabromo-

30

bisphenol A and glycidyl ether of brominated phenol novolak, but these are not limitative.

Furthermore, as far as the present advantage is not damaged, there may be additionally

35

used other thermosetting resins. Examples are epoxy resins such as diglycidyl ethers of bisphenol

A or bisphenol F, and glycidyl ethers of phenol novolak or cresol novolak; addition polymers of bismaleimides with diamine compounds; alkenylaryl ether resins such as bisvinylbenzyl ethers of
5 bisphenol A or tetrabromobisphenol A, and vinylbenzyl ether of 4,4'-diaminodiphenylmethane; alkynyl ether resins such as dipropargyl ethers of bisphenol A or tetrabromobisphenol A, and propargyl ether of
10 diaminodiphenylmethane; and furthermore, phenolic resins, resol resins, allyl ether compounds, allylamine compounds, triallyl cyanurate, and vinyl group-containing polyolefin compounds. These are not limitative. Thermoplastic resins may also be added. Examples are polyphenylene ether, poly-
15 styrene, polyethylene, polybutadiene, polyimide and modified products thereof. These are not limitative. These resins may be used by incorporating into the cyanate resin compositions of the present invention, or by previously allowing them to react with the
20 cyanate resins.

Known additives such as flame retardants, releasing agents, surface treating agents and fillers may be added to the compositions. Examples
25 of the flame retardants are antimony trioxide and red phosphorus, those of the releasing agents are waxes and zinc stearate, those of the surface treating agents are silane coupling agents, and those of the fillers are silica, alumina, talc, clay
30 and glass fibers.

The copper-clad laminate of the present invention is produced by known methods. That is, a substrate is impregnated with a resin varnish
35 prepared by dissolving the thermosetting resin composition of the present invention or a prepolymer

thereof in an organic solvent and the impregnated substrate is heat-treated to obtain a prepreg. Thereafter, the prepreg and a copper foil are laminated and heat-molded to make a copper-clad laminate.

The organic solvent used is selected from one or mixtures of acetone, methyl ethyl ketone, methyl isobutyl ketone, ethylene glycol monomethyl ether, propylene glycol monomethyl ether, toluene, xylene, N,N-dimethylformamide, dioxane, tetrahydrofuran and the like.

The substrate to be impregnated with resin varnish includes, for example, woven or nonwoven fabrics or mats comprising inorganic fibers or organic fibers such as glass fibers, polyester fibers and polyamide fibers and papers. These may be used each alone or in combination of two or more.

The heat-treating conditions for making the prepreg are selected depending on varieties of solvents, catalysts and additives used and amounts thereof, but usually at 100-200°C for 3-30 minutes.

The heat-molding conditions include, for example, hot press molding conducted at 150-300°C, under a molding pressure of 10-100 kg/cm² for 20-300 minutes.

The following examples are illustrative of the invention. They should not be construed as limiting the invention in any manner.

Preparation Example 1

This example concerns with preparation of 1,1-bis(4-hydroxy-3-methylphenyl)cyclohexane which is a starting material for the cyanate compound used in the present invention.

Cyclohexanone (147.3 g, 1.50 mol) was charged in a reactor equipped with a thermometer, a stirrer and a condenser and dissolved in o-cresol (648.6 g, 6.00 mol). Concentrated hydrochloric acid (600 g) was added thereto, followed by stirring at 60°C for 10 hours. After completion of the reaction, toluene was added to the reaction mixture and the resulting precipitate containing a condensate of o-cresol and cyclohexanone was collected by filtration. The thus obtained precipitate was washed with water to remove hydrochloric acid to obtain the desired bis-o-cresolhexane (222 g). FD-MASS spectrum of the product showed that it had a molecular weight of 296 and a melting point of 190-195°C.

Preparation Example 2

This example concerns with preparation of 1,1-bis(4-cyanatophenyl)cyclohexane which is the cyanate compound used in the present invention.

1,1-Bis(4-hydroxyphenyl)cyclohexane (Antigen W manufactured by Sumitomo Chemical Co., Ltd., 200 g, 0.75 mol) as a starting material was dissolved in acetone (1,200 g) and the solution was cooled to -2°C. Cyanogen chloride (90.1 ml, 1.79 mol) was added to the solution and thereto was added dropwise triethylamine (158.6 g, 1.57 mol) over a period of 1 hour with taking care that the reaction temperature did not rise to higher than 0°C.

After completion of the addition, the reaction mixture was kept at 5-8°C for 2 hours and then diluted with chloroform (500 g). Salts were removed by filtration and the residue was washed with water. The solvent was evaporated under reduced pressure to obtain a red liquid product (207.1 g).

It was confirmed by infrared absorption spectrum of the resulting cyanate compound that absorption 3,200-3,600 cm^{-1} of phenolic OH disappeared and it had an absorption of 2250 cm^{-1} of nitrile of cyanate.

Preparation Example 3

This example concerns with preparation of 1,1-bis(4-cyanato-3-methylphenyl)cyclohexane which is the cyanate compound used in the present invention.

The bisphenol obtained in Preparation Example 1 (200 g, 0.68 mol) was dissolved in acetone (600 g) and the solution was cooled to -5°C. Cyanogen chloride (81.6 ml, 1.62 mol) was added to the solution and thereto was added dropwise triethylamine (143.6 g, 1.42 mol) over a period of 1 hour with taking care that the reaction temperature did not rise to higher than 0°C. After completion of the addition, the reaction mixture was kept at 2-5°C for 1 hour and then diluted with chloroform (500 g). Salts were removed by filtration and the residue was washed with water. The solvent was evaporated under reduced pressure to obtain a red resinous product (233.8 g).

It was confirmed by infrared absorption spectrum of the resulting cyanate compound that

absorption 3,200-3,600 cm^{-1} of phenolic OH disappeared and it had an absorption of 2250 cm^{-1} of nitrile of cyanate.

5 Preparation Example 4

This example concerns with preparation of N,N'-bis(4-aminophenoxyphenyl)menthanebismaleimide which is the maleimide compound used in the present invention.

10

Maleic anhydride (237.3 g) and chlorobenzene (2,373 g) were charged in a 5 liter four-necked flask and stirred under a nitrogen stream to dissolve maleic anhydride. YP-90 (reaction product of dipentene with phenol manufactured by Yasuhara Chemical Co.; hydroxyl equivalent: 162 g/eq) was allowed to react with p-chlorobenzene and the reaction product was reduced to obtain (4-aminophenoxyphenyl)menthane. A solution prepared by dissolving the resulting (4-aminophenoxyphenyl)-menthane in dimethylacetamide (DMAc) (adjusted to 34.3% by weight in concentration) (1,625.1 g) was added dropwise to the above flask at $25 \pm 5^\circ\text{C}$ over a period of 2 hours by a dropping funnel. The reaction was allowed to proceed at 35°C for 2 hours to complete the formation reaction of amic acid.

25

Then, p-toluenesulfonic acid monohydrate (10.46 g) was added to the reaction product and dehydration-cyclization reaction was carried out at 100°C for 1 hour and 110°C for 1 hour with conducting azeotropic dehydration under reduced pressure and subsequently at 135°C for 4 hours with gradually returning the pressure to normal pressure. The reaction was allowed to proceed with removing the produced water out of the system using

35

Dean-Stark apparatus.

Then, chlorobenzene and successively DMAc were recovered in an amount of totally 89% under reduced pressure. Then, methylisobutyl ketone (MIBK) (2,200 g) was added to dissolve the residue. The resulting solution was cooled to 60°C, neutralized by adding thereto sodium bicarbonate in an amount weighed so as to adjust the pH of the aqueous layer to 5-7 and water (1,000 g) and subjected to washing and separation twice. Furthermore, this was subjected to washing and separation twice with 15% aqueous sodium chloride solution (1,000 g) at 60°C and then subjected to azeotropic dehydration under reduced pressure, and the salts were removed by filtration. The filtrate was concentrated under reduced pressure and the product in molten state was taken out of the flask after the conditions in the system finally reached 150°C/5 Torr to obtain a light brown solid (724 g) (yield 98.7%). Gel permeation chromatography showed that it contained 95% of N,N'-bis(4-aminophenoxy-phenyl)menthanebismaleimide and 5% of polymeric component.

25

Properties of the product are shown below.

mass spectrum $M^+ = 666$

melting point 96 - 98°C

¹H-NMR spectrum

30

δ : 0.6 - 2.1 ppm (m, aliphatic),
2.8 ppm (m, methine),
6.8 ppm (s, imide group),
6.9 - 7.4 ppm (m, aromatic),

Infrared absorption spectrum:

35

1,238 cm^{-1} (ether bond),
1,712 cm^{-1} (imide bond).

Preparation Example 5

This example concerns with preparation of bis(4-aminophenoxyphenyl)dicyclopentanebismaleimide which is the polymaleimide compound used in the present invention.

The procedure of Preparation Example 4 was repeated except for using a solution (932.9 g) (concentration: 34.3%) prepared by dissolving in DMAc bis(4-aminophenoxyphenyl)dicyclopentane derived from DPP-600T (manufactured by Nippon Oil Co., Ltd.) in place of bis(4-aminophenoxyphenyl)-menthane derived from YP-90 (reaction product of dipentene and phenol; hydroxyl equivalent: 162 g/eq manufactured by Yasuhara Chemical Co., Ltd.) to obtain bis(4-aminophenoxyphenyl)dicyclopentane-bismaleimide (191.7 g, yield 97.4%) as a yellow crystal.

20

Properties of the product are shown below.

mass spectrum $M^+ = 662, 1060$

1H -NMR spectrum

δ : 1.0 - 2.5 ppm (m, aliphatic),
2.7 ppm (m, methine),
6.8 ppm (s, imide group),
6.6 - 7.3 ppm (m, aromatic),

Infrared absorption spectrum:

1,222 cm^{-1} (ether bond),
1,712 cm^{-1} (imide bond).

Preparation Example 6

This example concerns with preparation of N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]-dicyclopentanebismaleimide which is the polyaleimide compound used in the present invention.

Maleic anhydride (58.8 g) and acetone (137.2 g) were charged in a 1 liter four-necked flask and stirred under nitrogen stream to dissolve the maleic anhydride. With keeping the temperature at room temperature to 35°C, to the flask was added dropwise over 2 hours a solution prepared by dissolving dicyclopentane oligomer having 4-(4-aminophenoxy)-3,5-dimethylphenyl groups at both ends [prepared by reacting DXP-L-9-1 (reaction product of 2,6-xyleneol and dicyclopentadiene; hydroxyl equivalent: 191 g/eq, manufactured by Nippon Oil Co., Ltd.) with p-chloronitrobenzene and then reducing the nitro group and containing 90% of bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]-dicyclopentane measured by GPC and having an amine equivalent of 275 g/eq] (150.0 g) in acetone (350 g). Stirring was continued for further 3 hours. Then, triethylamine (16.6 g) was added, followed by stirring for 30 minutes at room temperature. Then, nickel acetate (0.58 g) was added and the temperature was raised to 40°C. Acetic anhydride (72.4 g) was added dropwise over a period of 1 hour and the temperature was kept until the reaction terminated. After termination of the reaction, the reaction mixture was discharged into pure water (1,000 g). The crystal was collected by filtration and washed with water and then with methanol, and dried by heating under reduced pressure to obtain the desired product of yellow crystal (189.4 g, yield: 97.9%).

Properties of the product are shown below.

mass spectrum M^+ = 718

¹H-NMR spectrum

δ : 1.0 - 2.5 ppm (m, aliphatic),
2.7 ppm (m, methine),
6.8 ppm (s, imide group),
6.5 - 7.3 ppm (m, aromatic),

5 Infrared absorption spectrum:
1,220 cm^{-1} (ether bond),
1,714 cm^{-1} (imide bond).

Preparation Example 7

10 This example concerns with preparation of
N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-
methylphenyl]butanebismaleimide which is the
polymaleimide compound used in the present
invention.

15 Maleic anhydride (97.1 g) and acetone
(226.5 g) were charged in a 2 liter four-necked
flask and stirred under nitrogen stream to dissolve
the maleic anhydride. With keeping the temperature
20 at room temperature to 35°C, to the flask was added
dropwise over 2 hours a solution prepared by
dissolving 1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-
methylphenyl]butane (256.5 g) in acetone (598.5 g).
Stirring was continued for further 3 hours. Then,
25 triethylamine (27.3 g) was added, followed by
stirring for 30 minutes at room temperature. Then,
nickel acetate (0.95 g) was added and the
temperature was raised to 40°C. Acetic anhydride
(119.9 g) was added dropwise over a period of 1
30 hour and the reaction was continued at that
temperature. After termination of the reaction, the
reaction mixture was discharged into water (2.5
kg). The crystal was collected by filtration and
washed with water and then with methanol, and dried
35 by heating under reduced pressure to obtain the
desired product of yellow crystal (306.1 g, yield:

93.9%). This can be recrystallized from a methylcellosolve/isopropyl alcohol mixed solvent.

Properties of the product are shown below.

5

melting point 127 - 130°C

mass spectrum $M^+ = 724$

1H -NMR spectrum

10

δ : 0.97 ppm (t, $-CHCH_2CH_2CH_3$),
1.34 ppm (s, t-butyl group),
1.92 ppm (q, $-CHCH_2CH_2CH_3$),
2.17 ppm (s, methyl group),
4.13 ppm (t, $-CHCH_2CH_2CH_3$),
6.65 ppm (s, imide group),
6.8 - 7.2 ppm (m, aromatic),

15

Infrared absorption spectrum:

1,219 cm^{-1} (ether bond),
1,712 cm^{-1} (imide bond).

Example 1

20

This example concerns with preparation of dicyanate of 4-[1-[4-[4-hydroxyphenyl]-4-methyl-cyclohexyl]-1-methylethyl]phenol of the present invention.

25

YP-90 (reaction product of dipentene and phenol manufactured by Yasuhara Chemical Co., Ltd.) (200 g, 0.645 mol), cyanogen chloride (84.4 ml, 1.677 mol) and chloroform (900 g) were charged in a 2 liter round separable four-necked flask equipped with a thermometer, a stirrer, a reflux condenser and a dropping funnel and dissolution was carried out at -5°C. Then, triethylamine (143.6 g, 1.419 mol) was added dropwise to the solution over a period of 1.5 hour. After completion of the addition, the temperature was raised to 5°C and kept at that temperature for 3 hours. The reaction

35

mixture was filtrated to remove salts, concentrated and dried under reduced pressure to obtain the desired product as a brown oil (210.3 g).

5 It was confirmed by infrared absorption spectrum of the thus obtained cyanate compound that absorption $3,200\text{--}3,600\text{ cm}^{-1}$ of phenolic OH disappeared and there was absorption of $2,250\text{ cm}^{-1}$ of nitrile of cyanate.

10 Examples 2-10

 The cyanate compounds obtained in Preparation Examples 2-3 and Example 1 were mixed with hardener at the ratio as shown in Tables 1 and 15 2 (part by weight). In Examples 5-10, for imparting flame retardancy to the resin, glycidyl ether of tetrabromobisphenol A (Sumiepoxy ESB-400T having an epoxy equivalent of 403 g/eq manufactured by Sumitomo Chemical Co., Ltd.) was further added in 20 such an amount that Br content was 10%. In Examples 2-7, the components were melt mixed at 170°C and the resulting prepolymer was press molded at 200°C for 2 hours to obtain a single resin cured product, and Tg and dielectric characteristics 25 thereof were measured. In Examples 8-10, the components were once melt mixed at 140°C to prepare a prepolymer and to the resulting prepolymer was further added zinc naphthenate as a catalyst, and the mixture was dissolved in methyl ethyl ketone to 30 prepare a homogeneous resin varnish. A glass cloth (KS-1600S962LP manufactured by Kanebo Ltd.) was impregnated with the varnish and treated at 160°C for 3-10 minutes by a hot-air dryer to obtain a prepreg. Five prepregs and a copper foil 35 (subjected to TTAI treatment; 35μ thick, manufactured by Furukawa Circuit Foil Co., Ltd.)

were stacked and hot press molded under a pressure of 50 kg/cm² at 200°C for 120 minutes and after-cured at 200°C for 120 minutes to obtain a copper-clad laminate of 1 mm thick. The properties are shown in Tables 1 and 2. Glass transition temperature (T_g) was obtained from the inflexion point of an expansion curve using a thermal analysis apparatus DT-30 manufactured by Shimadzu Seisakusho Ltd. Dielectric constant and dissipation factor at room temperature were measured using 4275A Multi-Frequency LCR meter manufactured by Yokogawa Hewlett Packard Co. and the value of dielectric constant was calculated from electric capacity. Peeling strength of the copper foil of the laminate, solder heat resistance and boiling water absorption were measured in accordance with JIS-C-6481. The properties in the following comparative examples and examples were measured also in the same manner as above.

20

Comparative Examples 1 and 2

The dicyanate compound of bisphenol A was mixed with the hardener or with the hardener and the brominated epoxy resin ESB-400T at the ratio as shown in Table 1. Resin cured products were obtained from the mixtures in the same manner as in Examples 1-6 and the properties thereof are shown in Table 1.

30

Comparative Example 3

The dicyanate compound of bisphenol A and other components were used at the ratio as in Table 2 and using the mixture, copper-clad laminate was produced in the same manner as in Examples 8-10. Properties thereof are shown in Table 2.

35

Examples 11-28

Each of the cyanate compounds obtained in Preparation Examples 2-3 and Example 1 was once melt mixed with zinc naphthenate at 140°C as a hardener to prepare prepolymers.

The resulting cyanate prepolymer was mixed with each of the polymaleimide compounds obtained in Preparation Examples 4-7 or N,N'-bis(4-aminophenyl)methanebismaleimide (manufactured by K.I. Kasei Co.) or N,N'-2,2-bis(4-aminophenoxyphenyl)propane bismaleimide (MB8000 manufactured by Mitsubishi Petrochemical Co., Ltd.) together with the hardener at the ratio as shown in Tables 3-5 and the resulting mixture was hot pressed at 200°C for 2 hours under a pressure of 50 kg/cm² to prepare cured products. Properties of the products are shown in Tables 3-5. The ratio in these tables is shown by "part by weight".

Examples 29-49

Each of the cyanate compounds obtained in Preparation Examples 2-3 and Example 1 was once melt mixed with zinc naphthenate as a hardener at 140°C to prepare prepolymers.

The resulting cyanate prepolymer was mixed with each of the polymaleimide compounds obtained in Preparation Examples 4-7 or N,N'-bis(4-aminophenyl)methanebismaleimide (manufactured by K.I. Kasei Co.) or N,N'-2,2-bis(4-aminophenoxyphenyl)propane bismaleimide (MB8000 manufactured by Mitsubishi Petrochemical Co., Ltd.) together with the hardener at the ratio as shown in Tables 6-8 and the resulting mixture was dissolved in dimethylformamide to prepare a homogeneous resin varnish. Using the

resin varnish, copper-clad laminates were produced in the same manner as in Examples 8-10.

5 In Examples 35, 42 and 49, for imparting flame retardancy, glycidyl ether of tetrabromo-bisphenol A (Sumiepoxy ESB-400T used hereabove) was added in such an amount that Br content in the resin composition was 5% by weight. Properties of the resulting copper-clad laminates are shown in
10 Tables 6-8. In Tables 6-8, the amounts are shown by "part by weight" except that the amounts of zinc naphthenate and 2-ethyl-4-methylimidazole are shown by part by weight (phr) based on totally 100 parts by weight of the cyanate compound and the epoxy
15 compound.

Dicyanate compound of bisphenol A was mixed with the hardener and the brominated epoxy resin ESB-400T at the ratio (part by weight) as
20 shown in Tables 6-8 and the mixture was dissolved in methyl ethyl ketone to obtain a homogeneous resin varnish. Using the varnish, copper-clad laminates were produced in the same manner as in Examples 8-10 and properties thereof were measured
25 as in Examples 8-10. The results are shown in Tables 6-8.

Comparative Examples 4-6

30 The dicyanate compound of bisphenol A was used at the same ratio as in Tables 3-5 and cured products of the mixtures were obtained in the same manner as in Examples 11-28. Properties thereof are shown in Tables 3-6.

35 Comparative Examples 7-9

The dicyanate compound of bisphenol A was

used at the same ratio as in Tables 6-8 and using the mixtures, copper-clad laminates were produced in the same manner as in Examples 29-49. Properties thereof are shown in Tables 6-8.



T a b l e 1

Mixing ratio and properties of resin-cured product								
	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7	Comparative Example 1	Comparative Example 2
Cyanate compound of Preparation Example 2	100	-	-	80	-	-	-	-
Cyanate compound of Preparation Example 3	-	100	-	-	80	-	-	-
Cyanate compound of Example 1	-	-	100	-	-	80	-	-
Bisphenol A dicyanate	-	-	-	-	-	-	100	80
Sumiepoxy ESB-400T	-	-	-	20	20	20	-	20
Zinc naphthenate (phr)	0.2	0.3	0.2	0.2	0.3	0.2	0.1	0.1
Glass transition temperature (°C)	238	231	246	215	210	238	220	191
Dielectric constant (1MHz)	2.90	2.88	2.90	2.98	2.96	2.97	3.23	3.32
- Dielectric loss tangent (1MHz)	0.004	0.005	0.005	0.005	0.006	0.006	0.008	0.005



T a b l e 3

	Mixing ratio and properties of resin-cured product									
	Example 11	Example 12	Example 13	Example 14	Example 15	Example 16	Comparative Example 4			
Cyanate compound of Preparation Example 2	90	90	90	90	90	90	-			
Bisphenol A dicyanate Compound 1	-	-	-	-	-	-	90			
Compound 2	10	10	-	-	-	-	-			
Compound 3	-	-	10	-	-	-	-			
Compound 4	-	-	-	10	-	-	-			
Compound 5	-	-	-	-	10	-	-			
Compound 6	-	-	-	-	-	10	10			
Zinc naphthenate	0.2	0.2	0.2	0.2	0.2	0.2	0.1			
2-Ethyl-4-methylimidazole	0.05	0.05	0.05	0.05	0.05	0.05	0.05			
Glass transition temperature (°C)	240	230	228	231	226	223	230			
Dielectric constant (1MHz)	2.92	2.90	2.91	2.91	2.95	2.94	3.15			
Dielectric loss tangent (1MHz)	0.005	0.004	0.004	0.004	0.005	0.005	0.006			

(Notes)

Cyanate compound of Preparation Example 2: 1,1-Bis(4-cyanatophenyl)cyclohexane

Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane

Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebismaleimide (Preparation Example 5)

Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanebismaleimide (Preparation Example 6)

Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanebismaleimide oligomer (Preparation Example 7)

Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebismaleimide (Preparation Example 8)

Compound 5: N,N'-bis(4-aminophenyl)methanebismaleimide (K.I. Kasei Co.)

Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebismaleimide (Mitsubishi Petrochemical Co., Ltd.)

T a b l e 4

	Mixing ratio and properties of resin-cured product									
	Example 17	Example 18	Example 19	Example 20	Example 21	Example 22	Example 23	Example 24	Example 25	Comparative Example 5
Cyanate compound of Preparation Example 3	90	90	90	90	90	90				-
Bisphenol A dicyanate	-	-	-	-	-	-				90
Compound 1	10	-	-	-	-	-				-
Compound 2	-	10	-	-	-	-				-
Compound 3	-	-	10	-	-	-				-
Compound 4	-	-	-	10	-	-				-
Compound 5	-	-	-	-	10	-				-
Compound 6	-	-	-	-	-	10				10
Zinc naphthenate	0.3	0.3	0.3	0.3	0.3	0.3				0.1
2-Ethyl-4-methylimidazole	0.05	0.05	0.05	0.05	0.05	0.05				0.05
Glass transition temperature (°C)	230	225	223	228	221	219				230
Dielectric constant (1MHz)	2.89	2.90	2.91	2.90	2.93	2.93				3.15
Dielectric loss tangent (1MHz)	0.005	0.005	0.005	0.005	0.006	0.005				0.006

(Notes)

Cyanate compound of Preparation Example 3: 1,1-Bis(4-cyanato-3-methylphenyl)cyclohexane
 Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane
 Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebismaleimide
 Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanebismaleimide
 Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanebismaleimide oligomer
 Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebismaleimide
 Compound 5: N,N'-bis(4-aminophenyl)methanebismaleimide
 Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebismaleimide



T a b l e 5

	Mixing ratio and properties of resin-cured product									
	Example 23	Example 24	Example 25	Example 26	Example 27	Example 28	Example 29	Example 30	Example 31	Comparative Example 6
Cyanate compound of Example 1	90	90	90	90	90	90	90	90	90	-
Bisphenol A dicyanate	-	-	-	-	-	-	-	-	-	90
Compound 1	10	-	-	-	-	-	-	-	-	-
Compound 2	-	10	-	-	-	-	-	-	-	-
Compound 3	-	-	10	-	-	-	-	-	-	-
Compound 4	-	-	-	10	-	-	-	-	-	-
Compound 5	-	-	-	-	10	-	-	-	-	10
Compound 6	-	-	-	-	-	10	-	-	-	-
Zinc naphthenate	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.1
2-Ethyl-4-methylimidazole	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05
Glass transition temperature (°C)	246	240	236	237	232	230	230	230	230	230
Dielectric constant (1MHz)	2.91	2.90	2.91	2.90	2.93	2.93	2.93	2.93	2.93	3.15
Dissipation factor (1MHz)	0.005	0.005	0.005	0.005	0.005	0.005	0.005	0.005	0.005	0.006

(Notes)

Cyanate compound of Example 1: Dicyanate of 4-[1-[4-[4-hydroxyphenyl]-4-methylcyclohexyl]-1-methylethyl]-phenol

Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane

Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebismaleimide

Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanebismaleimide

Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanebismaleimide oligomer

Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebismaleimide

Compound 5: N,N'-bis(4-aminophenyl)methanebismaleimide

Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebismaleimide



Table 6

	Mixing ratio and properties of laminate										
	Example 29	Example 30	Example 31	Example 32	Example 33	Example 34	Example 35	Comparative Example 7			
Cyanate compound of Preparation Example 2 Bisphenol A dicyanate	90	90	90	90	90	90	80	-			
Compound 1	-	-	-	-	-	-	-	90			
Compound 2	10	10	-	-	-	-	-	-			
Compound 3	-	-	10	-	-	-	-	-			
Compound 4	-	-	-	10	-	-	-	-			
Compound 5	-	-	-	-	10	-	10	-			
Compound 6	-	-	-	-	-	10	-	10			
Sumiepoxy ESB-400T	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.3			
Zinc naphthenate	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05			
2-Ethyl-4-methylimidazole	242	235	228	232	233	228	225	227			
Glass transition temperature (°C)	3.81	3.79	3.80	3.81	3.89	3.90	3.92	4.20			
Dielectric constant (1MHz)	0.005	0.004	0.004	0.004	0.005	0.005	0.006	0.004			
Dielectric loss tangent (1MHz)	0.51	0.55	0.56	0.53	0.50	0.70	0.65	0.70			
Boiling water absorption (%, 48h)	○	○	○	○	○	○	○	○			
Solder heat resistance (260°C x 3 min.)	○	○	○	○	○	○	○	○			

(Notes)

Cyanate compound of Preparation Example 2: 1,1-Bis(4-cyanatophenyl)cyclohexane
 Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane
 Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebismaleimide
 Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanebismaleimide
 Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanebismaleimide
 Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebismaleimide
 Compound 5: N,N'-bis(4-aminophenyl)methanebismaleimide
 Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebismaleimide



T a b l e 7

	Mixing ratio and properties of laminate									
	Example 36	Example 37	Example 38	Example 39	Example 40	Example 41	Example 42	Comparative Example 8		
Cyanate compound of Preparation Example 3	90	90	90	90	90	90	80	-		
Bisphenol A dicyanate Compound 1	-	-	-	-	-	-	-	90		
Compound 2	10	10	-	-	-	-	-	-		
Compound 3	-	-	10	-	-	-	-	-		
Compound 4	-	-	-	10	-	-	-	-		
Compound 5	-	-	-	-	10	-	10	-		
Compound 6	-	-	-	-	-	10	-	10		
Sumiepoxy ESB-400T	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3		
Zinc naphthenate	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05		
2-Ethyl-4-methylimidazole										
Glass transition temperature (°C)	231	230	228	225	228	221	220	227		
Dielectric constant (1MHz)	3.78	3.75	3.81	3.80	3.85	3.87	3.89	4.20		
Dielectric loss tangent (1MHz)	0.005	0.005	0.005	0.005	0.006	0.005	0.006	0.004		
Boiling water absorption (% , 48h)	0.40	0.45	0.41	0.43	0.44	0.56	0.55	0.70		
Solder heat resistance (260°C x 3 min.)	○	○	○	○	○	○	○	○		

(Notes)

Cyanate compound of Preparation Example 3: 1,1-Bis(4-cyano-3-methylphenyl)cyclohexane
 Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane
 Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebismaleimide
 Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanebismaleimide
 Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanebismaleimide oligomer
 Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebismaleimide
 Compound 5: N,N'-bis(4-aminophenoxy)methanebismaleimide
 Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebismaleimide



Table 8

	Mixing ratio and properties of laminate									
	Example 43	Example 44	Example 45	Example 46	Example 47	Example 48	Example 49	Comparative Example 9		
Cyanate compound of Example 1	90	90	90	90	90	90	80	-		
Bisphenol A dicyanate Compound 1	-	-	-	-	-	-	-	90		
Compound 2	10	-	-	-	-	-	-	-		
Compound 3	-	10	-	-	-	-	-	-		
Compound 4	-	-	10	-	-	-	-	-		
Compound 5	-	-	-	10	-	-	-	-		
Compound 6	-	-	-	-	10	-	10	-		
Sumiepoxy ESB-400T	-	-	-	-	-	10	-	10		
Zinc naphthenate	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.3		
2-Ethyl-4-methylimidazole	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05		
Glass transition temperature (°C)	258	251	246	249	245	243	239	227		
Dielectric constant (1MHz)	3.82	3.82	3.80	3.83	3.91	3.92	3.93	4.20		
Dielectric loss tangent (1MHz)	0.005	0.005	0.005	0.005	0.005	0.006	0.006	0.004		
Boiling water absorption (% , 48h)	0.39	0.43	0.41	0.43	0.45	0.53	0.58	0.70		
Solder heat resistance (260°C x 3 min.)	○	○	○	○	○	○	○	○		

(Notes)

Cyanate compound of Example 1: Dicyanate of 4-[1-[4-hydroxyphenyl]-4-methylcyclohexyl]-1-methylethyl]phenol
 Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane
 Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebismaleimide
 Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanebismaleimide
 Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanebismaleimide oligomer
 Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebismaleimide
 Compound 5: N,N'-bis(4-aminophenyl)methanebismaleimide
 Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebismaleimide


As explained above, copper-clad laminates obtained using the cyanate resin composition of the present invention are lower in dielectric constant than conventional laminates and furthermore
5 superior in water resistance and heat resistance. Therefore, the copper-clad laminates are suitable for multilayer printed circuit boards for high speed operation processing.



CLAIMS:

1. A cyanate resin composition comprising as essential components:


(A) a cyanate compound represented by the following formula (1):



15

wherein R and Q each represents a halogen atom, an alkyl group of 1-10 carbon atoms, a cycloalkyl group of 5-7 carbon atoms or a hydrocarbon group of 6-20 carbon atoms which contains a cycloalkyl group of 5-7 carbon atoms, i and j each represents an integer of 0-4 with a proviso that, when i and j represent 2 or more, R and Q may be identical or different and M represents a group shown by the following formula (2):

25



35




wherein T represents a halogen atom, an alkyl group of 1-10 carbon atoms, a cycloalkyl group of 5-7 carbon atoms or a hydrocarbon group of 6-20 carbon atoms which contains a cycloalkyl group of 5-7 carbon atoms, k represents an integer of 0-10 and m represents an integer of 0-8 with a proviso that, when k or m represents 2 or more, T may be identical or different, or a prepolymer of the cyanate compound, and

(B) a hardener.


2. A cyanate resin composition according to claim 1, which comprises as essential components the above (A) and (B) and additionally (C) at least one selected from a brominated epoxy compound, a prepolymer thereof, a maleimide compound and a prepolymer thereof.

3. A cyanate compound represented by the following formula (3):








wherein R, Q, i and j are as defined in the formula (1).

4. A cyanate resin composition according to claim 2, wherein the maleimide compound is represented by the following formula (5):



10 wherein X represents a group having the following formula (6), (7), (8), (9), (10) or (11):





- 37 -

5. A copper-clad laminate obtained by heat-molding a copper foil and a prepreg obtained by impregnating a substrate with a solution prepared by dissolving the cyanate resin composition of claim 1, 2 or 4 in an organic solvent.

2. S-2000000

ABSTRACT


CYANATE RESIN COMPOSITION AND COPPER-CLAD LAMINATE

5

A cyanate resin composition suitable for a copper-clad laminate comprises components (A) and (B).

(A) a cyanate compound of the formula:

10




15

wherein R and Q each represents halogen, C_{1-10} alkyl, C_{5-7} cycloalkyl or C_{6-20} hydrocarbon; i and j each represents 0-4 and M is

20

(2):

25






30

wherein T represents halogen, C_{1-10} alkyl, C_{5-7} cycloalkyl or C_{6-20} hydrocarbon; k represents 0-10 and m represents 0-8, and

(B) a hardener.

35

21 MAR 1996



25 The cyanate compounds, brominated epoxy compounds and maleimide compounds used in the present invention may be used in the form of prepolymers. The prepolymers are produced by heating the compounds each alone or mixtures thereof in the presence of the hardener described above.

30 When flame retardancy is imparted to the copper-clad laminate, for example, a brominated epoxy compound is added to the composition so that bromine content is in the range of 5-25%. Considering easiness in availability and economical advantage, the brominated epoxy compounds usable include, for example, glycidyl ether of tetrabromobisphenol A and glycidyl ether of brominated phenol novolak, but these are not limitative.

35 Furthermore, as far as the present advantage is not damaged, there may be additionally used other thermosetting resins. Examples are epoxy resins such as diglycidyl ethers of bisphenol

21 MAR 1996

Table 1

	Mixing ratio and properties of resin-cured product										Comparative Example 2
	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7	Example 8	Example 9	Example 10	Comparative Example 1	
Cyanate compound of Preparation Example 2	100	-	-	80	-	-	-	-	-	-	-
Cyanate compound of Preparation Example 3	-	100	-	-	80	-	-	-	-	-	-
Cyanate compound of Example 1	-	-	100	-	-	80	-	-	-	-	-
Bisphenol A dicyanate	-	-	-	-	-	-	-	-	100	100	80
Sumiepoxy ESB-400T	-	-	-	20	20	20	-	-	-	-	20
Zinc naphthenate (phr)	0.2	0.3	0.2	0.2	0.3	0.2	-	-	0.1	0.1	0.1
Glass transition temperature (°C)	238	231	246	215	210	238	-	-	220	220	191
Dielectric constant (1MHz)	2.90	2.88	2.90	2.98	2.96	2.97	-	-	3.23	3.23	3.32
- Dielectric loss tangent (1MHz)	0.004	0.005	0.005	0.005	0.006	0.006	-	-	0.008	0.008	0.005

21 MAR 1996

Table 3

	Mixing ratio and properties of resin-cured product									
	Example 11	Example 12	Example 13	Example 14	Example 15	Example 16	Comparative Example 4			
Cyanate compound of Preparation Example 2	90	90	90	90	90	90	-			
Bisphenol A dicyanate	-	-	-	-	-	-	90			
Compound 1	10	-	-	-	-	-	-			
Compound 2	-	10	-	-	-	-	-			
Compound 3	-	-	10	-	-	-	-			
Compound 4	-	-	-	10	-	-	-			
Compound 5	-	-	-	-	10	-	10			
Compound 6	-	-	-	-	-	10	-			
Zinc naphthenate	0.2	0.2	0.2	0.2	0.2	0.2	0.1			
2-Ethyl-4-methylimidazole	0.05	0.05	0.05	0.05	0.05	0.05	0.05			
Glass transition temperature (°C)	240	230	228	231	226	223	230			
Dielectric constant (1MHz)	2.92	2.90	2.91	2.91	2.95	2.94	3.15			
Dielectric loss tangent (1MHz)	0.005	0.004	0.004	0.004	0.005	0.005	0.006			

(Notes)

Cyanate compound of Preparation Example 2: 1,1-Bis(4-cyanatophenyl)cyclohexane

Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane

Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebismaleimide (Preparation Example 5)

Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanbismaleimide (Preparation Example 6)

Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanbismaleimide oligomer (Preparation Example 7)

Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebismaleimide (Preparation Example 8)

Compound 5: N,N'-bis(4-aminophenyl)methanebismaleimide (K.I. Kasei Co.)

Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebismaleimide (Mitsubishi Petrochemical Co., Ltd.)

21 MAR 1996

Table 5

	Mixing ratio and properties of resin-cured product										Comparative Example 6
	Example 23	Example 24	Example 25	Example 26	Example 27	Example 28	Example 29	Example 30	Example 31	Example 32	
Cyanate compound of Example 1	90	90	90	90	90	90	90	90	90	90	-
Bisphenol A dicyanate	-	-	-	-	-	-	-	-	-	-	90
Compound 1	10	-	-	-	-	-	-	-	-	-	-
Compound 2	-	10	-	-	-	-	-	-	-	-	-
Compound 3	-	-	10	-	-	-	-	-	-	-	-
Compound 4	-	-	-	10	-	-	-	-	-	-	-
Compound 5	-	-	-	-	10	-	-	-	-	-	10
Compound 6	-	-	-	-	-	10	-	-	-	-	-
Zinc naphthenate	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.1
2-Ethyl-4-methylimidazole	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05
Glass transition temperature (°C)	246	240	236	237	232	230	230	230	230	230	230
Dielectric constant (1MHz)	2.91	2.90	2.91	2.90	2.93	2.93	2.93	2.93	2.93	2.93	3.15
Dissipation factor (1MHz)	0.005	0.005	0.005	0.005	0.005	0.005	0.005	0.005	0.005	0.005	0.006

(Notes)

Cyanate compound of Example 1: Dicyanate of 4-[1-[4-[4-hydroxyphenyl]-4-methylcyclohexyl]-1-methylethyl]-phenol

Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane

Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebisaleimide

Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanebisaleimide

Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanebisaleimide

Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebisaleimide

Compound 5: N,N'-bis(4-aminophenyl)methanebisaleimide

Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebisaleimide

21 MAR 1996

Table 6

	Mixing ratio and properties of laminate											Comparative Example 7
	Example 29	Example 30	Example 31	Example 32	Example 33	Example 34	Example 35	Example 36	Example 37	Example 38	Example 39	
Cyanate compound of Preparation Example 2	90	90	90	90	90	90	80					-
Bisphenol A dicyanate	-	-	-	-	-	-	-					90
Compound 1	10	-	-	-	-	-	-					-
Compound 2	-	10	-	-	-	-	-					-
Compound 3	-	-	10	-	-	-	-					-
Compound 4	-	-	-	10	-	-	-					-
Compound 5	-	-	-	-	10	-	-					-
Compound 6	-	-	-	-	-	10	-					10
Sumiepoxy ESB-400T	0.2	0.2	0.2	0.2	0.2	0.2	0.2					-
Zinc naphthenate	0.05	0.05	0.05	0.05	0.05	0.05	0.05					0.3
2-Ethyl-4-methylimidazole												0.05
Glass transition temperature (°C)	242	235	228	232	233	228	225					227
Dielectric constant (1MHz)	3.81	3.79	3.80	3.81	3.89	3.90	3.92					4.20
Dielectric loss tangent (1MHz)	0.005	0.004	0.004	0.004	0.005	0.005	0.006					0.004
Boiling water absorption (%, 48h)	0.51	0.55	0.56	0.53	0.50	0.70	0.65					0.70
Solder heat resistance (260°C x 3 min.)	○	○	○	○	○	○	○					○

(Notes)

Cyanate compound of Preparation Example 2: 1,1-Bis(4-cyanatophenyl)cyclohexane
 Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane
 Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebismaleimide
 Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanebismaleimide
 Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanebismaleimide oligomer
 Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebismaleimide
 Compound 5: N,N'-bis(4-aminophenyl)methanebismaleimide
 Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebismaleimide

21 MAR 1996

Table 7

	Mixing ratio and properties of laminate										Comparative Example 8
	Example 36	Example 37	Example 38	Example 39	Example 40	Example 41	Example 42	Example 43	Example 44	Example 45	
Cyanate compound of Preparation Example 3	90	90	90	90	90	90	80				-
Bisphenol A dicyanate	-	-	-	-	-	-	-				90
Compound 1	10	-	-	-	-	-	-				-
Compound 2	-	10	-	-	-	-	-				-
Compound 3	-	-	10	-	-	-	-				-
Compound 4	-	-	-	10	-	-	-				-
Compound 5	-	-	-	-	10	-	-				-
Compound 6	-	-	-	-	-	10	-				-
Sumiepoxy ESB-400T	-	-	-	-	-	-	-				10
Zinc naphthenate	0.3	0.3	0.3	0.3	0.3	0.3	0.3				-
2-Ethyl-4-methylimidazole	0.05	0.05	0.05	0.05	0.05	0.05	0.05				0.3
											0.05
Glass transition temperature (°C)	231	230	228	225	228	221	220				227
Dielectric constant (1MHz)	3.78	3.75	3.81	3.80	3.85	3.87	3.89				4.20
Dielectric loss tangent (1MHz)	0.005	0.005	0.005	0.005	0.006	0.005	0.006				0.004
Boiling water absorption (%, 48h)	0.40	0.45	0.41	0.43	0.44	0.56	0.55				0.70
Solder heat resistance (260°C x 3 min.)	○	○	○	○	○	○	○				○

(Notes)

Cyanate compound of Preparation Example 3: 1,1-Bis(4-cyanato-3-methylphenyl)cyclohexane
 Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane
 Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebismaleimide
 Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanebismaleimide
 Compound 3: N,N'-bis[4-(4-aminophenoxy)-3,5-dimethylphenyl]dicyclopentanebismaleimide
 Compound 4: N,N'-1,1-bis[4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebismaleimide
 Compound 5: N,N'-bis(4-aminophenyl)methanebismaleimide
 Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebismaleimide

21 MAR 1996

Table 8

	Mixing ratio and properties of laminate											Comparative Example 9
	Example 43	Example 44	Example 45	Example 46	Example 47	Example 48	Example 49	Example 49	Example 48	Example 47	Example 46	
Cyanate compound of Example 1	90	90	90	90	90	90	90	80	90	90	80	-
Bisphenol A dicyanate Compound 1	-	-	-	-	-	-	-	-	-	-	-	90
Compound 2	10	-	-	-	-	-	-	-	-	-	-	-
Compound 3	-	10	-	-	-	-	-	-	-	-	-	-
Compound 4	-	-	10	-	-	-	-	-	-	-	-	-
Compound 5	-	-	-	10	-	-	-	-	-	-	-	-
Compound 6	-	-	-	-	10	-	-	-	-	-	-	-
Sumiepoxy ESB-400T	-	-	-	-	-	10	-	-	10	-	-	10
Zinc naphthenate	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.3
2-Ethyl-4-methylimidazole	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05
Glass transition temperature (°C)	258	251	246	249	245	243	239	227	243	245	239	227
Dielectric constant (1MHz)	3.82	3.82	3.80	3.83	3.91	3.92	3.93	4.20	3.92	3.91	3.93	4.20
Dielectric loss tangent (1MHz)	0.005	0.005	0.005	0.005	0.005	0.006	0.006	0.004	0.006	0.005	0.006	0.004
Boiling water absorption (% 48h)	0.39	0.43	0.41	0.43	0.45	0.53	0.58	0.70	0.53	0.45	0.58	0.70
Solder heat resistance (260°C x 3 min.)	○	○	○	○	○	○	○	○	○	○	○	○

(Notes)

Cyanate compound of Example 1: Dicyanate of 4-[1-[4-hydroxyphenyl]-4-methylcyclohexyl]-1-methylethylphenol
 Bisphenol A dicyanate: 2,2-Bis(4-cyanatophenyl)propane
 Compound 1: N,N'-bis(4-aminophenoxyphenyl)methanebisaleimide
 Compound 2: N,N'-bis(4-aminophenoxyphenyl)dicyclopentanetanebisaleimide
 Compound 3: N,N'-bis(4-aminophenoxy)-3,5-dimethylphenyl[dicyclopentanetanebisaleimide oligomer
 Compound 4: N,N'-1,1-bis(4-(4-aminophenoxy)-5-t-butyl-2-methylphenyl]butanebisaleimide
 Compound 5: N,N'-bis(4-aminophenoxy)methanebisaleimide
 Compound 6: N,N'-2,2-bis(4-aminophenoxyphenyl)propanebisaleimide