

CLAIMS

What is claimed is:

1. A thermoset material containing β -hydroxyesters wherein said thermoset material is
subject to a mechano-chemical process to regenerate an epoxide and a carboxylic acid
5 functionality.
2. The thermoset material according to claim 1 wherein said resin comprises a reaction
product between an epoxidized triglyceride and a naturally occurring polyfunctional
carboxylic acid.
3. The thermoset material according to claim 1 wherein said mechano-chemical process
10 transforms the thermoset material into a millable gum.
4. The thermoset material according to claim 1 wherein said regenerated epoxide and
carboxylic acid functionality is sufficient to affect a re-crosslinking of said thermoset
material after said mechano-chemical process.
5. The thermoset material according to claim 1 wherein:
15
 - a. said thermoset material is added to an epoxidized natural rubber, and
 - b. said thermoset material acts as a curative for the epoxidized natural rubber.
6. The thermoset material according to claim 1 wherein said thermoset material is added to
an epoxidized natural rubber as a sole curative.
7. The thermoset material according to claim 1 wherein said thermoset material constitutes
20 over 20% by weight of an elastomeric content of a rubber compound.
8. The thermoset material according to claim 1 wherein said epoxidized natural rubber
constitutes over 20% by weight of an elastomeric content of said thermoset material.
9. The thermoset material according to claim 1 wherein a power-per-unit-volume of said
thermoset material required to regenerate said epoxide and carboxylic acid functionality
25 is at least 1.9×10^5 W/l.

10. The thermoset material according to claim 1 wherein a power-per-unit-volume of said thermoset material required to regenerate said epoxide and carboxylic acid functionality is between 1.9×10^5 W/l and 6.67×10^5 W/l.
11. The thermoset material according to claim 9 wherein an average temperature of said thermoset material during said mechano-chemical process does not exceed 75°C.
12. The thermoset material according to claim 1 wherein the thermoset material is further defined as being a thermoset resin.
13. A rubber compound containing over 20% by weight of an elastomeric content of a previously thermoset material, wherein said previously thermoset material is mechano-chemically de-crosslinked during the mixing of the rubber compound.
14. The rubber compound according to claim 13 wherein said previously thermoset material consists of a reaction product between an epoxidized triglyceride and a naturally occurring polyfunctional carboxylic acid.
15. The rubber compound according to claim 14 wherein said epoxidized triglyceride is selected from a group consisting of epoxidized soybean oil, epoxidized linseed oil, epoxidized corn oil, epoxidized cottonseed oil, epoxidized canola oil, epoxidized rapeseed oil, epoxidized grape seed oil, epoxidized poppy seed oil, epoxidized tongue oil, epoxidized sunflower oil, epoxidized safflower oil, epoxidized wheat germ oil, epoxidized walnut oil, and epoxidized microbial-produced oil.
16. The rubber compound according to claim 13 wherein said naturally occurring polyfunctional carboxylic acid is selected from a group consisting of citric acid, tartaric acid, succinic acid, malic acid, maleic acid, and fumaric acid.
17. The rubber compound according to claim 13 wherein said mechano-chemical de-crosslinking regenerates an epoxide and a carboxylic acid functionality in the previously thermoset material.

18. The rubber compound according to claim 13 wherein an elastomeric content of the compound consists of at least 20% by weight of an epoxidized natural rubber.
19. The rubber compound according to claim 13 wherein:
- a. the previously thermoset material is mechano-chemically de-crosslinked during a mixing of the rubber compound, and
 - b. the mechano-chemically de-crosslinked thermoset material constitutes at least 20% of a total elastomer content of the compound.
20. A material comprising:
- a. an epoxidized natural rubber; and
 - b. a thermoset material reaction product of an epoxidized triglyceride and a naturally occurring polyfunctional carboxylic acid.
21. The material according to claim 20 wherein the epoxidized natural rubber and the thermoset material reaction product of an epoxidized triglyceride and a naturally occurring polyfunctional carboxylic acid are self-reactive towards each other so that the epoxidized natural rubber is crosslinked via β -hydroxyesters.
22. The material according to claim 20 wherein the material further contains at least 20% by weight of a self-same material that had previously been cured.
23. The material according to claim 20 further comprising a filler selected from among various non-petrochemically derived sources that include: cork powder, ground rice hulls, activated carbon, activated charcoal, kaolin clay, metakaolin clay, precipitated silica, talc, mica, corn starch, mineral pigments, cotton, jute, hemp, ramie, sisal, coconut fiber, kapok fiber, silk, or wool.
24. The material according to claim 20 wherein said thermoset material is further defined as a thermoset resin.
25. A material comprising:

- a. an epoxidized natural rubber cured with a reaction product of an epoxidized triglyceride and a naturally occurring polyfunctional carboxylic acid, and
- b. wherein said material contains at least 20% by weight of a remilled elastomer that was a self-same epoxidized natural rubber cured with a reaction product of an epoxidized triglyceride and a naturally occurring polyfunctional carboxylic acid.
26. The material according to claim 25 wherein the remilled elastomer constitutes at least 50% by weight of the material content.
27. The material according to claim 25 wherein the remilled elastomer constitutes at least 75% by weight of the material content.
28. The material according to claim 25 further comprising a filler selected from among various non-petrochemically derived sources that include: cork powder, ground rice hulls, activated carbon, activated charcoal, kaolin clay, metakaolin clay, precipitated silica, talc, mica, corn starch, mineral pigments, cotton, jute, hemp, ramie, sisal, coconut fiber, kapok fiber, silk, or wool.