

Substrate with Antimicrobial Properties

The present invention relates to a substrate of any type: metal, glass, glass ceramic, wherein at least one of its surfaces has antimicrobial, in particular antibacterial or antifungal, properties. The present invention also relates to processes for the production of such a substrate.

5 In the field of ceramic substrates, EP 653 161, for example, describes the possibility of covering these with a glaze composed of silver to provide them with antibacterial properties.

 In the field of glass-type substrates, sol-gel type processes are known to provide an antimicrobial surface. These processes require a hardening stage of the sol-gel
10 layer, which involves elevated temperatures in the order of 500°-600°C (sintering temperature). Processes are also known that require the substrate to be dipped in a composition comprising a silver salt. In this case, a silver layer is not deposited, but an ion exchange takes place in the solution at an elevated temperature.

 A process for producing a glass substrate having antimicrobial properties is
15 also known from EP 1449816. This process requires both a drying stage between 20° and 105°C and a thermal treatment at 600°-650°C. This thermal treatment has some disadvantages particularly with respect to cost and uniformity of the product. Moreover, it renders the process very poorly reproducible, since it has been found that at these temperatures the diffusion of the silver is very rapid and a slight variation in the duration
20 of the thermal treatment results in a significant variation in the depth of diffusion of the silver, and therefore this causes variation in the antibacterial properties of the substrate. It may also be noted that such a thermal treatment causes an undesirable yellow colouration of a soda-lime glass substrate. Furthermore, with this process, after having been treated, the product may no more be cut into particular size because of the necessary tempering
25 process.

 Therefore, there is a need to provide a substrate, either glass or metallic, with antimicrobial properties, which is easy to use and inexpensive to produce.

 The present invention relates to a substrate coated with at least one mineral layer, particularly selected from metal oxides, oxynitrides, oxycarbides,

carbides, DLC (diamond like carbon) or nitrides, said layer comprising at least one antimicrobial agent. In particular, the mineral layer can be selected from oxides of silicon, tin, zinc, titanium, niobium, aluminium, zirconium or mixture thereof, for example ZnSnOx. Particularly preferred nitrides are silicon, titanium and aluminium nitrides and mixture thereof.

The antimicrobial agent can be selected from various inorganic agents known for their antimicrobial properties, in particular silver, copper and zinc. Advantageously, the antimicrobial agent is in metallic form.

The substrate can be metallic, e.g. made of steel, or stainless steel or ceramic type or plastic or thermoplastic type substrate or a glass-type substrate, in particular a sheet of flat glass, particularly soda-lime glass which may be float glass. It may be clear glass or coloured glass. It may comprise a reflective layer (to form a mirror) or a layer of enamel or painting (for wall covering), generally at the surface opposite to the antimicrobial surface.

The substrate may have a thickness within the range of 2.5 to 12 mm.

The substrate may have a surface area of greater than 0.8 m to 0.8m; it may be adapted to be cut to a finished size by a subsequent cutting operation.

In some embodiments of the invention, a substrate having antimicrobial agents present at at least one exposed surface may be an annealed sheet of glass. The term annealed sheet of glass is used herein to mean that the glass may be cut to size without breaking in the way that a tempered or hardened sheet of glass would break upon cutting. Such an annealed sheet of glass preferably has a surface compression of less than 5 MPa.

It has been found that it is possible to cause antimicrobial agents to diffuse into a mineral coating formed from one or more layers of metal oxides, oxynitrides, oxycarbides or nitrides, when this coating has been firstly deposited on a substrate of whatever type. The diffusion of the antimicrobial agent can also occur in a topcoat deposited above the layer containing the antimicrobial agent.

For example, the substrate can be coated with a first layer that blocks or slows down the diffusion of the antimicrobial agents and optionally with a second layer serving as a reservoir for the antimicrobial agents. Those functions can be

ascertained on a product made according to the invention by comparing the antimicrobial effect of similar products with and without undercoating and/or by analysing diffusion profiles.

Each layers of the undercoat may in particular have a thickness comprised
 5 between 1 and 1000 nm, preferably between 1.5 and 800 nm, most preferably between 2 and 600 nm.

In particular, the blocking underlayer is chosen amongst pyrolytic and sputtered layers, in particular layers comprising metal oxide, metal or metal alloy compound, such as Pd, Ni-Cr, TiO_x, NiCrO_x, Nb, Ta, Al, Zr or ZnAl, or mixture
 10 thereof.

In the case of a glass substrate, it is conceivable that the antimicrobial glass substrate thus obtained is subjected to a thermal treatment stage such as thermal tempering, bending or hardening, while still retaining its antimicrobial properties.

15 In the case of metallic substrate, particularly preferred undercoat and/or mixed layers are chosen amongst titanium oxide, titanium nitride or zirconium oxide.

The substrate according to the invention preferably has an antibacterial effect on a large number of bacteria, whether gram positive or gram negative bacteria, in particular on at least one of the following bacteria: *Escherichia coli*,
 20 *Staphylococcus aureus*, *Pseudomonas aeruginosa*, *Enterococcus hirae*. The antibacterial effect measured in accordance with the standard JIS Z 2801 is in particular, at least on any one of these bacteria, higher than log 1, preferably higher than log 2 and particularly preferred higher than log 2.5. The substrate will be considered bactericidal according to the standard JIS Z 2810 if it has an effect higher
 25 than log 2. However, the invention also relates to substrates that have a lesser effect (for example bacteriostatic effect, which means that the bacteria are not necessarily killed but can not developed any more).

The substrate according to the invention advantageously has an antifungal (fungicidal or fungistatic) effect on at least one fungus, in particular
 30 *Candida albicans* or *Aspergillus niger*.

It has been found that it is possible to deposit the mineral layer and the antimicrobial agent in one single step over the entire substrate, whether it is made of metal, e.g. steel, or is a glass-type substrate. In particular, with the classic method of magnetron sputtering, it is possible to form a layer, e.g. of a metal oxide doped with an antimicrobial agent, e.g. silver, using two metal targets in the same deposition chamber (co-sputtering) or using a sole target with mixed metal. With this process no additional or subsequent diffusion of the antimicrobial agent may be needed. We obtain a antimicrobial substrate in one step, without any thermal treatment which is cost saving.

It has also been discovered that, if a tempered and antimicrobial glass is required, the same process may be used, and optionally an underlayer may be added. Antimicrobial (in particular bactericidal but also bacteriostatic) properties may be maintained even after a tempering process (implying high temperature treatment during perhaps 5 to 10 min).

Layers of Ag doped metal oxide deposited in a single step by co-sputtering, wherein the concentration of Ag can vary from 0.1 to 5%, have been made which have antimicrobial properties with a simple process which does not require any thermal treatment.

When the substrate used is a clear glass, it can advantageously have antimicrobial properties as well as a neutral colouration in reflection. In particular, the colorimetric indexes (CIELAB system) in reflection a^* and b^* (Illuminant C, 10° observer) may be in the range of between -10 and 6, preferably between -5 and 3 and particularly preferred between -2 and 0, and the purity may be less than 15%, preferably less than 10% and particularly preferred less than 5%.

If the substrate is a coloured glass, antimicrobial properties may be obtained without changing very much the initial colour of the substrate. The change of coloration is generally expressed with the colorimetric index by ΔE^* ; $\Delta E^* = [(l^*_1 - l^*_2)^2 + (a^*_1 - a^*_2)^2 + (b^*_1 - b^*_2)^2]^{1/2}$. A ΔE^* lower than 3, preferably lower than 2 may be obtained for an antimicrobial substrate according to the invention.

When the glass substrate used is a clear glass, it may advantageously have both antimicrobial properties and a visible light absorption of less than 1.5%, preferably

less than 1.4% and particularly preferred less than 1.3%. It may have a visible light transmission within the range of 80 to 91%, preferably 84 to 90%. And the visible light reflection may be less than 15, preferably less than 12%, most preferably less than 10%.

5 The substrate according to the invention preferably has in particular an antimicrobial effect after at least one of the following accelerated ageing tests: wet spray test (test over 20 days in a chamber with a humidity of more than 95% at 40°C), after 500 hours of UV irradiation (4 340A ATLAS lamps, chamber at 60°C), after 24 hours immersed in a solution of H₂SO₄ (0.1 N), after 24 hours immersed in a solution of NaOH (0.1 N).

10 It may be advantageous to use an undercoat comprising an oxide of zirconium. This may particularly be so when the mixed layer comprises an antibacterial agent and an oxide of titanium, particularly comprising or consisting essentially of titanium oxide in its anatase crystallised form.

15 Additional or alternative embodiments of the present invention are described in dependant claims.

The present invention shall be described in more detail below, in a non-restrictive manner:

20

Example 1

Two samples of clear soda-lime glass were coated with a layer of $\text{SiO}_2(\text{Al})\text{:Ag}$ by co-sputtering. Two metal targets were used in a mixed atmosphere of argon and oxygen: one was composed of silicon doped with 8% Al and the second target was a metallic silver target. The electric power supply to the layers was regulated in order to obtain 0.5 atomic % of Ag in the layer for the first sample and 1 atomic % of Ag in the layer for the second. The layer thickness was 80 nm for the first sample and 150 nm for the second.

The bactericidal and fungicidal properties (in particular on *E. Coli*) of the samples were analysed in accordance with standard JIS Z 2801. A log 1 level indicates that 90% of the bacteria inoculated onto the surface of the glass were killed in 24 hours in the conditions of the standard; log 2 indicates that 99% of the bacteria were killed; log 3 indicates that 99.9% of the bacteria deposited were killed etc.

A value of log 4.2 was obtained for both samples of example 1.

Example 2

Two samples of clear soda-lime glass were coated with a layer of $\text{SnO}_2\text{-Ag}$ by co-sputtering using two metallic targets (Sn and Ag). The thickness of the layer is respectively 80 and 40 nm and the quantity of Ag deposited is respectively 2 and 30 mg/m². The antibacterial effect was measured in the same manner as in the previous example. Values of log 4.4 and 4.5 were obtained.

Example 3

Two samples of clear soda-lime glass were coated with a layer of $\text{ZrO}_2\text{-Ag}$ by co-sputtering using two metallic targets (Zr and Ag). The electric power supply to the layers was regulated in order to obtain 1.2 atomic % of Ag for the first sample and 3.4 atomic % of Ag for the second. The antibacterial effect was measured in the

same manner as in the previous examples. Values of log 4 were obtained for both samples.

Example 4

5 A co-sputtering of SnO₂-Ag was deposited over two different substrates. The quantity of Ag deposited amounts to 46 mg/m² of surface and the thickness of the mixed layer is 17 nm.

The first substrate is a clear soda lime glass with an double underlayer SiO_x (70 nm) and SnO₂:F (320 nm) deposited by Chemical Vapor Deposition. The
10 second substrate is a clear soda lime-glass coated with a 50nm thick SiO₂ layer deposited by vacuum sputtering. Both samples were subjected to a common tempering process (670°C during 10min follow by quick cooling).

The antibacterial effect on E. Coli, measured as in the previous examples gives values of log 1.76 and 1.38. This meant a bactericid effect were
15 between 90 and 99% of the inoculated bacteria were killed.

Example 5

A co-sputtering of SnO₂-Ag was deposited over 2 different metallic substrates. The quantity of Ag deposited amounts to 46 mg/m² of surface and the
20 thickness of the mixed layer is 17 nm.

The first substrate is a galvanized steel of the commercial type "ST37" with a thickness of 1.5 mm. The second substrate is a sample of steel laminated under cold condition and without oil of a thickness of 0.2 mm.

The antibacterial effect on E. Coli, measured as in the previous
25 examples gives values of log 3.53 for both samples.

Claims

1. Process for the production of a metallic, ceramic type, or glass type substrate having antimicrobial properties, characterised in that it consists of depositing by a sputtering under vacuum (preferably magnetically enhanced) process using metallic target, at least one mixed layer, the layer comprising from 2 to 1000 mg per m² of substrate of at least one metallic antimicrobial agent mixed with a binder material chosen amongst metal oxides, oxynitrides, oxycarbides, carbides, DLC or nitrides, in particular SiO₂, SnO₂, ZrO₂, ZnO, TiO₂, NbOx, Al₂O₃, Si₃N₄, TiN, AlN and mixture thereof.
2. Substrate obtained with a process according to the preceding claim.
3. Substrate according to the preceding claim, characterised in that it is coated with an underlayer with a function of slowing down or blocking the diffusion of antimicrobial agents.
4. Substrate according to any one of claims 2 to 3, characterised in that the antimicrobial agent is selected from silver, copper and zinc.
5. Substrate according to any one of claims 2 to 4, characterised in that the total quantity of antimicrobial agents that it comprises is more than 0.1 mg/m², preferably more than 1 mg/m² and particularly preferred more than 10 mg/m² of antimicrobial surface.
6. Substrate according to any one of claims 2 to 5, characterised in that on at least 2 one of the following bacteria: *E. coli*, *S. aureus*, *P. aeruginosa* (measured in accordance with the standard JIS Z 2801), it has a

bactericidal effect higher than log 1, preferably higher than log 2 and particularly preferred higher than log 2.5.

7. Substrate according to any one of claims 2 to 6, characterised in that the layer comprises tin oxide and an antimicrobial agent selected from silver, copper and zinc.

8. Substrate according to any one of claims 2 to 7, characterised in that it is covered with an undercoating comprising a first layer based on ZrO_2 and a second layer based on TiO_2 , in particular TiO_2 at least partially crystallised in the anatase form.

9. Substrate according to any one of Claims 1 and 6, characterised in that the substrate is a glass-type substrate.

10. Substrate according to the preceding claim, characterised in that it is able to be tempered at a later stage and in that it keeps antimicrobial properties after the treatment of tempering.

11. Substrate according to any of claim 9 to 10, characterised in that it presents annealed characteristics.

12. Process according to claim 1 for the production of a substrate having antimicrobial properties, characterised in that it consists of depositing a mixed layer of a metal oxide doped with an antimicrobial agent by sputtering.

13. Process according to the preceding claim, characterised in that two separate targets are used.

14. Process according to any one of claims 11 or 12, characterised in that the mixed layer consists of a layer of

Ag doped SiO_2 , SnO_2 , ZrO_2 , ZnO , TiO_2 , NbOx , Al_2O_3 , or mixture thereof, in particular ZnSnOx .

15. Process according to any one of Claims 12 to 14, characterised in that a layer comprising from 10 to 250 mg of antimicrobial agent per m^2 of substrate, preferably 20 to 100 mg/m^2 is deposited on the substrate.

16. Process for the production of a tempered and antimicrobial glass type substrate comprising the steps of

(i) depositing by sputtering vacuum process a mixed layer comprising from 2 to 1000 mg of at least one metallic antimicrobial agent and a binder material;

(ii) tempering the coated substrate at temperature comprised between 600 and 800°C during 5 to 15 min according to the thickness of the substrate.

17. Process according to the preceding claim, characterised in that at least one underlayer is deposited on the substrate before the deposition of step (i).

18. Process according to the preceding claim, characterised in that the underlayer has a function of blocking or slowing down the migration of the antimicrobial agent during the tempering step.

19. Process according to any one of claims 17 or 18, characterised in that the underlayer is chosen amongst pyrolitic and sputtered layers, in particular layers comprising metal oxide, metal or metal alloy compound, such as Pd, Ni-Cr, TiOx , NiCrOx , Nb, Ta, Al, Zr or ZnAl , or mixture thereof.