

- 18 -



162162

ABSTRACT



G00002

There is provided a modifier composition for a methacrylate resin, which can stably give a molded article excellent in strength without deteriorating transparency, color tone and appearance thereof under a wide range of injection molding conditions. A modifier composition for a methacrylate resin of the present invention comprises an impact modifier, a polymer processing aid and a reducing compound, wherein an amount of the impact modifier to the polymer processing aid is 95/5 to 80/20 in weight, and an amount of the reducing compound is 0.25 to 1.25 parts by weight based on 100 parts by weight of the total amount of the impact modifier and the polymer processing aid.