

Method and Device for Prefixing Substrates

Specification

This invention relates to a method for prefixing substrates and a device for prefixing substrates.

In the publications US6563133B1 and US7332410B2, the bonding of oxide-free substrate pairs at room temperature without external expenditure of force is disclosed. In this case, the substrate surfaces are modified by plasma treatment or ion implantation by the surfaces being treated with a semi-amorphous layer that consists of boron or arsenic ions. After full-surface contact is made under normal pressure, the substrate pairs remain in a light vacuum atmosphere. A binding energy of approximately 400 mJ/m^2 is achieved at room temperature. In order to create a permanent bond, an annealing step also follows at up to 400°C . The substrates are limited to semiconductors such as Si, InGaAs, GaAs, Ge, and SiC.

The publication EP2672509A1 shows a cluster system with a pretreatment unit and a bonding unit. In this case, bonding surfaces are to be produced, which allow a bonding with sufficient bonding force without high vacuum.

The publication US2006/0132544A1 describes the sticking (English: "tacking") or prefixing of a composite film that has an adhesive layer. Partial areas of the adhesive layer are heated by a laser and thus the sticking is made possible.

The publication US5686226 uses a locally applied resin adhesive for sticking (product) substrates to one another by hardening (polymerization) of the adhesive by means of UV radiation.

In particular, the transport of substrates or substrate stacks causes considerable problems in the state of the art, since the substrates, on the one hand, are not to be damaged and, on the other hand, a possible alignment of the substrates is not to be changed. In addition, the transport is to be carried out in the smallest possible space.

Embodiments of this invention disclose a method and a device with which in particular the transport of the aligned substrates is improved. In addition, the

bonding quality is to be enhanced, and less scrap is to be produced. Moreover, the flexibility is to be improved, and the cycle times are to be reduced.

According to a first aspect of the present invention, there is provided a method for prefixing substrates, whereby at least one substrate surface of the substrates is amorphized in at least one surface area, characterized in that the substrates are aligned and then make contact on the amorphized surface areas and are prefixed only at partial surfaces, wherein local application of force is used to reach equivalent pressure for spontaneous bonds in the partial surfaces and thereby to prefix the substrates.

According to a second aspect of the present invention, there is provided a device for prefixing substrates with at least one pretreatment system for pretreating at least one substrate surface of the substrates in at least one surface area, an alignment system for aligning the substrates, and a prefixing system, downstream from the alignment system, for making contact with and prefixing the aligned substrates on the pretreated, in particular amorphized, surface areas, wherein the prefixing is done only at partial surfaces, wherein local application of force is used to reach equivalent pressure for spontaneous bonds in the partial surfaces and thereby to prefix the substrates.

Also, all combinations of at least two of the features that are indicated in the specification, the claims, and/or the figures fall within the scope of the invention. In the indicated ranges of values, values as boundary values that lie within the above-mentioned limits are also to be considered as disclosed and can be claimed in any combination.

The basic idea of embodiments of this invention is substrates in which at least one substrate surface of the substrates is pretreated, in particular amorphized, in at least one surface area, to align the substrates and then to make contact and to prefix them on the pretreated surface areas. The alignment and making contact as well as prefixing are done preferably in one and the same vacuum module chamber (prefixing module) that is uninterrupted in particular during alignment and making contact.

According to an advantageous embodiment of the invention, the substrates are then bonded, in particular without interrupting the vacuum in the module chamber. In a preferred high-vacuum environment (in particular $< 10e^{-7}$ mbar, preferably $< 10e^{-8}$ mbar),

polished and/or pretreated substrate surfaces bond spontaneously and covalently by making pure contact without additional pressure (or at least only very low pressure), in particular at room temperature. Reference is made to the publication PCT/EP 2014/063303 with respect to the pretreatment.

The method according to embodiments of the invention, the device derived therefrom, and the articles produced therefrom used the effects of the pretreatment in particular to prefix substrate pairs in an adjusting system (alignment system, in particular outside of the bonding chamber), without in this case using high contact forces and/or high temperatures, as were necessary in the case of full-surface permanent bonds. Preferably, the substrates are prefixed or temporarily bonded only at a few points or partial surfaces (surface areas).

Only in a subsequent bonding step (in the bonding chamber of a bonding module) are higher forces with a uniform surface load applied. This process can be supported by an additional temperature input.

The pretreatment is carried out in particular in a pretreatment module that can be separated from the prefixing module and/or the bonding module, in particular by sluices. In the latter, an amorphized substrate surface of the substrates (semiconductor material, oxides or polished metals such as Al, Cu, glass, ceramics) is created. The substrates are activated, and a high proportion of microcontact surface contacts are made possible upon contact between two substrates. Thus, spontaneous covalent bonds can be formed at low temperatures, in particular at room temperature. Making contact is preferably carried out under high vacuum.

The prefixing is done in particular by local energy input, in particular from a side that faces away from the substrate surface with which contact is to be made.

In order to reach an equivalent pressure for spontaneous bonds in partial surfaces and to prefix (to stick or “to tack”) the substrates, in particular wafers, preferably a local application of energy, in particular force and/or heat, is carried out. The substrates are applied locally, in particular with one or more pressure dies, and are thus prefixed locally. The in particular three-axis adjusting system is preferably designed only for the resulting force of the partial application, so that the latter are less expensive and thus economical.

An in particular covalent bond (prefixing) that is strong enough to transfer the prefixed substrate pair into the bonding chamber is produced on the applied surface areas. There, pressurization over the entire surface is carried out for permanent bonding with optional heating.

The bonding strength of the prefixing is in particular so strong that the substrates retain their mutual alignment during transport.

For handling, in particular the transport from the alignment module or prefixing module to the bonding module or other processing modules, in particular a receiving system (substrate holder or chuck) on one of the two or on both holding sides (sides facing away from the substrate surfaces) of the substrate stack can be eliminated.

In a further embodiment of the invention, it is provided that at least one – and preferably all - of the substrate surfaces has/have a mean roughness index Ra that is less than 20 nm, preferably a mean roughness index Ra that is less than 1 nm. For all polished surfaces with a mean roughness index Ra of less than 20 nm (such as in particular

aluminum, copper, oxides, semiconductor materials, and glass), a prefixing by local input of force in the adjusting system is possible.

An embodiment of the method has in particular the following steps:

- 1) Introducing substrates or a pair of substrates into a high vacuum environment, in particular by a sluice, and transfer (in particular by means of a robotic arm) of at least one of the substrates into a pretreatment chamber of a pretreatment module,
- 2) Pretreatment of at least one of the substrates in such a way that the latter are suitable for spontaneous room temperature bonding,
- 3) Transfer (in particular by means of the robotic arm) to an adjusting system/alignment system/prefixing module (first module chamber),
- 4) Alignment of the two substrates to one another in the alignment system,
- 5) The two substrates making contact and local application of energy, in particular one or more local surface loads; as a result, prefixing takes place in such a way that the alignment of the substrates is fixed with respect to one another. As an alternative, it can also be prefixed over the entire surface,
- 6) Transfer (in particular by means of the robotic arm) of the prefixed substrate stack in a bonding module (second module chamber),
- 7) Partial or (preferably) full-surface application of a bonding force and optional heating for further strengthening of the connection, and
- 8) Discharging of the bonded substrates from the high-vacuum environment.

According to an embodiment of the invention, the method can optionally be repeated multiple times after step 5 in order to add additional substrates to the substrate stack before being bonded.

The method according to embodiments of the invention is preferably applied in a high-vacuum, preferably ultrahigh-vacuum, environment that can be closed by sluicing. The modules that in particular can be additionally subjected to pressure are arranged within the high-vacuum environment.

According to an embodiment of the invention, a separation of the (precision) alignment from the high input of force and optionally higher temperature taking place during bonding is carried out. Advantages in design are produced therefrom and lead to cost

savings. Even forces greater than 1 kN along a Z-axis would make a precision mechanism for adjustment in the sub- μm range along an X- and Y-axis, in particular under high vacuum, extremely expensive, if not impossible. Thus, for example, no lubricants are allowed under high vacuum, and also no air bearings. Rolling and sliding bearings produce particles or even high backlash due to friction forces. In addition, the introduction of a high force along a Z-axis creates a high risk of having a negative influence on the X-Y alignment and thus the alignment accuracy.

Another advantage is the optimal productivity. Thus, for example, in a unit, the number of prefixing systems and bonding modules can be selected in such a way that an optimal throughput for the respective process is ensured. In particular, at the required temperature input and the associated heating and cooling times, it is preferred to use multiple bonding modules with a prefixing unit.

Another advantage of embodiments of the invention is the modularity and thus retrofittability of the prefixing unit. With locally prebonded substrates, which are prefixed/stuck in an adjusting unit with prefixing, a high-vacuum unit can be retrofitted by adding a prefixing unit according to embodiments of the invention.

The mean roughness index or arithmetic mean roughness index R_a describes the roughness of a technical surface. To determine this measurement value, the surface is scanned on a defined measurement section and all height and depth differences of the rough surface are recorded. After the calculation of the specific integral of this roughness plot on the measurement section, this result is subsequently divided by the length of the measurement section. The range of the roughness value reaches 25 μm in the case of very rough surfaces with traceable grooves, up to $< 20\text{ nm}$ for polished surfaces.

Advantageous material combinations for the substrates are combinations that consist of all materials that have a polished or polishable surface, preferably with a mean roughness index R_a of less than 20 nm. The following materials or combinations of materials are preferred:

- Semiconductor materials, in particular Si, InP, GaAs, semiconductor alloys, III-V and II-IV compounds,

- Metals, in particular Cu, Al,
- Oxides, in particular SiO₂ or other oxides of semiconductor materials or semiconductor wafers with oxidized surfaces,
- Nitrides, in particular SiN_x,
- Glass,
- Glass ceramics, in particular Zerodur[®],
- Ceramic.

An embodiment of the invention is limited in particular to polished surfaces, which allow a pretreatment for covalent bonds. These are preferably surfaces with a mean roughness index Ra that is less than 20 nm, more preferably with an Ra of less than 1 nm, measured on a 2x2 μm^2 field with a scanning force microscope (English: Atomic Force Microscope, AFM). The local energy input or input of force is in particular large in order to sufficiently equalize microroughnesses so that a higher proportion of binding energies acting on surface molecules between the substrates can build up. The smaller the mean distance of the surfaces of two substrates on the atomic plane, the greater the adhesion. The adhesion accordingly depends on the roughness of the surfaces of the substrates that are to make contact.

The substrate surfaces can be pretreated by plasma treatment, whereby the microroughness of the substrate surfaces (topological structures) changes. When reaching an optimal surface roughness, maximal bonding energies can be achieved.

A further embodiment of this invention, in particular relating to the pretreatment, is disclosed in PCT/EP2014/063303, and reference is made to this disclosure. PCT/EP2014/063303 describes a method and a device for surface treatment of substrates. The basic idea of PCT/EP2014/063303 is to create a predominantly amorphized layer on a substrate surface that is to be bonded. The amorphization of the substrate surface results in a better bonding result, in particular in the case of comparatively low temperatures. A cleaning of the surface for oxide removal and an amorphization are preferably carried out simultaneously. PCT/EP2014/063303 relates in particular to a method for permanent bonding of two substrates, of which at least one, preferably two, as described below, was/were treated before the bonding. Surface areas, in particular a contact side (preferably over the entire surface) of the two or

of at least one of the two substrates, are amorphized before the bonding process. A layer that is one nanometer thick and in which the atoms of at least one of the surfaces to be bonded (contact sides) are arranged randomly is created by the amorphization. This random arrangement results in a better bonding result, in particular in the case of comparatively low temperatures. To create a bond according to embodiments of the invention, in particular a cleaning of the surfaces (at least the contact sides), is performed in particular for releasing oxides. Preferably, cleaning and amorphization are carried out simultaneously, even more preferably by the same treatment. An embodiment of the invention is the use of low-energy particles, in particular ions, whose energy is comparatively low, but is sufficient to produce the amorphization that is described according to embodiments of the invention.

The removal of oxide from the substrate surfaces is advantageous for an optimal bonding process and a substrate stack with correspondingly high bonding strength. This applies in particular for all materials in which an oxygen-containing atmosphere forms an undesirable, native oxide. This does not necessarily apply for deliberately created oxygen substrate surfaces, such as, for example, for silicon oxide. In particular, preferably at least predominantly, even more preferably exclusively, damaging, unnecessary and/or native, in particular metal, oxides are removed according to embodiments of the invention. Preferably, the above-mentioned oxides are removed as much as possible, in particular completely, before a bonding process, in order not to be embedded in the bonding boundary surfaces (contact surfaces of two substrates). Embedding of such oxides would result in mechanical destabilization and in a very low bonding strength. The removal of the oxide is carried out by physical or chemical methods. In an embodiment of the invention, the removal of the undesirable oxides is carried out with the same pretreatment system with which the pretreatment is implemented. As a result, the following:

- Oxide removal
- Surface smoothing
- Amorphization

can be performed simultaneously, in particular under optimal circumstances. In alternative embodiments of the invention, the oxide removal is not carried out

different materials, and in particular also have different thermal expansion coefficients, are reduced.

In further development in this connection, a plasma treatment for cleaning and activation of a substrate surface takes place in order to be able to bond at low temperatures, in particular if no oxygen-affine surfaces, in particular metal surfaces, are used. Monocrystalline silicon, which forms a silicon dioxide layer, is preferred, however. The silicon dioxide layer is extremely well suited for bonding.

In the state of the art, there are multiple approaches for direct bonding at lower temperatures. One approach in PCT/EP2013/064239 consists in applying a sacrificial layer, which is dissolved in substrate material during and/or after the bonding process. Another approach in PCT/EP2011/064874 describes the production of a permanent connection by phase conversions. The above-mentioned publications relate in particular to metal surfaces, which are bonded more likely via a metal bond and not via covalent bonds. In PCT/EP2014/056545, an optimized direct bonding process of silicon by surface cleaning is described. The above-mentioned methods can be combined with embodiments of this invention, and in this respect reference is made to the disclosure of the above-mentioned publications.

According to an advantageous embodiment of the invention, in particular substances or materials of the same type are to be connected to one another (bonded). The type similarity ensures that the same physical and chemical properties are present on the contact surfaces of the substrate surfaces (bond interfaces). This is in particular important for connections, across which electrical current is to be conducted, which are to have a slight tendency toward corrosion and/or the same mechanical properties. Preferred substances of the same type are:

- Copper-copper
- Aluminum-aluminum
- Tungsten-tungsten
- Silicon-silicon
- Silicon oxide-silicon oxide.

Another embodiment of this invention consists in particular of using the capability of different materials, in particular metals and/or oxides, to connect under external influences, in particular temperature and/or pressure, in order to obtain a local, in particular locally greatly limited, prefixing between the substrates. This is also referred to as "tacking." The method according to embodiments of the invention is preferably used for substrates with amorphized layers. The amorphized layer can in this case be applied by chemical and/or physical deposition processes on the substrate surface or be created directly on the substrate surface. An embodiment of the invention consists in that the amorphized layer is not created by a material that is applied by means of physical and/or chemical processes but rather by a phase conversion of the substrate material. As a result, the deposition of a material that is in particular undesirable or harmful can be completely eliminated.

Below, further embodiments of the method steps of the invention are disclosed:

Pretreatment of the Substrate Surfaces

Embodiments of the invention relate to a method for tacking at least two substrates, of which at least one, preferably two, were treated as described below before the tacking.

Surface areas, in particular a contact side (preferably over the entire surface) of the two substrates or of at least one of the two substrates, are amorphized before the bonding process. According to embodiments of the invention, the amorphization of surface areas that are in particular separated from one another and that are smaller than the substrate surface can also be carried out.

A layer that is a few nanometers thick, in which the atoms are arranged randomly, is created by the amorphization. The random arrangement leads to a better bonding result, in particular in the case of comparatively low temperatures.

To create a bond and/or prefixing according to embodiments of the invention, in particular a cleaning of the substrate surfaces (at least the contact sides), in particular for releasing oxides, is performed. Preferably, cleaning and amorphization are carried out simultaneously, even more preferably by the same treatment.

Another embodiment of the invention is the use of low-energy particles, in particular ions, whose energy is set when striking against the substrate surface in order to produce the amorphization described according to embodiments of the invention.

A step for removing an oxide from the substrate surfaces is preferably performed. This applies in particular for materials in which an oxygen-containing atmosphere forms a native oxide, but not for oxygen substrate surfaces that are created according to embodiments of the invention, such as in particular for silicon oxide. In particular, oxides according to embodiments of the invention - preferably at least predominantly, even more preferably exclusively, harmful, unnecessary and/or native, in particular metal oxides - are removed. Preferably, the above-mentioned oxides are removed to a very large extent, in particular completely, before a bonding process in order not to be embedded in the bonding boundary surface (contact surface of two substrates). An embedding of such oxides would lead to a mechanical destabilization and to a very low bonding strength. The removal of the oxide is carried out in particular by physical or chemical methods. In an embodiment of the invention, the removal of the undesirable oxides is carried out with the same pretreatment module, with which the pretreatment of the substrates is performed. As a result, the following can be performed simultaneously, in particular under optimal circumstances: oxide removal, surface smoothing, and/or amorphization. In alternative embodiments of the invention, the oxide removal is not carried out in the same unit. In this case, it must be ensured in particular that no renewed oxidation of the substrate surfaces occurs during transfer of the substrates between the two units. This can be ensured in that the high vacuum during the oxide removal, the transport, and the pretreatment occurring until bonding is completed is not interrupted.

In other words, the idea according to embodiments of the invention consists in particular in the efficient, in particular locally limited, prefixing by increasing the bonding strength between two substrate surfaces by amorphization. In this case, the amorphization solves multiple problems:

The amorphization according to embodiments of the invention in particular produces a planarization of the substrate surface. The planarization thus takes place in particular during the amorphization, in particular in addition to a planarization that is provided during the bonding process by the application of force.

In addition, the amorphization ensures a higher movability of the material on the interfaces. As a result, any possible residual roughness can be better compensated for. In particular, remaining gaps between the substrate surfaces can be closed.

In particular, a thermodynamically metastable state at the substrate surface (bonding boundary surface) is created by the amorphization.

In another process step (in particular after the surfaces to be bonded make contact), this metastable state results in a (back) conversion of partial areas of the amorphous layer into a crystalline state. In the ideal case, a complete conversion of the amorphous layer is carried out. The resulting layer thickness after making contact and the subsequent heat treatment of the amorphous layer are in particular greater than zero.

Another idea according to embodiments of the invention consists in particular in the creation of the amorphous layer that consists of the existing basic material of the substrate, in particular by particle bombardment. Preferably, before the bonding of the substrates, no material is applied to the substrate surfaces that are to be brought together. Since the prefixing of the substrates is preferably carried out only at a few points, another idea according to embodiments of the invention consists in performing the amorphization only at the points provided for the prefixing. If the substrates that are prefixed by tacking according to embodiments of the invention are completely bonded in a subsequent process step, a complete amorphization is preferred.

The method according to embodiments of the invention makes possible in particular the production of a complete and/or local and/or full-surface, in particular mixed, contact of two substrate surfaces, of which at least one, preferably two, is/are amorphized according to embodiments of the invention.

The method according to embodiments of the invention is used in particular for the production of a contact that is complete and/or full-surface and/or unmixed of two, preferably different substrate surfaces.

In particular, the following materials can be prefixed with one another in any combination, preferably in each case the same materials:

- Metals, in particular Cu, Ag, Au, Al, Fe, Ni, Co, Pt, W, Cr, Pb, Ti, Te, Sn, and/or Zn,
- Alloys
- Semiconductors (with corresponding doping), in particular

- Element semiconductors, preferably Si, Ge, Se, Te, B, and/or α -Sn,
- Compound semiconductors, in particular GaAs, GaN, InP, $\text{In}_x\text{Ga}_{1-x}\text{N}$, InSb, InAs, GaSb, AlN, InN, GaP, BeTe, ZnO, CuInGaSe_2 , ZnS, ZnSe, ZnTe, CdS, CdSe, CdTe, $\text{Hg}(1-x)\text{Cd}(x)\text{Te}$, BeSe, HgS, $\text{Al}_x\text{Ga}_{1-x}\text{As}$, GaS, GaSe, GaTe, InS, InSe, InTe, CuInSe_2 , CuInS_2 , CuInGaS_2 , SiC, and/or SiGe,
- Organic semiconductors, in particular flavanthrone, perinone, Alq3, perinone, tetracene, quinacridone, pentacene, phthalocyanines, polythiophenes, PTCDA, MePTCDI, acridone, and/or indanthrone.

In other words, embodiments of the invention relate to a method for, in particular locally limited, direct bonding. In this case, an embodiment of the invention is preferably based on the idea of amorphizing at least one surface (arranged in particular on the contact side) or a partial area of the surface of a substrate before the bonding process or the prefixing. The amorphization is preferably carried out not by the deposition of a material that is amorphously resublimated or condensed under the given deposition parameters at the substrate surface but rather in particular by an alteration, primary forming and/or phase conversion of an amorphous layer at the substrate surface. This is done in particular by the introduction of kinetic energy by particle bombardment, in particular ion bombardment, most preferably by a low-energy ion bombardment.

An at least partially amorphous structure of the formed amorphous layer is defined in particular as a phase batch, which consists at least of one amorphous phase and one crystalline phase.

The volume ratio between the amorphous phase and the total volume is to be referred to as the degree of amorphization. According to embodiments of the invention, the degree of amorphization is in particular greater than 10%, preferably greater than 25%, even more preferably greater than 50%, most preferably greater than 75%, and all the more preferably greater than 99%.

The amorphization is limited in particular to the area that is near the surface of the substrates that are to be bonded to one another, preferably by selection of the process parameters temperature, pressure, ionization energy and/or ion current density during the

amorphization. In particular, the material of the substrate, in this case apart from the amorphized layer according to embodiments of the invention, remains at least predominantly, preferably completely, crystalline. In a first embodiment of the invention, only the substrate surface or a part of the substrate surface of a first substrate is amorphized. The thickness d of the amorphous layer immediately after the creation according to embodiments of the invention in a substrate surface is in particular less than 100 nm, preferably less than 50 nm, even more preferably less than 10 nm, most preferably less than 5 nm, and all the more preferably less than 2 nm.

In accordance with a further embodiment of the invention, the substrate surface of a first substrate and the substrate surface of a second substrate or partial areas of the substrate surfaces are amorphized. In another embodiment of the invention, the amorphization of two substrate surfaces is carried out in the same unit, in particular simultaneously, in order to create the same amorphous layers with the same process parameters. The amorphous layers that are created preferably have the same thickness d_1 of the first amorphous layer of the first substrate and d_2 of the second amorphous layer of the second substrate. The ratio of the thicknesses d_1/d_2 of the two amorphous layers, in particular created simultaneously, is $0.6 < d_1/d_2 < 1.4$, preferably $0.7 < d_1/d_2 < 1.3$, even more preferably $0.8 < d_1/d_2 < 1.2$, most preferably $0.9 < d_1/d_2 < 1.1$, and all the more preferably $0.99 < d_1/d_2 < 1.01$.

The substrate surfaces or the partial areas of the substrate surfaces that are treated according to embodiments of the invention have a slight, but in particular not insignificant, roughness before, during, and after the amorphization. In a preferred embodiment, the roughness of the substrate surface or of the partial areas of the substrate surface that are treated according to embodiments of the invention during the amorphization is reduced and has a minimum after the amorphization. The roughness is indicated either as a mean roughness, quadratic roughness, or as an averaged depth of roughness. The determined values for the mean roughness, the quadratic roughness, and the averaged depth of roughness are different in general for the same measurement section or measurement surface, but lie in the same range of order of magnitude. A measurement of the surface roughness is done with one of the measuring devices (known to one skilled in the art), in particular with a profilometer and/or an atomic force microscope (AFM). In this case, the measuring surface is in

particular $2\text{ }\mu\text{m} \times 2\text{ }\mu\text{m}$. Therefore, the following numerical value ranges for the roughness are defined either as values for the mean roughness, the quadratic roughness, or for the averaged depth of roughness. The roughness of the substrate surface or of the partial areas of the substrate surface that are treated according to embodiments of the invention before the amorphization is in particular, according to embodiments of the invention, less than 20 nm, preferably less than 10 nm, even more preferably less than 8 nm, most preferably less than 4 nm, and all the more preferably less than 1 nm. The roughness of the substrate surface or of the partial areas of the substrate surface that are treated according to embodiments of the invention after the amorphization is in particular less than 10 nm, preferably less than 8 nm, even more preferably less than 6 nm, most preferably less than 4 nm, and all the more preferably less than 1 nm.

The ratio between the entire surface F of the substrate and the cleaned and/or amorphized surface f is referred to as a degree of purity r . Before the bonding process according to embodiments of the invention, the degree of purity is in particular greater than 0, preferably greater than 0.001, even more preferably greater than 0.01, most preferably greater than 0.1, and all the more preferably 1. The degree of purity r also corresponds in particular to the ratio between the surface of the tacked partial areas f' and the surface of the entire surface F .

The cleaning and/or amorphization preferably take place in the pretreatment module that is designed preferably as a vacuum chamber. The vacuum chamber can be evacuated to be in particular less than 1 bar, preferably less than 1 mbar, even more preferably less than 10^{-3} mbar, most preferably less than 10^{-5} mbar, and all the more preferably less than 10^{-8} mbar. In particular before the ions are used for amorphization, the vacuum chamber is evacuated preferably to a pre-established pressure, and is even more preferably completely evacuated. In particular, the proportion of oxygen and in particular also the proportion of moisture (water content) in the process chamber are greatly reduced so that a renewed oxidation of the substrate surfaces is not possible.

The ionization process is described in particular in PCT/EP2014/063303, to which reference is made in this respect. The exact selection of the angle of incidence makes possible the control of the removal rate and thus the surface roughness. The angle of incidence is selected in particular so that amorphization, removal of contaminants, in

particular oxides, and surface smoothing are maximized for the target result. Maximization is defined in particular as a complete removal of contaminants, in particular oxides, a still further, in particular complete, smoothing of the surface (i.e., a reduction of the roughness value to zero), as well as an optimal amorphized layer. Gases or gas mixtures and parameters such as kinetic energy of particles, angle of incidence of the ion beam, current density, and treatment time were described in PCT/EP2014/063303.

Alignment/Adjustment and Prefixing/Tacking

After the pretreatment (amorphization and/or cleaning) of at least one of the two substrate surfaces, in particular an alignment of the two substrates to one another is carried out in an alignment module. Preferably, the alignment is carried out by adjusting or aligning units (English: aligner), in particular based on alignment marks on the substrates. The moment that the substrates are laid down/make contact is especially critical since alignment errors add up and/or can no longer be easily corrected. This results in considerable scrap. According to embodiments of the invention, in particular an adjustment accuracy or an offset of less than 100 μm is thus the goal, in particular less than 10 μm , preferably less than 1 μm , with utmost preference less than 100 nm, and most preferably less than 10 nm.

The tacking is carried out in particular in the same module, i.e., in the alignment module, in which also the alignment of the respective substrates takes place/took place. In an alternative embodiment, the tacking can also take place in a separate prefixing module. The tacking is performed by means of a prefixing unit, which is suitable to connect two substrates at least locally to one another. Preferably, the entire surface or preferably one (or more) partial surface(s) is/are subjected to a preset (low) force and/or an energy input for prefixing. Then, a bonding strength that is sufficient for the prefixing is produced therefrom. Preferably, because of the prefixing, a full bonding strength between the substrates is not achieved. The bonding strength is preferably set in such a way that the substrates are fixed during transport.

According to a first embodiment, only a partial surface of a substrate makes contact with the second substrate. This is in particular by local application of a force in order to achieve the equivalent pressure for spontaneous bonds in partial surfaces for

prefixing substrates. Spontaneous bonding is dependent on the surface type (material, roughness, etc.) and on the surface pretreatment (polishing, chemical cleaning, etc.). Bonding is referred to as spontaneous when the bonding wave propagates without external action (such as, e.g., pressure), i.e., on its own. Thus, the alignment is fixed with the prescribed alignment accuracy, without in this case using the disadvantageously necessary high contact forces or temperature for full-surface bonding.

In a second embodiment, it is tacked over the entire surface, and a corresponding bond is produced by still lower bonding force relative to the entire substrate surface. The bonding strength is sufficient in particular to fix the substrates during transport. In this case, it applies in principle that the bonding strength is a function of roughness, degree of amorphization, and thickness of the amorphous layer as well as the applied force.

In an embodiment of the invention, the prefixing unit is a device that is able to apply heat locally, in particular in a pulsed manner, on the contact surface. To create heat, in particular electric fields, magnetic fields, or electromagnetic radiation, preferably lasers, can be used.

In a further embodiment of the invention, the prefixing unit is designed as an electrode. The electrode is capacitively coupled via the two substrates that are to be connected to one another with a counter electrode, in particular a plate or part of a corresponding specimen holder. The electrode preferably has an electrode tip that is as pointed as possible in order to increase the electric field strength. The electric field strength is in particular greater than 0.01 V/m, preferably greater than 1 V/m, even more preferably greater than 100 V/m, most preferably greater than 10,000 V/m, and all the more preferably greater than 1 MV/m. In a quite especially preferred embodiment, the electrodes are loaded with an a.c. voltage. The frequency of the a.c. voltage is in particular greater than 10 Hz, preferably greater than 1,000 Hz, even more preferably greater than 100,000 Hz, and most preferably greater than 10 MHz. The a.c. voltage is suitable in particular for point tacking according to embodiments of the invention when the substrates consist, in particular predominantly, of dielectric material, which represents a barrier for the current flux of a d.c. voltage. In the case of at least partially present metal layers, a heating by the so-called "skin effect" is carried out by the use of a.c. voltage according to embodiments of the invention.

In an alternative further development, the prefixing unit is designed as a unit for generating electromagnetic radiation, preferably as lasers. The laser has in particular a wavelength that ensures an optimal heating at least of a material in the substrate stack. The wavelength preferably lies in a range of between 1 nm and 1 mm, even more preferably between 200 nm and 1 mm, even more preferably between 400 nm and 1 mm, most preferably between 600 nm and 1 mm, and all the more preferably between 800 nm and 1 mm. The laser is therefore preferably an infrared laser. The diameter of the laser beam is in particular less than 10 mm, preferably less than 5 mm, even more preferably less than 2 mm, most preferably less than 1 mm, and all the more preferably less than 0.5 mm. The laser output is in particular greater than 10 W, preferably greater than 100 W, even more preferably greater than 1,000 W, and most preferably greater than 0.01 MW.

In another alternative embodiment, the prefixing unit has a microwave source, in particular an amplifron, magnetron, stablotron, carcinotron or klystron. The microwaves of the microwave source are directed, in particular focused, by optical elements, in particular waveguides, even more preferably hollow waveguides, onto the points on the substrates that are to be tacked, preferably without striking the points of the substrates that are not to be tacked. The use of microwave sources is especially preferred when the substrate surfaces are wetted with a residual moisture, in particular a monoatomic layer of water. Owing to the specific, local irradiation with microwaves, the substrate surfaces are greatly heated by means of the water, so that a permanent connection of the substrate surfaces, in particular silicon and/or silicon dioxide surfaces, is produced by oxygen bridges. The diameter of the microwave beam focused by waveguides, in particular hollow waveguides, is in particular less than 10 mm, preferably less than 5 mm, even more preferably less than 2 mm, most preferably less than 1 mm, and all the more preferably less than 0.5 mm. The microwave source output is preferably greater than 10 W, preferably greater than 100 W, even more preferably greater than 1,000 W, and most preferably greater than 0.01 MW.

In another embodiment of the invention, the prefixing unit is designed as a pressure device, which is designed to impose one or more local surface loads onto the substrates. The surface load is introduced in particular by a pressure die. A pressure surface of the pressure die on a pressure side of the substrate that faces away from the

Preferably, the pressure dies are arranged uniformly distributed on the substrates.

When multiple pressure dies are used, the latter can be subjected to force sequentially individually or in groups in order to minimize the load for the substrate holders.

In an embodiment of the invention, the prefixing module has specifically a prefixing unit, which is suitable for exerting an in particular mechanical pressure on the surface of the substrate stack, in particular on the surface of the product substrate. The prefixing unit can be a point force-application unit according to embodiments of the invention. The point force-application unit is preferably created in the shape of a pin. The tip of the pin can have different shapes. Thus, pointed tapering shapes, rounded, in particular spherical, shapes, or rectangular shapes are conceivable. The tacking uses local application of force in order to reach the equivalent pressure for spontaneous bonds in partial surfaces and thus to prefix or to tack the substrates.

In a further embodiment of the invention, the prefixing unit is in addition heatable. The temperature of the prefixing unit can be regulated in particular with an accuracy of better than 5°C, preferably better than 2°C, even more preferably better than 1°C, most preferably better than 0.1°C, and all the more preferably better than 0.01°C. The controllable temperature range of the prefixing unit lies in particular between room temperature and 700°C, preferably between room temperature and 300°C, even more preferably between room temperature and 120°C, most preferably between 18°C and 30°C, and all the more preferably at room temperature. The introduction of heat primarily leads to a (locally limited) heating.

In another embodiment of the invention, the point force-application unit has a laser that can be focused in particular as exactly as possible. The coherent laser light is bundled by optics, preferably in a focus that is located between the product substrate and the carrier substrate, i.e., in the connecting layer. As a result, an intensive and quick heating of the connecting layer that is as locally limited as possible is produced. The laser is preferably pulsed, in particular by continuous, preferably high-frequency, switching on and off. By such a pulsing, the heating of the environment is avoided to a large extent or completely. The laser is in particular an infrared laser, a laser for visible light, or a laser for UV light.

In an especially preferred embodiment, the prefixing unit combines a heating unit and/or pressure unit and/or laser unit, so that at the same time, thermal and/or mechanical and/or photochemical stresses are possible. According to a preferred embodiment of the invention, the prefixing unit can be moved at least along the z-axis in any embodiment.

According to another embodiment of the invention, it is conceivable to tack to the full surface and to produce a corresponding bond by a force that is smaller but corresponds to the entire substrate surface. This embodiment involves the prefixing unit, preferably a pressure device that can apply a surface load on the full surface with a pressure plate. The prebond that is produced is distinguished in particular by a bond strength of between 0.01 J/m^2 and 5 J/m^2 , preferably greater than 0.1 J/m^2 , preferably greater than 0.2 J/m^2 , even more preferably greater than 0.5 J/m^2 , most preferably greater than 1 J/m^2 , and with utmost preference greater than 1.5 J/m^2 .

An embodiment of the invention is preferably applied in the case of polished substrate surfaces, which make possible a pretreatment for covalent bonds. These are typically substrate surfaces with a mean roughness index Ra that is less than 20 nm, preferably with an Ra of less than 10 nm, even more preferably with an Ra of less than 2 nm, and most preferably with an Ra of less than 1 nm measured on a $2 \times 2 \text{ } \mu\text{m}^2$ field with AFM. The mean roughness index or arithmetic mean roughness index Ra describes the roughness of a technical surface. To determine this measured value, the surface is scanned on a defined measurement section and all differences in height and depth of the rough surface are recorded. After the calculation of the specific integral of this roughness plot on the measurement section, this result is ultimately divided by the length of the measurement section.

The local input of force is carried out in particular in such a way that the microroughness of the substrate surfaces is overcome, and as high a proportion of surface molecules of the opposite substrates as possible builds up binding energies. In particular, polished substrate surfaces that consist of metals, such as aluminum, copper, oxides, semiconductor materials and glass, are suitable for a prefixing by local input of force. For many types of bonds, such as in particular glass-frit bonding or eutectic bonding or in the case of unpolished metal surfaces or solder joints, the surface quality is not sufficient to generate a spontaneous partial-surface connection with the disclosed force ranges. In

these cases, preferably in addition mechanical clamping of the substrate stack is done after the alignment and after contact is made. This is achieved in particular by clamping according to PCT/EP2013/056620.

In another embodiment of the invention, it is conceivable not to use any polished substrate surfaces and/or to allow the pretreatment to be omitted, in particular when the substrates are equipped with spontaneously bonding structures. This is the case in particular when the substrates have surface structures that are similar to a Velcro closure. By contact, elastic or else plastic deformation of the surface structures is produced, and it results in a connection by friction of the substrate surfaces on the microscopic plane. In the bonding step below, the prefixing can be expanded on the entire surface and stabilized with use of high full-surface force and temperature.

Bonding

The bonding is done in particular in a separate bonding chamber, whereby the bonding chamber, preferably in a cluster unit, is connected integrally to the process chamber for pretreatment, in particular amorphization, and even more preferably, with a steadily maintained evacuation, can be moved from the process chamber into the bonding chamber.

In another step according to an embodiment of the invention, the bonding process of the prefixed/tacked substrate stack for forming a permanent bond is carried out. The bonding process consists in particular of the action of a force and/or temperature. The bonding temperature according to embodiments of the invention is in particular less than 1,100°C, preferably less than 400°C, even more preferably less than 200°C, most preferably between 18°C and 200°C, and all the more preferably room temperature. In this case, the bonding force lies in particular between 0.5 and 500 kN, preferably between 0.5 and 250 kN, more preferably between 0.5 and 200 kN, and most preferably between 1 and 100 kN. The corresponding pressure areas are produced by standardizing the bonding force according to embodiments of the invention on the surface of the substrates. The target bonding strength for the full-surface bond is preferably greater than 1 J/m², preferably greater than 1.5 J/m², and more preferably greater than 2 J/m². The substrates can have any shape. In particular, the substrates are round and are characterized across the diameter according to the industry

standard. For substrates, in particular the so-called wafers, the industry-standard diameters of 1 inch, 2 inches, 3 inches, 4 inches, 5 inches, 6 inches, 8 inches, 12 inches and 18 inches preferably apply. In principle, however, with the method according to embodiments of the invention, any substrate, in particular a semiconductor substrate, can be processed independently of its diameter.

According to embodiments of the invention, pressurization causes the substrate surfaces to approach each other additionally in the boundary layer (formed along the contact surface of the substrate surfaces) at which no contact is yet made by the prebonding. The bringing of the substrate surfaces closer and closer together results in a continuous reduction and an ultimate closure of cavities. According to embodiments of the invention, in this case, the amorphization plays a decisive role, since a surface-isotropic electrostatic attraction is created by the amorphous state. Since the amorphous layers of the substrate surfaces that make contact with one another are both not crystalline, it is also not necessary to take into account a suitable contact that continues onto the crystal lattice. The contact between two substrate surfaces with amorphous layers thus results in creating a new, larger, amorphous layer. The transition is configured in a flowing manner and is characterized according to embodiments of the invention in particular by the complete disappearance of a boundary layer.

The thickness of the entire finish-bonded amorphous layer of the substrate stack, in particular immediately after the bonding process, is in particular less than 100 nm, preferably less than 50 nm, even more preferably less than 10 nm, most preferably less than 5 nm, and all the more preferably less than 2 nm. The bonding strength is influenced in particular by the following parameters; namely

- The thickness of the amorphous layer,
- The roughness,
- The number of ions that are present in the boundary layer and that have a negative effect, and
- The bonding force.

The bonding strength in particular increases with increasing thickness of the amorphous layer. The thicker the amorphous layer, the larger the number of randomly arranged atoms. The randomly arranged atoms are not subject to any long-range and/or

short-range parameters, and cavities are filled to the boundary layer by the above-mentioned processes, in particular diffusion and/or bringing together by pressurization. In this connection, the contact surface and thus the bonding strength are increased. The mean thickness of the amorphous layer is preferably greater than the mean roughness, so that sufficient atoms of the amorphous phase are available in order to close the cavities. Preferably, a substrate surface with a very slight roughness is selected, so that the latter has cavities that are as small as possible. That is to say, the slighter the roughness of a substrate surface, the smaller the thickness of the amorphous layer can also be in order to obtain a target bonding result. A correspondingly thick amorphous layer is achieved according to embodiments of the invention by a correspondingly high ionization energy, which results in that the ions can penetrate as deeply as possible into the substrate.

The bonding strength is also a function of the purity of the amorphous layer. Any embedded undesirable atom or ion can lead in particular to destabilization, in particular reduction of the bonding strength. The ions that are used for amorphization can therefore also have a negative influence on the bonding strength, in particular if they remain in the amorphous layer after the amorphization. Therefore, in addition to correspondingly low ionization energy, a lowest possible current density and treatment time are also desired. If the current intensity is multiplied by the treatment time, the ions that strike the substrate surface within the treatment time per unit surface section are obtained. In order to minimize this number, the current density and/or the treatment time can be reduced. The fewer ions per unit surface strike the substrate surface, the fewer ions are implanted in the amorphous layer. Primarily the particles that cannot enter into any bond with the material to be amorphized can have negative effects on the bonding strength and are present only as defects, in particular point defects. These primarily include the noble gases, but also molecular gases. In particular, according to embodiments of the invention, the use of gases or gas mixtures, whose ions are responsible for a reinforcement of the bonding interface, in particular by forming new phases, is conceivable. A preferred option is the use of ionized nitrogen, which nitrates the amorphous layer.

Analogous considerations apply for all other types of elements that participate in a connection, in particular a metal, covalent or ionic bond with the material of the amorphous layer. In order to be able to reduce the current density, in particular substrate

surfaces that already have a minimal roughness are preferred. The smoother the substrate surface, the fewer and lower-energy ions are required according to the invention for the reduction of roughness. As a result, a reduction of the ionization energy and/or the ion stream and thus the number of ions per unit surface is made possible, which in turn leads to a lower number of incorporated ions and consequently to fewer defects and ultimately to an increased bonding strength.

Bonding strength is a function of bonding force, since a higher bonding force leads to bringing the substrate surfaces closer together and thus to a better contact surface. The higher the bonding force, the more easily the substrate surfaces are brought toward one another, and the cavities are thus closed by locally deformed areas.

A heat treatment, which is separate in particular from the amorphization process, is carried out in particular either during and/or after the bonding occurs in the bonder or after the bonding occurs in an external heat treatment module (in particular integrated into the cluster). The heat treatment module can be a hot plate, a heating tower, a furnace, in particular a continuous furnace, or any other type of heat-generating device. The heat treatment takes place in particular at temperatures of less than 500°C, preferably less than 400°C, even more preferably less than 300°C, most preferably less than 200°C, and all the more preferably less than 100°C, but above room temperature. The time period of the heat treatment is selected in particular in such a way that after the heat treatment, the thickness of the amorphous residual layer according to the invention is less than 50 nm, preferably less than 25 nm, even more preferably less than 15 nm, most preferably less than 10 nm, and all the more preferably less than 5 nm.

In particular, during and/or after bonding and/or in the case of heat treatment, a phase conversion from the amorphous state into the crystalline state is carried out. In a quite preferred embodiment according to embodiments of the invention, the above-mentioned process parameters are selected in such a way that a complete conversion of the amorphous layer into the crystalline phase is carried out.

According to an advantageous embodiment, a material with a purity of the material to be converted is selected in percent by mass (m%) in particular to be greater than 95 m%, preferably greater than 99 m%, even more preferably greater than 99.9 m%, most preferably greater than 99.99 m%, and all the more preferably greater than

99.999 m%. Because of the high purity of the substrate material, an even better bonding result is achieved.

Finally, the bonded substrates are discharged from the high vacuum. This can be carried out, for example, via a sluice gate, in particular a “gate valve.”

With the method and device according to embodiments of the invention, very high bonding strengths ($> 2 \text{ J/m}^2$) can be achieved at room temperature. In this case, devices with or without precision adjustment (without an adjustment unit) can be used. The pretreatment module preferably creates an amorphized surface of the substrates (for example, semiconductor material, oxides or polished metals, such as Al, Cu, glass, ceramics). The substrates are in particular activated, and a higher proportion of microcontact surface contacts is made possible upon contact between two substrates. Thus, spontaneous covalent bonds can be formed at low temperatures, also at room temperature. These spontaneous bonds are promoted by making contact under high vacuum, preferably under ultrahigh vacuum ($< 1 \text{ E}^{-6}$, better $< 1 \text{ E}^{-7}$ mbar).

Additional advantages, features, and details of the invention follow from the description below of embodiments that are preferred and based on the drawings. The latter show in:

- Figure 1 a diagrammatic depiction of an embodiment of the device according to the invention, suitable for performing a method according to the invention, in a view from above,
- Figure 2 a lateral partial view of the embodiment of Figure 1 with an alignment module F and a bonding station G with in each case a transfer chamber B in between,
- Figure 3a an overview of a first substrate of a substrate stack in a diagrammatically-indicated prefixed state,
- Figure 3b an overview of the first substrate of Figure 3a in a bonded state,
- Figure 4 a lateral view of a substrate stack with an enlargement cutaway,
- Figure 5a an overview of a substrate stack with a hatched prefixing area, and
- Figure 5b an overview of a bonded substrate stack.

In the figures, features that are the same or that have the same effect are identified with the same reference numbers.