

DESCRIPTION

GLASS SUBSTRATE FOR INFORMATION RECORDING MEDIUM AND MAGNETIC DISK

5

TECHNICAL FIELD

The present invention relates to a glass substrate to be used for an information recording medium such as a magnetic disk (hard disk), and a magnetic disk.

10 BACKGROUND ART

As substrates for information recording media, particularly for magnetic disks, glass substrates are widely used, and, for example, a glass containing, as represented by mass%, from 47 to 60% of SiO_2 , from 8 to 20% of Al_2O_3 , from 2 to 8% of Na_2O , from 1 to 15% of K_2O , from 1 to 6% of TiO_2 and from 1 to 5% of ZrO_2 has been proposed.

15 Patent Document 1: WO08/117758

DISCLOSURE OF THE INVENTION

PROBLEMS TO BE SOLVED BY THE INVENTION

20 A glass substrate for a magnetic disk is required to have an appropriate expansion coefficient and Young's modulus, and further, it is required that its surface property does not significantly change during storage to prevent films formed on the substrate, such as a base film, a magnetic film and a protective film, from being likely to be peeled, i.e., it is required to have weather resistance.

25 An object of the present invention is to provide a glass substrate for a magnetic disk having improved weather resistance.

MEANS TO SOLVE THE PROBLEMS

30 The present invention provides a glass substrate for an information recording medium, which is made of an alkali aluminosilicate glass, wherein the difference obtained by subtracting the glass transition temperature T_g from the fictive temperature T_f , i.e. $T_f - T_g$, is at most 5°C .

Further, the present invention provides the glass substrate for an information

recording medium, wherein the alkali aluminosilicate glass has an alkali metal oxide content of from 15 to 26 mol%.

Further, the present invention provides the glass substrate for an information recording medium, which comprises, as represented by mol% based on the following oxides, from 64 to 67% of SiO_2 , from 8 to 10% of Al_2O_3 , from 10 to 13% of Li_2O , from 9 to 12% of Na_2O , from 0 to 2% of K_2O and from 2 to 4% of ZrO_2 , provided that the total content of Li_2O , Na_2O and K_2O , i.e. $\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$, is from 21 to 25%. For example, "comprises . . . from 0 to 2% of K_2O " means that K_2O is not essential but may be contained in an amount of at most 2%.

Further, the present invention provides a magnetic disk having a magnetic recording layer formed on such a glass substrate for an information recording medium.

The weather resistance of a glass substrate for an information recording medium depends mainly on its glass composition, but the present inventors have found that the weather resistance can be improved by a decrease in the fictive temperature even with the same glass composition, and they have thus arrived at the present invention.

EFFECTS OF THE INVENTION

According to the present invention, a glass for an information recording medium substrate, which is excellent in weather resistance can be obtained. And, films formed on the substrate, such as a base film, a magnetic film and a protective film, are thereby made hardly likely to be peeled.

BEST MODE FOR CARRYING OUT THE INVENTION

The density d of the glass (hereinafter referred to as the glass of the present invention) of the glass substrate for an information recording medium of the present invention (hereinafter referred to as the glass substrate of the present invention) is preferably at most 2.60 g/cm^3 . If it exceeds 2.60 g/cm^3 , a load is applied to a motor during rotation of a drive, and thus it is possible that the power consumption is increased or rotation of the drive becomes unstable. It is preferably at most 2.54 g/cm^3 .

The glass of the present invention preferably has a Young's modulus E of at least 76 GPa. If it is less than 76 GPa, warpage or deflection is likely to occur during rotation of the drive, and it may possibly become difficult to obtain an information

recording medium having a high recording density. E is more preferably at least 77 GPa.

The glass of the present invention preferably has a specific modulus E/d of at least 28 MNm/kg. If E/d is less than 28 MNm/kg, warpage or deflection is likely to occur, and it may possibly be difficult to obtain an information recording medium having a high recording density. E/d is more preferably at least 30 MNm/kg.

The glass of the present invention preferably has a glass transition point T_g of at least 450°C. If it is less than 450°C, the magnetic layer forming-heat processing temperature cannot be made sufficiently high, and it may possibly be difficult to increase the coercive force of the magnetic layer. It is more preferably at least 460°C.

The glass of the present invention preferably has an average linear expansion coefficient α of at least $56 \times 10^{-7}/^\circ\text{C}$ within a range of from -50 to 70°C. If it is less than $56 \times 10^{-7}/^\circ\text{C}$, the difference from the thermal expansion coefficient of another component such as a drive made from a metal becomes large, and thus a substrate may possibly be easily broken due to generation of a stress at the time of a temperature change. It is more preferably at least $58 \times 10^{-7}/^\circ\text{C}$. α is typically at most $100 \times 10^{-7}/^\circ\text{C}$.

Next, the glass of the present invention will be described using a content represented by mole percentage.

The glass of the present invention is an alkali aluminosilicate glass, and typically, it has a SiO_2 content of from 61 to 71%, an Al_2O_3 content of from 7 to 17% and an alkali metal oxide content of from 15 to 26%.

If SiO_2 is less than 61%, the acid resistance will be decreased, d will become large, or the liquid phase temperature will be raised, and the glass will become unstable. If it exceeds 71%, temperature T_2 where the viscosity becomes 10^2 dPa·s and temperature T_4 where the viscosity becomes 10^4 dPa·s will be raised, and melting and forming of the glass will be difficult, E or E/d will be decreased, or α will become small.

If Al_2O_3 is less than 7%, the weather resistance will be decreased, E or E/d will be decreased, or T_g will be lowered. If it exceeds 17%, the acid resistance will be decreased, T_2 and T_4 will be raised, and thus melting and forming of the glass will be difficult, α will become small, or the liquid phase temperature will be too high.

As the alkali metal oxide, Li_2O , Na_2O or K_2O is common, but if the total content of alkali metal oxides is less than 15%, α will become small, or melting performance of

the glass will be declined. If it exceeds 26%, the weather resistance will be decreased.

It is preferred that Li_2O is from 6 to 16%, Na_2O is from 2 to 13%, and K_2O is from 0 to 8%.

If Li_2O is less than 6%, it may be possible that α becomes small, or melting performance of the glass will be declined. If it exceeds 16%, the weather resistance or T_g may possibly be decreased.

If Na_2O is less than 2%, it may be possible that α becomes small, or melting performance of the glass will be declined. If it exceeds 13%, the weather resistance or T_g may possibly be decreased.

K_2O is not essential, but may be contained in an amount of at most 8% in order to increase α or improve the melting performance of the glass. If it exceeds 8%, it may be possible that the weather resistance is decreased, or E or E/d will be decreased.

This alkali aluminosilicate glass may contain components other SiO_2 , Al_2O_3 and alkali metal oxides in an amount within a range not to impair the properties as a substrate for an information recording medium, but the content of such components is typically at most 8% in total.

As one of preferred embodiments of the glass of the present invention, a glass comprising from 64 to 67% of SiO_2 , from 8 to 10% of Al_2O_3 , from 10 to 13% of Li_2O , from 9 to 12% of Na_2O , from 0 to 2% of K_2O and from 2 to 4% of ZrO_2 , provided that the total content of Li_2O , Na_2O and K_2O , i.e. $\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$, is from 21 to 25%, may be mentioned (this glass will hereinafter be referred to as glass A of the present invention).

Next, the composition of glass A of the present invention will be described

SiO_2 is a component to form the skeleton of the glass and is essential. If it is less than 64%, the acid resistance will be decreased, d will become large, or the liquid phase temperature will be raised and the glass will become unstable. If it exceeds 67%, T_2 and T_4 will be raised and melting and forming of the glass will become difficult, E or E/d will be decreased, or α will become small.

Al_2O_3 has an effect to increase weather resistance, and is essential. If it is less than 8%, such an effect will be small, E or E/d will be decreased, or T_g will be lowered. If it exceeds 10%, the acid resistance will be decreased, T_2 and T_4 will be raised and melting and forming of the glass will become difficult, α will become small or the liquid phase temperature will be too high.

Li_2O has an effect to increase E , E/d or α , or to improve the melting performance of the glass, and is essential. If it is less than 10%, such an effect will be small. If it exceeds 13%, the weather resistance will be decreased, or T_g will be lowered.

Na_2O has an effect to increase α or to improve melting performance of the glass, and is essential. If it is less than 9%, such an effect will be small. If it exceeds 12%, the weather resistance will be decreased, or T_g will be lowered.

K_2O is not essential, but it has an effect to increase α , or to improve melting performance of the glass, and it may be contained in an amount of at most 2%. If it exceeds 2%, the weather resistance will be decreased, or E or E/d will be decreased.

In the case where K_2O is contained, its content is preferably at least 0.1%.

If the total content of Li_2O , Na_2O and K_2O , i.e. $\text{Li}_2\text{O}+\text{Na}_2\text{O}+\text{K}_2\text{O}$ (hereinafter referred to as R_2O), is less than 21%, α will become small, or the melting performance of the glass will be declined. If R_2O exceeds 25%, the weather resistance will be decreased.

ZrO_2 has an effect to increase E , E/d or T_g , to increase the weather resistance or to improve melting performance of the glass, and thus it is essential. If it is less than 2%, such an effect will be small. If it exceeds 4%, it may be possible that d becomes large or the liquid phase temperature becomes too high.

The glass of the present invention consists essentially of the above components, but it may contain other components within a range not to impair the object of the present invention. In such a case, the content of the other components is, in total, preferably at most 2%, more preferably at most 1%, particularly preferably at most 0.5%.

Next, examples of components other than the above components will be described.

MgO is not essential, but it has an effect to increase E , E/d or α , to make the glass being hardly scratched, or to improve melting performance of the glass, while maintaining the weather resistance, and it may be contained in an amount of at most 2%. If it exceeds 2%, the liquid phase temperature will be too high. It is more preferably at most 1%, particularly preferably at most 0.5%. No MgO is typically contained.

CaO is not essential, but it has an effect to increase α or to improve melting performance of the glass, while maintaining the weather resistance, and it may be

contained in an amount of at most 2%. If it exceeds 2%, it may be possible that d becomes large, E is decreased, or the liquid phase temperature becomes too high. It is more preferably at most 1%, particularly preferably at most 0.5%. No CaO is typically contained.

5 SrO may be contained in an amount of at most 2% in order to increase α or to improve melting performance of the glass. If it exceeds 2%, it may be possible that d becomes large or the glass becomes likely to be scratched. It is more preferably at most 1%, particularly preferably at most 0.5%. No SrO is typically contained.

10 BaO may be contained in an amount of at most 2% in order to increase α or to improve melting performance of the glass. If it exceeds 2%, it may be possible that d becomes large or the glass becomes likely to be scratched. It is more preferably at most 1%, particularly preferably at most 0.5%. No BaO is typically contained.

15 TiO₂ may be contained in an amount of less than 2% in order to increase E , E/d or T_g , to increase weather resistance, etc. If it is 2% or more, T_L may possibly be too high, or phase separation may possibly be likely to occur. It is more preferably at most 1%, particularly preferably at most 0.5%. No TiO₂ is typically contained.

20 B₂O₃ may be contained in an amount of at most 2% in order to increase E or E/d , to increase weather resistance, to improve melting performance of the glass, etc. If it exceeds 2%, phase separation may possibly be likely to occur. It is more preferably at most 1%, particularly preferably at most 0.5%. No B₂O₃ is typically contained.

25 La₂O₃ may be contained in order to e.g. improve E while maintaining the weather resistance, but in such a case, it is preferably at most 2%. If it exceeds 2%, it may be possible that d becomes large or the liquid phase temperature becomes too high. It is more preferably at most 1%, particularly preferably at most 0.5%. No La₂O₃ is typically contained.

30 Nb₂O₅ may be contained in order to e.g. improve E while maintaining the weather resistance, but in such a case, it is preferably at most 2%. If it exceeds 2%, it may be possible that d becomes large or the liquid phase temperature becomes too high. It is more preferably at most 1%, particularly preferably at most 0.5%. No Nb₂O₅ is typically contained.

RE₂O₃ may be contained in an amount of less than 1% in total. The RE₂O₃ represents an oxide of a rare earth selected from the group consisting of Sc, Y, La, Ce,

Pr, Nd, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb and Lu, and a mixture thereof.

A clarifier such as SO_3 , Cl, As_2O_3 , Sb_2O_3 or SnO_2 maybe contained in an amount of up to 2% in total.

A colorant such as Fe_2O_3 , Co_3O_4 or NiO may be contained in an amount of up to
5 2% in total.

Another preferred embodiment of the glass of the present invention may be, for example, one which contains from 64 to 69% of SiO_2 , from 9 to 11% of Al_2O_3 , from 6 to 9% of Li_2O , from 9 to 13% of Na_2O , from 0 to 2% of K_2O , from 0 to 4% of MgO , from 1 to 5% of CaO and from 0 to 2% of ZrO_2 , provided that $\text{Li}_2\text{O}+\text{Na}_2\text{O}+\text{K}_2\text{O}$ is from 16 to
10 20%; one which contains from 66 to 71% of SiO_2 , from 7 to 9% of Al_2O_3 , from 0 to 3% of B_2O_3 , from 12 to 16% of Li_2O , from 2 to 5% of Na_2O , from 0 to 3% of K_2O , from 0 to 5% of MgO , from 0 to 3% of TiO_2 , from 0 to 2% of ZrO_2 , from 0 to 2% of La_2O_3 and from 0 to 2% of Nb_2O_5 , provided that $\text{Li}_2\text{O}+\text{Na}_2\text{O}+\text{K}_2\text{O}$ is from 16 to 21%; and one which contains
15 from 61 to 66% of SiO_2 , from 11.5 to 17% of Al_2O_3 , from 8 to 16% of Li_2O , from 2 to 8% of Na_2O , from 2.5 to 8% of K_2O , from 0 to 6% of MgO , from 0 to 4% of TiO_2 and from 0 to 3% of ZrO_2 , provided that $\text{Al}_2\text{O}_3+\text{MgO}+\text{TiO}_2$ is at least 12% and $\text{Li}_2\text{O}+\text{Na}_2\text{O}+\text{K}_2\text{O}$ is from 16 to 23%, and that the content of B_2O_3 is less than 1% if it is contained.

The glass plate of the present invention is typically a circular glass plate.

The weather resistance of the glass substrate of the present invention is
20 evaluated by C_R defined by $C_R=C_{\text{Li}}+C_{\text{Na}}+C_{\text{K}}$, wherein C_{Li} , C_{Na} and C_{K} are amounts of Li, Na and K, respectively, which are precipitated on the surface of the glass after it is hold under a water-vapor atmosphere at 120°C at 0.2 MPa for 20 hours.

The difference obtained by subtracting the glass transition temperature T_g from the fictive temperature T_f , i.e. T_f-T_g , of the glass substrate of the present invention is at
25 most 5°C in order to improve the weather resistance. If it exceeds 5°C, the effect to improve weather resistance will be hardly obtained. T_f-T_g is preferably at most -10°C, but if it is at most -25°C, this effect will be more distinct. T_f-T_g is typically at least -35°C.

In a case where the glass of the present invention is the above glass A, C_R of the glass substrate of the present invention is preferably at most 7 nmol/cm². If C_R
30 exceeds 7 nmol/cm², films formed on the substrate, such as a base film, a magnetic film and a protective film, will be likely to be peeled.

The glass substrate of the present invention is typically used as a glass

substrate for a magnetic disk.

Glass substrates for magnetic disks are widely used for 2.5-inch substrates (outside diameter of a glass substrate: 65 mm) used for e.g. notebook PCs, 1.8-inch substrates (outside diameter of a glass substrate: 48 mm) used for e.g. portable MP3
 5 players and so on. Their market is growing every year, and on the other hand, they are desired to be supplied at a low price. Glass used for such glass substrates is preferably suitable for mass production.

A plate glass is widely mass-produced by continuous molding methods such as a float process, a fusion method and a down-draw method, and the glass of the present
 10 invention includes a glass which is able to be formed by e.g. a float process and thus it is suitable for mass production.

The melting and forming method for the glass substrate of the present invention is not particularly limited, and various methods can be applied. For example, materials for the respective components commonly used are blended to have a desired
 15 composition, and such a mixture is heated and melted in a glass melting furnace. Then, the glass is homogenized by e.g. bubbling, stirring or addition of a clarifier, followed by forming into a plate glass having a predetermined thickness by a known method such as a down-draw method including a fusion method, a float process or a press method, and then, after annealing, processing such as grinding or polishing is
 20 carried out as necessary, to obtain a glass substrate having prescribed size and shape. As the forming method, particularly, a float process suitable for mass production is preferred. Further, a continuous forming method other than a float process, i.e. a fusion method or a down-draw method, is also suitable.

A method for producing the glass substrate of the present invention is preferably
 25 such that, in cooling of the glass in the last step where the glass temperature becomes at least its strain point, the time t during which the glass temperature is at least its strain point and at most a temperature where the glass viscosity becomes 10^{10} dPa·s is at least 13 minutes. If the time t is less than 13 minutes, it may be possible that it becomes difficult to bring the above $T_f - T_g$ to at most 5°C . It is more preferably at least
 30 18 minutes.

EXAMPLES

Materials were prepared so that a glass having a composition comprising, as represented by mol%, 65.7% of SiO_2 , 8.5% of Al_2O_3 , 12.4% of Li_2O , 10.9% of Na_2O and 2.5% of ZrO_2 would be obtained, and they were melted at a temperature of from 1,550 to 1,600°C for 3 to 5 hours using a platinum crucible. In the melting, a platinum stirrer
 5 was put into the molten glass, and the glass was stirred for 2 hours to be homogenized. Then, the molten glass was cast to form a plate and annealed to room temperature at a cooling rate of 1°C/min.

Thus obtained plate glass had a density d of 2.51 g/cm³, an average linear expansion coefficient α of $77 \times 10^{-7}/^\circ\text{C}$, a Young's modulus E of 84 GPa, a specific
 10 modulus E/d of 33.7 MNm/kg, a glass transition point T_g of 494°C, a fictive temperature T_f of 478°C, a strain point T_{Str} of 457°C at which the glass viscosity becomes $10^{14.5}$ dPa·s and a temperature T_{10} of 580°C at which the glass viscosity becomes 10^{10} dPa·s. These measurements were carried out by the methods described below.

d : d was measured by an Archimedes method using from 20 to 50 g of a glass
 15 having no bubble in it.

α : By means of a differential thermal dilatometer and using quartz glass as a reference sample, the rate of elongation of a glass when it was heated at a rate of 5°C/min from room temperature to a temperature at which the glass is softened and elongation is no longer observed, i.e. to an yield point, was measured, and from the
 20 obtained thermal expansion curve, an average linear expansion coefficient within a range of -50 to 70°C was calculated.

E : With respect to a glass plate having a thickness of from 5 to 10 mm and a size of 3 cm square, the measurement was carried out by an ultrasonic pulse method.

T_g : By means of a differential thermal dilatometer and using quartz glass as a
 25 reference sample, the rate of elongation of a glass when it was heated at a rate of 5°C/min from room temperature to its yield point, and the temperature corresponding to the critical point in the obtained thermal expansion curve was taken as the glass transition point.

T_{Str} : The strain point was measured in accordance with "Determination of
 30 annealing point and strain point by fiber elongation" (JIS R 3103-2:2001).

T_{10} : A temperature-viscosity curve within a viscosity range of from $10^{1.5}$ dPa·s to $10^{4.5}$ dPa·s was measured with a rotation viscometer. Further, a softening point at

which the viscosity becomes $10^{7.6}$ dPa·s was measured in accordance with “Determination of softening point” (JIS R 3103-1:2001), and an annealing point at which the viscosity becomes 10^{13} dPa·s was measured in accordance with “Determination of annealing point and strain point” (JIS R 3103-2:2001). A temperature-viscosity curve including these viscosity ranges was obtained by fitting using Fulcher’s equation based on the above temperature-viscosity curve, the softening point, the annealing point and the strain point, and T_{10} was obtained from this temperature-viscosity curve.

The fictive temperature T_f was measured by the following method.

First, the above plate glass was processed into a glass plate having a thickness of 0.4 mm and a size of 1 cm square. This glass plate was placed in a box-shaped electric furnace, and the temperature was raised to 630°C. It was maintained at 630°C for 10 minutes, and then cooled to a holding temperature T_k at a cooling rate of 1°C/min by a program control. After it was maintained at T_k for 140 hours, the sample was retrieved from the electric furnace and quenched to room temperature under the air atmosphere. T_k was set to be 510°C, 500°C, 490°C, 480°C and 450°C. The thickness of the glass is sufficiently thin, and thus each T_f of the glass becomes T_k . The refractive index of each sample was measured, and a calibration curve of T_f and the refractive index was prepared.

Next, the above plate glass was processed into a glass plate having a thickness of 1.2 mm and a size of 4 cm square. The glass plate was placed into a box-shaped electric furnace, and the temperature was raised to 630°C. It was maintained at 630°C for 10 minutes, and then two types of samples were prepared, for which the cooling rates were set to be 0.1°C/min and 1°C/min, respectively, by a program control (the former is identified as Example 1, the latter as Example 2). The refractive index of each sample was measured, and T_f was obtained using the above calibration curve. The results were 463°C for Example 1 and 478°C for Example 2.

Further, the above plate glass was processed into a glass plate having a thickness of 1.2 mm and a size of 4 cm square. This glass plate was flowed through a belt conveyer type electric furnace, and two types of samples i.e. Example 3 and Example 4 were prepared, which have different cooling histories by controlling of the belt velocity. That is, the electric furnace has a length of 3.4 m and has five heaters installed at 0.3 m, 1 m, 1.7 m, 2.4 m and 3 m away from the inlet, and the preset

temperatures of the five heaters were set to be, in ascending order of distance from the inlet, 350°C, 450°C, 520°C, 610°C and 630°C; and a sample for which the belt velocity was 11 mm/min was identified as Example 3, and a sample for which the belt velocity was 94 mm/min was identified as Example 4. The refractive index of each sample was measured and T_f was obtained by using the above calibration curve. The results were 497°C for Example 3 and 513°C for Example 4.

In the preparation of a sample using such a belt conveyor type electric furnace, there was concern that T_f of a sample varies depending on the position, and thus the glass plate was divided into nine equal parts having a thickness of 1.2 mm and a size of 1.2 cm square, and the refractive index of each part was measured. As a result, it was found that the refractive index of all parts were equal and T_f of all parts have no difference. Further, the center part among the nine parts was divided in the thickness direction into three parts and the refractive index of each part was measured, and it was found that the refractive index of all parts were equal and T_f of all parts have no difference. Thus, it was confirmed that T_f of a glass plate having a thickness of 1.2 mm and a size of 4 cm square is uniform in the whole plate.

$T_f - T_g$ of the Examples were -32°C for Example 1, -17°C for Example 2, 2°C for Example 3 and 19°C for Example 4, wherein Examples 1 to 3 are Working Examples of the present invention and Example 4 is a Comparative Example. $T_f - T_g$ of a glass plate which is continuously industrially produced by forming a glass into a plate by a float process, a down-draw method or the like and then an annealing step is at least 15°C, and Example 4 is a model of such an industrial product.

Weather resistance index C_R of the glass plates of Examples 1 to 4 were measured as described below, and the results were 6.2 nmol/cm² for Example 1, 6.9 nmol/cm² for Example 2, 6.9 nmol/cm² for Example 3 and 7.3 nmol/cm² for Example 4. Thus, it is found that by permitting $T_f - T_g$ to be at most 5°C, the weather resistance of a glass is improved even if the composition is the same.

C_R : Both surfaces of a glass plate having a thickness of from 1 to 2 mm and a size of 4 cm × 4 cm was subjected to mirror polishing using cerium oxide and washed using calcium carbonate and a neutral detergent, and then the glass plate was placed in a highly accelerated stress test chamber (unsaturated-type pressure cooker EHS-411M, manufactured by ESPEC Corp.) and was statically left under a water-vapor atmosphere

at 120°C at 0.2 MPa for 20 hours. The tested sample and 20 ml of ultrapure water were put into a washed reclosable poly bag and a surface precipitate was dissolved in a ultrasonic bath for 10 minutes, and the quantity of eluted substances of respective alkaline components (Li and Na) was determined using ICP-MS. The eluted amounts
5 of respective alkaline components were converted to moles and were normalized by the surface area of the sample, and their sum was regarded as C_R .

INDUSTRIAL APPLICABILITY

The present invention is useful for production of an information recording
10 medium such as a magnetic disk and for a glass substrate for an information recording medium.

The entire disclosure of Japanese Patent Application No. 2009-265079 filed on November 20, 2009 including specification, claims and summary is incorporated herein
15 by reference in its entirety.

Claims:

1. A glass substrate, comprising:
an alkali aluminosilicate glass,
wherein a difference $T_f - T_g$ obtained by subtracting a glass transition temperature T_g of the alkali aluminosilicate glass from a fictive temperature T_f of the alkali aluminosilicate glass is from -32 to $+5^\circ\text{C}$., and
the alkali aluminosilicate glass has an alkali metal oxide content of from 15 to 26 mol%.
2. A glass substrate, comprising:
an alkali aluminosilicate glass,
wherein a difference $T_f - T_g$ obtained by subtracting a glass transition temperature T_g of the alkali aluminosilicate glass from a fictive temperature T_f of the alkali aluminosilicate glass is from -32 to $+5^\circ\text{C}$., and
the alkali aluminosilicate glass has an alkali metal oxide content of from 15 to 26 mol%, comprising, by mol% based on the following oxides:
from 64 to 67% of SiO_2 ,
from 8 to 10% of Al_2O_3 ,
from 10 to 13% of Li_2O ,
from 9 to 12% of Na_2O ,
from 0 to 2% of K_2O , and
from 2 to 4% of ZrO_2 ,
wherein a total content of Li_2O , Na_2O , and K_2O , ($\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$), is from 21 to 25%.
3. A magnetic disk, comprising:
the substrate of claim 1, and
a magnetic recording layer on the substrate.
4. The substrate of claim 1,
wherein a sum

$$C_{Li} + C_{Na} + C_K$$

is at most 7 nmol/cm^2 , and

C_{Li} , C_{Na} , and C_K are respectively amounts of Li, Na, and K that are precipitated on a glass surface of the substrate after exposure to a water-vapor atmosphere at 120°C . at 0.2 MPa for 20 hours.

5. The substrate of claim 1, wherein a density of the substrate is at most 2.60 g/cm^3 .

6. The substrate of claim 1, wherein a Young's modulus of the substrate is at least 76 GPa .

7. The substrate of claim 1, wherein a specific modulus of the substrate is at least 28 MNm/kg.

8. The substrate of claim 1, wherein an average linear expansion coefficient of the substrate is at least $56 \cdot 10^{-7}/^{\circ}\text{C}$. from -50 to 70°C .

9. The substrate of claim 1,
wherein a content of SiO_2 is from 61 to 71%, and
a content of Al_2O_3 is from 7 to 17%.

10. The substrate of claim 1,
wherein a content of Li_2O is from 6 to 16%,
a content of Na_2O is from 2 to 13%, and
a content of K_2O is from 0 to 8%.