

MIXED METAL OXIDE CATALYST FOR DECOMPOSITION OF NITROGEN OXIDES

DESCRIPTION

5

Technical Field

The present invention relates to a mixed metal oxide catalyst in which a hydrotalcite precursor containing an alkali metal is impregnated or intercalated with a nonprecious metal, a method of manufacturing the same, and a method of decomposing nitrogen oxide using the mixed
10 metal oxide catalyst.

Background Art

As the damage caused by climate change increases all over the world, air pollution problem has recently attracted considerable attention. Among materials related to global
15 warming, nitrous oxide (N_2O) contributes to the greenhouse effect, 310 times as much as carbon dioxide (CO_2), is a compound stable in air, and is presumed to stay in the air for 20 ~ 100 years. Further, nitrous oxide (N_2O) destroys the ozone layer of the stratosphere. Therefore, it is known that, when the amount of nitrous oxide (N_2O) increases two fold, the amount of ozone decreases by 2%.

20 Nitrogen oxides are necessary by-products of the procedure of burning fossil fuels or incinerating various wastes, and generate photochemical smog and various secondary pollutants (O_3 , PAN, etc.) through a photochemical reaction that takes place in the air. That is, nitrogen oxides are very important in terms of air pollution. In order to cope with such crises caused by climate change, it is required to effectively remove nitrous oxide (N_2O) as a greenhouse gas
25 together with nitrogen oxides (NO_x).

Referring to conventional technologies related to the decomposition of N_2O and NO_x , there are proposed a method of controlling the temperature of a combustion furnace, a method of

recirculating exhaust gas, a method of mounting a special burner, and the like. However, these methods are poor in terms of performance. Thereafter, selective catalytic reduction (SCR) has been put to practical use, but has the problems of high equipment cost and its performance worsening with aging of the catalyst.

5 Patent document 1, filed by Alini et al, discloses a method of decomposing N_2O gas at a temperature of 400 or more using a rhodium (Rh)-containing hydrotalcite catalyst. However, this method is problematic in that N_2O at a very low concentration of 200 ppm or less must react at a high temperature of 400 or more and the rhodium (Rh)-containing hydrotalcite catalyst is expensive.

10 Patent document 2 discloses a method of catalytically reducing nitrogen oxides included in exhaust gas containing light hydrocarbons using the exhaust gas as a reductant and using β -Zeolite exchanged with a cobalt salt as a catalyst. However, this method is problematic in that the conversion ratio of N_2O is low although N_2O is reacted at high temperature using a large amount of a reductant which is two or more times larger than that used with NO_x .

15 According to the paper [Reduction of N_2O with CO Over FeMFI zeolites., Catal. 223(2004)] written by Javier P.R. et al., when N_2O was decomposed using a zeolite catalyst coated with iron (Fe) in the presence of carbon monoxide (CO) as a reductant, the decomposition rate of N_2O was improved compared to those of conventional technologies. However, there is a problem in that N_2O must be decomposed at a high temperature of 400 or more.

20 Patent document 3 discloses a method of directly reducing nitrogen oxide by catalytic reduction using a catalyst in which a solid powdered carrier is supported with a metal. However, this method is problematic in that the conversion ratio of N_2O is 50% or less even at a high temperature of 400 or more.

 Patent document 4, filed by Schwefer et al., discloses a method of decomposing N_2O and
25 NO_x at a temperature of 450 and a pressure of 6.5 bar using an iron-containing ZSM-5 catalyst and a reductant (ammonia). However, this method is problematic in that the conversion ratio of N_2O is 64% and the conversion ratio of NO_x is 78%, each of which is somewhat low, and in that

the decomposition temperature and pressure are high.

In Patent document 5 filed by Nagata, Hihara et al., β -Zeolite exchanged with iron ion was impregnated with ferric nitrate and then calcinated at 500 for 5 hours to prepare an ion-exchanged catalyst containing about 4% of iron oxide, and then this catalyst was mixed with a binder and then applied onto a honeycomb support, and then the performance of the catalyst was tested. In this case, when NO_x included in the exhaust gas of a diesel engine was decomposed at the low temperature of 200 using urea as a reductant, there is a problem in that the conversion ratio of NO_x is about 43%, which is low.

Patent document 1: European Patent Publication No. 1262224

10 Patent document 2: Korea Patent No. 0359675

Patent document 3: Korea Patent No. 0408880

Patent document 4: US Patent No. 7462340

Patent document 5: US Patent No. 7501105

15 **Disclosure**

Technical Problem

Thus, in order to solve the above-mentioned problems, the present inventors have done broad research. As a result, they found that the catalytic activity of a mixed metal oxide catalyst, in which a hydrotalcite precursor containing an alkali metal is impregnated or intercalated with a nonprecious metal, is equal to that of a precious metal catalyst such as Rh, Pd or the like in the decomposition of nitrogen oxides. Based on this finding, the present invention was completed.

Accordingly, an object of the present invention is to provide a catalyst for the decomposition of nitrogen oxides, in which a hydrotalcite precursor containing an alkali metal is impregnated or intercalated with a nonprecious metal.

25 Another object of the present invention is to provide a method of manufacturing the catalyst for the decomposition of nitrogen oxides.

Still another object of the present invention is to provide a method of decomposing NO_x ,


N₂O or a mixture thereof even at low temperature using the catalyst for the decomposition of nitrogen oxides.

Technical Solution

5 In order to accomplish the above objects, an aspect of the present invention provides a mixed metal oxide catalyst for the decomposition of nitrogen oxides, in which a hydrotalcite precursor containing an alkali metal is impregnated or intercalated with a nonprecious metal.

Here, the hydrotalcite precursor containing an alkali metal is represented by Formula 1 below:

10 [Formula 1]



wherein L⁺ is at least one selected from the group consisting of Na⁺, K⁺, Li⁺, Rb⁺, Cs⁺ and Fr⁺; M²⁺ is at least one selected from the group consisting of Mg²⁺, Ca²⁺, Ni²⁺, Zn²⁺, Sr²⁺, Ba²⁺, Fe²⁺, Cu²⁺, Co²⁺, Pd²⁺ and Mn²⁺; N³⁺ is at least one selected from the group consisting of Al³⁺,
15 Mn³⁺, Fe³⁺, Co³⁺, Ni³⁺, Cr³⁺, Ga³⁺, B³⁺, La³⁺, Ce³⁺ and Rh³⁺; Aⁿ⁻ is at least one selected from the group consisting of CO₃²⁻, NO₃⁻, SO₄²⁻, Cl⁻, OH⁻, SiO₃²⁻, MnO₄²⁻, HPO₃²⁻, MnO₄²⁻, HGaO₃²⁻, HVO₄²⁻, ClO₄⁻ and BO₃²⁻; x is 0.01 ~ 0.5; a is 0.01 ~ 1; and b is an integer of 0 ~ 20.

Further, the nonprecious metal may be at least one selected from the group consisting of Ni, Co, Fe, Mn, Al, Ce, Cu, Zn, Ba, Mg, Ca and Sr, and an amount of the nonprecious metal may
20 be 0.01 ~ 20 wt%.

Another aspect of the present invention provides a method of manufacturing a mixed metal oxide catalyst for decomposition of nitrogen oxides, including the steps of: providing a hydrotalcite precursor containing an alkali metal; impregnating or intercalating the hydrotalcite precursor with a nonprecious metal; and calcinating the hydrotalcite precursor impregnated or
25 intercalated with the nonprecious metal at a temperature of 100 ~ 1000 to form a mixed metal oxide catalyst.

Still another aspect of the present invention provides a method of decomposing nitrogen

oxide using a mixed metal oxide catalyst, comprising the step of reacting nitrogen oxide including nitrogen oxides including N_2O , NO_x and a mixture thereof with a gas mixture including a reductant in the presence of a mixed metal oxide catalyst in which a hydrotalcite precursor containing an alkali metal is impregnated or intercalated with a nonprecious metal.

5 Here, the reductant may be at least one selected from the group consisting of a hydrocarbon of 1 to 6 carbon atoms, an alcohol of 1 to 6 carbon atoms, SO_2 , NH_3 and CO .

 Further, gas may pass through the catalyst at a gas hour space velocity of $1,000\text{h}^{-1} \sim 200,000\text{h}^{-1}$, and the pressure of the gas may be 1 atm or more.

 Further, the reaction temperature may be $150 \sim 500$.

10 Further, the amount of the nitrogen oxide may be $0.001 \sim 31$ wt%, and the amount of the reductant may be $0.001 \sim 21$ wt%.

Advantageous Effects

 According to the present invention, when the mixed metal oxide catalyst manufactured
15 using a hydrotalcite precursor containing an alkali metal is used to decompose nitrogen oxides, the mixed metal oxide catalyst can exhibit catalytic activity equal to that of a precious metal catalyst without using a precious metal such as Pd, Rh or the like, thus reducing production cost. Further, the mixed metal oxide catalyst can effectively decompose nitrogen oxides even at a low temperature of 300 or less, so that operation cost can be reduced, with the result that this
20 catalyst can be used for a long period of time.

Best Mode

 Hereinafter, the present invention will be described in detail.

 As described above, the present invention provides a mixed metal oxide catalyst for the
25 decomposition of nitrogen oxide, in which a hydrotalcite precursor is impregnated or intercalated with an alkali metal such as potassium (K) or the like, and thus which can decompose industrially-produced nitrogen oxides including N_2O , NO_x and a mixture thereof by a simple and economical

process.

Further, the present invention provides a method of manufacturing a mixed metal oxide catalyst for decomposition of nitrogen oxides, including the steps of: providing a hydrotalcite precursor containing an alkali metal; impregnating or intercalating the hydrotalcite precursor with
5 a nonprecious metal; and calcinating the hydrotalcite precursor impregnated or intercalated with the nonprecious metal at a temperature of 100 ~ 1000 to form a mixed metal oxide catalyst.


A hydrotalcite compound is an anionic clay compound whose upper and lower layers are charged with cations and whose intermediate layer is can be exchanged with anions. A hydrotalcite compound is composed of a magnesium hydrate, an aluminum hydrate or the like,
10 which resourcefully exists in the Earth, and is artificially synthesized by forming anions of a chelating agent and a complex compound and then co-precipitating the anions to introduce metal cations into a doubly-layered hydrate.

A hydrotalcite compound has a large surface area, a high memory effect and a basic composition, and is formed by heating into a homogeneous oxide having a very small particle
15 size, crystallinity and stability to heat treatment. In the hydrotalcite compound, bivalent metals are partially substituted with trivalent metals whose sizes are similar to those of the bivalent metals, so that the negative charge of the layers thereof is relatively insufficient to allow the hydrotalcite compound to be positively charged to form positive charges, and anions such as CO_3^{2-} , OH^- or the like intercalated between the layers in order to offset the formed positive charges, and water
20 coordinates with the anions, thereby forming a layered structure.

In the present invention, a hydrotalcite compound containing an alkali metal such as potassium (K) or the like is used as a precursor of a mixed metal oxide catalyst.

The hydrotalcite precursor containing an alkali metal is a porous material represented by Formula 1 below, and is variously used as a catalyst.

25 [Formula 1]



In the hydrotalcite precursor, L^+ , M^{2+} and N^{3+} are metal cations, respectively. Here, L^+ is

a monovalent alkali metal cation selected from the group consisting of Na^+ , K^+ , Li^+ , Rb^+ , Cs^+ and Fr^+ ; M^{2+} is a bivalent alkali metal cation selected from the group consisting of Mg^{2+} , Ca^{2+} , Ni^{2+} , Zn^{2+} , Sr^{2+} , Ba^{2+} , Fe^{2+} , Cu^{2+} , Co^{2+} , Pd^{2+} and Mn^{2+} ; N^{3+} is a trivalent alkali metal cation selected from the group consisting of Al^{3+} , Mn^{3+} , Fe^{3+} , Co^{3+} , Ni^{3+} , Cr^{3+} , Ga^{3+} , B^{3+} , La^{3+} , Ce^{3+} and Rh^{3+} .

5 The molar ratio of M^{2+} and N^{3+} may be 1:1 ~ 100:1, preferably 1:1 ~ 5:1.

Further, in the hydrotalcite precursor, A^{n} is at least one anionic compound selected from the group consisting of CO_3^{2-} , NO_3^- , SO_4^{2-} , Cl^- , OH^- , SiO_3^{2-} , MnO_4^{2-} , HPO_3^{2-} , MnO_4^{2-} , HGao_3^{2-} , HVO_4^{2-} , ClO_4^- , BO_3^{2-} and combinations thereof.

Meanwhile, in Formula 1 above, a is 0.01 ~ 1, x is 0.01 ~ 0.5, and b is an integer of 0 ~

10 20.

Since the mixed metal oxide catalyst produced from the hydrotalcite precursor containing an alkali metal is impregnated or intercalated with a nonprecious metal, an expensive precious metal, as is normally used to improve catalytic activity, may be replaced by a nonprecious metal.

In the manufacture of the mixed metal oxide catalyst, the hydrotalcite precursor
15 containing an alkali metal can be impregnated or intercalated with a nonprecious metal by preparing a nonprecious nitrate solution and then mixing the solution with a hydrotalcite precursor to cause an ion exchange reaction therebetween.

Here, the nonprecious metal may be at least one selected from the group consisting of Ni, Co, Fe, Mn, Al, Ce, Cu, Zn, Ba, Mg, Ca and Sr, preferably, Ni, Co, Fe, Mg, Al, Ca, and most
20 preferably, Ni. The amount of the nonprecious metal is 0.01 ~ 20 wt%, preferably, 0.01 ~ 15 wt%. When the amount thereof is less than 0.01 wt%, the effect of increasing catalytic activity is barely realized depending on the use of the nonprecious metal. Further, when the amount thereof is more than 20 wt%, pores formed in the mixed metal oxide catalyst are blocked, so that the specific surface area of the catalyst is reduced, thereby decreasing the decomposition ratio.

25 In the present invention, when the hydrotalcite precursor impregnated or intercalated with a nonprecious metal is calcinated at a temperature of 100 ~ 1000 preferably, 400 ~ 800 it is reliably formed into a mixed metal oxide.

The mixed metal oxide catalyst of the present invention may be further impregnated or intercalated with a new precious metal after the calcination in consideration of the purpose and efficiency of the catalyst. For example, the mixed metal oxide produced from the hydrotalcite precursor impregnated or intercalated with aluminum (Al) as a nonprecious metal is mixed with a
5 magnesium (Mg) nitrate solution and then dried to manufacture the mixed metal oxide catalyst of the present invention.

The process of manufacturing the mixed metal oxide catalyst including an alkali metal may be variously modified without departing from the scope and spirit of the invention.

According to a modified embodiment of the present invention, a mixed metal oxide
10 produced from a hydrotalcite precursor containing only an alkali metal is calcinated, and is then impregnated with a nonprecious metal to manufacture a mixed metal oxide containing a nonprecious metal and an alkali metal. According to another modified embodiment of the present invention, a mixed metal oxide produced from a hydrotalcite precursor containing only a nonprecious metal is calcinated, and is then impregnated with an alkali metal to manufacture a
15 mixed metal oxide containing a nonprecious metal and an alkali metal.

The catalytic activity of the alkali metal-containing mixed metal oxide catalyst impregnated or intercalated with a nonprecious metal according to the present invention is equal to that of a conventional catalyst impregnated or intercalated with a precious metal in the decomposition of nitrogen oxide. According to the present invention, in the reaction that
20 decomposes NO_x , N_2O and a mixture thereof using the mixed metal oxide catalyst produced from the hydrotalcite precursor, the gas mixture passing through the catalyst layer includes 0.001 ~ 31 wt% of nitrogen oxide and 0.001 ~ 21 wt% of a reductant.

The reductant used in the present invention may be selected from the group consisting of hydrocarbons of 1 to 6 carbon atoms such as methane, ethane, propane, butane, pentane, hexane,
25 isopropane, isobutene, 2-butane, isopentane, 2-pentane, tertiary pentane, isohexane, 2-hexane and the like; alcohols of 1 to 6 carbon atoms such as methanol, ethanol, propanol, butanol, hexanol and the like; SO_2 ; NH_3 ; CO ; and combinations thereof. In this case, it is preferred that the amount

of the reductant in the gas mixture be 0.001 ~ 21 wt%. When the amount of the reductant is less than 0.001 wt%, NO and N₂O cannot be sufficiently reduced into N₂ and O₂ because of insufficient reduction ability. Further, when the amount thereof is more than 21 wt%, a large amount of untreated reductant and a large amount of side product are produced, and thus a process is additionally required to remove the untreated reductant and side products.

Moreover, the reductant may be used together with oxygen (O₂). It is preferred that the amount of oxygen in the gas mixture be 0.001 ~ 21 wt%. When the amount thereof is less than 0.001 wt%, NO and N₂O cannot be reduced into N₂ and O₂ because the reductant cannot be oxidized. Further, when the amount thereof is more than 21 wt%, oxygen (O₂) occupies the active sites of the catalyst, so that NO and N₂O cannot react, thereby remarkably decreasing the decomposition ratio thereof.

In the decomposition reaction of the present invention, the gas hour space velocity (GHSV) of the gas passing through the catalyst layer may be 1,000h⁻¹ ~ 200,000h⁻¹, preferably 30,000 ~ 100,000h⁻¹. When the GHSV thereof is less than 1,000h⁻¹, the amount of the treated gas is small, and thus the catalyst is economically inefficient. Further, when the GHSV thereof is more than 200,000h⁻¹, the contact time between the gas and the catalyst is short, thus decreasing the decomposition efficiency of NO_x or N₂O.

Meanwhile, it is preferred that the pressure of the gas passing through the catalyst layer be 1 atm or more. As the pressure thereof increases, the decomposition ratio of nitrogen oxide increases.

According to the present invention, in the reaction of decomposing NO_x, N₂O and a mixture thereof using the mixed metal oxide catalyst produced from the hydrotalcite precursor, the temperature of the gas passing through the catalyst layer may be 100 ~ 500 °C preferably 100 ~ 300 °C and more preferably 150 ~ 250 °C. When the temperature thereof is lower than 100 °C, sufficient activation energy cannot be obtained, and thus NO_x and N₂O cannot be decomposed. In the case of the catalyst of the present invention, the decomposition efficiency of gas is high even at 500 °C or lower. Therefore, when the temperature thereof is higher than 500 °C, energy

consumption is excessive so that it takes a lot of money to decompose NO_x and N_2O .

The nitrogen oxide decomposition rate of the mixed metal oxide catalyst of the present invention is equal to that of a mixed metal oxide catalyst in which a hydrotalcite precursor is impregnated or intercalated with a precious metal. Meanwhile, the above-mentioned effects can also be achieved by a mixed metal oxide catalyst produced from a brucite precursor, not a hydrotalcite precursor. The brucite precursor is represented by Formula 1 above wherein $a=0$ and $x=0$. As described in the following Example, it can be seen that, when nitrogen oxide is decomposed using the mixed metal oxide catalyst in which a brucite precursor is impregnated or intercalated with a nonprecious metal, the decomposition efficiency of nitrogen oxide is high even at low temperature (refer to Comparative Example 6).

Mode for Invention

Hereinafter, the present invention will be described in more detail with reference to the following Examples. However, the scope of the present invention is not limited to these Examples.

Examples

Manufacture of a mixed metal oxide catalyst

NaOH and Na_2CO_3 were dissolved in distilled water at a molar ratio of 3.5: 1 to prepare a solution. The solution was put into a reactor, and was then stirred at a predetermined speed while slowly adding a solution prepared by dissolving metal (II) nitrate (Co nitrate, Fe nitrate or the like), metal (III) nitrate (Al nitrate, Mn nitrate or the like) and alkaline nitrate (K nitrate or the like) in distilled water at a predetermined molar ratio for 4 hours to obtain precipitates. The precipitates were stirred for 30 minutes to uniformly mix them. The mixed precipitate was aged at 65 for 16 hours to obtain a reaction product. The reaction product was washed with an excessive amount of distilled water three times to obtain a hydrotalcite compound. The obtained hydrotalcite compound was mixed with a nonprecious metal nitrate (nickel nitrate or the like)

solution to impregnate or intercalate it with a nonprecious metal as a result of an ion exchange reaction. Thereafter, the hydrotalcite compound impregnated or intercalated with a nonprecious metal was washed with distilled water, and was then dried at 110°C for 12 hours to obtain a hydrotalcite precursor. The hydrotalcite precursor was heated from 25°C to 500 and was then
5 calcinated at 500°C for 4 hours to manufacture a mixed metal oxide catalyst. The manufactured mixed metal oxide catalyst was put into a desiccator and then pretreated (completely reduced) under a nitrogen or CO atmosphere before it was used in the N₂O decomposition test.

Measurement of decomposition rate of nitrogen oxide

10 [Comparative Example 1]

The decomposition rate of N₂O in a gas mixture including 12,500 ppm of N₂O, 12,500 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 200ml/min(SV 42,000hr⁻¹) was measured using 0.2 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Co-Pd-Ce-Al of 2/0.01/0.01/1. The decomposition rate thereof under
15 these conditions was 96% at 200 and 100% at 250°C or more.

[Comparative Example 2]

The decomposition rates of N₂O and NO in a gas mixture including 12,500 ppm of N₂O, 12,500 ppm of CO, 100 ppm of NO and nitrogen (N₂, remainder) and having a flow rate of
20 200ml/min (SV 30,000hr⁻¹) were measured using 0.4 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Co-Rh-Ce-Al of 1/0.2/0.01/1. The decomposition rate of N₂O under these conditions was 99% at 200°C and the composition rate of NO was 99% at 200 and the decomposition rate of N₂O was 100% at 250°C or more and the composition rate of NO was 100% at 250°C or more.

25

[Comparative Example 3]

The decomposition rate of N₂O in a gas mixture including 12,500 ppm of N₂O, 17,500

ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 200ml/min(SV 30,000hr⁻¹) was measured using 0.3 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Co-Rh-Al of 1/0.2/1. The decomposition rate thereof under these conditions was 98% at 200 °C and was 100% at 250°C or more.

5

[Comparative Example 4]

The decomposition rate of N₂O in a gas mixture including 12,500 ppm of N₂O, 12,500 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 200ml/min (SV 30,000hr⁻¹) was measured using 0.285 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Co-Pd-Al of 1/0.1/1. The decomposition rate thereof under these conditions was 100% at 200°C or more.

10

[Comparative Example 5]

The decomposition rate of NO in a gas mixture including 344 ppm of NO, 3,900 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 200ml/min (SV 30,000hr⁻¹) was measured using 3.397 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-Pd-Co of 1/0.05/1. The decomposition rate thereof under these conditions was 100% at 250°C or more.

15

20

[Comparative Example 6]

The decomposition rate of NO in a gas mixture including 446 ppm of NO, 3,866 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 500ml/min (SV 41,000hr⁻¹) was measured using 3.397 g of a nickel (Ni) oxide catalyst produced from a brucite precursor. The decomposition rate thereof under these conditions was 100% at 200°C or more.

25

[Example 1]

The decomposition rate of N₂O in a gas mixture including 12,500 ppm of N₂O, 17,500

ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 400ml/min(SV 55,000hr⁻¹) was measured using 0.20 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K of 1/1. The decomposition rate thereof under these conditions was 92% at 175 °C and was 100% at 200 °C or more.

5

[Example 2]

The decomposition rate of N₂O in a gas mixture including 12,500 ppm of N₂O, 17,500 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 400ml/min (SV 55,000hr⁻¹) was measured using 0.20 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K of 1/0.5. The decomposition rate thereof under these conditions was 68% at 175 °C and was 100% at 200 °C or more.

10

[Example 3]

The decomposition rate of N₂O in a gas mixture including 12,500 ppm of N₂O, 17,500 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 400ml/min (SV 55,000hr⁻¹) was measured using 0.20 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K of 1/0.2. The decomposition rate thereof under these conditions was 51% at 175 °C and was 100% at 200°C or more.

15

20 [Example 4]

The decomposition rate of N₂O in a gas mixture including 12,500 ppm of N₂O, 12,500 ppm of NO, 30,000 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 400ml/min (SV 55,000hr⁻¹) was measured using 0.20 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K of 1/1. The decomposition rate thereof under these conditions was 55% at 175 °C and was 100% at 200 °C or more.

25

[Example 5]

The decomposition rate of N₂O in a gas mixture including 12,500 ppm of N₂O, 12,500 ppm of NO, 30,000 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 400ml/min (SV 55,000hr⁻¹) was measured using 0.20 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K of 1/0.5. Under these conditions,
5 the decomposition rate thereof was 78% at 200 and was 100% at 250°C or more.

[Example 6]

The decomposition rate of N₂O in a gas mixture including 12,500 ppm of N₂O, 12,500 ppm of NO, 30,000 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of
10 400ml/min (SV 55,000hr⁻¹) was measured using 0.20 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K of 1/0.2. Under these conditions, the decomposition rate thereof was 65% at 200 and was 100% at 250 or more.

[Example 7]

15 The decomposition rate of NO in a gas mixture including 2,000 ppm of NO, 4,000 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 500ml/min (SV 75,000hr⁻¹) was measured using 1.355 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K of 1/1. Under these conditions, the decomposition rate thereof was 100% at 200°C.

20

[Example 8]

The decomposition rate of NO in a gas mixture including 2,000 ppm of NO, 4,000 ppm of CO and nitrogen (N₂, remainder) and having a flow rate of 500ml/min (SV 75,000hr⁻¹) was measured using 1.898 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor
25 and having a molar ratio of Ni-K-Pd of 1/1/0.1. Under these conditions, the decomposition rate thereof was 85% at 200 and was 100% at 220 or more.

[Example 9]

The decomposition rates of N_2O and NO in a gas mixture including 900 ppm of N_2O , 520 ppm of NO, 5,000 ppm of CO, and nitrogen (N_2 , remainder) and having a flow rate of 500ml/min (SV 33,000 hr^{-1}) were measured using 3.72 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K-Pd of 1/0.2/0.1. Under these conditions, the decomposition rates of NO and N_2O were 100% and 80% at 200 °C respectively, and the decomposition rates of NO and N_2O were all 100% at 250 °C or more.

[Example 10]

The decomposition rate of N_2O in a gas mixture including 785 ppm of N_2O , 30,000 ppm of CO and nitrogen (N_2 , remainder) and having a flow rate of 500ml/min (SV 39,000 hr^{-1}) was measured using 3.582 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K-Rh of 1/0.2/0.02. Under these conditions, the decomposition rate thereof was 98% at 200 °C and was 100% at 220 °C or more.

[Example 11]

The decomposition rate of NO in a gas mixture including 435 ppm of NO, 20,000 ppm of CO and nitrogen (N_2 , remainder) and having a flow rate of 500ml/min (SV 39,000 hr^{-1}) was measured using 3.582 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K-Rh of 1/0.2/0.02. Under these conditions, the decomposition rate thereof was 100% at 200 °C or more.

[Example 12]

The decomposition rate of N_2O in a gas mixture including 12,500ppm ppm of N_2O , 12,500 ppm of NO, 17,500 ppm of CO, 125 ppm of SO_2 and nitrogen (N_2 , remainder) and having a flow rate of 400ml/min (SV 55,000 hr^{-1}) was measured using 0.20 g of a mixed metal oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K of 1/1. Under

these conditions, the decomposition rate thereof was 100% at 200 or more.

[Example 13]

The decomposition rate of N₂O in a gas mixture including 12,500ppm ppm of N₂O,
 5 12,500 ppm of NO, 17,500 ppm of CO, 150 ppm of NH₃ and nitrogen (N₂, remainder) and
 having a flow rate of 400ml/min (SV 55,000hr⁻¹) was measured using 0.20 g of a mixed metal
 oxide catalyst produced from a hydrotalcite precursor and having a molar ratio of Ni-K of 1/1.
 Under these conditions, the decomposition rate thereof was 100% at 200 or more.

10 The compositions, reaction conditions and nitrogen oxide decomposition rates of
 Comparative Examples 1 to 6 and Examples 1 to 13 are given in Table 1 below.

[Table 1]

	Composition		Total gas composition	Flow rate	Results of decomposition of nitrogen oxide		
	Component	Ratio (mass)			Target	Decomposition rate	
Comp. Ex. 1	Co-Pd-Ce-Al	2/0.01/0.01/1 (0.2g)	N ₂ O 125000ppm/ CO 125000ppm/ nitrogen gas	200ml/min (SV 42000hr ⁻¹)	N ₂ O	200	96%
						250 ≥	100%
Comp. Ex. 2	Co-Rh-Ce-Al	2/0.2/0.01/1 (0.4g)	N ₂ O 125000ppm/ CO 125000ppm/ NO 100ppm/ nitrogen gas	200ml/min (SV 30000hr ⁻¹)	N ₂ O	200	99%
						250 ≥	100%
					NO	200	99%
						250 ≥	100%
Comp. Ex. 3	Co-Rh-Al	1/0.2/1 (0.3g)	N ₂ O 125000ppm/ CO 175000ppm/ nitrogen gas	200ml/min (SV 30000hr ⁻¹)	N ₂ O	200	98%
						250 ≥	100%

Comp. Ex. 4	Co-Pd-Al	1/0.1/1 (0.285g)	N ₂ O 125000ppm/ CO 125000ppm/ nitrogen gas	200ml/min (SV 30000hr ⁻¹)	N ₂ O	200 ≥	100%
Comp. Ex. 5	Ni-Pd-Co	1/0.05/1 (3.397g)	NO 344ppm/ CO 3900ppm/ nitrogen gas	400ml/min (SV 39000hr ⁻¹)	NO	250 ≥	100%
Comp. Ex. 6	Ni	(3.394g)	NO 446ppm/ CO 3866ppm/ nitrogen gas	500ml/min (SV 41000hr ⁻¹)	NO	200 ≥	100%
Ex. 1	Ni-K	1/1 (0.20g)	N ₂ O 125000ppm/ CO 175000ppm/ nitrogen gas	400ml/min (SV 55000hr ⁻¹)	N ₂ O	175	92%
						200 ≥	100%
Ex. 2	Ni-K	1/0.5 (0.20g)	N ₂ O 125000ppm/ CO 175000ppm/ nitrogen gas	400ml/min (SV 55000hr ⁻¹)	N ₂ O	175	68%
						200 ≥	100%
Ex. 3	Ni-K	1/0.2 (0.20g)	N ₂ O 125000ppm/ CO 175000ppm/ nitrogen gas	400ml/min (SV 55000hr ⁻¹)	N ₂ O	175	51%
						200 ≥	100%
Ex. 4	Ni-K	1/1 (0.20g)	N ₂ O 125000ppm/ CO 30000ppm/ NO 12500ppm/ nitrogen gas	400ml/min (SV 55000hr ⁻¹)	N ₂ O	175	55%
						200 ≥	100%

Ex. 5	Ni-K	1/0.5 (0.20g)	N ₂ O 125000ppm/ CO 30000ppm/ NO 12500ppm/ nitrogen gas	400ml/min (SV 55000hr ⁻¹)	N ₂ O	200	78%
						250 ≥	
Ex. 6	Ni-K	1/0.2 (0.20g)	N ₂ O 125000ppm/ CO 30000ppm/ NO 12500ppm/ nitrogen gas	400ml/min (SV 55000hr ⁻¹)	N ₂ O	200	65%
						250 ≥	
Ex. 7	Ni-K	1/1 (1.355g)	NO 2000ppm/ CO 4000ppm/ nitrogen gas	700ml/min (SV 75000hr ⁻¹)	NO	200 ≥	100%
Ex. 8	Ni-K-Pd	1/1/0.1 (1.898g)	NO 2000ppm/ CO 4000ppm/ nitrogen gas	500ml/min (SV 75000hr ⁻¹)	NO	200	85%
						220 ≥	
Ex. 9	Ni-K-Pd	1/0.2/0.1 (3.72g)	N ₂ O 900ppm/ CO 5000ppm/ NO 520ppm/ nitrogen gas	500ml/min (SV 33000hr ⁻¹)	N ₂ O	200	80%
						250 ≥	
					NO	200	100%
						250 ≥	
Ex. 10	Ni-K-Rh	1/0.2/0.02 (3.582g)	N ₂ O 785ppm/ CO 3000ppm/ nitrogen gas	500ml/min (SV 39000hr ⁻¹)	N ₂ O	200	98%
						220 ≥	
Ex. 11	Ni-K-Rh	1/0.2/0.02 (3.582g)	NO 435ppm/ CO	500ml/min (SV	NO	200 ≥	100%

			2000ppm/ nitrogen gas	39000hr ⁻¹)			
Ex. 12	Ni-K	1/1 (0.20g)	N ₂ O 125000ppm/ CO 17500ppm/ NO 12500ppm/ SO ₂ 125ppm/ nitrogen gas	400ml/min (SV 55000hr ⁻¹)	N ₂ O	200 ≥	100%
Ex. 13	Ni-K	1/1 (0.20g)	N ₂ O 125000ppm/ CO 17500ppm/ NO 12500ppm/ NH ₃ 150ppm/ nitrogen gas	400ml/min (SV 55000hr ⁻¹)	N ₂ O	200 ≥	100%

From Table 1 above, it can be ascertained that the effect of the mixed metal oxide catalyst of the present invention, in which a hydrotalcite precursor containing an alkali metal is impregnated or intercalated with a nonprecious metal, is equal to that of a conventional metal oxide catalyst containing a precious metal such as Rh, Pd or the like in the point that the nitrogen oxide decomposition of the mixed metal oxide catalyst of the present invention reaches 100% at 250 or lower.

Further, it can be ascertained that, in the present invention, the increase in the decomposition rate of nitrogen oxide depends on the increased amount of an alkali metal (refer to Example 1 to 3) or the increased amount of a reductant (refer to 4, 13 and 14).

Although the embodiments of the present invention have been disclosed for illustrative purposes, it will be appreciated that the present invention is not limited thereto, and those skilled in the art will appreciate that various modifications, additions and substitutions are possible, without

departing from the scope and spirit of the invention.

Accordingly, any and all modifications, variations or equivalent arrangements should be considered to be within the scope of the invention, and the detailed scope of the invention will be disclosed by the accompanying claims.


5

CLAIMS

1. A mixed metal oxide catalyst for decomposition of nitrogen oxides, in which a hydrotalcite precursor containing an alkali metal is impregnated or intercalated with a nonprecious metal.

2. The mixed metal oxide catalyst according to claim 1, wherein the hydrotalcite precursor containing an alkali metal is represented by Formula 1 below:

[Formula 1]



wherein L^+ is at least one selected from the group consisting of Na^+ , K^+ , Li^+ , Rb^+ , Cs^+ and Fr^+ ; M^{2+} is at least one selected from the group consisting of Mg^{2+} , Ca^{2+} , Ni^{2+} , Zn^{2+} , Sr^{2+} , Ba^{2+} , Fe^{2+} , Cu^{2+} , Co^{2+} , Pd^{2+} and Mn^{2+} ; N^{3+} is at least one selected from the group consisting of Al^{3+} , Mn^{3+} , Fe^{3+} , Co^{3+} , Ni^{3+} , Cr^{3+} , Ga^{3+} , B^{3+} , La^{3+} , Ce^{3+} and Rh^{3+} ; A^{n-} is at least one selected from the group consisting of CO_3^{2-} , NO_3^- , SO_4^{2-} , Cl^- , OH^- , SiO_3^{2-} , MnO_4^{2-} , HPO_3^{2-} , MnO_4^{2-} , $HGaO_3^{2-}$, HVO_4^{2-} , ClO_4^- and BO_3^{2-} ; x is 0.01 ~ 0.5; a is 0.01 ~ 1; and b is an integer of 0 ~ 20.

3. The mixed metal oxide catalyst according to claim 1, wherein the nonprecious metal is at least one selected from the group consisting of Ni, Co, Fe, Mn, Al, Ce, Cu, Zn, Ba, Mg, Ca and Sr, and an amount of the nonprecious metal is 0.01 ~ 20 wt%.

4. A method of manufacturing a mixed metal oxide catalyst for decomposition of nitrogen oxides, comprising the steps of:

providing a hydrotalcite precursor containing an alkali metal;
impregnating or intercalating the hydrotalcite precursor with a nonprecious metal; and
calcinating the hydrotalcite precursor impregnated or intercalated with the nonprecious metal at a temperature of 100 ~ 1000 to form a mixed metal oxide catalyst.

5. A method of decomposing nitrogen oxide using a mixed metal oxide catalyst, comprising the step of reacting nitrogen oxide including nitrogen oxides including N_2O , NO_x and a mixture thereof with a gas mixture including a reductant in the presence of a mixed metal oxide catalyst in which a hydrotalcite precursor containing an alkali metal is impregnated or intercalated with a nonprecious metal.

6. The method of decomposing nitrogen oxide using a mixed metal oxide catalyst according to claim 5, wherein the reductant is at least one selected from the group consisting of a hydrocarbon of 1 to 6 carbon atoms, an alcohol of 1 to 6 carbon atoms, SO_2 , NH_3 and CO .

7. The method of decomposing nitrogen oxide using a mixed metal oxide catalyst according to claim 5, wherein gas passes through the catalyst at a gas hour space velocity of $1,000\text{h}^{-1} \sim 200,000\text{h}^{-1}$, and a pressure of the gas is 1 atm or more.

15

8. The method of decomposing nitrogen oxide using a mixed metal oxide catalyst according to claim 5, wherein the reaction temperature is $150 \sim 500$.

9. The method of decomposing nitrogen oxide using a mixed metal oxide catalyst according to claim 5, wherein an amount of the nitrogen oxide is $0.001 \sim 31$ wt%, and an amount of the reductant is $0.001 \sim 21$ wt%.