The present application will be further illustrated with embodiments.

Table 1

Items	First polyvinyl alcohol	Viscosity of the first polyvinyl alcohol mPas	Second polyvinyl alcohol	Viscosity of the second polyvinyl alcohol mPas	Hydroxyethyl cellulose	First polyvinylpyrrolidone	Molecular weight of the first polyvinylpyrrolidone	Second polyvinylpyrrolidone	Molecular weight of the second polyvinylpyrrolidone	Sucrose	Trehalose	Sodium citrate	Sodium chloride	Sodium hydroxide
Embodiment 1	0.5	2.4	1.5	17.2	5.0	2.5	3500	7.0	210000	1.0	10.0	0.3	0.5	0.002
Embodiment 2	0.8	2.8	1.8	22.4	5.4	2.8	10000	7.5	350000	1.3	10.5	0.4	0.7	0.003
Embodiment 3	1.1	4.8	2.1	28.2	5.7	3.2	45000	8.0	600000	1.7	11.0	0.5	1.0	0.005
Embodiment 4	1.4	6.2	2.4	31.7	6.2	3.7	60000	8.5	800000	2.0	11.5	0.5	1.2	0.006
Embodiment 5	1.7	8.4	2.7	39.5	6.5	4.2	100000	9.0	1150000	2.3	12.0	0.6	1.5	0.007
Embodiment 6	2.0	10.5	3.1	41.2	6.8	4.5	120000	9.5	1300000	2.6	12.5	0.7	1.7	0.009

Embodiment 7	2.4	12.3	3.5	42.6	7	5	150000	10	1500000	3.0	13.0	0.8	2.0	0.010
Comparative example 1	0	-	2	23.5	5.0	2.5	3500	7.0	500000	1.0	10.0	0.3	0.5	0.002
Comparative example 2	2	2.4	0	-	5.0	2.5	3500	7.0	500000	1.0	10.0	0.3	0.5	0.002
Comparative example 3	0.5	2.4	1.5	23.5	5.0	0	-	9.5	500000	1.0	10.0	0.3	0.5	0.002
Comparative example 4	0.5	2.4	1.5	23.5	5.0	9.5	3500	0	-	1.0	10.0	0.3	0.5	0.002

Table 2

Items	Water addition of Group A	Water addition of Group B	Water content of the first dehydration %	Water content of following dehydration %	Duration of first dehydration min
Embodiment 1	15	12	3	1	192
Embodiment 2	25	20	5	1	221
Embodiment 3	35	28	7	1	203
Embodiment 4	45	36	9	2	205
Embodiment 5	55	44	11	2	211
Embodiment 6	65	52	13	2	218
Embodiment 7	75	60	15	2	224
Comparative example 1	75	60	15	3	217
Comparative example 2	75	60	15	3	202
Comparative example 3	75	60	15	3	209
Comparative example 4	75	60	15	3	196
Comparative example 5	75	60	15	-	473