

Uncoated fabric for manufacturing air bags

Akzo nv, Arnhem

* * *

Abstract:

Uncoated tightly woven synthetic filament yarn fabric for manufacturing an air bag. The fabric is manufactured from polyamide yarns having a filament linear density of 3.5-4.5 dtex. The air permeability of this fabric is $< 10 \text{ l/dm}^2 \cdot \text{min}$ and its specific stiffness is $< 1.0 \cdot 10^{-2}$.

This Sheet Has Been Replaced

