

G403320-3

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 18/08, 18/22, C08J 9/14		A1	(11) International Publication Number: WO 96/25443
			(43) International Publication Date: 22 August 1996 (22.08.96)
(21) International Application Number: PCT/US96/02063		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ, BY, KG, KZ, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 15 February 1996 (15.02.96)			
(30) Priority Data: 08/389,955 ✓ 17 February 1995 (17.02.95) US 08/498,276 ✓ 3 July 1995 (03.07.95) US			
(71) Applicant: ATLAS ROOFING CORPORATION [US/US]; 2322 Valley Road, Meridian, MS 39307 (US).			
(72) Inventors: BLANPIED, Robert, H.; 1114 64th Court, Meridian, MS 39305 (US). THORNSBERRY, James, D.; 2508 Willow Bend Drive, Meridian, MS 39301 (US).			
(74) Agent: BURNAM, H., Warren, Jr.; Nixon & Vanderhye P.C., 1100 North Glebe Road, Arlington, VA 22201-4714 (US).		Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(54) Title: METHOD OF PRODUCING RIGID FOAMS AND PRODUCTS PRODUCED THEREFROM			
(57) Abstract			
A thermosetting plastic foam solid is obtained using a blowing agent comprised at least partially from depolymerization of dicyclopentadiene into essentially pure cyclopentane. This unique hydrocarbon is miscible in polyester polyols, where others, such as extracted cyclopentane, are not. In a blend of 15 parts of liquid flame retardant per hundred parts polyester polyol, the mixture is both stable and has a suitably low viscosity.			