

05 JUN 2002

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
14 June 2001 (14.06.2001)

PCT

(10) International Publication Number
WO 01/42154 A1

- (51) International Patent Classification⁷: C03C 1/02, C03B 1/02 (74) Agent: HOLME PATENT A/S; Vesterbrogade 20, DK-1620 Copenhagen V (DK).
- (21) International Application Number: PCT/DK00/00672 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (22) International Filing Date: 6 December 2000 (06.12.2000)
- (25) Filing Language: Danish
- (26) Publication Language: English
- (30) Priority Data:
PA 1999 01742 6 December 1999 (06.12.1999) DK
- (71) Applicant (*for all designated States except US*): RGS90 [DK/DK]; Selinevej 4, DK-2300 Copenhagen S (DK).
- (72) Inventors; and
(75) Inventors/Applicants (*for US only*): JUUL, Martin [DK/DK]; Klintevænget 18, DK-4681 Herfølge (DK). FUNDAL, Erling [DK/DK]; Østergade 4, DK-4140 Borup (DK).
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— With international search report.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: METHOD FOR PRODUCING A GLASS AND GLASS PRODUCED THEREBY



162162



ACTION

WO 01/42154 A1

(57) Abstract: Glass produced on basis of a raw material in form of a mixture of mainly mineral-containing components comprising sludge from e.g. purification plants and waste products from the industry, and having a determined chemical composition adjusted on basis of knowledge of the chemical composition of the mineral-containing components forming part of the glass. The glass is produced from the raw material which after mineralization is pressed into briquettes that are hardened and subsequently melted in e.g. a blast furnace under oxygen supply, and where the melt is quenched and dried. Large amounts of waste products and waste substances that are normally deposited either treated or untreated can be reused and utilised at production of the glass.