CLAIMS

1. A primer composition comprising:

an alkoxysilane polymer comprising a unit derived from a silane-based monomer containing at least two amino or imino groups and a unit derived from a trialkoxysilane-based monomer;

an acrylic resin comprising at least one selected from units derived from non-functional acrylate monomers; and

an epoxy resin,

wherein the acrylic resin further comprises a unit derived from a functional acrylate monomer, and the functional acrylate monomer comprises a glycidyl group-containing acrylate monomer and a hydroxyl group-containing acrylate monomer in a weight ratio of 0.8:1 to 5:1,

wherein the weight average molecular weight of the acrylic resin is 100,000 to 200,000 g/mol and the viscosity of the acrylic resin measured at 25℃ using a Brookfield viscometer is 50 to 300 cPs.

2. The primer composition according to claim 1, wherein the alkoxysilane polymer comprises an alkoxysilane polymer obtained by reacting the trialkoxysilane-based monomer and the silane-based monomer containing at least two amino or imino groups in a weight ratio of greater than 1:1 and 5:1 or less.

3. The primer composition according to claim 1, wherein the epoxy resin comprises a bisphenol-based epoxy resin.

4. The primer composition according to claim 1, wherein the epoxy resin is comprised in an amount of 10 to 50 parts by weight based on 100 parts by weight of the alkoxysilane polymer.

5. The primer composition according to claim 1, further comprising at least one selected from the group consisting of a pigment, a solvent, a moisture absorbent, a dispersant, and a storage stabilizer.