

INSULATING PACKAGING

RELATED APPLICATION

[0001] The present patent application is a continuation-in-part of Application Serial No. 11/728,973 filed March 27, 2007 and which claims the benefit of the filing date under 35 U.S.C. §119(e) of Provisional U.S. Patent Application Serial No. 60/789,297, filed April 3, 2006. All of the foregoing applications are hereby incorporated by reference.

BACKGROUND

[0002] Consumers frequently purchase ready-made products, such as food and beverages, in containers. Thermally insulated containers may be designed for hot or cold liquids or foods, such as hot coffee, iced-tea, or pizza. These containers may maintain the temperature of the liquid or food contents by reducing heat or cold transfer from the contents to the consumer's hand.

BRIEF SUMMARY

[0003] A package, container, or container sleeve includes a side wall, the side wall having an inner surface and an outer surface. At least one of the inner surface or the outer surface of the side wall may include a layer of an insulating material.

[0004] Other systems, methods, features and advantages of the invention will be, or will become, apparent to one with skill in the art upon examination of the following figures and detailed description. It is intended that all such additional systems, methods, features and advantages be included within this description, be within the scope of the invention, and be protected by the following claims.

BRIEF DESCRIPTION OF THE DRAWINGS

[0005] FIG. 1 is a perspective view of a cup assembled with an outer wall.

[0006] FIG. 2 is a side cutaway view of a double wall cup.

[0007] FIG. 3 is a perspective view of an integrated container with channels.

[0008] FIG. 4 is a perspective view of an integrated container with channels.

[0009] FIG. 5 is a cross section view of a sleeve with a cup.

[0010] FIG. 6 is a top perspective view of a cross section of a cup assembled with an outer wall.

[0011] FIG. 7 is a view of a method of making a double wall cup.

[0012] FIG. 8 is a view of a cup with insulating material applied in a pattern.

[0013] FIG. 9 is a view of a cup with insulating material applied in a pattern.

[0014] FIG. 10 is a view of a cup with insulating material applied in a pattern.

[0015] FIG. 11 is a view of an outer wall disassembled from a cup.

[0016] FIG. 12 is a view of an outer wall disassembled from a cup.

[0017] FIG. 13 is a view of an outer wall disassembled from a cup.

[0018] FIG. 14 an outer wall disassembled from a cup.

[0019] FIG. 15 is a view of a cup assembled with a sleeve illustrating heat transfer.

[0020] Fig. 16 is a block diagram of an exemplary process for applying an insulating material to substrates.

[0021] Fig. 17 is a schematic of applying an insulating material to a substrate with spray nozzles.

[0022] Fig. 18 is a schematic of applying an insulating material to a substrate with non-spray nozzles.

DETAILED DESCRIPTION

[0023] A package, container, or container sleeve may be constructed of, and/or insulated with a insulating material. The insulating material may be fixed to a container or it may be applied to a removable sleeve. Insulating material, such as thermally-expandable and/or void containing material may be applied to the container or an outer wall or both. Insulating materials that are not expandable, or that are expanded in ways other than by temperature may also be used, for example, pressure sensitive materials, light sensitive materials, microwave sensitive materials and others. The insulating material may be expanded before reaching an end user, such as when the container and/or container sleeve are manufactured, and/or the insulating material may be expanded only on end use and only in response to, for example, temperature or pressure. The insulating

material may be used to aid with insulating capabilities of the container and/or container sleeve, and/or to add rigidity to the container and/or the container sleeve, such as to reduce a thickness of the material components of container and/or container sleeve.

[0024] FIG.1 illustrates a container **100**, such as a cup, with an inner wall **102** and an outer wall **104**. The blank for the outer wall **104** may be in the form of a container sleeve or a wall or body of a container **100**. The container is not limited to a cup and may be any other container, including but not limited to, a bulk coffee container, a soup tub, press-formed containers, plate, sleeve (e.g., single face corrugated, double face corrugated, uncorrugated, cardboard, etc.), folding cartons, trays, bowls, clamshells, and others with or without covers or sleeves. The container **100** may be a cylindrical cup or a container having other geometrical configurations, including conical, rectangular, etc. The outer wall **104** blank is not limited to a corrugated die cut blank, and may be constructed of any kind of paperboard, paper, foil, film, fabric, foam, plastic, and etc. The outer wall **104** may be made of any nominal paper stock, including but not limited to, natural single-face, white-topped single face, coated bleached top single-face, corrugate, fluted corrugate or any combination of these. The outer wall **104** may be removable from the container **100** or the outer wall **104** may be adhered to the container **100**. The outer wall **104** may be adhered, for example, by laminating the outer wall **104** blank onto the container, using a hot melt, cold melt and/or any other adhesive or sealing mechanisms. Alternatively or in addition, the outer wall **104** blank may be adhered with an insulating material. If the outer wall **104** is attached to the cup during manufacture, it may increase efficiency by eliminating an assembly step by the commercial end-user. Further, it may decrease the amount of storage space required by the commercial end-user, e.g., storing one item as opposed to two.

[0025] FIG. 1 is not necessarily drawn to scale. For example, the outer wall **104** may cover a larger or smaller portion of the container's **100** surface than illustrated. For example, the outer wall **104** may provide full body coverage. Increasing the surface area of the outer wall **104** may provide a larger insulated

area as well as a larger print surface. Although the drawing illustrates the outer wall **104** on a cup, the outer wall **104** may be added to any other containers, such as but not limited to, a bulk beverage container, press-formed container, and soup tub. Alternatively or additionally, the outer wall **104** may be added to a container sleeve.

[0026] Fig. 2 is a side cutaway view of a container **100**, which may be a double wall cup. The container **100** may provide a jacket of air **200** between an outer wall **104** and contents **206**, such as a hot or cold beverage or food, of the container **100**. The air jacket **200** may provide thermal insulation as measured by an outside surface temperature T_0 . The air jacket **200** may partially or completely surround the container **100**. When the container **100** is grabbed, a pressure exerted on the outer wall **104** may act to collapse the outer wall **104** at pressure points to reduce the air jacket **200** and potentially initiate contact with an inner wall **102** of the container **100**. The air jacket **200** may collapse under pressure points and may give a sense of low rigidity, and the contact may create hot spots on the outer wall **104**.

[0027] An insulating material **216** applied between the inner wall **102** and the outer wall **104** may reduce or eliminate this effect. If a sufficient amount of insulating material **216** is used, the insulating material **216** may act to provide rigidity without compromising the thermal insulation of the air jacket **200** to the outer wall **104** such that the outer wall **104** does not collapse, completely or partially. The insulating material **216** may add mechanical strength to the container **100**. Lighter weight materials may be used to produce the container **100** due to mechanical strength added by the insulating material **216**, such that the source of a substrate forming the container **100** may be reduced. The insulating material **216** may be applied in spots, such as dots, or another pattern, either on the inner wall **102**, the outer wall **104**, or both, such that the insulating material **216** defines an air gap **200** and prevents the outer wall **104** from collapsing onto the inner wall **102** under holding pressure. The insulating material **216** may also provide a rigid feel to the user, while allowing a reduction of a substrate material, for example the inner wall **102** or outer wall **104**.

[0028] The insulating material **216** may expand when activated, or may be pre-expanded, for example, by the inclusion of air or inert gas, in situ air voids, microspheres, expandable microspheres or other foaming agents. The insulating material **216** may be activated by, for example, temperature, pressure, moisture, or otherwise. In one example, the insulating material **216** may be thermally-activatable, by a hot or cold temperature. The insulating material **216** may be an expandable insulating material or adhesive. Additionally or alternatively, the insulating material **216** may include but is not limited to, binder, expandable microspheres or other micro-encapsulated particles, pigment and other additives, adhesives (e.g., hot melt, pressure sensitive), inert gas foamed hot melt, aqueous coating containing heat expandable microspheres, starch-based adhesives, natural polymer adhesives, PVC, foam coatings, biodegradable glues, or any combination of these or other materials. The insulating material **216** may include in-situ air voids, microspheres, microparticles, fibers, expandable fibers, dissolving particles, and etc. The insulating material **216** may be biodegradable, compostable, and/or recyclable.

[0029] The insulating material **216** may be expandable when wet or dry. The insulating material **216** may include any synthetic or natural material including aqueous based, solvent based, high solids, or 100% solid materials. The amount of solid content is typically 30% to 80% of the material, and more preferably 40% to 70%. Additional ingredients may be added to the binder and/or insulating material **216**, including but not limited to, pigments or dyes, fillers/extenders, surfactants for dispersion, thickeners or solvents to control viscosity for optimized application, foaming agents, defoaming agents, additives like waxes or slip aids, etc. Alternatively, the binder and/or insulating material **216** may be an adhesive. The insulating material **216** may have several properties, including but not limited to thermal insulation to keep container contents hot or cold, absorption of condensation and/or liquid, and/or it may expand on contact with hot material (such as, over 150 °F), and preferably remains inactive before a determined designed activation temperature, such as at about room temperatures. The insulating material **216** may be repulpable, recyclable, and/or biodegradable.

[0030] In a further example an inert gas, such as nitrogen gas, may be injected into the insulating material **216**. For example, an inert gas, such as nitrogen gas, may be injected into a hot-melt adhesive, starch-based adhesive, or natural polymer adhesive may be used. The gas may be applied onto the outer surface of the inner wall **102** before placing the outer wall **104** to give these materials foam structure, and therefore improve the mechanical and thermal insulation properties of the double wall container. The gas may be injected into the insulating material **216**, for example, before it is applied to the outer wall **104**, or during application to outer wall **104**.

[0031] Alternatively or additionally, the insulating material **216** may be a coating or adhesive that is combined with a blowing agent or foaming agent. The blowing or foaming agent may generate a gas upon heating which may activate the insulating material **216** to assume, for example, air voids, a cellular structure, or otherwise. Alternatively, the blowing or foaming agent may be a material that decomposes to release a gas under certain conditions such as temperature or pressure. Heating may occur during filling of the container with contents **206**, such as hot food or beverage. Alternatively, heating may occur from an external source – such as a microwave or water bath.

[0032] FIGS. 3 and 4 illustrate a container **100** with an outer wall **104**. The container **100** may be constructed as a double-wall cup assembly. The container **100** may be a cylindrical cup, container sleeve or container having other geometrical configurations, including conical, rectangular, etc. The outer wall **104** may fully or partially cover the body of the container **100**. The container **100** and outer wall **104** may be integrated into a double wall cup and the insulating material **216** and/or adhesive may be applied between the inner wall **102** and the outer wall **104**. The insulating material may additionally have adhesive properties and thus may form the only attachment between the container and the blank. The outer wall **104** may be made of any nominal paper stock, including but not limited to, natural single-face, white-topped single face, coated bleached top single-face or any combination of these. Alternatively or additionally, the outer wall **104** may be

made with foil, film, fabric, plastic, or other materials. The outer wall **104** and/or container may be repulpable, recyclable and/or biodegradable.

[0033] The outer wall **104** may include, for example, corrugated, flute (e.g., E-flute, F-flute, N-flute, or G-flute) uncorrugated or embossed air channels. The air channels may be in a vertical, diagonal, or other direction and may channel heat away from the hands. Additionally or alternatively, air channels may arise from the application of the insulating material **216**. For example, the insulating material **216** may be applied to the outer wall **104** in a striped, swirled, or dotted pattern such that air channels are formed or expanded before, during or after activation by, e.g., heat or pressure. The insulating material **216** may include blowing agents, foaming agents, and/or other agents that, upon activation, dissolve, generate gas, or disintegrate, and thus create air voids or foam structure.

[0034] The outer wall **104** may be removable from the container **100**, such as a sleeve, or the outer wall **104** may be adhered to the container **100**, such as in a double wall container. For example, a double wall container, such as a cup, or a double wall container sleeve may be manufactured by laminating the outer wall **104** onto the container or container sleeve blank, using an insulating material **216** (e.g., void containing, foamed, or other) to secure the insulating material **216**, or may be secured by any other adhesive or sealing method. If the outer wall **104** is permanently attached to the container **100** during manufacture (e.g., creating an integrated double wall cup or double wall sleeve), it may increase efficiency by eliminating an assembly step by the commercial end-user. Further, it may decrease the amount of storage space required by the commercial end-user, e.g., storing one item as opposed to two.

[0035] The outer wall **104** may be removable from the container. For example, a die cut blank, such as a sleeve, may be manufactured to be stored separately and removable from the container **100**.

[0036] The outer wall **104** may remain open ended on one side or on opposing sides, which may permit airflow. For example, in FIG. 3 the container may contain openings **302** near the top of the outer wall **104**. For example, in FIG. 4, the container may contain openings **402** near the top or bottom **404** of the outer

wall **104**. The opening may be formed into the outer wall **104**, for example as holes, and air channels may be created allowing air flow when the space between the inner wall **102** and the outer wall **104** is expanded by activation of the insulating material **216**. Airflow may be further manipulated, for example, upward and away from the holding fingers by corrugated, flute corrugated, or other air channels created by the interaction of the insulating material **216** and the outer wall **104** or expandable material application pattern **216**. For example, the pattern of application of the insulating material **216** may create air channels **304**, **402**.

[0037] FIG. 3 illustrates an alternate non-limiting example of how application of the insulating material **216** may form openings **302** near the top **306** of the container **100**. The channels may be formed by expansion of the insulating material **216**. There may be openings on opposing ends of the container **100**, such as at the top **306** and the bottom **308**. The openings may be formed by wrapping the outer wall **104** on the container without completing the seal at the top **306** or bottom **308**.

[0038] FIG. 5 illustrates a cross section of an outer wall **104**, such as a sleeve, assembled with the container **100**. This figure is meant to be illustrative and not limiting. The cup may be replaced with any container, for example, a press-formed tray, a soup tub, or a bulk beverage container. The outer wall **104** may have an inner face **506** and an outer face **504**. An insulating material **216** may be applied to the inner face **506**, the outer face **504**, and/or to a surface between **502** the inner face **506** and the outer face **504**, such as to an inner wall of the sleeve. The inner face **506** and outer face **504** do not necessarily contain a space **502** between.

[0039] A insulating material **216**, such as an expandable material, may be applied to an inner face **506** of the outer wall **104** in an inactive form. The inactivated insulating material **216** may be applied as a thin film that does not materially alter the thickness of the outer wall **104**. Applying the insulating material **216** to the inside of the outer wall **104** may also maintain the printability of the outer face of the outer wall **104**. If the inactivated insulating material **216**

on the outer wall **104** is assembled, for example, with a standard paper cup, it may maintain the slim profile of the cup. Maintenance of the slim profile may retain the efficient nesting qualities of a standard cup, allowing it to be efficiently cased, crated and shipped. Additionally, activation of the insulating material **216** at end use may create manufacturing efficiencies by reducing the activation or foaming or curing step during manufacturing of the container or sleeve and thereby also reducing energy used during manufacturing.

[0040] The insulating material **216** may be activated and thereby expanded by, for example, adding contents **206**, such as hot liquid, beverage or food into the container **100**. Alternatively or additionally, the container **100** may be prefilled with contents **206**, such as beverage or food and the insulating material **216** may be activated upon heating such as by microwave or water bath. Activation may occur only at the consumption stage and not at the processing stage of the outer wall **104**, such that the outer wall **104** may be shipped to the consumer with a substantially inactivated insulating material **216**. For example, the activation point of the insulating material **216** may be about 120 °F or higher and/or less than 60 °F, such that the insulating material **216** may be activated only by the temperature of hot (or cold) liquids, beverages, or food and not activated by ambient or body temperature. The activation may cause the expandable material to expand and “push back” the outer wall **104** from the container **100** creating an increased air gap. The air gap may create a thermal barrier between the hot beverage container **100** and the hand of the consumer. The activation may also enhance the stiffness and/or rigidity of the container, which may allow for a reduction in the material or thickness of the container wall. As described in more detail below, the insulating material **216** may also be activated, or at least partially activated, before reaching the consumer. Consequently, this ability of the insulating material **216** to respond to target temperature can make the container or sleeve “smart” in the sense that it can increase its insulation as the packaged content **206** gets hotter.

[0041] The insulating material **216** may be applied to the outer wall **104** in an unexpanded state. Expansion of the insulating material **216** may not occur until activated by adding hot fluid or solids, such as at the point of serving. This may

be different from expanding the material during manufacture of the outer wall **104**. Expansion during manufacture may increase the bulk of the outer wall **104**. The insulating material **216** may be controlled to effect nesting efficiency. The properties of the insulating material **216** may be further controlled by, for example but not limited to, combining a outer wall **104** constructed from fluted corrugate material with patterned application of insulating material **216** to provide specific insulation, air flow characteristics and container rigidity enhancement. For example, the corrugation and/or the pattern of insulating material **216** applied to the outer wall **104** may direct heat convection upward, and may therefore reduce heat transfer horizontally toward the holding hand of consumer. Alternatively, the insulating material **216** may be extruded into a sheet to which a pattern may be applied, such as by fluting, die-cutting shapes, lines, channels, or other markings into the sheet before attaching the sheet of insulating material **216** to an outer wall **104**. In other implementations, expansion may occur before shipping, such as before, during or after the manufacturing of the container **100**.

[0042] FIG. 6 is an exemplary top view of a cross-section of a container **100** assembled with an outer wall **104**. This figure is illustrative only and not limiting. The insulating material **216** may be applied to an outer wall **104**. For example, the insulating material **216** may be applied between the outer wall **104** and the wall of the container **100** and may form an integrated two-layer cup with thermally-activatable insulated expandable material in between, or between an outer wall **104** and an inner wall of a container sleeve. The insulating material **216** may include, for example, insitu air voids, or expandable microspheres or foaming agents **602** dispersed in a binder or any other suitable material disclosed above and may include an adhesive property.

[0043] FIG. 7 illustrates an exemplary method of applying the insulating material **216** to a container **100**. The method may be adapted to a cup wrapping machine. In this example, the insulating material **216** may be applied continuously or intermittently via an applicator **706** such as a nozzle, glue gun, or slot die applicator onto the outside of, e.g., a paper cup **100** which may be secured to a mandrel **702**. The pattern may be manipulated by movement of the container

100 relative to the applicator **706**. For example, the mandrel **702** may be spun and/or moved up or down or in another direction to achieve a desired pattern, e.g., spiral, dotted, lined, and etc.

[0044] Alternatively or additionally, the applicator **706** may move relative to the container **100** to achieve a desired pattern. For example, mandrels **702** may be arranged on a rotating arm **700**. Containers **100** such as cups may be loaded onto the mandrel **702** manually or by machine feed. The arm **700** may move the container **100** proximate to the applicator **706**. The applicator **706** may apply patterns of insulating material **216** to the container **100** by moving relative to the container **100**. The mandrel **702** may also move the container **100** relative to the applicator **706**, such as by rotation. As an example, stripes may be applied to the cup by side to side movement of the applicator **706** combined with rotational movement of the mandrel **702**. The spray from the applicator **706** may be constant or intermittent and may create broken lines, stripes, dots, or ellipses of foam. Swirls may be applied by constant spray from the applicator **706** combined with side movement and rotation of the mandrel **702**.

[0045] The applicator **706** may be attached to a line which may deliver the insulating material **216**. Gas, such as nitrogen gas, may be added to the insulating material **216** by a separate line and mixed in the applicator **706**, or during application, or in the applicator feed line, or otherwise.

[0046] After the insulating material **216** has been applied, the arm **700** may move the container **100** to a different position where the cup may be removed from the mandrel for further processing. For example, an integrated double wall container, such as a cup, may be formed by inserting the container **100** into an outer wall **104**. The outer wall **104** may be preformed and located in a cavity **704** into which the container **100** may be inserted.

[0047] FIG. 8 illustrates an exemplary outer wall **104** blank. This drawing is illustrative and not meant to be limited to a size or shape. The size and shape may be adapted to the dimensions of any container. An insulating material **216** may be applied to the outer wall **104**. The insulating material **216** may be applied by a number of methods, such as but not limited to, a nozzle spray gun, printing, a slot

coater, or other methods, such as those described above or in more detail below. Alternatively or additionally, the insulating material **216** may be extruded into a sheet and may be applied to a container, container sleeve, or die cut blank by laminating the sheet of insulating material to the blank of the container, container sleeve, or die cut blank. The insulating material **216** may be applied to the outer wall **104**, for example, on an in-line cup wrapping machine, in-line on a folder/gluer, or by other suitable methods, such as off-line coating and drying. The insulating material **216** may be applied to the outer wall **104** in any suitable pattern, such as but not limited to, banded, dotted, waved, squares, circles, diamonds, random, a combination of these or any other pattern. For example, the insulating material **216** may be applied in a pattern that manipulates air flow and/or conducts heat, for example, vertically upward away from the holding fingers. The insulating material **216** may be applied such that it forms channels, or expands to form channels on activation. The channels may direct natural convection. The insulating material **216** may fully or only partially cover the surface being coated.

[0048] The outer wall **104** may be removably or permanently attached to a container **100** or cup by, for example, wrapping the outer wall **104** around the container **100**. For example, a double wall cup or container **100** may be manufactured by laminating the outer wall **104** onto the container, using an insulating material **216** such as a starch based material, a hot melt and expandable material, an expandable material with adhesive properties, a combination of these or any other adhesive or sealing method. If the outer wall **104** is permanently attached to the container **100** during manufacture (for example, creating an integrated double wall cup), it may increase the efficiency of using an outer wall **104** by eliminating an assembly step by the commercial end-user. Further, it may decrease the amount of storage space required by the commercial end-user (storing one item as opposed to two). The shape of the outer wall **104** in the drawing is not meant to be limiting. The shape of the outer wall **104** may be adapted to the shape of other containers, for example but not limited to, a container sleeve, a soup tub,

press-formed container, or bulk beverage containers. Alternatively the container **100** may be a container sleeve that is open on both ends.

[0049] The outer wall **104** may, optionally, contain in-seam hot-melt or cold-set glue. If the insulating material **216** is also an adhesive, the in-seam hot-melt or cold-set may be omitted. The in-seam hot-melt/cold-set glue may be used in addition to the insulating material **216**, such as, for bonding reinforcement. The outer wall **104** may be applied to a container **100**, such as a cup or sleeve by, for example, wrapping, laminating, or other manufacturing processes.

[0050] FIGS. 8 through 12 illustrate many examples of an outer wall **104**. These examples are merely illustrative and not limiting. FIG. 8 illustrates outer wall **104** with insulating material **216** applied in a pattern **809** to channel the release of heat. The insulating material **216** may be made of, for example, corrugated paper, such as but not limited to fluted corrugate. Convection may be manipulated by corrugation, the pattern of application of the insulating material **216**, or in another suitable manner.

[0051] FIGS. 9 through 10 illustrate other possible, non-limiting examples of potential patterns of insulating material **216**. The patterns of insulating material **216** are represented by numbers **909** and **1009**, respectively. The insulating material **216** may be applied in patterns other than those illustrated in FIGS. 8-10. The insulating material **216**, may vary in thickness and may provide graduated flow to channel heat to openings.

[0052] FIGS. 11-14 illustrate patterns of openings that may be used to allow air flow. Openings are represented by numbers **1112**, **1212**, **1312**, and **1412**, respectively. Openings may also be located and/or include shapes such as illustrated by numbers **1214**, **1314**, and **1414**. There may be die cut openings at opposing ends of the blank, or only at one end. The shapes of the openings in Figs. 11-14 are illustrative only and not limiting. For example, the patterns of insulating material **216** and the shape of the openings may be so arranged as to manipulate air flow, for example but not limited to, creating a Venturi effect.

[0053] FIG. 15 is an illustrative example showing exemplary heat transfer. This example is not meant to be limiting, but merely illustrative of possible heat

loss manipulation. Total heat loss of the system may be represented by the following equation:

$$Q^T \text{ [Cal./second]} = Q_1 + Q_2 + Q_3 + Q_4$$


Where Q^T is the total heat loss. Q_1 **1504** may be the heat loss due to water evaporation. Q_2 , Q_3 , and Q_4 , represented by **1502**, **1506**, and **1508**, respectively, may represent the convectonal and conductional heat loss.

[0054] The objective of keeping contents hot may be achieved by minimizing Q^T . The outer wall **104** may minimize Q^T by minimizing Q_2 , Q_3 , and Q_4 . The low thermal conductivity of the insulating material may result in much lower heat loss due to Q_2 , Q_3 , and Q_4 .

[0055] The objective of preventing consumer flesh burns may be achieved by, for example, minimizing Q_2 , Q_3 , and Q_4 , especially Q_2 , Q_3 , while allowing Q_1 and Q_4 to channel the unavoidable high heat flux (due to the hot liquid) vertically up or down. This may be achieved by, for example, adding corrugated grooves to the outer wall **104**. The grooves may be, for example, in a generally vertical or diagonally tilted.

[0056] Non-limiting examples follow.

[0057] Example 1. Example 1 provides a graphical representation of how the insulating material **216** may alter thermal conductivity. The temperature on the inside of a cup may be represented by T_i . The temperature on the outside of the cup may be represented by T_o . The top line, X, may represent a container without the coated outer wall **104**. The second line, Y, may represent a container assembled with a coated outer wall **104**. This example may illustrate that, in a container without an outer wall **104** coated with the insulating material **216**, the difference in the temperature inside versus the outside of the container may be very small. In a container with a outer wall **104** coated with the insulating material **216**, the difference in the temperature between inside and outside may be small when the hot food or beverage is added to the container. However, the food or beverage may activate the material, A, on contact, causing the material to expand. When the material expands, the difference in temperature $T_i - T_o$, may increase.



[0058] Example 2. Example 2 illustrates temperature sensory comparison of various outer wall **104** materials coated with the insulating material **216** compared to without the insulating material **216**. The following experiment is for illustration only and is not limiting, other experimental results might be obtained.

[0059] An insulating material **216**, such as a thermally, or other, expandable material may be applied to outer wall **104** blanks made of various materials, such as but not limited to paper, paperboard, and fluted corrugated paper. Each outer wall **104** blank may be wrapped around a container, such as a cup. The cup may be filled with hot water. The cups may then be handled with bare hands and a comparison made between the sensory responses to the two conditions. In each test, the cups with coated outer wall **104** were less “hot” to the touch than those with uncoated outer wall **104**. Expansion occurred within a few minutes of pouring hot water into the cup.

[0060] Example 3. Coatings of insulating material **216** may be applied to a single face medium. The coating may be expanded when wet using a MASTER-MITE 120 V, 475 W heat gun at 600 degrees F.

[0061] Example 4. Coatings of insulating material **216** may be applied to the outside of a 12 Oz cup and allowed to air-dry overnight. The next day, 190 degree F hot water may be poured into the cup. Noticeable expansion may be observed shortly after filling the 190 degree F hot water into the cup. Lids may be placed on the cup, and after 7 minutes more expansion may be observed, but still partial

expansion. A benefit of post-heat activation may be that the hotter the liquid the more the coating expands.


[0062] Example 5. A coating of an insulating material **216** was applied to a cup. A 250 W IR heater manufactured by Fisher Scientific model no. 11-504-50 may be used to heat the insulating material **216**. Expansion may be slow when the lamp is six inches away from the insulating material **216** and immediate when one inch away from the insulating material **216**.

[0063] Example 6. Coatings of insulating material **216** may be applied to paper, which may then be wrapped around a paper cup after the coating is allowed to air dry. Heat from a heat gun may be used to heat the part of the insulating material **216** coating indirectly through the paper shell for one minute. The coating expanded. Another part of the unheated insulating material **216** coating may be heated under an IR lamp through the paper. The insulating material **216** coating expanded.

[0064] Example 7. An insulating material **216**, such as a heat expandable coating, may be applied within the walls of a double wall sleeve or container, such as a cup. During manufacture, the insulating material **216** may be adequately dried but not expanded, or not fully expanded. When the sleeve or container is exposed to high temperature, such as the temperature of coffee or soup, the insulating material **216** may expand pushing the walls of the double wall sleeve or container away from each other. This expansion through activation may “smartly” increase the air voids in the insulating material **216** as well as the insulation and rigidity of the package. The following details an experiment illustrating how use of the insulating material **216** decreases a weight of a material used in the manufacture of a container or container sleeve. Although the experiment employs a limited set of materials, they demonstrate the feasibility and benefits of the insulating material **216**.

[0065] Two samples were compared. The reference container was a 16 ounce disposable cup with a 16pt outer wrap. The experimental container was a 16 ounce disposable cup with a pattern of insulating material **216**, in this case a foam coating, and a 12pt outer wrap. Both cups were filled with 190F water. The

insulating material **216** of the experimental container expanded upon addition of the 190F water. The outer surface temperature of each cup was measured and plotted below. The experimental cup displayed improved insulating properties during the first few minutes of the experiment.




[0066] A second trial illustrated the use of container sleeves. The reference container sleeve was an N-flute single face sleeve. The experimental container sleeve was an N-flute single face sleeve with an inside layer of insulating material **216**, in this case, foam coating. A layer of kraft paper was laminated over the layer of insulating material **216** and the material was dried, but not expanded. The insulating material **216** was applied in two patterns: full coverage and lines running from the top to the bottom of the sleeve. To summarize, there were five formats of container sleeves tested:

- N-flute single face sleeve with inner layer of kraft paper
- N-flute single face sleeve with inner layer of dried non-expanded heat activatable aqueous coating (“AP”) and an inner layer of kraft paper
- N-flute single face sleeve with inner layer of expanded heat activatable aqueous coating and no layer of kraft paper

- N-flute single face sleeve with inner layer of expanded heat activatable aqueous coating arranged in vertical lines and inner layer of kraft paper
- N-flute single face sleeve with a full coverage inner layer of expanded heat activatable aqueous coating and inner layer of kraft paper

[0067] The sleeves were applied to a 16oz disposable cup which was filled with 190F water. After filling, the temperature of the outside of the cup was tested at one minute intervals for 5 minutes. The results are charted below.



[0068] The cups and sleeves containing the foam coatings also had higher rigidity, even at a reduced paper stock. The patterned foamed coating prevented even the 12pt outer wrap from collapsing into the inner wall during handling. This may allow the use of lower basis weight and caliper paper board while maintaining good insulation.

[0069] Fig. 16 is a block diagram of an exemplary process for applying a micro-particle coating to substrates. The process may include applying a microsphere or other expandable coating to any of a substrate, die cut blank, container, sleeve, catering trays, double-wall cups, press-formed tray, soup tub and bag-in-the box containers. The process may include inline **1600** and off-line **1610** procedures. The inline procedure **1600** may include stacking stations **1620**,

manufacturing stations **1630**, and packaging stations **1640** used for the manufacturing of the container from paper or die cut stock. The stacking, manufacturing and packaging stations may be completely automated and/or include manual stations.

[0070] Coating application processes may occur in-line **1600** or offline **1610**, at the same or another facility. In-line application may include the application of the insulating material **216** at one or more of the stacking stations **1620**, manufacturing stations **1630**, and packaging stations **1640**. The insulating material **216** may be applied in various ways, including but not limited to brushes, sponges, printing, a nozzle, spray, a slot die coater, or by lamination to an extruded sheet of coating. Any of these applications, or various combinations of them, may occur in-line **1600** or offline **1610**, where the off-line process may occur before the stacking stage **1620**.

[0071] Application with a brush or brushes may occur by feeding the insulating material with pressure through a tube to the brush. The brush may be manufactured from different materials such as horse hair or synthetic materials. The brush may include hollow filaments such that the insulating material is applied through the filaments. The brush may apply a swatch or pattern of the insulating material. The amount of insulating material to the brush may be controlled such that the amount of insulating material applied to the substrate may be metered. As an illustrative and not limiting example, the amount may be controlled such that a 1/64th inch layer of insulating material is applied, which may expand to 1/16 or 1/32 of an inch, or the distance of the gap between an inner and outer layer of a double-wall cup. It may be preferable that the insulating material does not deform a shape of the outer layer once expanded. The insulating material **216** may be distributed in a uniform or varying pattern. The brush may be used for broader applications, such as to coat the inside of a bag-in-the-box container.

[0072] Application with a printing press may occur by running substrates through rollers. The substrates may be roll or web form of paper stock, or alternatively in sheet form. The insulating material **216** may be press applied in spots or patterns or with full coverage, depending on an implementation.

[0073] In Fig. 17, spray nozzles **1700** may be used to apply a insulating material **216** to a substrate **1720**. The nozzles may diffuse the insulating material to apply a thin, uniform layers of the insulating material **216** on the substrate. One or more spray nozzles may be used to form continuous or interrupted patterns of the insulating material **216**. The nozzles may be arranged such that the applied insulating materials **216** overlap, are side-by-side and/or are separated by a space. The spray may be metered to control a thickness of the applied insulating material **216**. The nozzle may also be positioned to direct spray of the insulating material **216** onto designated portions of the substrate, such as at a corner.

[0074] In Fig. 18, non-spray nozzles **1800** may be used to apply a stream **1810** of insulating material **216** to the substrate **1820**. The stream may be metered through the nozzle to apply a precise amount. The nozzle may be sized to control a specified width and height of the stream **1810**. Flow from the nozzles may be turned on and off to accommodate a specified pattern of the insulating material **216** to the substrate.

[0075] In a trough or a dip insulating material **216** application, substrates may be moved through the trough that contains insulating material **216**. One or both sides of the substrate may be run through the trough. A thickness of the insulating material **216** being applied to the trough may be controlled by how long the substrate sits in the material. A temperature of the insulating material **216** and substrate may be controlled to activate or not activate the expandable insulating material **216** during the application process. A control blade may be used to meter off excess insulating material **216**. The substrates may be belt fed though the through or individually held in the through.

[0076] With any of the above application processes, and with any other process, the applied insulating material **216** may be dried or set , such as by applying or blowing cool air or warm air without activating the insulating material **216**, if it is desired to expand the insulating material **216** in a later process, such as during manufacturing or at the time of consumer use. The insulating material **216** may also be expanded after manufacturing and before consumer use, such as at the

stacking station. The insulating material **216** may be expanded before or after stacking the containers.

[0077] Coated or uncoated blanks may be fed to the stacking station. The insulating material **216** may be applied during in-line or off-line processing. If applied in-line, the insulating material **216** may be allowed to dry before the cups, sleeves, containers, etc. are formed, or they may be formed while the insulating material **216** is wet. Depending on the properties of the insulating material **216**, it may take a couple of seconds to several minutes to dry. The insulating material **216** may be activated during the in-line manufacturing or afterwards, such as at the consumer stage. To activate the insulating material **216** in-line, any or all of infrared (IR), air, convection or conductive heating methods may be used. The insulating material **216** may take a couple of seconds to several minutes to fully expand. For example, a mandrel, which holds a container from the inside of the container, and/or a collar, which holds a cup from the outside of the container, may be used to apply heat to expand the insulating material **216** during the container manufacturing process. If a wet or partially dry insulating material **216** contacts the mandrel during process, the mandrel may be manufactured to include a non-stick material, such as TEFLON to prevent sticking or transfer of the insulating material **216** onto the mandrel. Lower activation temperatures may be preferred if the activation occurs in-line. By activating the insulating material **216**, the insulating material **216** expands to form a reinforced air gap. The insulating material **216** may be partially expanded during manufacturing of the container, and then the expansion may continue to the consumption stage.

[0078] As mentioned, use of the insulating material **216** may help to reduce the thickness of substrate needed to make the container, sleeves, etc., while maintaining a better rigid feel to the consumer. The insulating material **216** may also improve insulation properties of the container, and to help keep the beverages or foods warm or cold longer, depending on the application. The substrates may be made of natural fibers, synthetic or both, such as SBS (solid bleached sulfate) paper board or box board. A sleeve materials, such as liner and medium, may be produced of 15LB/3000ft² to 100LB/3000ft² material, and preferably

18LB/3000ft² to 50LB/3000ft². The caliper of the paper substrate for hot or cold cups, soup tub, press-formed container and other non-corrugated containers may range from 9 point to 24 point, and preferably 10 point to 24 point, where a point is equal to 1/1000 inch.

[0079] While various embodiments of the invention have been described, it will be apparent to those of ordinary skill in the art that many more embodiments and implementations are possible that are within the scope of the invention.

WE CLAIM:

1. A double-wall container, comprising:
 - an inner wall;
 - an outer wall attached to the inner wall, where the inner wall and the outer wall form an air gap therebetween;
 - and insulating material positioned between the inner wall and the outer wall;
 - wherein the foam creates air channels.
2. The double-wall container of claim 1 where the insulating material comprises in situ air voids.
3. The double-wall container of claim 1 where the insulating material is foamed with nitrogen gas.
4. The double-wall container of claim 1 where the insulating material is foamed with expandable microspheres.
5. The double-wall container of claim 1 where the insulating material is a starch based foam.
6. The double-wall container of claim 5 where the starch based foam is foamed with nitrogen gas.
7. The double-wall container of claim 4 where the expandable insulating material accommodates a reduction in a weight of the paper stock.
8. The double-wall container of claim 1 where the insulating material is activated to expand by a hot temperature.
9. The double-wall container of claim 1 where the insulating material is applied is a striped pattern.
10. A method of making a double-wall container, comprising:
 - providing a first substrate to form an inner wall of a container;
 - providing a second substrate to form an outer wall of the container;
 - providing an applicator to apply insulating material to the container;
 - moving the container into alignment with the applicator;

applying an insulating material to the inner wall of the first substrate; and

attaching the second substrate to the container to form the outer wall.

11. The method of claim 10 where the insulating material is applied in a pattern.
12. The method of claim 11 where the pattern is applied by movement of the applicator relative to the container.
13. The method of claim 11 where the pattern is applied by movement of the mandrel relative to the applicator.
14. The method of claim 11 wherein the pattern is applied by intermittent applications from the applicator.
15. The method of claim 14 where the insulating material is applied is a lined pattern.
16. The method of claim 14 where the insulating material is applied to an outer surface of the inner wall of the first substrate.
17. A sleeve, comprising:
 - a blank having an inner surface and an outer surface;
 - an insulating material applied to at least one of the inner surface or outer surface of the blank,
 - where the insulating material forms channels.
18. The container of claim 17, where the insulating material comprises a starch based foam.
19. The container of claim 17 where the insulating material comprises in situ air voids.
20. The container of claim 18 where the starch based material is foamed with nitrogen gas.
21. The container of claim 17 where the material is expanded upon manufacturing.
22. The container of claim 17 where the material is expanded by a hot beverage or food.

23. The container of claim 17 where the expandable material is thermally expandable.