

(19) World Intellectual Property Organization
International Bureau



PCT



(43) International Publication Date
28 September 2006 (28.09.2006)

(10) International Publication Number
WO 2006/101927 A3

(51) International Patent Classification:

D01F 6/30 (2006.01) **C08F 295/00** (2006.01)
C08F 297/08 (2006.01) **C08F 4/646** (2006.01)

77566 (US). **PENG, Hong** [US/US]; 420 GARLAND DRIVE, Apt. 1403, Lake Jack, Texas 77566 (US).

(21) International Application Number:

PCT/US2006/009405

(74) Agents: **BAI, J., Benjamin** et al.; JONES DAY, 717 TEXAS, Suite 3300, Houston, Texas 77002 (US).

(22) International Filing Date: 15 March 2006 (15.03.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

PCTUS22000/008917
17 March 2005 (17.03.2005) US
60/717,863 16 September 2005 (16.09.2005) US

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(71) Applicant (*for all designated States except US*): **DOW GLOBAL TECHNOLOGIES INC.** [US/US]; WASHINGTON STREET, 1790 Building, Midland, Michigan 48674 (US).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **POON, Benjamin, C.** [US/US]; 6520 Broadway, Pearland, Texas 77581 (US). **CHEUNG, Yunwa, Wilson** [US/US]; 104 Rosemary Lane, Lake Jackson, Texas 77566 (US). **LAI, Shih-Yaw** [US/US]; 3602 Abbeywood Drive, Pearland, Texas 77584 (US). **SEN, Ashish** [US/US]; 215 Canyon Oak Drive, Lake Jackson, Texas 77566 (US). **CHEN, Hongyu** [CN/US]; 146 India Warrior Trail, Lake Jackson, Texas 77566 (US). **CHIU, Yeun-Yuen, D.** [US/US]; 2422 Devonshire Drive, Pearland, Texas 77584 (US). **PATEL, Rajen, M.** [US/US]; 114 Scarlet Oak Street, Lake Jackson, Texas 77566 (US). **CHANG, Andy, C.** [US/US]; 2301 Norfolk St., #3, Houston, Texas 77098 (US). **DOUFAS, Antonios, K.** [GR/US]; 167 India Warrior Trail, Lake Jackson, Texas

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:

7 June 2007

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: FIBERS MADE FROM COPOLYMERS OF PROPYLENE/ALPHA-OLEFINS

(57) Abstract: A fiber is obtainable from or comprises a propylene/ α -olefin interpolymer characterized by an elastic recovery, Re, in percent at 300 percent strain and 1 cycle and a density, d, in grams/cubic centimeter, wherein the elastic recovery and the density satisfy the following relationship: $Re > 1481 - 1629(d)$. Such interpolymer can also be characterized by other properties. The fibers made therefrom have a relatively high elastic recovery and a relatively low coefficient of friction. The fibers can be cross-linked, if desired. Woven or non-woven fabrics can be made from such fibers.

WO 2006/101927 A3