

Description

The invention pertains to a method of and apparatus for autogenously (ie, without adhesives) laminating plural layers or laminae of sheet material together, at least one layer of which is thermoplastic film or web or non-woven or the like, according to the preambles of the independent claims. It is, however, not intended to thereby limit the invention to precluding adhesive augmentation of such autogenous laminating.

Laminated Sheet Material And Methods of Making Such Material are disclosed in US-A-3 530 023, upon which the preambles of the independent claims are based. As disclosed, such material comprises at least two adjacent layers of cellulosic fiber sheet material, and a layer of thermoplastic material which layers are secured together at a plurality of bonding areas by heat and pressure without the addition of any adhesive material. This patent states that such bonding may be achieved by forwarding the layers through a nip between two rolls which rolls are arranged to maintain a fixed spacial relationship relative to each other. As further disclosed, one of the rolls may be smooth surfaced with the other having spaced projections extending outwardly from its cylindrical surface; or both rolls may have such projections. Bonding areas of a size of from about 0.0005 to about 0.002 square inches (from about 0.003 to about 0.013 square centimeters) are said to be preferred.

A non-woven structure, method and apparatus for producing non-wovens is disclosed in US-A-4 035 219. In this apparatus as disclosed, a thermoplastic non-woven is first formed as by extruding the thermoplastic from a spinneret; and then passing the filamentary mass through bonding means. In the bonding means, a bonding member such as a roll is provided which has projections on it; the bonding member is heated to a temperature below the softening point of the thermoplastic to be bonded, and the bonding member is pressure biased towards a backing member such as a roll; and the material to be bonded is passed therebetween. For example, through the nip between a pair of pressure biased nip rollers: a heated pattern roller having projections; and a backing roller. Bonding is said to be effected by virtue of the work done by the pressure biased, heated projections to compress the material. Projections having areas of from about 0.00001 to about 0.0005 square inches (from about 0.00006 to about 0.003 square centimeters) are stated to be preferred albeit projections having areas of up to about 0.001 square inches (about 0.006 square centimeters) are claimed.

While prior art laminating apparatuses and methods for laminating web materials together have addressed some of the problems of achieving such lamination in the absence of adhesives, they have not addressed the problems to the extent of or in the manner of the present invention. For example, and without intending to thereby limit the scope of the present invention, providing an apparatus wherein laminating is achieved through the use of pressure biased laminating rolls which are operated with a predetermined surface velocity differential between them as provided by one aspect of the present invention; and providing an apparatus having heated, velocity matched laminating members having pattern elements having areas of greater than 0.002 square inches (about 0.013 square centimetres) which apparatus is particularly useful at intermediate and high level velocities as is provided by another aspect of the present invention.

The invention provides, in one aspect, a method of dynamically bonding plural laminae together, at least one of which laminae comprises thermoplastic material, comprising the steps of forwarding said laminae with portions thereof in face to face relation, through a pressure biased nip between a relief patterned nip defining member having pattern element segments, and a nip defining anvil member, said nip defining members being biased towards each other with a predetermined pattern-element loading; wherein the method comprises driving said nip defining members to provide a predetermined surface velocity differential therebetween, in the range of from 2 to 40 percent of the surface velocity of said nip defining member having the lower surface velocity.

Preferably, the nip defining anvil member is smooth surfaced; and is operated at a surface velocity that is greater than the surface velocity of the patterned nip defining member. More preferably, the surface velocity differential is in the range of from about 2 to about 20 percent.

In another aspect of the invention, an apparatus is provided for carrying out the above method of dynamically bonding plural laminae together said apparatus comprising a relief patterned nip defining member and a nip defining anvil member, means for mounting said nip defining members to define a nip therebetween through which nip said laminae may be forwarded with portions thereof in face to face relation, means for controllably biasing said nip defining members towards each other, and means for driving said nip defining members

characterised in that said driving means is adapted to provide differential surface velocities within a range of from 2 to 40 percent of the surface velocity of said nip defining member having the lower surface velocity.

The method may further comprise the step of heating each of the nip defining members to a surface temperature that is a predetermined number of degrees below the melt temperature of the thermoplastic lamina disposed closest to it as the laminae are forwarded through the nip between the nip defining members.

5 Preferably, the apparatus further comprises means for independently heating the nip defining members so that the surface temperature of each is within a predetermined range below the melt temperature of whichever lamina of the laminae that comprises thermoplastic material is disposed closest to each respective nip defining member as the laminae are forwarded through the nip defined by the nip defining members.

10 A method of operating the above apparatus for dynamically bonding plural laminae together is also provided which assures bonds of high structural integrity in the absence of tearing and the like while assuring longevity of the pattern elements of its patterned nip defining member. Essentially this method entails operating one of the nip defining members at a predetermined velocity, e.g. a predetermined line speed in a converting apparatus. The velocity of the other nip defining member and the level of pressure
15 biasing of the nip defining members towards each other is then adjusted to determine an operating point (i.e. a desired line velocity at a given velocity differential between the nip defining members and at a given level of nip pressure biasing) at which satisfactory autogenous bonding can be achieved at a level of nip pressuring biasing substantially lower than would be required in the absence of a velocity differential between the nip defining members. Preferably, the operating point for each line speed will be at a
20 sufficiently high differential velocity to enable operating at a non-deleterious level of nip biasing pressure to achieve satisfactory bonding, i.e. strong bonding in the absence of a deleterious tearing or perforating of the laminae. However, at intermediate and high line velocities, operating points may be realized at zero velocity differential, i.e. with the nip defining members having equal surface velocities. Generally speaking, non-deleterious levels of nip biasing pressures are pressures below the yield strength of the pattern elements of patterned nip defining members and the like. Such biasing levels assure substantial useful life of the
25 patterns elements disposed on the patterned nip defining member.

While the specification concludes with claims which particularly point out and distinctly claim the subject matter regarded as forming the present invention, it is believed that the invention will be better understood from the following description taken in conjunction with the accompanying drawings in which:

30 Figure 1 is a fragmentary, somewhat schematic side elevational view of an exemplary apparatus embodiment of the present invention.

Figure 2 is a perspective view of the patterned cylinder of the bonding apparatus shown in Figure 1.

Figure 3 is an enlarged scale, fragmentary view looking radially inwardly toward a pattern element - a bonding lug - which is disposed on the cylindrical surface of the patterned cylinder shown in Figure 2.

35 Figure 4 is a fragmentary sectional view taken along section line 4-4 of Figure 3.

Figure 5 is an enlarged scale, fragmentary plan view of two laminae having overlapping edge portions bonded together through the use of the present invention.

Figure 6 is a somewhat schematic, fragmentary sectional view taken along section line 6-6 of Figure 5.

40 Figure 7 is an enlarged scale, fragmentary plan view that is similar to Figure 5 but wherein a different pattern of bonds is shown for lap bonding edge portions of two laminae together through the use of the present invention.

A somewhat schematic, fragmentary side elevational view of a dynamic mechanical bonding apparatus 20 which is an embodiment of the present invention is shown in Figure 1. Apparatus 20 comprises: patterned cylinder 22; anvil cylinder 24; means 26 for adjustably biasing cylinders 22 and 24 towards each
45 other with a predetermined pressure within a predetermined range of pressures; means 28 and 29 for rotating cylinders 22 and 24, respectively, at independently controlled velocities to provide a predetermined surface velocity differential therebetween; temperature control means 30a and 30b for independently heating cylinders 22 and 24, respectively, to provide predetermined surface temperatures thereon; and rolls 31 through 38. Laminae 41 and 42, and laminate 45 are also shown in Figure 1. Additionally, apparatus 20
50 comprises a frame, not shown; and means, not shown, for driving roll 31 through 38 for controllably forwarding laminae 41 and 42 through the nip 43 defined between cylinder 22 and cylinder 24, and for enabling forwarding the resulting laminate --laminate 45--to downstream apparatus such as a roll winder or web converting apparatus: for example, a disposable diaper converter.

For clarity of the present invention, neither the upstream ends or sources of laminae 41 and 42, nor the
55 downstream destination or user of laminate 45 are shown. However, for example, it is well known to provide laminae of thermoplastic films, and paper and other webs in roll form; and to provide upstream unwinding

and splicing means to enable forwarding continuous lengths of such laminae through laminating means and or converters to make products comprising laminated and/or other web elements at controlled velocities and under controlled tension.

5 Parenthetically, for simplicity and clarity of the invention, apparatus 20 is described herein as comprising cylinders 22 and 24. However, cylinders are but exemplary nip defining members as stated hereinbefore. Accordingly, it is not intended to thereby limit the invention to apparatus comprising cylinders per se. In the same vein, use of the term pattern element is not intended to limit the invention to bonding patterns consisting of only discrete, spaced pattern elements to the exclusion of other patterns: eg, reticulated patterns or patterns comprising continuous or elongate lines of bonding.

10 Briefly, referring to apparatus 20, Figure 1 the present invention enables thermolaminating certain laminae together --providing at least one of the laminae comprises sufficient thermoplastic material that is susceptible to being thermobonded to the other laminae -- by forwarding the laminae together through a pressure biased nip between a patterned cylinder and an anvil cylinder which cylinders have a predetermined surface velocity difference between them. Such laminating can be effected at substantially lower nip biasing pressure (ie, substantially lower psi loadings on the pattern elements of the patterned cylinder) than 15 if the cylinders are operated at equal surface velocities. Directionally, the greater the surface velocity differential, the lower the required nip biasing pressure. However, too great a surface velocity differential may precipitate tearing of the laminae, or the formation of unwanted holes or perforations therein so should preferably be avoided. Additionally, such laminating may be effected with even lower nip biasing pressure if 20 one or both of the cylinders is heated: preferably to temperatures which are sufficiently lower than the melting points of the laminae that the laminae will not melt or stick to the laminating cylinders in the event, for example, the apparatus is temporarily stopped.

Referring now to Figure 2, patterned cylinder 22 is configured to have a circular cylindrical surface 52, and a plurality of protuberances or or pattern elements 51 which extend outwardly from surface 52. The 25 protuberances are disposed in a predetermined pattern: each pattern element being configured and disposed to precipitate a bond site in the laminate being produced to effect a predetermined pattern of bond sites in the laminate. As shown in Figure 2, cylinder 22 has a saw-tooth shape pattern of protuberances 51 which extend circumferentially about each end of the cylinder. Such a cylinder is configured, for example, to laminate or lap-seam together a relatively narrow perforated web to each 30 machine direction side edge of an imperforate web or thermoplastic film to form a backsheet for a disposable diaper having breathable side edges. Fragmentary side edge portions of exemplary such lap-seamed laminates comprising laminae having overlapping side edges are illustrated in Figures 5, 6 and 7 albeit neither lamina is shown to be perforated in those figures. In an exemplary embodiment of the invention, cylinder 22 is steel, and has a diameter of about 11.4 inches (about 29 cm.).

35 Anvil cylinder 24, Figure 1, is preferably a smooth surfaced, right circular cylinder of steel. In an exemplary embodiment of the invention, anvil cylinder 24 has a 4.5 inch (about 11.4 cm.) diameter, and is independently power rotated by a speed controlled direct current motor.

Means 26, Figure 1, for biasing patterned cylinder 22 towards anvil cylinder 24 comprises pressure regulating means 55, and pneumatic actuator means 56. Pressure regulating means 55 is adapted to have 40 its inlet connected to a supply source P of pressurized air, and to have its outlet connected to pneumatic actuator means 56 in order to adjust and control the pneumatic actuator means loading of cylinders 22 and 24 towards each other. Whereas only one pneumatic actuator or means 56 is visible in Figure 1, identical actuators are in fact connected to each end journal of the cylinder; and, of course, each end journal is supported by frame members and ancillary hardware (not shown) to be vertically moveable so that, in fact, 45 the pressure biasing means can be effective.

50 Drive means 28, and drive means 29, Figure 1, are provided to independently drive cylinders 22 and 24, respectively. Thus, they constitute means for power rotating the cylinders so that there is a predetermined but adjustable relationship between their surface velocities. This can be synchronous, or asynchronous: equal surface velocities; or with a predetermined surface velocity differential with either cylinder being driven faster than the other. In an exemplary embodiment that is integrated into a disposable diaper converter, patterned cylinder 22 is driven by the converter line drive through a gear train so that its surface velocity is essentially matched to the line velocity of the converter; and, as stated above, anvil cylinder 24 is powered by an independently speed controlled DC (direct current) drive. This enables adjusting the surface velocity of the anvil cylinder to be equal to, or less than, or greater than the surface velocity of the 55 patterned cylinder by predetermined amounts of percentages.

Temperature control means 30a and 30b, Figure 1, are provided to adjustably control the surface temperatures of cylinders 22 and 24, respectively. As stated above, these means enable independently heating each of the cylinders 22 and 24 to establish surface temperatures thereon that are predetermined

degrees below the melt temperature of the thermoplastic lamina disposed most adjacent to each. As also stated above, such heating enables effecting thermobonding of the laminae at lower nip biasing pressure than would otherwise be required for any given line speed and surface velocity differential between cylinders 22 and 24; and obviates having the laminae melting and sticking to the cylinders during, for example, converter and/or laminator stops.

Rolls 31 through 38, inclusive, are provided for guiding and advancing webs or laminae 41 and 42, and laminate 45 through and away from nip 43. Preferably these rolls are driven at surface velocities which maintain predetermined levels of tension or stretch so that neither slack web conditions nor excessively tensioned/stretched webs and or laminate precipitate undesirable deleterious consequences. For example, in an exemplary disposable diaper converter comprising the present invention, rolls 31 through 38, and cylinder 22 are driven through gear trains and the like from the main converter drive to provide a nominal draw of about one percent in the lengths of webs 41 and 42 being forwarded to nip 43 from the S-wrap roll pairs 31/32 and 33/34 for web forwarding control purposes; and about an equal amount of additional draw in the length of laminate 45 being forwarded from nip 43 by the S-wrap drive rolls 37 and 38.

Turning now to Figure 3, a fragmentary portion of cylinder 22 is shown which comprises one pattern element 51 disposed on cylindrical surface 52. Figure 4, a fragmentary sectional view taken along section line 4-4 of Figure 3, shows that the pattern element 51 is an integral portion of cylinder 22, has substantially vertical side surfaces, and projects radially outwardly a distance H: ie, the radial height of the pattern element. While such an integral relationship is preferred, it is not intended to thereby limit the present invention to such integral constructions. In an exemplary apparatus 20, pattern element 51 has an oval planform having a width of about 0.055 inch (about 0.14 cm.), length of about 0.086 inch (about 0.22 cm.), end radii of about 0.0275 inch (about 0.07 cm.), end areas of about 0.004 square inches (about 0.026 square centimeters) and are oriented on the surface of cylinder 22 with their width dimensions extending circumferentially. Starting with a right circular cylinder, pattern elements 51 were machined by removing surrounding metal by electric discharge machining to a depth of from about 0.015 to about 0.020 inch (about 0.4 mm to about 0.5 mm). Additionally, they were spaced -- center to center -- about 0.010 inch circumferentially (ie, in the machine direction), and about 0.072 inch laterally (ie, in the cross machine direction). A variation of such an element has a slightly chamfered edge: ie, about 0.010 inch wide edge portion beveled at about forty-five degrees.

Figure 5 is a plan view of a fragmentary portion of laminate 45, Figure 1, comprising overlapping edge portions of laminae 41 and 42 which have been thermobonded together by a pattern of bond sites 51b: the pattern being the pattern of pattern elements which extends circumferentially about one end of pattern cylinder 22, Figure 2. For clarity, the machine direction oriented edges of laminae 41 and 42 are designated 41e and 42e, respectively, in Figure 5.

Figure 6, is a somewhat schematic, fragmentary sectional view taken along section line 6-6 of Figure 5, which illustratively shows a bond site 51b which thermobonds laminae 41 and 42 together to form laminate 45. As shown, the bond site 51b has a bottom surface 51bb; substantially vertical side walls 53 and 54; and shows the top surface of the bond site to be recessed substantially further below the top surface of web 41 than the bottom surface 51bb is recessed from the bottom surface of web 42. While not wishing to be bound by a theory of operation, it is believed that such recessing on the pattern-element side of laminate 45 may be precipitated by the pattern elements 51 displacing portions of the laminae per se; and the recessing on the anvil facing side of the laminate may be precipitated by cooling and removal of compressive forces upon laminate 45 upon its issuing from nip 43, Figure 1. Indeed, in some lamina, portions of bond sites may even protrude rather than being recessed.

Figure 7, a plan view of a fragmentary portion of an alternate laminate 145 made in accordance with the present invention. Laminate 145 is different from laminate 45 inasmuch as the zig zag pattern of bond sites of laminate 145 comprises only 3 bond sites per leg whereas the pattern of laminate 45, Figure 5, comprises 5 bond sites per leg; and the bond sites of laminate 145 were precipitated by pattern elements similar to pattern elements 51, Figure 4, but for having sloped sides rather than vertical sides. Thus, each bond site 151b of laminate 145 has tapered or filleted side walls 151f.

An exemplary embodiment of apparatus 20, Figure 1, comprising the exemplary elements described above was operated as follows to make sample laminates comprising overlapping side edge portions of two thermoplastic laminae.

SAMPLE SET 1

A first set of samples -- samples 1a, 1b, 1c, 1d, and 1e -- comprising identical polyethylene laminae having nominal thicknesses of about one-and-two-tenths mil (about 0.03 mm), and melt temperatures of about 225 degrees Fahrenheit (about 107 degrees Celcius) were run at a constant line velocity of about four-hundred-fifty feet per minute (about 137 meters per minute); and with both nip defining cylinders heated to provide surface temperatures of about one-hundred-sixty degrees Fahrenheit (about 73 degrees Celcius). Four different anvil cylinder surface velocities were set: minus five, zero, five, ten, and twenty percent faster than the patterned cylinder/line velocity. At each differential velocity condition, the nip biasing pressure was adjusted to precipitate bonds having about equal nominal peel strengths. The results are tabulated in TABLE 1. Note that nip biasing air pressure (ie, the pressure adjusted by regulator 55, Figure 1) values are included as well as calculated nominal pattern element loadings in pounds per square inch (psi). Without intending to thereby limit the present invention, it is believed that the relative values of pressure (ie, their differences) manifest a principal benefit of the invention: that substantially lower pressures can be used in combination with greater velocity differentials to achieve bonds having approximately the same nominal peel strengths. This benefit translates, of course, into substantially longer pattern element lives.

TABLE 1

Sample No.	Differential Velocity, Anvil Cylinder Faster Than Patterned Cyl.	Nip Biasing Actuating Cylinders, kPa	Calculated Pattern Element Loading, kPa	Relative Peel Strength
1a	-5 %	275.8	6.2×10^5	475
1b	0 %	344.7	7.8×10^5	500
1c	5 %	275.8	6.2×10^5	475
1d	10 %	206.8	4.7×10^5	475
1e	20 %	137.9	3.1×10^5	450

Generally speaking, Table 1 illustrates that nip biasing pressure and differential velocity are inversely related. That is, all other things being equal; nip biasing pressure may be reduced as differential velocity is increased. Thus, nip biasing pressure may be set at values below the yield point of the pattern elements to assure relatively long operating lives for the pattern elements.

SAMPLE SET 2

A second set of samples -- samples 2a, 2b, 2c, and 2d -- were run using the same laminae as for sample Set No. 1 at constant nip biasing cylinder pressure of 275.8 kPa (40 psi) (ie, a calculated pattern element value of 6.2×10^5 kPa (90,000 psi)); and with the cylinders still heated to 71 °C (one-hundred-sixty degrees Fahrenheit). At four selected line velocities, the velocity differential was adjusted to precipitate bonds having about equal nominal peel strengths. The resulting data are tabulated in TABLE 2.

TABLE 2

Sample No.	Line Velocity, meters Per Minute	Differential Velocity, Anvil Cylinder Faster Than Patterned Cylinder	Relative Peel Strength
2a	137	20 %	620
2b	182	10	600
2c	206	5 %	580
2d	274	0	630

Generally speaking, TABLE 2 illustrates that line velocity and differential velocity are inversely related. That is, all other things being equal, as line speed increases, lower or no differential velocity is required to achieve a given nominal level of bond peel strength. Additionally, while peel strength data were taken in grams per inch units, only relative values are listed in the tables inasmuch as different test methodologies may precipitate different values.

SAMPLE SET 3

A third set of samples -- Samples 3a, 3b, 3c, 3d, and 3e -- were laminated from the same laminae as Sample Sets 1 and 2 above, using zero differential velocity, and heating both nip defining cylinders to about one-hundred-eighty degrees Fahrenheit (about 82 degrees Celsius). Five values of line velocity were set; then, the nip biasing pressure was adjusted to precipitate bonds having about equal nominal peel strengths. The resulting data are tabulated in TABLE 3.

TABLE 3

Sample No.	Line Velocity, metres Per Minute	Biasing Actuating Cylinders, kPa	Calculated Pattern Element Loading, kPa	Relative Peel Strength
3a	30.5	70 482.7	10.9×10^5	420
3b	51.8	344.7	7.8×10^5	460
3c	91.5	344.7	7.8×10^5	470
3d	450 137	275.8	6.2×10^5	450
3e	600 182	30 206.8	4.7×10^5	450

Generally speaking, these data illustrate that - in the absence of differential velocity between the nip defining cylinders -- the amount of nip biasing pressure required decreases as line velocity increases: particularly above three-hundred feet per minute (about 91.4 meters per minute); and, more particularly, at and above about four-hundred-fifty feet per minute (about 137 meters per minute).

Reflecting back to TABLES 1, 2 and 3, they essentially resulted from exploring three parameters two at a time: nip biasing pressure, velocity differential between the defining cylinders, and line velocity. Another important variable with respect to this invention is the temperature(s) to which the surfaces of the nip defining members (is, their surfaces) are heated. Generally speaking all other things being equal, as cylinder temperature is increased from ambient towards the melting temperature of the thermoplastic lamina disposed closest to or in contact with the cylinder, bonds of increasing strength will be realized up to a point; and further increases in cylinder temperatures will produce bonds of lesser strength. In general, cylinder surface temperatures in the range of from 22°-55° Centigrade (about forty to about one-hundred degrees Fahrenheit) below the melt temperature of the lamina disposed closest to or in contact with each respective nip defining cylinder produce high strength bonds, and without precipitating holes in the laminae. Directionally, optimum cylinder surface temperatures are inversely related to line velocity: higher cylinder temperatures being preferred at relatively slow line velocities, and lower cylinder temperatures being preferred at relatively high line velocities. Thus, for example, with the identical laminae (both polyethylene having a melting temperature of 107.5° C (about two-hundred-twenty-five degrees Fahrenheit)) as utilized for Sample Sets 1, 2, and 3, satisfactory bond strengths--all other things being equal--were achieved at cylinder temperatures of about one hundred-forty degrees Fahrenheit (about 60 degrees Celsius) at a line velocity of about six-hundred feet per minute (about 183 meters per minute). When one lamina was replaced with a higher melting point polyethylene--a film having a melting point of about two-hundred-fifty-seven degrees Fahrenheit (about 125 degrees Celsius)--comparable strength bonds were achieved by heating the cylinder in contact with that lamina to a temperature of about one-hundred-seventy degrees Fahrenheit (about 77 degrees Celsius).

While not wishing to be bound by a theory of operation, it is believed that differential velocity--when used--contributes shear energy to enable dynamic, mechanically induced, thermobonding. This is in addition to heat generated from molecular flow/fluid friction as bond-site thermoplastic is quickly displaced by the intrusion of pattern elements into the thermoplastic laminae. Additionally, inasmuch as effective bonding of webs or laminae occurs when they are at room ambient temperature going into the nip, it is believed that heating the nip defining members (eg, cylinders 22 and 24) acts more to retard heat flow from the bond sites rather than being a source of heat flow into the bond sites. Moreover, inasmuch as maximum bond strengths are normally achieved at cylinder temperatures well below the melt temperatures of the laminae, it is believed that bonds made at higher temperatures do not wholly set as the laminate is forwarded from the bonding nip. Indeed, at high line speeds, good bonding may be achieved without heating the cylinders; ie, having the cylinders at room ambient temperature.

While specific examples have been described above, generally speaking, velocity-differentials in the range of from about 2 to about 40 percent are preferred; from about 2 to about 20 percent are more preferred; and the surface velocity of the anvil cylinder is preferably greater than the pattern cylinder albeit

it is not intended to thereby limit the present invention. Additionally, while it is preferred that the anvil cylinder have a smooth cylindrical surface, it is also not intended to thereby limit the invention to a laminating apparatus comprising a smooth surfaced anvil cylinder. Moreover, while the invention has been discussed above through the use of two laminae in continuous length web forms, it is not intended to thereby limit the invention to either continuous laminae or to two laminae. That is, discontinuous discrete lengths of lamina can also be laminated through application of this invention; and, of course, greater than two laminae may be laminated through application of this invention.

Referring back to Figure 4, pattern element 51 is shown to have a height H. Generally speaking, bond sites of minimum thickness are obtained when H is greater than the sum of the thicknesses of the laminae being laminated: eg, the sum of the thicknesses of laminae 41 and 42 for the examples described above. Such dimensioned pattern elements generally precipitate bond sites having nominal thicknesses of about one-half mil (about 0.0127 mm) when the laminae have nominal thicknesses of about one mil each. In the event thicker bond sites are desired, the pattern elements must have heights which are about equal to or sufficiently less than the sum of the thicknesses of the laminae to precipitate bond sites having the desired thicknesses.

Claims

1. A method of dynamically bonding plural laminae (41, 42) together, at least one of which laminae comprises thermoplastic material, said method comprising the steps of: forwarding said laminae (41, 42) with portions thereof in face to face relation, through a pressure biased nip (43) between a relief patterned nip defining member (22) having pattern element segments (51), and a nip defining anvil member (24), said nip defining members (22, 24) being biased towards each other with a predetermined pattern-element loading; characterised in that the method comprises driving said nip defining members (22, 24) to provide a predetermined surface velocity differential therebetween, in the range of from 2 to 40 percent of the surface velocity of said nip defining member having the lower surface velocity.
2. A method according to Claim 1 wherein said laminae are forwarded at a velocity of at least 91.4 metres per minute, said pattern element segments comprise discrete projections having tip surface areas greater than 0.013-square centimetres said predetermined pattern-element loading is no more than 62×10^4 kPa and each said nip defining member is heated sufficiently to permit said laminae to be dynamically thermobonded together.
3. A method according to either one of claims 1 & 2 wherein said nip defining anvil member (24) is rotatably mounted, and comprises smooth surface portions for opposing said pattern elements (51), said surface portions being circular cylindrical sectors.
4. A method according to any of the preceding claims wherein said patterned nip defining member (22) is rotatably mounted and is driven at a surface velocity essentially matched to the forwarding velocity of said laminae (41, 42) through said nip (43).
5. A method according to any of the preceding claims wherein said nip defining anvil member (24) is driven with a greater surface velocity than said patterned nip defining member (22).
6. An apparatus for carrying out a method of dynamically bonding plural laminae together according to any one of claims 1-5, said apparatus comprising a relief patterned nip defining member (22) and a nip defining anvil member (24), means for mounting said nip defining members to define a nip (43) therebetween through which nip said laminae (41, 42) may be forwarded with portions thereof in face to face relation, means (55, 56) for controllably biasing said nip defining members towards each other, and means (28, 29) for driving said nip defining members (22, 24) characterised in that said driving means is adapted to provide differential surface velocities within a range of from 2 to 40 percent of the surface velocity of said nip defining member having the lower surface velocity.



it is not intended to thereby limit the present invention. Additionally, while it is preferred that the anvil cylinder have a smooth cylindrical surface, it is also not intended to thereby limit the invention to a laminating apparatus comprising a smooth surfaced anvil cylinder. Moreover, while the invention has been discussed above through the use of two laminae in continuous length web forms, it is not intended to thereby limit the invention to either continuous laminae or to two laminae. That is, discontinuous discrete lengths of lamina can also be laminated through application of this invention; and, of course, greater than two laminae may be laminated through application of this invention.

Referring back to Figure 4, pattern element 51 is shown to have a height H. Generally speaking, bond sites of minimum thickness are obtained when H is greater than the sum of the thicknesses of the laminae being laminated: eg, the sum of the thicknesses of laminae 41 and 42 for the examples described above. Such dimensioned pattern elements generally precipitate bond sites having nominal thicknesses of about one-half mil (about 0.0127 mm) when the laminae have nominal thicknesses of about one mil each. In the event thicker bond sites are desired, the pattern elements must have heights which are about equal to or sufficiently less than the sum of the thicknesses of the laminae to precipitate bond sites having the desired thicknesses.

Claims

1. A method of dynamically bonding plural laminae (41, 42) together, at least one of which laminae comprises thermoplastic material, said method comprising the steps of:
forwarding said laminae (41, 42) with portions thereof in face to face relation, through a pressure biased nip (43) between a relief patterned nip defining member (22) having pattern element segments (51), and a nip defining anvil member (24),
said nip defining members (22, 24) being biased towards each other with a predetermined pattern-element loading;
characterised in that the method comprises driving said nip defining members (22, 24) to provide a predetermined surface velocity differential therebetween, in the range of from 2 to 40 percent of the surface velocity of said nip defining member having the lower surface velocity.
2. A method according to Claim 1 wherein said laminae are forwarded at a velocity of at least 91.4 metres per minute, said pattern element segments comprise discrete projections having tip surface areas greater than 0.013-square centimetres said predetermined pattern-element loading is no more than 62×10^4 kPa and each said nip defining member is heated sufficiently to permit said laminae to be dynamically thermobonded together.
3. A method according to either one of claims 1 & 2 wherein said nip defining anvil member (24) is rotatably mounted, and comprises smooth surface portions for opposing said pattern elements (51), said surface portions being circular cylindrical sectors.
4. A method according to any of the preceding claims wherein said patterned nip defining member (22) is rotatably mounted and is driven at a surface velocity essentially matched to the forwarding velocity of said laminae (41, 42) through said nip (43).
5. A method according to any of the preceding claims wherein said nip defining anvil member (24) is driven with a greater surface velocity than said patterned nip defining member (22).
6. An apparatus for carrying out a method of dynamically bonding plural laminae together according to any one of claims 1-5, said apparatus comprising a relief patterned nip defining member (22) and a nip defining anvil member (24), means for mounting said nip defining members to define a nip (43) therebetween through which nip said laminae (41, 42) may be forwarded with portions thereof in face to face relation, means (55, 56) for controllably biasing said nip defining members towards each other, and means (28, 29) for driving said nip defining members (22, 24) characterised in that said driving means is adapted to provide differential surface velocities within a range of from 2 to 40 percent of the surface velocity of said nip defining member having the lower surface velocity.



7. An apparatus according to claim 6 further comprising means (30a, 30b) for independently controlling the surface temperatures of said nip defining members (22, 24) whereby each said nip defining member may be operated so that its surface temperature is within a predetermined range below the melt temperature of whichever lamina of said laminae (41, 42) that comprises thermoplastic material is disposed closest to each respective said nip defining member as said laminae are forwarded through said nip.
8. An apparatus according to either one of claims 6 or 7 wherein said patterned nip defining member (22) comprises pattern element segments (51), and said nip defining anvil member (24) is rotatably mounted and comprises smooth surface portions for opposing said pattern element segments, said surface portions being circular cylindrical sectors.
9. An apparatus according to any one of claims 6 to 8 wherein said patterned nip defining member (22) is a rotatably mounted component comprising a circular cylindrical sector (52) having pattern element segments (51) disposed thereon.
10. An apparatus according to any one of claims 6 to 9 wherein said patterned nip defining member (22) comprises pattern element segments (51) having heights that are greater than the sum of the thicknesses of said laminae.
11. An apparatus according to any one of claims 6 to 9 wherein said patterned nip defining member (22) comprises pattern element segments (51) having heights that are about equal to or less than the sum of the thicknesses of said laminae, thereby to precipitate bond sites having predetermined thicknesses.

Revendications

1. Un procédé d'assemblage dynamique de stratifiés multiples (41, 42), dont au moins un des stratifié est constitué d'un matériau thermo-plastique, ledit procédé comprenant les étapes suivantes :
on avance lesdits stratifiés (41, 42), des parties de ceux-ci étant disposées face à face, à travers un pincement réalisé par pression (43) entre un élément à motifs en relief définissant un pincement (22) ayant des segments d'éléments à motifs (51), et un pincement définissant un élément d'enclume (24),
lesdits éléments définissant le pincement (22, 24) étant poussés l'un vers l'autre avec une charge prédéterminée d'éléments à motifs ;
caractérisé en ce qu'il consiste
à entraîner lesdits éléments définissant le pincement (22, 24) pour assurer une vitesse différentielle superficielle prédéterminée entre eux, de l'ordre de 2 à 40 pourcent de vitesse superficielle dudit élément définissant le pincement ayant la vitesse superficielle inférieure.
2. Un procédé selon la revendication 1 dans lequel
lesdits stratifiés sont avancés à une vitesse d'au moins 91,4 mètres par minute, lesdits segments d'éléments à motifs comportant des saillies discrètes ayant des zones superficielles à pointes supérieure à 0,013 centimètre carré, ladite charge d'éléments à motifs prédéterminés étant supérieure à 62×10^4 kPa et chacun desdits éléments définissant le pincement étant chauffé suffisamment pour permettre auxdits stratifiés d'être thermoscellés dynamiquement.
3. Un procédé selon l'une quelconque des revendications 1 et 2, dans lequel ledit élément d'enclume définissant le pincement (24) est monté à rotation et comporte des parties superficielles lisses opposées auxdits éléments à motifs (51) lesdites parties superficielles étant des secteurs circulaires cylindriques.
4. Un procédé suivant l'une quelconque des revendications précédentes, dans lequel ledit élément définissant le pincement à motifs (22) est monté à rotation et est entraîné à une vitesse superficielle correspondant essentiellement à la vitesse d'avance desdits stratifiés (41, 42) à travers ledit pincement (43).



5. Un procédé selon l'une quelconque des revendications précédentes dans lequel ledit pincement définissant ledit élément d'enclume (24) est entraîné à une vitesse superficielle supérieure à celle dudit élément définissant le pincement à motifs (22).
- 5 6. Un dispositif pour la mise en oeuvre d'un procédé d'assemblage dynamique de plusieurs stratifiés conforme à l'une quelconque des revendications 1-5, ledit dispositif comportant un élément définissant un pincement à motifs à relief (22) et un élément d'enclume définissant un pincement (24), un moyen pour monter lesdits éléments définissant un pincement pour définir un pincement (43) entre eux à travers lequel lesdits stratifiés (41, 42) peuvent être avancés, des parties de ceux-ci étant disposées face à face, des moyens (51, 56) pour régler la poussée l'un vers l'autre desdits éléments définissant le pincement, et des moyens (28, 29) pour entraîner lesdits éléments définissant le pincement (22, 24) caractérisé en ce que ledit moyen d'entraînement est destiné à fournir des vitesses différentielles superficielles de l'ordre de 2 à 40 pourcent de la vitesse superficielle dudit élément définissant le pincement ayant la vitesse superficielle inférieure.
- 15 7. Un dispositif selon la revendication 6 comportant en outre des moyens (30a, 30b) pour régler indépendamment les températures superficielles desdits éléments définissant le pincement (22, 24) grâce à quoi chacun desdits éléments définissant le pincement peut être actionné de telle sorte que sa température superficielle est dans une gamme prédéterminée en dessous de la température de fusion de l'un ou l'autre stratifié desdits stratifiés (41, 42) qui comporte le matériau thermo-plastique disposé le plus près respectivement de chacun desdits éléments définissant le pincement lorsque lesdits stratifiés sont avancés à travers lesdits pincements.
- 20 8. Un dispositif selon l'une quelconque des revendications 6 ou 7, dans lequel ledit élément définissant le pincement à motifs (22) comporte des segments d'éléments à motifs (51) et ledit élément d'enclume définissant le pincement (24) est monté à rotation et comporte des parties superficielles lisses opposées auxdits segments d'éléments à motifs, lesdites parties superficielles étant des secteurs circulaires cylindriques.
- 25 9. Un dispositif selon l'une quelconque des revendications 6 à 8, dans lequel ledit élément définissant le pincement à motifs (22) est un élément monté à rotation comportant un secteur circulaire cylindrique (52) ayant des segments d'éléments à motifs (51) disposés sur celui-ci.
- 30 10. Un dispositif selon l'une quelconque des revendications 6 à 9, dans lequel ledit élément définissant le pincement à motifs (22) comporte des segments d'éléments à motifs (51) ayant des hauteurs qui sont plus grandes que la somme des épaisseurs desdits stratifiés.
- 35 11. Un dispositif selon l'une quelconque des revendications 6 à 9, dans lequel ledit élément définissant le pincement à motifs (22) comporte des segments d'éléments à motifs (51) ayant des hauteurs qui sont égales ou inférieures environ à la somme des épaisseurs desdits stratifiés de manière à précipiter des sites d'assemblage ayant des épaisseurs prédéterminées.
- 40

Patentansprüche

- 45 1. Ein Verfahren zum dynamischen Aneinander-Binden mehrerer dünner Plättchen (41, 42), wobei mindestens ein dünnes Plättchen davon thermoplastisches Material aufweist, wobei das genannte Verfahren die Schritte enthält:
Vorwärtsbewegen der genannten dünnen Plättchen (41, 42), mit Abschnitten von ihnen in Gegenüberstellung, durch einen durch Druck vorgespannten Einlaufspalt (43) zwischen einem im Relief gemusterten einlaufspaltbegrenzenden Bauteil (22) mit Musterelementsegmenten (51) und einem einlaufspaltbegrenzenden Anschlagbauteil (24),
wobei die genannten einlaufspaltbegrenzenden Bauteile (22, 24) gegeneinander mit einer vorausbestimmten Musterelementbelastung vorgespannt sind, dadurch gekennzeichnet, daß das Verfahren umfaßt
50 Antreiben der genannten einlaufspaltbegrenzenden Bauteile (22, 24), um eine vorausbestimmte Oberflächengeschwindigkeitsdifferenz dazwischen, im Bereich von 2% bis 40% der Oberflächengeschwindigkeit des genannten einlaufspaltbegrenzenden Bauteiles mit der geringeren Oberflächengeschwindigkeit, zu ergeben.
- 55



2. Ein Verfahren nach Anspruch 1, bei welchem die genannten dünnen Plättchen bei einer Geschwindigkeit von mindestens 91,4 m/min. vorwärtsbewegt werden, wobei die genannten Musterelementsegmente getrennte Vorsprünge umfassen, welche Spitzen-Oberflächenzonen mit einer Größe von mehr als 0,013 cm² aufweisen,
 5 die genannte vorausbestimmte Musterelementbelastung nicht größer als 62×10^4 kPa ist und jeder genannte einlaufspaltbegrenzende Bauteil hinreichend erhitzt wird, um den genannten dünnen Plättchen zu gestatten, aneinander dynamisch thermogebunden zu werden.
3. Ein Verfahren nach einem der Ansprüche 1 und 2, bei welchem der genannte einlaufspaltbegrenzende Anschlagbauteil (24) rotierbar gelagert ist und glatte Oberflächenabschnitte umfaßt, um den genannten Musterelementen (51) entgegenzuwirken, wobei die genannten Oberflächenabschnitte kreisförmige zylindrische Sektoren sind.
 10
4. Ein Verfahren nach einem der vorhergehenden Ansprüche, bei welchem der genannte gemusterte einlaufspaltbegrenzende Bauteil (22) rotierbar gelagert ist und bei einer Oberflächengeschwindigkeit angetrieben wird, welche im wesentlichen an die Vorwärtsbewegungsgeschwindigkeit der genannten dünnen Plättchen (41, 42) durch den genannten Einlaufspalt (43) angepaßt ist.
 15
5. Ein Verfahren nach einem der vorhergehenden Ansprüche, bei welchem der genannte einlaufspaltbegrenzende Anschlagbauteil (24) mit einer größeren Oberflächengeschwindigkeit als der genannte gemusterte einlaufspaltbegrenzende Bauteil (22) angetrieben wird.
 20
6. Eine Vorrichtung zum Ausführen eines Verfahrens zum dynamischen Aneinanderbinden mehrerer dünner Plättchen entsprechend einem der Ansprüche 1 bis 5, wobei die genannte Vorrichtung einen im Relief gemusterten einlaufspaltbegrenzenden Bauteil (22) und einen einlaufspaltbegrenzenden Anschlagbauteil (24) Mittel zum Lagern der genannten einlaufspaltbegrenzenden Bauteile, um einen Einlaufspalt (43) dazwischen zu begrenzen, durch welchen Einlaufspalt die genannten dünnen Plättchen (41, 42) mit Abschnitten von ihnen in Gegenüberstellung vorwärtsbewegt werden können, Mittel (55, 56) zum kontrollierbaren Vorspannen der genannten einlaufspaltbegrenzenden Bauteile gegeneinander, und Mittel (28, 29) zum Antreiben der genannten einlaufspaltbegrenzenden Bauteile (22, 24) aufweisen, dadurch gekennzeichnet, daß das genannte Antriebsmittel adaptiert ist, um differentielle Oberflächengeschwindigkeiten innerhalb eines Bereichs von 2% bis 40% der Oberflächengeschwindigkeit des genannten einlaufspaltbegrenzenden Bauteiles mit der geringeren Oberflächengeschwindigkeit zu erzielen.
 25
 30
 35
7. Eine Vorrichtung nach Anspruch 6, welche weiters Mittel (30a, 30b) zum unabhängigen Steuern der Oberflächentemperaturen der genannten einlaufspaltbegrenzenden Bauteile (22, 24) umfaßt, wobei jeder genannte einlaufspaltbegrenzende Bauteil so betätigt werden kann, daß seine Oberflächentemperatur innerhalb eines vorausbestimmten Bereiches unterhalb der Schmelztemperatur von irgendeinem dünnen Plättchen der genannten dünnen Plättchen (41, 42) ist, welches thermoplastisches Material enthält und am nächsten zu jedem jeweiligen genannten einlaufspaltbegrenzenden Bauteil angeordnet ist, wenn die genannten dünnen Plättchen durch den genannten Einlaufspalt vorwärtsbewegt werden.
 40
8. Eine Vorrichtung nach einem der Ansprüche 6 oder 7, bei welcher der genannte gemusterte einlaufspaltbegrenzende Bauteil (22) Musterelementsegmente (51) umfaßt und der genannte einlaufspaltbegrenzende Anschlagbauteil (24) rotierbar gelagert ist und glatte Oberflächenabschnitte umfaßt, um den genannten Musterelementsegmenten entgegenzuwirken, wobei die genannten Oberflächenabschnitte kreisförmige zylindrische Sektoren sind.
 45
9. Eine Vorrichtung nach einem der Ansprüche 6 bis 8, bei welcher der genannte gemusterte einlaufspaltbegrenzende Bauteil (22) ein rotierbar gelagerter Bestandteil ist, welcher einen kreisförmigen zylindrischen Sektor (52) mit darauf angeordneten Musterelementsegmenten (51) umfaßt.
 50
10. Eine Vorrichtung nach einem der Ansprüche 6 bis 9, bei welcher der genannte gemusterte einlaufspaltbegrenzende Bauteil (22) Musterelementsegmente (51) umfaßt, welche Höhen aufweisen, welche größer sind als die Summe der Dicken der genannten dünnen Plättchen.
 55



11. Eine Vorrichtung nach einem der Ansprüche 6 bis 9, bei welcher der genannte gemusterte einlaufspaltbegrenzende Bauteil (22) Musterelementsegmente (51) umfaßt, welche Höhen aufweisen, welche ungefähr gleich wie oder geringer sind als die Summe der Dicken der genannten dünnen Plättchen, um dadurch Bindungsstellen mit vorausbestimmten Dicken auszubilden.

5

10

15

20

25

30

35

40

45

50

55