

FLAME RETARDANT THERMOPLASTIC ELASTOMERS

CLAIM OF PRIORITY

[0001] This application claims priority from U.S. Provisional Patent Application Serial Number 60/969,629 bearing Attorney Docket Number 12007016 and filed on September 2, 2007, which is incorporated by reference. This application also claims priority from U.S. Provisional Patent Application Serial No. 61/080,500 bearing Attorney Docket Number 12008018 and filed on July 14, 2008.

FIELD OF THE INVENTION

[0002] This invention relates to thermoplastic elastomers, polymer compounds which exhibit elasticity while remaining thermoplastic, which are also flame retardant.

BACKGROUND OF THE INVENTION

[0003] The world of polymers has progressed rapidly to transform material science from wood and metals of the 19th Century to the use of thermoset polymers of the mid-20th Century to the use of thermoplastic polymers of later 20th Century.

[0004] Thermoplastic elastomers combine the benefits of elastomeric properties of thermoset polymers, such as vulcanized rubber, with the processing properties of thermoplastic polymers.

[0005] For safety reasons in some uses, thermoplastic elastomers should be flame retardant. There is customer demand for essentially non-halogen flame retardant thermoplastic elastomers.

SUMMARY OF THE INVENTION

[0006] What the art needs is a new thermoplastic elastomer (also called "TPE") that is flame retardant without the use of brominated flame retardants or

chlorinated polyethylene flame retardants or other halogen-containing flame retardants. The art needs an essentially halogen-free flame retardant TPE ("HFFR TPE").

[0007] "Essentially halogen-free" means that there is no intention to include any halogen moieties in any of the ingredients of the compound of the present invention, but that one cannot control trace amounts of impurities that may exist in such ingredients.

[0008] Unfortunately, essentially halogen-free flame retardants are very sensitive to processing conditions typically experienced by TPEs. Therefore, there is little predictable to one of ordinary skill in the art in the creation of a HFFR TPE.

[0009] The present invention solves the problem by formulating a HFFR TPE that utilizes ammonium polyphosphate as an essentially halogen-free flame retardant.

[0010] One aspect of the invention is an essentially halogen-free thermoplastic elastomer compound, comprising (a) styrene-containing thermoplastic elastomer; (b) an ammonium polyphosphate-containing flame retardant; and optionally (c) plasticizer.

[0011] Another aspect of the invention is a plastic article made from the compound.

[0012] Another aspect of the invention is an essentially halogen-free thermoplastic compound described above, further comprising expandable graphite filler. This filler can expand in the presence of heat and form a char.

[0013] Another aspect of the invention is a plastic article made from the expandable compound described above.

[0014] Features of the invention will become apparent with reference to the following embodiments.

EMBODIMENTS OF THE INVENTION

[00015] Styrene-Containing TPE

[00016] TPEs of the present invention are based on styrene ("TPE-S") and are often compounded with plasticizer, antioxidant, thermal stabilizer, and one or more secondary polymers.

[00017] Non-limiting examples of TPE-S include styrene-ethylene-butylene-styrene, styrene-ethylene-propylene-styrene, styrene-ethylene-ethylene/propylene-styrene, styrene-isobutylene-styrene, styrene-butadiene-styrene, styrene-isoprene-styrene, and combinations thereof. These examples of TPE-S may or may not be maleated but have weight average molecular weights in excess of 75,000 and preferably in excess of 200,000. Commercially available grades of these TPE-S compounds are Kraton MD6917ES and Kraton G 1633 from Kraton Polymers and Septon 4077 and Septon 4099 from Kuraray.

[00018] Essentially Halogen-Free Flame Retardant

[00019] It has been found that flame retardants that contain ammonium polyphosphate are particularly suited to endure the processing conditions employed in compounding TPE-S.

[00020] It has been found, particularly, that Exolit AP brand flame retardants from Clariant GmbH of Germany work well in compounds of the present invention. Presently preferred is Exolit AP 766 brand flame retardant.

[00021] Optional Additives

[00022] The compound of the present invention can include conventional plastics additives in an amount that is sufficient to obtain a desired processing or performance property for the compound. The amount should not be wasteful of the additive nor detrimental to the processing or performance of the compound. Those skilled in the art of thermoplastics compounding, without undue experimentation but with reference to such treatises as Plastics Additives Database (2004) from Plastics Design Library (www.williamandrew.com), can

select from many different types of additives for inclusion into the compounds of the present invention.

[00023] Non-limiting examples of optional additives include adhesion promoters; biocides (antibacterials, fungicides, and mildewcides), anti-fogging agents; anti-static agents; bonding, blowing and foaming agents; dispersants; fillers and extenders; smoke suppressants; expandable char formers; impact modifiers; initiators; lubricants; micas; pigments, colorants and dyes; plasticizers; processing aids; other polymers; release agents; silanes, titanates and zirconates; slip and anti-blocking agents; stabilizers; stearates; ultraviolet light absorbers; viscosity regulators; waxes; and combinations of them.

[00024] Any conventional plasticizer, preferably a paraffinic oil, is suitable for use the present invention.

[00025] A preferred secondary polymer for the present invention is polypropylene.

[00026] A preferred anti-oxidant is an Irganox brand pentaerythritol antioxidant identified as CAS 6683-19-8.

[00027] A preferred thermal stabilizer an Irganox brand thiodipropionate compound identified as CAS 123-28-4.

[00028] An expandable graphite filler can serve as an expandable char former in formulations of the compound in those instances when the article formed from the compound should expand as it is heated. The expandable graphite filler should have an onset of expansion temperature greater than the processing temperature of the compound, but low enough and with a high enough activity to provide a suitable expansion. Suitable expansion could be as much as 300%, in an embodiment of a door seal where the gap during normal operation becomes sealed upon onset of exposure to heat or flame. Preferred expandable graphite filler products are commercially available as Nord-Min branded products from Nordmann Rassmann of Germany.

[00029] Table 1 shows the acceptable, desirable, and preferable ranges of ingredients for the HFFR-TPE of the present invention.

Table 1 Ranges of Ingredients			
Ingredient (Wt. Percent)	Acceptable	Desirable	Preferable
TPE-S	5-40%	10-35%	15-25%
Flame retardant containing ammonium polyphosphate	20-70%	25-60%	30-50%
Plasticizer	0-60%	10-40%	15-30%
Secondary Polymer(s)	0-30%	5-25%	5-20%
Anti-oxidant	0-3%	0-2%	0-1%
Thermal Stabilizer	0-3%	0-2%	0-1%
Expandable graphite filler	0-30%	10-25%	15-20%
Other Optional Additives	0-15%	0-10%	0-5%

[00030] Processing

[00031] The preparation of compounds of the present invention is uncomplicated once the proper ingredients have been selected. The compound of the present can be made in batch or continuous operations.

[00032] Mixing in a continuous process typically occurs in an extruder that is elevated to a temperature that is sufficient to melt the polymer matrix with addition of all additives at the feed-throat, or by injection or side-feeders downstream. Extruder speeds can range from about 50 to about 500 revolutions per minute (rpm), and preferably from about 100 to about 300 rpm. Typically, the output from the extruder is pelletized for later extrusion or molding into polymeric articles.

[00033] Mixing in a batch process typically occurs in a Banbury mixer that is also elevated to a temperature that is sufficient to melt the polymer matrix to permit homogenization of the compound components. The mixing

speeds range from 60 to 1000 rpm and temperature of mixing can be ambient. Also, the output from the mixer is chopped into smaller sizes for later extrusion or molding into polymeric articles.

[00034] Subsequent extrusion or molding techniques are well known to those skilled in the art of thermoplastics polymer engineering. Without undue experimentation but with such references as "Extrusion, The Definitive Processing Guide and Handbook"; "Handbook of Molded Part Shrinkage and Warpage"; "Specialized Molding Techniques"; "Rotational Molding Technology"; and "Handbook of Mold, Tool and Die Repair Welding", all published by Plastics Design Library (www.williamandrew.com), one can make articles of any conceivable shape and appearance using compounds of the present invention.

USEFULNESS OF THE INVENTION

[00035] TPE-S of the present invention is an excellent versatility because of its elastomeric performance and its thermoplastic processing. The addition of anti-oxidant properties, thermal stabilization, and essentially halogen-free flame retardancy by those respective functional additives makes the HFFR TPE of the present invention an excellent compound for molding into plastic articles which need flame retardancy when in use in enclosed spaces. Use in motor vehicle passenger compartments and aircraft passenger compartments are two of many ways the compounds of the present invention can benefit people around the world.

EXAMPLES

[00036] Table 2 shows seven examples of the present invention, their formulations, sources of ingredients, and processing conditions.

Table 2 Formulations and Processing Conditions							
Ingredient Name (Wt. Parts)	1	2	3	4	5	6	7
Kraton MD6917ES SEBS (Kraton)	21.5	21.5	23.5	25.0	20.0	23.0	24.0
BP 401-NA06 PP copolymer (Ineos)	17.0	17.0	18.0	5.0	11.0	13.0	20.0
Primol 382 oil (Exxon/Mobil)	21.5	21.5	23.5	30.0	29.0	27.0	21.0
Exolit AP766 flame retardant (Clariant)	40.0	40.0	35.0	40.0	40.0	37.0	35.0
Irganox 1010 anti-oxidant (Ciba)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Irganox PS800 thermal stabilizer (Ciba)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
W&P ZE25 twin screw compounder							
Mixing Equipment							
Mixing Temp. progressing through the Zones(°C)	160-185	160-185	160-185	160-170	160-170	160-170	160-170
Mixing Speed (rpm)	320						
Plasticizer amount added at the injection port (%)	9.5%	9.5%	10%	15%	14%	10%	10%
Form of Product After Mixing	Pellets						

[00037] Pellets of all Examples 1-7 were molded into tensile test bars using a Demag injection molding machine, operating at 160-180°C temperature and medium-high pressure.

[00038] Table 3 shows the experimental results.

Table 3 Test Results							
Test	1	2	3	4	5	6	7
Density (DIN 53479) g/cm ³	1.10	1.097	1.062	1.084	1.081	1.069	1.059
Shore Durometer (DIN 53505) Shore A	85	87	81	47	65	74	87
Tensile Strength (DIN 53504)	5.1 MPa	5.1 MPa	5.5 MPa	2.6 MPa	3.1 MPa	4 MPa	6.2 MPa
Elongation at break (DIN 53504)	420 %	420 %	455 %	380%	420%	350%	340%
Compression Set (DIN 53 517)	59 %	59 %	55 %	44%	49%		
Melt Flow Index (190°C/5Kg) (DIN EN ISO 1133) g/10min	2.3	3.1	2.3	0.3	4.7	2.4	2.9
Flame Resistance UL94@0.8 mm (UL94)		V-2					
Flame Resistance UL94@1.5mm (UL94)	V-0	V-0	V-0	V-0	V-0	V-0	V-0
Flame Resistance UL94@3 mm (UL94)		V-0					
Glow-wire @0.8mm (IEC 695-2-1)		960°C					
Glow-wire @1.5mm (IEC 695-2-1)	960°C						
Glow-wire @2mm (IEC 695-2-1)		960°C	960°C	960°C	960°C	960°C	960°C
Glow-wire @3mm (IEC 695-2-1)		960°C					

[00039] Examples 1-7 exhibit a variety of hardnesses as well as excellent flame retardancy using an essentially halogen-free flame retardant compound. Not only were the compounds easy to process, a manufacturing requirement, but also the compounds showed excellent performance. All of the compounds met the UL-94-V0 test at 1.5 mm and passed the IEC695-2-1 glow wire test at 960°C at 2 mm.

[00040] Table 4 shows the formulations and processing conditions for an embodiment of the invention where expandable graphite filler is also used. Examples 9 and 10 differ from Example 8 because they contain expandable graphite filler.

Table 4			
Formulations and Processing Conditions			
Ingredients (Wt. %)	8	9	10
Kraton G 1651 SEBS (Kraton)	27.24	0.00	21.71
Kraton G 1654 SEBS (Kraton)	0.00	27.78	0.00
BP 100-GB06 polypropylene homopolymer (Ineos)	10.09	10.91	0.00
BP 101-YA35 polypropylene homopolymer (Ineos)	0.00	5.95	0.00
Primol 382 paraffinic white oil (ExxonMobil)	25.22	39.69	23.88
Exolit AP766 flame retardant (Clariant)	37.33	0.00	32.57
Nord Min 503 expandable graphite (Nordmann Rassmann)	0.00	14.88	0.00
Nord Min 249 expandable graphite (Nordmann Rassmann)	0.00	0.00	21.71
Anox 20 tetrakis(methylene) anti-oxidant (Chemtura)	0.11	0.11	0.12
Epikote 1004 epoxy resin (Hercules)	0.00	0.42	0.00

Table 4 Formulations and Processing Conditions			
Ingredients (Wt. %)	8	9	10
Uvinul 3027 benzotriazole (BASF)	0.00	0.26	0.00
Mixing Equipment	W&P ZE25 twin screw compounder		
Mixing Temp.	150-170°C		
Mixing Speed	320 rpm		
Plasticizer amount added at the injection port (%)	10%	15%	10%
Form of Product After Mixing	Pellets		

[00041] Table 5 shows the test results.

Table 5 Test Results				
Test	Test Method	8	9	10
Hardness, Shore A	DIN 53 505	75	70	83
Density (g/cm ³)	DIN 53479-A	1.07	0.977	1.189
Tensile Strength (MPa)	DIN 53 504	5.3	5.1	2.9
Elongation at Break (%)	DIN 53 504	375	530	200
UL 94 @ 1.5 mm	UL 94	V-0	HB	V-0
Glow Wire @ 2mm	IEC 695-2-1	960°C	-	960°C
Expansion Volume	At 300°C after 20 min	15%	190%	>400%

[00042] Example 9 has 190% expansion, and Example 10 has over 400% expansion.

[00043] Example 10 would be particularly suitable in the form of a seal for a fire door between the door leaf and door frame. In order to cover the gap between the leaf and the frame, that seal would need to expand during a fire. The expansion over the gap, which could be up to 5mm, as compared to the dimension of the seal, considering present seal designs, could be at least 300%. A door seal made from the compound of Example 10 is expandable in the presence of heat at least 300% over its dimension when not heated. That

expansion would cover a door gap during a fire, leading to better fire protection of life and property.

[00044] The invention is not limited to the above embodiments. The claims follow.

What is claimed is:

1. An essentially halogen-free thermoplastic elastomer compound, comprising:
 - (a) styrene-containing thermoplastic elastomer;
 - (b) an ammonium polyphosphate-containing flame retardant; andoptionally
 - (c) plasticizer.
2. The compound of Claim 1, further comprising polypropylene.
3. The compound of Claim 1 or Claim 2, wherein the styrene-containing thermoplastic elastomer has a weight average molecular weight of at least 200,000.
4. The compound of Claim 1 or Claim 2 or Claim 3, wherein the styrene-containing thermoplastic elastomer is selected from the group consisting of styrene-ethylene-butylene-styrene, styrene-ethylene-propylene-styrene, styrene-ethylene-ethylene/propylene-styrene, styrene-isobutylene-styrene, styrene-butadiene-styrene, styrene-isoprene-styrene, and combinations thereof.
5. The compound of any of Claims 2-4, wherein the styrene-containing thermoplastic elastomer is not maleated but has a weight average molecular weight in excess of 75,000.
6. The compound of any of Claims 1-5, wherein the plasticizer is a paraffinic oil.
7. The compound of any of Claims 1-6, further comprising adhesion promoters; biocides; anti-fogging agents; anti-static agents; bonding, blowing and foaming agents; dispersants; fillers and extenders; fire and flame retardants

and smoke suppressants; impact modifiers; initiators; lubricants; micas; pigments, colorants and dyes; plasticizers; additional processing aids; release agents; silanes, titanates and zirconates; slip and anti-blocking agents; stabilizers; stearates; ultraviolet light absorbers; viscosity regulators; waxes; and combinations of them.

8. The compound of any of Claims 1-7, wherein the weight percents of the ingredients comprise:

Styrene-containing thermoplastic elastomer	5-40%
Flame retardant containing ammonium polyphosphate	20-70%
Plasticizer	0-60%
Secondary Polymer(s)	0-30%
Anti-oxidant	0-3%
Thermal Stabilizer	0-3%
Other Optional Additives	0-15%

9. The compound of Claim 9, wherein the weight percents of the ingredients comprise:

Styrene-containing thermoplastic elastomer	15-25%
Flame retardant containing ammonium polyphosphate	30-50%
Plasticizer	15-30%
Secondary Polymer(s)	5-20%
Anti-oxidant	0-1%
Thermal Stabilizer	0-1%
Other Optional Additives	0-5%

10. A thermoplastic article, comprising the compound of any of Claims 1-9.

11. The compound of Claim 1, further comprising expandable graphite filler.

12. The compound of any of Claims 1-9, further comprising expandable graphite filler in amount from 0 to about 30 weight percent of the compound.

13. A thermoplastic article, comprising the compound of Claims 11 or 12, wherein the article is expandable in the presence of heat.

14. The thermoplastic article of Claim 13, wherein the article is in the shape of a door seal and is expandable in the presence of heat at least 300% over its dimension when not heated.