

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



G00002

(43) International Publication Date
14 March 2002 (14.03.2002)


PCT

(10) International Publication Number
WO 02/20665 A2

- (51) International Patent Classification⁷: **C08L 97/02 //** (C08L 97/02, 3:02, 101:00) (C08L 97/02, 101:00)
- (74) Agent: **TAN JINHWEE, EUNICE & LIM CHOOENG,**
PO Box 1381, Robinson Road, Singapore 902731 (SG)
- (21) International Application Number: **PCT/SG01/00178**
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW
- (22) International Filing Date:
7 September 2001 (07.09.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
200005117-7 9 September 2000 (09.09.2000) SG
200104759-6 8 August 2001 (08.08.2001) SG
- (84) Designated States (*regional*): ARIPO patent (GI, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- (71) Applicant and
(72) Inventor: **CHOO, Thiam, Huay, Gary** [SG/SG], 139
Namly Avenue, Singapore 267704 (SG)

[Continued on next page]

(54) Title: **MOULDING MIXTURE FOR MANUFACTURE OF MOULDBLE PRODUCT**



(57) Abstract: The present invention relates to a moulding mixture, for manufacturing moulded products. The moulding mixture including (i) 40 to 60 wt % plant fibre pieces and optionally combined with added starch, and (ii) 10 to 55 wt % water and 3 to 10 wt % one or more water-soluble binding agents or adhesives. The amount of starch added in between 0 and 10 wt preferably 0 to 2 wt % or 2 to 10 wt %.



162162

WO 02/20665 A2