

SEMICONDUCTOR ASSEMBLIES, STACKED SEMICONDUCTOR
DEVICES, AND METHODS OF MANUFACTURING
SEMICONDUCTOR ASSEMBLIES AND STACKED
SEMICONDUCTOR DEVICES

5 TECHNICAL FIELD

The present invention is related to stacked semiconductor devices and methods for manufacturing stacked semiconductor devices.

BACKGROUND

10 Packaged semiconductor devices are utilized in cellular phones, pagers, personal digital assistants, computers and many other types of consumer or industrial electronic products. Microelectronics manufacturers are developing more sophisticated devices in smaller sizes. To meet current design criteria, semiconductor components have increasingly dense arrays of input/output terminals within decreasing "footprints" on printed circuit boards (i.e. the height and surface area the device occupies on a printed circuit board).

15 Semiconductor devices are typically fabricated on semiconductor wafers or other types of workpieces using methods that simultaneously process a large number of dies (i.e., chips). Microelectronic devices generally have a die that includes an integrated circuit having a high density of very small components. The dies typically include an array of bond-pads or other external electrical terminals for transmitting supply voltage, signals, etc. to and from the
20 integrated circuitry. The bond-pads are usually very small and are assembled in dense arrays having fine pitches between bond-pads.

One technique to increase the density of microelectronic devices within a given footprint is stacking one microelectronic die on top of another. Through-substrate interconnects, for example, can electrically connect bond pads at a front side of a lower die
25 with contacts at a back side of the lower die such that bond pads of a top die can be electrically coupled to the back side contacts of the lower die. An existing process for stacking such dies includes thinning first and second wafers by removing material from the back side of the wafers to (1) expose interconnect contact points on the back side of the dies,

and (2) reduce the thickness of the dies. The second wafer is generally thinned to not less than 300 microns. After thinning, the second wafer is singulated (i.e., cut) and separate dies from the second wafer are stacked onto dies on the first wafer. An encapsulant is subsequently disposed between individual second dies, and the first wafer and encapsulant are cut to separate stacked devices.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a cross-sectional view schematically illustrating stacked semiconductor devices in accordance with an embodiment of the invention.

Figures 2A-2F are cross-sectional views schematically illustrating stages of a method for manufacturing semiconductor assemblies.

Figure 3 is a cross-sectional view of a portion of a stacked device as shown in Figure 2F illustrating three stacked microelectronic dies.

Figure 4 is a flow chart illustrating a method for manufacturing stacked die semiconductor assemblies.

Figure 5 is a flow chart illustrating another method for manufacturing stacked die semiconductor assemblies.

Figure 6 is a schematic view of a system that incorporates stacked semiconductor devices.

DETAILED DESCRIPTION

Specific details of several embodiments of the disclosure are described below with reference to semiconductor assemblies, stacked semiconductor devices, methods of manufacturing semiconductor assemblies, and methods of forming stacked semiconductor devices. The devices are manufactured on semiconductor wafers that can include substrates upon which and/or in which microelectronic devices, micromechanical devices, data storage elements, optics, read/write components, and other features are fabricated. For example, SRAM, DRAM (e.g., DDR/SDRAM), flash memory (e.g., NAND/memory), processors, imagers, and other types of devices can be constructed on semiconductor wafers. Although many of the embodiments are described below with respect to semiconductor wafers, other types of devices manufactured on other types of substrates (e.g., dielectric or conductive

substrates) may be within the scope of the invention. Moreover, several other embodiments of the invention can have different configurations, components, or procedures than those described below in this section. A person of ordinary skill in the art, therefore, will accordingly understand that other embodiments of the invention may have additional
5 elements, or still more embodiments may not have several of the features and elements shown and described below with reference to Figures 1-6.

Figure 1 is a cross-sectional view that schematically illustrates a semiconductor assembly 100. In this embodiment, the semiconductor assembly 100 includes a semiconductor wafer 110 having a plurality of first microelectronic dies 120 (identified
10 individually by reference numbers 120a and 120b), a temporary carrier 130 releasably attached to an active side 112 of the wafer 110, and a plurality of singulated second microelectronic dies 140 (identified individually by reference numbers 140a and 140b). Individual second dies 140a and 140b are attached to a back side 114 of the wafer 110 in a die pattern corresponding to the arrangement of the first dies 120a and 120b, respectively. The
15 stacked first/ second dies 120a/140a and 120b/140b form stacked microelectronic devices 150a and 150b, respectively. The wafer 110 can be releasably attached to the temporary carrier 130 (e.g. carrier substrate) using an adhesive layer 132 such as an adhesive film, epoxy, tape, paste, or other suitable material that secures the wafer 110 in place during processing. The adhesive 132 should have suitable release characteristics for removing the
20 carrier 130 from the wafer 110 and/or stacked microelectronic devices 150 following singulation.

In the illustrated embodiment of the assembly 100, the first dies 120 are at the active side 112 of the wafer 110. Individual first dies 120 can include first integrated circuits 122 (shown schematically) and a plurality of first terminals 124 (e.g. bond pads) electrically
25 coupled to the first integrated circuits 122 and exposed at the active side 112 of the wafer 110. In the specific embodiment shown, the first terminals 124 are in contact with the adhesive layer 132; however, in other arrangements, the individual first dies 120 may include a redistribution structure intermediate the first terminals 124 and the adhesive layer 132. The individual first dies 120 further include first through die interconnects 125 electrically
30 coupling the first terminals 124 to corresponding first back side contacts 126. For example, the plurality of first dies 120 can have a first via 127 that extends through a final thickness T_1 of the wafer substrate 110 in alignment with at least a portion of the first terminals 124. The

first via 127 can then be at least partially filled with a conductive material, such as copper, to form the first through die interconnect 125. The first interconnects 125 can accordingly carry electrical signals and power between the first terminals 124 and the first contacts 126. In some embodiments, the first dies 120 can be individually tested before attaching the
5 temporary carrier 130 to the active side 112 of the wafer 110. From the test, a plurality of known good first dies 120a and a plurality of known bad first dies 120b can be determined and marked for reference.

In the embodiment shown in Figure 1, the wafer 110 can be thinned to the final thickness T_1 through suitable processing steps such as back grinding, chemical-mechanical
10 planarization, polishing, etc. Removing material from the back side 114 of the wafer 110 can expose the first back side contacts 126, and etching or other further processing can remove additional material from the back side 114 of the wafer 110 such that the exposed contacts 126 project beyond the back side 114 of the wafer 110. In some embodiments, thinning the wafer 110 can result in a final wafer thickness T_1 of approximately less than 100 microns. In
15 other embodiments, the wafer thickness T_1 can be approximately less than 50 microns, and in further embodiments the wafer 110 can have a thickness T_1 of approximately 20 to 150 microns.

In the specific embodiment shown in Figure 1, the second dies 140 can be the same as the first dies 120, or the second dies 140 can be different than the first dies 120. Individual
20 second dies 140 can include a second active side 142, a second back side 144, a second integrated circuit 145, and second terminals 146 at the second active side 142 that are electrically coupled to the second integrated circuit 145. The separate second dies 140 can further include a plurality of second through die interconnects 147 extending through second vias 149 from the second terminals 146 at the second active side 142 to second backside
25 contacts 148 at the second back side 144.

The plurality of second dies 140 have a final die thickness T_2 . As illustrated, the final die thickness T_2 of the individual second dies 140 is uniform. Furthermore, the conductive material of the second through die interconnects 147 extends beyond the thickness T_2 to provide stud-shaped second contacts 148 at the second back side 144 of the second dies 140.
30 The second die thickness T_2 can be approximately less than 100 microns. In other embodiments, however, the final second die thickness T_2 can be approximately less than 50

microns, and in further embodiments, the plurality of second dies 140 can have a final thickness T_2 of approximately 20 to 150 microns.

5 The second dies 140 are attached to the corresponding first dies 120 such that the second terminals 146 are electrically coupled to the first contacts 126 at the back side 114 of the wafer 110. Before mounting the second dies 140, a soft malleable metal, such as nickel with aluminum, can be plated through under bump metallurgy (UBM) processing to form plated pads 152 at the second active side 142 of the second dies 140. UBM aluminum plated pads 152 can form suitable electrical connections with copper and other electrically conductive materials used to form the first and second through die interconnects 125, 147.

10 The UBM plated pads 152, in conjunction with the stud-shaped first contacts 126, space the second dies 140 apart from the back side 114 of the wafer 110 by a stand-off height. An underfill material 154 can be disposed between the back side 114 of the wafer 110 and the plurality of stacked second dies 140 to fill the stand-off space and provide support for the stacked second dies 140.

15 Before stacking the second dies 140 onto the first dies 120, the second dies 140 can also be individually tested to determine known good second dies 140a and known bad second dies 140b. As shown in Figure 1, known good second dies 140a are mounted to corresponding known good first dies 120a to form a plurality of known good stacked devices 150a. Likewise, known bad second dies 140b are mounted to corresponding known bad first

20 dies 120b to form known bad stacked devices 150b.

The singulated second dies 140 are spaced apart from each other creating a plurality of gaps 156. In the illustrated embodiment, an encapsulant material 158 (e.g., an epoxy) is disposed in the gaps 156 between the second dies 140. The individual stacked microelectronic devices 150 can be separated from one another by cutting through the encapsulant material 158 in the intervening gaps 156 and through the wafer 110 along lines A-A. After singulation, known bad stacked devices 150b can be discarded.

25

The embodiment of the stacked devices 150 illustrated in Figure 1 have an ultra-thin profile enabled by the thin final thicknesses T_1 and T_2 of both of the individual stacked dies 120 and 140. As previously described, there is a continuous drive among semiconductor manufacturers to reduce the "footprint" and height of semiconductor components. In

30 conventional devices, both the first and second dies are fully thinned to their final thicknesses

at the wafer level using temporary carriers for supplying structural support during back grinding and other thinning techniques. In conventional devices, the fully thinned second dies are accordingly singulated and stacked on corresponding first dies at their final thickness. The present inventor recognized that handling the second dies after thinning and singulation is challenging because the thinned individual second dies are fragile and subject to breaking. Consequently, conventional second or top dies are not thinned to final thicknesses less than 300 microns. Following discovery of this problem and the limitations of conventional techniques, the present inventor developed new processes for forming stacked die assemblies 100 with top dies substantially less than 300 microns thick.

Figures 2A-2F illustrate stages of a specific embodiment of a method for manufacturing semiconductor assemblies 100. Figure 2A illustrates a stage of the method at which the front side 112 of the wafer 110 is releasably attached to the temporary carrier 130 by the adhesive layer 132. At this point, the wafer 110 has an initial thickness T_i between the front side 112 and the back side 114. The initial thickness T_i of the wafer 110 can be approximately 500 to 1000 microns (e.g., fully thick before any thinning). In other embodiments, the wafer 110 may be partially thinned before it is attached to the carrier substrate 130 (e.g., T_i of approximately 300 to 700 microns). The conductive material for the through die interconnects 125 can be embedded within the substrate of the wafer 110 at an intermediate depth D_1 at this stage of processing.

Figure 2B illustrates a stage after the wafer 110 has been thinned from the initial thickness T_i to the desired thickness T_1 . For example, material can be removed from the back side 114 of the wafer 110 using a suitable back grinding process in which the temporary carrier 130 and wafer 110 are mounted in a grinding machine. In the embodiment shown in Figure 2B, material has been removed from the back side 114 of the wafer 110 to at least the intermediate depth D_1 to expose the first back side contacts 126 of the first through die interconnects 125. As described above with reference to Figure 1, the thickness T_1 can be less than approximately 150 microns, 100 microns, or even less than approximately 50 microns. For example, the thickness T_1 can be about 20-150 microns. Further processing, such as etching, can remove additional material from the back side 114 of the wafer 110 such that the first contacts 126 project beyond the surface of the substrate and have an elevated stud-shape. In some embodiments, the first contacts 126 can project 5 to 10 microns beyond the surface of the back side 114 of the wafer 110.

Referring next to Figure 2C, a plurality of singulated second dies 140 are stacked on the back side 114 of the wafer 110 and spaced apart from each other by intervening gaps 156 so that the second dies 140 are arranged in the die pattern of the first dies 120. At this stage, individual second dies 140 have a handling thickness T_h between a first side 142 (e.g., the second active side 142 of Figure 1) and a second side 144 (e.g., the second back side 144 of Figure 1) opposite the first side 142. The second dies 140 can be full-thick when attached to the wafer 110; however, in some arrangements, the second dies 140 can be partially thinned when attached to the wafer 110. For example, the handling thickness T_h can be approximately greater than 300 microns. In other embodiments the handling thickness T_h can be approximately 500 to 1000 microns. The handling thickness T_h of the second dies 140 is generally such that the second contacts 148 of the second through die interconnects 147 are located at an intermediate depth D_2 where they are not exposed on the second side 144 when the second dies 140 are stacked on the first dies 120.

The second dies 140 can be attached to corresponding first dies 120 by placing the second terminals 146 with overlaying plated pads 152 in contact with corresponding first contacts 126 and using a reflow process, or other thermal heating process, to electrically and physically couple the second dies 140 to corresponding first dies 120. As mentioned previously, the second dies 140 can be individually tested to ensure that known good second dies 140a are attached to known good first dies 120a to form known good stacked devices 150a, and that known bad second dies 140b are attached to known bad first dies 120b to form known bad stacked devices 150b.

Figure 2D illustrates a subsequent stage of the method in which the underfill material 154 has been dispensed between the thinned wafer 110 and the plurality of stacked second dies 140. Referring next to Figure 2E, the encapsulant material 158 is deposited in the gaps 156 between the stacked second dies 140 to at least partially encapsulate the stacked microelectronic devices 150. The encapsulant material 158 can be deposited in the gaps 156 using a needle-like dispenser, stenciling, molding, a glob-type dispensing process, or other suitable technique. The encapsulant material 158 is generally a polymer or other suitable material that protects the stacked devices 150. The encapsulant material 158 can fill the gaps 156 to the extent that the encapsulant material 158 is generally co-planar or below the second side 144 of the second dies 140. The upper surface of the encapsulant material 158, however,

can project above the second side 144 so long as the encapsulant material 158 does not interfere with subsequent back grinding/thinning processes.

Figure 2F illustrates a stage of the method after the second dies 140 have been thinned from the handling thickness T_h to the desired thickness T_2 . The semiconductor assembly 100
5 can be mounted in a grinding machine and the second side 144 of the second dies 140 can be thinned simultaneously to the desired thickness T_2 using back grinding, chemical-mechanical planarization, or other suitable processes. The second dies 140 are accordingly thinned after they have been mounted to the first dies 120. Removing material from the second side 144 of the second dies 140 through a back grinding process can yield a uniform thickness T_2 across
10 the plurality of second dies 140, and the underfill 154 and the encapsulant material 158 can support and protect the stacked first and second dies 120, 140 from downward forces during the grinding process.

As shown, the second dies 140 are thinned to at least the depth D_2 to expose the second contacts 148 of the second through die interconnects 147. As described above with
15 reference to Figure 1, the thickness T_2 can be less than approximately 150 microns, 100 microns, or in some embodiments less than approximately 50 microns. The thickness T_2 , for example, can be about 20 to 150 microns.

After forming the semiconductor assembly 100, the temporary carrier 130 can be removed from the active side 112 of the wafer 110 and the stacked microelectronic devices
20 150 can be separated from each other by cutting through the encapsulant material 158 and through the wafer 110 along lines A-A. Alternatively, the temporary carrier 130 can also be cut along lines A-A and be removed from the stacked devices 150 following separation of the stacked devices 150. Furthermore, the known bad stacked devices 150b can be discarded following the separation process.

25 The second contacts 148 can also provide electrical connections for additional stacked dies such that an additional plurality of dies (not shown) can be mounted on the second dies 140 followed by a simultaneous thinning process as described above. For example, Figure 3 illustrates a portion of the semiconductor assembly 100 (indicated in broken lines in Figure 2F) with a third die 302 attached to the second side 144 of the second die 140. Figure 3
30 shows an enlarged portion of the first through die interconnect 125 extending through the wafer 110 to the first contact 126 which is bonded to the plated pad 152. Power and signals

can then be routed through the second terminal 146 and the second through die interconnect 147 to the second contact 148. The second contact 148 can then be bonded to a second plated pad 304 which is electrically connected to a third terminal 306 and a third through die interconnect 308.

5 In the illustrated embodiment, the third through die interconnect 308 extends from a front side 310 of the third die 302 to a back side 312 of the third die 302 and culminates in a third contact 314 on the back side 312 of the third die 302. Additional underfill material 316 can be dispersed between the second and third dies 140, 302. Furthermore, the third die 302 can have an initial thickness (not shown) that can be thinned to a desired thickness T_3 through
10 a back grinding process after the third die 302 has been attached to the second die 140. In one embodiment, the desired thickness T_3 is less than approximately 150 microns, 100 microns, or 50 microns. The thickness T_3 can accordingly be about 20 to 150 microns.

Figure 4 is a flow chart of an embodiment of a method 400 for manufacturing stacked semiconductor assemblies. The method 400 can include mounting a semiconductor wafer to
15 a temporary carrier (block 410). The wafer can have a plurality of first dies arranged in a die pattern on the wafer. The method 400 can further include thinning the wafer (block 420). Additionally, the method 400 can include attaching a plurality of singulated second dies to corresponding first dies, wherein the second dies are arranged in the die pattern and spaced apart from each other by gaps (block 430). After attaching the second dies to the first dies,
20 the method 400 can further include disposing encapsulating material in the gaps between the second dies (block 440) and thinning the second dies (block 450).

Figure 5 is a flow chart of another embodiment of a method 500 for manufacturing stacked semiconductor assemblies. The method 500 can include testing a plurality of first dies to determine known good first dies and known bad first dies (block 510). The method
25 500 can also include testing a plurality of second dies to determine known good second dies and known bad second dies (block 520). Additionally, the method 500 can include attaching known good second dies to known good first dies to form a plurality of good stacked devices (block 530). Furthermore, the method 500 can include attaching known bad second dies to known bad first dies to form a plurality of bad stacked devices (block 540).

30 The illustrated embodiment of the stacked first and second dies 120, 140 can be thinned to a greater degree than devices manufactured using conventional die stacking

techniques. For example, by stacking the second dies 140 onto the first dies 120 while the second dies 140 are sufficiently thick to be handled without breaking, and then subsequently thinning the second dies 140, both the first and second dies 120, 140 can be thinned to less than 300 microns in the final device (e.g., 20-150 microns). Furthermore, in some arrangements, several layers of dies can be added while at a robust thickness and then be thinned. Because of the extreme thinness of the stacked dies, several layers (e.g. three, four, five, etc.) of dies can be stacked to form multi-layer stacked microelectronic devices in a low-profile package.

The individual first and second dies 120, 140 can also be tested before stacking the dies. Defective dies (known bad dies) can be detected and stacked together so that entire defective stacked devices 150b can be discarded. Also, by stacking the singulated known bad second dies 140b onto known bad first dies 120b, the second known bad dies 140b can support a polishing or grinding pad to enable wafer-level thinning after stacking the second dies 140 onto the first dies 120. The throughput of good stacked devices 150a can accordingly be increased because the individual known good dies will only populate other known good dies.

The illustrated embodiments of microelectronic devices 150 also enable a wide range of mounting parameters that can be used during the manufacturing process, including a wide variety of suitable underfill materials 154. The electrical connections between first contacts 126 and the plated pads 152 can be enhanced compared to connections made from stacking pre-thinned second dies. For example, because the handling thickness T_h is large, the second dies 140 are quite strong and can withstand high down forces when mounting the thick second dies 140 to the corresponding first dies 120. Moreover, the down forces exerted during the thinning of the second dies 140 also press the second dies 140 against the first dies 120. The high down forces produce better connections to avoid undesirable disconnects.

Figure 6 illustrates a system 600 that includes a stacked semiconductor device as described above with reference to Figures 1-5. More specifically, a stacked semiconductor device as described above with reference to Figures 1-5 can be incorporated into any of a myriad of larger and/or more complex systems, and the system 600 is merely a representative sample of such as system. The system 600 can include a processor 601, a memory 602 (e.g., SRAM, DRAM, flash, or other memory devices), input/output devices 603, and/or subsystems and other components 604. The stacked semiconductor devices may be included

in any of the components shown in Figure 6. The resulting system 600 can perform any of a wide variety of computing processing, storage, sensing, imaging, and/or other functions. Accordingly, the system 600 can be, without limitation, a computer and/or other data processor, for example, a desktop computer, laptop computer, Internet appliance, hand-held
5 device, multi-processor system, processor-based or programmable consumer electronic, network computer, and/or mini-computer. Suitable hand-held devices for these systems can include palm-type computers, wearable computers, cellular or mobile phones, personal digital assistants, etc. The system 600 can further be a camera, light or other radiation sensor, server and associated server subsystems, and/or any display device. In such systems, individual dies
10 can include imager arrays, such as CMOS imagers. Components of the system 600 may be housed in a single unit or distributed over multiple, interconnected units (e.g., though a communications network). The components of the system 600 can accordingly include local and/or remote memory storage devices and any of a wide variety of computer-readable media.

From the foregoing, it will be appreciated that specific embodiments of the invention
15 have been described herein for purposes of illustration, but that various modifications may be made without deviating from the spirit and scope of the invention. For example, specific elements of any of the foregoing embodiments can be combined or substituted for elements in other embodiments. Accordingly, the invention is not limited except as by the appended claims.

CLAIMS

I/We claim:

1. A method of manufacturing stacked semiconductor assemblies, comprising:
mounting a semiconductor wafer to a temporary carrier wherein the semiconductor wafer has a plurality of first dies arranged in a die pattern on the semiconductor wafer, the individual first dies having a first terminal at a first side and a through-die interconnect, wherein the through-die interconnect is in contact with the first terminal and extends from the first terminal at the first side towards a second side of the semiconductor wafer, wherein the through-die interconnects are spaced apart from the second side of the semiconductor wafer;
thinning the semiconductor wafer to expose conductive ends of the through-die interconnects at the second side such that exposed conductive material of the conductive ends projects beyond an exposed surface of the semiconductor wafer at the second side;
attaching a plurality of singulated second dies to corresponding first dies, wherein the second dies are arranged in the die pattern and spaced apart from each other by gaps, the individual second dies having a second terminal in contact with one of the exposed and protruding conductive ends of the through-die interconnects;
disposing an encapsulating material in the gaps between the second dies; and
thinning the second dies after attaching the second dies to the first dies.
2. The method of claim 1 wherein thinning the second dies includes grinding a back side of the second dies.
3. The method of claim 1, further comprising cutting through the encapsulating material in the gaps and cutting the semiconductor wafer to singulate stacked microelectronic devices having a first die and a corresponding second die.

4. The method of claim 1 wherein:

before mounting the semiconductor wafer to the temporary carrier, the method further comprises forming the through-die interconnects in at least a portion of the individual first dies in electrical contact with the first terminal;
attaching the second dies to the first dies further comprises electrically coupling the second terminals of the second dies to corresponding exposed through-die interconnects.

5. A method of manufacturing stacked semiconductor assemblies, comprising:

mounting a semiconductor wafer to a temporary carrier wherein the semiconductor wafer has a plurality of first dies arranged in a die pattern on the semiconductor wafer, the individual first dies having a first terminal at a first side and a through-die interconnect in contact with the first terminal and extending from the first side towards a second side of the semiconductor wafer, wherein the through-die interconnects are spaced apart from the second side of the semiconductor wafer;
thinning the semiconductor wafer to expose the through-die interconnects at the second side;
attaching a plurality of singulated second dies to corresponding first dies, wherein the second dies are arranged in the die pattern and spaced apart from each other by gaps, the individual second dies having a second terminal in contact with one of the exposed through-die interconnects;
disposing an encapsulating material in the gaps between the second dies; and
thinning the second dies after attaching the second dies to the first dies;
before attaching the plurality of second dies to corresponding first dies, the method further comprises testing individual first dies and individual second dies to determine known good first and second dies and known bad first and second dies; and
attaching the second dies to corresponding first dies comprises attaching known good second dies to known good first dies and attaching known bad second dies to known bad first dies to form a plurality of known good stacked devices and a plurality of known bad stacked devices.

6. The method of claim 1, further comprising:
attaching singulated third dies to corresponding second dies such that the third dies
are spaced apart from each other by gaps;
disposing additional encapsulant material in the gaps between the third dies; and
removing material from a back side of the third dies after disposing the encapsulant
material in the gaps between the third dies.

7. The method of claim 1 wherein the individual second dies have a handling
thickness when the second dies are attached to the first dies, and thinning the second dies
comprises reducing the thickness of the second dies to about 20-150 microns.

8. The method of claim 1 wherein the individual second dies have a handling
thickness when the second dies are attached to the first dies, and thinning the second dies
comprises reducing the thickness of the second dies to less than 100 microns.

9. The method of claim 1 wherein the semiconductor wafer has an initial
thickness before thinning of approximately 700-1000 microns, and thinning the
semiconductor wafer comprises reducing the thickness to approximately less than 50 microns,
wherein the individual second dies have a handling thickness greater than 150 microns when
the second dies are attached to the first dies, and thinning the second dies comprises reducing
the thickness of the second dies to about 20-150 microns.

10. The method of claim 1 wherein the through-die interconnects of adjacent first
dies are spaced apart from one another.

11. The method of claim 1, further comprising keeping the semiconductor wafer
mounted to the temporary carrier while thinning the semiconductor wafer, attaching the
plurality of singulated second dies to corresponding first dies, disposing the encapsulating
material in the gaps between the second dies, and thinning the second dies.

12. A method of manufacturing semiconductor workpieces, comprising:

reducing an initial thickness of a semiconductor wafer between a front side of the wafer and a back side of the wafer, wherein the semiconductor wafer has a plurality of first dies individually having a first terminal and first interconnects in contact with the first terminal and extending between the first terminal at the front side and the back side of the semiconductor wafer, wherein the first interconnects are spaced apart from the back side of the semiconductor wafer; exposing the first interconnects at the back side via reducing the initial thickness of the semiconductor wafer, wherein exposed conductive material of the conductive ends of the first interconnects project beyond an exposed surface of the semiconductor formed by reducing the initial thickness of the semiconductor wafer; mounting a plurality of separated second dies to corresponding first dies in a stacked configuration to form a plurality of stacked microelectronic devices, wherein individual second dies have second interconnects connected to second terminals on a first side of the second die and extending to an intermediate level such that the second interconnects are not exposed on a second side of the second die opposite the first side, the second terminals being in contact with the conductive end of one of the exposed first interconnects; at least partially encapsulating the stacked devices; and thinning the second dies and exposing the second interconnects on the second side after at least partially encapsulating the stacked devices.

13. The method of claim 12 wherein reducing the initial thickness of the semiconductor wafer comprises reducing the initial thickness between the front side and the back side to approximately less than 100 microns, and wherein thinning the second dies comprises reducing a second die thickness between the first and second sides to less than 300 microns.

14. A method of manufacturing semiconductor workpieces, comprising:

reducing an initial thickness of a semiconductor wafer between a front side of the wafer and a back side of the wafer, wherein the semiconductor wafer has a

plurality of first dies individually having a first terminal and first interconnects in contact with the first terminal and extending between the front side and the back side of the semiconductor wafer, wherein the first interconnects are spaced apart from the back side of the semiconductor wafer;
exposing the first interconnects at the back side via reducing the initial thickness of the semiconductor wafer;
mounting a plurality of separated second dies to corresponding first dies in a stacked configuration to form a plurality of stacked microelectronic devices, wherein individual second dies have second interconnects connected to second terminals on a first side of the second die and extending to an intermediate level such that the second interconnects are not exposed on a second side of the second die opposite the first side, the second terminals being in contact with one of the exposed first interconnects;
at least partially encapsulating the stacked devices;
thinning the second dies and exposing the second interconnects on the second side after at least partially encapsulating the stacked devices;
before mounting the plurality of second dies to corresponding first dies, testing individual first dies and individual second dies to determine known good first and second dies and known bad first and second dies; and
mounting the second dies to corresponding first dies comprises mounting known good second dies to known good first dies arranged in a stacked configuration and mounting known bad second dies to known bad first dies arranged in a stacked configuration to form a plurality of known good stacked devices and known bad stacked devices.

15. The method of claim 12 wherein thinning the second dies comprises simultaneously thinning the second dies to a thickness between the first and second sides of approximately less than 300 microns.

16. The method of claim 12 wherein:
before encapsulating the stacked devices, the method further comprises dispensing an underfill material between the second dies and the semiconductor wafer; and

thinning the second dies includes grinding the second sides of the second dies while in a stacked configuration.

17. The method of claim 13 wherein the initial thickness of the semiconductor wafer is approximately 500-1000 microns and the second die has a thickness of approximately 500-1000 microns after the mounting stage but before the thinning stage.

18. A method of manufacturing semiconductor assemblies, the method comprising:

forming first and second semiconductor wafers having front sides and back sides opposite the front sides and an array of dies at the front sides arranged in a die pattern, the individual dies including an integrated circuit and a terminal electrically coupled to the integrated circuit;

forming a plurality of interconnects in electrical contact with the die terminals on the first and second wafers;

attaching a carrier substrate to the front side of the first wafer;

processing the back side of the first wafer to form a thinned base wafer and to expose the interconnects so as to expose conductive material of the interconnect studs such that the exposed conductive material protrudes from the back side of the assembly;

dividing the second wafer to form singulated second dies;

populating the first dies with singulated second dies to form an array of stacked semiconductor devices in the die pattern, the terminals on the front side of the second dies being in contact with one of the exposed interconnect studs on the first wafer, wherein the terminals on the front side of the second dies are electrically coupled with the corresponding interconnect studs of the first dies;

at least partially encapsulating the stacked devices; and

grinding the back side of the second dies after encapsulating the stacked devices.

19. A method of manufacturing semiconductor assemblies, the method comprising:

forming first and second semiconductor wafers having front sides and back sides opposite the front sides and an array of dies at the front sides arranged in a die pattern, the individual dies including an integrated circuit and a terminal electrically coupled to the integrated circuit;

forming a plurality of interconnects in electrical contact with the die terminals on the first and second wafers;

attaching a carrier substrate to the front side of the first wafer;

processing the back side of the first wafer to form a thinned base wafer with exposed interconnect studs at the back side of the first wafer;

dividing the second wafer to form singulated second dies;

populating the first dies with singulated second dies to form an array of stacked semiconductor devices in the die pattern, the terminals on the front side of the second dies being in contact with one of the exposed interconnect studs on the first wafer, wherein the terminals on the front side of the second dies are electrically coupled with the corresponding interconnect studs of the first dies;

at least partially encapsulating the stacked devices;

grinding the back side of the second dies after encapsulating the stacked devices;

before populating the first dies with the second dies, testing individual first dies and second dies to determine known good first and second dies and known bad first and second dies; and

populating the first dies with second dies comprises attaching known good second dies to known good first dies arranged in a stacked configuration and attaching known bad second dies to known bad first dies arranged in a stacked configuration to form a plurality of known good stacked devices and known bad stacked devices.

20. A semiconductor assembly, comprising:

a thinned semiconductor wafer having an active side, a back side opposite the active side, and a plurality of first dies arranged in a die pattern at the active side, wherein individual first dies have an integrated circuit and first through die

interconnects electrically connected to the integrated circuit, and wherein the first through die interconnects extend from the active side of the wafer to the back side of the wafer, and wherein the interconnects have conductive ends and interconnect contacts exposed at the back side of the wafer;

a plurality of separate second dies spaced apart from each other and arranged in the die pattern relative to the thinned semiconductor wafer, individual second dies having a second active side, a second back side, a second integrated circuit, and a second terminal electrically coupled to the second integrated circuit on the second active side, wherein the individual second dies have a thickness of approximately less than 150 microns; and

an underfill material coupling the second dies to the first dies and surrounding and insulating the exposed conductive ends of the interconnects protruding from the backside of the thinned semiconductor wafer.

21. The assembly of claim 20, further comprising an underfill deposited between the first and second dies.

22. The assembly of claim 20 wherein the thickness of the plurality of second dies is substantially uniform across the thinned semiconductor wafer.

23. The assembly of claim 20 wherein the thinned semiconductor wafer has a thickness of approximately less than 100 microns.

24. The assembly of claim 20 wherein the thinned semiconductor wafer has a wafer thickness of approximately less than 50 microns and the thickness of the second die is approximately less than 50 microns.

25. The assembly of claim 20, further comprising:

a plurality of separate third dies spaced apart from each other and arranged in the die pattern relative to the thinned semiconductor wafer, individual third dies having a third active side, a third back side, a third integrated circuit, a third terminal electrically coupled to the third integrated circuit on the third active

side, wherein the third die has a thickness of approximately less than 100 microns.

26. An intermediate stacked semiconductor assembly, comprising:

a thinned semiconductor wafer having an active side, a plurality of first dies arranged in a die pattern, and first through die interconnects extending from the active side to a back side of the wafer;

a plurality of singulated second dies mounted to corresponding first dies, wherein the individual second dies are spaced apart from each other by gaps, and wherein the second dies have a first side, a second side spaced apart from the first side by a handling thickness, and a second interconnect extending from the first side to an intermediate depth in the second die such that the second interconnects are not exposed on the second side of the second dies;

an underfill material coupling the second dies to the first dies and surrounding and insulating exposed conductive ends of the interconnects, wherein the exposed conductive ends extend beyond a backside surface of wafer; and

an encapsulant in the gaps.

27. The assembly of claim 26 wherein the individual second dies have a handling thickness approximately greater than 300 microns.

28. The assembly of claim 26 wherein the thinned semiconductor wafer has a final thickness approximately less than 50 microns.

29. A semiconductor assembly, comprising:

a wafer including a plurality of known good first dies and a plurality of known bad first dies;

a plurality of separated known good second dies attached to corresponding known good first dies, and a plurality of separated known bad second dies attached to corresponding known bad first dies, wherein the second dies are spaced apart from each other by gaps; and

an encapsulant material in the gaps.

30. The assembly of claim 29 wherein the wafer has a thickness approximately less than 100 microns.

31. The assembly of claim 29 wherein the separated second dies have a thickness approximately less than 100 microns.

32. The assembly of claim 29 wherein the known good first dies individually comprise a first integrated circuit electrically coupled to a first terminal and a through die interconnect, and wherein the known good second dies individually comprise a second terminal electrically coupled to a second integrated circuit and an interconnect contact point of the corresponding through die interconnect.

33. A method of manufacturing semiconductor assemblies, the method comprising:

attaching a first front side of a first semiconductor wafer to a carrier substrate, the first semiconductor wafer having an array of first dies at the first front side and arranged in a die pattern, the individual first dies having a first terminal at the first front side and a first interconnect in contact with the first terminal and extending between the first front side and a first back side of the semiconductor wafer, wherein the first interconnects are spaced apart from the first back side of the semiconductor wafer;

removing material from the first back side of the first semiconductor wafer until conductive material of protruding ends of the first interconnects at the first back side are exposed, the first back side being opposite the first front side;

singulating a second wafer into a plurality of singulated second dies individually having a second terminal at a second front side and a second back side opposite the second front side;

stacking the singulated second dies onto the individual first dies with the second front side facing the first back side of the first semiconductor wafer with the second terminal in contact with one of the exposed first interconnects;

at least partially encapsulating the stacked first and second dies; and

removing material from the second back side of the second dies after encapsulating the stacked first and second dies to achieve a target thickness of the second dies.

34. The method of claim 33 wherein removing material from the second back side includes grinding the second back side of the second dies.

35. The method of claim 33, further comprising cutting through the encapsulating material and the first semiconductor wafer to singulate stacked microelectronic devices individually having one of the first dies and one of the corresponding second dies.

36. The method of claim 33 wherein:
stacking the singulated second dies comprises electrically coupling the second terminals at the second front side of the second dies to the corresponding first interconnect of the first dies exposed at the first back side of the first semiconductor wafer.

37. The method of claim 33, further comprising:
attaching a third front side of individual singulated third dies to the corresponding second back side of the second dies;
at least partially encapsulating the first, second, and third dies with an additional encapsulant; and
removing material from a third back side of the third dies after at least partially encapsulating the first, second, and third dies, the third back side being opposite the third front side.

38. The method of claim 33 wherein removing material from the second back side of the second dies includes removing material from the second back side of the second dies after encapsulating the stacked devices to achieve a target thickness of about 20-150 microns.

39. The method of claim 33 wherein removing material from the second back side of the second dies includes removing material from the second back side of the second dies

after encapsulating the stacked devices to achieve a target thickness of about less than 100 microns.

40. The method of claim 33 wherein:

the first semiconductor wafer has a first thickness of approximately 700-1000 microns prior to removing material from the first back side of the first semiconductor wafer;

removing material from the first back side of the first semiconductor wafer includes reducing the thickness of the first semiconductor wafer to approximately less than 50 microns;

the individual second dies have a second thickness greater than 150 microns when the singulated second dies are stacked onto the individual first dies; and

removing material from the second back side of the second dies comprises reducing the second thickness

of the second dies to about 20-150 microns.