

METHOD FOR FORMING DIFFUSION REGIONS IN A SILICON SUBSTRATE

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

[0001] The United States government has a paid-up license in this invention and the right in limited circumstances to require the patent owner to license others on reasonable terms as provided by the terms of DE-FC36-07GO17043 awarded by the DOE.

TECHNICAL FIELD

[0002] Embodiments of the subject matter described herein relate generally to solar cell manufacture. More particularly, embodiments of the subject matter relate to thin silicon solar cells and techniques for manufacture.

BACKGROUND

[0003] Solar cells are well known devices for converting solar radiation to electrical energy. They may be fabricated on a semiconductor wafer using semiconductor processing technology. A solar cell includes P-type and N-type diffusion regions. Solar radiation impinging on the solar cell creates electrons and holes that migrate to the diffusion regions, thereby creating voltage differentials between the diffusion regions. In a backside contact solar cell, both the diffusion regions and the metal contact fingers coupled to them are on the backside of the solar cell. The contact fingers allow an external electrical circuit to be coupled to and be powered by the solar cell.

[0004] Accordingly, techniques for improving the fabrication process and reducing the cost of manufacturing solar cells are generally desirable. Such techniques include printing and curing of dopants on silicon substrates through processes like ink-jet printing. These or other similar embodiments form the background of the current invention.

SUMMARY

[0004a] According to a first aspect, there is provided a method of manufacturing solar cells, the method comprising: depositing, in a liquid phase, an etch-resistant dopant material on a silicon substrate, the etch-resistant dopant material comprising a

dopant source and a solvent; forming a cross-linked matrix in the etch-resistant dopant material using a non-thermal cure of the etch-resistant dopant material, the cross-linked matrix having a structure, and the non-thermal cure causing a phase change of the etch-resistant dopant material from liquid to solid; subsequently, removing the solvent from the etch-resistant dopant material without altering the structure of the cross-linked matrix; and heating the silicon substrate and the etch-resistant dopant material having the cross-linked matrix to a temperature sufficient to cause the dopant source to diffuse into the silicon substrate.

[0004b] According to a second aspect, there is provided a method of manufacturing solar cells, the method comprising: depositing, in a liquid phase, a dopant material on a silicon substrate having a photovoltaic solar cell structure, the dopant material comprising a dopant and a solvent; forming a cross-linked matrix in the dopant material using a non-thermal exposure of the dopant material to ultraviolet light through a photo-polymerization process, the cross-linked matrix having a structure, and the photo-polymerization process causing a phase change of the dopant material from liquid to solid; subsequently, removing the solvent from the dopant material without altering the structure of the cross-linked matrix; and heating the silicon substrate and the dopant material having the cross-linked matrix to a temperature sufficient to cause the dopant to diffuse into the silicon substrate.

BRIEF DESCRIPTION OF THE DRAWINGS

[0005] A more complete understanding of the subject matter may be derived by referring to the detailed description and claims when considered in conjunction with

the following figures, wherein like reference numbers refer to similar elements throughout the figures.

[0006] FIGS 1-9 are cross-sectional representations of a solar cell being fabricated in accordance with an embodiment of the invention

[0007] FIGS 10-17 are cross-sectional representations of a solar cell being fabricated in accordance with another embodiment of the invention

[0008] FIGS 18-31 are cross-sectional representations of a solar cell being fabricated in accordance with yet another embodiment of the invention

DETAILED DESCRIPTION

[0009] The following detailed description is merely illustrative in nature and is not intended to limit the embodiments of the subject matter or the application and uses of such embodiments. As used herein, the word “exemplary” means “serving as an example, instance, or illustration.” Any implementation described herein as exemplary is not necessarily to be construed as preferred or advantageous over other implementations. Furthermore, there is no intention to be bound by any expressed or implied theory presented in the preceding technical field, background, brief summary or the following detailed description.

[0010] One technique for simplifying formation of doped diffusion regions in a silicon substrate during the photovoltaic solar cell manufacturing process is using printed dopant paste, including ink-jet dispensed dopants, on a silicon substrate. The printed dopant paste can be then heated to drive dopant material into the underlying silicon to create a doped diffusion region in the silicon substrate, a step in creating a photovoltaic solar cell. Certain printed dopant pastes can become thermally unstable, resulting in outgassing of dopant material from the dopant paste into the ambient environment. This, in turn, can cause counterdoping, where the outgassed dopant in the ambient environment may re-deposit in undesired areas of the silicon substrate. This thermal instability can manifest during any post-print heating process, including bake and dopant driving processes, when the temperature of the environment is being raised. It should be noted that any reference to a dopant paste refers to a suspension or solution of any type which includes doping materials. The substance need not be a paste, but can be a liquid, solution, suspension, solid, semi-solid, or any other physical state.

[0011] An improvement to the process can be to perform a non-thermal cure process to form a cross-linked matrix in the dopant paste prior to the thermal dopant driving step. In one embodiment, for example, this process can reduce the thermal-driven mass-loss phenomena or outgassing during the heating for dopant driving by photo-polymerization or photo-curing of the dopant paste.

[0012] A method of manufacturing solar cells is disclosed. The method comprises depositing an etch-resistant dopant material on a silicon substrate, the etch-resistant dopant material comprising a dopant source, forming a cross-linked matrix in the etch-resistant dopant material using a non-thermal cure of the etch-resistant dopant material, and heating the silicon substrate and the etch-resistant dopant material to a temperature sufficient to cause the dopant source to diffuse into the silicon substrate.

[0013] Another method of manufacturing solar cells is disclosed. The method comprises depositing a dopant material on a silicon substrate having a photovoltaic solar cell structure, forming a cross-linked matrix in the dopant material using a non-thermal exposure of the etch-resistant dopant material to ultraviolet light through a photo-polymerization process, and heating the silicon substrate of the dopant material to a temperature sufficient to cause the dopant source to diffuse into the silicon substrate.

[0014] Yet another method of manufacturing solar cells is disclosed. The method comprises forming a thin dielectric layer on a surface of a silicon substrate, forming a polysilicon layer over the thin dielectric layer, depositing an etch-resistant dopant material comprising a dopant source material on the polysilicon layer, forming a cross-linked matrix in the etch-resistant dopant material using a non-thermal cure of the etch-resistant dopant material, heating the etch-resistant dopant material to a temperature wherein the dopant source material diffuses into the polysilicon layer, and selectively etching to remove the dopant source material without etching the polysilicon layer.

[0015] The various tasks performed in connection with the manufacturing process shown in FIGS. 2-6 may include any number of additional or alternative tasks such as FIGS. 7-9. The manufacturing process shown in FIGS. 10-17 and FIGS. 18-31 need not be performed in the illustrated order, and it may be incorporated into a more comprehensive procedure, process or fabrication having additional functionality not described in detail herein.

[0016] FIG. 1 illustrates a solar cell **100** comprising a silicon substrate **104**. The solar cell **100** comprises the silicon substrate **104** and an etch-resistant dopant material **110, 112** deposited on the surface of the silicon substrate **104**. The etch-resistant dopant material **110, 112** can be dispensed in liquid or semi-liquid form on the silicon substrate **104** through various techniques, but is not limited to, comprising the following: screen printing, ink-jet printing and spin coating. Although two regions of etch-resistant dopant material **110, 112** are shown, more or fewer can be deposited on the silicon substrate **104** in other embodiments. The etch-resistant dopant material **110, 112** can be formed in repeated patterns, including masked patterns, on the silicon substrate **104**.

[0017] In certain embodiments, each deposition of etch-resistant dopant material **110, 112** can comprise a solvent, a pre-matrix material, and a dopant source **120, 122**. Various embodiments of the etch-resistant dopant material **110, 112** can contain all or some selection of these components, as well as other components, as desired. In certain embodiments, the etch-resistant dopant material **110, 112** can have properties similar to those disclosed in dopant materials described in U.S. Patent Application No. 13/250,215, titled "DOPANT INK COMPOSITION AND METHOD OF FABRICATING A SOLAR CELL THERE FROM", filed on September 30, 2011.

[0018] The dopant source **120, 122** can comprise a single-polarity dopant source including either a positive-type dopant source or negative-type dopant source. For example, a positive-type dopant source can include boron or a boron composite, while a negative-type dopant source can include phosphorus or a phosphorus composite.

[0019] Although referred to as an etch resistant dopant material, the dopant material containing the dopant source and other components described above can in some embodiments have no etch resistance properties accordingly, in some embodiments the dopant material can be used solely for doping and not in any etch process. Additionally, when referred to as etch resistant the dopant material need only be resistant to a single type of etchant. In some embodiments the etch resistant dopant material can resist a wide spectrum of etchants. In other embodiments it can resist a few. Moreover the etch resistant dopant material can be resistant to one type of etchant while susceptible to etching by another type of etchant. Thus the dopant material or etch resistant dopant material is used interchangeably throughout to refer to dopant materials which have the appropriate properties to perform the functions described throughout. Therefore although referred to as an etch resistant dopant

material it should be understood that the appropriate dopant material can be selected for the desired embodiment, depending on whether etch resistance is required or not.

[0020] The configuration of etch-resistant dopant material **110**, **112** in independent groups merely suggests one configuration in which the dopant sources **120**, **122** are intended to be driven into the silicon substrate and, hence, the arrangement into which the etch-resistant dopant materials **110**, **112** can be dispensed. In some embodiments it is possible for a positive-type dopant source to be found in the location of the etch-resistant dopant material **110** and a negative-type dopant source to be found in the etch-resistant dopant material **112**. The opposite can also be true, where negative-type dopant source is dispensed in the location of the etch-resistant dopant material **110** and a positive-type dopant source is dispensed in the etch-resistant dopant material **112**. In another embodiment, it is possible for both the etch-resistant dopant materials **110**, **112** to both contain either only positive-type dopant sources or negative-type dopant sources.

[0021] The solar cell **100** formed can be a back contact, back junction (BCBJ) solar cell in any of a number of embodiments, including those illustrated and described herein. Although the solar cell **100** can have any number of the discussed embodiments it is not limited to the structures described therein.

[0022] FIGS. 2-6 further illustrate processing of solar cell **100** in sequential steps of the solar cell manufacturing process using printed dopants on silicon substrates.

[0023] FIGS. 2-3 illustrate a non-thermal cure of the etch-resistant dopant material **110**, **112** forming a cross-linked matrix **130** on the silicon substrate **104**.

[0024] A non-thermal cure **150** of the etch-resistant dopant material **110**, **112** can be performed after deposition of the etch-resistant dopant material **110**, **112**. A non-thermal cure **150** can be causing a phase change of the etch-resistant dopant material **110**, **112** during the forming of the cross-linked matrix **130** on the silicon substrate **104**. In some embodiments, the non-thermal cure **150** of the etch-resistant dopant material **110**, **112** forming a cross-linked matrix **130** can comprise exposing the etch-resistant dopant material **110**, **112** to non-infrared electromagnetic radiation. The exposure to the non-infrared electromagnetic radiation can further comprise exposure of the etch-resistant dopant material **110**, **112** to ultraviolet light. In some embodiments, the non-thermal cure **150** can further comprise exposure of the etch-resistant dopant material **110**, **112** to light in the visible spectrum. For example, the non-thermal cure **150** can include exposure of the etch-resistant dopant material **110**,

112 to electromagnetic (EM) radiation having a wavelength between 380 and 760 nanometers, including sequences of such EM radiation, such as pulses, flashes, or changing intensity. In certain embodiments, the sequences can include repetitions of the same wavelength of EM radiation, while in others, several different wavelengths of EM radiation can be used in the same sequence.

[0025] In yet another embodiment the non-thermal cure **150** of the etch-resistant dopant material **110, 112** can comprise transmitting acoustic waves toward the etch-resistant dopant material **110, 112**, thereby forming a cross-linked matrix **130** in the etch-resistant dopant material **110, 112** on the silicon substrate **104**.

[0026] FIG. 3 illustrates the ordered structure of the dopant sources **120, 122** is due to the cross-linked matrix **130** within the etch-resistant dopant material **110, 112** formed on the silicon substrate **104**. Although illustrated as a rectilinear grid, the cross-linked matrix **130** present in the dopant material **110, 112** can form any arrangement resulting from the non-thermal cure step **150** and composition of the dopant material **110, 112**. Thus, in certain embodiments, crystalline structures can be formed, as an example. Moreover, although the dopant source **120, 122** is illustrated as arranged at vertices within the cross-linked matrix **130**, the dopant source **120, 122** can be interstitially arranged, or otherwise present in the dopant material **110, 112** without being bonded with or coupled to or integral of the cross-linked matrix **130**. Additionally, the cross-linked matrix **130** need not be a physical arrangement and can instead be formed of chemical bonding, such as covalent bonding, within the dopant material **110, 112**, where such bonds are formed as a result of the non-thermal cure step **150**. Thus, the cross-linked matrix **130** can include spirals, helical, or other structural arrangements, including bonds or linking between such structures.

[0027] FIGS. 4-6 illustrates heating **160** the silicon substrate **104** and the etch-resistant dopant material **110, 112** to a temperature sufficient to cause the dopant source to diffuse **140, 142** into the silicon substrate **104**. Such a diffusion can include interstitial substitution of the dopant source **120** into the silicon lattice. In certain embodiments, the silicon substrate **104** can then be selectively etched to remove the etch-resistant dopant material **110, 112** without etching the silicon substrate **104**.

[0028] FIG. 4 illustrates the thermal heating **160** of the etch-resistant dopant material **110, 112** on the silicon substrate **104** causing the dopant source **120, 122** to diffuse into the silicon substrate **104**. The thermal heating **160** can comprise of raising the temperature of the etch-resistant dopant material **110, 112** on the silicon

substrate **104** to a first temperature of at least 400° Celsius, at most 1200° C anywhere therebetween. In certain embodiments, thermal cycling can be used, raising and lowering the temperature to any desired temperature for any desired length of time to accomplish the dopant diffusion. This process may be performed using specific temperature profiles that are optimized to get the most uniform diffusion of dopant source **120, 122** into the silicon substrate **104**. The dopant source **120, 122** can have a concentration in the diffusion regions **140, 142** of at least 1×10^{17} atoms per cubic centimeter. In other embodiments, greater or lower concentrations of dopant source **120, 122** in the diffusion regions **140, 142** can be present. Any type of doping of the silicon substrate **104** or other target surface can be accomplished using this technique, including interstitial or substitution diffusion.

[0029] FIG. 5 illustrates the diffusion of the dopant sources **120, 122** into the silicon substrate **104** after performing the thermal heating **160**. The dopant source **120, 122** shown in FIG. 5 may comprise a single-polarity dopant source including either a positive-type dopant source or negative-type dopant source resulting in the corresponding polarity in the diffusion regions **140, 142**.

[0030] FIG. 6 illustrates a subsequent step, wherein the silicon substrate **104** is selectively etched to remove the etch-resistant dopant material **110, 112** without etching the silicon substrate **104**, including the diffusion regions **140, 142**. With the etch-resistant dopant material **110, 112** removed, the solar cell **100** comprises at least the silicon substrate **104** and the diffused regions **140, 142**, though earlier processing steps may have added other structures, as later processing steps may also.

[0031] FIG. 7-9 illustrates an alternative embodiment in which the step of reducing the volume of solvent in the etch-resistant dopant material **110, 112** by heating the etch-resistant dopant material to at least 200° Celsius after forming the cross-linked matrix **130** in the reduced etch-resistant dopant material **170, 172** is performed. As shown in FIG. 7, the reduced volume of the etch-resistant dopant material **110, 112** can be caused by heating the silicon substrate **104**, including the etch-resistant dopant material **110, 112**. In certain embodiments, the drive-off of the solvent can be accomplished without altering the structure of the cross-linked matrix **130**. FIGS. 8 and 9 illustrate a subsequent diffusion step, similar to that shown in FIG. 5 above, and a dopant material removal step similar to that shown in FIG. 6 above.

[0032] FIG. 10 illustrates an embodiment of a solar cell **200** formed with a thin dielectric layer **270** atop of the silicon substrate **204**. Unless otherwise indicated, components in FIGS. 10-17 are similar to those described above with reference to FIGS. 1-9, except that the numerical indicator used to designate the component has been incremented by 100. Below the silicon substrate **204** can be an anti-reflective coating (ARC) **280**. These and other elements of a solar cell structure can be present on either side of the solar cell **200** at various points during fabrication of the solar cell **200**. Accordingly, the formation of diffusion regions can occur during any appropriate place in the fabrication process. Thus, an etch-resistant dopant material **210**, **212** can be deposited on the surface of the dielectric layer **270**. The etch-resistant dopant material **210**, **212** can include a member of a chemical group comprising silanes, cyclosilanes, and siloxanes.

[0033] FIG. 11 illustrates exposure of the etch-resistant dopant material **210**, **212** to ultraviolet light **250**. The ultraviolet light **250** cause a phase change in the etch-resistant dopant material **210**, **212**, causing the formation of the cross-linked matrix **230** through a photo-polymerization process. In one embodiment the ultraviolet light exposure **250** of the etch-resistant dopant material **210**, **212** forming a cross-linked matrix **130** can comprise of exposing the etch-resistant dopant material **210**, **212** to electromagnetic radiation having a wavelength of between 8 and 400 nanometers. UV exposure can last for any desired period of time, although a shorter duration of exposure to achieve sufficient cross-linked matrix formation can be beneficial, as compared to a relatively longer duration, for throughput purposes during mass production. The exposure to the ultraviolet light exposure **250** can cause a curing step such as acrylate polymerization, cationic polymerization, thiolene chemical application, and hydrosilane addition.

[0034] FIG. 12 illustrates the cross-linked matrix **230** within the etch-resistant dopant material **210**, **212** formed on the dielectric layer **270**.

[0035] FIG. 13 illustrates the thermal heating **260** of the etch-resistant dopant material **210**, **212**, thereby causing the dopant source **220**, **222** to diffuse into the silicon substrate **204**.

[0036] FIG. 14 illustrates the diffusion of the dopant sources **220**, **222** into the silicon substrate **204** after performing the thermal heating **260** resulting in the diffused region **240**, **242**.

[0037] FIG. 15 illustrates an embodiment of the solar cell **204** further comprising the step of etching the silicon substrate **204** using the etch-resistant dopant material **210, 212** as an etch-mask after forming the cross-linked matrix **230** in the etch-resistant dopant material **210, 212**. The result is an etched away exposed region **290** seen in FIG. 15 that may act as a potential barrier between the diffused region **240** and the diffused region **242**. The type of etch performed can be selected to etch the dielectric layer **270**. Similarly, the underlying silicon substrate **204** can be additionally etched, depending on the selection of etchant and duration of etch bath. The ARC **280** layer can be etched or not, as desired for the embodiment.

[0038] FIG. 16 illustrates the solar cell **200** as a result of performing a selective etching process to remove the etch-resistant dopant material **210, 212** without further etching the silicon substrate **204**. With the etch-resistant dopant material removed, the solar cell **200** is comprised of the diffused region **240** and the diffused region **242** separated by the etched away exposed region within the silicon substrate **204**.

[0039] FIG. 17 illustrates an embodiment wherein etching the silicon substrate **204** using the etch-resistant dopant material **210, 212** as an etch-mask after forming the cross-linked matrix **230** in the etch-resistant dopant material **210, 212** does not damage the silicon substrate **204**, dielectric layer **270**, or any other structure present on the solar cell **200**. Such an etching can be used to further process other structural elements of the solar cell **200** not illustrated for clarity.

[0040] FIG. 18 illustrates a solar cell **300** formed with a dielectric layer **370** formed on top of the silicon substrate **304**. Unless otherwise indicated, components in FIGS. 18-24 are similar to those described above with reference to FIGS. 10-17, except that the numerical indicator used to designate the component has been incremented by 100. In certain embodiments of the solar cell **300**, a polysilicon layer **380** can be formed on top of dielectric layer **370**. An etch-resistant dopant material **310, 312** can be deposited, such as by ink-jet or other dispensation, as described above with reference to FIG. 1, on the surface of the polysilicon layer **380**. The etch-resistant dopant material **310, 312** can include dopant source **320, 322**.

[0041] With reference to FIGS. 19-20, a non-thermal cure **350** of the etch-resistant dopant material **310, 312** can be performed to form cross-linked matrix **330** on the silicon substrate **304**. FIG. 21 illustrates the ordered structure of the dopant sources **320, 322** is due to the cross-linked matrix **330** within the etch-resistant dopant material **310, 312** formed on the polysilicon layer **380**.

[0042] FIGS. 22-24 illustrate the heating 360 of the solar cell 300, including the etch-resistant dopant material 310, 312 and the polysilicon layer 380 to a temperature sufficient to cause the dopant source to diffuse into the silicon substrate 304, as described above with reference to FIGS. 1-9. This process may be performed using specific temperature profiles that are optimized for uniformity of diffusion of dopant source 320, 322 into the polysilicon layer 380, or so as to reach a desired concentration of the dopant source 320, 322 in the silicon substrate 304, thus forming the diffusion regions. Subsequently, the solar cell 300 can be etched to remove the etch-resistant dopant material 310, 312 without etching the silicon substrate 304.

[0043] FIGS. 25-26 illustrate the step of etching the polysilicon layer 380 using the etch-resistant dopant material 310, 314 as an etch-mask after thermal heating 360 the etch-resistant dopant material 310, 312. In certain embodiments, the dielectric layer 370 can be similarly etched. The result is an etched away exposed region 390 that acts as a potential barrier between the diffused regions 340, 342. The etch-resistant dopant material 310, 312 can be subsequently washed or etched from the polysilicon layer 380.

[0044] FIG. 27 illustrates an alternative embodiment of solar cell 300, wherein the etch-resistant dopant material 310, 312 may be dispensed in an arrangement of interdigitated contact fingers 400 on the polysilicon layer 380. In other embodiments, the interdigitated contact fingers 400 can be formed directly atop the silicon substrate 304, while in still others, the interdigitated contact fingers 400 can be formed atop a dielectric layer or other solar cell structure formed on the substrate 304.

[0045] FIGS. 28 to 31 illustrate an alternative embodiment of the solar cell 300, wherein the step of etching the polysilicon layer 380 using the etch-resistant dopant material 310, 312 as an etch-mask is performed following formation of the cross-linked matrix 330. This step can be followed by the thermal heating 360 of the etch-resistant dopant material 310, 312 to diffuse the dopant source 320, 322 into the polysilicon layer 380. The polysilicon layer 380 can then be exposed to a selective etchant to remove the etch-resistant dopant material 310, 312 without etching the polysilicon layer 380 as seen in FIG. 26. In another embodiment, the polysilicon layer 380 can be exposed to an etchant to remove the etch-resistant dopant material 310, 312 while also etching the polysilicon layer 380 resulting in an exposed region 390 that can form a potential barrier between the diffusion regions 340, 342. The etch-resistant dopant material 310, 312 can be subsequently washed or etched from

the polysilicon layer **380** resulting in the solar cell structure illustrated in the embodiment of FIG. 26.

[0046] FIG. 31 illustrates another embodiment of a solar cell. In some embodiments of the solar cell fabrication, etching or washing of the etch-resistant dopant material 310, 312 (including use of an etchant selected for efficacy against the etch-resistant properties of the dopant material 310, 312), the etched-away exposed region **410** may etch through the dielectric layer and can reach and etch the silicon substrate **304**, depending on the etchant and etchant concentration used. Thus, as illustrated in FIG. 31, in some embodiments, the exposed region 410 can extend through the dielectric layer 370. In certain embodiments, structural formation can occur in the exposed region **410**, forming a randomly-texturized pattern.

[0047] The step of etching any of the polysilicon layer 380, dielectric layer 370, or silicon substrate 304 during the fabrication process can be performed at any stage of the overall process after deposition of the etch-resistant dopant material 310, 312. Thus, the material itself can act as an etch mask. In some embodiments, the desired etch-resistant properties can be present prior to the non-thermal cure step, wherein the cross-linked matrix is formed. In other embodiments, the dopant material can act as an etch mask after solvent drive-out, after dopant drive into the dielectric layer, silicon substrate, or a polysilicon layer, after any number of other process steps, so long as it occurs prior to removal of the etch-resistant dopant material. Thus, the etch-resistant dopant material can serve as an mask for etching in any desired process step, contributing to the formation of any solar cell structure illustrated herein or manufacturable using the techniques described.

[0048] In some embodiments, however, the etch-resistant dopant material 310, 312 need not be used as an etching mask at all. The etch-resistant dopant material can be used solely as a dopant source and thereafter removed from the solar cell structure without performing a role in etching other features. In some embodiments, the dopant material, etch-resistant or not, can remain on the solar cell and incorporated into the emitter or contact structure.

[0049] It should be appreciated that the various tasks performed in connection with the solar cell manufacturing process can include any number of additional or alternative tasks. The tasks shown in FIG. 1-31 need not be performed in the illustrated order, and additional steps may be incorporated into a more comprehensive procedure or process having additional functionality not described in detail herein.

[0050] While at least one exemplary embodiment has been presented in the foregoing detailed description, it should be appreciated that a vast number of variations exist. It should also be appreciated that the exemplary embodiment or embodiments described herein are not intended to limit the scope, applicability, or configuration of the claimed subject matter in any way. Rather, the foregoing detailed description will provide those skilled in the art with a convenient road map for implementing the described embodiment or embodiments. It should be understood that various changes can be made in the function and arrangement of elements without departing from the scope defined by the claims, which includes known equivalents and foreseeable equivalents at the time of filing this patent application.

What is claimed is:

1. A method of manufacturing solar cells, the method comprising:
 - depositing, in a liquid phase, an etch-resistant dopant material on a silicon substrate, the etch-resistant dopant material comprising a dopant source and a solvent;
 - forming a cross-linked matrix in the etch-resistant dopant material using a non-thermal cure of the etch-resistant dopant material, the cross-linked matrix having a structure, and the non-thermal cure causing a phase change of the etch-resistant dopant material from liquid to solid; subsequently,
 - removing the solvent from the etch-resistant dopant material without altering the structure of the cross-linked matrix; and
 - heating the silicon substrate and the etch-resistant dopant material having the cross-linked matrix to a temperature sufficient to cause the dopant source to diffuse into the silicon substrate.
2. The method of claim 1, wherein forming the cross-linked matrix in the etch-resistant dopant material using the non-thermal cure of the etch-resistant dopant material comprises exposing the etch-resistant dopant material to non-infrared electromagnetic radiation.
3. The method of claim 2, wherein exposing the etch-resistant dopant material to the non-infrared electromagnetic radiation comprises exposing the etch-resistant dopant material to ultraviolet light.
4. The method of claim 2, wherein exposing the etch-resistant dopant material to the non-infrared electromagnetic radiation comprises exposing the etch-resistant dopant material with light from the visible spectrum or electromagnetic radiation having a wavelength of 380 to 760 nanometers.
5. The method of claim 1, wherein forming the cross-linked matrix in the etch-resistant dopant material using the non-thermal cure of the etch-resistant dopant material comprises transmitting acoustic waves toward the etch-resistant dopant material.
6. The method of claim 1, wherein depositing the etch-resistant dopant material comprises dispensing the etch-resistant dopant on the silicon substrate.

7. The method of claim 6, wherein dispensing the etch-resistant dopant material comprises screen printing the etch-resistant dopant material onto the silicon substrate.
8. The method of claim 6, wherein dispensing the etch-resistant dopant material comprises ink-jet printing the etch-resistant dopant material onto the silicon substrate.
9. The method of claim 6, wherein dispensing the etch-resistant dopant material comprises spin coating the etch-resistant dopant material onto the silicon substrate.
10. The method of claim 6, wherein dispensing the etch-resistant dopant material comprising the dopant source onto the silicon substrate comprises dispensing a dopant material comprising a single-polarity dopant source onto the silicon substrate.
11. The method of claim 10, wherein dispensing the dopant material comprising the single-polarity dopant source onto the silicon substrate comprises dispensing a positive-type dopant onto the silicon substrate.
12. The method of claim 10, wherein dispensing the dopant material comprising the single-polarity dopant source onto the silicon substrate comprises dispensing a negative-type dopant onto the silicon substrate.
13. The method of claim 1, further comprising selectively etching the silicon substrate to remove the etch-resistant dopant material without etching the silicon substrate.
14. The method of claim 1, removing the solvent from the etch-resistant dopant material comprises heating the etch-resistant dopant material to at least 400° Celsius.
15. A method of manufacturing solar cells, the method comprising:
 - depositing, in a liquid phase, a dopant material on a silicon substrate having a photovoltaic solar cell structure, the dopant material comprising a dopant and a solvent;
 - forming a cross-linked matrix in the dopant material using a non-thermal exposure of the dopant material to ultraviolet light through a photo-polymerization process, the cross-linked matrix having a structure, and the photo-polymerization process causing a phase change of the dopant material from liquid to solid; subsequently,

removing the solvent from the dopant material without altering the structure of the cross-linked matrix; and

heating the silicon substrate and the dopant material having the cross-linked matrix to a temperature sufficient to cause the dopant to diffuse into the silicon substrate.

16. The method of claim 15, wherein forming the cross-linked matrix in the dopant material using the non-thermal exposure of the dopant material to the ultraviolet light comprises exposing the dopant material to electromagnetic radiation having a wavelength of 8 to 400 nanometers.

17. The method of claim 15, wherein forming the cross-linked matrix in the dopant material using the non-thermal exposure of the dopant material to the ultraviolet light comprises exposing the dopant material to perform a curing step selected from the group comprising acrylate polymerization, cationic polymerization, thiolene chemical application and hydrosilane addition.

18. The method of claim 15, wherein depositing the dopant material comprises depositing a chemical group comprising a chemical structure selected from the group comprising silanes, cyclosilanes, and siloxanes.

19. The method of claim 15, further comprising the step of etching the silicon substrate using the dopant material as an etch-mask after forming the cross-linked matrix in the dopant material.

20. The method of claim 19, wherein etching the silicon substrate comprises etching at least part of the photovoltaic solar cell structure of the silicon substrate.