

SiO₂ slurry for the production of quartz glass and use of the slurry

The present invention relates a SiO₂ slurry for the production of quartz glass, with the slurry containing a dispersion liquid and amorphous SiO₂ particles with particle
5 sizes up to a maximum of 500 µm, wherein the largest volume fraction is composed of SiO₂ particles with particles sizes in the range of 1 µm to 60 µm, as well as SiO₂ nanoparticles with particle sizes of less than 100 nm in the range of 0.2% by wt. to 15% by wt. (of the entire solids content).

Moreover, the present invention relates to a special use of the slurry.

- 10 The quartz glass to be produced is present as a functional coating of a base body (carrier), or in the form of an opaque or translucent quartz glass component, for instance a band- or plate-shaped quartz glass component.

A great number of different techniques are known for the production of plate-shaped quartz glass components. For instance, US-PS 4,363,647 suggests that a
15 planar layer of SiO₂ soot should be continuously deposited by means of deposition burners on a pre-sintered sand bed and vitrified by means of a ribbon burner while producing a quartz glass plate.

Crucible pulling methods for producing quartz glass plates are also known. However, the lateral dimensions of the plate are limited by the diameter of the
20 crucible. This may lead to corrugations of the withdrawn quartz glass plate, and the achievable dimensional stability is relatively poor. Moreover, the manufacture of opaque quartz glass plates in a melting method is not possible without taking special measures for producing or maintaining opacity in the molten state.

For some time components and layers consisting in part or entirely of opaque
25 quartz glass have been used in applications as optical reflectors for generating a diffuse reflection. These reflectors are distinguished by an adequately high degree of reflection at a very high temperature and thermal shock resistance. DE 10 2004

051 846 A1 describes the manufacture of such a reflector by means of a slurry method. In this process a highly filled, castable, aqueous slurry is prepared that contains amorphous SiO_2 particles and is applied in the form of a slurry layer to a base body of quartz glass. The amorphous SiO_2 particles are produced by wet
5 milling SiO_2 granules and have a particle size in the range of not more than 500 μm , with SiO_2 particles with particle sizes in the range between 1 μm and 50 μm accounting for the greatest volume fraction.

The solids content, the particle size and the particle size distribution of the SiO_2 particles have impacts on the drying shrinkage of the slurry layer. For instance,
10 drying shrinkage can be reduced by using rather coarse SiO_2 particles. Together with a high solids content, SiO_2 particles in the order of 1 μm and 50 μm show advantageous sintering properties and a comparatively low drying shrinkage. Therefore, the known slurry layer can be dried and vitrified without crack formation, which is also due to interactions arising among the SiO_2 particles in the
15 aqueous phase of the slurry.

For the application of the slurry layer to the base body, spraying, electrostatically supported spraying, flow coating, spinning, immersion and dispersion coating are suggested. The slurry layer is subsequently dried and vitrified.

DE 103 19 300 A1 discloses a method for the production of a shaped silica glass
20 body by electrophoretic deposition. A dispersion according to the type mentioned at the outset is here started from, the dispersion containing larger amorphous SiO_2 particles with a D_{50} value between 1 μm and 200 μm and smaller amorphous SiO_2 nanoparticles with a grain size in the range of 1 nm to 100 nm. The fraction of the SiO_2 nanoparticles is preferably between 1-10% by wt., with the larger amorphous
25 SiO_2 particles forming the remainder up to 100%. The filling degree of the dispersion is between 10% by wt. and 80% by wt., preferably between 50% by wt. and 70% by wt., and its viscosity is between 1 - 1000 mPa·s, preferably between 1 - 100 mPa·s.

However, it has been found that the flow behavior of the known slurry is not
30 optimal for some coating techniques. With a highly filled slurry according to DE 10

2004 051 846 A1, for instance, „dressing“ or spreading by doctor blade of the slurry mass turns out to pose problems, and although the low-viscosity dispersion according to DE 103 19 300 A1 can be poured out easily, it flows off from the coated surface immediately, so that only flat coating geometries are possible and
5 small layer thicknesses are also only achievable, which in addition tend to form cracks during drying and sintering.

Since the slurry technique as such would permit an inexpensive production of exact layers and whole quartz glass components, it would be desirable to eliminate said drawbacks.

10 It is therefore the object of the present invention to prepare a slurry with a flow behavior that has been optimized with respect to processing by dressing or pouring of the slurry mass and with respect to drying and sintering without cracks.

Moreover, it is the object of the present invention to indicate a special use of the slurry according to the invention.

15 As for the slurry, said object starting from the slurry mentioned at the outset is achieved according to the invention in that the SiO_2 particles have a multimodal particle size distribution with a first maximum of the size distribution in the range of $1\text{ }\mu\text{m}$ to $3\text{ }\mu\text{m}$ and a second maximum in the range of $5\text{ }\mu\text{m}$ to $50\text{ }\mu\text{m}$, and that the solids content (percentage by weight of the SiO_2 particles and the SiO_2
20 nanoparticles together) are in the range of 83 % to 90%

Typically, the above-mentioned highly filled and highly viscous slurry shows a dilatant-rheopexic behavior. This means that upon mechanical action (such as stirring, shaking, filling, dispersion coating, stripping, spreading by doctor blade) the slurry exhibits increased viscosity (dilatancy) or that after mechanical impact
25 the viscosity is increased for a short period of time (rheopexy). These closely related flow properties of the slurry shall be termed „rheopexy“ or „rheopexic“ in the following.

Thus the known slurry thickens under mechanical action. This flow behavior turns out to be disadvantageous when a slurry layer is applied to and distributed over a

surface by means of a tool, for instance during dispersion coating or stripping, troweling, dressing, scraping, filling, or the like. The known high-viscosity slurry is not well suited for these application techniques, which shall be summarized hereinafter under the term "spreading by doctor blade", as it solidifies under the
5 action of the distributing force, thereby counteracting a uniform distribution. In the inactive condition it can become liquid again and then flow off from oblique surfaces. The photo of Fig. 2 shows the result of a doctor blade test using a slurry as described in DE 10 2004 051 846 A1.

It has been found that the flow behavior of such a slurry will change due to the
10 addition of a small amount of SiO₂ nanoparticles towards a structurally viscous thixotropic behavior.

„Thixotropy“ of the slurry manifests itself in that with a constant shear stress (for instance at a constant stirring rate) its viscosity is continuously decreasing for some time. Related therewith is "structural viscosity" in the case of which the
15 viscosity is also reduced due to shear, but which is not further decreasing at a constant shear stress.

These closely related flow properties of the slurry shall be jointly termed as "thixotropy" or "thixotropic" in the following.

Due to its thixotropic flow behavior the slurry according to the invention will liquefy
20 under shear stress. This property is conducive to a uniform outflow and to the distribution of the slurry mass over a surface – also under the action of a force with a distributing effect.

The flow behavior of the slurry is above all defined by the solids content, namely in combination with and in dependence upon the content of SiO₂ nanoparticles and
25 the particle size distribution of the amorphous SiO₂ particles. This shall be explained in more detail hereinafter:

- The solids content (percentage by weight of the SiO₂ particles and the SiO₂ nanoparticles together) of the slurry according to the invention is relatively high at a value ranging between 83% and 90%. Also without the addition of

nanoparticles, the high solids content effects a high viscosity of the slurry, thereby contributing to a uniform and low shrinkage of the slurry layer, so that cracks caused by drying and sintering are reduced. Very high solids contents of more than 90% reduce the further processing possibilities of the slurry even if it is mixed with SiO₂ nanoparticles.

- The addition of SiO₂ nanoparticles creates interactions between the amorphous SiO₂ particles. The rather thixotropic behavior of the slurry according to the invention is due to diminishing interactions between the SiO₂ particles upon occurrence of shear forces. After omission of the shear forces, in the passive state of the slurry mass, these interactions will augment again, leading to the formation of physical or chemical bonds between the amorphous SiO₂ particles of the slurry mass among one another, which stabilize the inactive slurry mass.
- The amorphous SiO₂ particles have a multimodal particle size distribution. Such a multimodal particle size distribution has at least two, preferably three or more, distribution maxima. This is conducive to the setting of a high true density of the slurry, whereby shrinkage during drying and sintering and thus the risk of crack formation is reduced. For instance, particle distributions with D₅₀ values of 2, 5, 15, 30 and 40 µm can be used alone or in combination.

The SiO₂ nanoparticles can e.g. be produced by oxidation or hydrolysis of silicon-containing starting compounds (also called "pyrogenic silica" in the following) or by polycondensation of polymerizable silicon compounds (SiO₂ sol). When "pyrogenic silica" is used, a previous cleaning step is often useful. For this purpose pyrogenic silica is preferably present in the form of a partly solidified, "temporary" SiO₂ granulate, which permits the use of a standard hot chlorination method for cleaning purposes. During homogenization of the slurry the purified granulate grains will again decompose into SiO₂ nanoparticles due to the shear forces acting thereon.

The slurry can be easily adapted to the corresponding processing techniques by adapting the solids contents, the multimodal particle size distribution and the amount of SiO₂ nanoparticles within the ranges indicated in claim 1. This shall be explained in more detail hereinafter. Suitable processing techniques using such a
5 slurry comprise spreading by doctor blade and pouring. As for the standard doctor blade techniques, a slightly higher content of SiO₂ nanoparticles is more appropriate for slurries to be processed by pouring.

The photo of Fig. 1 shows the result of a doctor blade test using a slurry according to the invention; it can just be seen as a uniform white area.

- 10 SiO₂ nanoparticles are here understood to be SiO₂ particles with particle sizes in the range of a few nanometers up to 100 nm. Such nanoparticles have a BET specific surface area of 40-800 m²/g, preferably between 55 m²/g and 200 m²/g.

At a content of less than 0.2% by wt. of said particles in the slurry the nanoparticles do not have any significant impact on the flow behavior of the slurry,
15 whereas contents of more than 15% by wt. lead to intensified shrinkage of the slurry during drying, which might aggravate a defect-free drying and sintering. With thin slurry layers a higher content of SiO₂ nanoparticles can be used because thinner layers are less prone to shrinkage cracks than thicker layers.

With respect to this it has turned out to be particularly advantageous when the
20 slurry contains between 0.5 and 5 and particularly preferably between 1 and 3% by wt. of SiO₂ nanoparticles (based on the entire solids content).

Preferably, the SiO₂ nanoparticles have particle sizes of less than 50 nm.

Small SiO₂ nanoparticles seal and consolidate the outer surface of the green body and thereby increase the green strength of the dried slurry as well as the sintering
25 activity.

It has turned out to be particularly advantageous when at least 80% by wt., preferably at least 90% by wt., of the SiO₂ particles are made spherical.

Spherical particles facilitate the setting of a high true density in the slurry, so that stresses are reduced during drying and sintering. Moreover, it has been found that spherical SiO₂ particles in opaque quartz glass layers contribute to enhanced reflection, above all in the infrared range. Ideally, all SiO₂ particles are made
5 spherical.

In connection with a basically high content of spherical SiO₂ particles it has, however, also turned out to be of advantage to some applications when the slurry contains finely divided, splintery SiO₂ granules.

Due to the addition of finely divided, splintery SiO₂ granules, which can be
10 produced by milling, the mechanical strength of the green body is even further enhanced after drying. The higher strength has a particularly positive effect in the case of thick slurry layers. The particle sizes of the finely divided, splintery SiO₂ granules correspond approximately to those of the amorphous SiO₂ particles and the weight fraction of splintery granules is 10% by wt. at the most (based on the
15 total solids content).

Preferably, the SiO₂ particles have a particle size distribution distinguished by a D₅₀ value of less than 50 µm, preferably less than 40 µm.

SiO₂ particles in this order of magnitude exhibit an advantageous sintering behavior and a comparatively low drying shrinkage so that a corresponding slurry
20 layer can be sintered and dried particularly easily without the formation of cracks. This is due to interactions between the SiO₂ particles that lead to the formation of molecular SiO₂ bonds already in the slurry mass and therefore facilitate drying and sintering.

The dispersion liquid may be made up of an aqueous base. The polar nature of
25 the aqueous phase of such a slurry may have an effect on the interaction of the SiO₂ particles. For the slurry according to the invention, however, a dispersion liquid is preferred that is based on an organic solvent, preferably on an alcoholic basis.

It has been found that a dispersion liquid of such a type makes it easy to keep a thixotropic flow behavior. Moreover, the drying process is much faster than in the case of an aqueous slurry phase. This saves time and leads to a faster fixation of the slurry layer on a carrier, so that a flowing out on the edges is avoided. With the
5 addition of a minor water amount (< 30% by vol.) in the dispersion liquid, the processing period can be adapted to the respective requirements.

It has turned out to be also advantageous, particularly with respect to a low affinity to form cracks, when the solids content (percentage by weight of the SiO_2 particles and the SiO_2 nanoparticles together) is preferably at least 85% by wt.

10 Preferably, the SiO_2 particles and the SiO_2 nanoparticles consist of synthetic SiO_2 .

Synthetic SiO_2 is distinguished by high purity. The slurry is therefore suited for forming opaque quartz glass of high purity. The quartz glass has an impurity content of less than 1 wt. ppm, whereby it absorbs not much in the UV range up to 180 nm and is thus suited as a diffuse optical broadband reflector for use over a
15 particularly wide wavelength range.

For the same reason the SiO_2 content of the amorphous SiO_2 particles is preferably at least 99.9% by wt.

The solids content of the slurry produced by using such particles consists of at least 99.9% by wt. of SiO_2 (apart from the addition of dopant). Binders or other
20 additives are normally not needed and are ideally not contained. The content of metal oxide impurities is preferably less than 1 wt. ppm.

The cristobalite content in the dried SiO_2 slurry should be not more than 0.1% by wt. at the most because, otherwise, sintering of the slurry layer may cause crystallization, which may lead to waste.

25 To enhance the etching resistance of the quartz glass made from the slurry it has turned out to be useful when the slurry contains nitrogen, carbon or a chemical compound of these components that are incorporated into the quartz glass structure in the form of nitrides or carbides.

Nitrogen and/or carbon and/or one or more compounds of said components are added to the slurry. Nitrides or carbides effect a reinforcement of the quartz glass structure and lead to improved resistance to etching. Suitable start substances, such as silazanes or siloxanes, are particularly evenly distributed in the slurry, 5 from which a homogeneous doping of the quartz glass of the glass mass will result in the end.

As for the use, the above-mentioned object is achieved according to the invention in that the SiO_2 slurry according to the invention is used for producing a diffusely reflecting reflector of quartz glass.

10 A diffusely reflecting reflector made from the slurry according to the invention is distinguished by a particularly high degree of reflection over a wide wavelength range. This is assumed to be due to the high solids content of the slurry and particularly to the addition of SiO_2 nanoparticles.

The diffusely reflecting reflector is present as an independent reflector component 15 which is used in combination with an optical radiator, a heating element or for thermal shielding, or the reflector is formed as an opaque SiO_2 layer on a carrier component. The reflector can e.g. be present in the form of a tube, bulb, a compartment, bell, semi-shell, spherical or ellipsoidal segment, a plate, a heat shield, or the like.

20 In a first preferred alternative the diffusely reflecting reflector is used as a reflector layer of quartz glass on a carrier of quartz glass.

After drying and sintering of the slurry the reflector layer formed from the slurry forms a coating on a carrier surface or a part thereof. The carrier of quartz glass substantially performs mechanical or chemical basic functions of the overall 25 component, e.g. mechanical strength, thermal stability and chemical resistance, while the reflector layer considerably defines the optical properties. Typical layer thicknesses are in the range of 0.2 mm to 3 mm.

The reflector layer and the carrier are here made of the same material or at least of similar materials, which has a particularly advantageous effect on the adhesion

of the reflector layer to the carrier and on the thermal shock resistance of the overall component.

An alternative and equally preferred use of the slurry is characterized in that the diffusely reflecting reflector is formed as a carrier-less, preferably band- or plate-
5 shaped quartz glass component.

The use of a highly concentrated slurry according to the invention will prevent the formation of cracks caused by shrinkage. To be more specific, plate- or band-shaped quartz glass bodies are obtained that are distinguished by a homogeneous quartz glass layer of a predetermined thickness, which may be
10 opaque or transparent, depending on the corresponding sintering temperature and duration. Opaque plates are preferably obtained at sintering temperatures between 1200°C and 1350°C. These are particularly suited as diffusely reflecting reflector components. At higher sintering temperatures or with long sintering periods translucence or even transparenence is achieved.

15 For obtaining a specific reflection behavior of the diffusely reflecting reflector it has turned out to be advantageous when a slurry is used that contains one or more dopants that generate optical absorption in quartz glass in the ultraviolet, visible or infrared spectral range.

The slurry is preferably used for producing a diffusely reflecting reflector for diffuse
20 reflection in the UV wavelength range below 240 nm.

A high reflection in the UV wavelength range (e.g. of more than 90%) down to wavelengths around 180 nm presupposes opacity and ultrahigh purity of the quartz glass. Purity is e.g. guaranteed through the use of synthetically produced SiO₂, where particularly a low degree of impurity with lithium oxide should be
25 noted. The content of lithium is below 100 wt. ppb, preferably at less than 20 wt. ppb.

The invention shall now be explained in more detail with reference to embodiments and a drawing, in which:

Figure 1 shows a photograph illustrating the result of a doctor blade test using a slurry according to the invention;

Figure 2 shows a photograph which illustrates the result of a doctor blade test using a slurry according to the prior art;

- 5 **Figure 3** shows a diagram of the SiO_2 particle size distribution of a raw material component for use in a slurry according to the invention (prior to the addition of SiO_2 nanoparticles); and

Figure 4 shows a micrograph of the SiO_2 particle size distribution of the raw material component of Fig. 3.

10

1. Preparation of a SiO_2 slurry

- Figure 3** shows a particle size distribution of a raw material component. This is a multimodal particle size distribution with a relatively narrow maximum of the size distribution at about 30 μm (D_{50} value) and with a secondary maximum in the
15 range around 2 μm . This raw material component with a D_{50} value at 30 μm shall be called R_{30} hereinafter.

Figure 4 shows the particle size distribution as a SEM micrograph. It can be seen that the individual SiO_2 particles are made round and spherical.

- For the preparation of the slurry other raw material components are used that
20 have a D_{50} value at 5 μm , 15 μm and 40 μm , and the particle size distributions of which are otherwise similar to the ones shown in Figs. 3 and 4. Depending on their D_{50} value, these raw material components are designated as R_5 , R_{15} , and as R_{40} , respectively. Each of the raw material components are first cleaned in a hot chlorination process at a temperature in the range between 600°C and 1200°C.

- 25 Moreover, SiO_2 nanoparticles with diameters of around 40 nm are used in the form of „pyrogenic silica“, or in the form of a SiO_2 sol. The pyrogenic silica is here present as a partly solidified “temporary” SiO_2 granulate that is pre-treated by sintering at a low temperature in the range of 600°C to 900°C and partly

- consolidated in this process. For setting a high purity the pre-treatment is carried out in a chlorine-containing atmosphere. On account of the small primary particle sizes of the granulates the comparatively low temperature during hot chlorination is sufficient. During homogenization of the suspension the granulate grains
- 5 decompose again into SiO_2 nanoparticles due to the shear forces acting on them.

The following recipes have turned out to be useful:

Recipe 1

- | | | |
|----|----------|-------|
| | R_{30} | 500 g |
| | R_{15} | 200 g |
| 10 | R_5 | 200 g |

Pyrogenic silica: 135 g with BET surface area of $50 \text{ m}^2/\text{g}$.

The said components are dispersed in pure ethanol, yielding a solids content of 85% by wt.

Recipe 2

- | | | |
|----|----------|-------|
| 15 | R_{15} | 395 g |
| | R_5 | 54 g |

Standard SiO_2 sol with tetraethylorthosilane (TEOS) as the SiO_2 degassing material in an amount yielding a SiO_2 weight of 6 g.

- The said solids components are dispersed in 111 g pure ethanol, and SiO_2 sol is
- 20 mixed into the homogeneous dispersion.

Recipe 3

- | | | |
|--|----------|-------|
| | R_{15} | 270 g |
| | R_5 | 35 g |

Pyrogenic silica: 4 g with BET surface area of $50 \text{ m}^2/\text{g}$

- 25 These components are dispersed in 70 g polyvinyl butural in methanol.

The highly filled slurry prepared in this way shows a thixotropic behavior. The slurries are therefore "spreadable" and that is why they are suited for processing

techniques such as doctor blade processes. In each recipe the grain sizes below 60 μm account for the greatest volume fraction of the granules.

The slurry which is exclusively produced with synthetically produced spherical SiO_2 particles of high purity is free of cristobalite and is distinguished by a low
5 impurity content of less than 1 wt. ppm.

Figure 1 shows the result of a doctor blade test using the slurry according to recipe 1. The layer produced thereby is continuous and exhibits a uniform layer thickness so that the photo just shows a homogeneous white area. By contrast, the photo of **Figure 2** shows an irregular mass distribution with clots, as issues
10 from spreading by doctor blade of a rheopexic SiO_2 slurry according to the prior art. A similar result is obtained when the pyrogenic silica is omitted in recipe 1.

2. Preparation of quartz glass using the slurry according to the invention

Example 1: preparation of diffusely reflecting surface areas on a carrier

15 A spreadable SiO_2 slurry according to the invention is used, wherein the slurry layer is produced by means of a dressing tool acting on a supply mass of the slurry in a metering and distributing manner.

The supply mass is either accumulated on the surface of the carrier, or it is contained in a reservoir from which it can pass to the carrier surface. Under the
20 mechanical distributing action of the dressing tool and in combination with the thixotropic properties of the slurry according to the invention the viscosity is reduced, which facilitates outflow and propagation of the slurry on the surface of the carrier. This is conducive to the formation of a uniform homogeneous layer of a predetermined thickness.

25 The dressing tool, which performs a relative movement with respect to the carrier surface, is for instance a doctor blade tool, such as a horizontally rotating rod, a roll, a shaping tool, or the like. It is essential that the dressing tool is spaced apart

from the surface of the carrier at a distance correlating with the thickness of the layer to be formed.

Preferably, the slurry supply mass is present on a gap formed between the dressing tool and the carrier, which is movable by relative movement between
5 dressing tool and carrier along the carrier. The distance between dressing tool and carrier forms a gap on which the slurry supply mass to be distributed is positioned and the width of which corresponds to the thickness of the slurry layer to be formed.

As a rule, a constant layer thickness is desired. As a result, the gap has a width
10 that is predetermined by a mechanical guide element along which the carrier or the dressing tool is guided for performing its relative movement. The carrier itself can here also be used as the guide element.

The relative movement of dressing tool and carrier is here carried out with the help of a mechanical guide element which, on the one hand, coordinates the relative
15 movement and which, on the other hand, predetermines the gap between carrier and dressing tool directly or indirectly. As a result, when the relative movement is carried out, a constant gap width can be upheld in an easy way. This may e.g. be a guide rail along which the dressing tool moves across the carrier. The gap width is directly set by the thickness of the guide rail or indirectly by a stripper connected
20 to the dressing tool.

The slurry supply mass is preferably contained in a reservoir which is arranged on the dressing tool and fluidically connected to the gap. The slurry supply mass passes continuously from the reservoir via the gap to the surface of the carrier. The reservoir is part of the dressing tool and ensures that slurry mass is always
25 present on the gap across the whole gap width. With a movable dressing tool the reservoir is also moved with the dressing tool.

As a rule, the gap has a shape adapted to a coating surface of the carrier. This is particularly useful in the case of an elongated carrier, the coating surface of which is not flat, but comprises, for instance, curved or obliquely extending areas
30 extending in longitudinal direction. The shape of the dressing tool is here adapted

to the surface profile of the carrier and it is thereby ensured that the gap width, viewed in a direction transverse to the direction of relative movement, is constant.

In the embodiment the slurry according to recipe 2 is used for producing a reflector layer on a cladding tube for an IR radiator in the form of a so-called „twin
5 tube“ made of quartz glass.

The twin tube consists of a cladding tube which is formed as an eight when viewed in cross section and is made of quartz glass, the tube being subdivided by a central web into two compartments, each serving to accommodate a heating coil. On the upper side of the cladding tube that is oriented away from the main
10 propagation direction a reflector layer shall be formed in the form of an opaque coating of SiO_2 for diffuse reflection. The production thereof shall be explained hereinafter.

The surface of the twin tube is cleaned with alcohol and then in 3% hydrofluoric acid for eliminating other surface impurities, particularly alkali and alkaline earth
15 compounds. The twin tube is then inserted into a doctor blade device. Said device consists of an elongated carrier for supporting the twin tube, a guide rail and a dressing tool with integrated slurry reservoir which is displaceable on the guide rail along the twin tube. The dressing tool comprises a stripper with a bottom side profiled in such a way that it maintains a drawing gap of a constant width of 2 mm
20 relative to the upper side of the twin tube. The reservoir is fluidically connected to the drawing gap and, viewed in the direction of displacement of the dressing tool, arranged in front thereof. Areas of the upper side of the twin tube that are not to be coated are covered with a sheet. The slurry is filled into the reservoir and the dressing tool is drawn off swiftly and uniformly via the guide rail along the twin
25 tube. A shear force that due to the thixotropic flow property of the slurry leads to a decrease in viscosity so that the slurry is distributed between twin tube and stripper and exits in a uniform way and at a constant thickness out of the drawing gap is here acting on the slurry in the area of the drawing gap. The viscosity of the slurry applied to and resting on the coating surface increases again due to
30 thixotropy immediately after application, so that the coating does not deliquesce,

but mainly maintains its form. The cover sheets are removed. A substantially constant layer thickness of the slurry layer of about 1 mm is thereby achieved.

Despite the curved surface of the twin tube, the use of the doctor blade device and of the thixotropic slurry according to the invention permits a uniform coating of the surface with slurry layer, thereby ensuring, after drying and sintering, the formation of an optically homogeneous and esthetically appealing opaque reflector layer with a thickness of 0.8 mm. Due to its high purity the layer also reflects in the ultraviolet wavelength range below 200 nm. The opaque reflector layer is also suited for use at elevated temperatures of more than 1000°C.

- 10 The reflectivity of the opaque reflector layer shall now be explained in more detail with reference to the reflection curve of Fig. 5.

Figure 5 shows the reflection behavior of the diffuse reflector produced according to Example 1 in the form of an opaque layer of opaque SiO₂ layer in the wavelength range of 250 nm to 3000 nm. The degree of reflection "R" in % based on the reflectivity of "Spectralon" is plotted on the y-axis and the wavelength λ of the operating radiation in nm on the x-axis. The reflectivity is determined by means of an Ulbricht sphere.

The curve shows the reflection progress in the case of an opaque layer of opaque SiO₂ with a thickness of 0.8 mm, with the sintering process being carried out in a sintering furnace at 1280°C (3h) in air. As can be seen therefrom, the SiO₂ opaque layer of undoped SiO₂ shows an approximately uniform degree of reflection R of around 95% in the wavelength range between about 300 nm and 2100 nm. The degree of reflection at 210 nm is here still higher than 98%. This high reflection in the VUV range permits the use of components coated in this way, for instance in the UV disinfection sector.

Example 2: production of a quartz glass plate

A homogeneous slurry is prepared with the help of recipe 3. The slurry is used for producing a quartz glass plate in a doctor blade process. A slurry layer with a

thickness of 5 mm is here produced on a carrier. This is only possible on account of the thixotropic flow behavior of the slurry.

- After drying of the layer, which on account of the high solids content and the alcoholic base of the dispersion liquid is carried out within a few hours, the layer is
- 5 sintered. Depending on sintering temperature and duration, a thin plate of transparent or opaque quartz glass is obtained.

Patent claims

1. A SiO₂ slurry for the production of quartz glass, containing a dispersion liquid
5 and amorphous SiO₂ particles with particle sizes to a maximum of 500 µm,
wherein the largest volume fraction is composed of SiO₂ particles with
particles sizes in the range of 1 µm to 60 µm, as well as SiO₂ nanoparticles
with particle sizes of less than 100 nm in the range of 0.2% by wt. to 15% by
wt. (of the entire solids content), characterized in that the SiO₂ particles have
10 a multimodal distribution of particle sizes with a first maximum of the size
distribution in the range of 1 µm to 3 µm and a second maximum in the range
of 5 µm to 50 µm, and that the solids content (percentage by weight of the
SiO₂ particles and the SiO₂ nanoparticles together) are in the range of 83 % to
90%.
- 15 2. The slurry according to claim 1, characterized in that it contains between 0.5%
by wt. and 5% by wt., preferably between 1% by wt. and 3% by wt., of SiO₂
nanoparticles (of the entire total solids content).
3. The slurry according to claim 1, characterized in that the SiO₂ nanoparticles
have particle sizes of less than 50 nm.
- 20 4. The slurry according to claim 1, characterized in that at least 80% by wt.,
preferably at least 90% by wt., of the SiO₂ particles are made spherical.
5. The slurry according to claim 4, characterized in that it contains finely divided,
splintery SiO₂ granules.
6. The slurry according to claim 1, characterized in that the SiO₂ particles have a
25 particle size distribution distinguished by a D₅₀ value of less than 50 µm,
preferably less than 40 µm.
7. The slurry according to claim 1, characterized in that the dispersion liquid is
made up on the basis of an organic solvent, preferably on an alcoholic basis.

8. The slurry according to claim 1, characterized in that the solids content (percentage by weight of the SiO_2 particles and the SiO_2 nanoparticles together) is at least 85% by wt.
9. The slurry according to claim 1, characterized in that the SiO_2 particles and
5 the SiO_2 nanoparticles consist of synthetic SiO_2 .
10. The slurry according to claim 1, characterized in that the SiO_2 content of the amorphous SiO_2 particles is at least 99.9% by wt.
11. The slurry according to claim 1, characterized in that it contains nitrogen,
carbon or a chemical compound of said components that are incorporated into
10 the quartz glass structure in the form of nitrides or carbides.
12. Use of SiO_2 slurry according to any one of claims 1 to 11 for producing a diffusely reflecting reflector of quartz glass.
13. Use according to claim 12, characterized in that the diffusely reflecting
reflector is formed as a reflector layer of quartz glass on a carrier of quartz
15 glass.
14. Use according to claim 12, characterized in that the diffusely reflecting
reflector is formed as a carrier-less, preferably band- or plate-shaped quartz
glass component.
15. Use according to claim 12, characterized in that the diffusely reflecting
20 reflector for creating a specific reflection behavior contains one or more dopants producing an optical absorption in quartz glass in the ultraviolet, visible or infrared spectral range.
16. Use according to claim 12, characterized in that the diffusely reflecting
reflector for diffuse reflection in the UV wave-length range is used below
25 240 nm.