

SPECIFICATION

ZINC OXIDE PARTICLE, METHOD FOR PRODUCING IT, EXOERGIC FILLER, RESIN COMPOSITION, EXOERGIC GREASE AND EXOERGIC COATING COMPOSITION

FIELD OF THE INVENTION

【0001】

The present invention relates to a zinc oxide particle, a method for producing it, an exoergic filler, a resin composition, an exoergic grease and an exoergic coating composition.

BACKGROUND OF THE INVENTION

【0002】

Zinc oxide is widely used in the various industrial fields such as rubber accelerators, pigments for coating compositions and inks, such electronic components as ferrite and varistor, medicinal products and cosmetics. As one of various applications of this zinc oxide, an exoergic filler has been proposed (see Japanese Kokai Publication 2008-19426, Japanese Kokai Publication Hei11-246885, Japanese Kokai Publication 2007-70492, Japanese Kokai Publication 2002-201483). However, alumina and aluminum nitride are usually used widely as the exoergic filler. Therefore, zinc oxide is hardly turned into actual utilization compared to these compounds.

【0003】

However, alumina has a problem that kneading machines become worn abundantly in the production process of exoergic sheets and so on because Mohs hardness of alumina is high. Further, it is difficult to fill aluminum nitride into a resin in high concentration, because of poor filling property. In addition, aluminum nitride is expensive, so exoergic parts made thereof is expensive. Therefore, new exoergic fillers which are made of other materials than such conventional materials are needed.

【0004】

Zinc oxide has almost intermediate thermal conductivity between alumina and aluminum nitride and is suitable for the exoergic filler. However, zinc oxides which are used widely for industrials are fine particles having particle diameter of not greater than 1 μm . Such zinc oxide fine particles are hardly used because heat resistance between particles is high and exoergic property is insufficient.

【0005】

On the other hand, in the field of electronic components, a thin film layer is formed using exoergic filler containing-liquid products such as exoergic greases and resin compositions, for example, coating compositions. There is a problem that the thin film layer cannot be obtained when coarse particles are contained in the exoergic filler. Coarse particles having particle diameter of 50 μm or more must not be contained in the exoergic filler to apply the filler into the exoergic grease. Zinc oxide of which particle size distribution kept under control is unknown to the public.

【0006】

On the other hand, the method of designing particle size distribution to enable closest packing by combining two or more fillers of various particle size, in order to achieve better thermal conductivity (see Japanese Kokai Publication 2002-201483). Therefore, zinc oxide particle showing sharp particle size distribution and having large particle diameter is required. The method of baking with the use of flax is known for increasing the particle diameter of inorganic compounds. However, the zinc oxide particles obtained by the above mentioned method show broad particle size distribution and cause a problem that coarse particles produced in the baking are mixed into the desired products.

【0007】

It can be expected that new effect, which resulted from physical properties different from common ones, will be achieved by using the zinc oxide particles having large particle

diameter and showing specific particle size distribution in the above-mentioned various applications of zinc oxide other than the exoergic filler.

DISCLOSURE OF INVENTION

OBJECT OF THE INVENTION

【0008】

The object of the present invention is to provide zinc oxide particle that can be used more suitably than common zinc oxide in the application such as an exoergic filler and so on.

PROBLEM TO BE SOLVED BY THE INVENTION

【0009】

The present invention relates to a zinc oxide particle having a median size of 1 to 30 μm and D90/D10 of 4 or less. The zinc oxide particle is preferably baking a raw zinc particle in the presence of ammonium bromide.

The zinc oxide particle is preferably obtained by mixing the raw zinc particle and 0.1 to 10 weight % of ammonium bromide relative to said raw zinc particle, and static baking the mixture at 600 to 1200 $^{\circ}\text{C}$.

【0010】

The present invention relates to a method for producing a zinc oxide particle, comprising baking a raw zinc particle in the presence of ammonium bromide to obtain the zinc oxide particle.

It is preferred that ammonium bromide is added in the proportion of 0.1 to 10 weight % relative to the raw zinc particle and the baking is performed by static baking at 600 to 1200 $^{\circ}\text{C}$.

The present invention relates to an exoergic filler comprising the zinc oxide particle.

The present invention relates to a resin composition comprising the zinc oxide particle.

The present invention relates to an exoergic grease comprising the zinc oxide particle.

The present invention relates to an exoergic coating

composition comprising the zinc oxide particle.

EFFECT OF THE INVENTION

【0011】

The zinc oxide particle of the present invention can be used suitably as the exoergic filler for various exoergic parts, such as exoergic sheets and exoergic greases even though it is large particle, because the mixing of coarse particles having particle diameter of 50 μm or more is almost never happened and the particle size distribution thereof is sharp. Furthermore, the zinc oxide particle can be used in the fields of rubber accelerators, pigments for coating compositions and inks, such electronic components as ferrite and varistor, medicinal products and such cosmetics as foundation and sunscreen.

BRIEF DESCRIPTION OF THE DRAWINGS

【0012】

FIG. 1 is a scanning electron microscope photograph of zinc oxide particles of the present invention obtained in Example 1.

FIG. 2 shows particle size distribution of zinc oxide particles of the present invention obtained in Example 1.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

【0013】

The present invention is described in more detail below. The zinc oxide particle of the present invention has a median size of 1 to 30 μm and D90/D10 of 4 or less. That is, the zinc oxide particle is one having larger particle diameter and showing smaller value of D90/D10 than conventional zinc oxide particles (that is, coarse particles having extremely-large particle diameter are small in amount). This zinc oxide particle is not common knowledge and is obtained by the inventors for the first time.

【0014】

The median size is also called D50. When powder is

divided by particle diameter based on the median size into two groups, bigger group and smaller group have equal amounts. D50 and D90 correspond to the point where the cumulative weight from the small-particle-diameter side reaches 10% and 90% in the cumulative particle size distribution. D10, D50, and D90 are values determined by measuring the particle size distribution, respectively. The particle size distribution is measured by using laser diffraction/ scattering particle size distribution analyzer (LS 13 320 type manufactured by BeckmanCoulter) according to the present invention.

【0015】

The lower limit of the median size is 1.0 μ m and more preferably 1.5 μ m. The upper limit of the median size is 30 μ m and more preferably 20 μ m.

【0016】

The particle shape of the zinc oxide particle of the present invention is not particularly limited, but includes needle shape, bar-like shape, plate-like shape, spherical shape and so on. Preferably, the particle shape is nearly spherical shape. In addition, the particle shape can be observed by Scanning Electron Microscope (JSM-5400 manufactured by JEOL Ltd.).

【0017】

In the zinc oxide particle of the present invention, the proportion of coarse particles having particle diameter of 50 μ m or more is preferably not more than 0.05 %. The proportion of coarse particles having particle diameter of 50 μ m or more can be measured according to JIS K1410 zinc oxide/sifted residue test.

【0018】

The zinc oxide particle of the present invention can be produced by baking a raw zinc particle in the presence of ammonium bromide. This method for producing the zinc oxide particle is one aspect of the present invention. The method for producing a zinc oxide particle is described in more detail below.

【0019】

In the method for producing a zinc oxide particle of the present invention, a raw zinc particle was used as a raw material. The raw zinc particle is not particularly limited if it is converted to zinc oxide by baking and there may be mentioned zinc oxide, zinc chloride, zinc sulfate, zinc carbonate, zinc acetate and so on. Particularly, the raw zinc particle is preferably zinc oxide. The raw zinc particle preferably has an average particle diameter of 0.6 to 0.8 μm . The average particle diameter of the raw zinc particle is measured by air permeability method.

【0020】

The zinc oxide which is used as a raw material is not particularly limited, but the zinc oxide produced by France Law, America Law and other common methods can be used. Particularly, zinc oxide which is produced by French Law is preferably used because the zinc oxide has few impurities.

【0021】

The method for producing a zinc oxide particle of the present invention is characterized by baking in the presence of ammonium bromide. In the production of inorganic particles, the baking in the presence of flax may be performed to increase particle diameter thereof. The inventors found that, when ammonium bromide is used as flax in this baking, the particle size distribution of the obtained zinc oxide particles became sharper than when other compounds were used as flax.

【0022】

Ammonium bromide is added in the amount of 0.1 to 10 weight % relative to the raw zinc particles as a raw material. If the addition level is less than 0.1 weight %, energy costs increase because it becomes difficult for the raw zinc particles to grow.

If the addition level exceeds 10 weight %, productivity is poor because many coarse particles occur leading to decrease yield ratio of desired products. As for the addition level of ammonium bromide, the lower limit is more preferably 0.2

weight % and the upper limit is more preferably 5 weight %
【0023】

The zinc oxide particle of the present invention can be produced by mixing the raw zinc particles and ammonium bromide according to the common manner and baking the obtained mixture. The baking is preferably, for example, a static baking with use of tunnel kiln or shuttle kiln, from industrial viewpoint. By static baking, particles fuse with each other and particles growth proceeds effectively, and thus zinc oxide particles having large particle diameter can be obtained effectively.
【0024】

The baking was performed at 600 to 1200 °C. When the temperature is less than 600 °C, it is not preferred because particle diameter may not increase sufficiently. When the temperature was exceeding 1200 °C, it is not preferred because many coarse particles occur and yield may be decreased.

【0025】

The zinc oxide particles obtained by the above method have a sharp particle size distribution, but the zinc oxide particles may be pulverized or classified using a sieve if sharper particle size distribution is required or in order to remove a few coarse particles. The method of pulverizing is not particularly limited but includes the method using an atomizer for example. The classification using a sieve is not particularly restricted but includes wet classification and dry classification.

【0026】

The zinc oxide particle of the present invention may be surface-treated according to need. The surface treatment method includes usual treatment methods in the technical field of inorganic particles. More specifically, there may be mentioned organic surface treatment using silane coupling agents or silicone oils and inorganic surface treatment using silica.

【0027】

The use of the zinc oxide particle of the present invention

is not particularly limited but the particles can be used as an exoergic filler, for example. This exoergic filler is one aspect of the present invention.

【0028】

The exoergic filler of the present invention is usually used in the fields such as exoergic resin compositions, exoergic greases and exoergic coating compositions. Many documents concerning such applications are known, the exoergic filler of the present invention is used as such known applications as exoergic resin compositions, exoergic greases and exoergic coating compositions.

【0029】

When used as an exoergic filler, rough zinc oxide particles having large particle diameter according to the present invention and fine zinc oxide particles having $1/3$ to $1/40$ μm of the particle diameter of the zinc oxide particle of the present invention may be used in combination. The mixing proportion of the rough particles and the fine particles is rough particles 90 to 40 %: fine particles 10 to 60 %, in volume. Preferably, the mixing proportion is rough particles 80 to 60 %: fine particles 20 to 40 %. When the mixing proportion of the rough particles and the fine particles is without the above mentioned range, rough particles 90 to 40 %: fine particles 10 to 60 %, exoergic property may not be improved sufficiently.

【0030】

When the zinc oxide particle of the present invention is used as an exoergic filler, the particle may be used in combination with other components. The other components which may be used together, include metal oxides such as magnesium oxide, titanium oxide, aluminum oxide, other exoergic fillers than zinc oxide such as aluminum nitride, boron nitride, silicon carbide, silicon nitride, titanium nitride, metallic silicon, and diamond, resins and surfactants.

【0031】

When the zinc oxide particle is used as exoergic filler, the particles can be used in the form of resin composition

obtained by mixing with a resin. Such resin composition is one aspect of the present invention. In this case, the resin may be a thermoplastic resin or a thermosetting resin and includes epoxy resins, phenol resins, polyphenylene sulfide resins (PPS), polyester resins, polyamides, polystylenes, polyethylenes, polypropylenes, polyvinyl chloride, polyvinylidene chloride, fluorine resins, polymethyl methacrylate, ethylene/ethyl acrylate copolymer resin (EEA), polycarbonates, polyurethanes, polyacetals, polyphenylene ethers, polyether imides, acrylic nitrile-butadiene-styrene copolymer resin (ABS), liquid crystal resins (LCP), silicone resins, acrylic resins and other resins.

【0032】

The resin composition of the present invention may be a resin composition for thermal molding obtained by kneading a thermoplastic resin and the zinc oxide particle in melting condition; a resin composition obtained by kneading a thermosetting resin and the zinc oxide particle following thermosetting; or other resin composition.

【0033】

The addition amount of the zinc oxide particle in the resin composition of the present invention can be arbitrarily determined according to the intended performance of the resin composition such as thermal conductivity, hardness and so on. In order to express the exoergic property of the zinc oxide particle sufficiently, the addition amount of the particle is preferably 10 to 90 volume % relative to the total solid matter of the resin composition. The addition amount can be adjusted according to the needed level of exoergic property. For the application required better exoergic property, the addition amount is more preferably 30 volume % or more, and still more preferably 50 volume % or more.

【0034】

In the resin composition of the present invention, the resin component may be selected in accordance to the use. For example, when the resin composition is placed between the heat

source and the exoergic plate and make them stick together, resins having high adhesion property and low hardness such as silicone resins and acrylic resins can be selected.

【0035】

When the resin composition of the present invention is a resin composition for thermal molding, the resin composition may be produced by the method comprising melt-kneading a thermoplastic resin and the zinc oxide particle using a double-screw extruder, for example, to pelletize the resin composition and then, molding to the desired shape by the arbitrary molding method such as injection molding and so on.

【0036】

When the resin composition of the present invention is the resin composition obtained by kneading a thermosetting resin and the zinc oxide particle following thermosetting, it is preferably molded by pressure forming. Such method for producing the resin composition is not particularly limited, but includes the method molding the resin composition by transfer molding.

【0037】

The applications of the resin composition of the present invention include exoergic parts of electronic components, thermal-conductive bulking agents, insulating bulking agents for temperature measurement. For example, the resin composition of the present invention can be used in order to transfer the heat from the exothermic electronic components, such as MPU, power transistor, transformer to the exoergic components such as exoergic fins and exoergic fan, and can be placed between the exothermic electronic components and exoergic components. This will allow good heat transfer between the exothermic electronic components and the exoergic components and will allow to decrease glitch of the exothermic electronic components for a long term. Furthermore, the resin composition of the present invention can be preferably used for connecting a heat pipe and a heat sink, or connecting a module incorporated into various exothermic bodies and a heat sink.

【0038】

When the zinc oxide particle is used as an exoergic filler, the particle may be used as an exoergic grease obtained by mixing with a base oil which contains a mineral oil or a synthetic oil. This exoergic grease is one aspect of the present invention.

【0039】

The addition amount of the zinc oxide particle in the exoergic grease of the present invention may be decided according to the intended degree of thermal conductivity. In order to express the exoergic property of the zinc oxide particle sufficiently, the addition amount of the particle is preferably 10 to 90 volume % relative to the total amount of the exoergic grease. The addition amount can be adjusted according to the needed level of exoergic property. For the application required better exoergic property, the addition amount is more preferably 30 volume % or more, and still more preferably 50 volume %.

【0040】

As the base oil, one or more kinds of oil materials selected from the group consisting of mineral oils, synthesis oils, silicone oils, fluorinated hydrocarbon oils and so on. The synthesis oil is preferably hydrocarbon oils. As the synthesis oil, there may be mentioned α -olefins, diesters, polyol esters, trimellitic esters, polyphenyl ethers, alkylphenyl ethers and so on.

【0041】

The exoergic grease of the present invention may contain a surfactant according to need. The surfactant is preferably a nonionic surfactant. By adding the nonionic surfactant, thermal conductivity can be improved and consistency of the exoergic grease can be controlled moderately.

【0042】

As the nonionic surfactant, there may be mentioned polyoxyethylene alkyl ethers, polyoxyethylene alkyl phenyl ethers, polyoxyethylene alkyl naphthylene ethers, polyoxyethylene castor oil, polyoxyethylene hydrogenated

castor oil, polyoxyethylene alkylamides, polyoxyethylene-polyoxypropylene glycols, polyoxyethylene-polyoxypropylene glycol ethylene diamines, decaglycerin fatty acid esters, polyoxyethylene fatty acid monoesters, polyoxyethylene fatty acid diesters, polyoxyethylene propylene glycol fatty acid esters, polyoxyethylene sorbitan fatty acid monoesters, polyoxyethylene sorbitan fatty acid triesters, ethylene glycol fatty acid monoesters, diethylene glycol fatty acid monoesters, propylene glycol fatty acid monoesters, glycerin fatty acid monoesters, pentaerythritol fatty acid monoesters, sorbitan fatty acid monoesters, sorbitan fatty acid sesquiesters, sorbitan fatty acid triesters.

【0043】

The effect of adding the nonionic surfactant depends on the kind of the thermal-conductive bulking agents, addition amount, and HLB which is the term showing the balance between hydrophilicity and lipophilicity (hydrophile-lipophile balance). Liquid surfactants with HLB of not more than 9 are preferred because good consistency is obtained at room temperature, in the practice of the present invention. Anionic surfactants, cationic surfactants and ampholytic surfactants may be used in the application such as high exoergic grease where the decrease of electrical insulation and electrical resistance are not emphasized.

【0044】

The exoergic grease of the present invention can be produced by mixing the above mentioned components using a mixing apparatus such as dow mixer (kneader), gate mixer, planetary mixer and so on.

【0045】

The exoergic grease of the present invention may be applied to the exothermic body or the exoergic body. As the exothermic body, there may be mentioned, for example, exothermic electric components such as general electrical source; power transistor for electrical source, power module, thermistor, thermo couple, temperature sensor and other

electrical apparatus: such integrated circuit element as LSI and CPU. As the exoergic body, there may be mentioned, for example, exoergic components such as heat spreader, heat sink; heat pipe, exoergic plate. The grease can be applied by the screen print method. The screen print method may be performed using metal mask or screen mesh. By applying the exoergic grease of the present invention between the exothermic body and the exoergic body, it is able to effectively remove heat from the exothermic body because heat transfer from the exothermic body to the exoergic body is performed efficiently.

【0046】

When the zinc oxide particle of the present invention is used as an exoergic filler, the filler can be used as a coating composition obtained by dispersing the filler in a resin solution or dispersion liquid. This exoergic coating composition is one aspect of the present invention. In this case, the resin contained in the composition may be a hardenable one or a nonhardenable one. The resin may include the exemplified resins which can be used in the resin composition mentioned above. The coating composition may be solvent type one containing organic solvents or an aqueous type one containing a resin dissolved or dispersed in water.

【0047】

The method for producing the coating composition is not particularly restricted but the coating composition can be produced by mixing and dispersing the necessary materials and solvents using a disper or beads mill.

【0048】

The addition amount of zinc oxide particle in the exoergic coating composition of the present invention may be decided according to the intended degree of thermal conductivity. In order to express the exoergic property of the zinc oxide particle sufficiently, the addition amount of the particle is preferably 10 to 90 volume % relative to the total amount of the coating composition. The addition amount can be adjusted according to the needed level of exoergic property. For the

application required better exoergic property, the addition amount is more preferably 30 volume % or more, and still more preferably 50 volume %.

【0049】

The zinc oxide particle of the present invention can be used in the fields such as rubber accelerators, pigments for coating compositions and inks, such electronic components as ferrite and varistor, medicinal products and cosmetics in addition to the exoergic filler.

【Example】

【0050】

Hereinafter, the present invention will be described in more detail by way of examples, but the present invention is not limited to these examples.

【0051】

Hereinafter, median size and particle size distribution of the obtained zinc oxide large particle were measured by laser diffraction/ scattering particle size distribution analyzer (LS 13 320 type manufactured by BeckmanCoulter). The observation of the particles was performed using Scanning Electron Microscope (JSM-5400 manufactured by JEOL Ltd.). Amounts of coarse particles having particle diameter of 50 μm or more were measured according to JIS K 1410 zinc oxide/sifted residue test.

【0052】

Example 1

One kind of zinc oxide (manufactured by Sakai Chemical Industry, average particle diameter 0.7 μm) 1200 g and 12 g of ammonium bromide were mixed and dried for 30 seconds, and the obtained mixed powder was charged into quartz pot with inside dimension of 235 mm $\times$ 160 mm $\times$ 56 mmH followed by baking at 910 $^{\circ}\text{C}$ for 3 hours.

【0053】

After cooling, the obtained mixed powder was dispersed into 3.5 liter of water and screened through 400 mesh (opening of screen 38 μm). The slurry passing through the mesh was

filtered and dried to obtain a white powder. The particle size distribution was measured and it was discovered that median size was 10.55 μm and D90/D10 was 3.71. Shifted residue at 45 μm was measured and found to be not more than 0.01 %.

【0054】

Example 2

The white powder was obtained by following the same procedure as that of Example 1 except that the baking temperature was changed to 700 °C and the baking time was changed to 2 hours. The median size of the powder particle was 2.03 μm , D90/D10 was 4.00 and sifted residue at 45 μm was not more than 0.01 %.

【0055】

Example 3

The white powder was obtained by following the same procedure as that of Example 1 except that the addition amount of ammonium bromide was changed to 60 g and the baking temperature was changed to 1100 °C. The median size of the powder particle was 19.70 μm , D90/D10 was 3.41 and sifted residue at 45 μm was not more than 0.01 %.

【0056】

Comparative Example 1

The white powder was obtained by following the same procedure as that of Example 1 except that ammonium bromide was changed to ammonium chloride and the baking temperature was changed to 750 °C. The median size of the powder particle was 7.82 μm , D90/D10 was 12.33 and sifted residue at 45 μm was not more than 0.01 %.

【0057】

Comparative Example 2

The white powder was obtained by following the same procedure as that of Example 1 except that ammonium bromide was changed to sodium chloride and the baking temperature was changed to 900 °C. The median size of the powder particle was 11.00 μm , D90/D10 was 6.85 and sifted residue at 45 μm was not more than 0.01 %.

【0058】

Comparative Example 3

The white powder was obtained by following the same procedure as that of Example 1 except that ammonium bromide was changed to potassium chloride and the baking temperature was changed to 930 °C. The median size of the powder particle was 10.16 μm , D90/D10 was 6.45 and sifted residue at 45 μm was not more than 0.01 %.

【0059】

Comparative Example 4

The white powder was obtained by following the same procedure as that of Example 1 except that ammonium bromide was changed to potassium bromide and the baking temperature was changed to 900 °C. The median size of the powder particle was 11.20 μm , D90/D10 was 5.79 and sifted residue at 45 μm was not more than 0.01 %.

【0060】

Comparative Example 5

The white powder was obtained by following the same procedure as that of Example 1 except that ammonium bromide was changed to magnesium chloride and the baking temperature was changed to 690 °C. The median size of the powder particle was 7.58 μm , D90/D10 was 13.56 and sifted residue at 45 μm was not more than 0.01 %.

【0061】

Comparative Example 6

The white powder was obtained by following the same procedure as that of Example 1 except that ammonium bromide was changed to barium chloride and the baking temperature was changed to 950 °C. The median size of the powder particle was 7.75 μm , D90/D10 was 6.30 and sifted residue at 45 μm was not more than 0.01 %.

【0062】

These results showed that zinc oxide particles having narrower particle size distribution can be obtained by using ammonium bromide as flux compared to other compounds.

【0063】

Examples 4 to 6

Resin compositions were prepared by heat mixing EEA resin and zinc oxide particles of Examples 1 and 2 as shown in Table 1 and then pressure molding. This resin composition was molded to be a molded article with 50 mmφ × 2 mm. Thermal conductivity of the molded articles were measured and results were shown in Table 1. In addition, thermal conductivity was measured at 25 °C according to the method with heat flow meter.

【0064】

Comparative Example 7

A molded article of EEA resin was obtained by following the same procedure as that of Examples 4 to 6 except that filler was not added. Thermal conductivity of the molded article was measured and the result was shown in Table 1.

【0065】

Comparative Examples 8 to 10

Thermal conductivity was measured by following the same procedure as that of Examples 4 to 6 except that zinc oxide particles changed to alumina. The results were shown in Table 1. In addition, the numeric values in Table mean the average particle diameter of alumina.

【0066】

Table 1

Addition amount (weight part)	Comparative Example 7	Example 4	Example 5	Example 6	Comparative Example 8	Comparative Example 9	Comparative Example 10
EBA resin	100	10	12	10	12	12	10
Zinc oxide particle of Example 1		100		70			
Zinc oxide particle of Example 2			100	30			
Alumina 20 μ m					68.5		
Alumina 10 μ m						68.5	51.4
Alumina 0.8 μ m							17.1
Filler (volume %)		62.9	58.6	62.9	58.6	58.6	62.9
Thermal conductivity (W/m·K)	0.3	2.4	2.5	3.0	2.2	1.7	1.3

【0067】

Example 7

Epoxy resin (jER 828 manufactured by JAPAN EPOXY RESIN Co., Ltd), curing agent for epoxy resin (jER CURE ST 12 manufactured by JAPAN EPOXY RESIN Co., Ltd) and the zinc oxide particle of Example 1 were mixed as shown in Table 2, and the obtained mixture was injected into a die with $50 \text{ mm}\phi \times 2 \text{ mm}$ and heat treated to obtain a molded article at 80°C for 3 hours. The thermal conductivity of the molded article was measured and the result was shown in Table 2.

【0068】

Comparative Example 11

Thermal conductivity measurement was done by following the same procedure as that of Example 7 except that the zinc oxide particle was changed to alumina $10 \mu\text{m}$. The result was shown in Table 2.

【0069】

Table 2

		Example 7	Comparative Example 11
Addition amount (weight part)	Epoxy resin	12	12
	Curing agent for epoxy resin	6	6
	Zinc oxide particle of Example 1	28	
	Alumina $10 \mu\text{m}$		20
Filler (volume %)		25	25
Thermal conductivity (W/m·K)		0.5	0.3

【0070】

Example 8

Silicone resin (KE-103 manufactured by Shin-Etsu Chemical Co., Ltd), curing agent for silicone resin (CAT-103 manufactured by Shin-Etsu Chemical Co., Ltd) and the zinc oxide particle of Example 1 were mixed as shown in Table 2, and the

obtained mixture was heat molded at 150 °C for 30 minutes to obtain a resin composition. Then, the resin composition was further molded to obtain a molded article with 50 mmφ × 2 mm. The thermal conductivity of the molded article was measured and the result was shown in Table 3.

【0071】

Comparative Example 12

Thermal conductivity measurement was done by following the same procedure as that of Example 8 except that the zinc oxide particle was changed to alumina 10 μm. The result was shown in Table 3.

【0072】

Table 3

		Example 8	Comparative Example 12
Addition amount (weight part)	Silicone resin	14	14
	Curing agent for silicone resin	0.7	0.7
	Zinc oxide particle of Example 1	84	
	Alumina 10 μm		60
Filler (volume %)		50	50
Thermal conductivity (W/m·K)		2.0	1.4

【0073】

Example 9

Silicone oil (KF-99 manufactured by Shin-Etsu Chemical Co., Ltd) and the zinc oxide particle of Example 1 were mixed as shown in Table 4 to obtain an exoergic grease. The thermal conductivity of the exoergic grease was measured and the result was shown in Table 4.

【0074】

Comparative Example 13

Thermal conductivity measurement was done by following the same procedure as that of Example 9 except that the zinc oxide particle was changed to alumina 10 μm . The result was shown in Table 4.

【0075】

Table 4

		Example 9	Comparative Example 13
Addition amount (weight part)	Silicone oil	5	5
	Zinc oxide particle of Example 1	28	
	Alumina 10 μm		20
Filler (volume %)		50	50
Thermal conductivity (W/m·K)		1.7	1.2

【0076】

Example 10

As shown in Table 4, epoxy resin (JER 828 manufactured by JAPAN EPOXY RESIN Co., Ltd), toluene and the zinc oxide particle of Example 1 were dispersed by disper to obtain an exoergic coating composition. The thermal conductivity of the exoergic coating composition was measured and the result was shown in Table 5.

【0077】

Comparative Example 14

Thermal conductivity measurement was done by following the same procedure as that of Example 10 except that the zinc oxide particle was changed to alumina 10 μm . The result was shown in Table 5.

【0072】

Table 5

		Example 10	Comparative Example 14
Addition amount (weight part)	Epoxy resin	6.3	6.3
	Toluene	11.7	11.7
	Zinc oxide particle of Example 1	56	
	Alumina 10 μ m		40
Filler (volume %) (relative to the total amount of the coating composition)		35	35
Thermal conductivity (W/m·K)		1.3	0.9

【0079】

Judging from the results shown in Tables 1 to 5, it's apparent that the exoergic filler of the present invention has superior performances to the exoergic fillers which are used widely. It's apparent that it is able to provide the exoergic property on any of resin compositions of Examples, no matter how great or small of addition amount of the exoergic filler.

INDUSTRIAL APPLICABILITY

【0080】

Zinc oxide particle of the present invention is used suitably as the exoergic fillers. In addition, the particle can be used for applications such as rubber accelerators, pigments for coating compositions and inks, such electronic components as ferrite and varistor, medicinal products and cosmetics.

CLAIMS

1. A zinc oxide particle having a median size of 1 to 30 μm and D90/D10 of 4 or less.
2. The zinc oxide particle according to Claim 1, obtained by baking a raw zinc particle in the presence of ammonium bromide.
3. The zinc oxide particle according to Claim 1 or 2, obtained by mixing the raw zinc particle and 0.1 to 10 weight % of ammonium bromide relative to said raw zinc particle, and static baking the mixture at 600 to 1200 $^{\circ}\text{C}$.
4. A method for producing a zinc oxide particle, comprising baking a raw zinc particle in the presence of ammonium bromide to obtain the zinc oxide particle according to Claim 1.
5. The method for producing a zinc oxide particle according to Claim 4,
wherein ammonium bromide is added in the proportion of 0.1 to 10 weight % relative to the raw zinc particle and the baking is performed by static baking at 600 to 1200 $^{\circ}\text{C}$.
6. An exoergic filler comprising the zinc oxide particle according to any one of Claims 1 to 3.
7. A resin composition comprising the zinc oxide particle according to any one of Claims 1 to 3.
8. An exoergic grease comprising the zinc oxide particle according to any one of Claims 1 to 3 and a base oil.
9. An exoergic coating composition comprising the zinc oxide particle according to any one of Claims 1 to 3.