

DESCRIPTION

TITLE OF INVENTION

5 SPUTTERING TARGET FOR MAGNETIC RECORDING MEDIA

TECHNICAL FIELD

[0001]

10 The present invention relates to a sputtering target for magnetic recording media, and in particular, to a sputtering target that contains metallic Co, metallic Pt, and an oxide.

BACKGROUND ART

[0002]

15 In a magnetic disk for a hard disk drive, information signals are recorded in fine bits of a magnetic recording medium. In order to further improve the recording density of the magnetic recording medium, it is necessary to increase the ratio of signal to noise, which is an index of the information quality, while reducing the
20 size of the bit holding one piece of recording information. In order to increase the ratio of signal to noise, it is essential to increase the signal or reduce the noise.

[0003]

25 At present, a magnetic thin film having a granular structure of a CoPt-based alloy-oxide is utilized as a magnetic recording

medium that serve to record information signals (see, for example, Non-Patent Literature 1). The granular structure is composed of columnar CoPt-based alloy crystal grains and crystal grain boundaries formed from an oxide that surrounds the columnar CoPt-based alloy crystal grains.

[0004]

When the recording density of such a magnetic recording medium is increased, it is necessary to smoothen transitional regions between recording bits to reduce noise. In order to smoothen the transitional regions between the recording bits, it is essential to micronize the CoPt-based alloy crystal grains contained in the magnetic thin film.

[0005]

As the magnetic crystal grains become finer, the intensity of the recording signal that one magnetic crystal grain can hold becomes smaller. In order to achieve both the micronization of the magnetic crystal grains and the intensity of the recording signal, it is necessary to reduce the distance between the centers of the crystal grains.

[0006]

On the other hand, the progress of micronization of the CoPt-based alloy crystal grains in a magnetic recording medium has sometimes resulted in occurrence of the so-called thermal fluctuation phenomenon, in which the superparamagnetic phenomenon impairs the thermal stability of recorded signals and leads to loss

of the recorded signals. This thermal fluctuation phenomenon has contributed a major obstacle to increasing the recording density of magnetic disks.

[0007]

5 In order to surmount this obstacle, the magnetic energy of respective CoPt-based alloy crystal grains needs to be increased such that the magnetic energy exceeds the thermal energy. The magnetic energy of respective CoPt-based alloy crystal grains is obtained by $v \times K_u$, which is a product of the volume v of the CoPt-based alloy crystal grains and the magnetocrystalline anisotropy constant K_u . Therefore, the magnetocrystalline anisotropy constant K_u of the CoPt-based alloy crystal grains needs to be increased in order to increase the magnetic energy of the CoPt-based alloy crystal grains (see, for example, Non-Patent Literature 2).

15 [0008]

 In addition, in order to grow the CoPt-based alloy crystal grains having large K_u in a columnar shape, phase separation between the CoPt-based alloy crystal grains and grain boundary material must be achieved. If the phase separation between the CoPt-based alloy crystal grains and the grain boundary material is insufficient to increase the grain interaction between the CoPt-based alloy crystal grains, the magnetic thin film having the granular structure of the CoPt-based alloy-oxide has had reduced coercive force H_c . As a result, the thermal stability is impaired, and the thermal fluctuation phenomenon may occur with ease. Thus, it is important

to reduce the grain interaction between the CoPt-based alloy crystal grains.

[0009]

The micronization of the magnetic crystal grains and the
5 reduction of the distance between the centers of the magnetic crystal grains may be achieved by micronizing the crystal grains in the Ru underlayer (underlayer provided for orientation control of the magnetic recording medium).

[0010]

10 However, it is difficult to micronize crystal grains in the Ru underlayer while maintaining the crystal orientation (see, for example, Non-Patent Literature 3). Therefore, the size of the crystal grains in the Ru underlayer of the current magnetic recording medium is almost the same as that when the longitudinal magnetic
15 recording media are switched to the perpendicular magnetic recording media, and is about 7 to 8 nm.

[0011]

From the viewpoint of improving the magnetic recording layer instead of the Ru underlayer, an investigation has been made to
20 advance the micronization of magnetic crystal grains. Specifically, an investigation was made to increase the addition amount of the oxide in the CoPt-based alloy-oxide magnetic thin film to decrease the volume ratio of the magnetic crystal grains to micronize the magnetic crystal grains (see, for example, Non-Patent Literature
25 4). This technique achieved the micronization of the magnetic

crystal grains, but has not been able to reduce the distance between the centers of the magnetic crystal grains because the width of the crystal grain boundary increases due to an increase in the addition amount of the oxide.

5 [0012]

In addition, an investigation was made to add a second oxide in addition to the single oxide used in the conventional CoPt-based alloy-oxide magnetic thin film (see, for example, Non-Patent Literature 5). However, when a plurality of oxide materials is added,
10 there is no clear guideline for selecting the materials, and even today, the investigation for searching oxides used as grain boundary materials for the CoPt-based alloy crystal grains is being continued.

CITATION LIST

15 Non-Patent Literature

[0013]

Non-Patent Literature 1: T. Oikawa et al., IEEE TRANSACTIONS ON MAGNETICS, Sep. 2002, VOL.38, NO.5, p.1976-1978

Non-Patent Literature 2: S. N. Piramanayagam, JOURNAL OF
20 APPLIED PHYSICS, 2007, 102, 011301

Non-Patent Literature 3: S. N. Piramanayagam et al., APPLIED PHYSICS LETTERS, 2006, 89, 162504

Non-Patent Literature 4: Y. Inaba et al., IEEE TRANSACTIONS ON MAGNETICS, Jul. 2004, VOL.40, NO.4, p.2486-2488

25 Non-Patent Literature 5: I. Tamai et al., IEEE TRANSACTIONS

SUMMARY OF INVENTION

Technical Problem

5 [0014]

The present invention has been made under such circumstances,
and an object of the present invention is to provide a sputtering
target for magnetic recording media capable of producing a magnetic
thin film in which the magnetic crystal grains are micronized and
10 the distance between the centers of the magnetic crystal grains
is reduced while good magnetic properties are maintained.

Solution to Problem

[0015]

15 The inventor of the present invention has diligently carried
out studies to solve the above-mentioned problems. As a result,
the inventor has found that, in order to realize the micronization
of magnetic crystal grains in a magnetic thin film and the reduction
of the distance between the centers of the magnetic crystal grains,
20 it is effective to make a sputtering target for magnetic recording
media contain oxides having a low melting point and a high melting
point (specifically, make the sputtering target contain B_2O_3 having
a melting point as low as $450^\circ C$ and a high-melting-point oxide having
a melting point higher than the melting point of the CoPt alloy
25 (about $1450^\circ C$)).

[0016]

The present invention has been made on the basis of this new findings.

[0017]

5 Namely, a first aspect of a sputtering target for magnetic recording media according to the present invention is a sputtering target for magnetic recording media comprising metallic Pt and an oxide, with the balance being metallic Co and inevitable impurities, wherein the metallic Co is contained in a range of 70 at% or more
10 and 90 at% or less and the metallic Pt is contained in a range of 10 at% or more and 30 at% or less relative to a total of metallic components in the sputtering target for magnetic recording media, the oxide is contained in a range of 26 vol% or more and 40 vol% or less relative to a total volume of the sputtering target for
15 magnetic recording media, and the oxide is composed of B_2O_3 and one or more high-melting-point oxides having a melting point of 1470°C or higher and 2800°C or lower.

[0018]

20 A second aspect of a sputtering target for magnetic recording media according to the present invention is a sputtering target for magnetic recording media comprising metallic Pt, metallic Cr, and an oxide, with the balance being metallic Co and inevitable impurities, wherein the metallic Co is contained in a range of 70 at% or more and less than 90 at%, the metallic Pt is contained in
25 a range of 10 at% or more and less than 30 at%, and the metallic

Cr is contained in a range of more than 0 at% and 10 at% or less, relative to a total of metallic components in the sputtering target for magnetic recording media, the oxide is contained in a range of 26 vol% or more and 40 vol% or less relative to a total volume of the sputtering target for magnetic recording media, and the oxide is composed of B_2O_3 and one or more high-melting-point oxides having a melting point of 1470°C or higher and 2800°C or lower.

[0019]

It is preferable that a volume ratio of B_2O_3 relative to a total of the one or more high-melting-point oxides is 0.5 or more and 4 or less.

[0020]

The one or more high-melting-point oxides may be selected from the group consisting of TiO_2 , SiO_2 , Ta_2O_5 , Cr_2O_3 , Al_2O_3 , and ZrO_2 .

[0021]

It is preferable that the one or more high-melting-point oxides are TiO_2 .

Advantageous Effects of Invention

[0022]

The present invention can provide a sputtering target for magnetic recording media capable of producing a magnetic thin film in which the magnetic crystal grains are micronized and the distance between the centers of the magnetic crystal grains is reduced while good magnetic properties are maintained.

BRIEF DESCRIPTION OF DRAWINGS

[0023]

FIG. 1 includes schematic diagrams showing a growth process
5 when a granular medium is formed by sputtering using the sputtering
target according to first embodiment of the present invention. FIG.
1(A) is a schematic diagram showing an initial stage of growth of
the granular medium (granular medium 10), and FIG. 1(B) is a schematic
diagram showing an advanced stage of growth of the granular medium
10 (granular medium 20).

FIG. 2 includes schematic diagrams showing a growth process
when a granular medium is formed by sputtering using a sputtering
target that uses only B_2O_3 as the oxide component. FIG. 2(A) is
a schematic diagram showing an initial stage of growth of the granular
15 medium (granular medium 30), and FIG. 2(B) is a schematic diagram
showing an advanced stage of growth of the granular medium (granular
medium 40).

FIG. 3 is a graph showing examples of the granular medium
magnetization curve of the samples for determining magnetic
20 properties of Examples 1, 4 to 6, and Comparative example 1.

FIG. 4 is a graph showing the measured results of X-ray
diffractometry in the in-plane direction (plane direction
perpendicular to the height direction of the columnar CoPt alloy
crystal grains) of the sample for determining magnetic properties
25 of Examples 1, 4 to 6, and Comparative example 1.

FIG. 5 includes plain TEM micrographs obtained by observing a sample for observing texture with a transmission electron microscope (TEM), showing (A) Example 1, (B) Example 4, and (C) Comparative Example 1.

5 FIG. 6 is a cross-section TEM micrograph obtained by observing a sample for observing texture of Example 4 with a transmission electron microscope (TEM).

DESCRIPTION OF EMBODIMENTS

10 [0024]

(1) First embodiment

A sputtering target for magnetic recording media according to a first embodiment of the present invention contains metallic Pt and an oxide, with the balance being metallic Co and inevitable
15 impurities, and is characterized in that the metallic Co is contained in a range of 70 at% or more and 90 at% or less and the metallic Pt is contained in a range of 10 at% or more and 30 at% or less relative to a total of metallic components in the sputtering target for magnetic recording media, the oxide is contained in a range
20 of 26 vol% or more and 40 vol% or less relative to a total volume of the sputtering target for magnetic recording media, and the oxide is composed of B_2O_3 and one or more high-melting-point oxides having a melting point of 1470°C or higher and 2800°C or lower.

[0025]

25 In the present description, a sputtering target for magnetic

recording media may be referred to simply as a sputtering target or a target. In the present description, metallic Co may be simply described as Co, metallic Pt may be simply described as Pt, and metallic Cr may be simply described as Cr.

5 [0026]

(1-1) Component of Sputtering Target

A sputtering target for magnetic recording media according to this first embodiment contains Co and Pt as metal components, and does not contain other metals except for inevitable impurities.

10 [0027]

Metallic Co and metallic Pt are components of magnetic crystal grains (fine magnet) in the granular structure of the magnetic thin film formed by sputtering.

[0028]

15 Co is a ferromagnetic metal element and plays a central role in the formation of the magnetic crystal grains (fine magnet) in the granular structure of the magnetic thin film. In order to increase the magnetocrystalline anisotropy constant K_u of the CoPt alloy crystal grains (magnetic crystal grains) in the magnetic thin
20 film obtained by sputtering and to maintain the magnetism of the CoPt alloy crystal grains (magnetic crystal grains) in the obtained magnetic thin film, the content percentage of Co in the sputtering target according to this first embodiment is 70 at% or more and 90 at% or less relative to the total metallic components (the total
25 of Co and Pt).

[0029]

Platinum, when alloying with Co in a predetermined composition range, has the function of reducing the magnetic moment of the alloy and thus has a role of adjusting the magnetic strength of the magnetic
5 crystal grains. In order to increase the magnetocrystalline anisotropy constant K_u of the CoPt alloy crystal grains (magnetic crystal grains) in the magnetic thin film obtained by sputtering and to adjust the magnetism of the CoPt alloy grains (magnetic crystal grains) in the obtained magnetic thin film, the content percentage
10 of Pt in the sputtering target according to this first embodiment is 10 at% or more and 30 at% or less relative to the total metallic components (the total of Co and Pt).

[0030]

The oxide components of the sputtering target according to
15 this first embodiment are composed of B_2O_3 and one or more high-melting-point oxides having a melting point of 1470°C or higher and 2800°C or lower (hereinafter, sometimes simply referred to as high-melting-point oxide). The oxide component serves as a non-magnetic matrix that separates the magnetic crystal grains (fine
20 magnet) from each other in the granular structure of the magnetic thin film.

[0031]

FIG. 1 includes schematic diagrams showing a growth process when a granular medium (hereinafter, a magnetic thin film may be
25 referred to as a granular medium) is formed by sputtering using

the sputtering target according to this first embodiment. FIG. 1(A) is a schematic diagram showing an initial stage of growth of the granular medium (granular medium 10), and FIG. 1(B) is a schematic diagram showing an advanced stage of growth of the granular medium
5 (granular medium 20).

[0032]

The melting point of the high-melting-point oxide used in the sputtering target according to this first embodiment is 1470°C or higher and 2800°C or lower, which is higher than the melting point
10 of the CoPt alloy serving as the magnetic crystal grains. Therefore, in the film formation process by sputtering using the sputtering target according to this first embodiment, the high-melting-point oxide 14 is deposited on the projected portions of the Ru underlayer 12, which are points where the CoPt alloy is likely to be deposited,
15 prior to the deposition of the CoPt alloy. Therefore, the crystal of the CoPt alloy is grown in a form divided by the deposited high-melting-point oxide 14 as schematically illustrated in FIGS. 1(A) and 1(B), whereby grain growth of the CoPt alloy crystal grains (magnetic crystal grains) 16 in the in-plane direction (in the plane
20 direction perpendicular to the height direction of the columnar CoPt alloy crystal grains 16) is suppressed. Therefore, the CoPt alloy crystal grains 16 grow into the CoPt alloy crystal grains 22 in a columnar shape, and are micronized in the in-plane directions.

[0033]

25 Among the oxide components, the oxide component which is not

a high-melting-point oxide is B_2O_3 (indicated by reference numeral 18 in FIGS 1 and 2), and B_2O_3 has a low melting point of $450^\circ C$. Therefore, in the sputtering-based film formation process, the deposition time of B_2O_3 is delayed, and B_2O_3 is present in a liquid state between the columnar CoPt alloy crystal grains during the columnar crystal growth of the CoPt alloy crystal grains (during the crystal growth of the CoPt alloy crystal grains 16 to the CoPt alloy crystal grains 22). Therefore, B_2O_3 is finally deposited so as to form a crystal grain boundary which separates the CoPt alloy crystal grains 22 grown in a columnar shape, and serves as a non-magnetic matrix which separates the magnetic crystal grains (fine magnets) in the granular structure of the magnetic thin film.

[0034]

FIG. 2 includes schematic diagrams showing a growth process when a granular medium is formed by sputtering using the sputtering target that uses only B_2O_3 as the oxide component. FIG. 2(A) is a schematic diagram showing an initial stage of growth of the granular medium (granular medium 30), and FIG. 2(B) is a schematic diagram showing an advanced stage of growth of the granular medium (granular medium 40).

[0035]

When sputtering is performed using a sputtering target that uses only B_2O_3 as the oxide component to form a granular medium, since the melting point of B_2O_3 , which is the oxide component, is as low as $450^\circ C$, the CoPt alloy having a melting point of about $1450^\circ C$

is first deposited on the projected portions of the Ru underlayer 12. Therefore, one CoPt alloy crystal grain 32 is deposited on one projected portion of the Ru underlayer 12, and the deposited CoPt alloy crystal grains 32 (see FIG. 2(A)) grow like the CoPt alloy crystal grains 42 (see FIG. 2(B)), so that the granular medium further grows.

[0036]

When sputtering is performed using a sputtering target that uses only B_2O_3 as the oxide component to form a granular medium, one CoPt alloy crystal grain 32 is deposited and grown on one projected portion of the Ru underlayer 12. Therefore, it is difficult to micronize the CoPt alloy crystal grains 42 in the in-plane direction beyond the distribution of the projected portions of the Ru underlayer 12.

[0037]

In FIG. 2(B), reference numeral 18A denotes B_2O_3 which has been deposited to become a solid, and reference numeral 18B denotes liquid-state B_2O_3 .

[0038]

The upper limit value of the melting point of the high-melting-point oxide used in the sputtering target according to this first embodiment is $2800^{\circ}C$. A magnetic thin film produced using a sputtering target (Comparative Example 10 indicated in the table 1) for magnetic recording media that used MgO having a melting point ($2852^{\circ}C$) exceeding $2800^{\circ}C$ as the oxide component had no good

magnetic properties, although the reason was unknown. Therefore, the upper limit value of the melting point of the high-melting-point oxide used in the sputtering target according to this first embodiment was defined to 2800°C.

5 [0039]

In the sputtering target according to this first embodiment, the total content percentage of the metal components and the total content percentage of the oxide components relative to the entire sputtering target are determined on the basis of the component
10 composition of the target magnetic thin film, and are not particularly limited. However, the total content percentage of the metal components relative to the entire sputtering target may be, for example, 88 mol% or more and 94 mol% or less, and the total content percentage of the oxide component relative to the entire sputtering
15 target may be, for example, 6 mol% or more and 12 mol% or less.

[0040]

As described above, in the granular structure of the magnetic thin film, the oxide components serve as a non-magnetic matrix that separates the magnetic crystal grains (fine magnets) from each other.
20 Therefore, it is preferable to increase the content of the oxides in the magnetic thin film because the magnetic crystal grains can be reliably and easily separated and the magnetic crystal grains can be easily made independent of each other. From this point of view, the content of the oxides contained in the sputtering target
25 according to this first embodiment is preferably 26 vol% or more,

more preferably 28 vol% or more, and further preferably 29 vol% or more.

[0041]

However, if the content of the oxides in the magnetic thin
5 film becomes too large, the oxides are mixed into the CoPt alloy
crystal grains (magnetic crystal grains) and adversely affect the
crystallinity of the CoPt alloy crystal grains (magnetic crystal
grains). As a result, the proportion of structures other than the
hcp in the CoPt alloy crystal grains (magnetic crystal grains) may
10 increase. This also reduces the number of the magnetic crystal grains
per unit area in the magnetic thin film, and thus makes it difficult
to increase the recording density. From these points of view, the
content of the oxides contained in the sputtering target according
to this first embodiment is preferably 40 vol% or less, more preferably
15 35 vol% or less, and further preferably 31 vol% or less.

[0042]

The content of the oxides contained in the sputtering target
according to this first embodiment relative to the entire sputtering
target is preferably 26 vol% or more and 40 vol% or less, more
20 preferably 28 vol% or more and 35 vol% or less, and further preferably
29 vol% or more and 31 vol% or less.

[0043]

As described above, the oxide components contained in the
sputtering target according to this first embodiment are composed
25 of B_2O_3 and one or more high-melting-point oxides having a melting

point of 1470°C or higher and 2800°C or lower. The volume ratio of B₂O₃ relative to the total of the one or more high-melting-point oxides is preferably 0.5 or more and 4.0 or less, more preferably 0.7 or more and 3.5 or less, and further preferably 0.8 or more and 3.0 or less from the viewpoint of depositing the high-melting-point oxide on the projected portions of the Ru underlayer by an appropriate amount prior to the deposition of the CoPt alloy to make the CoPt alloy crystal grains (magnetic crystal grains) appropriately fine.

10 [0044]

Examples of the high-melting-point oxide that can be the oxide component of the sputtering target according to this first embodiment include TiO₂, SiO₂, Ta₂O₅, Cr₂O₃, Al₂O₃, and ZrO₂. From the viewpoint of micronization of the magnetic crystal grains in the magnetic thin film and reduction of the distance between the centers of the magnetic crystal grains, the high-melting-point oxide contained in the sputtering target according to this first embodiment is preferably one or more types of oxides selected from the group consisting of TiO₂, SiO₂, Ta₂O₅, Cr₂O₃, Al₂O₃, and ZrO₂, and is more preferably TiO₂.

[0045]

(1-2) Microstructure of Sputtering Target

The microstructure of the sputtering target according to this first embodiment is not particularly limited, but is preferably a microstructure in which a metal phase and an oxide phase are finely

dispersed in each other. Such a microstructure makes it difficult to generate defects such as nodules and particles during sputtering.

[0046]

(1-3) Process for Production of Sputtering Target

5 The sputtering target according to this first embodiment can be produced, for example, in the following manner.

[0047]

(1-3-1) Preparation of CoPt Alloy-Atomized Powder

Co and Pt are weighed so as to obtain a prescribed composition
10 (the atomic ratio of metallic Co to the total of the metallic Co and metallic Pt is 70 at% or more and 90 at% or less), and a molten CoPt alloy is produced. Subsequently, the molten CoPt alloy is gas-atomized to prepare a CoPt alloy-atomized powder. The produced CoPt alloy-atomized powder is classified so that the particle size
15 becomes not larger than a predetermined particle size (for example, 106 μm or smaller).

[0048]

(1-3-2) Preparation of Powder Mixture for Pressure Sintering

A B_2O_3 powder and high-melting-point oxides powder (for example,
20 TiO_2 powder, SiO_2 powder, Ta_2O_5 powder, Cr_2O_3 powder, Al_2O_3 powder, and ZrO_2 powder) are added to the CoPt alloy-atomized powder prepared in (1-3-1). The mixture is dispersedly mixed with a ball mill to prepare a powder mixture for pressure sintering. By dispersedly mixing the CoPt alloy-atomized powder, the B_2O_3 powder, and the
25 high-melting-point oxides powder with the ball mill, a powder mixture

for pressure sintering in which the CoPt alloy-atomized powder, the B_2O_3 powder, and high-melting-point oxides powder are finely dispersed in each other can be prepared.

[0049]

5 In the magnetic thin film formed by using the obtained sputtering target, the volume fraction of the total of the B_2O_3 powder and the high-melting-point oxides powder in the entire powder mixture for pressure sintering is preferably 26 vol% or more and 40 vol% or less, more preferably 28 vol% or more and 35 vol% or less, and
10 still more preferably 29 vol% or more and 31 vol% or less in order to easily make the magnetic crystal grains independent from each other by assuredly separating the magnetic crystal grains from each other by B_2O_3 and high-melting-point oxides, to makes it easy for the CoPt alloy crystal grains (magnetic crystal grains) to have
15 the hcp structure, and to increase the recording density.

[0050]

(1-3-3) Molding

The powder mixture for pressure sintering prepared in (1-3-2) is pressure-sintered and molded using, for example, a vacuum hot
20 pressing method to produce a sputtering target. Since the powder mixture for pressure sintering prepared in (1-3-2) has been dispersedly mixed with a ball mill and the CoPt alloy-atomized powder and the oxides powder (the B_2O_3 powder and the high-melting-point oxides) are finely dispersed in each other, defects such as generation
25 of nodules and particles are unlikely to occur during sputtering

using the sputtering target obtained by this production process.

[0051]

The method for pressure-sintering the powder mixture for pressure sintering is not limited. The method may be a method other
5 than a vacuum hot pressing method and may be, for example, a HIP method.

[0052]

(1-3-4) Modification

The example of production process described in (1-3-1) to
10 (1-3-3) involves preparing the CoPt alloy-atomized powder by an atomizing method, adding the B_2O_3 powder and the high-melting-point oxides powder to the prepared CoPt alloy-atomized powder, and dispersedly mixing the mixture with the ball mill to prepare the powder mixture for pressure sintering. A Co single powder and a
15 Pt single powder may be used instead of using the CoPt alloy-atomized powder. In such a case, four types of powder, which are a Co single powder, a Pt single powder, a B_2O_3 powder, and a high-melting-point oxide powder are dispersedly mixed with a ball mill to prepare a powder mixture for pressure sintering.

20 [0053]

(2) Second embodiment

A sputtering target for magnetic recording media according to a second embodiment of the present invention contains metallic Pt, metallic Cr, and an oxide, with the balance being metallic Co
25 and inevitable impurities, and is characterized in that the metallic

Co is contained in a range of 70 at% or more and less than 90 at%,
the metallic Pt is contained in a range of 10 at% or more and less
than 30 at%, and the metallic Cr is contained in a range of more
than 0 at% and 10 at% or less, relative to a total of metallic components
5 in the sputtering target for magnetic recording media, the oxide
is contained in a range of 26 vol% or more and 40 vol% or less relative
to a total volume of the sputtering target for magnetic recording
media, and the oxide is composed of B_2O_3 and one or more
high-melting-point oxides having a melting point of 1470°C or higher
10 and 2800°C or lower.

[0054]

(2-1) Component of Sputtering Target

A sputtering target for magnetic recording media according
to this second embodiment contains Co, Pt, and Cr as metal components,
15 and does not contain other metals except for inevitable impurities.

[0055]

The roles of the metallic Co and the metallic Pt in the sputtering
target for magnetic recording media according to this second
embodiment are the same as the roles of the metallic Co and the
20 metallic Pt in the sputtering target for magnetic recording media
according to the first embodiment, and therefore a description
thereof is omitted here.

[0056]

Cr has a function of reducing the magnetic moment of Co when
25 alloyed with Co within a prescribed composition range and plays

a role in controlling the strength of the magnetism of the magnetic crystal grains.

[0057]

In order to increase the magnetocrystalline anisotropy
5 constant K_u of the CoPtCr alloy crystal grains (magnetic crystal grains) in the magnetic thin film obtained by sputtering and to maintain the magnetism of the CoPtCr alloy crystal grains in the obtained magnetic thin film, the content percentage of Co in the sputtering target according to this second embodiment is 70 at%
10 or more and less than 90 at% relative to the total metallic components (the total of Co, Pt, and Cr), the content percentage of Pt in the sputtering target according to this second embodiment is 10 at% or more and less than 30 at% relative to the total metallic components (the total of Co, Pt, and Cr), and the content percentage of Cr
15 in the sputtering target according to this second embodiment is more than 0 at% and 10 at% or less relative to the total metallic components (the total of Co, Pt, and Cr).

[0058]

The oxide components of the sputtering target according to
20 this second embodiment are composed of B_2O_3 and one or more high-melting-point oxides having a melting point of 1470°C or higher and 2800°C or lower. The oxide component serves as a non-magnetic matrix that separates the magnetic crystal grains (fine magnet) from each other in the granular structure of the magnetic thin film.

25 [0059]

The melting point of the high-melting-point oxide used in the sputtering target according to this second embodiment is 1470°C or higher and 2800°C or lower, which is higher than the melting point of the CoPtCr alloy serving as the magnetic crystal grains. Therefore, in the film formation process (the growth process of a granular medium) by sputtering using the sputtering target according to this second embodiment, the high-melting-point oxide is deposited on the projected portions of the Ru underlayer, which are points where the CoPtCr alloy is likely to be deposited, prior to the deposition of the CoPtCr alloy. Therefore, the crystal of the CoPtCr alloy is grown in a form divided by the deposited high-melting-point oxide, whereby grain growth of the CoPtCr alloy crystal grains in the in-plane direction (in the plane direction perpendicular to the height direction of the columnar CoPtCr alloy crystal grains) is suppressed. Therefore, the CoPtCr alloy crystal grains (magnetic crystal grains) grow in a columnar shape, and are micronized in the in-plane directions.

[0060]

Among the oxide components, the oxide component which is not a high-melting-point oxide is B₂O₃, and B₂O₃ has a low melting point of 450°C. Therefore, in the sputtering-based film formation process, the deposition time of B₂O₃ is delayed, and B₂O₃ is present in a liquid state between the columnar CoPtCr alloy crystal grains during the columnar crystal growth of the CoPtCr alloy crystal grains. Therefore, B₂O₃ is finally deposited so as to form a crystal grain

boundary which separates the CoPtCr alloy crystal grains grown in a columnar shape, and serves as a non-magnetic matrix which separates the magnetic crystal grains (fine magnets) in the granular structure of the magnetic thin film.

5 [0061]

The upper limit value of the melting point of the high-melting-point oxide used in the sputtering target according to this second embodiment is 2800°C. A magnetic thin film produced using a sputtering target (Comparative Example 10 described later)
10 for magnetic recording media that used MgO having a melting point (2852°C) exceeding 2800°C as the oxide component had no good magnetic properties, although the reason was unknown. Therefore, the upper limit value of the melting point of the high-melting-point oxide used in the sputtering target according to this second embodiment
15 was defined to 2800°C.

[0062]

In the sputtering target according to this second embodiment, the total content percentage of the metal components and the total content percentage of the oxide components relative to the entire
20 sputtering target are determined on the basis of the component composition of the target magnetic thin film, and are not particularly limited. However, the total content percentage of the metal components relative to the entire sputtering target may be, for example, 88 mol% or more and 94 mol% or less, and the total content
25 percentage of the oxide component relative to the entire sputtering

target may be, for example, 6 mol% or more and 12 mol% or less.

[0063]

As described above, in the granular structure of the magnetic thin film, the oxide components serve as a non-magnetic matrix that separates the magnetic crystal grains (fine magnets) from each other. Therefore, it is preferable to increase the content of the oxides in the magnetic thin film because the magnetic crystal grains can be reliably and easily separated and the magnetic crystal grains can be easily made independent of each other. From this point of view, the content of the oxides contained in the sputtering target according to this second embodiment is preferably 26 vol% or more, more preferably 28 vol% or more, and further preferably 29 vol% or more.

[0064]

However, if the content of the oxides in the magnetic thin film becomes too large, the oxides are mixed into the CoPtCr alloy crystal grains (magnetic crystal grains) and adversely affect the crystallinity of the CoPtCr alloy crystal grains (magnetic crystal grains). As a result, the proportion of structures other than the hcp in the CoPtCr alloy crystal grains (magnetic crystal grains) may increase. This also reduces the number of the magnetic crystal grains per unit area in the magnetic thin film, and thus makes it difficult to increase the recording density. From these points of view, the content of the oxides contained in the sputtering target according to this second embodiment is preferably 40 vol% or less,

more preferably 35 vol% or less, and further preferably 31 vol% or less.

[0065]

The content of the oxides contained in the sputtering target according to this second embodiment relative to the entire sputtering target is preferably 26 vol% or more and 40 vol% or less, more preferably 28 vol% or more and 35 vol% or less, and further preferably 29 vol% or more and 31 vol% or less.

[0066]

As described above, the oxide components contained in the sputtering target according to this second embodiment are composed of B_2O_3 and one or more high-melting-point oxides having a melting point of 1470°C or higher and 2800°C or lower. The volume ratio of B_2O_3 relative to the total of the one or more high-melting-point oxides is preferably 0.5 or more and 4.0 or less, more preferably 0.7 or more and 3.5 or less, and further preferably 0.8 or more and 3.0 or less from the viewpoint of depositing the high-melting-point oxide on the projected portions of the Ru underlayer by an appropriate amount prior to the deposition of the CoPt alloy to make the CoPtCr alloy crystal grains (magnetic crystal grains) appropriately fine.

[0067]

Examples of the high-melting-point oxide that can be the oxide component of the sputtering target according to this second embodiment include TiO_2 , SiO_2 , Ta_2O_5 , Cr_2O_3 , Al_2O_3 , and ZrO_2 . From

the viewpoint of micronization of the magnetic crystal grains in the magnetic thin film and reduction of the distance between the centers of the magnetic crystal grains, the high-melting-point oxide contained in the sputtering target according to this second

5 embodiment is preferably one or more types of oxides selected from the group consisting of TiO_2 , SiO_2 , Ta_2O_5 , Cr_2O_3 , Al_2O_3 , and ZrO_2 , and is more preferably TiO_2 .

[0068]

(2-2) Microstructure of Sputtering Target

10 The microstructure of the sputtering target according to this second embodiment is not particularly limited, but is preferably a microstructure in which a metal phase and an oxide phase are finely dispersed in each other. Such a microstructure makes it difficult to generate defects such as nodules and particles during sputtering.

15 [0069]

(2-3) Process for Production of Sputtering Target

The process for production of the sputtering target according to the second embodiment differs from the process for production of the sputtering target according to the first embodiment in that
20 a CoPtCr alloy-atomized powder having a predetermined composition is prepared instead of the CoPt alloy-atomized powder having a predetermined composition, but the other points are the same as those of the process for production of the sputtering target according to the first embodiment, and therefore descriptions thereof are
25 omitted here.

[0070]

In the process for production of the sputtering target according to this second embodiment, a Co single powder, a Pt single powder, and a Cr single powder may be used instead of producing the CoPtCr alloy-atomized powder having a predetermined composition. In such a case, five types of powder, which are a Co single powder, a Pt single powder, a Cr single powder, a B₂O₃ powder, and a high-melting-point oxide powder are dispersedly mixed with a ball mill to prepare a powder mixture for pressure sintering.

10

EXAMPLES

[0071]

Examples and Comparative Examples are described below.

[0072]

15 (Example 1)

The composition of the entire target prepared as Example 1 is (80Co-20Pt)-15vol%B₂O₃-15vol%TiO₂, and is represented as 89.3(80Co-20Pt)-3.6B₂O₃-7.1TiO₂ in terms of molar ratio.

[0073]

20 To prepare the target according to Example 1, an 80Co-20Pt alloy-atomized powder was prepared first. Specifically, metals were weighed so as to obtain an alloy composition of Co: 80 at% and Pt: 20 at% and heated to 1500°C or higher to prepare a molten alloy. The molten alloy was gas-atomized to prepare an 80Co-20Pt alloy-atomized powder.

25

[0074]

The prepared 80Co-20Pt alloy-atomized powder was separately classified through 150 mesh sieves to obtain 80Co-20Pt alloy-atomized powder having a particle diameter of 106 μm or smaller.

5 [0075]

In order to obtain the composition of (80Co-20Pt)-15vol%B₂O₃-15vol%TiO₂, a B₂O₃ powder and a TiO₂ powder were added to the classified 80Co-20Pt alloy-atomized powder, and mixed and dispersed with a ball mill to obtain a mixed powder for
10 pressure sintering.

[0076]

The obtained powder mixture for pressure sintering was subjected to hot pressing under the conditions of sintering temperature: 920°C, pressure: 24.5 MPa, time: 30 min, and atmosphere:
15 5×10^{-2} Pa or lower to prepare a sintered test piece (ϕ 30 mm). The relative density of the prepared sintered test piece was 97.419%. The calculated density is 9.39 g/cm³. The cross section in the thickness direction of the obtained sintered test piece was observed with a metallograph, and it was found that the metal phase (80Co-20Pt
20 alloy phase) and the oxide phase (B₂O₃ + TiO₂ phase) were finely dispersed.

[0077]

Next, the prepared powder mixture for pressure sintering was subjected to hot pressing under the conditions of sintering
25 temperature: 920°C, pressure: 24.5 MPa, time: 60 min, and atmosphere:

5×10^{-2} Pa or lower to prepare a target with $\phi 153.0 \times 1.0$ mm + $\phi 161.0 \times 4.0$ mm. The relative density of the prepared target was 98.4%.
[0078]

A magnetic thin film made of (80Co-20Pt)-15 vol% B₂O₃-15 vol%
5 TiO₂ was deposited on a glass substrate by sputtering with DC
sputtering device using the prepared target to produce a sample
for determining magnetic properties and a sample for observing
texture. The stacked structure of these samples includes, in order
of increasing distance from the glass substrate, Ta (5 nm, 0.6 Pa)
10 / Ni₉₀W₁₀ (6 nm, 0.6 Pa) / Ru (10 nm, 0.6 Pa) / Ru (10 nm, 8 Pa) /
CoPt alloy-oxide (16 nm, 4 Pa) / C (7 nm, 0.6 Pa). The number on
the left side in parenthesis indicates the film thickness, and the
number on the right side indicates the pressure of an Ar atmosphere
during sputtering. The magnetic thin film formed using the target
15 that is prepared in this Example 1 is formed of a CoPt alloy-oxide
(B₂O₃ + TiO₂) and is a magnetic thin film serving as a recording
layer of a perpendicular magnetic recording medium. This magnetic
thin film was deposited at room temperature without heating the
substrate during film deposition.

20 [0079]

A vibration type magnetometer and a torque magnetometer were
used to determine the magnetic properties of the obtained sample
for determining magnetic properties, and a polar Kerr effect
measuring apparatus was used to determine the thermal fluctuation
25 resistance of the sample for determining magnetic properties. In

addition, an X-ray diffraction apparatus and a transmission electron microscope were used to evaluate the structure of the obtained sample for observing texture (evaluation of the grain size and the like of the magnetic crystal grains).

5 [0080]

An example of the granular medium magnetization curve of the sample for determining magnetic properties of Example 1 is shown in FIG. 3 together with the results of other Examples and Comparative Examples. The horizontal axis of FIG. 3 represents the strength
10 of the applied magnetic field, and the vertical axis of FIG. 3 represents the strength of magnetization per unit volume.

[0081]

In addition, the saturation magnetization M_s , the coercive force H_c , and the inclination α at the point crossing the horizontal
15 axis were obtained from the measured results of the granular medium magnetization curve of the sample for determining magnetic properties. The magnetocrystalline anisotropy constant K_u was measured using a torque magnetometer. These values are shown in Table 1 together with the results of other Examples and Comparative
20 Examples.

[0082]

FIG. 4 shows the measured results of X-ray diffractometry in the in-plane direction (plane direction perpendicular to the height direction of the columnar CoPt alloy crystal grains) of the sample
25 for determining magnetic properties of Example 1 together with the

results of other Examples and Comparative Examples. Among the measured results of the X-ray diffraction shown in FIG. 4, the Sherrer equation was applied to the measured result of the diffraction line of the hexagonal CoPt (11.0) to calculate the grain size GD_{inplane} (nm) of the CoPt alloy crystal grains. The calculation results are shown in Table 1 together with the results of other Examples and Comparative Examples.

[0083]

In addition, it was confirmed from the measured results of the X-ray diffractometry of Example 1 in the in-plane direction that all the CoPt alloy crystal grains were oriented in the C-plane.

[0084]

In addition, the thermal fluctuation resistance was measured, and the magnetized regions inverted by thermal energies, that is, the grain size GD_{act} of the magnetic crystal grains determined considering the interchange coupling between grains was determined. The measured results are shown in Table 1 together with the results of other Examples and Comparative Examples.

[0085]

In addition, the samples for observing texture were observed by a transmission electron microscopy (TEM) on a plane substantially perpendicular to the height direction of the columnar CoPt alloy crystal grains. The plane TEM micrographs of the observation results are shown in FIG. 5 together with the results of Example 4 and Comparative Example 1.

[0086]

Further, in the plane TEM micrographs obtained, the diameter (circumference corresponding diameter) determined by specifying each CoPt crystal grain by image-processing and replacing the circumference thereof with a perfect circle was defined as GD_{TEM} . The centers of gravity of the respective particles were calculated by the image-processing, and the distance between the centers of gravity of adjacent particles was obtained as GP_{TEM} . The measured results are shown in Table 1 together with the results of other Examples and Comparative Examples.

[0087]

In addition, thin grain boundaries were observed in some of the CoPt crystal grains, as can be seen from the plane TEM micrograph of this Example 1 that used TiO_2 as a high-melting-point oxide. As described above, this thin grain boundary is considered to be a high-melting-point oxide TiO_2 deposited prior to the deposition of the CoPt alloy. Note that, in FIG. 5(A), the CoPt crystal grains in which thin grain boundaries of TiO_2 were observed are surrounded by a dotted line.

[0088]

(Examples 2 to 27 and Comparative Examples 1 to 16)

Samples for determining magnetic properties and samples for observing texture were prepared in the same manner as that in Example 1 except that the target composition was changed from that of Example 1, and evaluated in the same manner as in Example 1. The measured

results are shown in Table 1 together with the target compositions. Concrete measured results for Examples 4 to 6 and Comparative Example 1 are also shown in FIGS. 3 and 4.

[0089]

5 As can be seen from the plane TEM micrograph in FIG. 5(B) of Example 4 that used Cr_2O_3 as the high-melting-point oxide, thin grain boundaries were observed in some CoPt alloy crystal grains in Example 4 as in Example 1. In FIG. 5(B), the CoPt alloy crystal grains in which the thin grain boundaries of Cr_2O_3 were observed are surrounded
10 by a dotted line.

[0090]

 For the sample for observing texture of Example 4, a cut surface that was approximately parallel to the height direction of the columnar CoPt alloy crystal grains was observed by TEM. A
15 cross-sectional TEM micrograph of the observation result is shown in FIG. 6. As shown in the cross-sectional TEM micrograph of FIG. 6, it is observed that a plurality of CoPt alloy crystal grains grow on one Ru crystal grain.

[0091]

20

25

[Table 1]

	Co	Pt	Cr	First Oxide	Second Oxide	M.P. of Second Oxide (°C)	First and Second Oxides Total vol.%	Volume Ratio of First Oxide to Second Oxide	K_u ($\times 10^6$ erg/cm ³)	M_s (emu/cm ³)	H_c (kOe)	α	GD_{act} (nm)	GD_{aplane} (nm)	GD_{TEM} (nm)	GP_{TEM} (nm)
Comparative Example 1	80	20	0	B2O3	30	0	450	30	7.4	818	7.2	1.8	6.5	5.6	6.7	8.1
Comparative Example 2	80	20	0	MoO3	30	0	795	30	5.3	690	5.3	1.4	7.8	6.2	6.8	8.1
Comparative Example 3	80	20	0	Ta2O5	30	0	1470	30	6.3	750	4.3	2.0	7.7	6.3	6.9	8.1
Comparative Example 4	80	20	0	SiO2	30	0	1600	30	5.9	746	4.6	2.1	7.9	6.4	6.8	8.1
Comparative Example 5	80	20	0	TiO2	30	0	1843	30	5.8	734	5.9	1.6	6.4	5.5	6.7	8.1
Comparative Example 6	80	20	0	Al2O3	30	0	2072	30	3.6	615	0.7	2.8	11.6	11.0	7.3	8.3
Comparative Example 7	80	20	0	Cr2O3	30	0	2435	30	3.8	611	1.6	4.0	11.5	10.6	7.5	8.5
Comparative Example 8	80	20	0	ZrO2	30	0	2700	30	4.8	725	1.0	5.0	11.5	10.7	7.6	8.5
Comparative Example 9	80	20	0	MgO	30	0	2852	30	4.3	640	1.1	5.5	11.9	10.9	7.7	8.6
Comparative Example 10	80	20	0	B2O3	15	MgO 15	2852	30	3.9	620	3.6	2.7	8.5	5.3	7.1	8.3
Comparative Example 11	80	20	0	B2O3	15	MoO3 15	795	30	5.2	695	5.3	1.5	7.0	5.4	7.2	8.1
Comparative Example 12	80	20	0	B2O3	21	TiO2 21	1843	42	6.2	710	5.2	2.0	6.7	5.2	6.5	7.4
Comparative Example 13	80	20	0	B2O3	12	TiO2 12	1843	24	7.2	840	6.7	1.9	7.0	5.6	6.9	7.9
Comparative Example 14	92	8	0	B2O3	15	TiO2 15	1843	30	5.5	889	4.1	2.1	6.8	5.4	6.5	7.7
Comparative Example 15	68	32	0	B2O3	15	TiO2 15	1843	30	6.1	727	4.3	2.2	7.1	5.7	6.5	7.7
Comparative Example 16	68	20	12	B2O3	15	TiO2 15	1843	30	5.9	702	5.1	1.4	6.9	5.2	6.6	7.8
Example 2	80	20	0	B2O3	15	ZrO2 15	2700	30	4.9	689	5.0	2.5	8.1	4.6	6.7	8.2
Example 3	80	20	0	B2O3	15	Al2O3 15	2435	30	5.7	705	5.3	2.4	7.9	4.5	6.8	8.0
Example 4	80	20	0	B2O3	15	Cr2O3 15	2435	30	6.5	733	5.9	2.2	7.6	4.7	6.7	7.9
Example 1	80	20	0	B2O3	15	TiO2 15	1843	30	7.7	806	7.1	1.8	6.6	4.8	6.5	7.7
Example 5	80	20	0	B2O3	15	SiO2 15	1600	30	7.3	795	6.2	2.0	7.3	5.8	6.7	7.8
Example 6	80	20	0	B2O3	15	Ta2O5 15	1470	30	6.5	765	6.5	1.8	7.9	5.2	6.9	8.1
Example 7	80	20	0	B2O3	24	ZrO2 6	2700	30	7.4	823	6.8	1.9	7.6	4.8	6.7	8.1
Example 8	80	20	0	B2O3	24	Al2O3 6	2435	30	6.6	774	6.2	1.9	7.4	4.9	6.7	7.9
Example 9	80	20	0	B2O3	24	Cr2O3 6	2435	30	7.4	814	7.1	1.6	7.2	4.8	6.7	7.9
Example 10	80	20	0	B2O3	24	TiO2 6	1843	30	7.6	819	7.3	1.7	6.4	4.7	6.7	7.9
Example 11	80	20	0	B2O3	24	SiO2 6	1600	30	7.4	812	6.7	1.9	7.6	5.7	6.8	7.7
Example 12	80	20	0	B2O3	24	Ta2O5 6	1470	30	6.9	795	6.9	1.6	8.1	5.4	6.7	7.8
Example 13	80	20	0	B2O3	10	ZrO2 20	2700	30	4.6	675	3.9	3.1	8.3	4.5	6.7	7.9
Example 14	80	20	0	B2O3	10	Al2O3 20	2435	30	5.4	697	4.6	2.8	8.0	4.3	6.7	8.0
Example 15	80	20	0	B2O3	10	Cr2O3 20	2435	30	6.2	715	5.1	2.4	7.8	4.2	6.7	8.0
Example 16	80	20	0	B2O3	10	TiO2 20	1843	30	7.2	795	6.4	2.1	6.8	4.3	6.7	8.0
Example 17	80	20	0	B2O3	10	SiO2 20	1600	30	6.9	776	5.5	2.2	7.4	4.6	6.7	7.9
Example 18	80	20	0	B2O3	10	Ta2O5 20	1470	30	6.1	751	5.7	2.0	7.8	4.7	6.7	7.9
Example 19	80	20	0	B2O3	13	TiO2 13	1843	26	8.1	835	7.4	1.9	6.8	4.9	6.8	7.9
Example 20	80	20	0	B2O3	18	TiO2 18	1843	36	7.4	770	6.7	1.6	6.4	4.6	6.6	7.6
Example 21	80	20	0	B2O3	20	TiO2 20	1843	40	7.0	739	6.2	1.5	6.2	4.4	6.5	7.5
Example 22	70	20	10	B2O3	15	TiO2 15	1843	30	7.2	771	7.6	1.6	6.3	4.3	6.7	7.8
Example 23	75	20	5	B2O3	15	TiO2 15	1843	30	7.5	790	7.3	1.7	6.4	4.6	6.6	7.7
Example 24	70	30	0	B2O3	15	TiO2 15	1843	30	7.5	801	7.1	1.9	6.6	4.8	6.6	7.7
Example 25	75	25	0	B2O3	15	TiO2 15	1843	30	7.8	815	7.3	1.8	6.7	4.7	6.6	7.7
Example 26	85	15	0	B2O3	15	TiO2 15	1843	30	7.4	830	7.0	1.9	6.7	4.7	6.6	7.7
Example 27	90	10	0	B2O3	15	TiO2 15	1843	30	7.1	871	6.5	1.9	6.5	4.7	6.6	7.7

[0092]

As is clear from Table 1, in Examples 1 to 27 which are within the scope of the present invention, the magnetic thin films in which the micronization of magnetic crystal grains and the reduction of the distance between centers of magnetic crystal grains were achieved
5 were obtained, and the magnetic thin films obtained in Examples 1 to 27 exhibit good magnetic properties.

[0093]

On the other hand, in Comparative Examples 1 to 16 which are
10 not within the scope of the present invention, any magnetic thin film was not obtained in which the micronization of the magnetic crystal grains, the reduction of the distance between the centers of the magnetic crystal grains, and the expression of good magnetic properties were simultaneously achieved.

15 [0094]

Here, from the viewpoint of being a good magnetic thin film, the magnetocrystalline anisotropy constant K_u and $GD_{inplane}$ are preferably $K_u > 4.6 \times 10^6 \text{ erg/cm}^3$ and $GD_{inplane} < 5.1 \text{ nm}$, and more preferably $K_u > 6.0 \times 10^6 \text{ erg/cm}^3$ and $GD_{inplane} < 4.8 \text{ nm}$. Most of the
20 magnetic thin films obtained in Examples 1 to 27 satisfy the preferable conditions ($K_u > 4.6 \times 10^6 \text{ erg/cm}^3$ and $GD_{inplane} < 5.1 \text{ nm}$), and some of the magnetic thin films obtained in Examples 1 to 27 also satisfy the more preferable conditions ($K_u > 6.0 \times 10^6 \text{ erg/cm}^3$ and $GD_{inplane} < 4.8 \text{ nm}$).

25 [0095]

It should be noted that the above-mentioned preferable conditions ($K_u > 4.6 \times 10^6 \text{ erg/cm}^3$ and $GD_{\text{inplane}} < 5.1 \text{ nm}$) and the above-mentioned more preferable conditions ($K_u > 6.0 \times 10^6 \text{ erg/cm}^3$ and $GD_{\text{inplane}} < 4.8 \text{ nm}$) are criteria for judging that the thin film
5 is a good magnetic thin film, and it does not mean that a sample that does not satisfy these conditions straightforwardly falls outside the scope of the present invention.

[0096]

For example, the values of GD_{inplane} of Examples 5 and 11 that
10 used SiO_2 as the second oxide were 5.8 nm and 5.7 nm, respectively, and the condition for GD_{inplane} among the above-mentioned preferable conditions ($K_u > 4.6 \times 10^6 \text{ erg/cm}^3$ and $GD_{\text{inplane}} < 5.1 \text{ nm}$) and the condition for GD_{inplane} among the above-mentioned more preferable conditions ($K_u > 6.0 \times 10^6 \text{ erg/cm}^3$ and $GD_{\text{inplane}} < 4.8 \text{ nm}$) were not satisfied.
15 However, the values were smaller than GD_{inplane} (6.4 nm) of Comparative Example 4 that used only SiO_2 as the oxide, and thus the effects of the present invention were exhibited. K_u 's of Examples 5 and 11 were $7.3 \times 10^6 \text{ erg/cm}^3$ and $7.4 \times 10^6 \text{ erg/cm}^3$, respectively, which were larger than K_u ($5.9 \times 10^6 \text{ erg/cm}^3$) of Comparative Example 4 that
20 used only SiO_2 as the oxide.

[0097]

The values of GD_{inplane} of Examples 6 and 12 that used Ta_2O_5 as the second oxide were 5.2 nm and 5.4 nm, respectively, and the condition for GD_{inplane} among the above-mentioned preferable
25 conditions ($K_u > 4.6 \times 10^6 \text{ erg/cm}^3$ and $GD_{\text{inplane}} < 5.1 \text{ nm}$) and the condition

for GD_{inplane} among the above-mentioned more preferable conditions ($K_u > 6.0 \times 10^6 \text{ erg/cm}^3$ and $GD_{\text{inplane}} < 4.8 \text{ nm}$) were not satisfied. However, the values were smaller than GD_{inplane} (6.3 nm) of Comparative Example 3 that used only Ta_2O_5 as the oxide, and the effects of the present invention were exhibited. In addition, K_u 's of Examples 6 and 12 were $6.5 \times 10^6 \text{ erg/cm}^3$ and $6.9 \times 10^6 \text{ erg/cm}^3$, respectively, which were larger than K_u of Comparative Example 3 ($6.3 \times 10^6 \text{ erg/cm}^3$) that used only Ta_2O_5 as the oxide.

[0098]

Further, K_u of Example 13 that used ZrO_2 as the second oxide was $4.6 \times 10^6 \text{ erg/cm}^3$ and the condition for K_u among the above-mentioned preferable conditions ($K_u > 4.6 \times 10^6 \text{ erg/cm}^3$ and $GD_{\text{inplane}} < 5.1 \text{ nm}$) and the condition for K_u among the above-mentioned more preferable conditions ($K_u > 6.0 \times 10^6 \text{ erg/cm}^3$ and $GD_{\text{inplane}} < 4.8 \text{ nm}$) were not satisfied. However, GD_{inplane} of Example 13 was 4.5 nm, which was remarkably smaller than GD_{inplane} (10.7 nm) of Comparative Example 8 that used only ZrO_2 as the oxide, and the effects of the present invention were exhibited.

Industrial Applicability

[0099]

The sputtering target for magnetic recording media according to the present invention is capable of producing a magnetic thin film in which magnetic crystal grains are micronized and the distance between the centers of the magnetic crystal grains is reduced while

good magnetic properties are maintained, and has industrial applicability.

Reference Signs List

- 5 [0100]
- 10, 20, 30, 40 granular medium
- 12 Ru underlayer
- 14 high-melting-point oxide
- 16, 22, 32, 42 CoPt alloy crystal grain
- 10 18 B_2O_3
- 18A B_2O_3 which has been deposited to become a solid
- 18B liquid-state B_2O_3

CLAIMS

1. A sputtering target for magnetic recording media comprising metallic Pt and an oxide, with the balance being metallic Co and inevitable impurities, wherein

5 the metallic Co is contained in a range of 70 at% or more and 90 at% or less and the metallic Pt is contained in a range of 10 at% or more and 30 at% or less relative to a total of metallic components in the sputtering target for magnetic recording media,

the oxide is contained in a range of 26 vol% or more and 40
10 vol% or less relative to a total volume of the sputtering target for magnetic recording media, and

the oxide is composed of B_2O_3 and one or more high-melting-point oxides having a melting point of 1470°C or higher and 2800°C or lower.

15 2. A sputtering target for magnetic recording media comprising metallic Pt, metallic Cr, and an oxide, with the balance being metallic Co and inevitable impurities, wherein

the metallic Co is contained in a range of 70 at% or more and less than 90 at%, the metallic Pt is contained in a range of 10
20 at% or more and less than 30 at%, and the metallic Cr is contained in a range of more than 0 at% and 10 at% or less, relative to a total of metallic components in the sputtering target for magnetic recording media,

the oxide is contained in a range of 26 vol% or more and 40
25 vol% or less relative to a total volume of the sputtering target

for magnetic recording media, and

the oxide is composed of B_2O_3 and one or more high-melting-point oxides having a melting point of $1470^{\circ}C$ or higher and $2800^{\circ}C$ or lower.

5 3. The sputtering target for magnetic recording media according to claim 1 or 2, wherein a volume ratio of B_2O_3 relative to a total of the one or more high-melting-point oxides is 0.5 or more and 4 or less.

10 4. The sputtering target for magnetic recording media according to any one of claims 1 to 3, wherein the one or more high-melting-point oxides are selected from the group consisting of TiO_2 , SiO_2 , Ta_2O_5 , Cr_2O_3 , Al_2O_3 , and ZrO_2 .

15 5. The sputtering target for magnetic recording media according to claim 4, wherein the one or more high-melting-point oxides are TiO_2 .