

Description

BACKGROUND AND SUMMARY OF THE INVENTION

The present invention relates to liners which are used to form an impermeable barrier as shown, for example, in EP-A-0 362 193. In particular, the invention relates to an improved liner which is capable of being used on steep slopes. Liners for which the present invention has particular application are those which incorporate a layer of swellable clay, such as bentonite.

The present invention is in the nature of an improvement to liners like that shown in US-A-4,501,788, in which a layer of granular bentonite is enclosed between two flexible sheets. In such liners, a water-soluble adhesive is used to attach the bentonite particles to a geotextile. The geotextile used will depend upon the application, but are preferably comprised of at least one woven polypropylene geotextile. Other fabrics include non-woven fleece-like geotextiles and lightweight polyester net-like scrims.

Bentonite clay upon hydration tends to expand and become a highly impervious material. However, like most other clays, exposure of bentonite to water causes it to become very slick, greatly reducing the ability of the clay to withstand shear stresses. As a result, use of clay liners on slopes must be restricted to those having relatively shallow angles.

Some manufacturers of clay liners have attempted to create shear resistance in clay liners by needlepunching connections between fabric layers through the bentonite layer. However, these systems have two distinct disadvantages. First, the strength of the connection formed by needlepunching fibers is low. In some cases, the expansion force of the hydrated bentonite is sufficient to break the needlepunched connections. Second, needlepunched fibers form a path for capillary migration of water through the bentonite layer.

Manufacturers of needlepunched liners have attempted to rely upon needlepunched connections to retain the bentonite between the fabric layers in an effort to avoid the use of adhesive bonding of the bentonite to a fabric layer. Such heavy reliance upon the needlepunched connections for both bentonite retention and shear resistance has resulted in problems with both delivery and performance of such products. Needlepunching is generally inadequate as a sole means for retaining bentonite between two layers of fabric. The bentonite tends to migrate laterally unless it is held in place by means such as adhesive bonding. The integrity of the needlepunched connections is further compromised by the flexible nature of bentonite liners. It is

an important feature of such liners that they be capable of being rolled up into a carpet-like form, so that installation can take place in an expedited manner. The stresses introduced to connections between fabric layers as a result of the rolling up of the liner during the manufacturing process, results in significant stresses upon the interfabric connections. After a needlepunched liner has been rolled and unrolled, the needlepunched connections may not have sufficient strength to resist the expansion of the bentonite layer, or to withstand shear stress on a slope.

Bentonite-based liners have found significant acceptance for use in preventing groundwater contamination. Bentonite liners have been used successfully in hazardous waste and municipal solid waste landfills. An important consideration in the construction of such landfills is the slope angle of the excavation. For a given area, significantly greater landfill volume can be achieved by the use of steeper slopes. The use of steep slopes allows more efficient use of a particular landfill site.

Similarly, clay liners are often used in tank farm applications in which berms or excavations are formed with sloping sides. Steeper slopes in tank farm applications allow more efficient use of real estate.

Accordingly, it is an aim of the present invention to provide an improved bentonite liner which may be used to form an impervious barrier along a relatively steep slope.

Another aim of the present invention is to provide a bentonite liner which does not allow for the migration of liquid through the liner.

It is a further aim of the present invention to provide a liner which has significantly improved resistance to shear stresses.

With these aims in view, the invention starts from what is shown in EP-A-0 362 193, on which the preamble of claim 1 is based, and is directed to a liner having the characterising features of claim 1. Preferred features of the liner are disclosed in the subsidiary claims.

The lateral spacing of the rows of stitching will depend upon the degree of shear resistance required by a particular application. However, it is preferable that the rows be spaced approximately two inches apart. The rows should extend along the length of the liner.

The advantages of the invention will become more apparent upon a reading of the following specification, read in conjunction with the accompanying drawings, in which :

Figure 1 is a perspective view of a slope to which the liner of the present invention has been applied;

Figure 2 is an enlarged perspective view of a portion of the liner of the present invention; and

Figures 3 and 4 are sectional views showing the advantage of using a liner of the present invention.

DETAILED DESCRIPTION OF THE DRAWINGS

Figure 1 is a perspective view which shows a prepared subgrade 10 with a sloping central portion 30 and flat upper and lower portions 32 and 34. The slope shown in Figure 1 is typical of those which are used in both landfill and tank farm applications. Liners 12 are applied to the sloping prepared subgrade 10, with overlapping seams 16. Rows 14 of stitching are shown schematically as dotted lines in Figure 1. The spacing of the rows 14 is discussed in more detail later. The upper ends of the liners 12 are placed in a trench 15, and cover soil 18 is applied on top of the overlapping liners 12. Figure 2 is an enlarged view showing in greater detail the construction of the liner 12 of the present invention. The liner is comprised of an upper geotextile 22, and a lower geotextile 24, preferably made of a woven, non-biodegradable propylene. The stitches 17 are at a frequency of approximately 3 stitches per inch, and the rows 14 are spaced approximately 2 inches apart. As can be seen from Figure 1, the rows 14 extend along the length of the liners 12. The parallel rows 14 of stitching extend along the length of the liner and transfer shearing forces from one geotextile to the other through the bentonite layer. The thread 19 which is used to form the stitches 17 is preferably a multifilament high density polyethylene thread. Multifilament threads are generally stronger than monofilament threads. However, multifilament threads should be coated to prevent wicking or capillary action of water and other liquids through the liners 12. The treatment of the thread used to make the stitches 17 may be the application of a polymer resin, such as nylon or polypropylene resin. While high density polyethylene thread will be resistant to most leachates, other thread materials may be required for particular waste containment applications. It is preferred that a two-thread chainstitch be used to ensure an effective interconnection between the geotextiles, although other kinds of stitches, such as a single-thread chainstitch, may be used.

While the geotextiles 22 and 24 shown on opposite sides of the bentonite layer 20 in Figure 2 are preferably woven polypropylene, liners of the present invention may be constructed of other geotextiles, such as nonwoven fabrics. The clay layer 20 is preferably bonded to at least one, and perhaps both, of the geotextiles by a water based, water soluble adhesive. It is important that the geotextiles be flexible so that the liner 12 may be rolled up. In the rolled up form, the rows 14 of

stitches will assume a spiral configuration around the axis of the roll. When unrolled, the rows 14 will extend up and down the sloped subgrade 10. With the rows 14 of stitching extending up and down the slope, shear stresses from the cover soil 18 are better transferred between the geotextiles 22 and 24 through the bentonite layer 20.

Figures 3 and 4 show more clearly the advantages of the present invention. The dotted line 40 in Figure 3 shows the outline of a liner applied at a steeper slope than the one along line 42. The hatched area 44 shows the increases available volume resulting from the use of a liner of the present invention. Because of the slick nature of bentonite after it is hydrated, slopes employing bentonite liners have generally been restricted to those with a 4:1 slope. A liner applied along the line 42 in Figure 3 is shown with a slope of approximately 4:1.

Figure 4 shows the advantage of using a steeper slope in tank farm applications. By using a slope of about 1.2:1, as shown in Figure 4, the radius of the excavation can be reduced by the length L. As a result, storage tanks can be spaced closer together, resulting in more efficient use of land area. The increased volume available for fill in landfill applications and the more efficient use of land area in tank farm applications can be achieved with a liner of the present invention without sacrificing the desirable aspects afforded by the use of bentonite liners.

It will be recognized by those skilled in the art that considerations such as the depth and angle of repose of the soil used as cover, and other factors, will determine the extent to which an excavation or berm can be sloped. By using the stitched liner of the present invention, geotechnical engineers can make greater use of land designated for landfills and tank farms. With the liner of the present invention, greater volumes of cover may be used as compared with liners of the prior art. The use of more cover on a slope means that it can better resist the process of erosion.

While a specific embodiment of the invention has been shown and described, it will be apparent to those skilled in the art that numerous alternatives, modifications, and variations of the embodiment shown can be made without departing from the scope of the appended claims.

Claims

1. A liner for use in containing liquid, the liner being of elongate shape and comprising at least two non-biodegradable sheets (22, 24) which are held together by stitching (17) and which have a layer of water-swellable clay (20) between them, the stitching (17) comprising



Figures 3 and 4 are sectional views showing the advantage of using a liner of the present invention.

DETAILED DESCRIPTION OF THE DRAWINGS

Figure 1 is a perspective view which shows a prepared subgrade 10 with a sloping central portion 30 and flat upper and lower portions 32 and 34. The slope shown in Figure 1 is typical of those which are used in both landfill and tank farm applications. Liners 12 are applied to the sloping prepared subgrade 10, with overlapping seams 16. Rows 14 of stitching are shown schematically as dotted lines in Figure 1. The spacing of the rows 14 is discussed in more detail later. The upper ends of the liners 12 are placed in a trench 15, and cover soil 18 is applied on top of the overlapping liners 12. Figure 2 is an enlarged view showing in greater detail the construction of the liner 12 of the present invention. The liner is comprised of an upper geotextile 22, and a lower geotextile 24, preferably made of a woven, non-biodegradable propylene. The stitches 17 are at a frequency of approximately 3 stitches per inch, and the rows 14 are spaced approximately 2 inches apart. As can be seen from Figure 1, the rows 14 extend along the length of the liners 12. The parallel rows 14 of stitching extend along the length of the liner and transfer shearing forces from one geotextile to the other through the bentonite layer. The thread 19 which is used to form the stitches 17 is preferably a multifilament high density polyethylene thread. Multifilament threads are generally stronger than monofilament threads. However, multifilament threads should be coated to prevent wicking or capillary action of water and other liquids through the liners 12. The treatment of the thread used to make the stitches 17 may be the application of a polymer resin, such as nylon or polypropylene resin. While high density polyethylene thread will be resistant to most leachates, other thread materials may be required for particular waste containment applications. It is preferred that a two-thread chainstitch be used to ensure an effective interconnection between the geotextiles, although other kinds of stitches, such as a single-thread chainstitch, may be used.

While the geotextiles 22 and 24 shown on opposite sides of the bentonite layer 20 in Figure 2 are preferably woven polypropylene, liners of the present invention may be constructed of other geotextiles, such as nonwoven fabrics. The clay layer 20 is preferably bonded to at least one, and perhaps both, of the geotextiles by a water based, water soluble adhesive. It is important that the geotextiles be flexible so that the liner 12 may be rolled up. In the rolled up form, the rows 14 of

stitches will assume a spiral configuration around the axis of the roll. When unrolled, the rows 14 will extend up and down the sloped subgrade 10. With the rows 14 of stitching extending up and down the slope, shear stresses from the cover soil 18 are better transferred between the geotextiles 22 and 24 through the bentonite layer 20.

Figures 3 and 4 show more clearly the advantages of the present invention. The dotted line 40 in Figure 3 shows the outline of a liner applied at a steeper slope than the one along line 42. The hatched area 44 shows the increases available volume resulting from the use of a liner of the present invention. Because of the slick nature of bentonite after it is hydrated, slopes employing bentonite liners have generally been restricted to those with a 4:1 slope. A liner applied along the line 42 in Figure 3 is shown with a slope of approximately 4:1.

Figure 4 shows the advantage of using a steeper slope in tank farm applications. By using a slope of about 1.2:1, as shown in Figure 4, the radius of the excavation can be reduced by the length L. As a result, storage tanks can be spaced closer together, resulting in more efficient use of land area. The increased volume available for fill in landfill applications and the more efficient use of land area in tank farm applications can be achieved with a liner of the present invention without sacrificing the desirable aspects afforded by the use of bentonite liners.

It will be recognized by those skilled in the art that considerations such as the depth and angle of repose of the soil used as cover, and other factors, will determine the extent to which an excavation or berm can be sloped. By using the stitched liner of the present invention, geotechnical engineers can make greater use of land designated for landfills and tank farms. With the liner of the present invention, greater volumes of cover may be used as compared with liners of the prior art. The use of more cover on a slope means that it can better resist the process of erosion.

While a specific embodiment of the invention has been shown and described, it will be apparent to those skilled in the art that numerous alternatives, modifications, and variations of the embodiment shown can be made without departing from the scope of the appended claims.

Claims

1. A liner for use in containing liquid, the liner being of elongate shape and comprising at least two non-biodegradable sheets (22, 24) which are held together by stitching (17) and which have a layer of water-swellaable clay (20) between them, the stitching (17) comprising



polymeric leachate-resistant stitching means (19) extending through the clay layer (20) so as to hold the sheets (22, 24) together after the water-swella- ble clay has become hydrated, characterised in that :

- (a) the stitching means (19) comprise spaced-apart rows (14) of stitching extending lengthwise of the liner; and
- (b) the clay layer (20) is, optionally, attached to at least one of the sheets (22 or 24) by means of a water-based and water-soluble adhesive.

2. A liner in accordance with claim 1, wherein the two sheets (22, 24) are made of flexible porous fabric.
3. A liner in accordance with claim 1 or claim 2, wherein at least one of the two sheets (22, 24) is a woven polypropylene geotextile.
4. A liner in accordance with any one of claims 1-3, wherein the two sheets (22, 24) are both woven polypropylene geotextiles.
5. A liner in accordance with any preceding claim, wherein the stitching means (19) comprise generally parallel rows (14) of stitches.
6. A liner in accordance with claim 5, wherein the liner is rolled up about an axis and the stitching means (19) extend spirally around that axis.
7. A liner in accordance with any preceding claim, wherein the layer of clay (20) is carried by at least one of the sheets (22, 24) independently of the stitching means (19).
8. A liner in accordance with any preceding claim, wherein the layer (20) of water-swella- ble clay is a layer of bentonite granules.

Patentansprüche

1. Deckschicht zum Zurückhalten von Flüssigkeiten, wobei die Deckschicht eine langgestreckte Form aufweist und aus mindestens Zwei biologisch nicht abbaubaren Bahnen (22, 24) besteht, welche durch Nähte (17) zusammengehalten sind, und zwischen denen eine Schicht von mit Wasser quellfähigem Ton (20) angeordnet ist, wobei die Nähte (17) aus polymeren, gegen Leckflüssigkeiten widerstandsfähigen Nähmitteln (19) bestehen, welche sich durch die Tonschicht (20) hindurch erstrecken, um so die Bahnen (22, 24) zusammenzuhalten, nachdem der mit Wasser quellfähige Ton hy-

driert wurde, dadurch gekennzeichnet, daß

- (a) die Nähmittel (19) aus im Abstand zueinander liegenden Reihen (14) von Nähten bestehen, die sich in Längsrichtung der Deckschicht erstrecken, und
- (b) daß die Tonschicht (20) gegebenenfalls an mindestens einer der Bahnen (22 oder 24) mittels eines wasserlöslichen Klebstoffs auf Wasserbasis befestigt ist.

2. Deckschicht nach Anspruch 1, dadurch gekennzeichnet, daß die beiden Bahnen (22, 24) aus einem flexiblen porösen Gewebe hergestellt sind.
3. Deckschicht nach Anspruch 1 oder 2, dadurch gekennzeichnet, daß mindestens eine der beiden Bahnen (22, 24) ein gewebtes Polypropylenegeotextil ist.
4. Deckschicht nach einem der vorstehenden Ansprüche 1 bis 3, dadurch gekennzeichnet, daß die beiden Bahnen (22, 24) beide aus gewebten Polypropylenegeotextilien bestehen.
5. Deckschicht nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, daß die Nähmittel (19) aus allgemein parallelen Reihen (14) von Nähten bestehen.
6. Deckschicht nach Anspruch 5, dadurch gekennzeichnet, daß die Deckschicht um eine Achse aufgerollt ist und sich die Nähmittel (19) spiralförmig um die Achse erstrecken.
7. Deckschicht nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, daß die Tonschicht (20) unabhängig von den Nähmitteln (19) von mindestens einer der Bahnen (22, 24) getragen ist.
8. Deckschicht nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, daß die Tonschicht (20) aus mit Wasser quellfähigem Ton eine Schicht aus Bentonitkörnern ist.

Revendications

1. Revêtement destiné à être utilisé pour retenir un liquide, le revêtement étant d'une forme allongée et comprenant au moins deux feuilles non biodégradables (22, 24) qui sont tenues l'une à l'autre par une couture (17) et entre lesquelles se trouve une couche d'argile (20) gonflant à l'eau, la couture (17) comprenant un moyen de couture (19) en polymère résistant aux résidus de lixiviation et passant à travers la couche d'argile (20) de manière à tenir les



feuilles (22, 24) assemblées après que l'argile gonflant à l'eau s'est hydratée, caractérisé en ce que

- (a) le moyen de couture (19) comprend des rangées (14) de coutures distantes les unes des autres et disposées dans la direction de la longueur du revêtement ; et 5
 - (b) la couche d'argile (20) est facultativement fixée à au moins l'une des feuilles (22 ou 24) au moyen d'un adhésif à base d'eau et soluble dans l'eau. 10
- 2. Revêtement selon la revendication 1, dans lequel les deux feuilles (22, 24) sont en une étoffe poreuse souple. 15
 - 3. Revêtement selon la revendication 1 ou la revendication 2, dans lequel au moins l'une des deux feuilles (22, 24) est un géotextile tissé en polypropylène. 20
 - 4. Revêtement selon l'une quelconque des revendications 1 à 3, dans lequel toutes les deux feuilles (22, 24) sont des géotextiles tissés en polypropylène. 25
 - 5. Revêtement selon l'une quelconque des revendications précédentes, dans lequel le moyen de couture (19) comprend des rangées de points de couture (14) sensiblement parallèles. 30
 - 6. Revêtement selon la revendication 5, dans lequel le revêtement est enroulé autour d'un axe et le moyen de couture (19) est disposé en spirale autour de l'axe. 35
 - 7. Revêtement selon l'une quelconque des revendications précédentes, dans lequel la couche d'argile (20) est portée par au moins l'une des feuilles (22, 24) indépendamment du moyen de couture (19). 40
 - 8. Revêtement selon l'une quelconque des revendications précédentes, dans lequel la couche (20) d'argile gonflant à l'eau est une couche de granulés de bentonite. 45

50

55

5