

DESCRIPTION

NAME OF INVENTION: CERAMIC, PROBE GUIDING MEMBER, PROBE CARD,
AND SOCKET FOR PACKAGE INSPECTION

TECHNICAL FIELD

[0001]

The present invention relates to a ceramic, a probe guiding member, a probe card, and a socket for package inspection.

BACKGROUND ART

[0002]

A probe card is used in, for example, an inspection process on IC chips. Figure 1 illustrates a cross-sectional view illustrating a configuration of a probe card as an example, and Figure 2 is a top view illustrating the configuration of the probe guide as an example. As illustrated in Figure 1 and Figure 2, a probe card 10 is an inspection jig that includes needle-shaped probes 11 and a probe guide (probe guiding member) 12 including through holes 12a for allowing the probes 11 to be inserted therethrough. By bringing the probes 11 into contact with IC chips 14 that are formed on a silicon wafer 13, inspection of the IC chips 14 is conducted.

[0003]

Patent Document 1 exemplifies a ceramic that contains a mixture of 25 to 60 mass% of silicon nitride and 40 to 75 mass% of boron nitride, as its main raw material. In addition, Patent Document 2 discloses an invention relating to a free-machining ceramic that contains 30 to 50 mass% of boron nitride and 50 to 70 mass% of zirconia, as its main raw material.

LIST OF PRIOR ART DOCUMENTS

PATENT DOCUMENT

[0004]

Patent Document 1: JP2005-226031A

Patent Document 2: WO 2002/082592

SUMMARY OF INVENTION

TECHNICAL PROBLEM

[0005]

As devices move toward finer design rules and higher performance in recent years, a probe guide used for an inspection apparatus for the devices are required to have a thermal expansivity as high as that of the silicon wafer 13, to have a mechanical strength (flexural strength) that allows the probe guide to withstand a probe load, and to allow high-precision machining of a large number of holes through which fine probes are to be inserted.

[0006]

For example, an inspection efficiency of an inspection process on IC chips depends on how many probes can be brought into contact with IC chips at the same time. Hence, recent years have been seeing a practical application of a probe card on which tens of thousands of minute probes are set upright with high density by the micro-electromechanical systems (MEMS). As illustrated in Figure 2 given above, the probe guide 12 needs to be provided with the through holes 12a at positions corresponding to the probes 11 of the probe card 10. Setting positions, a shape, and the like of the probes 11 of the probe card 10 vary according to specifications of the inspection apparatus, and setting positions, a shape, and the like of the through holes 12a vary accordingly. For example, in a case where the probes 11 have a pin shape, a circular hole is adapted for the through holes 12a, and the through holes 12a need to be formed in various shapes according to the shape of the probes 11.

[0007]

An inner diameter of the holes and a pitch of the holes depend on a kind or an arrangement of the probes 11; for example, there is a case where through holes having a diameter of 50 μm are arranged with a 60 μm pitch (a wall thickness between the through holes is about 10 μm). It is necessary to provide tens of thousands of such

small through holes. This requires a material that facilitates precise machining. In particular, particles, which could be produced when the through holes 12a of the probe guide 12 come into contact with the probes 11, may give rise to damage to the device, a poor inspection, and an increase in number of maintenance times of the probe card 10. Therefore, the through holes 12a of the probe guide 12 are also required to have inner surfaces with a low roughness, that is, smooth machined surfaces.

[0008]

Here, with finer wiring of IC chips, there have been a tendency of an increase in the number of probes and a decrease in the distance (pitch) between pads to be in contact with the probes, and a need for further enhancement in positional precision of the probes. To support this narrow pitch, miniaturization of probes is in progress, and use of probes having various shapes has been started. At the same time, for a material used for the probe guide, there arise needs for decreasing its thickness, forming fine holes that are accommodated to changes in shapes of probes, and the like, for a purpose of improving the positional precision of the probes.

[0009]

However, as a thickness of the material for the probe guide is reduced, a strength of the member is decreased, so that the probe guide cannot withstand a probe load to deform, and consequently, the positional precision of the probes decreases. Moreover, the material for the probe guide can be broken in some cases. To deal with these demands, the probe guide is required to have extremely excellent mechanical properties.

[0010]

The above description is made mainly about the probe guide, and applications of which similar qualities are required include a socket for inspection such as a socket for package inspection.

[0011]

Here, the ceramics described in Patent Documents 1 and 2 are ceramics having coefficients of thermal expansion as high as that of silicon and having a certain level of mechanical strengths and free-machining properties, but no consideration is given to

smoothness of their machined surfaces.

[0012]

The present invention has an objective to provide a ceramic that has a coefficient of thermal expansion as high as that of silicon and an excellent mechanical strength, allows fine machining with high precision, includes a smooth machined surface, and can prevent particles from being produced in its use, and to provide a probe guiding member, a probe card, and a socket for inspection that are made of the ceramic.

SOLUTION TO PROBLEM

[0013]

To achieve the objective, the present inventors conducted intensive studies on a basis of obtaining a ceramic that has a thermal expansivity as high as that of a silicon wafer and a high strength by combining Si_3N_4 , which is a high strength ceramic, and ZrO_2 , which is a high expansive ceramic, and as a result, obtained the following findings.

[0014]

(a) A ceramic material made by combining Si_3N_4 and ZrO_2 is an extremely hard material and thus difficult to form fine holes by machining. Hence, it is preferable to form the fine holes by laser beam machining to obtain the probe guide plate.

[0015]

(b) However, it is difficult for simply performing the laser beam machining to smooth the machined surface (e.g., inner surfaces of the through holes of the probe guide). Hence, a predetermined amount of oxides are contained. Examples of the oxides include MgO , Y_2O_3 , CeO_2 , CaO , HfO_2 , TiO_2 , Al_2O_3 , SiO_2 , MoO_3 , CrO , CoO , ZnO , Ga_2O_3 , Ta_2O_5 , NiO , and V_2O_5 .

[0016]

The present invention is made based on the above findings, and the gist of the present invention is as follows.

[0017]

(1) A ceramic containing, in mass percent:

Si₃N₄: 20.0 to 60.0%;

ZrO₂: 25.0 to 70.0%; and

one or more oxides selected from MgO, Y₂O₃, CeO₂, CaO, HfO₂, TiO₂, Al₂O₃, SiO₂, MoO₃, CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅: 5.0 to 15.0%.

[0018]

(2) The ceramic according to the above (1) containing, in mass percent:

one or more oxides selected from MgO, Y₂O₃, CeO₂, CaO, and HfO₂; and

one or more oxides selected from TiO₂, Al₂O₃, SiO₂, MoO₃, CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅.

[0019]

(3) The ceramic according to the above (1) or (2), wherein a crystal phase of ZrO₂ is one of a crystal phase being a tetragonal crystal, a crystal phase being a tetragonal crystal and a monoclinic crystal, a crystal phase being a cubic crystal, a crystal phase being a cubic crystal and a tetragonal crystal, and a crystal phase being a cubic crystal and a monoclinic crystal.

[0020]

(4) The ceramic according to any one of the above (1) to (3), wherein a crystal phase of ZrO₂ is a cubic crystal.

[0021]

(5) The ceramic according to any one of the above (1) to (4), wherein the ceramic has a coefficient of thermal expansion at -50 to 500°C ranging from 3.0×10^{-6} to 6.0×10^{-6} /°C and has a three-point flexural strength of 700 MPa or more.

[0022]

(6) A probe guiding member that guides probes of a probe card, the probe guiding member including:

a plate-shaped main body that is made of the ceramic according to any one of the above (1) to (5); and

the main body includes a plurality of through holes and/or slits through which the probes are to be inserted.

[0023]

(7) The probe guiding member according to the above (6), wherein a surface roughness of inner surfaces of the plurality of through holes and/or slits is 0.25 μm or less in terms of Ra.

[0024]

(8) A probe card including:
a plurality of probes; and
the probe guiding member according to the above (6) or (7).

[0025]

(9) A socket for package inspection, wherein the socket for package inspection is made of the ceramic according to any one of the above (1) to (5).

ADVANTAGEOUS EFFECTS OF INVENTION

[0026]

The present invention makes it possible to obtain a ceramic that has a coefficient of thermal expansion as high as that of silicon and an excellent mechanical strength, allows fine machining with high precision, includes a smooth machined surface, and can prevent particles from being produced in its use, which is thus useful particularly to a probe guiding member, a probe card, and a socket for inspection.

BRIEF DESCRIPTION OF DRAWINGS

[0027]

[Figure 1] Figure 1 is a cross-sectional view illustrating a configuration of a probe card as an example.

[Figure 2] Figure 2 is a top view illustrating the configuration of the probe guide as an example.

[Figure 3] Figure 3 is a picture of micromachined holes in Example 6 captured from above.

[Figure 4] Figure 4 is a picture of micromachined holes in Comparative example 3 captured from above.

[Figure 5] Figure 5 is a picture of micromachined holes in Comparative example 4 captured from above.

[Figure 6] Figure 6 is a picture of a micromachined hole in Example 6 captured from inside.

[Figure 7] Figure 7 is a picture of a micromachined hole in Comparative example 5 captured from inside.

[Figure 8] Figure 8 is a schematic diagram of laser beam machining.

DESCRIPTION OF EMBODIMENTS

[0028]

1. Ceramic

A ceramic according to the present invention contains, in mass percent, Si_3N_4 : 20.0 to 60.0%, ZrO_2 : 25.0 to 70.0%, and one or more oxides selected from MgO , Y_2O_3 , CeO_2 , CaO , HfO_2 , TiO_2 , Al_2O_3 , SiO_2 , MoO_3 , CrO , CoO , ZnO , Ga_2O_3 , Ta_2O_5 , NiO , and V_2O_5 : 5.0 to 15.0%. In the following description, the symbol "%" for contents means "percent by mass."

[0029]

Si_3N_4 : 20.0 to 60.0%;

Si_3N_4 is useful for giving a high strength to the ceramic, and in order to obtain a flexural strength as high as 700 MPa or more, 20.0% or more of Si_3N_4 needs to be contained. However, if a content of Si_3N_4 is more than 60.0%, it is difficult to obtain a thermal expansivity as high as that of a silicon wafer, that is, it is difficult to bring the coefficient of thermal expansion at -50 to 500°C to $3.0 \times 10^{-6} / ^\circ\text{C}$ or more. Accordingly, the content of Si_3N_4 is to range from 20.0 to 60.0%. A lower limit of the content of Si_3N_4 is preferably 25.0%, and more preferably 30.0%. An upper limit of the content of Si_3N_4 is preferably 55.0%, and more preferably 50.0%.

[0030]

ZrO_2 : 25.0 to 70.0%

ZrO_2 is useful for giving a high thermal expansivity to the ceramic, and 25.0% or more of ZrO_2 needs to be contained. However, if a content of ZrO_2 is more than

70.0%, the thermal expansivity becomes excessively high, which makes it difficult to obtain a thermal expansivity as high as that of a silicon wafer, that is, it is difficult to bring the coefficient of thermal expansion at -50 to 500°C to $6.0 \times 10^{-6} / ^\circ\text{C}$ or less. Accordingly, the content of ZrO_2 is to range from 25.0 to 70.0%. A lower limit of the content of ZrO_2 is preferably 30.0%, and more preferably 35.0%. An upper limit of the content of ZrO_2 is preferably 65.0%, and more preferably 60.0%.

[0031]

Some ZrO_2 have a crystalline structure being a monoclinic crystal, a tetragonal crystal, or a cubic crystal. In general, in order to give a high strength to a ZrO_2 ceramic, a tetragonal crystal ZrO_2 with several percent of oxides dissolved therein is preferably used. However, if this tetragonal crystal ZrO_2 is exposed for a long time, the tetragonal crystal undergoes phase transition to a monoclinic crystal even when the exposure occurs at a low temperature (less than 200°C), and this phase transition changes dimensions of the ceramic. For example, this phase transition proceeds at 40°C or more, and proceeds more significantly at 150°C or more. Therefore, if such a ceramic is used for a probe guiding member that guides probes of a probe card, the probe guiding member fulfills a function of a probe guiding member at room temperature, whereas as a temperature range for use increases, positions of a plurality of through holes and/or slits through which probes are to be inserted may deviate to inhibit the insertion of the probes. For that reason, it is more preferable to use a cubic crystal ZrO_2 , which does not undergo the phase transition, that is, does not change the dimensions in a use temperature. Note that the cubic crystal ZrO_2 contains about 3 mol% of elements such that Y, and the content of ZrO_2 also includes an amount of these elements. Note that the monoclinic crystal ZrO_2 is lower in strength than the tetragonal crystal ZrO_2 or the cubic crystal ZrO_2 , and therefore, even in a case where the crystalline structure includes the monoclinic crystal ZrO_2 , a proportion of the monoclinic crystal ZrO_2 is preferably 50% or less, more preferably 10% or less, and may be 0%.

[0032]

One or more oxides selected from MgO , Y_2O_3 , CeO_2 , CaO , HfO_2 , TiO_2 , Al_2O_3 ,

SiO₂, MoO₃, CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅: 5.0 to 15.0%

In a case where the ceramic according to the present invention is used to various applications, the ceramic needs to be subjected to fine machining. For example, in order to use the ceramic as a probe guiding member, a plurality of through holes and/or slits need to be formed. However, since the ceramic according to the present invention is a high hardness material containing Si₃N₄ and ZrO₂ as main components, it is difficult to perform this fine machining by mechanical work. Its machined surfaces (e.g., inner surfaces of the through holes of the probe guide) are therefore rough, and when a member subjected to such work is used, particles are produced, which incur damage to various devices or poor inspection. For that reason, it is preferable to perform the fine machining on this ceramic by laser beam machining, but it is difficult even for the laser beam machining to smooth the machined surfaces (e.g., the inner surfaces of the through holes of the probe guide), and it is difficult to completely prevent particles from being produced in the use of the ceramic.

[0033]

Hence, the ceramic according to the present invention is made to contain a proper amount of oxides. That is, one or more oxides selected from MgO, Y₂O₃, CeO₂, CaO, HfO₂, TiO₂, Al₂O₃, SiO₂, MoO₃, CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅ need to be contained at 5.0% or more. In contrast, if a content of these oxides is excessive, these oxides incur a decrease in flexural strength, and accordingly, the content of one or more of these oxides is to be 15.0% or less. Therefore, the content of one or more oxides selected from MgO, Y₂O₃, CeO₂, CaO, HfO₂, TiO₂, Al₂O₃, SiO₂, MoO₃, CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅ is to range from 5.0 to 15.0%. A lower limit of the content is preferably 7.0%, and more preferably 9.0%. An upper limit of the content is preferably 13.0%, and more preferably 11.0%.

[0034]

In particular, MgO, Y₂O₃, CeO₂, CaO, and HfO₂ each act as a sintering agent as well as the above effect and are additionally effective for stabilizing the crystalline structure of ZrO₂ in a form of the cubic crystal. TiO₂, Al₂O₃, SiO₂, MoO₃, CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅ each act as a sintering agent as well as the above

effect. Therefore, it is preferable for the ceramic to contain one or more oxides selected from MgO, Y₂O₃, CeO₂, CaO, and HfO₂, and one or more oxides selected from TiO₂, Al₂O₃, SiO₂, MoO₃, CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅.

Contents of the respective components (mass %) can be measured by the ICP emission spectral analysis. Note that no specific limitation is imposed on the balance other than the components described above, but it is preferable to reduce the balance as much as possible, and a content of the balance is preferably 10.0% or less, more preferably 5.0% or less, and may be 0%. Examples of the balance include BN, AlN, SiC, and the like.

[0035]

Coefficient of Thermal Expansion at -50 to 500°C: 3.0×10^{-6} to 6.0×10^{-6} /°C

In a case where the ceramic according to the present invention is used for a probe guide, the ceramic is required to have a coefficient of thermal expansion as high as that of a silicon wafer on which IC chips are formed. This is because, when a temperature in the inspection changes, positions of the IC chips move with thermal expansion of the silicon wafer. At the time, in a case where the probe guide has a coefficient of thermal expansion as high as that of the silicon wafer, the probe guide moves in synchronization with expansion and contraction of the silicon wafer, which enables a high precision inspection to be kept. This also applies to a case where the ceramic according to the present invention is used for a socket for inspection. Accordingly, a reference coefficient of thermal expansion at -50 to 500°C is 3.0×10^{-6} to 6.0×10^{-6} /°C.

[0036]

Flexural Strength: 600 MPa or more

In a case where the ceramic according to the present invention is used for a probe guide, the ceramic is required to have mechanical properties sufficient to withstand contact and a load of probes and the like in the inspection. In particular, the ceramic is required to have a flexural strength that is higher than ever before, in order to meet a demand for reductions of size and thickness of probe guides. This also applies to a case where the ceramic according to the present invention is used for a socket for

inspection. Accordingly, a reference flexural strength is 600 MPa or more, and more preferably 700 MPa or more.

[0037]

Micromachinability

Regarding micromachinability, a machining precision of pulse laser machining performed on a ceramic material having a thickness of 0.3 mm to form nine 50- μ m-square through holes is evaluated by observing shapes of the holes on a side to which laser beams come out by a vision measuring system (e.g., Quick Vision from Mitutoyo Corporation) (a case where the machining precision falls within ± 2 μ m is rated as good).

[0038]

Roughness of Machined Surface

Regarding a roughness of the machined surface, nine 50- μ m square through holes are formed on a ceramic material having a thickness of 0.3 mm by the pulse laser machining, given five visual fields of inner surfaces of the machined holes are measured over a length of 100 μ m or more under a laser confocal microscope (VK-X150 from KEYENCE CORPORATION), skew correction is performed to calculate Ra, and an average value of Ra is evaluated. Ra being 0.25 μ m or less is rated as good.

[0039]

Occurrence of Crack after Heat Treatment at 150°C

Regarding occurrence of a crack after heat treatment at 150°C, a ceramic material having a thickness 0.3 mm is heated from room temperature to 150°C at 5°C/min, retained at 150°C for 100 hours, then allowed to be naturally cooled at room temperature, and after being left still for 5 hours since a temperature of the ceramic reaches the room temperature, five or more visual fields of the ceramic are captured under a digital microscope (VHX-6000 from KEYENCE CORPORATION) at 200x observation magnification, and from captured images, whether a crack occurs is evaluated. A case where no crack occurs is rated as ○, and a case where a crack occurs is rated as ×.

[0040]

2. Method for Producing Ceramic

An example of a method for producing the ceramic according to the present invention will be described below.

[0041]

Si₃N₄ powder, ZrO₂ powder, and one or more oxide powders selected from MgO, Y₂O₃, CeO₂, CaO, HfO₂, TiO₂, Al₂O₃, SiO₂, H₂MoO₄ (to be MoO₃ after sintering), CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅ are mixed by a known method such as one using a ball mill. That is, the powders, solvent, resin-made balls each including a ceramic-made or iron-made core therein are mixed in a container to be formed into slurry. At that time, as the solvent, water or alcohol can be used. In addition, an additive such as a dispersant and a binder may be used as necessary.

[0042]

The obtained slurry is formed into grains by a known method such as spray drying and a method using a decompression evaporator. That is, the slurry is spray-dried by a spray dryer to be formed into granules or is dried by the decompression evaporator to be formed into powder.

[0043]

The obtained powder is sintered under a high temperature and a high pressure by, for example, a known method such as hot pressing and hot isostatic pressing (HIP) to be formed into a sintered ceramic body. In the case of the hot pressing, the powder may be calcined in a nitrogen atmosphere. In addition, a temperature of the calcination is to range from 1300 to 1800°C. If the temperature is excessively low, the sintering becomes insufficient, and if the temperature is excessively high, a problem such as liquating oxide components arises.

[0044]

An appropriate pressing force ranges from 10 to 50 MPa. In addition, a duration of maintaining the pressing force is normally about 1 to 4 hours, which however depends on the temperature or the dimensions. Also in a case of the HIP, calcination conditions including the temperature and the pressing force are to be set as appropriate. Alternatively, a known calcination method such as a pressureless

calcination method and an atmosphere pressing calcination may be adopted.

EXAMPLE

[0045]

In order to confirm the effects of the present invention, Si_3N_4 powder, ZrO_2 powder, and one or more oxide powders selected from MgO , Y_2O_3 , Al_2O_3 , SiO_2 , CeO_2 , TiO_2 , and H_2MoO_4 (to be MoO_3 after sintering) were mixed at various compounding ratios with water, dispersant, resin, and ceramic-made balls, and obtained slurries were each spray-dried by a spray dryer to be formed into granules. The obtained granules were charged into a graphite-made dice (mold) and subjected to hot pressing calcination in a nitrogen atmosphere, under a pressure of 30 MPa, at 1700°C, for 2 hours, to be formed into test materials being 150 mm long $\times$ 150 mm wide $\times$ 30 mm thick.

[0046]

From the obtained test materials, test specimens were taken and subjected to various kinds of tests.

[0047]

<Thermal Expansivity>

A coefficient of thermal expansion of each of the test materials at -50 to 500°C was determined in conformity with JIS R1618.

[0048]

<Flexural Strength>

A three-point flexural strength of each of the test materials was determined in conformity with JIS R1601. A case where the flexural strength was 600 MPa or more was rated as good.

[0049]

<Relative Density>

A bulk density of each of the test materials was determined in conformity with JIS C2141, and the determined bulk density was divided by a theoretical density, by which a relative density was determined. A case where the relative density was 90% or more was rated as good.

[0050]

<Young's Modulus>

A Young's modulus of each of the test materials was determined in conformity with JIS R1602. A case where the Young's modulus was 230 GPa or more was rated as good.

[0051]

<Micromachinability>

Regarding micromachinability, a machining precision of pulse laser machining performed on a ceramic material having a thickness of 0.3 mm to form nine 50- μ m-square through holes was evaluated by observing shapes of the holes on a side to which laser beams came out by a vision measuring system (e.g., Quick Vision from Mitutoyo Corporation) (a case where the machining precision fell within ± 2 μ m was rated as good). A case where holes each having a machining precision of within ± 2 μ m were successfully formed was rated as "O," and the other cases (a case where the material was left, a case where shapes of the holes were distorted, etc.) were rated as "x." Figure 8 is a schematic diagram of the laser beam machining. As illustrated in Figure 8, a side of a ceramic to be irradiated with laser light will be referred to as a laser irradiation side, and a side of the ceramic opposite to the laser irradiation will be referred to as a laser beam coming-out side.

[0052]

<Roughness of Machined Surface>

Regarding a roughness of the machined surface, nine 50- μ m square through holes were formed on the ceramic material having a thickness of 0.3 mm by the pulse laser machining, given five visual fields of inner surfaces of the machined holes were measured over a length of 100 μ m or more under a laser confocal microscope (VK-X150 from KEYENCE CORPORATION), skew correction was performed to calculate Ra, and an average value of Ra was evaluated. Ra being 0.25 μ m or less was rated as good. The roughness of the machined surface is determined by observing a cross section of the ceramic material parallel to a thickness direction of the ceramic material in an area including a thickness center portion of an inner surface of each hole

(specifically, a portion surrounded by a rectangle illustrated in Figure 8).

[0053]

[Table 1]

Table 1

	Component (mass%)																Young's modulus (GPa)	Relative Density (%)	Whether to form fine square hole	Surface roughness Ra(um)	Crack after heat treatment at 150°C	
	Main component		Oxide 1								Oxide 2				Total of oxide							
			Oxide 1								Oxide 2											
			ZrO2	Others	MgO	Y2O3	CeO2	Al2O3	SiO2	TiO2	MoO3	SiO2	TiO2	MoO3								
Examples	1	24.0	68.2	-	-	4.6	-	1.8	0.9	0.5	-	7.8	5.0	910	98.4	259	○	-	○	0.11	○	
	2	30.6	57.9	-	1.8	5.3	1.8	2.6	-	-	-	11.5	4.8	815	98.8	269	○	-	○	0.13	○	
	3	40.7	51.5	-	-	5.5	-	1.8	-	-	0.5	7.8	4.2	890	98.2	268	○	-	○	0.19	○	
	4	40.5	51.2	-	5.5	-	-	2.8	-	-	-	8.3	4.3	943	97.5	264	○	-	○	0.17	○	
	5	51.1	41.5	-	-	6.5	-	0.9	-	-	-	7.4	3.7	1021	98.3	271	○	-	○	0.18	○	
	6	50.9	41.3	-	-	5.5	-	1.9	-	0.4	-	7.8	3.4	1166	98.3	273	○	-	○	0.16	○	
	7	58.8	27.9	-	3.5	7.3	-	0.8	1.7	-	-	13.3	3.0	855	99.0	281	○	-	○	0.19	○	
	8	34.0	57.3	-	-	4.1	-	-	3.7	0.9	-	8.7	4.6	882	98.6	263	○	-	○	0.16	○	
	9	52.8	37.0	-	2.3	7.4	-	0.5	-	-	-	10.2	3.4	937	98.4	277	○	-	○	0.18	○	
	10	52.3	33.1	-	3.4	7.4	-	3.4	-	0.4	-	14.6	3.2	847	98.6	263	○	-	○	0.18	○	
	11	36.1	56.1	-	-	6.9	-	-	-	0.2	0.7	7.8	4.6	808	98.0	268	○	-	○	0.15	○	
	12	24.6	69.9	-	-	4.6	0.9	-	-	-	-	5.5	5.0	877	97.4	261	○	-	○	0.13	○	
	13	40.0	50.6	-	-	5.7	3.7	-	-	-	-	9.4	4.4	912	98.1	274	○	-	○	0.19	○	
	14	40.0	50.6	-	-	-	-	9.4	-	-	-	9.4	4.5	1334	99.1	299	-	○	-	○	0.21	×
	15	40.0	50.6	-	-	1.1	-	8.3	-	-	-	9.4	4.5	1221	98.8	295	-	○	○	○	0.18	×
	16	29.7	62.4	-	-	6.6	-	1.2	-	-	-	7.8	5.3	854	99.1	261	○	-	-	○	0.16	○
	17	21.0	70.0	-	1.1	5.8	-	2.1	-	-	-	9.0	5.7	863	98.4	252	○	-	-	○	0.14	○
Comparative examples	1	75.1*	15.8*	-	-	5.5	-	3.6	-	-	-	9.1	2.0#	944	97.0	280	○	-	-	○	0.28	○
	2	17.5*	77.6*	-	1.4	-	-	1.0	1.0	1.0	0.5	4.9*	6.1#	984	98.1	257	○	-	-	×	Shape distorted	-
	3	10.7*	81.8*	-	1.9	1.9	-	3.7	-	-	-	7.5	6.7#	1014	98.9	256	○	-	-	×	Material left	-
	4	27.6	52.4	-	-	20.0	-	-	-	-	-	20.0*	5.3	561#	99.2	265	○	-	-	×	Shape distorted	-
	5	44.8	-*	BN:32.6	-	5.6	-	1.9	-	-	-	7.5	1.4#	452#	97.2	130	○	-	-	○	0.33	○
	6	12.5*	47.4	BN:32.6	-	5.6	-	1.9	-	-	-	7.5	4.7	361#	97.7	157	○	-	-	×	Material left	-
	7	95.8*	-*	-	-	3.1	-	1.1	-	-	-	4.2*	1.7#	785	97.6	285	-	-	-	○	0.29	○
	8	-*	-*	AlN:94.0	-	6.0	-	-	-	-	-	6.0	4.4	348#	98.7	320	-	-	-	×	Material left	-
	9	-*	100.0*	-	-	-	-	-	-	-	-	0.0*	8.0#	880	97.8	245	-	-	○	-	-	×

* It means that the content falls out of the respective range specified in the present invention.

It means that it does not have required properties in the present invention.

[0054]

Figure 3 is a picture of micromachined holes in Example 6 captured from above, Figure 4 is a picture of micromachined holes in Comparative example 3 captured from above, and Figure 5 is a picture of micromachined holes in Comparative example 4 captured from above. Figure 6 is a picture of a captured inner surface of a micromachined hole in Example 6, and Figure 7 is a picture of a captured inner surface of a micromachined hole in Comparative example 5.

[0055]

As shown in Table 1, in Comparative examples 1 and 7, they were excessively high in Si_3N_4 and excessively low in ZrO_2 , and thus their thermal expansivities were decreased. In Comparative examples 2 and 3, they were excessively low in Si_3N_4 and excessively high in ZrO_2 , and thus they had high thermal expansivities and degraded micromachinability. In Comparative example 4, it was excessively high in Y_2O_3 , and thus its thermal expansivity was high, and its flexural strength and micromachinability were degraded. In Comparative examples 5 and 6, although they contained BN as their main components, their contents of Si_3N_4 or ZrO_2 fell out of the respective ranges specified in the present invention, and thus their flexural strengths were degraded. In Comparative example 8, although it contained AlN as its main component, its content of Si_3N_4 or ZrO_2 fell out of the respective ranges specified in the present invention, and thus its flexural strength was degraded. In Comparative example 9, it consisted of only ZrO_2 , and thus it had excellent qualities such as flexural strength, whereas its thermal expansivity was excessively high, and its micromachinability was degraded.

[0056]

In contrast, in Examples 1 to 17, their thermal expansivities and flexural strengths both fell within satisfactory ranges, and in addition, they were excellent in the micromachinability and the roughness of machined surface. In particular, as a result of the micromachining, precise holes were successively formed in Example 6, whereas the material was left in Comparative example 3, and shapes of holes were distorted in Comparative example 4, as illustrated in Figures 3 to 5. As illustrated in Figure 6 and Figure 7, Example 6 shows a low surface roughness inside its holes (R_a : 0.16 as shown

in Table 1), whereas Comparative example 5 showed a high surface roughness inside its holes (Ra: 0.33 as shown in Table 1). In Example 14 and Example 15, although they satisfied the required qualities, they contained the tetragonal crystal ZrO_2 , and thus the occurrence of a crack was recognized after the heat treatment at 150°C . These ceramics can be used at normal temperature without any trouble but are unfit for use in a heated condition.

INDUSTRIAL APPLICABILITY

[0057]

The present invention makes it possible to obtain a ceramic that has a coefficient of thermal expansion as high as that of silicon and an excellent mechanical strength, allows fine machining with high precision, includes a smooth machined surface, and can prevent particles from being produced in its use, which is thus useful particularly to a probe guiding member, a probe card, and a socket for inspection.

CLAIMS

[Claim 1]

A ceramic containing, in mass percent:

Si₃N₄: 20.0 to 60.0%;

ZrO₂: 25.0 to 70.0%; and

one or more oxides selected from MgO, Y₂O₃, CeO₂, CaO, HfO₂, TiO₂, Al₂O₃, SiO₂, MoO₃, CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅: 5.0 to 15.0%.

[Claim 2]

The ceramic according to claim 1 containing, in mass percent:

one or more oxides selected from MgO, Y₂O₃, CeO₂, CaO, and HfO₂; and

one or more oxides selected from TiO₂, Al₂O₃, SiO₂, MoO₃, CrO, CoO, ZnO, Ga₂O₃, Ta₂O₅, NiO, and V₂O₅.

[Claim 3]

The ceramic according to claim 1 or 2, wherein a crystal phase of ZrO₂ is one of a crystal phase being a tetragonal crystal, a crystal phase being a tetragonal crystal and a monoclinic crystal, a crystal phase being a cubic crystal, a crystal phase being a cubic crystal and a tetragonal crystal, and a crystal phase being a cubic crystal and a monoclinic crystal.

[Claim 4]

The ceramic according to any one of claims 1 to 3, wherein ZrO₂ is a cubic crystal.

[Claim 5]

The ceramic according to any one of claims 1 to 4, wherein the ceramic has a coefficient of thermal expansion at -50 to 500°C ranging from 3.0×10^{-6} to 6.0×10^{-6} /°C and has a three-point flexural strength of 700 MPa or more.

[Claim 6]

A probe guiding member that guides probes of a probe card, the probe guiding member comprising:

a plate-shaped main body that is made of the ceramic according to any one of

claims 1 to 5; and

the main body includes a plurality of through holes and/or slits through which the probes are to be inserted.

[Claim 7]

The probe guiding member according to claim 6, wherein a surface roughness of inner surfaces of the plurality of through holes and/or slits is 0.25 μm or less in terms of Ra.

[Claim 8]

A probe card comprising:

a plurality of probes; and

the probe guiding member according to claim 6 or 7.

[Claim 9]

A socket for package inspection, wherein the socket for package inspection is made of the ceramic according to any one of claims 1 to 5.