

5433 PCT

GLASS FRITS

TECHNICAL FIELD

[0001] Embodiments of the invention relate to glass frits, conductive inks including a frit, and articles having such conductive inks applied thereto.

5 BACKGROUND

[0002] Conductive inks, obscuration enamels and decorative enamels typically use lead-based glass frits because they have a low melting range, low molten viscosity and stability against uncontrolled devitrification. Obscuration enamels are used in the automotive industry and conductive inks are used in the electronics industry, including in the manufacture of solar cells or photovoltaic cells.

10 [0003] Photovoltaic ("PV") cells convert sunlight into electricity by promoting charge carriers in the valence band of a semi-conductor into the conduction band of the semiconductor. The interaction of photons in the sunlight and doped semiconductor materials form electron-hole pair charge carriers. These electron-hole pair charge carriers migrate in the electric field generated by the p-n semiconductor junction and collected by a conductive grid or metal contact printed or applied to the surface of the semiconductor, through which it flows to the external circuit. Crystalline silicon PV cells in today's industry are typically coated with an anti-reflective coating to promote light adsorption, which increases PV cells efficiency. However, the anti-reflective coating imposes high electrical resistance to the charge carrier flowing from the semiconductor to the metal contact. Such anti-reflective coatings often comprise silicon nitride, titanium oxide or silicon oxide.

20 [0004] Conductive inks are used to form these conductive grids or metal contacts. Conductive inks typically include a glass frit, a conductive species, such as silver particles, and an organic medium. To form the metal contacts, conductive inks are printed onto the substrate in a pattern of grid lines or other pattern by screen printing or other process. The substrate is then fired, during which electrical contact is made between the grid lines and the substrate. This contact is enhanced by the formation of individual silver crystallites at the glass-substrate interface. Without being bound by theory, it is believed that charge carriers are transferred from the substrate to the silver crystallites and then transferred to the gridline

25

5433 PCT

either through the glass layer by tunneling or directly to the silver of the gridline, if there is direct contact of the crystallite with both the gridline and the semiconductor. Lower firing temperatures are desirable in this process because of the lower cost involved and energy saved.

5 [0005] As otherwise mentioned herein, the anti-reflective coating enhances light absorption but also acts as an insulator which impairs the excited electrons from flowing from the substrate to the metal contacts. Accordingly, the conductive ink should penetrate the anti-reflective coating to form metal contacts having ohmic contact with the substrate. To accomplish this, conductive inks incorporate glass frits to aid with sintering silver particles to
10 a substrate and to promote adhesion and ohmic contact between the formed metal contact and the substrate. When the glass frit liquefies, it tends to flow toward the interface between the silver particles and the anti-reflective coating on the substrate. The melted glass dissolves the anti-reflective coating materials as well as some of the metal particles and substrate. Once the temperature decreases, the molten silver and the melted or dissolved substrate recrystallize
15 through the liquid phase. As a result, some of the silver crystallites are able to penetrate the antireflective layer and form ohmic contact with the substrate. This process is referred to as "fire-through" and facilitates a low contact resistance formation and a stronger bond between conductive grid or metal contact and the substrate.

[0006] The automotive, electronics and solar cell industries place greater emphasis on
20 using environmentally-friendly components and processes. This emphasis has been further urged by the need to comply with environmental regulations. In response, the solar cell industry is moving to eliminate the use of lead in components and materials used in solar panels of cells.

[0007] Accordingly, there is a need for a lead-free glass frit which can be fired at a
25 lower temperature and that can penetrate the anti-reflective layer and form metal contacts in ohmic contact with a substrate.

SUMMARY

[0008] Embodiments of the present invention relate to tellurium containing frits having no intentionally added lead and the uses thereof. According to one or more
30 embodiments, the frits described herein have very low viscosity and are particularly corrosive.

5433 PCT

For example, in one or more embodiments, the frits tend to dissolve refractory materials typically used in PV applications as anti-reflective layers such as SiO_2 , TiO_2 and SiN_x .

[0009] Specific embodiments include a frit having no intentionally added lead which includes TeO_2 and Bi_2O_3 and/or SiO_2 . As used throughout this application, the terms “no intentionally added lead” and “substantially lead-free” shall mean a frit having lead in an amount less than about 1,000 ppm. In one or more embodiments, TeO_2 is present in an amount between about 0.01% by weight to about 10% by weight. Another embodiment also includes B_2O_3 . According to one embodiment, the frit also includes at least one first oxide component. A second embodiment of the invention further includes at least one second oxide component, while a third embodiment includes at least one alkali metal oxide component. At least one alkaline earth metal oxide is included in another embodiment of the invention.

[0010] The first oxide component of one or more embodiments can include ZnO and/or Al_2O_3 . ZnO is present in one embodiment in an amount of about 0% by weight to about 15% by weight, while the Al_2O_3 is present in an amount of about 0% by weight to about 3% by weight in another embodiment. The second oxide component of one embodiment includes Ag_2O , Sb_2O_3 , GeO_2 , In_2O_3 , P_2O_5 , V_2O_5 , Nb_2O_5 , and Ta_2O_5 and can be present in the following amounts: Ag_2O , P_2O_5 , V_2O_5 , Nb_2O_5 , and/or Ta_2O_5 are present in an amount of about 0% by weight to about 8% by weight; In_2O_3 and/or Sb_2O_3 are present in an amount in the range from about 0% by weight to about 5% by weight; and GeO_2 is present in an amount in the range from about 0% by weight to about 10% by weight. Embodiments with at least one alkali metal oxide component utilize Na_2O , Li_2O , and/or K_2O in an amount in the range from about 0% by weight to about 3% by weight, while embodiments with at least one alkaline earth metal oxide component utilize BaO , CaO , MgO and/or SrO in an amount in the range from about 0% by weight to about 8% by weight.

[0011] In accordance with another aspect of the present invention, a conductive ink includes a substantially lead-free frit having TeO_2 and Bi_2O_3 and/or SiO_2 , along with a conductive species, and no intentionally added lead. One or more embodiments of the conductive ink include TeO_2 in an amount in the range from about 0.01% by weight to about 10% by weight. Another embodiment utilizes silver as a conductive species. In accordance with one or more embodiments, the conductive ink includes frits which also incorporate B_2O_3 . Further conductive ink embodiments can have a frit which includes at least one first oxide

5433 PCT

component, at least one second oxide component, at least one alkali metal oxide component, and/or at least one alkaline earth metal oxide component. According to one embodiment, frit is present in the conductive ink in the amount in the range from about 1% by weight to about 5% by weight.

5 [0012] Another aspect of the invention includes an article comprising a substrate, and a conductive ink as described herein disposed on the substrate. According to one or more embodiments, the substrate is a semiconductor, a glass sheet and/or an enamel disposed on a glass sheet. Embodiments with a semiconductor substrate also include an anti-reflective layer disposed on the substrate with the conductive ink is disposed on the anti-reflective layer. In a
10 more specific embodiment, the anti-reflective layer includes SiO_2 , TiO_2 or SiN_x

[0013] In one or more embodiments of the article, the conductive ink comprises a substantially lead-free frit and a conductive species. In a specific embodiment, the frit includes B_2O_3 and TeO_2 .

[0014] The foregoing has outlined rather broadly certain features and technical
15 advantages of the present invention. It should be appreciated by those skilled in the art that the specific embodiments disclosed may be readily utilized as a basis for modifying or designing other structures or processes within the scope of the present invention. It should also be realized by those skilled in the art that such equivalent constructions do not depart from the spirit and scope of the invention as set forth in the appended claims.

20 DETAILED DESCRIPTION

[0015] Before describing several exemplary embodiments of the invention, it is to be understood that the invention is not limited to the details of construction or process steps set forth in the following description. The invention is capable of other embodiments and of being practiced or being carried out in various ways.

25 [0016] Specific embodiments of the present invention include a frit having no intentionally added lead which includes TeO_2 and Bi_2O_3 and/or SiO_2 . In one or more embodiments, TeO_2 is present in an amount between about 0.01% by weight to about 10% by weight. In a more specific embodiment, TeO_2 is present in an amount between about 0.5% by weight to about 5% by weight. In an even more specific embodiment, TeO_2 is present in an
30 amount between about 0.5% by weight to about 2% by weight. In one or more embodiments,

5433 PCT

Bi₂O₃ is present in the frit in an amount in the range from about 40% by weight to about 95% by weight. In a specific embodiment, Bi₂O₃ is present in the range from about 50% by weight to about 80% by weight, while an even more specific embodiment has Bi₂O₃ in the range from about 60% by weight to about 75% by weight.

5 [0017] One or more embodiments of the frit include SiO₂ in an amount in the range from about 0% by weight to about 30% by weight. In specific embodiments, SiO₂ can be present in an amount in the range from about 1% by weight to about 4% by weight.

[0018] According to one or more embodiments, B₂O₃ is also included in the frit. In a specific embodiment, B₂O₃ is present in an amount in the range from about 0.1% by weight to about 10% by weight. In a more specific embodiment, B₂O₃ is present in an amount in the range from about 0.5% by weight to about 8% by weight. In an even more specific embodiment, B₂O₃ is present in an amount in the range from about 1% by weight to about 4% by weight.

[0019] One embodiment of the present invention includes a frit having TeO₂, Bi₂O₃, SiO₂, and B₂O₃. Another example of a frit includes TeO₂, Bi₂O₃, SiO₂, B₂O₃, ZnO and Al₂O₃. An additional embodiment of a frit includes 0.01% to 10% by weight of TeO₂, 40% to 95% by weight of Bi₂O₃, 0% to 30% by weight of SiO₂, 0.1% to 10% by weight of B₂O₃, 0% to 15% by weight of ZnO and 0% to 3% by weight of Al₂O₃. A further embodiment of the present invention includes a frit having TeO₂, Bi₂O₃, SiO₂, B₂O₃, ZnO and a second oxide component.

20 One or more embodiments substitute ZnO with Al₂O₃, while another embodiment incorporates both ZnO and Al₂O₃.

[0020] One embodiment of the invention includes at least a first oxide component such as:

ZnO in an amount in the range from about 0% by weight to about 10% by weight; and/or

25 Al₂O₃ in an amount in the range from about 0% by weight to about 2% by weight.

[0021] Another embodiment of the invention incorporates at least one second oxide component including:

Ag₂O in an amount in the range from about 0% by weight to about 4% by weight;

Sb₂O₃ in an amount in the range from about 0% by weight to about 4% by weight;

30 GeO₂ in an amount in the range from about 0% by weight to about 4% by weight;

5433 PCT

In_2O_3 in an amount in the range from about 0% by weight to about 4% by weight;

P_2O_5 in an amount in the range from about 0% by weight to about 4% by weight;

V_2O_5 in an amount in the range from about 0% by weight to about 4% by weight;

Nb_2O_5 in an amount in the range from about 0% by weight to about 4% by weight; and/or

5 Ta_2O_5 in an amount in the range from about 0% by weight to about 4% by weight.

[0022] One or more embodiments of the present invention incorporate at least one alkali metal oxide component including:

Na_2O in an amount in the range from about 0% by weight to about 2% by weight;

Li_2O in an amount in the range from about 0% by weight to about 2% by weight;

10 and/or

K_2O in an amount in the range from about 0% by weight to about 2% by weight.

[0023] Additional embodiments of the invention also include at least one alkaline earth metal oxide component such as:

BaO in an amount in the range from about 0% by weight to about 4% by weight;

15 CaO in an amount in the range from about 0% by weight to about 2% by weight;

MgO in an amount in the range from about 0% by weight to about 2% by weight;

and/or

SrO in an amount in the range from about 0% by weight to about 4% by weight.

[0024] One or more embodiments of the present invention include conductive inks
20 which utilize the frits disclosed herein and a conductive species. In one or more
embodiments, the conductive ink utilizes a conductive species such as silver in powdered or
particulate form. In one or more embodiments, the silver particles can be spherical, flaked or
amorphous or provided in a colloidal suspension. Other non-limiting examples of suitable
conductive species include conductive metals such as gold, copper and platinum in powdered
25 or particulate form.

[0025] The silver species used in one or more embodiments can be in the form of fine
powders of silver metal or silver alloys. In other embodiments, some of the silver can be
added as silver oxide (Ag_2O), silver salts such as silver chloride (AgCl), silver nitrate
(AgNO_3) and/or silver acetate.

5433 PCT

[0026] Conductive inks according to one or more embodiments of the present invention also incorporate bismuth tellurate and/or bismuth silicate powders. It has been found that the addition of bismuth tellurate and/or bismuth silicate powders can control crystallization of the glass frit by shifting the onset of crystallization to lower temperatures.

5 While the present invention should not be bound by theory, it is believed that bismuth tellurate and/or bismuth silicate powders provide nucleation sites for crystal growth. In a photovoltaic application, the glass frit should penetrate through or dissolve the anti-reflective layer to enable the silver to form ohmic contact, however, controlling the aggressiveness of glass frit is desired to prevent it from penetrating through the junction of the semiconductor
10 which would shunt the device. Other embodiments utilize other known phases which produce the same or similar effect as bismuth tellurate and/or bismuth silicate, such as titania, zirconia, phosphorous compound and others.

[0027] The conductive ink according to one or more embodiments may also include a liquid vehicle. It is believed that the liquid vehicle disperses the particulate components and
15 facilitates transfer of the ink composition onto a surface. Specifically, the liquid vehicle, which, according to one or more embodiments, is composed of solvent(s) and dissolved organic resin(s), disperses the conductive species and frit to obtain an ink having suitable viscosity. In addition to influencing paste viscosity it is believed that the resin(s) improve the adhesion and green-strength of the paste after it has been deposited on the substrate and dried.
20 Various liquid vehicles with or without thickening agents, stabilizing agents, surfactants, defoamers and/or other common additives are suitable for use in the preparation of the embodiments of the present invention. Exemplary liquid vehicles which can be used include alcohols (including glycols), esters of such alcohols such as the acetates, propionates and phthalates, for instance dibutyl phthalate, terpenes such as pine oil, terpineol and the like.
25 More specific liquid vehicles include diethylene glycol monbutyl ether, terpineol, isopropanol, tridecanol, water, and 2,2,4-trimethyl-1,3-pentanediol monoisobutyrate. Some embodiments utilize vehicles that also contain volatile liquids to promote fast setting after application to the substrate.

[0028] Examples of suitable organic resins dissolved into the liquid vehicle include
30 ethyl cellulose, methyl cellulose, nitrocellulose, ethyl hydroxyl ethyl cellulose, carboxymethyl cellulose, hydroxypropyl cellulose and other cellulose derivatives. Other examples include

5433 PCT

resins such as acrylic acid esters, methacrylic acid esters, polyvinyl alcohols, polyvinyl butyrals, polyesters and polyketones.

[0029] In one specific embodiment, solutions of resins such as polymethacrylates of lower alcohols are used, while in a more specific embodiment, the liquid vehicle includes ethyl cellulose dissolved in solvents such as pine oil and monobutyl ether of diethylene glycol.

[0030] The ratio of liquid vehicle to solids in the conductive ink according to one or more embodiments can vary considerably and is determined by the final desired formulation viscosity which, in turn, is determined by the printing requirements of the system. In one or more embodiments, the conductive ink can contain about 50 to about 95% by weight solids and about 5 to about 50% by weight liquid vehicle.

[0031] One or more embodiments of the conductive inks may additionally comprise further additives known in the art, such as colorants and staining agents, rheology modifiers, adhesion enhancers, sintering inhibitors, green-strength modifiers, surfactants and the like.

[0032] In one or more embodiments of the present invention, a preservative is incorporated into the coating composition. Some embodiments utilize preservatives such as boric acid, phosphoric acid, hydrochloric acid, nitric acid, sulphuric acid and/or combinations thereof, while other embodiments utilize other preservatives known in the art.

[0033] Another aspect of the present invention pertains to articles including a substrate, and a conductive ink disposed on the substrate. One or more embodiments include a conductive ink having a frit as described herein, that is, a frit comprising TeO_2 and having no intentionally added lead. Examples of substrates include semiconductor wafers, glass sheets and other suitable substrates used in the photovoltaic industry for the formation of photovoltaic cells. In one embodiment, the semiconductor substrate is doped with phosphorous, while another embodiment includes doped conductive inks. According to one embodiment of the present invention, the semiconductor substrate comprises amorphous, multicrystalline or monocrystalline silicon.

[0034] In one or more embodiments, the semiconductor substrate has an anti-reflective coating disposed thereon and the conductive ink is printed on top of the anti-reflective coating. The anti-reflective coating according to some embodiments comprises silicon dioxide, titanium oxide, silicon nitride or other coatings known in the art.

5433 PCT

[0035] Methods known in the art can be used to produce semiconductor substrates having a conductive ink disposed thereon. One or more embodiments employ crystalline silicon such can be either amorphous, monocrystalline or multicrystalline. Coatings may be applied to the substrates, and such coatings or layers can be produced according to known processes, such as chemical vapor deposition, plasma vapor deposition, and the like. The anti-reflective coatings can also be applied using chemical vapor deposition techniques. In some embodiments, plasma enhanced chemical vapor deposition techniques are used to dispose the anti-reflective coating on the substrate. Semiconductor articles, according to one or more embodiments, may also be etched or textured to reduce reflection of sunlight and enhance the level of light absorption. According to one or more embodiments, the conductive ink is thereafter applied to the surface of the substrate or anti-reflective coating by screen printing or other technique. The substrate is heated or fired to a temperature of about 750° to 850° C to sinter the particles of the conductive ink into gridlines. As otherwise discussed in this application, the firing process allows the glass frit to melt and penetrate or dissolve the anti-reflective coating disposed on the substrate. In one or more embodiments, the conductive species forms crystallites at the interface of the frit and substrate interface, which enhances electrical or ohmic contact between the metal contacts formed from the conductive ink and the semiconductor substrate.

[0036] One or more embodiments of the invention include glass sheet substrates with conductive ink printed thereon. In a specific example, the glass sheet is an automotive backlite. In other examples, the glass sheet has an enamel disposed thereon and a conductive ink is printed on the enamel. Enamels used in some embodiments may be obscuration enamels which provide protection from ultra-violet rays which can deteriorate the adhesive glues that bond the automotive windshields to a vehicle body. Embodiments of glass sheet substrates may also include a pliable interlayer usually made up of polyvinyl butyrate ("PVB").

[0037] As with embodiments of the invention related to semiconductor articles with conductive ink disposed thereon, the conductive ink can be applied to the glass sheet substrate or enamel substrate by screen printing or other known method. In further embodiments, the substrates are fired heated or fired to a temperature of about 600° to 750° C to sinter the particles of the conductive ink into grid lines.

5433 PCT

[0038] Without intending to limit the invention in any manner, embodiments of the present invention will be more fully described by the following examples.

EXAMPLES

[0039] Two inks (Ink A and Ink B) were prepared having at least a frit and a conductive species. Inks A and B were prepared using a general procedure. The general procedure includes batching and dispersing the examples using triple roll milling. Alternative dispersion processes known in the industry such as bead milling, sand milling and colloid milling could also be used to disperse the solid particles in the organic binder medium.

[0040] Inks A and B both had a frit content of 3% by weight and silver in an amount of 97% by weight (on a solids basis). Both frits were bismuth borosilicate compositions, had similar coefficients of thermal expansion and glass transition temperatures. Ink A contained a frit known in the art which had no intentionally added lead. Ink B contained a frit known in the art which had no intentionally added lead and also incorporated TeO₂.

[0041] Eight textured, monocrystalline silicon wafers with a 40 ohm/square phosphorus doped emitter and boron doped base having a silicon nitride anti reflective coating were used. The back surfaces of the eight wafers were printed with commercially available back surface aluminum ink and silver rear contact ink. Both inks were thoroughly dried. Four wafers were then printed on the front surface with Ink A using a 325 mesh screen (Cells 1-4). Four additional wafers were printed on the front surface with Ink B in an identical manner (Comparative Cells 5-8). The PV cells were then dried and fired in an infrared furnace to a peak firing temperature as noted in Table 1. Each wafer was fired at the peak temperature for approximately 3 to 5 seconds. After cooling, the parts were tested for their current-voltage (I-V) characteristics.

TABLE 1: COMPARISON OF ENAMEL LAYERS

	Cell 1	Cell 2	Cell 3	Cell 4
Fill Factor (FF)	0.467	0.523	0.494	0.562
Efficiency (Eff)	9.8	11.4	10.8	12.3
Peak Firing Temp	800° C	820° C	820° C	820° C

	Comparative Cell 5	Comparative Cell 6	Comparative Cell 7	Comparative Cell 8
Fill Factor (FF)	0.519	0.659	0.659	0.681
Efficiency (Eff)	11.2	14.3	14.3	14.8
Peak Firing Temp	800° C	820° C	820° C	820° C

5433 PCT

[0042] The "fill factor" and "efficiency" refer to measurements of the performance of a semiconductor. The term "fill factor" is defined as the ratio of the maximum power ($V_{mp} \times J_{mp}$) divided by the short-circuit current (I_{sc}) and open-circuit voltage (V_{oc}) in light current density - voltage (J-V) characteristics of solar cells. The open circuit voltage (V_{oc}) is the maximum voltage obtainable at the load under open-circuit conditions. The short circuit current density (J_{sc}) is the maximum current through the load under short-circuit conditions. The fill factor (FF), is thus defined as $(V_{mp}J_{mp})/(V_{oc}J_{sc})$, where J_{mp} and V_{mp} represent the current density and voltage at the maximum power point. The cell efficiency, η , is given by the equation $\eta = (I_{sc}V_{oc}FF)/P_{in}$ where I_{sc} equals the short circuit current, V_{oc} equals the open circuit voltage, FF equals fill factor and P_{in} is the power of the incident solar radiation.

[0043] The fill factor and efficiency of Comparative Cells 5-8, which contain TeO_2 , was significantly higher than Cells 1-4, which did not contain TeO_2 . This improvement was observed at both firing temperatures. Without being bound by theory, it is believed that the use of TeO_2 reduces the viscosity of the molten frit, thereby enabling the frit to penetrate, dissolve and/or digest the anti-reflective layer of the PV cell and improving ohmic contact between the silver or formed metal contact and the substrate cell.

[0044] Reference throughout this specification to "one embodiment," "certain embodiments," "one or more embodiments" or "an embodiment" means that a particular feature, structure, material, or characteristic described in connection with the embodiment is included in at least one embodiment of the invention. Thus, the appearances of the phrases such as "in one or more embodiments," "in certain embodiments," "in one embodiment" or "in an embodiment" in various places throughout this specification are not necessarily referring to the same embodiment of the invention. Furthermore, the particular features, structures, materials, or characteristics may be combined in any suitable manner in one or more embodiments.

[0045] Although the invention herein has been described with reference to particular embodiments, it is to be understood that these embodiments are merely illustrative of the principles and applications of the present invention. It will be apparent to those skilled in the art that various modifications and variations can be made to the method and apparatus of the present invention without departing from the spirit and scope of the invention. Thus, it is

5433 PCT

intended that the present invention include modifications and variations that are within the scope of the appended claims and their equivalents.

5433 PCT

What is claimed is:

1. A frit comprising: TeO_2 ; and one or more of Bi_2O_3 and SiO_2 , the frit containing no intentionally-added lead.

5

2. The frit of claim 1, further comprising B_2O_3 .

3. The frit of claim 2, further comprising at least one first oxide component selected from one or more of ZnO , Al_2O_3 and combinations thereof.

10

4. The frit of claim 2 or 3, further comprising at least one second oxide component selected from one or more of Ag_2O , Sb_2O_3 , GeO_2 , In_2O_3 , P_2O_5 , V_2O_5 , Nb_2O_5 , Ta_2O_5 and combinations thereof.

15

5. The frit of claim 2 further comprising at least one alkali metal oxide component selected from one or more of Na_2O , Li_2O , K_2O and combinations thereof.

6. The frit of claim 2 further comprising at least one alkaline earth metal oxide component selected from one or more of BaO , CaO , MgO , SrO and combinations thereof.

20

7. The frit of claim 2, wherein the TeO_2 is present in an amount in the range from about 0.1% by weight to about 10% by weight.

8. The frit of claim 7 further comprising at least one first oxide component selected from one or more of

25

ZnO in an amount in the range from about 0% by weight to about 15% by weight; and Al_2O_3 in an amount in the range from about 0% by weight to about 3% by weight.

9. The frit of claim 7 or 8, further comprising at least one second oxide component selected from one or more of

30

Ag_2O in an amount in the range from about 0% by weight to about 8% by weight;

5433 PCT

Sb₂O₃ in an amount in the range from about 0% by weight to about 5% by weight;
GeO₂ in an amount in the range from about 0% by weight to about 10% by weight;
In₂O₃ in an amount in the range from about 0% by weight to about 5% by weight;
P₂O₅ in an amount in the range from about 0% by weight to about 8% by weight;
5 V₂O₅ in an amount in the range from about 0% by weight to about 8% by weight;
Nb₂O₅ in an amount in the range from about 0% by weight to about 8% by weight; and
Ta₂O₅ in an amount in the range from about 0% by weight to about 8% by weight.

10 10. A conductive ink comprising a substantially lead-free frit according to any of claims 2-9 and a conductive species.

11. The ink of claim 10, wherein the frit is present in amount in the range from about 1% by weight to about 5% by weight.

15 12. The ink of claim 10, further comprising one or more of bismuth tellurate and bismuth silicate, titania, zirconia, phosphorous compounds, and combinations thereof.

20 13. An article comprising a substrate and a conductive ink according to claim 10 disposed on the substrate.

14. The article of claim 13, wherein the substrate is one of a semiconductor, a glass sheet or an enamel disposed on a glass sheet.

25 15. The article of claim 14, wherein an anti-reflective layer comprising TiO₂ and Si₃N₄ is disposed directly on the substrate and the conductive ink disposed on the anti-reflective layer.