



A PROCESS FOR THE PRODUCTION OF ETHYLENICALLY UNSATURATED CARBOXYLIC ACIDS OR ESTERS AND A CATALYST THEREFOR

The present invention relates to a process for the
5 production of ethylenically unsaturated carboxylic acids
or esters, particularly α , β unsaturated carboxylic acids
or esters, more particularly acrylic acids or esters such
as (alk)acrylic acids or alkyl (alk)acrylates particularly
(meth)acrylic acid or alkyl (meth)acrylates by the
10 condensation of carboxylic acid or esters with
formaldehyde or a source thereof such as dimethoxymethane
in the presence of catalysts, in particular, but not
exclusively, a process for the production of (meth)
acrylic acid or alkyl esters thereof, for example, methyl
15 methacrylate, by the condensation of propionic acid or
alkyl esters thereof with formaldehyde or a source thereof
such as dimethoxymethane in the presence of such a
catalyst system. The invention is particularly relevant to
the production of methacrylic acid (MAA) and methyl
20 methacrylate (MMA).

Such acids or esters may be made by reacting an alkanoic
acid (or ester) of the formula $R^3-CH_2-COOR^4$, where R^3
and R^4 are each, independently, a suitable substituent
25 known in the art of acrylic compounds such as hydrogen or
an alkyl group, especially a lower alkyl group containing,
for example, 1-4 carbon atoms, with a suitable methylene
source such as formaldehyde. Thus, for instance,
methacrylic acid or alkyl esters thereof, especially
30 methyl methacrylate, may be made by the catalytic reaction
of propionic acid, or the corresponding alkyl ester, e. g.
methyl propionate, with formaldehyde as a methylene source
in accordance with the reaction sequence 1.



and





5

Sequence 1


An example of reaction sequence 1 is reaction sequence 2

10



Sequence 2


15 A further reaction sequence is one which uses an acetal



20 Sequence 3

A theoretical example of reaction sequence 3 is reaction sequence 4 which uses dimethoxymethane

25



Sequence 4

30 The use of dimethoxymethane thus theoretically gives an anhydrous system which avoids the difficulty of subsequent water separation and/or subsequent product hydrolysis. In addition, the use of dimethoxymethane avoids the use of

free formaldehyde but nevertheless acts in a general sense as a source of formaldehyde. The absence of water and free formaldehyde could greatly simplify the separation of MMA from the product stream.

5

However, in practice, Sequence 4 is problematic because methanol dehydrates to dimethyl ether and water. In addition, dimethoxymethane decomposes under catalytic conditions to dimethylether and formaldehyde. Any water
10 formed in these reactions can hydrolyse the ester feedstock or product to its corresponding acid which may be undesirable.

US4560790 describes the production of α , β unsaturated
15 carboxylic acids and esters by the condensation of methylal(dimethoxymethane) with a carboxylic acid or ester using a catalyst of general formula $M^1/M^2/P/O$ wherein M^1 is a group IIb metal, preferably aluminium, and M^2 is a group IVb metal, preferably silicon.

20

As mentioned above, a known production method for MMA is the catalytic conversion of methyl propionate (MEP) to MMA using formaldehyde. A suitable catalyst for this is a caesium catalyst on a support, for instance, silica.

25

US4118588 discloses the production of methyl methacrylate and methacrylic acid by reacting propionic acid or methyl propionate with dimethoxymethane in the presence of catalysts based on the phosphates and/or silicates of
30 magnesium, calcium, aluminium, zirconium, thorium and/or titanium and also in the presence of 0 to 0.5 moles of water per mole of the acetal. The preferred phosphates are aluminium, zirconium, thorium and titanium. The catalysts

generally include an oxide modifier to improve the catalytic activity. Magnesium phosphate is not exemplified and calcium phosphate is not exemplified alone but one example with an oxide modifier is provided. The results
5 are poor compared with the other phosphates, particularly aluminium.

Gupta et al in the Beilstein Journal of Organic Chemistry 2009, 5, No. 68 disclose the Knoevenagel condensation
10 between aromatic aldehydes and malononitrile, ethyl cyanoacetate or malonic acid with hydroxyapatite supported caesium carbonate in water. However, the condensation with malonic acid resulted in decarboxylation.

15 Calcium hydroxyapatite exists in a number of crystalline forms. In addition, amorphous precursors of Hydroxyapatite, with calcium: phosphorus ratios which are similar to those for crystalline forms are disclosed. These can convert to crystalline Hydroxyapatite either by
20 a physical or chemical treatment. The crystalline forms are generally divided into two types:- rods and plates but crystalline nano-spheres are also known. These three crystal forms are well documented in the scientific literature. The typical natural rod-like and plate-like
25 crystal forms of hydroxyapatite are disclosed in many documents for example in J Mater Chem 2004, 14, 2277, Rosanna Gonzalez-McQuire et al; Particuology 2009, 7, 466, Padmanabhan et al; Chemical Physics Letters 2004, 396, 429, Liu et al; Biomaterials 2007, 28, 2275, Chen et al;
30 and Journal of the Japan Petroleum Institute 2009, 52, 51, Tsuchida et al.

Hydroxyapatite in the rod-like crystal form may develop structures such as bowknot-like or flower-like structures (Chemical Physics Letters 2004, 396, 429 by Liu).

5 The conditions for producing the various crystal forms of calcium hydroxyapatite are also well documented(J Mater Chem 2004, 14, 2277, Rosanna Gonzalez-McQuire et al; Particuology 2009, 7, 466, Padmanabhan et al; Chemical Physics Letters 2004, 396, 429, Liu et al; Biomaterials
10 2007, 28, 2275, Chen et al; Journal of the Japan Petroleum Institute 2009, 52, 51, Tsuchida et al; and J Phys Chem B 2007, 111, 13410, Tao et al). In addition, conversion of nano-spheres into rod-like and sheet-like structures has been disclosed by Tao et al (J Phys Chem B
15 2007, 111, 13410).

Specifically, methods for producing hydroxyapatite rods are well documented in the literature. Hydroxyapatite rods have been successfully synthesized using hydrothermal
20 (Zhang et al., Journal of Crystal Growth, 2007, 308, 133-140,), wet chemical (Materials Chemistry and Physics, 2004, 86, 69-73, Liu et al), ultrasonic spray pyrolysis (Materials Science and Engineering A, 2007, 449-451,821-824, An et al) and sol-gel routes (Particuology 2009, 7,
25 466, Padmanabhan et al).

Most of the interest in the natural crystal forms of hydroxyapatite relates to its use or application in the study of biomedical applications due to its similarity to
30 human bone. Few of the studies of morphological effects relate to industrial catalytic applications of hydroxyapatite.

Crystalline spheres or nano-spheres or amorphous calcium phosphates with calcium:phosphorus ratios similar to crystalline hydroxapatites in the form of spheres and nano-spheres are also well documented in the literature and are generally favoured by manufacturers (J Phys Chem B 2007, 111, 13410 Tao et al). Sometimes a crystalline core is encapsulated by an amorphous shell to create spheres. However, amorphous spheres can form initially followed by subsequent crystallisation as disclosed by Kandori et al (Polyhedron 2009, 28, 3036). Catalytic applications of hydroxyapatite are known but no mention of crystallinity or particular crystal forms is disclosed therein. Due to the wide availability of nano-spherical amorphous precursors or crystal forms of hydroxyapatite it can be assumed that the catalytic applications relate to this common amorphous or nano-spherical form unless otherwise mentioned.

Surprisingly, it has now been found that particular metal phosphates of a particular crystal form are remarkably selective catalysts for the production of α , β ethylenically unsaturated carboxylic acid or esters by condensation of the corresponding acid or ester with a methylene source such as formaldehyde or dimethoxymethane providing high selectivity and low dimethylether (DME) production. In particular, the catalysts are particularly suited to the production of α , β ethylenically unsaturated carboxylic esters because they produce little water in such reactions.

30

According to a first aspect of the present invention there is provided a method of producing an ethylenically unsaturated carboxylic acid or ester, preferably an α , β

ethylenically unsaturated carboxylic acid or ester, comprising the steps of contacting formaldehyde or a suitable source thereof with a carboxylic acid or ester in the presence of a catalyst and optionally in the presence
5 of an alcohol, wherein the catalyst comprises group II metal phosphate crystals having rod or needle like morphology or a suitable source thereof.

Suitable examples of phosphates in accordance with the
10 present invention include hydroxyapatite, pyrophosphate, hydroxyphosphate, PO_4^{2-} phosphate and mixtures thereof, more preferably, hydroxyapatite, pyrophosphate and mixtures thereof.

15 By the term "a suitable source thereof" in relation to the phosphate crystals is meant that the morphology may be formed in situ from the phosphate source under reaction conditions. Therefore, one phosphate may act as the source of another. For instance, the group II pyrophosphates may
20 form the group II hydroxyapatites under reaction conditions and thus the pyrophosphate is a suitable source of the hydroxyapatite.

By the term "a suitable source thereof" in relation to
25 formaldehyde is meant that the free formaldehyde may either form in situ from the source under reaction conditions or that the source may act as the equivalent of free formaldehyde under reaction conditions, for example it may form the same reactive intermediate as formaldehyde
30 so that the equivalent reaction takes place.

The references to a rod like crystal morphology of metal phosphates is self explanatory to the skilled person but

in case of doubt may be taken to indicate a crystal with preferential growth in one key dimension (the z axis) and a substantially lesser growth in the second and third dimension (the x and y axes). More specifically, a rod
5 like crystal has a length, a width and a thickness. The z axis can be defined as the length. The x and y axes can be defined interchangeably as the width and thickness. The thickness to width ratio may be unequal. Alternatively the width : thickness ratio may be substantially equal, for
10 example it may be between 1:2 and 2:1, more typically between 2:3 and 3:2 and most typically between 3:4 and 4:3. In any case, the thickness and width will be less than the length; wherein an aspect ratio of the length (z axis): thickness and/or width (x and y axes) is typically
15 >2, more typically, >5, most typically, >10.

The rod like shape as defined in the present invention is intended to cover any crystal that has the above dimensions and therefore has the crystal habit or
20 appearance, macroscopically or microscopically, of being in an elongated member form with likeness to a rod. Therefore, rod like shape covers any of the official crystal forms capable of a rod like crystal habit i.e. hexagonal, orthorhombic, tetragonal, monoclinic, triclinic
25 or cubic. Preferably, the crystal form of the rod like crystals of the present invention is hexagonal.

Preferably, the group II metal of the phosphate of the invention may be a mixture of group II metals but is
30 preferably selected from Ca, Sr or Ba or mixtures thereof, more preferably, Ca or Sr, especially, Ca. Particularly preferred catalysts are strontium pyrophosphate, strontium hydroxyapatite, barium hydroxyapatite and calcium

hydroxyapatite which display rod like morphology in their crystal form, more preferred are strontium hydroxyapatite, barium hydroxyapatite and calcium hydroxyapatite, most preferred are strontium hydroxyapatite and calcium
5 hydroxyapatite. The group II metal magnesium is more typically used as a doping metal with one or more of Ca, Sr or Ba in the phosphates of the present invention.

Preferably, the catalyst is at least 50% w/w metal
10 phosphate, more preferably, at least 70% metal phosphate, most preferably, at least 80% metal phosphate. The metal phosphate has a significant crystalline metal phosphate fraction but may also include amorphous material. Known crystalline forms of the metal phosphates are rod/needle
15 like, plate like or crystalline spheres. The inventors have surprisingly found that crystalline metal phosphates with at least some rod/needle like crystals have surprisingly high selectivity in the present invention.

20 The crystal morphology of the crystalline metal phosphate may be determined by techniques known to those skilled in the art, for example by transmission electron microscopy (TEM) or scanning electron microscopy (SEM), or from the relative intensities of XRD peaks by comparison with known
25 morphological variants of the crystalline metal phosphates. Preferably, rod/needle like crystals are on average the dominant crystalline form numerically in the phosphate. Preferably, rod/needle like crystals are on average the dominant crystalline form by amount of average
30 TEM image area covered in the phosphate. By dominant is meant that the crystalline form is the largest group of crystals. However, it is not necessary for the rod or needle like morphology to be the dominant crystalline form

for the invention to be effective. Even a metal phosphate with a minority of the crystals in the rod or needle like form will be still effective as a catalyst. Accordingly, the group II metal phosphate crystals having the rod or
5 needle like morphology or suitable source thereof need only be present or become present at a level that is effective to catalyse the reaction with sufficient selectivity such as those selectivities set out below.

10 Preferably, the selectivity of the reaction to ethylenically unsaturated carboxylic acid or ester, preferably α , β ethylenically unsaturated carboxylic acid or ester product, especially (alk)acrylic acid or alkyl (alk)acrylate product is at least 40 mole %, more
15 preferably, at least 60 mole %, most preferably, at least 70 mole %, especially, at least 80 or 90 mole %. Typical selectivities as set out above are in the range 45-100 mole%, more preferably, 65-100 mole%, most preferably, 75-100 mole%, especially, 85 or 90-100 mole%. The mole% may
20 be determined by gas chromatography. Selectivity is based on mole % of total product converted from the starting carboxylic acid or ester. For example, if 100g methyl propionate reacts to produce 90g of methyl propionate and 10g of propionate derived product of which 9g is methyl
25 methacrylate then the reaction is 90% selective to methyl methacrylate by weight which may be converted to mole % selectivity using the relevant molecular weights to determine moles methyl propionate converted to product and moles of methyl methacrylate produced and calculating the
30 mole % of methyl methacrylate therefrom. Similarly, the same analysis can be carried out for other components such as methacrylic acid. A suitable gas chromatography device is a Shimadzu GC GC2010, equipped with a RTX1701 column

(supplied by Thames Restek UK Ltd) & a Flame Ionization Detector (FID).

Reactor feed compositions and samples of the condensed
5 flow exiting the catalytic reactor may all be analysed by
gas chromatography. A suitable device is the Shimadzu GC
detailed above. For each analysis, the resultant
chromatograph may be processed using Shimadzu's "GC
10 Solutions" software to obtain peak areas for individual
components. The FID response factors for the individual
components obtained using standards are applied to convert
peak areas, first into wt%, and then into mole%, of
detectable material in the sample.

15 Water content in the product of the catalytic reaction may
be measured by a Karl-Fischer titration (Mettler Toledo
DL38, with a probe DM143-SC, Hydranal Working Medium K and
Composite K).

20 Preferably, the rod like crystals are in a sufficiently
open arrangement to provide access to their surfaces to
effect sufficient catalysis. In a congealed mass of
crystals the surface area of the rod like crystals
available for catalysis may be reduced thus reducing
25 although not removing catalytic effectiveness.
Accordingly, the phosphate crystals of the invention are
preferably, substantially non-agglomerated or non-
congealed.

30 Preferably, at least 10% mol/mol of the total metal
phosphate in the catalyst is in a crystalline form, more
preferably, at least 30% mol/mol, most preferably, at
least 50% mol/mol. Typically, amorphous material (or

fraction of crystalline phase) can be estimated based on XRD results from the equation :

$$X_c = (1 - v_{112}/300) / I_{300}$$

5

where I_{300} is the intensity of the (3 0 0) diffraction peak and $v_{112}/300$ is the intensity of the hollow between the (1 1 2) and (3 0 0) diffraction peaks; X_c is the degree of crystallinity.

10

Generally, the crystal size of the metal phosphate crystals on the z axis is in the range $0.01-10^4$, more preferably, $0.1-10^4$ nm, most preferably, $0.1-10^3$ nm i.e. the crystals of the invention are typically nano-crystals. In particular, the rods are generally $0.001-10^3$ nm wide, more preferably, $0.01-10^3$ nm wide, most preferably, $0.1-10^2$ nm wide or thick and preferably have the aspect ratios defined herein. In preferred embodiments, the metal phosphate crystals on the z and x or y axis are in the respective ranges 1-5000nm and 0.1 to 500nm, more preferably, 5- 1000nm and 0.5 to 100nm, most preferably, 10-500nm and 1 - 50nm. Accordingly, in this context, the morphology of the crystals of the invention may be termed nano-rods.

25

Advantageously, the use of metal phosphate catalyst in the process of the invention also results in surprisingly low levels of dimethyl ether in the product stream whether the formaldehydic component of the vaporised reactor feed composition is based on formaldehyde or dimethoxymethane.

30

It has also been found that the catalyst of the invention has increased effectiveness when the surface layer of the

crystals is depleted below the optimum M:P ratio for hydroxyapatite i.e. below 1.67. Crystal surface M:P ratios of between 1.30 and 1.55 have been found to be particularly effective. By surface ratio herein we refer to the ratio as determined by X-ray photoelectron spectroscopy (XPS). However, it has also been found that the use of low M:P pre-cursor ratios can result in final crystals with increased surface M:P ratios above the bulk. Bulk crystal M:P ratios in the range 1-1.3 can result in increased surface M:P ratios correspondingly higher than those found in the bulk. Therefore, it may be that increased catalytic effectiveness is found as a result of a favoured metal phosphate surface arrangement. Typically, the M:P surface ratio, particularly that for Ca:P is in the range 1.30-1.55. This may be a metal hydroxyapatite structure depleted in metal.

It is possible that a particularly preferred metal hydroxyapatite formula of


20



is therefore highly catalytically active with a preferred ratio of M:P of 1.5, wherein the metal is a group II metal, more preferably, Ca, Sr or Ba, most preferably, Ca or Sr, especially, Ca or mixtures thereof.

The general formula of metal hydroxyapatite (HAP) in accordance with the invention may be given as formula I

30



wherein M represents a group II metal, preferably, Ca, Sr or Ba or mixtures thereof, more preferably Ca or Sr or mixtures thereof, and wherein X is 0-1.

5

The general formula of metal pyrophosphate in accordance with the invention may be given as formula II



10

wherein M represents a group II metal, preferably, Ca, Sr or Ba or mixtures thereof, more preferably, Ca or Sr or mixtures thereof.

15 As will be appreciated, the M:P mole ratio in a pure metal phosphate can be varied for example around the optimum ratio of 5:3 for metal hydroxyapatite and 1:1 for metal pyrophosphate. The metal hydroxyapatite is typically varied to be a metal deficient hydroxyapatite whereas the
20 metal pyrophosphate may be varied to be metal rich. It is possible for the M:P mole ratio to vary between 0.8-1.8 but typical surface M:P ranges are 1.00-1.55, especially, 1.10-1.50, more especially, 1.20-1.50 as determined by XPS whereas bulk M:P mole ratios vary between 0.8-1.8, more
25 typically, 1.00-1.70, as determined by X-Ray Fluorescence Spectrometry (XRF). A suitable instrument for determining surface M:P ratios by XPS is a Kratos "Axis Ultra" X-ray Photoelectron Spectrometer. A suitable instrument for determining bulk M:P ratios by XRF is an Oxford
30 Instruments X-Supreme 8000 which is based on Energy Dispersive X Ray Fluorescence measurements (EDXRF).

Varying M:P ratios in the final crystals can be achieved by varying precursor M:P ratios and/or in the case of a wet production method, the solution pH and/or solution temperatures.

5

Generally, production of the rod or needle like morphology of the invention is achieved by appropriate methods known to the skilled person as already set out above.

- 10 A preferred production method for production of hydroxyapatite and pyrophosphate rod or needle like crystals according to the invention uses a simple wet method of combining the group II metal nitrate and diammonium hydrogenphosphate as metal and phosphorus
- 15 precursors respectively in aqueous solution to form a precipitate. The combination of the nitrate and phosphate typically takes place between 20 and 115°C. The pH of the suspension during production is preferably kept between 4.5 and 13. Continuous stirring may maintain the product
- 20 in suspension. After aging, the product is preferably dried and calcined at different temperatures ranging from 300 to 700°C. If more than one group II metal is present or if other metals are present the water-soluble metal salt (preferably nitrate) may be dissolved into the same
- 25 solution as the first group II nitrate.

Other preferred methods include aqueous recrystallisation by forming the crystals on a substrate surface under the

30 same temperature and pH conditions as the simple wet method above. Heating the catalyst precursors in steam (Steaming) at for example 120°C with pH10 aqueous ammonia, or even under reaction conditions of 100 - 400°C is also

possible. Possible reagents for steaming with aqueous ammonia include a wide range of calcium phosphate compounds, preferably with Ca:P stoichiometry $1 \leq x \leq 1.5$, such as dicalcium phosphate dihydrate (DCPD) or tricalcium phosphate (TCP).

Still further techniques include thermolysis, in a furnace at $<700^{\circ}\text{C}$. For preparation by thermolysis, a physical mixture of thermally unstable calcium and phosphorus compounds (e.g. calcium nitrate, calcium hydroxide, diammonium hydrogen phosphate, phosphoric acid) is heated in a flow of air at temperatures up to 700°C .

The crystalline form of the HAP may be determined by TEM or XRD. Preferably, it is determined by TEM inspection and optionally confirmed by XRD. The absence or presence of crystallinity is preferably determined by XRD. A suitable instrument for XRD analysis is the Siemens Bruker D5000 Diffractometer D6. A suitable instrument for TEM analysis is a Philips CM12 Transmission Electron Microscope.

Crystalline HAP has characteristic XRD peaks at $2\theta^{\circ}$ 25.9 (002), 31.9 (211), 32.3 (112) and 33.0 (300), all $\pm 0.2^{\circ}$

According to a second aspect of the present invention there is provided a catalyst system comprising a crystalline metal phosphate catalyst and a catalyst support wherein the metal phosphate has rod/needle like morphology.

Advantageously, the rod/needle like morphology provides a surprisingly high selectivity for an ethylenically unsaturated acid or ester product in a catalysed reaction according to the first aspect of the present invention.

5

The rod/needle like crystal morphology of metal phosphates is self explanatory to the skilled person but in case of doubt may be taken to indicate a crystal with preferential growth along the z-axis. More specifically, a rod/needle
10 like crystal has a length, a width and a thickness wherein the width and thickness ratio is between 1:2 and 2:1, more typically between 2:3 and 3:2 and most typically between 3:4 and 4:3. In any case, the thickness and width will always be far less than the length; wherein an aspect
15 ratio of the length (z axis): thickness and/or width (x and y axes) is typically >2, more typically, >3, most typically, >5, especially > 10.

Optionally, the catalytic performance and/or the level of
20 rod/needle like morphology can be modified by changes applied to the catalyst synthesis conditions such as pH, temperature, pressure, M:P ratio and through doping with other elements, especially metals.

25 Typically, the catalyst synthesis pH may be from 4-13, more typically, from 4.5-12, most typically, from 5-11.5, especially, 6.5-11.5.

30 The wet synthesis solution temperature is not particularly critical and may be from 0 - 150°C, typically, from 10-130°C, more typically, from 20-125°C.

The pressure of reaction is also not critical and the catalyst can be prepared at reduced or high pressure. Typically, however, the catalyst is synthesised at or around atmospheric pressure.

5

Suitable doping elements may be present in the catalyst at a level up to 20 mol % of the metal M. Suitable doping metal cations are Cs, K, Rb, Na, Li, Zn, Ti, Si, Ln, Ce, Eu, Mg(if not used as a group II metal), Ba(if not used as a group II metal), Pb, Cd, Ag, Co, Cu, Ni and Zr. Preferred dopants are group I alkali metals and group II alkaline earth metals from the above list, more preferably, group I metals, especially Cs.

15 The doping cations may replace Ca, Sr and/or Ba in the above formulas.


Suitable doping anions may be present at a level of up to 20 mol % phosphate. Suitable doping anions are carbonate, chloride and fluoride. These may be assumed to partially replace the group II metal or phosphorus or hydroxide in the formulas herein as appropriate.

25 Preferably, the carboxylic acid or ester reactant of the present invention is of formula $R^3-CH_2-COOR^4$ wherein R^4 is either hydrogen or an alkyl group and R^3 is either hydrogen, an alkyl or aryl group.

Formaldehyde and Sources Thereof

30

A suitable source of formaldehyde may be a compound of formula I



wherein R^5 and R^6 are independently selected from C_1 - C_{12} hydrocarbons or H, X is O, n is an integer from 1 to 100, and m is 1.

- 5 Preferably, R^5 and R^6 are independently selected from C_1 - C_{12} alkyl, alkenyl or aryl as defined herein, or H, more preferably, C_1 - C_{10} alkyl, or H, most preferably, C_1 - C_6 alkyl or H, especially, methyl or H. Preferably, n is an integer from 1 to 10, more preferably 1 to 5, especially, 1-3.
- 10 However, other sources of formaldehyde may be used including trioxane.

Therefore, a suitable source of formaldehyde includes any equilibrium composition which may provide a source of
 15 formaldehyde. Examples of such include but are not restricted to dimethoxymethane, trioxane, polyoxymethylenes $\text{R}^1\text{-O-(CH}_2\text{-O)}_i\text{-R}^2$ wherein R^1 and/or R^2 are alkyl groups or hydrogen, $i=1$ to 100, paraformaldehyde, formalin (formaldehyde, methanol, water) and other
 20 equilibrium compositions such as a mixture of formaldehyde, methanol and methyl propionate.

Typically, the polyoxymethylenes are higher formals or hemiformals of formaldehyde and methanol $\text{CH}_3\text{-O-(CH}_2\text{-O)}_i\text{-CH}_3$ ("formal-i") or $\text{CH}_3\text{-O-(CH}_2\text{-O)}_i\text{-H}$ ("hemiformal-i"),
 25 wherein $i=1$ to 100, preferably, 1-5, especially 1-3, or other polyoxymethylenes with at least one non methyl terminal group. Therefore, the source of formaldehyde may also be a polyoxymethylene of formula $\text{R}^{31}\text{-O-(CH}_2\text{-O)}_i\text{R}^{32}$,
 30 where R^{31} and R^{32} may be the same or different groups and

at least one is selected from a C₁-C₁₀ alkyl group, for instance R³¹ = isobutyl and R³² = methyl.

Preferably, the suitable source of formaldehyde is
5 selected from dimethoxymethane, higher hemiformals of formaldehyde and methanol, CH₃-O-(CH₂-O)_i-H where i=2, formalin or a mixture comprising formaldehyde, methanol and methyl propionate.

10 It is particularly advantageous that dimethoxymethane can be used as a source of formaldehyde in the present invention. Advantageously, this provides the possibility of reacting dimethoxymethane with methyl propionate to form MMA and methanol without the production of water.
15 This provides a potentially anhydrous system i.e. a system with reduced water side reactions and separation requirements than one using other sources of formaldehyde which contain or generate water. In addition, dimethoxymethane is stable, unlike other sources of
20 formaldehyde which require water and methanol which then need to be taken into account in subsequent reaction and product separation. A further advantage of the present invention is the low level of decomposition in the present invention of dimethoxymethane to dimethylether and
25 formaldehyde.

Preferably, by the term formalin is meant a mixture of formaldehyde:methanol:water in the ratio 25 to 65%: 0.01 to 25%: 25 to 70% by weight. More preferably, by the term
30 formalin is meant a mixture of formaldehyde:methanol:water in the ratio 30 to 60%: 0.03 to 20%: 35 to 60% by weight. Most preferably, by the term formalin is meant a mixture

of formaldehyde:methanol:water in the ratio 35 to 55%:
0.05 to 18%: 42 to 53% by weight.

Preferably, the mixture comprising formaldehyde, methanol
5 and methyl propionate contains less than 5% water by
weight. More preferably, the mixture comprising
formaldehyde, methanol and methyl propionate contains less
than 1% water by weight. Most preferably, the mixture
comprising formaldehyde, methanol and methyl propionate
10 contains 0.1 to 0.5% water by weight.

Preferably, the ethylenically unsaturated acid or ester
produced by the process of the invention is selected from
methacrylic acid, acrylic acid, methyl methacrylate, ethyl
15 acrylate or butyl acrylate, more preferably, it is an
ethylenically unsaturated ester, most preferably, methyl
methacrylate.

The process of the invention is particularly suitable for
20 the production of acrylic, alkacrylic, 2-butenic,
cyclohexenoic, maleic, itaconic and fumaric acids and
their alkyl esters, and also methylene substituted
lactones. Suitable, alkacrylic acids and their esters are
(C₀₋₈alk)acrylic acid or alkyl (C₀₋₈alk)acrylates, typically
25 from the reaction of the corresponding alkanic acid or
ester thereof with a methylene source such as formaldehyde
in the presence of the catalyst, preferably the production
of methacrylic acid or especially methyl methacrylate (MMA)
from propanoic acid or methyl propionate respectively.
30 Suitable methylene substituted lactones include 2-
methylene valerolactone and 2-methylene butyrolactone from
valerolactone and butyrolactone respectively.

The reaction of the present invention may be a batch or continuous reaction.

The term "alkyl" when used herein, means, unless otherwise specified, C₁ to C₁₂ alkyl and includes methyl, ethyl, ethenyl, propyl, propenyl butyl, butenyl, pentyl, pentenyl, hexyl, hexenyl and heptyl groups, preferably, the alkyl groups are selected from methyl, ethyl, propyl, butyl, pentyl and hexyl, more preferably, methyl. Unless otherwise specified, alkyl groups may, when there is a sufficient number of carbon atoms, be linear or branched, be cyclic, acyclic or part cyclic/acyclic, be unsubstituted, substituted or terminated by one or more substituents selected from halo, cyano, nitro, -OR¹⁹, -OC(O)R²⁰, -C(O)R²¹, -C(O)OR²², -NR²³R²⁴, -C(O)NR²⁵R²⁶, -SR²⁹, -C(O)SR³⁰, -C(S)NR²⁷R²⁸, unsubstituted or substituted aryl, or unsubstituted or substituted Het, wherein R¹⁹ to R³⁰ here and generally herein each independently represent hydrogen, halo, unsubstituted or substituted aryl or unsubstituted or substituted alkyl, or, in the case of R²¹, halo, nitro, cyano and amino and/or be interrupted by one or more (preferably less than 4) oxygen, sulphur, silicon atoms, or by silano or dialkylsilcon groups, or mixtures thereof. Preferably, the alkyl groups are unsubstituted, preferably, linear and preferably, saturated.

The term "alkenyl" should be understood as "alkyl" above except at least one carbon carbon bond therein is unsaturated and accordingly the term relates to C₂ to C₁₂ alkenyl groups.

The term "alk" or the like should, in the absence of information to the contrary, be taken to be in accordance with the above definition of "alkyl" except "C₀ alk" means non-substituted with an alkyl.

5

The term "aryl" when used herein includes five-to-ten-membered, preferably five to eight membered, carbocyclic aromatic or pseudo aromatic groups, such as phenyl, cyclopentadienyl and indenyl anions and naphthyl, which groups may be unsubstituted or substituted with one or more substituents selected from unsubstituted or substituted aryl, alkyl (which group may itself be unsubstituted or substituted or terminated as defined herein), Het (which group may itself be unsubstituted or substituted or terminated as defined herein), halo, cyano, nitro, OR¹⁹, OC(O)R²⁰, C(O)R²¹, C(O)OR²², NR²³R²⁴, C(O)NR²⁵R²⁶, SR²⁹, C(O)SR³⁰ or C(S)NR²⁷R²⁸ wherein R¹⁹ to R³⁰ each independently represent hydrogen, unsubstituted or substituted aryl or alkyl (which alkyl group may itself be unsubstituted or substituted or terminated as defined herein), or, in the case of R²¹, halo, nitro, cyano or amino.

The term "halo" when used herein means a chloro, bromo, iodo or fluoro group, preferably, chloro or fluoro.

The term "Het", when used herein, includes four- to twelve-membered, preferably four- to ten-membered ring systems, which rings contain one or more heteroatoms selected from nitrogen, oxygen, sulfur and mixtures thereof, and which rings contain no, one or more double bonds or may be non-aromatic, partly aromatic or wholly aromatic in character. The ring systems may be monocyclic,

bicyclic or fused. Each "Het" group identified herein may be unsubstituted or substituted by one or more substituents selected from halo, cyano, nitro, oxo, alkyl (which alkyl group may itself be unsubstituted or substituted or terminated as defined herein) -OR¹⁹, -OC(O)R²⁰, -C(O)R²¹, -C(O)OR²², -N(R²³)R²⁴, -C(O)N(R²⁵)R²⁶, -SR²⁹, -C(O)SR³⁰ or -C(S)N(R²⁷)R²⁸ wherein R¹⁹ to R³⁰ each independently represent hydrogen, unsubstituted or substituted aryl or alkyl (which alkyl group itself may be unsubstituted or substituted or terminated as defined herein) or, in the case of R²¹, halo, nitro, amino or cyano. The term "Het" thus includes groups such as optionally substituted azetidiny, pyrrolidinyl, imidazolyl, indolyl, furanyl, oxazolyl, isoxazolyl, oxadiazolyl, thiazolyl, thiadiazolyl, triazolyl, oxatriazolyl, thiatriazolyl, pyridazinyl, morpholinyl, pyrimidinyl, pyrazinyl, quinolinyl, isoquinolinyl, piperidinyl, pyrazolyl and piperazinyl. Substitution at Het may be at a carbon atom of the Het ring or, where appropriate, at one or more of the heteroatoms.

"Het" groups may also be in the form of an N oxide.

Suitable optional alcohols for use in the catalysed reaction of the present invention may be selected from a C₁-C₃₀ alkanol, including aryl alcohols, which may be optionally substituted with one or more substituents selected from alkyl, aryl, Het, halo, cyano, nitro, OR¹⁹, OC(O)R²⁰, C(O)R²¹, C(O)OR²², NR²³R²⁴, C(O)NR²⁵R²⁶, C(S)NR²⁷R²⁸, SR²⁹ or C(O)SR³⁰ as defined herein. Highly preferred alkanols are C₁-C₈ alkanols such as methanol, ethanol, propanol, iso-propanol, iso-butanol, t-butyl alcohol, phenol, n-butanol and chlorocapryl alcohol, especially,

methanol. Although the monoalkanols are most preferred, poly-alkanols, preferably, selected from di-octa ols such as diols, triols, tetra-ols and sugars may also be utilised. Typically, such polyalkanols are selected from
5 1, 2-ethanediol, 1,3-propanediol, glycerol, 1,2,4 butanetriol, 2-(hydroxymethyl)-1,3-propanediol, 1,2,6 trihydroxyhexane, pentaerythritol, 1,1,1 tri(hydroxymethyl)ethane, nannose, sorbase, galactose and other sugars. Preferred sugars include sucrose, fructose
10 and glucose. Especially preferred alkanols are methanol and ethanol. The most preferred alkanol is methanol. The amount of alcohol is not critical. Generally, amounts are used in excess of the amount of substrate to be esterified. Thus the alcohol may serve as the reaction
15 solvent as well, although, if desired, separate or further solvents may also be used.

Typical conditions of temperature and pressure in the process of the first aspect of the invention are between
20 100°C and 400°C, more preferably, 200°C and 375°C, most preferably, 300°C and 360°C; between 0.001 MPa and 1 MPa, more preferably, 0.03 MPa and 0.5 MPa, most preferably, between 0.03 MPa and 0.3 MPa. Typical residence times for the reactants in the presence of the catalyst are between
25 0.1 and 300 secs, more preferably, 1-100 secs, most preferably, 2-30 secs, especially, 3-20 secs.

Advantageously, use of the catalyst of the present invention has been found to produce remarkably low levels
30 of unwanted side products in the reaction of formaldehyde or a suitable source thereof with a carboxylic acid or ester to produce an ethylenically unsaturated carboxylic acid or ester. In particular, remarkably low levels of

dimethyl ether (DME) are produced compared to conventional catalysts such as aluminium phosphate. In addition, the catalysts provide excellent selectivity and activity.

5 The amount of catalyst used in the process of the present invention is not necessarily critical and will be determined by the practicalities of the process in which it is employed. However, the amount of catalyst will generally be chosen to effect the optimum selectivity and
10 yield. Nevertheless, the skilled person will appreciate that the minimum amount of catalyst should be sufficient to bring about effective catalyst surface contact of the reactants during the contact time. In addition, the skilled person would appreciate that there would not
15 really be an upper limit to the amount of catalyst relative to the reactants but that in practice this may be governed again by the contact time required.

The relative amount of reagents in the process of the
20 invention can vary within wide limits but generally the mole ratio of formaldehyde or suitable source thereof to the carboxylic acid or ester is within the range of 20:1 to 1:20, more preferably, 5:1 to 1:15, The most preferred ratio will depend on the form of the formaldehyde and the
25 ability of the catalyst to liberate formaldehyde from the formaldehydic species. Thus highly reactive formaldehydic substances where one or both of R^{31} and R^{32} in $R^{31}O-(CH_2-O-)_iR^{32}$ is H require relatively low ratios, typically, in this case, the mole ratio of formaldehyde or suitable
30 source thereof to the carboxylic acid or ester is within the range of 1:1 to 1:9. Where neither of R^{31} and R^{32} is H, as for instance in $CH_3O-CH_2-OCH_3$, or in trioxane higher ratios are most preferred, typically, 3:1 to 1:3.

As mentioned above, due to the source of formaldehyde, water may also be present in the reaction mixture. Depending on the source of formaldehyde, it may be
5 necessary to remove some or all of the water therefrom prior to catalysis. Maintaining lower levels of water than that in the source of formaldehyde may be advantageous to the catalytic efficiency and/or subsequent purification of the products. Water at less than 10 mole % in the reactor
10 is preferred, more preferably, less than 5 mole %, most preferably, less than 2 mole %.

The molar ratio of alcohol to the acid or ester is typically within the range 20:1 to 1:20, preferably 10:1
15 to 1:10, most preferably 5:1 to 1:5, for example 1:1. However the most preferred ratio will depend on the amount of water fed to the catalyst in the reactants plus the amount produced by the reaction, so that the preferred molar ratio of the alcohol to the total water in the
20 reaction will be at least 1:1 and more preferably at least 3:1.

The reagents may be fed to the reactor independently or after prior mixing and the process of reaction may be
25 continuous or batch. Preferably, however, a continuous process is used.

Typically, the reaction takes place in the gas phase. Accordingly, suitable condensing equipment is generally
30 required to condense the product stream after reaction has taken place. Similarly, a vaporiser may be used to bring the reactants up to temperature prior to the catalyst bed.

Preferably, the metal phosphate of the invention forms 50 - 100 wt% of the catalyst, more preferably, 55-100wt%, most preferably, 60-100wt%, especially, 70-100wt%, more especially, 75-100wt%, most especially, 80-100wt% of the catalyst. The balance of the catalyst is made up of impurities, binders or inert materials. Generally, the metal phosphate forms about 80-90% of the catalyst. Included in the definition of metal phosphate is metal deficient phosphate having the M:P ratios defined herein.

10

When binder is used in the present invention it may form up to 50 wt% of the catalyst. Alternatively, the binder may be used in conjunction with a catalyst support to bind the catalyst to the support. In the latter case, the binder does not form part of the catalyst as such.

15

Suitable binders for the catalyst of the present invention will be known to those skilled in the art. Non-limiting examples of suitable binders include silica (including colloidal silica), silica-alumina, such as conventional silica-alumina, silica-coated alumina and alumina-coated silica, and alumina, such as (pseudo)boehmite, gibbsite, titania, titania-coated alumina, zirconia, cationic clays or anionic clays such as saponite, bentonite, kaolin, sepiolite or hydrotalcite or mixtures thereof. Preferred binders are silica, alumina and zirconia or mixtures thereof.

20

25

The metal phosphate particles can be embedded in the binder or vice versa. Generally, when used as part of the catalyst, the binder functions as an adhesive to hold the particles together. Preferably, the particles are homogeneously distributed within the binder or vice versa.

30

The presence of the binder generally leads to an increase in mechanical strength of the final catalyst.

The typical average surface area of the metal phosphate catalyst is in the range $2\text{-}1000\text{m}^2\text{g}^{-1}$, more preferably, $5\text{-}400\text{m}^2\text{g}^{-1}$, most preferably, $10\text{-}300\text{m}^2\text{g}^{-1}$ as measured by the B.E.T. multipoint method using a Micromeritics TriStar 3000 Surface Area and porosity Analyser. The reference material used for checking the instrument performance is a carbon black powder supplied by Micromeritics with a surface area of $30.6\text{m}^2/\text{g}$ ($\pm 0.75\text{m}^2/\text{g}$), part number 004-16833-00.

The typical average particle size of the catalyst particles is in the range $1\text{nm}\text{-}10000\text{nm}$ (10μ), more preferably, $5\text{nm} - 4000\text{nm}$ (4μ), most preferably, $10\text{nm} - 3000\text{nm}$ (3μ) as measured by a Malvern Zetasizer Nano S using dynamic light scattering and using NIST standards.

If the material is porous, it is preferably mesoporous with an average pore size of between 2 and 50nm . Pore size can be determined by mercury intrusion porosimetry using NIST standards.

The average pore volume of the catalyst particles may be less than $0.01\text{cm}^3/\text{g}$ but is generally in the range $0.01 - 5\text{cm}^3/\text{g}$ as measured by nitrogen adsorption. However, microporous catalysts are not the most preferred because they may inhibit movement of reagents through the catalyst and a more preferred average pore volume is between $0.3\text{-}1.2\text{cm}^3/\text{g}$ as measured by BET multipoint method using nitrogen adsorption according to ISO 15901-2:2006. The Micromeritics TriStar Surface Area and Porosity Analyser

is used to determine pore volume as in the case of surface area measurements and the same standards are employed.

In the case of a non supported catalyst, the metal
5 phosphate may be used directly in the form of a catalyst particles either free flowing or together with a suitable binder to create a solid of the desired shape and/or size. The particles may be of any suitable size and therefore also in the form of powder, granules or beads either with
10 or without binder. Typically, the catalyst is used in the form of a fixed bed and for this purpose may be used alone or on a support and in the latter case may include a suitable catalytic binder to bind it to the support.

15 As mentioned above, the catalyst may be used on a support. In this case, the metal phosphate catalyst may form a suitable surface coating on a suitable support for a catalyst.

20 For the purposes of the present invention, the support does not form part of the catalyst.

The metal phosphates of the present invention are either unsupported or supported on a suitable support, for
25 example, alumina, silica, silicon nitride, silicon carbide, colloidal silica, titania or aluminium phosphate.

It will be understood by the skilled person that a catalyst of the invention may be added to a support by any
30 suitable means. The catalyst may be fixed, preferably by calcination, onto a suitable support after deposition of the compound onto the support using a suitable salt in a suitable solvent and subsequent drying of the surface

coated support. Alternatively, the catalyst or suitable catalyst salt precursors may be co-precipitated with the support or suitable support precursors such as a silica sol from a suitable solvent. Preferably, an oxide support
5 is used, more preferably, an oxide support as mentioned herein.

It is also possible to use the catalyst of the present invention in a mixture or admixture with another catalyst
10 according to the present invention or otherwise with or without a suitable binder.

Generally, the metal phosphate of the present invention is a neutral molecule and therefore the negatively charged
15 phosphate anions and optionally, hydroxide and any other non-metals balance the positively charged metals present.

The metal phosphate compound may be supported on a suitable support such as silica, silicon nitride, silicon
20 carbide, colloidal silica, alumina, titania or aluminium phosphate. The support may or may not be an alkali metal doped support. If the support is alkali metal doped, the alkali metal doping agent may be selected from one or more of caesium, potassium, sodium, or lithium, preferably,
25 caesium or potassium, more preferably, caesium. Alternatively, the metal phosphate may itself be doped with any one or more of the above mentioned doping metals.

Preferably, when a separate support for the catalyst of
30 the first or second aspect is used, the weight ratio of catalyst:support is in the range 10:1 to 1:50, more preferably, 1:1 to 1:20, most preferably, 2:3 to 1:10.

Advantageously, unsaturated ester selectivity is increased by doping cations having a low charge to radius ratio; thus caesium was found to be more selective than lithium. Preferably, therefore, if used, the doping metal cation is
5 caesium, rubidium and/or potassium, more preferably, rubidium and/or caesium, most preferably caesium.

Embodiments of the invention will now be described with reference to the following non-limiting examples and
10 figures and by way of illustration only in which:-
Figure 1 shows the surface and bulk M:P ratios for a selection of samples;
Figure 2 shows the TEM Image of Example 1 crystals;
Figure 3 shows the TEM Image of Comparative Example 4;
15 Figure 4 shows the TEM image of example 3 crystals;
Figure 5 shows the TEM image of example 6 crystals;
Figure 6 shows the TEM image of example 8 crystals;
Figure 7 compares crystallite morphology by XRD for several examples and comparative examples; and
20 Figure 8 shows a TEM Image of Example 11 at 100nm scale showing the presence of nano-rods.

Experimental

Analytical Methods

25

XRD Experimental

The samples were prepared as dry compressed powder thin layer specimens mounted on single silicon crystal discs.
30 The following instrument and settings were used.

Instrument Siemens Bruker D5000 Diffractometer D6

X-ray Tube Cu LFF

- | | | |
|----|---|--|
| | Radiation | Ca K α |
| | Generator Voltage | 40 kV |
| | Generator Current | 40 mA |
| | Diffraction Geometry | Reflection Bragg Brentano |
| 5 | Variable Divergence Slit-12mm irradiated length | |
| | Variable Antiscatter Slit-12mm irradiated length | |
| | Receiving Slit | 0.2mm |
| | Primary soller slit | 2.3° |
| | Detector | Si/Li Energy dispersive (monochromating) |
| 10 | Monochromator | Detector (K α) |
| | Step Size | 0.02° |
| | Time per step | 3 seconds ("Sr ₂ P ₂ O ₇ pH7_1.67" = 6 seconds) |
| | Scan start angle | 1.5 |
| | Scan finish angle | 90 |
| 15 | Specimen format | Bulk |
| | Specimen loading | Compressed powder on silicon discs |
| | Specimen spinning | Yes |
| | Temperature | Ambient |
| 20 | Data output is in the form of a diffractogram, showing reflection intensity (counts per second) vs. angle 2 θ °. Crystalline phase identification is carried out by comparison to reference ICDD (formerly JCPDS) diffractograms. Peak intensity or peak broadening analysis | |
| 25 | is performed to quantify morphological parameters for a crystalline phase. | |

XRF Experimental

- 30 Powder samples were ground and sieved to achieve particle size <100 μ m (mesh). Approximately 1 gram of powder was lightly compacted into a primary sample cup with a thin film transmission base. The primary cup was held within

the instrument by a secondary safety cup also with a thin film transmission base. The following instrument and conditions were used.

5	Instrument	Oxford Instruments X-Supreme 8000 (EDXRF)
	X-ray source	Tungsten
	Source Energy	6 keV
	Tube Current	10 μ A
10	Chamber purge gas	Helium
	Detector	Silicon Drift proportional detector (SDD)
	Primary cup base	Poly4 film (4 μ m thick)
	Secondary cup base	Poly4 film (4 μ m thick)
15	Specimen spinning	Yes
	Temperature	Ambient
	Repeat scans	3

Ca $K\alpha$ and P $K\alpha$ fluorescence intensities (counts per second) were recorded. The ratio of peak intensities was converted to give a Ca:P ratio for the material, using a calibration scale obtained from the Ca $K\alpha$ and P $K\alpha$ signals for stoichiometric reference materials.

25 XPS Experimental

A microspatula of the powder sample was placed onto a piece of silicone-free tape attached to the instrument sample holder, and the loose powder gently flattened with the microspatula tip. The following instrument and settings were used.

Instrument Kratos "Axis Ultra" X-ray Photoelectron Spectrometer

X-ray source Al K α

Monochromator Yes

5 Pass Energy- 160eV(survey scan), 40eV&10eV(high-res scan)

Spot size Ellipitic area, ~300 μm x ~700 μm .

Repeat scans 2

Established Electron Spectroscopy for Chemical Analysis
10 (ESCA) methods were utilised for qualification of the surface composition by elemental atomic percentage. Signal depth for oxide materials was ca. 3-5nm, and the detection limit was about 1 atom in 1000 (i.e. 0.1 atom%, or 1000ppm). Ca:P ratios were initially calculated from the
15 experimental atomic percentages, and subsequently corrected for the presence of surface carbonaceous species.

TEM Experimental

20

Powder samples of the materials were suspended in water and drops were applied to copper grids bearing Lacey carbon support films. After drying, these were examined in a Philips CM12 TEM at an accelerating voltage of 120kV.

25

Micrographs and electron diffraction patterns were collected at matching magnifications/tube-lengths. Selected regions were analysed using the associated NORAN Vantage EDX system. The variety of morphologies,
30 compositions and crystalline species observed were recorded as images. The following instrument and settings were used.

Instrument-Philips CM12 Transmission Electron Microscope
Accelerating Voltage 120kV

Two sets of experiments were run against various prepared
5 examples of the invention and comparative examples. The
first series of experiments were run using formaldehyde as
a feed stream and the second series were run using
dimethoxymethane as a feed stream. Analysis was carried
out by gas chromatography, formaldehyde titration and with
10 Karl Fischer apparatus. The analytical data were used to
calculate the yield and selectivity of MMA + MAA. The
selectivities in mole% relative to mole% MMA + MAA of
diethylketone (DEK), dimethyl ether (DME) and toluene by-
products are also tabulated in the catalyst test results
15 below.

A Formaldehyde feed

Table 1.

	Catalyst composition	Contact time [s]	MMA+MAA yield [%]	MAA selectivity [mole %]	MMA+MAA selectivity [mole %]	DME [mole%]	DEK [mole%]	Toluene [mole%]
Ex 1	Ca-HAp pH7_1.67	10.3	4.1	1.3	93.5	0.5	0.0036	0.00014
Ex 2	Ca-HAp pH9- 10_1.67	5.0	4.3	0.6	84.6	0.6	0.0040	0.00009
Ex 3	Ca-PO pH9- 10_1.67_120	11.4	3.3	0.8	92.1	0.6	0.0026	0.00009
Ex 4	Ca-HAp pH7_1.67_EtOH	7.1	2.8	3.7	93.7	3.1	0.0014	0.00018
Ex 5	Ca-HAp pH7_1.67_ 1%Cs	6.9	4.1	0.3	93.6	0.2	0.0014	0.00007
Comp Ex 1	AlPO ₃ TiO ₂ B_ urea	3.1	4.7	12.6	69.2	14.4	0.0609	0.00528
Comp Ex 2	AlPO	1.5	4.8	12.9	78.0	10.6	0.0457	0.00446
Comp Ex 3	Comm Ca-HAp 289396	7.0	0.2	0.1	72.3	0.2	0.0004	0.00005

Comp ex 4	Comm 677418	Ca-HAp	10.1	0.1	1.4	11.4	0.0021	0.0025	0.00000
--------------	----------------	--------	------	-----	-----	------	--------	--------	---------

Example 1

Preparative Example 1

23.6 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was adjusted to 7 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ dissolved in 50 ml of demineralised water at pH 7 was added dropwise to the solution of calcium nitrate at the temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 7 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight and calcined in air at 400 °C for 1 hr. BET surface area of the material was 44 m²/g. The sample was identified as a crystalline hydroxyapatite type by XRD analysis. Some amorphous material was found. TEM confirmed the presence of rod like crystal form.

Catalyst testing: 3 g of catalyst as prepared in preparative example 1 was placed in a stainless steel tubular reactor connected to a vaporiser. The reactor was heated to 350 °C and vaporiser to 300 °C. The mixture of 56.2 mole% of methyl propionate, 33.7 mole% of methanol, 9.6 mole% of formaldehyde and 0.5 mole% of water was passed through with the contact time indicated. The condensed reaction mixture was analysed by gas chromatography using a Shimadzu GC, equipped with a DB1701 column & a Flame Ionization Detector. For each analysis, the resultant chromatograph is processed using Shimadzu's

GCsolution software to obtain peak areas for individual components. FID response factors for the individual components are applied to convert peak areas, first into wt%, and then into mol%, of detectable material in the sample.

Selectivity with respect to MAA or MAA + MMA is calculated from the molar amount of the component produced (exit molar content, less feed molar content), as percentage of the molar amount of propionate converted to products.

Example 2

Preparative Example 2

23.6 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was adjusted to 9-10 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 9-10 was added dropwise to the solution of calcium nitrate at the temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 9-10 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight and calcined in air at 400 °C for 1 hr.

The preparative example 2 catalyst was tested as described in example 1.

Example 3

Preparative Example 3

23.6 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was adjusted to 9-10 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 9-10 was added dropwise to a boiling solution of the calcium nitrate while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete, then filtered and washed with demineralised water. After that it was dried at 110 °C overnight and then calcined in air at 400 °C for 1 hr. BET surface area of the material was 9 m²/g. The sample was identified as monetite and pyrophosphate by XRD analysis. TEM confirmed the presence of plate, rod, leaf and sphere like crystal forms.

The catalyst was tested as described in example 1.

Example 4

Preparative Example 4

23.6 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and 100 ml of ethanol mixture. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 100 ml of demineralised water was added dropwise to the solution of calcium nitrate at the temperature of 25 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred overnight after the dropwise addition and pH was maintained at 7 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight and calcined in air at 400 °C for 1 hr. BET surface area of the material was 73 m²/g.

The sample was identified as a crystalline hydroxyapatite type by XRD analysis. Some amorphous material was found. TEM confirmed the presence of rod like crystal form. The catalyst was tested as described in example 1.

5

Example 5

Preparative Example 5

3 g of the catalyst prepared as in preparative example 1 was impregnated with 1 wt% of caesium using caesium acetate in methanol and tested as described in example 1.

10

Comparative example 1

Preparative Comparative example 1

The catalyst was synthesised following the preparation method disclosed in US 4118588 patent in Example 4.

15

3 g of titanium dioxide TiO_2 (Aldrich catalogue number 634662), 2.3 g of aluminium phosphate (prepared as in comparative example 2) and 0.75 g of boric acid H_3BO_3 were mixed together. A paste was produced by addition of 0.25 g of urea in 5 ml of demineralised water. The paste was dried for 2 hrs at 120 °C and then heated for 4 hrs at 600 °C.

20

The catalyst was tested as described in example 1. Modest selectivity was observed but a high level of DME was found.

25

Comparative example 2

Preparative Comparative example 2

37.5 g of aluminium nitrate nonahydrate $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ and 13.2 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ were dissolved together in 160 ml of demineralised water acidified with nitric acid HNO_3 . Solution of ammonium

30

hydroxide was added until pH 7 was reached. Formed hydrogel was mixed for further 1 hr, after that it was filtered and washed with water. It was dried at 80 °C overnight and then calcined in air at 600 °C for 1 hr. BET surface area of the material was 181 m²/g.

The catalyst was tested as described in example 1. Modest selectivity was observed but a high level of DME was found.

10 Comparative example 3

Commercial Ca-hydroxyapatite was used from Aldrich with catalogue number of 289396. The sample was confirmed as a crystalline hydroxyapatite type by XRD analysis. Some amorphous material was found. TEM showed the presence of agglomerated irregular sphere like particles.

The catalyst was tested as described in example 1. The results are shown in table 1. Although selectivity was modest and DME was low the yield was very low indicating a high level of inactivity.

Comparative example 4

Commercial Ca-hydroxyapatite was used from Aldrich with catalogue number of 677418.

The samples were confirmed as crystalline hydroxyapatite type by XRD analysis. TEM showed evenly-shaped nanospheres, typically 50-100nm diameter (although with some individual spheres of 300-800nm diameter), with no evidence of any non-spherical morphology.

The catalyst was tested as described in example 1. The results are shown in table 1. The yield and selectivity were both very low.

5 **Table 2.**

Ex.	Catalyst composition	Contact time [s]	MMA+MAA yield [%]	MAA selectivity [%]	MMA+MAA selectivity [%]	DME [mole%]	DEK [mole%]	Toluene [mole%]
Ex 6	Ca-HAp pH11_1.67	1.2	1.6	0.2	80.0	0.1	0.0020	0.00015

Example 6

Preparative Example 6

23.6 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was adjusted to 11 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 11 was added dropwise to the solution of calcium nitrate at the temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 11 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight and calcined in air at 400 °C for 1 hr. BET surface area of the material was 96 m²/g.

The sample was identified as a crystalline hydroxyapatite type by XRD analysis, although the presence of some amorphous material was indicated. TEM showed highly crystalline nano-rod structures grouped in bundles of similar orientation.

The catalyst was tested as described in example 1. The results are shown in table 2.

Table 3

Ex.	Catalyst composition	Contact time [s]	MMA+MAA yield [%]	MAA selectivity [%]	MMA+MAA selectivity [%]	DME [mole%]	DEK [mole%]	Toluene [mole%]
Ex 7	Ca-HAp pH7_1.5	10.27	4.4	1.7	92.0	2.6	0.0020	0.00014
Ex 8	Ca-HAp pH7_1	3.0	1.6	1.6	92.3	1.2	0.0007	0.00015

Example 7

5 Preparative example 7

14.2 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was adjusted to 7 with ammonium hydroxide. 5.3 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 100 ml of demineralised water at pH 7 was added dropwise to the solution of calcium nitrate at the temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 7 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight followed by calcination in air at 400 °C for 1 hr. BET surface area of the material was 64 m²/g. The sample was identified as a crystalline hydroxyapatite type by XRD analysis. Some amorphous material was found.

The catalyst was tested as described in example 1.

25 Example 8

Preparative example 8

14.2 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was adjusted to 7 with ammonium hydroxide. 7.9 g of diammonium

hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 100 ml of demineralised water at pH 7 was added dropwise to the solution of calcium nitrate at the temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 7 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight followed by calcination in air at 400 °C for 1 hr. BET surface area of the material was 58 m²/g. The major phase was identified as a crystalline hydroxyapatite type by XRD analysis. A trace phase similar to calcium hydrogen phosphate CaHPO_4 was present. Some amorphous material was found. TEM showed the presence of rod and sheet like crystal forms.

The catalyst was tested as described in example 1. The results are shown in table 3.

20 Table 4

Ex.	Catalyst composition	Contact time [s]	MMA+MAA yield [%]	MAA selectivity [%]	MMA+MAA selectivity [%]	DME [mole%]	DEK [mole%]	Toluene [mole%]
Ex 9	Ca-HAp pH7_1.67_25	10.4	4.1	2.8	89.8	3.1	0.0017	0.00008
Ex 10	Ca-HAp pH11_1.00	9.8	4.8	4.0	91.4	4.7	0.0033	0.00011
Ex 11	Ca-PO pH5_1.67	15.6	4.4	1.4	94.6	0.42	0.002	0.00024
ex 12	Ca-PO pH5_1.00	6.9	3.1	1.4	90.1	1.8	0.0023	0.00008

Example 9

Preparative example 9

23.6 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was

adjusted to 7 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 7 was added dropwise to the solution of calcium nitrate at the temperature of 25 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 7 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight and calcined in air at 400 °C for 1 hr. TEM showed short crystalline nano-rods <100nm in length, and some amorphous material. The catalyst was tested as described in Example 1. The results are shown in Table 4.

Example 10

Preparative example 10

14.2 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was adjusted to 11 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 11 was added dropwise to the solution of calcium nitrate at the temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 11 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight and calcined in air at 400 °C for 1 hr. The sample was identified as a crystalline hydroxyapatite type by XRD analysis. Some amorphous

material was found. TEM showed densely-packed short crystalline nano-rods <100nm in length, and about 10nm in diameter. The catalyst was tested as described in Example 1. The results are shown in Table 4.

5

Example 11

Preparative Example 11.

23.6 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was adjusted to 5 with dilute aqueous nitric acid. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 5 was added dropwise to the solution of calcium nitrate at the temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 5 with dilute aqueous nitric acid throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight and calcined in air at 400 °C for 1 hr. TEM showed large flat structures, blade or sheet-like, greater than 1 micron in 2 of their dimensions. The edges of the flat structures were fractured into parallel nano-rods of high aspect ratio: greater than 100nm long, but less than 20nm diameter. It was identified by XRD that the sample is a combination of monetite CaHPO_4 and pyrophosphate $\text{Ca}_2\text{P}_2\text{O}_7$ phases probably masking an underlying HAP phase. The catalyst was tested as described in Example 1. The results are shown in Table 4.

30

Example 12

Preparative Example 12.

14.2 g of calcium nitrate tetrahydrate $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ was dissolved in 100 ml of demineralised water and pH was adjusted to 5 with dilute aqueous nitric acid. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 5 was added dropwise to the solution of calcium nitrate at the temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 5 with dilute aqueous nitric acid throughout. After that the suspension was filtered and washed with demineralised water. Then it was dried at 110 °C overnight and calcined in air at 400 °C for 1 hr. TEM showed non-uniform particles, predominantly as sheets, but also as rods enmeshed in amorphous material. XRD identified the presence of pyrophosphate $\text{Ca}_2\text{P}_2\text{O}_7$. Amorphous material was also found.

The catalyst was tested as described in Example 1. The results are shown in Table 4.

Table 5

Ex.	Catalyst composition	Contact time [s]	MMA+MAA yield [%]	MAA selectivity [%]	MMA+MAA selectivity [%]	DME [mole%]	DEK [mole%]	Toluene [mole%]
New Ex 13	Sr-HAp pH11_1.67	5.2	7.0	0.7	85.9	0.04	0.0045	0.00005
New Ex 14	Sr-HAp pH11_1.50	5.2	6.8	0.8	92.0	0.17	0.0024	0.00010
New Ex 15	Sr-HAp pH11_1.00	5.0	5.6	1.2	94.1	0.21	0.0012	0.00006

Example 13

Preparative example 13

21.2 g of strontium nitrate $\text{Sr}(\text{NO}_3)_2$ was dissolved in 100 ml of demineralised water and pH was adjusted to 11 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate
5 $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 11 was added dropwise to the solution of strontium nitrate at the temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after
10 the dropwise addition was complete and pH was maintained at 11 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water.

Then it was dried at 110 °C overnight and calcined in air
15 at 400 °C for 1 hr. The sample was identified as a crystalline strontium-apatite type by XRD analysis. TEM images show nano-rods as the only observed morphology, typically 100nm length and 20nm diameter. The catalyst was tested as described in Example 1. The results are shown in
20 Table 5.

Example 14

Preparative example 14

25 19.0 g of strontium nitrate $\text{Sr}(\text{NO}_3)_2$ was dissolved in 100 ml of demineralised water and pH was adjusted to 11 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 11 was added dropwise to the solution of strontium nitrate at the
30 temperature of 80 °C while stirring. A suspension forms on addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained

at 11 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water.

Then it was dried at 110 °C overnight and calcined in air
5 at 400 °C for 1 hr. The sample was identified as a crystalline strontium-apatite type by XRD analysis. TEM images show tightly clustered nano-rods, typically 100nm length and 20nm diameter. The catalyst was tested as described in Example 1. The results are shown in Table 5.

10

Example 15

Preparative example 15

12.7 g of strontium nitrate $\text{Sr}(\text{NO}_3)_2$ was dissolved in 100
15 ml of demineralised water and pH was adjusted to 11 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 11 was added dropwise to the solution of strontium nitrate at the temperature of 80 °C while stirring. A suspension forms on
20 addition of the phosphate to the nitrate solution. This mother suspension was continuously stirred for 3 hrs after the dropwise addition was complete and pH was maintained at 11 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised
25 water.

Then it was dried at 110 °C overnight and calcined in air
at 400 °C for 1 hr. The sample was identified as a strontium-apatite type by XRD analysis. TEM images show clusters of long nano-rods, typically 100-500nm in length,
30 and 10-20nm in diameter. The catalyst was tested as described in Example 1. The results are shown in Table 5.

B Dimethoxymethane feed

Table 6

	Catalyst composition	Contact time [s]	MMA+MAA yield [%]	MAA selectivity [%]	MMA+MAA selectivity [%]	DME [mole%]	Water content [wt%]	DEK [mole%]	Toluene [mole%]
Ex 16	Ca-HAp pH7_1.67	16.0	4.9	0.03	89.59	1.0	0.06	0.0095	0.00009
Ex 17	Ca-HAp pH11_1.67	14.9	6.2	1.7	81.9	0.6	0.09	0.0249	0.00018
Comp Ex 5	AlPO ₃ TiO ₂ B_urea	14.3	4.9	3.7	57.8	11.4	2.21	0.0263	0.00388
Comp Ex 6	AlPO	9.7	15.0	9.6	81.01	8.3	2.32	0.0107	0.00604
Comp Ex 7	AlPO ₃ MgPO	12.0	3.0	0.2	50.3	6.5	0.15	0.0104	0.00086
Comp Ex 8	TiO ₂ Ca ₃ (PO ₄) ₂ B_urea	9.4	3.2	0.1	58.3	0.8	0.05	0.0149	0.00046
Comp Ex 9	Comm Ca-HAp 289396	11.7	0.23	0.0	64.7	0.4	0.03	0.0033	0.00008
Comp Ex 10	Comm Ca-HAp 677418	10.3	0.008	0.8	1.36	0.006	0.05	0.1477	0.00000
Comp Ex 11	Comm Ca ₂ P ₂ O ₇ 693871_1	10.5	0.095	2.6	29.0	2.5	0.03	0.0009	0.00017

Example 16

- 5 The catalyst was prepared as in preparative example 1.

Catalyst testing: 3 g of catalyst was placed in a stainless steel tubular reactor connected to a vaporiser. The reactor was heated to 350 °C and vaporiser to 300 °C. The mixture of 70 wt% of methyl propionate and 30 wt% of dimethoxymethane was passed through. The condensed reaction mixture was analysed by gas chromatography equipped with CP-Sil 1701.

Example 17

- 15 The catalyst was prepared as in preparative example 6. The catalyst was tested as described in example 16.

Comparative example 5

The catalyst was prepared as in comparative preparative example 1.

The catalyst was tested as described in example 16.

5 Comparative example 6

The catalyst was prepared as in comparative preparative example 2

The catalyst was tested as described in example 16.

10 Comparative example 7

Comparative preparative example 7

3 g of magnesium phosphate hydrate $\text{Mg}_3(\text{PO}_4)_2 \cdot x\text{H}_2\text{O}$ (Aldrich catalogue number 344702) was mixed with 3 g of aluminium phosphate (prepared as in comparative example 2). A paste

15 was produced by addition of 5 ml of demineralised water. The paste was dried for 2 hrs at 120 °C and then heated for 4 hrs at 600 °C.

The catalyst was tested as described in example 16.

20 Comparative example 8

Comparative preparative example 8

The catalyst was synthesised following the preparation method disclosed in US 4118588 patent in Example 3.

3 g of titanium dioxide TiO_2 (Aldrich catalogue number 634662), 2.3 g of calcium phosphate $\text{Ca}_3(\text{PO}_4)_2$ (Aldrich catalogue number 50552) and 0.75 g of boric acid H_3BO_3 were mixed together. A paste was produced by addition of 0.25 g of urea in 5 ml of demineralised water. The paste was dried for 12 hrs at 120 °C and then heated for 3 hrs
30 at 580 °C.

The catalyst was tested as described in example 16.

Comparative example 9

Commercial Ca-hydroxyapatite was used from Aldrich with catalogue number of 289396.

The sample was confirmed as a crystalline hydroxyapatite type by XRD analysis. TEM showed the presence of
5 agglomerated irregular sphere like particles.

Some amorphous material was found.

The catalyst was tested as described in example 16.

Comparative example 10

10 Commercial Ca-hydroxyapatite was used from Aldrich with catalogue number of 677418.

BET surface area disclosed by Aldrich is 9.4 m²/g.

The sample was confirmed as a crystalline hydroxyapatite type by XRD analysis. TEM analysis revealed sphere like
15 crystals. Some amorphous material was found.

The catalyst was tested as described in example 16.

Comparative example 11

Commercial Ca₂P₂O₇ was used from Aldrich with catalogue
20 number of 693871.

BET surface area disclosed by Aldrich is 12 m²/g. TEM showed sphere like non-crystalline particles.

The catalyst was tested as described in example 16. The results are shown in table 6.

25

Table 7

Ex.	Catalyst composition	Contact time [s]	MMA+MAA yield [%]	MAA selectivity [%]	MMA+MAA selectivity [%]	DME [mole%]	Water content [wt%]	DEK [mole%]	Toluene [mole%]
Ex 18	Ca-HAp pH7_1.5	10.5	5.9	0.02	89.29	2.5	0.03	0.0048	0.00025
Ex 19	Ca-HAp pH7_1	3.3	1.2	0.1	84.1	0.7	0.02	0.0050	0.00015

Example 18

The catalyst was prepared as in preparative Example 7.

The catalyst was tested as described in example 16 and the results are shown in table 7.

Example 19

- 5 The catalyst was prepared as in preparative Example 8.
The catalyst was tested as described in example 16 and the results are shown in table 7.

10 Example 20

The catalyst of preparative example 13 was tested as described in example 16. The results are shown in table 8.

15 Example 21

The catalyst of preparative example 14 was tested as described in example 16. The results are shown in table 8.

20 Example 22

The catalyst of preparative example 15 was tested as described in example 16. The results are shown in table 8.

Table 8

25

Ex.	Catalyst composition	Contact time [s]	MMA+M AA yield [%]	MAA selectivity [%]	MMA+ MAA selectivity [%]	DME [mole %]	Water content [wt%]	DEK [mole%]	Toluene [mole%]
Ex 20	Sr-HAp pH11_1.67	11.6	4.1	0.03	73.3	0.07	0.04	0.0747	0.00012
Ex 21	Sr-HAp pH11_1.50	10.9	5.9	0.02	91.3	0.45	0.06	0.0030	0.00011

Ex 22	Sr-HAp pH11_1.00	12.4	8.7	0.02	92.4	0.66	0.11	0.006 4	0.00008
----------	---------------------	------	-----	------	------	------	------	------------	---------

Example 23

5 Preparative Example 23

21.2 g of strontium nitrate $\text{Sr}(\text{NO}_3)_2$ was dissolved in 100 ml of demineralised water and pH was adjusted to 7 with ammonium hydroxide. 7.9 g of diammonium hydrogen phosphate $(\text{NH}_4)_2\text{HPO}_4$ in 50 ml of demineralised water at pH 7 was added dropwise to a solution of strontium nitrate at the temperature of 80 °C while stirring. The mother suspension was mixed for 3 hrs and pH was maintained at 7 with ammonium hydroxide throughout. After that the suspension was filtered and washed with demineralised water.

15 Then it was dried at 110 °C overnight and calcined in air at 400 °C for 1 hr. The sample was identified as a crystalline strontium pyrophosphate by XRD analysis. TEM images show large flat structures, blade or sheet-like, typically 2 - 5 micron in length and 0.2 - 0.5 micron in width. The flat structures were fringed with clusters of nano-rod structures, with individual rods being typically 20 nm in diameter and 200 nm in length.

The catalyst was tested as described in example 1. The results are shown in Table 9.

Example 24

The catalyst of example 23 was tested with dimethoxymethane feed, as described in Example 16. The results are shown in Table 9.

Table 9

Ex.	Catalyst composition	Contact time [s]	MMA+MAA yield [%]	MAA selectivity [%]	MMA+MAA selectivity [%]	DME [mole%]	Water content [wt%]	DEK [mole%]	Toluene [mole%]
Ex. 23	Sr2P2O7 pH7_1.67	11.3	4.5	0.6	94.1	0.2	—	0.0011	0.00014
Ex. 24	Sr2P2O7 pH7_1.67	11.1	2.5	0.05	88	0.4	0.03	0.0058	0.00009

Table 10 shows the Ca:P synthesis ratios of various examples and comparative examples as well as the Ca:P ratios in the final crystals(XRF) and on the crystal surfaces(XPS). Comparative example 12 is a commercial pyrophosphate in the form of amorphous spheres purchased from Aldrich under catalogue number 693871. It can be seen that at the ideal hydroxyapatite ratio of 1.67 both the bulk crystal and the crystal surface are depleted in calcium but that the surface is more depleted. However, at low M:P synthesis ratios ideal for pyrophosphates of 1:1, the surface is richer in metal than the bulk of the crystal. This suggests the formation of a preferred surface arrangement on the crystals. The surface and bulk ratios for a series of examples are plotted in figure 1. It can be seen that at higher overall ratios the surface ratio is depressed and that at lower overall ratios the surface ratio is increased.

20

The XRD peak intensity data was collected and the ratios of certain peaks for several samples were compared. The results are shown in figure 7. The 002:211 ratio for the samples of the invention could be indicative of a strong nano-rod presence.

25

<u>Table 10</u>				
<u>Example</u>	<u>Ca:P (stoich)</u>	<u>XRF Peak Area Ratio (Ca:P)</u>	<u>Bulk Ca:P (XRF m/m)</u>	<u>Surface Ca:P (XPS m/m)</u>
Comp Ex 12	1.00	2.505	0.940	0.89
Comp Ex 3	1.67	4.046	1.597	1.42
Comp ex 4	1.67	4.748	1.896	1.78
Ex 3	1.67	2.711	1.028	1.08
Ex 6	1.67	4.086	1.614	1.49
Ex 1	1.67	4.168	1.648	1.46
Ex 8	1.00	3.531	1.377	1.31
Ex 7	1.50	3.846	1.511	1.38
Ex 9	1.67	3.801	1.492	1.36
Ex 11	1.67	2.945	1.128	1.23

CLAIMS

1 A method of producing an ethylenically unsaturated
carboxylic acid or ester, preferably an α , β ethylenically
5 unsaturated carboxylic acid or ester, comprising the steps
of contacting formaldehyde or a suitable source thereof
with a carboxylic acid or ester in the presence of a
catalyst and optionally an alcohol, wherein the catalyst
comprises group II metal phosphate crystals having rod or
10 needle like morphology.

2 A method according to claim 1, wherein the phosphate
is selected from hydroxyapatite, pyrophosphate,
hydroxyphosphate, PO_4^{2-} phosphate and mixtures thereof.

15

3 A method according to claim 1 or 2, wherein the group
II metal of the phosphate is selected from Ca, Sr or Ba or
mixtures thereof.

20 4 A method according to any of claims 1 to 3, wherein
the catalysts are selected from strontium hydroxyapatite
and calcium hydroxyapatite.

5 A method according to any of claim 1 to 4, wherein the
25 catalyst is at least 50% w/w metal phosphate.

6 A method according to any of claims 1-5, wherein the
catalyst of the invention has its surface layer of
crystals depleted below the hydroxyapatite metal to
30 phosphate mole ratio of 1.67.

- 7 A method according to claim 6, wherein the crystal surface metal:phosphorus (M:P) mole ratio is between 1.30 and 1.55.
- 5 8 A catalyst system comprising a crystalline group II metal phosphate catalyst and a catalyst support wherein the group II metal phosphate has rod and/or needle like morphology.
- 10 9 A method according to any of claims 1-7, wherein the carboxylic acid or ester reactant of the present invention is of formula $R^3-CH_2-COOR^4$, wherein R^4 is either hydrogen or an alkyl group and R^3 is either hydrogen, an alkyl or aryl group.
- 15 10 A method according to any of claims 1-7, or 9 wherein the ethylenically unsaturated acid or ester produced by the process of the invention is selected from acrylic, alkacrylic, 2-butenic, cyclohexenoic, maleic, itaconic and fumaric acids and their alkyl esters, and also
20 methylene substituted lactones.
- 11 A method according to any of claims 1-7, 9 or 10, wherein doping elements are present in the catalyst at a level up to 20 mol % of the metal M.
- 25 12 A method according to claim 11, wherein the doping elements are metal cations selected from Cs, K, Rb, Na, Li, Zn, Ti, Si, Ln, Ce, Eu, Mg (if not used as a group II metal), Ba(if not used as a group II metal), Pb, Cd, Ag,
30 Co, Cu, Ni and Zr.

13 A method according to any of claims 1-7, or 9-11,
wherein doping anions are present in the catalyst at a
level of up to 20 mol % phosphate.

5 14 A method according to claim 13, wherein the doping
anions are selected from carbonate, chloride and fluoride.

15 A method or catalyst system according to any preceding
claim wherein the catalyst is on a support selected from
10 alumina, silica, silicon nitride, silicon carbide,
colloidal silica, titania or aluminium phosphate.

16 A method according to any of claims 1-7, or 9-15,
wherein the metal:phosphorus (M:P) mole ratio is between
15 0.8-1.8.