



159159

- 1 -

DESCRIPTION

Conductive-resin-coated Steel Pipe and Method of
Extrusion-Forming Same

5 FIELD OF SEARCH

The present invention belongs to a technical field of a
conductive-resin-coated steel pipe and a method of extrusion-
forming it. More specifically, the present invention relates
to a conductive-resin-coated steel pipe which is suited to be
10 used as, for example, a frame component of a structure such as
a flow-through rack, a driven conveyor or the like for holding
or transporting parts of low electrical current devices or the
like, and a method of extrusion-forming it.

15 BACKGROUND OF THE INVENTION

A conductive-resin-coated steel pipe of about 28-32 mm in
outer diameter is used as a frame component of a structure such
as a flow-through rack, a driven conveyor or the like for
holding or transporting parts of low electrical current devices
20 or the like, in order to prevent static electrification. Thus,
a coating of about 1 mm in thickness of conductive synthetic
resin containing carbon black is formed on the outer
circumferential surface of a thin-walled steel pipe of about
26-30 mm in outer diameter.

25 However, due to the use of carbon black, the above-
mentioned conductive-resin-coated steel pipe has problems.
That is, the use of carbon black makes the unit cost of the
pipe expensive and makes the pipe black, which is not of
pleasing appearance. Further, the carbon adheres to things
30 that comes in contact with the pipe.

Taking these problems into consideration, the applicant
has proposed a conductive-resin-coated steel pipe disclosed in
Japanese Examined Utility Model Publication No. H8(1996)-5796,

G00002



wherein on the outer circumferential surface of a thin-walled steel pipe, a coating of about 1 mm in thickness of synthetic resin such as AAS resin or the like of a chromatic color is formed, and on top of that coating a strip of conductive
5 synthetic resin containing carbon black is formed integrally in the axial direction of the conductive-resin-coated steel pipe.

In this conductive-resin-coated steel pipe, the use of carbon black is reduced, which contributes to lowering the unit production cost.

10 Regarding the above-mentioned conductive-resin-coated steel pipe disclosed in Japanese Examined Utility Model Publication No. H8(1996)-5796, improvement in cost and appearance is acknowledged, to be sure, but conductive synthetic resin containing carbon black is still exposed
15 although in the form of a strip. Therefore, the problem that the exposed carbon black adheres to things that come in contact with the pipe remains unsolved. Further, when an earth wire is to be connected to this pipe, it is necessary to pay attention to the position of a conductive portion. This causes another
20 problem in that work efficiency is reduced.

In recent years, filler (fiber) having high impact resistance has been attracting attention. However, like the above-mentioned carbon black, the filler is expensive. Therefore, a steel pipe coated with resin containing the filler,
25 particularly a steel pipe coated with conductive resin containing the filler has not been widely promoted.

Thus, the object of the present invention is to provide a conductive-resin-coated steel pipe in which filler is used in place of carbon black and which enables lower unit production
30 cost and a better appearance, and a method of extrusion-forming such pipe.

DISCLOSURE OF THE INVENTION

To achieve the objects described above, the invention as recited in claim 1 relates to a conductive resin-coated steel pipe(1), is characterized in that a coating of reprocessed resin(3) such as polyethylene, ABS, AAS, polypropylene or the like is formed on an outer circumferential surface of a thin-walled steel pipe(2) and a coating of conductive resin(4) such as polyethylene, ABS, AAS, polypropylene or the like, which said conductive resin is combined with a filler, is formed on an outer circumferential surface of said coating of reprocessed resin(3), wherein said coating of conductive resin includes at least one portion arranged in a circumferential direction of said pipe and having a thickness and width(4b) required for said portion to exhibit electrical conductivity, and said coating of reprocessed resin and said coating of conductive resin form a thin two-layer coating that covers an entire outer circumferential surface of said thin-walled steel pipe and has a uniform cross-section in an axial direction of said pipe.

In the conductive-resin-coated steel pipe according to claim 1, the invention recited in claim 2 is characterized in that said thin-walled steel pipe(2) is round in cross section, and said coating of conductive resin(4), which said conductive resin is combined with said filler, consists of equal thinner-and-wider layer-portions(4a) and equal thicker-and-narrower layer-portions(4b) which alternate along the outer circumferential surface of said coating of reprocessed resin(3).

In the conductive-resin-coated steel pipe(1) according to claim 1 or 2, the invention recited in claim 3 is characterized in that said thickness and width required for a portion of the coating of conductive resin(4), which said conductive resin is combined with said filler, to exhibit electrical conductivity is at least approximately 0.5 mm and at least 2 mm, respectively.

In the conductive-resin-coated steel pipe(1) according to any of claims 1 to 3, the invention recited in claim 4 is characterized in that said conductive resin(4), which said conductive resin is combined with said filler, is loaded with a colorant to give to said conductive-resin-coated steel pipe a chromatic color.

The invention recited in claim 5 relate to a method of extrusion-forming a conductive-resin-coated steel pipe, is characterized in that a coating of reprocessed resin(3) such as polyethylene, ABS, AAS, polypropylene or the like is extrusion-formed on an outer circumferential surface of a thin-walled steel pipe(2) and a coating of conductive resin(4) such as polyethylene, ABS, AAS, polypropylene or the like, which said conductive resin is combined with a filler, is extrusion-formed on an outer circumferential surface of said coating of reprocessed resin(3), wherein at least one portion of said coating of conductive resin, arranged in a circumferential direction of said pipe, is made to have a thickness and width(4b) required for said portion to exhibit electrical conductivity, and said coating of reprocessed resin and said coating of conductive resin are made to form a thin two-layer coating that covers an entire outer circumferential surface of said thin-walled steel pipe and has a uniform cross-section in an axial direction of said pipe.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A is a cross-sectional view of a conductive-resin-coated steel pipe according to the present invention; FIG. 1B shows part X of FIG. 1A on an enlarged scale;

FIG. 2 is an elevation of a main part of a cross die type extruding machine;

FIG. 3 is a cross-sectional view taken along line III-III of FIG. 2;

FIG. 4A and 4B are a front view and a cross-sectional view of a head for inner-layer forming resin, respectively; and

FIG. 5A and 5B are a front view and a cross-sectional view of a head for outer-layer forming resin, respectively.

5

THE MOST PREFERRED EMBODIMENT OF THE INVENTION

FIGS. 1A and 1B shows an embodiment of a conductive-resin-coated steel pipe 1 recited in claim 1. The conductive-resin-coated steel pipe 1 is suited to be used as, for example, a
10 frame component of a structure such as a flow-through rack, a driven conveyor or the like for holding or transporting parts of low electrical current devices or the like. The conductive-resin-coated steel pipe 1 is based on a technical idea of using inexpensive reprocessed resin as much as possible and reducing
15 the use of conductive resin containing expensive filler as much as possible and at the same time ensuring sufficient electrical conductivity.

In the conductive-resin-coated steel pipe 1, first, a coating of reprocessed resin 3 such as polyethylene, ABS, AAS,
20 polypropylene or the like is formed on the outer circumferential surface of a thin-walled steel pipe 2. Then, on the outer circumferential surface of this coating of resin(reprocessed resin 3), a coating of conductive resin 4 such as polyethylene, ABS, AAS, polypropylene or the like,
25 combined with a filler, is formed in a manner that, in the case of FIG.1, 12 equal portions 4b each having a thickness and width required for the portion 4b to exhibit electrical conductivity are arranged in 12 positions equally spaced apart in the circumferential direction of the pipe. Here, each
30 portion 4b extends continuously in the axial direction of the pipe, in the form of a strip, and the coating of reprocessed resin 3 and the coating of conductive resin 4 form a thin two-layer coating that covers the entire outer circumferential

surface of the thin-walled steel pipe 2 and has a uniform cross-section in the axial direction of the pipe.

Substantially the same embodiment can be made by using resin other than the above mentioned ones, such as polystyrene or methacrylate resin, as the reprocessed resin 3. The
5 conductive resin 4 is not restricted to the above mentioned ones, either.

In the case of FIG. 1, 12 equal conductive portions 4b are provided equally spaced apart in the circumferential direction
10 of the pipe. The reason that so many conductive portions 4b are provided is that, in that case, a structure such as a flow-through rack, a driven conveyor or the like can be constructed freely without paying special attention to the positions of the
15 conductive portions 4b to which a ground wire can be connected. As long as at least one conductive portion 4b extends
20 continuously in the axial direction of the pipe, it is enough in order to construct a structure to which a ground wire can be connected. However, in the case where only one conductive
25 portion 4b is provided, it is necessary to construct a structure, taking the position of the conductive portion 4b
30 into consideration.

The coating of conductive resin 4 on the outer circumferential surface of the coating of reprocessed resin 3 consists of thinner-and-wider layer-portions 4a and thicker-
25 and-narrower layer-portions(i.e., conductive portions)4b. Accordingly, the coating of reprocessed resin 3 necessarily consists of thicker-and-wider layer-portions 3a and thinner-
30 and-narrower layer-portions 3b. In the conductive-resin-coated steel pipe 1 shown in FIG. 1, the thin-walled steel pipe 2 is round in cross section, and the coating of conductive resin 4
35 consist of 12 equal thinner-and-wider layer-portions 4a and 12 equal thicker-and-narrower layer-portions(conductive portions) 4b which alternate along the circumferential surface of the

coating of reprocessed resin 3. Needless to say, the number of the portions 4a(portions 4b) is not restricted to 12.

Specifically, in the example of FIG.1, the thin-walled steel pipe 2 is a little less than 1 mm in wall thickness and about 26-30 mm in outer diameter. Each thinner-and-wider layer-portion 4a of the coating of conductive resin 4 is about 0.2 mm in thickness, and each thicker-and-narrower layer-portion (conductive portion) 4b thereof is about 0.7 mm in thickness and about 2 mm in width (invention recited in claim 3). Each thicker-and-wider layer-portion 3a of the coating of reprocessed resin 3 is about 0.7 mm in thickness, and each thinner-and-narrower layer-portion 3b thereof is about 0.2 mm in thickness. Therefore, the conductive-resin-coated steel pipe 1 being round in cross section and about 27.8-32 mm in outer diameter is extrusion-formed.

In the conductive-resin-coated steel pipe 1, the conductive resin 4 is loaded with a colorant to have a chromatic color such as green, ivory or the like.

Thus, in the case of the above-described conductive-resin-coated steel pipe 1, (1) inexpensive reprocessed resin 3 is used as much as possible and the use of conductive resin 4 containing expensive filler is restricted to the amount required to produce electrical conductivity. Thus, resources can be conserved and the unit production cost can be lowered. Of course, a ground wire can be connected. (2) Since a resin combined with filler is used, there is no concern that color may come off and produce stains. (3) By using the resin loaded with a colorant for green, ivory or the like to have a desired chromatic color, the appearance of the conductive-resin-coated steel pipe can be improved. Not only it is possible to make a conductive-resin-coated steel pipe having a bright color, but also it is possible to choose the color to match the work environment.

Next, an embodiment of the method of extrusion-forming a conductive-resin-coated steel pipe having the above-described structure according to the invention will be described on the basis of FIG.2, etc.

5 FIGS.2 and 3 show a cross die type extruding machine used in the above-mentioned extrusion-forming method. In FIG.2, reference numeral 10 denotes a head portion of a cross die that is a main part of the extruding machine. The basic structure is similar to that of an extruding machine according to the
10 applicant's Japanese Patent No.2867244.

 In the extruding machine, an adaptor 11 is fixed at the front end of a cross die (not shown), and a distribution piece 14 and a head 15 for inner-layer forming resin are fixed to the front end of the adaptor 11 by means of a distribution plate 12.
15 Further, in front of the afore mentioned pieces, a radial distribution piece 16 and a head 17 for outer-layer forming resin are fixed by means of a distribution plate 13. The distribution plates 12 and 13 are joined together. A connecting piece 20, which is connected to a heating cylinder,
20 is fixed to the upper are as of the joint surface of the distribution plates 12 and 13. By means of the head 15 for inner-layer forming resin, reprocessed resin 3 supplied from the cross die is formed into a coating on the outer circumferential surface of the thin-walled steel pipe 2, and
25 then by means of the head 17 for outer-layer forming resin, conductive resin 4 supplied from the heating cylinder is formed into a coating on the outer circumferential surface of the coating of reprocessed resin 3.

 The flow path for conductive resin 4 from the connecting
30 piece 20 to the head 17 for outer-layer forming resin includes a first flow path 18 in the form of a large semicircular arch running around the thin-walled steel pipe 2. The opposite end portions of the first flow path 18 are bent and connected to

inside second flow paths 19, 19, which are of a smaller diameter. The second flow paths 19, 19 are joined, wherein their joint portions are narrowed so that resin can be extruded uniformly toward the center.

5 The second flow paths 19, 19 are connected to radial flow paths formed in the radial distribution piece 16, and radial flow paths 17a and a through-hole 17b of the head 17 for outer-layer forming resin (see FIG.5).

10 As shown in FIGS.4A and 4B, the head 15 for inner-layer forming resin has a through-hole 15a for forming a coating of reprocessed resin 3. The circumferential surface defining the through-hole 15a consists of 12 equal ridges and 12 equal channels 15b which alternate in the circumferential direction and each extend in the axial direction of the pipe. The ridges
15 are provided for forming thinner portions, and have a width of 2 mm. The channels 15b are provided for forming thicker portions, and have a depth of about 0.7 mm.

20 As shown in FIGS.5A and 5B, the head 17 for outer-layer forming resin has radial paths 17a and a through-hole 17b for forming a coating of conductive resin 4 on the coating of reprocessed resin 3. The flow paths 17a are arranged to correspond to the ridges for forming thinner portions of the head 15 for inner-layer forming resin, and have substantially the same width as that of the ridge. The through-hole 17b
25 defines the outer diameter of the conductive-resin-coated steel pipe 1.

30 The conductive-resin-coated steel pipe 1 is extrusion-formed with the above-described extruding machine as follows: First, on the outer circumferential surface of a thin-walled steel pipe 2 that is being moved from the cross die (not shown) to the right, a coating of reprocessed resin 3 is formed by means of the head 15 for inner-layer forming resin, wherein the reprocessed resin 3 is supplied to the head 15 through the

adaptor 11 and the distribution piece 14.

Then, when the thin-walled steel pipe 2 reaches the head 17 for outer-layer forming resin, a coating of conductive resin 4 is formed on the outer circumferential surface of the coating of reprocessed resin 3 by means of the head 17, wherein the conductive resin 4 is supplied to the through-hole 17b from the connecting piece 20 through the first flow path 18, the second flow paths 19, the radial distribution piece 16, a space between the head 15 for inner-layer forming resin and the head 17 for outer-layer forming resin, and the flow paths 17a.

Thus, as shown in FIG.1, a two-layer coating consisting of the coating of reprocessed resin 3 and the coating of conductive resin 4 and having a uniform outer diameter and cross-section in the axial direction of the pipe is extrusion-formed, wherein the coating of reprocessed resin 3 consists of alternating 12 equal thicker portions and 12 equal thinner portions and also the coating of conductive resin 4 consists of alternating 12 equal thicker portions and 12 equal thinner portions.

In the above, one embodiment of the present invention has been described on the basis of the drawings, however, the present invention is not limited to the shown embodiment. It is to be noted that the present invention encompasses changes of design and various applications which a person skilled in the art would ordinarily make, not deviating from the technical thought of the present invention.

INDUSTRIAL UTILIZATION

In the present invention relate to the steel pipe formed by the method of extrusion-forming a conductive-resin-coated steel pipe,

I) inexpensive reprocessed resin is used as much as possible and the use of conductive resin containing expensive filler is

restricted to the amount required to produce electrical conductivity. Thus, less resources are used, thereby contributing to environmental conservation, and the unit production cost can be lowered. Of course, a ground wire can
5 be connected.

II) Further, since the resin loaded with filler is used, there is no concern that color may come off, producing stains.

III) Further, by using the resin loaded with a colorant for green, ivory or the like to have a desired chromatic color, the
10 appearance of the conductive-resin-coated steel pipe can be improved. Thus, not only it is possible to make a conductive-resin-coated steel pipe with a bright color, but also it is possible to choose the color to match the working environment.

CLAIMS

1. A conductive-resin-coated steel pipe, characterized in that a coating of reprocessed resin(3) such as polyethylene, ABS, AAS, polypropylene or the like is formed on an outer circumferential surface of a thin-walled steel pipe(2) and a coating of conductive resin(4) such as polyethylene, ABS, AAS, polypropylene or the like, which said conductive resin is combined with a filler, is formed on an outer circumferential surface of said coating of reprocessed resin(3), wherein said coating of conductive resin includes at least one portion arranged in a circumferential direction of said pipe and having a thickness and width(4b) required for said portion to exhibit electrical conductivity, and said coating of reprocessed resin and said coating of conductive resin form a thin two-layer coating that covers an entire outer circumferential surface of said thin-walled steel pipe and has a uniform cross-section in an axial direction of said pipe.

2. The conductive-resin-coated steel pipe according to claim 1, characterized in that said thin-walled steel pipe(2) is round in cross section, and said coating of conductive resin(4), which said conductive resin is combined with said filler, consists of equal thinner-and-wider layer-portions(4a) and equal thicker-and-narrower layer-portions(4b) which alternate along the outer circumferential surface of said coating of reprocessed resin(3).

3. The conductive-resin-coated steel pipe according to claim 1 or 2, characterized in that said thickness and width required for a portion of the coating of conductive resin(4), which said conductive resin is combined with said filler, to exhibit electrical conductivity is at least approximately 0.5

mm and at least 2 mm, respectively.

4. The conductive-resin-coated steel pipe according to any of claims 1 to 3, characterized in that said conductive
5 resin(4), which said conductive resin is combined with said filler, is loaded with a colorant to give to said conductive-resin-coated steel pipe a chromatic color.

5. A method of extrusion-forming a conductive-resin-
10 coated steel pipe, characterized in that a coating of reprocessed resin(3) such as polyethylene, ABS, AAS, polypropylene or the like is extrusion-formed on an outer circumferential surface of a thin-walled steel pipe(2) and a coating of conductive resin(4) such as polyethylene, ABS, AAS,
15 polypropylene or the like, which said conductive resin is combined with a filler, is extrusion-formed on an outer circumferential surface of said coating of reprocessed resin(3), wherein at least one portion of said coating of conductive resin, arranged in a circumferential direction of said pipe, is
20 made to have a thickness and width(4b) required for said portion to exhibit electrical conductivity, and said coating of reprocessed resin and said coating of conductive resin are made to form a thin two-layer coating that covers an entire outer circumferential surface of said thin-walled steel pipe and has
25 a uniform cross-section in an axial direction of said pipe.