## CLAIMS

[Claim 1] A silver powder comprising:

a surface treatment agent;

a ratio of oxygen content to BET specific surface area of 0.11 or more and 0.60 or less; and

a crystallite diameter of 30 nm or more and 38 nm or less.

[Claim 2] The silver powder according to claim 1, comprising a ratio of Ig-loss to the BET specific surface area of 0.51 or more.

[Claim 3] The silver powder according to claim 1, comprising:

a volume-based cumulative 50% diameter $D_{50}$ measured by a laser diffraction method of 0.1 μm or more and 1.0 μm or less; and

a volume-based cumulative 90% diameter $D_{90}$ measured by the laser diffraction method of 1.2 μm or less.

[Claim 4] The silver powder according to claim 1, wherein the BET specific surface area is 0.90 $m^2/g$ or more and 2.50 $m^2/g$ or less.

[Claim 5] The silver powder according to any one of claims 1 to 4, for use in a resin-curable conductive paste.

[Claim 6] A resin-curable conductive paste comprising the silver powder according to any one of claims 1 to 4.