

**MOULD, MOULDING APPARATUS AND METHOD FOR CONTROLLED
OVERMOULDING OF A CARRIER WITH ELECTRONIC COMPONENTS
AND MOULDED PRODUCT**

- 5 The present invention relates to a mould for at least partially encapsulating a carrier with electronic components, comprising: at least two mould parts, at least one of which being provided with at least one mould cavity recessed into a contact side for enclosing electronic components placed on a carrier, the contact surface at least partially enclosing the mould cavity for medium-tight connection onto the carrier; and a feed channel for
- 10 moulding material recessed into the contact surface of the mould part provided with the mould cavity. The invention also relates to a moulding apparatus, a method for at least partially encapsulating a carrier with electronic components and a carrier with electronic components encapsulated with moulding material according to this method.
- 15 The encapsulation of electronic components mounted on a carrier, and more particularly the encapsulation of semiconductor circuits (chips) / integrated circuits (IC's), according to the prior art makes use of encapsulating presses provided with at least two co-operating mould parts. Into at least one of the mould parts one or plural mould cavities are recessed. After placing the carrier with the electronic components for
- 20 encapsulating between the mould parts, the mould parts may be moved towards each other, e.g. such that they clamp the carrier. Subsequently a, normally heated, liquid moulding material may then be fed through at least one moulding material feed channel (also referred to as "runner") to the mould cavity or the plural mould cavities, usually by means of transfer moulding. Epoxy may be applied as moulding material (also
- 25 referred to as resin), which is generally provided with filler material. After at least partial (chemical) curing of the moulding material in the mould cavity/cavities, the mould parts are moved apart and the carrier with encapsulated electronic components is removed from the encapsulating press. In a subsequent processing step the encapsulated products may be separated from each other, for instance by sawing, laser cutting and/or
- 30 water cutting. The at least partial covered electronic components may be used in various applications. This method of moulding is practised on large industrial scale and enables well controlled moulding of electronic components. Problems with moulding electronic components relate the control of the filling of the mould cavity/cavities with moulding

material and the control of the removal of the moulded products from the encapsulation press.

5 The present invention has for its object to provide an efficient method and device that enable an enhanced control on both; the filling the of the mould cavity/cavities with moulding material and the removal of the moulded products from the mould.

10 This object is achieved with a mould for at least partially encapsulating a carrier with electronic components, comprising: at least two mould parts, at least one of which being provided with at least one mould cavity recessed into a contact side for enclosing electronic components placed on a carrier, the contact surface at least partially enclosing the mould cavity for medium-tight connection onto the carrier; and a feed channel for moulding material recessed into the contact surface of the mould part provided with the mould cavity; wherein in the mould part with the feed channel is provided with a
15 displaceable barrier element connecting to the feed channel for regulating the size of an moulding material passage in the feed channel, which barrier element is displaceable in a direction substantially perpendicular to the contact surface.

20 The mould parts are displaceable relative to each other so that in a closed position at least one mould cavity encloses an electronic component. The feed of moulding material (which may also be referred to as “encapsulating material”) usually takes place by means of a plunger with which moulding material, which has become liquid as a result of heating and is then pressed into the mould cavities. Such moulding process is also referred to as “transfer moulding”. Within the context of this invention other
25 methods of feeding moulding material are however possible, such as for instance by means of injection moulding. In respect of the moulding material there are also other alternatives within the context of the invention, such as for instance the feed of moulding material supplied in liquid form (liquid epoxy) or for instance a thermo-curing moulding material consisting of at least two separately supplied components
30 which cure as a result of mixing. Flow rate and pressure of the feed of moulding material can hereby be adjusted.

One of the advantages of the present invention is that the displaceable barrier element may provide plural functions. First the feed of the moulding material may be controlled

such that an optimal filling of the moulding cavity may be realised. In this respect situational circumstances may influence the best position of the displaceable barrier element in the feed channel, which may – among others – be dependent from the type of moulding material, the temperature of the moulding material, the number of moulding cavities connected to a source of moulding material, the contamination of a mould part, the specification of the carrier with electronic components, and so on. Dependent on these and other variables the size of a moulding material passage in the feed channel may be regulated by displacement of the barrier element more or less in the feed channel. A further advantage of the displaceable barrier element is that after at least partial curing of the moulding material in the feed channel the barrier element may also be used to exert a pressure on the moulding material in the feed channel and to so at least support the release of the moulded product from a mould part in the situation where the mould parts are moved apart. The release of the moulded product from a mould part is also referred to as “degating”. As the pressure to release the moulded product from the mould may be exerted by the displaceable barrier element at the moulding material in the feed channel the displaceable will not leave any marks on the moulded product and on the other hand the pressure may be exerted on the moulded product close to the moulding cavity which is supportive for an effective and efficient moulded product release. An even further option to use the displaceable barrier element is to close off the feed channel after filling the mould cavity with liquid moulding material but before the moulding material in the feed channel is cured. By closing off the feed channel already in this early stage of the moulding process (before the at least partial curing of the moulding material in the feed channel) the situation of the filling of the mould cavity is not dependent anymore of the situation before the closed off feed channel (so e.g. the situation of the plunger(s) feeding the moulding material towards the mould cavity. This also provides the additional opportunity to control the pressure on the liquid moulding material in the moulding cavity (so before the curing of the moulding material in the moulding cavity takes place) by controlling the force of the mould parts to clamp the carrier (also referred to as “the clamping force of the mould parts). By for instance increase of the clamping force after the moulding cavity is “isolated” from the feed channel by blocking the feed channel with the displaceable barrier element the moulding process may even be compared with “compression moulding” wherein the pressure on the moulding material is dependent on the clamping force. An advantage may be that the pressure on the moulding material in the moulding

cavity (cavities) may be more constant over a mould cavity compared to the situation wherein the pressure is exerted from the runner wherein a pressure change occurs from the connection of the runner to the moulding cavity to locations in the moulding cavity on a distance of the connection of the runner to the moulding cavity. The more even
 5 pressure distribution in the moulding cavity may lead to an increase of the moulding quality. A further advantage of the “isolation” of the mould cavity from the runner in this early stage of the moulding process is that it enables to vary the pressure on the moulding material in the moulding cavity during the moulding (so e.g. to raise the pressure during a sort period of time once or several times). The additional freedom in
 10 pressure control on the moulding material before and during the curing of the moulding material in the moulding cavity provides an additional measure of freedom in control of the moulding process.

The mould part with the feed channel and the displaceable barrier element may be
 15 provided with a drive for controlling the relative position of the displaceable barrier element to the feed channel for moulding material. The provision of a drive system to control the position of the displaceable barrier element enables to optimise the use of the barrier segment. As an alternative, or in combination with a driven displaceable barrier element control, the displaceable barrier element may be resiliently connected to
 20 the mould part. The resilient connection may be provided with a positioning element to hold the displaceable barrier in a position wherein the displaceable barrier is not (or only limited) blocking the feed channel for moulding material in a closed situation of the mould. However when the mould is opened the positioning element may be constructed such that the positioning element is not supported anymore by a counter
 25 mould part such that the resilient connection forces the positioning element into the feed channel.

The mould part may also be provided with a foil handling mechanism. As to shield the displaceable barrier element from the moulding material a foil layer may be applied in
 30 between the wall of the feed channel and the displaceable barrier element. The use of a foil layer prevents (liquid) moulding material to penetrate between the wall of the feed channel and the displaceable barrier element. The foil layer may also cover the wall of the moulding cavity. Apart from keeping the mould part clean a further advantage of the use of a foil layer to shield the mould part is that it supports an easy release of the

moulded product from the mould part. The first step of the release may be provided by activating the displaceable barrier element pushing onto the foil and after a partial and/or local release of the foil from the mould part further release may be provided by for instance gas pressure. The mould part may thus also be provided from a least one
5 gas outlet to blow a gas between the foil material (covering the moulded product) and the mould part.

The displaceable barrier element on the free end directed towards the contact side of the mould part may be provided with a tapering end. Such a tapering end provides the
10 opportunity to separate the moulding material in the feed channel with the displaceable barrier element, especially when the moulding material is not fully hardened yet.

The mould part may also be provided with a plurality of feed channels for moulding material, each connecting to a displaceable barrier element. Often moulds are provided
15 with a plurality of feed channels. For such moulds the choice is to provide one or more of the plurality of feed channels with a displaceable barrier element. Dependent on the situational conditions a part or all of the plurality of feed channels may be provided each with an individual displaceable barrier element. The plurality of feed channels for moulding material may be connected to a single moulding cavity. The present invention
20 may be applied in mould configurations with only a single mould cavity or plural mould cavities provided in a mould part. Even a combination of two mould parts, both with at least one moulding cavity, may connect on opposite sides of the carrier and so to arrange layers of moulding material on the two opposite sides of the carrier.

Furthermore the mould part with the feed channel for moulding material may also be
25 provided with an outlet channel recessed into the contact surface and connecting to the mould cavity for discharge of gas from the mould cavity.

For more control of the moulding conditions the mould part with a moulding cavity may be provided with at least one sensor for detecting the pressures prevailing in the mould
30 cavity and/or the feed channel for moulding material.

In a further alternative embodiment a first mould part may be provided with an additional clamping mould part, which additional clamping mould part is movable in respect to the first mould part to clamp at least one edge of a board to the first mould

part, which clamping mould part in a closed position of the mould connects to the feed for moulding material. By including such clamping mould part a covered side of the board may kept free of moulding material which may be useful during further processing of the moulded product.

5

The present invention also provides a moulding apparatus for at least partially encapsulating a carrier with electronic components, comprising: a press including at least two mould carriers and a drive for relative movement of mould carriers; a mould according to the present invention and as disclosed above; and a feed for liquid

10 moulding material connecting onto the feed channel for moulding material. The feed for liquid moulding material may comprise one or more plungers which are each movable in a cylinder casing. Also the moulding apparatus may be provided with an intelligent control for controlling the press, the feed for liquid encapsulation material and the displaceable barrier element in the mould. In such a moulding apparatus the

15 displaceable barrier element will provide the additional functionality as already explained in relation to the mould according to the present invention. For intelligent control and/or steering of the displaceable barrier element the moulding apparatus may be provided with an (electronic) intelligent control system. Also included in such intelligent control system may be means for controlling the closing pressure with which

20 the mould parts connect to the carrier so that the pressure exerted by the liquid moulding material on the mould may partially or fully be compensated by a regulated closing pressure.

The present invention also provides a method for at least partially encapsulating a

25 carrier with electronic components, comprising the processing steps: A) placing a carrier with electronic components on a first mould part; B) moving the mould parts towards each other such that the carrier with electronic components is clamped between at least two mould parts and the electronic components to be encapsulated are enclosed by a mould cavity recessed into a contact side of a mould part; C) feeding a liquid

30 moulding material via a feed for liquid encapsulation material recessed into a contact side of a mould part into the mould cavity; and D) moving apart the mould parts to remove the carrier with at least partially cured moulded material from the mould parts; wherein during processing step C) a displaceable barrier element is moved in the feed for liquid encapsulation material to control the liquid moulding material flow, and

wherein during processing step D) the displaceable barrier element is moved to push the at least partially cured moulding material out of the feed. With this method the moulding process of carriers with electronic components may be further optimised as it enables better control of the feed of the encapsulating material and it facilitates an improved removal of the moulded product from the mould. The displaceable barrier element may be moved in a direction substantially perpendicular to a contact surface of the mould part wherein the feed for liquid encapsulation material is recessed. For a further explanation of the advantages of the method according to the present invention reference is made to the above listed advantages of the mould according to the present invention. During the closing of the mould a contact surface at least partially enclosing a mould cavity may medium-tight (so tight that a medium like a gas or liquid may not pass) connect onto the carrier to prevent leakage of liquid moulding material between the contact surface of a mould part and the carrier. Furthermore the closing pressure exerted on the carrier by the mould parts may be controlled during feed of the moulding material to prevent the contact surface to exert to high pressure on the carrier at the moments when the liquid moulding material is not providing substantial counter-pressure and to prevent the contact surface to exert to low pressure on the carrier at the moments when the liquid moulding material is providing substantial counter-pressure. After to moulding process is completed and the moulded product is removed from the mould the carrier may be subdivided into smaller segments.

After a carrier with electronic components may be placed on a first mould part according to processing step A) and before the mould parts are moved towards each other such that the carrier with electronic components is clamped between two mould parts according to processing step B) at least one edge of the board the board is clamped to the first mould part with an additional mould part which additional mould part also guides the liquid moulding material to the mould cavity during processing step C). This type of moulding is also referred to a “top edge moulding” as the liquid moulding material is fed over the edge with an intermediate mould part covering the edge of the carrier. The advantages are that the edge of the carriers is kept free of moulding material and that the carrier is clamped in its position.

The method may also comprise that before feeding a liquid moulding material according processing step C) via a feed for liquid encapsulation material recessed into a

contact side of a mould part into the mould cavity at least a part of the mould part is covered by a foil layer. The advantages of using a foil layer, shielding the mould from contamination and enabling easy release of the moulded product, are already explained in more detail above in relation to the mould part according the present invention which
 5 motivation is here incorporated by reference in relation to the method according the present invention.

The method may also provide that the displaceable barrier element after finishing processing step C) is moved further in the feed for liquid encapsulation material to
 10 separate the mould cavity filled with liquid moulding material from the runners part faced away from the mould cavity and that the force that a closing force of the mould parts is varied to change the pressure on the moulding material in the moulding cavity. Also some advantages of this embodiment of the method according the present invention, especially the enhanced control of the pressure on the moulding material in
 15 the moulding cavity during the curing, are explained above and are here incorporated by reference.

Finally the present invention also provides a carrier with electronic components, which electronic components are at least partially encapsulated with moulding material
 20 according to the method according the present invention as specified above. The carrier may be a semiconductor wafer, a layered substrate, a glass carrier or any other carrier or carrier combination for electronic components.

The present invention will be further elucidated on the basis of the non-limitative
 25 exemplary embodiments shown in the following figures. Herein shows:

figure 1 a perspective view of a mould part of a mould according to the invention;
 figures 2A - 2C three successive cross-sectional views of the method
 encapsulating a carrier with electronic components according to the invention;
 30 figure 3A a cross-sectional view of a second embodiment of a mould according to the invention;
 figure 3B a front view on a displaceable barrier element of the mould part shown in figure 3A; and

figure 4 a perspective view of an alternative embodiment of a displaceable barrier element.

Figure 1 shows schematic perspective view on a mould part 1 of a mould for encapsulating carriers for electronic components. Into the mould part 1 a mould cavity 2 and a moulding material feed channel 3 are recessed while a contact surface 4 – except for the feed channel - surrounds the mould cavity 2. For moulding a carrier (not shown in this figure) is placed against a contact surface 4 such that the electronic components to be moulded (also not shown here) are located in the mould cavity 2. Though the feed channel 3 (also referred to as “runner”) subsequently a liquid moulding material is fed to the mould cavity 2. To regulate the flow of moulding material in the feed channel 3, and thus also to regulate the moulding material flow into the mould cavity 2, a displaceable barrier element 5 is moveable in the feed channel 3 according arrow P₁. The direction of movement of the displaceable barrier element 5 substantially perpendicular to the contact surface 4. When the displaceable barrier element 5 is moved more into the feed channel 3 the displaceable barrier element 5 will more obstruct the feed channel 3 and thus, as a result, during moulding the flow of liquid moulding material into the mould cavity 2 will be limited. By moving the displaceable barrier element 5 more out of the feed channel 3 the feed channel will be less obstructed and thus the flow of liquid moulding material into the mould cavity 2 will increase.

In figure 2A a cross-sectional view of a mould part 10 and a carrier 11 with electronic component 12 showing a processing step before moulding material is fed to a moulding cavity 13. In the mould part 10 a feed channel 14 for moulding material is recessed into a contact surface 15. The figure also shows a displaceable barrier element 16 connecting to the feed channel 14 for regulating the size of an moulding material passage in the feed channel 14. The displaceable barrier element 16 is shown in a position where it partially obstructs the feed channel 14. For the displacement of the barrier element 16 in the mould part 10 a drive 17 is incorporated which is able to move the barrier element 16 in a direction substantially perpendicular to the contact surface 15 of the mould part 10. For control of the drive 17 - and thus for control of the position of the displaceable barrier element 16 – a power and control line 18 is connected to the drive, which will be connected with an intelligent control system (which is not shown in this figure). Also depicted in this figure is a foil layer 21 which covers the mould part 10, at least the wall

forming the feed channel 14 and the wall forming the moulding cavity 13, from the volume of the feed channel 14 and the moulding cavity 13 to be filled with moulding material (see figure 2B). The foil layer 21 keeps the barrier element 16 free of contact with moulding material (and thus prevents it to become polluted with remaining
 5 moulding material) and assists an easy release of moulded products from the mould part 10.

In figure 2B a cross-sectional view of the mould part 10 from figure 2A is shown again, however now in the situation wherein a moulding material 19 is fed through the feed
 10 channel 14 which also fills the moulding cavity 13. For control of the filling of the moulding cavity 13 in this specific situation the barrier element 16 is moved more away (in this situation upward) from the feed channel 14 compared to the position of the barrier element 16 shown in figure 2A. The foil layer 21 keeps mould part 10 free from contact with the moulding material 19.

15 Also in figure 2C a cross-sectional view of the mould part 10 from figures 2A and 2B is shown however this figure shows the situation after the moulding material 19 in the feed channel 14 and the moulding cavity 13 is at least partially cured. The barrier element 16 is in this situation used as a pusher (“ejector”) to make the moulded carrier
 20 11 with electronic component 12 free from the mould part 10. During the release of the cured moulding material 19 the foil layer 21 keeps attached to the moulding material 19. For instance the detachment of moulded product 20 may be further supported with a gas pressure system (which not shown here).

25 In figure 3A a cross-sectional view of a part of a complete mould 30 is shown as well as a feed 31 for liquid moulding material. Moulding material 32 is supplied by a plunger 33 which is movable in a cylinder casing 34. The mould 30 is provided with an upper mould part 35 and a lower mould part 36. Both mould parts 35, 36 can be moved apart for the purpose of placing a carrier 37 for encapsulating or removing an encapsulated
 30 carrier 38. The moulding material 32 is transferred by the plunger 33 through a feed channel 39 and subsequently into a moulding cavity 40. In this figure also an additional mould part 41 is provided that clamps an edge part of the carrier 37 against the lower mould part 36. The additional mould part 41 in this embodiment is combined with the cylinder casing 34. The moulding material 32 thus flows through the feed channel 39,

over a part of the additional mould part 41 to the moulding cavity 40. In the upper mould part 35 a displaceable barrier element 42 is incorporated connecting to the feed channel 39, which displaceable barrier element 42 may be driven by a spring package 43. For a further explanation of the working of the drive by the spring package 43 see also figure 3B wherein the displaceable barrier element 42 is shown in a side view (compared to the cross-sectional view of figure 3A). The displaceable barrier element 42 is provided with protruding parts 44 that in a closed situation of the mould 30 rests on the lower mould part 36. When the upper and lower mould parts 35, 36 are moved apart the protruding parts 44 of the displaceable barrier element 42 are not supported anymore by the lower mould part and thus the pressure exerted by the springs 43 may push the displaceable barrier element 42 downwards so that the displaceable barrier element 42 acts as a ejector.

In figure 4 an alternative embodiment of a displaceable barrier element 50 is shown. Dependent on the shape of a feed channel the barrier element 50 is cooperating with the shape may be adapted. In the illustrated embodiment the contact part 51 of the displaceable barrier element 50 is curved. Also different compared to the embodiments shown in the previous figures here the drive 52 is embodied as two cylinders.

It will be apparent that the measures discussed in the different embodiments may be combined with each other.

Claims

1. Mould for at least partially encapsulating a carrier with electronic components, comprising:

- 5 - at least two mould parts, at least one of which being provided with at least one mould cavity recessed into a contact side for enclosing electronic components placed on a carrier, the contact surface at least partially enclosing the mould cavity for medium-tight connection onto the carrier; and
- 10 - a feed channel for moulding material recessed into the contact surface of the mould part provided with the mould cavity;

wherein in the mould part with the feed channel is provided with a displaceable barrier element connecting to the feed channel for regulating the size of an moulding material passage in the feed channel, which barrier element is displaceable in a direction substantially perpendicular to the contact surface.

15

2. Mould as claimed in claim 1, **characterized in that** the mould part with the feed channel and the displaceable barrier element is provided with a drive for controlling the relative position of the displaceable barrier element to the feed channel for moulding material.

20

3. Mould as claimed in claim 1 or 2, **characterized in that** the displaceable barrier element is resilient connected to the mould part.

4. Mould as claimed in any of the foregoing claims, **characterized in that** the mould part is provided with a foil handling mechanism.

25

5. Mould as claimed in any of the foregoing claims, **characterized in that** the mould part is provided with a plurality of feed channels for moulding material, each connecting to a displaceable barrier element.

30

6. Mould as claimed in any of the foregoing claims, **characterized in that** the mould part with the feed channel for moulding material is also provided with an outlet channel recessed into the contact surface and connecting to the mould cavity for discharge of gas from the mould cavity

7. Mould as claimed in any of the foregoing claims, **characterized in that** the mould part with a moulding cavity is provided with at least one sensor for detecting the pressures prevailing in the mould cavity and/or the feed channel for moulding material.
- 5
8. Mould as claimed in any of the foregoing claims, **characterized in that** at a first mould part is provided with an additional clamping mould part, which additional clamping mould part is movable in respect to the first mould part to clamp at least one edge of a board to the first mould part, which clamping mould part in a closed position
- 10 of the mould connects to the feed for moulding material.
9. Moulding apparatus for at least partially encapsulating a carrier with electronic components, comprising:
- a press including at least two mould carriers and a drive for relative movement
 - 15 of mould carriers;
 - a mould as claimed in any of the foregoing claims; and
 - a feed for liquid moulding material connecting onto the feed channel for moulding material.
- 20 10. Moulding apparatus as claimed in claim 9, **characterized in that** the feed for liquid moulding material comprises a plunger which is movable in a cylinder casing.
11. Method for at least partially encapsulating a carrier with electronic components, comprising the processing steps:
- 25 A) placing a carrier with electronic components on a first mould part;
 - B) moving the mould parts towards each other such that the carrier with electronic components is clamped between at least two mould parts and the electronic components to be encapsulated are enclosed by a mould cavity recessed into a contact side of a mould part;
 - 30 C) feeding a liquid moulding material via a feed for liquid encapsulation material recessed into a contact side of a mould part into the mould cavity; and
 - D) moving apart the mould parts to remove the carrier with at least partially cured moulded material from the mould parts;

wherein during processing step C) a displaceable barrier element is moved in the feed for liquid encapsulation material to control the liquid moulding material flow, and wherein during processing step D) the displaceable barrier element is moved to push the at least partially cured moulding material out of the feed.

5

12. Method as claimed in claim 11, **characterized in that** the displaceable barrier element is moved in a direction substantially perpendicular to a contact surface of the mould part wherein the feed for liquid encapsulation material is recessed.

10 13. Method as claimed in claim 11 or 12, **characterized in that** after a carrier with electronic components is placed on a first mould part according to processing step A) and before the mould parts are moved towards each other such that the carrier with electronic components is clamped between two mould parts according to processing step B) at least one edge of the board the board is clamped to the first mould part with
15 an additional mould part which additional mould part also guides the liquid moulding material to the mould cavity during processing step C).

14. Method as claimed in any of the claims 11 - 13, **characterized in that** before feeding a liquid moulding material according processing step C) via a feed for liquid
20 encapsulation material recessed into a contact side of a mould part into the mould cavity at least a part of the mould part is covered by a foil layer.

15. Method as claimed in any of the claims 11 - 14, **characterized in that** the displaceable barrier element after finishing processing step C) is moved further in the
25 feed for liquid encapsulation material to separate the mould cavity filled with liquid moulding material from the runners part faced away from the mould cavity and that the force that a closing force of the mould parts is varied to change the pressure on the moulding material in the moulding cavity.

30