

CONDUCTIVE ADHESIVE FILM

TECHNICAL FIELD

[0001] The present invention relates to an adhesive film that shows conductivity, which can be used for packaging semiconductor device and heat radiation member etc., a dicing die bonding film obtained by combining said film with a dicing tape, and a method for processing semiconductor wafer using the same.

Background Art

[0002] The use of solder, which contains lead, has widely been known as a method for packaging semiconductor device on lead frames etc. However, in recent years, due to heightened awareness on environmental issues, movement to regulate the use of lead is spreading. Under such circumstances, lead-free solder pastes such as sintered silver, Sn-Bi type, Cu-Sn type, Cu-Ag-Sn type are attracting attention. In particular, sintered silver and Cu-Sn type solder, which can be sintered at a relatively low temperature, while showing high melting temperature after being sintered, is extremely useful, since it can achieve both easy packaging and high heat resistance.

[0003] However, sintered silver are very costly, and require sintering at a high temperature of 300°C or above, thereby being likely to cause damage on other materials surrounding the semiconductor device. Further, because lead-free solders are poor in wet-spreading on semiconductor rear-side electrodes, in order to obtain sufficient adhesive strength, one had to use plenty on the semiconductor chip to be installed. Therefore, there was a problem in that balancing overflow and bond strength was difficult.

[0004] To deal with such problems, adhesive tapes containing conductive particles in epoxy resins or acrylic resins have been proposed (Patent Documents 1 to 3). By dicing a wafer along with the adhesive tape after fixing such adhesive tape on the semiconductor wafer, problems that arise when installing semiconductor chips can be solved.

[0005] However, there are issues concerning the heat resistance of such resins

at environments of, for example, 250°C or higher, and when combined with devices that use wide-gap semiconductors such as Si-C, it was difficult to make the most of the excellent heat resistance of the device. While enlarging the crosslinking density of the epoxy or acrylic resin improves heat resistance, the hardness of the cured resin becomes excessive, thereby leading to a lack of stress relaxation property and causing problems of chips and lead frames curving.

[0006] For such problems regarding the balance of heat resistance and stress relaxation, the use of silicone resin, which is flexible while showing excellent heat resistance, has been proposed.

[0007] However, when such silicone resins are used as binders, the diffusion of metals during sintering becomes poor. In particular, because sintering between metal particles is inhibited when combined with lead-free solders that form intermetallic compounds, there was a problem in that obtaining sufficient conductivity for use in, for example, rear-side electrodes of high voltage or high frequency power semiconductors was difficult.

RELATED ART

Patent Documents

[0008] Patent Document 1: JP-A-2004-160508
Patent Document 2: WO2011/083824
Patent Document 3: US2014/0120356 A1
Patent Document 4: JP-A-2013-221082
Patent Document 5: WO2010/103998


SUMMARY

[0009] The present disclosure was made in order to solve the above-described problems, and provides an adhesive film that shows excellent heat resistance while showing excellent stress relaxation property, which further shows high conductivity that enables application to rear-side electrode for power semiconductors without the use of expensive precious metals such as silver, which also shows sufficient adhesive strength

without protruding from the device, and a method for processing semiconductors using the same.

[0009a] In a first aspect, there is provided a conductive adhesive film, which comprises two or more types of metal particles including at least Cu, and a polymer that has a polydimethylsiloxane structure, wherein said polydimethylsiloxane structure:

- i) contains -COOH, -CR_x(OH)_y, or -NR₂ as a functional group, where R is selected from H, alkyl, or aryl group, and x+y=3;
- ii) contains a double bond or
- iii) has the following structure;



and wherein the conductive adhesive film contains at least one type of flux component selected from alcohol, ketone, carboxylic acid, or amine, wherein the flux component is in a state of phase separation with the polymer that has the polydimethylsiloxane structure.

[0010] That is, the present disclosure is related to a conductive adhesive film, which comprises two or more types of metal particles including at least Cu, and a polymer that has a polydimethylsiloxane structure, a dicing die bonding film, which comprises the conductive adhesive film and a dicing tape, and further, a method for processing semiconductor using the same.

Further, it is preferable that the metal particles contain a component with a melting point of 250°C or lower, and are capable of forming an intermetallic compound.

Further, in order to facilitate intermetallic compound reaction, it is preferable that the conductive adhesive tape contains at least one type of flux component selected from alcohol, ketone, carboxylic acid, or amine, wherein the flux component is in a state of phase separation with the polymer that has a polydimethylsiloxane structure.

Furthermore, it is preferable that at least part of the polymer that has a polydimethylsiloxane structure contains -COOH, -CR_x(OH)_y, or -NR₂ as a functional group (where R is selected from H, alkyl, or aryl group, and x+y=3), and further, contains

a double bond.

Furthermore, it is preferable that the amount of the metal particle based on the entire film is 55 volume% or more and that the amount of the polymer that has a polydimethylsiloxane structure is 5 volume% or more.

Further, it is preferable that the conductive adhesive film comprises a radical generator with a one-hour half-life temperature of 200°C or higher.

[0010a] In another aspect, there is provided a dicing die bonding film, which comprises the conductive adhesive film as defined above and a dicing tape laminated thereon.

[0010b] In another aspect, there is provided a method for processing semiconductor wafer using the conductive adhesive film as defined above.

[0010c] In another aspect, there is provided a method for processing semiconductor wafer using the dicing die bonding film as defined above.

Effect

[0011] By dicing after adhering to a semiconductor wafer, the above-described adhesive film of the present disclosure allows semiconductor chips to be packaged on a lead frame, using proper quantities of the adhesive film in a state of lamination on the rear-side electrode.

Preferably, it contains a metal component with a melting point of 250°C or lower and can be sintered at a temperature of 250°C or lower, contains Cu, and is capable of

forming intermetallic compounds.

Further, because the binder resin is of a silicone-type, it shows high heat resistance up to a temperature of 300°C after sintering.

Furthermore, by combining a flux component that is in a state of phase separation with the silicone component, a silicone component modified by the functional group having flux function, a radical-type catalyst that accelerates the curing reaction of the silicone at a temperature of 200°C or higher, or a combination thereof, the intermetallic reaction proceeds smoothly, thereby enabling high conductivity.

Further, by including Cu, the film can be provided at a lower price than, for example, sintered silver, and since it does not include lead, environmental burden becomes low, too.

[0012] The adhesive film of the present disclosure is especially suitable for adhering the rear-side electrode of a high-voltage, high-frequency power semiconductor to a lead frame etc., or for adhering a lead frame packaged with power semiconductors etc. to a heat dissipation member, and in particular, for packaging wide-gap semiconductor device, which is expected to operate at high temperature.

BRIEF DESCRIPTION OF DRAWINGS

[0013]

[FIG. 1] FIG. 1 shows an adhesive film with dicing tape that uses the adhesive agent of the present invention.

[FIG. 2] FIG. 2 is a sectional scheme of an embodiment of the adhesive film with dicing tape that differs from FIG. 1.

DESCRIPTION OF SOME EMBODIMENTS

[0014] The present invention comprises at least a metal particle and a silicone-type resin that serves as a binder.

[0015] (Metal Particles)

The metal particle contains at least Cu. The form of the Cu particle is not

particularly limited, but may be, for example, spherical or flake-shaped, and preferably has a BET diameter of 0.01 to 30 μm , or more preferably, is a spherical particle with a BET diameter of 0.1 to 10 μm . The Cu particle preferably has some form of coating performed to prevent oxidation of the surface. As such coating, Au, Ag, organic acid, alcohol, thiol, alkylamine, silane coupling agent, titanium complex, silicone resin etc. may be used, but from the view point of price and coatability, organic acids, alcohols, thiol, and alkylamines are particularly favorable.

[0016] The metal particle also contains metal components other than Cu. Such metal component may be any metal other than lead, without limitation, and may be Au, Ag, Pt, Ti, Al, Ni, Fe, Co, Mo, Sn, Zn, Pd, Ga, Ge, In, Sb, Bi, metallic silicon, boron, and alloys thereof or combinations thereof. However, by selecting a component with a melting point of 250°C or lower as at least part of it, it becomes favorable in that its sintering temperature can be lowered.

As such low-melting point metal, Sn, Ga, In, Sn-Bi alloy, Sn-Zn alloy, Sn-Ag alloy, Sn-Au alloy, Sn-Mg alloy, In-Sn alloy, Ga-Sn alloy, Ga-In-Sn alloy etc., and combinations thereof may be used.

In order to attain both, low-temperature workability before sintering and heat resistance after sintering, the metal particle is preferably Sn, which forms intermetallic compounds with Cu, or an alloy of Sn and another metal.

Further, the metal particle is preferably a combination containing Cu and a transition metal (Ag, Ni, Fe, Zn, Bi) and Sn, which is capable of forming an intermetallic compound. Among these, Sn-Bi alloy and Sn-Zn alloy are favorable because they are able to lower the melting point to below 200°C.

[0017] Since low volume resistivity can be obtained by sintering, the amount of the metal particle is preferably 55 volume% or more, based on the entire film, and more preferably, 60 volume% or more.

[0018] (Silicone Resin Binder Containing Polymer with a Polydimethylsiloxane Structure)

The silicone resin that serves as a binder comprises at least a polymer that has a

polydimethylsiloxane structure. The polydimethylsiloxane structure adds relaxation ability to the adhesive film, thereby suppressing curvature of the lead frame and semiconductor chip.

[0019] The polymer that has a polydimethylsiloxane structure is preferably crosslinked or crosslinkable from the view point of heat resistance. On the other hand, it is preferable that it is not crosslinked or crosslinked very lightly prior to sintering, so as not to inhibit metal diffusion for the formation of intermetallic compounds. As a polymer that contains crosslinkable polydimethylsiloxane structure, those containing hydrolyzable siloxane and those containing C=C double bond are preferable. However, from the view point of suppressing out gas components, those containing C=C double bonds, in which crosslinking proceeds through addition reaction, are more preferable. As such polymer, vinyl-modified or aryl-modified polydimethylsiloxane can be listed.

[0020] Furthermore, from the view point of adding flux function, it is preferable that at least part of the polymer that has a polydimethylsiloxane structure contains -COOH, -CR_x(OH)_y, or -NR₂ as a functional group (where R is selected from H, alkyl, or aryl group, and x+y=3).

[0021] In particular, from the view point of easy film-forming of the adhesive, a both terminal vinyl-modified polydimethylsiloxane with a weight-average molecular weight of 10,000 or more is preferable, and more preferably, it may be a both terminal vinyl-modified polydimethylsiloxane with a weight-average molecular weight of 100,000 or more.

[0022] As the curing agent of the polydimethylsiloxane, a hydrosiloxane compound that contains Si-H bond is favorable. Such as hydrosiloxane compound, a polyhydrogen-modified polydimethylsiloxane, wherein part of the methyl group in the polydimethylsiloxane is substituted by a hydrogen is preferable, from the view point of its stability and low-pollution property.

[0023] In addition to the above, silicone resins containing many vinyl groups in the molecule may be added to control hardness and tack, and silane coupling agents and other additives may be added to enhance adhesiveness and dispersion of metal particles.

In the adhesive film of the present invention, it is preferable that the above-described components are provided in a crosslinkable state or in a crosslinked state. However, it is more preferable that parts of the components are provided crosslinked, while some unreacted C=C double bonds remain, making it possible for the crosslinking to proceed by heating.

[0024] In order to avoid compromising sinterability and conductivity after sintering, the amount of the polymer that has a polydimethylsiloxane structure is preferably 5 volume% or more based on the entire film, and more preferably, is 20 volume% or more, and even more preferably, is 25 volume% or more.

[0025] (Radical Generator)

As a catalyst that accelerates hardening reaction, noble metal complexes such as platinum complex, and radical-type catalysts such as organic peroxides, diazo compounds, α acyloin, aromatic ketone, 2,3-diaryl-2,3-dimethylbutane etc., may be listed, but radical initiators, which are less likely to be affected by tin, and for which the reaction temperature can be easily controlled, is preferable. Among such radical initiators, those of thermal fission-type, with a one-hour half-life temperature of 200°C or higher are especially preferable, since they suppress the inhibition of intermetallic reaction due to the crosslinking reaction proceeding too quickly, while sufficiently sintering at a temperature of 250°C or lower, making it easy to obtain low volume resistivity. Those with a one-hour half-life temperature of 230°C or more to 260°C or lower are even more preferable.

[0026] As such radical initiators, for example, 2,3-diaryl-2,3-dimethylbutane etc. may be listed. These radical initiators may also be combined with noble metal catalysts.

[0027] The amount of such radical generators are preferably 0.1 percent by mass or more, based on the entire film.

[0028] (Flux)

In order to accelerate intermetallic reaction, it is preferable to add flux.

As flux, any compound may be used, as long as it does not inhibit the hardening

reaction of the curable resin and other curable resins. For example, alcohols, carboxylic acids, inorganic acids, alkanolamines, phenols, rosins, chloride compounds and their salts, halide compounds and their salts, may be listed, but alcohols, aldehydes, ketones, carboxylic acids, and amines are preferable.

The flux may be of one type or may be used as a combination of 2 or more types.
[0029] In a specific embodiment, the flux is composed of carboxylic acid and a salt of a tertiary amine or mixture thereof, and may be of potentiality.

[0030] As the aforementioned alcohol, for example, ethylene glycol, diethylene glycol, triethylene glycol, propylene glycol, octene glycol, polyethylene glycol, glycerin, propanediol, and mixtures thereof may be listed.

[0031] As the aforementioned carboxylic acid, for example, acrylic acid, methacrylic acid, maleic acid, fumaric acid, valeric acid, hexanoic acid, heptanoic acid, 2-ethylhexanoic acid, octanoic acid, 2-methyl heptanoic acid, 4-methyl octanoic acid, nonanoic acid, decanoic acid, neodecanoic acid, dodecanoic acid, tetradecanoic acid, lauric acid, myristic acid, palmitic acid, stearic acid, oleic acid, linoleic acid, linolenic acid, lactic acid, malic acid, citric acid, benzoic acid, phthalic acid, isophthalic acid, oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pyruvic acid, butyric acid, pivalic acid, 2,2-dimethyl butyrate, 3,3-dimethyl butyrate, 2,2-dimethyl valerate, 2,2-diethyl butyrate, 3,3-diethyl butyrate, naphthenic acid, cyclohexanedicarboxylic acid, 2-acryloyloxyethyl succinate, 2-methacryloyloxyethyl succinate, 2-acryloyloxyethyl hexahydro phthalate, 2-methacryloyloxyethyl hexahydro phthalate, 2-acryloyloxyethyl phthalate, 2-methacryloyloxyethyl phthalate, etc. may be listed. In a particular embodiment, the carboxylic acid has a molecular weight of 150 to 300.

[0032] In another embodiment, dicarboxylic acid are used. As such dicarboxylic acid, oxalic acid, malonic acid, succinic acid, glutaric acid, fumaric acid, maleic acid etc. may be listed. The tertiary amine is used as a mixture or salt with acidic functional groups, and forms a buffer solution or salt with the acidic functional group of the carboxylic acid in order to prevent excessively rapid reaction with other

resin components, or to suppress migration.

[0033] The amine may be a monomer, oligomer, or polymer combined with one or more compound. In particular, alkanolamines are preferable, and for example, as tertiary alkanolamines such as triethanolamine and N,N,N, N,N,N',N'-Tetrakis (2-hydroxyethyl) ethylenediamine can be listed as those favorable in forming buffer mixtures or salts with the carboxylic acidic functional group.

[0034] As aldehydes, aldoses such as glutaraldehyde, perillaldehyde, and glyceraldehyde may be listed.

As ketones, acetylacetone, β diketones such as 3,5-heptanedione, or ketoses such as erythrulose may be listed.

[0035] By having such flux components in a state of phase separation with the polymer having the polydimethylsiloxane structure, a phase that is unevenly distributed near the high polarity metal particles can easily be formed, thus being able to express its flux function even more, and being further preferable.

[0036] The amount of such flux components added is preferably 1 percent by mass or more to 5 percent by mass or less, based on the entire film.

[0037] (Other Optional Components)

In another embodiment, the conductive adhesive composition of the present invention may further include one or more additive such as a plasticizer, an oil, a stabilizer, an antioxidant, a corrosion preventative, an inhibitor, a chelating agent, a silane coupling agent, a leveling agent, a pigment, a dye, a polymer additive, a defoaming agent, a preservative, a thickener, a rheology-adjusting agent, a moisturizing agent, a tackifier, a dispersant, and water.

[0038] (Method for Producing Adhesive Film)

The adhesive film may be produced by ordinary methods. For example, after preparing a varnish containing a curable resin, the varnish may be applied on a cover film at a certain thickness to form a coated layer, and drying the coated layer under a certain condition, the adhesive film may be produced. The method of application is not particularly limited, and roll coating, screen coating, and gravure coating etc. may

be listed. Further, as the drying condition, for example, drying may be performed at a temperature of 80 to 130°C for a time range of 1 to 5 minutes. As the cover film, polyethylene-terephthalate (PET), polyethylene or polypropylene, or a plastic film or paper that is coated with a peeling agent such as fluorine-type peeling agent and long-chain alkylacrylate-type peeling agent, may be used. By using such method to obtain a film, it becomes easier to maintain the thickness between the adherend and to handle, and is thus, preferable. In order to form a film from the adhesive composition, the curable resin preferably has a molecular weight of 1000 or more, or contains polymer components.

[0039] The thickness of the adhesive film is not particularly limited, but may preferably be 1 to 300 μm . When adhering two layers of adherends, the thickness is preferably 5 to 60 μm , and when stress-relaxation is required, the thickness is preferably 60 to 200 μm .

[0040] Further, by combining the adhesive film with a dicing tape in the form of a laminate, the adhesive film may be used favorably as an adhesive film with a dicing tape. A dicing tape is a tape that is used mainly in the process of cutting and dicing integrated circuits and packages formed on a semiconductor wafer.

[0041] Since the adhesive film is radically curable, it may be used in combination with a dicing tape that has a radiation curable adhesive layer that is irradiated beforehand, or a pressure-sensitive adhesive layer on the part of the wafer that is to be adhered.

[0042] FIG 1 and FIG 2 are schematic diagrams that show the sectional views of one embodiment of the adhesive film with dicing tape of the present invention.

[0043] In FIG 1, the structure of the adhesive film with dicing tape 10, in which the adhesive film 3 is laminated on the dicing tape 11, is shown. The dicing tape 11 is composed of a pressure-sensitive adhesive layer 2 laminated on a substrate 1, and the adhesive film 3 is provided on top of the pressure-sensitive adhesive layer 2. As shown in the adhesive film with dicing tape 12 of FIG 2, the adhesive film 3' may be formed only on the work-sticking part.

[0044] The substrate 1 is the strength matrix of the adhesive film with dicing tape 10, 12 and preferably shows ultraviolet transmission property and expandability when expanded. For example, polyolefins such as polyethylene, polypropylene, polybutene, and polymethylpentene, ethylene-vinyl acetate copolymer, ionomer resin, ethylene-(meth)acrylic acid copolymer, ethylene-(meth)acrylic acid ester (random, alternating) copolymer, ethylene-butene copolymer, ethylene-hexene copolymer, polyurethane, polyesters such as polyethylene terephthalate and polyethylene naphthalate,, polycarbonate, polyimide, polyether ether ketone, polyether imide, wholly aromatic polyamide, polyphenylsulfide, aramid (paper), glass, glass cloth, fluorine resin, polyvinylchloride, polyvinylidenechloride, cellulose-type resin, silicone resin, crosslinked bodies of the aforementioned resins, metal (foil), paper etc. can be listed.

[0045] In order to enhance adhesion, retention, etc., the surface of the substrate 1 may be subjected to conventional surface treatments such as various chemical and physical treatments like chromic acid treatment, ozone exposure, flame exposure, high voltage lightening exposure, ionizing radiation treatment, coating treatment using primers (such as the later-described adhesive substance).

[0046] As the substrate 1 , the same or different materials may be arbitrarily selected and used, and several types may be blended and used as necessary. Further, different types may be layered and used.

[0047] The thickness of substrate 1 is not particularly limited, but may generally be about 50 to 200 μm .

[0048] The adhesive material to be used in the pressure-sensitive adhesive layer 2 is not particularly limited, and general pressure-sensitive adhesive such as acrylic-type adhesive and rubber-type adhesive.

[0049] As the adhesive material used to form the pressure-sensitive adhesive layer 2, radiation-curable resins may also be used. The adhesive strength of radiation-curable resins may easily be reduced by irradiation of radiation such as ultraviolet ray to increase the degree of crosslinking.

[0050] As the radiation-curable adhesive agent, those having radiation curable

functional groups such as carbon-carbon double bonds that also show adhesiveness may be used without particular limitation. For example, addition-type radiation-curable adhesive agents obtained by combining radiation-curable monomer components and oligomer components to general pressure-sensitive adhesive agents such as the aforementioned acrylic-type adhesive agent and rubber-type adhesive agent may be exemplified.

[0051] As the radiation-curable monomer component to be combined, for example, urethane oligomer, urethane(meth)acrylate, trimethylol propane tri(meth)acrylate, tetramethylol methane tetra(meth)acrylate, pentaerythritol tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, dipentaerythritol monohydroxy penta(meth)acrylate, dipentaerythritol hexa(meth)acrylate, 1,4-butanediol di(meth)acrylate etc. may be listed. Further, as the radiation-curable oligomer component, various oligomers such as urethane-type, polyether-type, polyester-type, polycarbonate-type, polybutadiene-type may be listed, and those with a molecular weight in the range of 100 to 30000 are suitable. The amount of radiation-curable monomer components and oligomer components may be determined arbitrarily according to the type of adhesive layer. In general, the amount is, for example, 5 to 500 parts by mass, or more preferably, 40 to 150 parts by mass, based on 100 parts by mass of the base polymer such as the acrylic polymer composing the adhesive layer.

[0052] Further, as the radiation-curable adhesive agent, other than the aforementioned addition-type radiation-curable adhesive agent, endogenous-type radiation-curable adhesive agents that have carbon-carbon double bonds on the polymer side chain, main chain, or end of the main chain may be listed as the base polymer. Such endogenous-type radiation-curable adhesive agents do not require the addition of oligomer components etc., or do not contain many. Thus, they are preferable since chronological migration of the oligomer components within the adhesive agent or to the adhesive film 3 does not occur.

[0053] Further, as the radiation-curable adhesive agent, for example, an addition polymerizable compound having two or more unsaturated bonds as disclosed in

JP-A-S60-196956, rubber-type adhesive agents and acrylic-type adhesive agents containing a photo-polymerizable compound that has an epoxy group such as alkoxysilane and a photopolymerization initiator such as carbonyl compounds, organic sulfur compounds, peroxides, amines, onium salt-type compounds may be listed.

[0054] The thickness of the pressure-sensitive adhesive layer 2 is not particularly limited, but is preferably about 1 to 50 μm . Preferably, the thickness is 2 to 30 μm , or further preferably, 5 to 25 μm , since an adequate adhesiveness with good balance between the support property of the chip and the detachability at pickup can be obtained.

[0055] FIG 1 shows a clear example of the structure and method for producing a semiconductor device using such an adhesive film with dicing tape.

[0056] More specifically, on the semiconductor wafer sticking part of the adhesive film 3 of the adhesive film with dicing film 10, a semiconductor wafer 4 is pressure bonded, and fixed by adhesion holding (adhesion process). This process is performed by a pressurizing means such as a pressurizing roll.

EXAMPLE

[0057] Hereinafter, the present invention will be described more specifically with reference to Examples. However, the present invention is not limited in anyway by these Examples.

[0058] <Adhesive Film>

(Example 1)

Copper particles coated with silver (a), Condensation polymerization type silanol-terminated polydimethylsiloxane (DMS-S45, product of Gelest, Inc.) (b), methyltriacetoxysilane (c) as a curing agent, and silicone resin (SQ-299, product of Gelest, Inc.) (d) were charged in a vessel at a ratio of (a) : (b) : (c) : (d) = 60 : 25 : 3 : 12, after which a sufficient amount of toluene was added and the mixture was kneaded using a rotating and revolving mixer to thereby obtain a varnish. This varnish was coated on a cover tape consisting of fluorine-treated PET film with a thickness of 50 μm , dried to

form a film-formed adhesive composition with a thickness of 50 μm , and bonded together with a dicing tape to prepare an adhesive film with dicing tape.

[0059] (Example 2)

A metal particle mixture consisting of 78 weight% of copper particle and 22 weight% of tin particle (a), a vinyl-terminal modified polydimethylsiloxane (DMS-V52, product of Gelest, Inc.) (b), hydrogen silane modified polydimethylsiloxane (HMS-501, product of Gelest, Inc.) (c) as a crosslinking agent, 2,3-dimethyl-2,3-diphenyl butane (d) as a catalyst, silicone resin (SQ-299, product of Gelest, Inc.), tetraethyleneglycol (f) as a flux, and a silane coupling agent (KBM1003, product of Shin-Etsu Silicone) (g) as an additive, were charged in a vessel at a ratio of (a) : (b) : (c) : (d) : (e) : (f) : (g) = 60 : 22 : 2 : 1 : 9 : 5 : 1, after which a sufficient amount of toluene was added as a solvent and the mixture was kneaded using a rotating and revolving mixer. Subsequently, a sufficient amount of hexane was added, and a varnish was prepared by high-speed stirring using a homogenizing disper. This varnish was coated on a cover tape consisting of fluorine-treated PET film with a thickness of 50 μm , dried to form a film-formed adhesive composition with a thickness of 50 μm , and bonded together with a dicing tape to prepare an adhesive film with dicing tape.

[0060] (Example 3)

Other than using a metal particle mixture consisting of 60 weight% of copper particle, 34 weight% of tin particle, and 6 weight% of zinc particle as (a), an adhesive film with dicing tape was prepared by the same method as that described in Example 2.

[0061] (Example 4)

Other than using a metal particle mixture consisting of 60 weight% of copper particle, 28 weight% of tin particle, and 12 weight% of bismuth particle as (a), an adhesive film with dicing tape was prepared by the same method as that described in Example 2.

[0062] (Example 5)

Other than adding the materials at a ratio of (a) : (b) : (c) : (d) : (e) : (f) : (g) = 55 : 23 : 2 : 1 : 12 : 6 : 1, an adhesive film with dicing tape was prepared by the same

method as that described in Example 4.

[0063] (Example 6)

Other than adding the materials at a ratio of (a) : (b) : (c) : (d) : (e) : (f) : (g) = 50 : 25 : 3 : 1 : 14 : 6 : 1, an adhesive film with dicing tape was prepared by the same method as that described in Example 4.

[0064] (Example 7)

Other than using an organic peroxide (diisopropylbenzene hydroperoxide) as (d), an adhesive film with dicing tape was prepared by the same method as that described in Example 4.

[0065] (Example 8)

Other than using a 0.1 M silicone oil solution of a platinum catalyst (Platinum(0)1,3-divinyl-1,1,3,3-tetramethyl) disiloxane complex) as (d), gum rosin as (f), and styrene ethylene butylene styrene elastomer as (g), and adding the materials at a ratio of (a) : (b) : (c) : (d) : (e) : (f) : (g) = 60 : 5 : 1 : 1 : 5 : 18 : 10, an adhesive film with dicing tape was prepared by the same method as that described in Example 4.

[0066] (Example 9)

A metal particle mixture consisting of 60 weight% of copper particles, 28 weight% of tin particles, and 12 weight% of bismuth particles (a), a carboxyl modified polydimethylsiloxane (X22-162C, product of Shin-Etsu Silicone) (b), silicone resin (SQ-299, product of Gelest, Inc.) (c), vinylmethoxysiloxane oligomer (VMM-010, product of Gelest, Inc.) (d) as a crosslinking agent, and an organic peroxide (diisopropylbenzene hydroperoxide) (e) as a catalyst, were charged in a vessel at a ratio in volume% of (a) : (b) : (c) : (d) : (e) = 60 : 25 : 11 : 3 : 1, after which a sufficient amount of toluene was added as a solvent and the mixture was kneaded using a rotating and revolving mixer to prepare a varnish. This varnish was coated on a cover tape consisting of fluorine-treated PET film with a thickness of 50 μm , dried to form a film-formed adhesive composition with a thickness of 50 μm , and bonded together with a dicing tape to prepare an adhesive film with dicing tape.

[0067] (Example 10)

A metal particle mixture consisting of 60 weight% of copper particles, 28 weight% of tin particles, and 12 weight% of bismuth particles (a), a 1 : 1 mixture of a vinyl-terminal modified polydimethylsiloxane (DMS-V52, product of Gelest, Inc.) and a carboxyl modified polydimethylsiloxane (X22-162C, product of Shin-Etsu Silicone) (b), a hydrogen silane modified polydimethylsiloxane (HMS-501, product of Gelest, Inc.) (c) as a crosslinking agent, 2,3-dimethyl-2,3-diphenyl butane (d), silicone resin (SQ-299, product of Gelest, Inc.) (e), and a silane coupling agent (KBM1003, product of Shin-Etsu Silicone) (f) as an additive, were charged in a vessel at a ratio in volume% of (a) : (b) : (c) : (d) : (e) : (f) = 60 : 27 : 3 : 1 : 8 : 1, after which a sufficient amount of toluene was added as a solvent and the mixture was kneaded using a rotating and revolving mixer to prepare a varnish. This varnish was coated on a cover tape consisting of fluorine-treated PET film with a thickness of 50 μ m, dried to form a film-formed adhesive composition with a thickness of 50 μ m, and bonded together with a dicing tape to prepare an adhesive film with dicing tape.

[0068] (Example 11)

Other than using a 1 : 1 mixture of a vinyl-terminal modified polydimethylsiloxane (DMS-V52, product of Gelest, Inc.) and a carbinol modified polydimethylsiloxane (KF6000, product of Shin-Etsu Silicone) as (b), an adhesive film with dicing tape was prepared by the same method as that described in Example 10.

[0069] (Example 12)

A metal particle mixture consisting of 60 weight% of copper particles, 28 weight% of tin particles, and 12 weight% of bismuth particles (a), a 1 : 1 mixture of a vinyl-terminal modified polydimethylsiloxane (DMS-V52, product of Gelest, Inc.) and a carboxyl modified polydimethylsiloxane (X22-162C, product of Shin-Etsu Silicone) (b), a hydrogen silane modified polydimethylsiloxane (HMS-501, product of Gelest, Inc.) (c) as a crosslinking agent, 2,3-dimethyl-2,3-diphenyl butane (d) as a catalyst, and a 0.1 M silicone oil solution of a platinum catalyst (Platinum(0)1,3-divinyl-1,1,3,3-tetramethyl disiloxane complex) (e), a silicone resin (SQ-299, product of Gelest, Inc.) (f), N, N, N', N'- tetrakis(2-hydroxyethyl) ethylenediamine (g) as a flux, and a silane

coupling agent (KBM1003, product of Shin-Etsu Silicone) (h) as an additive, were charged in a vessel at a ratio in volume% of (a) : (b) : (c) : (d) : (e) : (f) : (g) : (h) = 60 : 22 : 3 : 1 : 1 : 6 : 6 : 1, after which a sufficient amount of toluene was added as a solvent and the mixture was kneaded using a rotating and revolving mixer. Subsequently, a sufficient amount of hexane was added, and a varnish was prepared by high-speed stirring using a homogenizing disper. This varnish was coated on a cover tape consisting of fluorine-treated PET film with a thickness of 50 μ m, dried to form a film-formed adhesive composition with a thickness of 50 μ m, and bonded together with a dicing tape to prepare an adhesive film with dicing tape.

[0070] (Comparative Example 1)

A metal particle mixture consisting of 70 weight% of tin particles and 30 weight% of bismuth particles (a), a bisphenol A-type epoxy (RE310, product of Nippon Kayaku Co., Ltd.) (b) as an epoxy resin, a phenoxy resin (YP50S, product of Nippon Steel and Sumikin Chemical Co., Ltd.) (c), dicyandiamide (d) as a curing agent, 1-phenylimidazole (e) as a catalyst, and tetraethyleneglycol (f) as a flux, were charged in a vessel at a ratio in volume% of (a) : (b) : (c) : (d) : (e) : (f) = 55 : 7 : 25 : 2 : 1 : 10, after which a sufficient amount of cyclohexanone was added as a solvent and the mixture was kneaded using a rotating and revolving mixer to prepare a varnish. This varnish was coated on a cover tape consisting of fluorine-treated PET film with a thickness of 50 μ m, dried to form a film-formed adhesive composition with a thickness of 50 μ m, and bonded together with a dicing tape to prepare an adhesive film with dicing tape.

[0071] (Comparative Example 2)

Other than using a metal particle mixture consisting of 60 weight% of copper particle, 28 weight% of tin particle, and 12 weight% of bismuth particle as (a), an adhesive film with dicing tape was prepared by the same method as that described in Comparative Example 1.

[0072] (Comparative Example 3)

A metal particle mixture consisting of 60 weight% of copper particles, 28

weight% of tin particles, and 12 weight% of bismuth particles (a), a silicone oil (KF-986, product of Shin-Etsu Silicone) (b), and tetraethyleneglycol (c) as a flux, were charged in a vessel at a ratio in volume% of (a) : (b) : (c) = 60 : 30 : 10, after which a sufficient amount of toluene was added as a solvent and the mixture was kneaded using a rotating and revolving mixer. Subsequently, a sufficient amount of hexane was added, and a varnish was prepared by high-speed stirring using a homogenizing disper. This varnish was coated on a cover tape consisting of fluorine-treated PET film with a thickness of 50 μm , dried to form high viscosity paste.

[0073] (Comparative Example 4)

Other than adding the materials at a ratio of (a) : (b) : (c) : (d) : (e) : (f) : (g) = 70 : 4 : 1 : 1 : 10 : 13 : 1, the same method was used as that described in Example 4 to obtain a varnish. This varnish was coated on a cover tape consisting of fluorine-treated PET film with a thickness of 50 μm , dried to form an extremely brittle thin layered solid laminated on the PET film.

[0074] (Comparative Example 5)

Other than using copper particles as (a), an adhesive film with dicing tape was prepared by the same method as that described in Example 2.

[0075] Note that evaluation methods for each performance were as follows.

[0076] <State of Phase>

The cross-section of the adhesive compositions of Examples 1 to 12 and Comparative Examples 1 to 5 were observed by an optical microscope, and those in which the resin composition parts were of a uniform phase were determined as being "compatible," while others were determined to be "separated."

[0077] <Film Formation>

The film-formed adhesive compositions of Examples 1 to 12 and Comparative Examples 1 to 5 were cut in to strips of 1 cm x 5 cm. One end was picked using tweezers to slowly peel, and those that could be peeled off from the cover tape in a film form were rated A, while those that could not be peeled due to being in fluid form or brittle solid form were rated B.

[0078] <Sinterability>

Among the adhesive composition of Examples 1 to 12 and Comparative Examples 1 to 5, those that were rated A for film formation were adhered to a silicon wafer, which was subjected to gold-plating treatment on the surface. The cover film was removed, after which it was sintered under nitrogen atmosphere at 200°C or 250°C for 2 hours. The surface of the sintered adhesive was polished, after which the polished surface was observed by electron microscope and fluorescent X-ray analysis. Those for which formation of intermetallic compounds were seen were rated A, while those for which formation of intermetallic compounds were not seen were rated B.

[0079] <Volume Resistivity>

Among the adhesive composition of Examples 1 to 12 and Comparative Examples 1 to 5, those that were rated A for film formation were adhered to glass. After removing the cover film, the samples were subjected to sintering under nitrogen atmosphere at 250°C for 2 hours. The surface of the sintered adhesive was polished, after which the volume resistivity of the polished surface was measured by the four-point probe method according to JIS-K7194.

[0080] <Curving>

Among the adhesive composition of Examples 1 to 12 and Comparative Examples 1 to 5, the cover films were removed from those that were rated A for film formation. Then, they were adhered to a silicon wafer, which was subjected to gold-plating treatment on the surface, with a thickness of 350 μm, and diced to a size of 5 mm x 5 mm using a dicing saw to obtain diced semiconductor chips with adhesive film on the dicing tape. These diced semiconductors with adhesive film were peeled from the dicing tape using a pickup die bonder, and 16 semiconductor chips were bonded at equal intervals on an iron nickel42 alloy lead frame with a surface that has been subjected to silver-plating treatment that is 100 mm x 200 mm x 160 μm in size. Then, the samples were subjected to sintering under nitrogen atmosphere at 250°C for 2 hours. When each lead frame with chip were set on an even surface, those that showed a gap of 2 mm or more due to the curving of the lead frame were rated B, while those that

showed a gap of less than 2 mm were rated A.

[0081] <Adhesive Strength>

As with the curving evaluation test, samples were prepared by bonding semiconductor chips to a lead frame, and by subjecting those to sintering under nitrogen atmosphere at 200°C or 250°C for 2 hours. The shear bond strength between the chip and lead frame was measured for each sample using a shear bond strength tester (Arctec, Inc. Series 4000).

[0082] Further, details of the components and dicing tape used were as follows.

[0083] <Base Substrate>

Commercial resin beads consisting of low-density polyethylene (Novatec LL, product of Japan Polyethylene Corporation) was melted at 140 °C, and molded in to a long film with a thickness of 100 µm using an extruder. <Adhesive Composition> In 400 g of toluene solvent, 240 g of n-octylacrylate, 13 g of 2-hydroxyethylacrylate, 6 g of methacrylic acid, and a mixed solution of benzoyl peroxide as a polymerization initiator were slowly added by adjusting the dripping amount, controlling the reaction temperature and reaction time, to obtain a solution of acrylic resin with a functional group. Subsequently, 6 parts by weight of Coronate L (product of Japan Polyurethane Industry Co., Ltd.) was added as a polyisocyanate, 300 parts by weight of ethyl acetate was added as a solvent, and subjected to mixing, to thereby obtain adhesive composition 1.

<Dicing Tape>

The above-described adhesive composition was coated on a support substrate, so that the thickness after the adhesive composition is dried becomes 5 µm, and dried at 110 °C for 3 minutes, to thereby obtain a dicing tape.

[0084] The evaluation results are shown in Table 1 (Examples) and Table 2 (Comparative Examples).

[0085] [Table 1]

Composition	Metal	Example 1 Example 2 Example 3 Example 4 Example 5 Example 6 Example 7 Example 8 Example 9 Example 10 Example 11 Example 12											
		Component 1	←	←	←	←	←	←	←	←	←	←	←
		Component 2	Ag	←	←	←	←	←	←	←	←	←	←
		Component 3	←	Zn	←	←	←	←	←	←	←	←	←
Composition	Binder	Component vol%	60	60	60	55	50	60	60	60	60	60	60
		Condensation-type PDMS	Vinyl modified PDMS	←	←	←	←	←	←	←	←	←	←
		vol%	25	22	←	23	25	22	5	25	27	27	22
		Component	MTAS	DMDPB	←	←	←	Organic Peroxide	Pt Catalyst	←	DMDPB	Vinyl modified PDMS + ROH modified PDMS	Vinyl modified PDMS + COOH modified PDMS
Composition	Curing Agent	1hr half-life temperature	234°C	234°C	←	←	←	183°C	←	←	234°C	←	←
		Flux	None	Tetraethyleneglycol	←	←	←	←	Resin	←	←	←	Hydroxylamine
		State of Phase	←	Separated	Separated	Separated	Separated	Separated	Separated	Compatible	Compatible	Compatible	Separated
		Film Formation	A	A	A	A	A	A	A	A	A	A	A
Evaluation Result	Sintering	200°C	B	B	A	A	A	A	A	A	A	A	A
		250°C	B	A	A	A	A	A	A	A	A	A	A
		Volume Resistivity $\mu\Omega\cdot\text{cm}$	120	37	46	39	55	98	45	30	83	49	33
		Curving	A	A	A	A	A	A	A	A	A	A	A
Evaluation Result	Adhesive Strength Mpa	Room Temperature	17	23	40	26	30	29	24	22	20	33	28
		200°C	3.2	5.8	12	6	7.2	7.6	5.5	2.3	4.6	8.7	6.5
		250°C	2.1	5	12	4.8	5.1	4.8	4	0.6	3.2	7	5.5

[0086]

[Table 2]

	Composition					Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4	Comparative Example 5
	Metal	Component 1	Sn	Cu	←	←	←	←	Cu	
Component 2		Bi	Sn	←	←	←	←	←	-	
Component 3		-	Bi	←	←	←	Bi	←	-	
vol%		55	55	60	70	60	70	60	60	
Binder	Component	Epoxy + Phenoxy	←	Silicone Oil	Vinyl modified PDMS	Vinyl modified PDMS	Vinyl modified PDMS	Vinyl modified PDMS	Vinyl modified PDMS	
	vol%	32	32	30	4	22	4	22	22	
	Component	DICY + Imidazole	←	-	DMDPB	←	←	←	←	
	1hr Half-life Temperature	-	-	-	234°C	←	←	←	←	
	Flux	Tetraethyleneglycol	←	←	←	←	←	←	←	
		State of Phase	-	-	-	Separated	Separated	Separated	Separated	
		Film Formation	A	A	B	B	A	B	A	
		Sintering	200°C	B	A	-	-	-	B	
	Sintering	250°C	B	A	-	-	-	B	B	
		Volume Resistivity $\mu \Omega \cdot \text{cm}$	220	52	-	-	-	-	270	
		Curving	B	B	-	-	-	-	A	
		Room Temperature	58	53	-	-	-	-	8.7	
	Adhesive Strength Mpa	200°C	0.3	4.6	-	-	-	1.7		
		250°C	0	1.7	-	-	-	-	0.9	

[0087]

As shown in Examples 1 to 12, the conductive adhesive film that

contains two or more types of metal particles including at least Cu and a polymer that has a polydimethylsiloxane structure proved to be a highly reliable adhesive film, maintaining high adhesive strength even in high temperature and showing no curvatures. In Example 1, even though intermetallic compounds were not formed, it showed no problem unless it is to be used in large current high frequency IGBT etc.

[0088] In Comparative Examples 1 to 3, because of the lack of polymer with a polydimethylsiloxane structure, crucial problems were found in basic film-forming aptitude such as film formability and curving.

Comparative Example 4 is a very brittle solid that is in the form of a powder aggregate, and shows no film formability (lacks all preconditions as a film).

Comparative Example 5 does not contain metals other than copper, and thus, its volume resistivity was extremely large, causing problems in its conductivity. Also it can be seen that its adhesive strength was inferior.

DESCRIPTION OF NOTATIONS


[0089]

- 1 substrate
- 2 pressure-sensitive adhesive layer
- 3 adhesive film (thermosetting-type adhesive film)
- 4 semiconductor wafer
- 10, 12 adhesive film with dicing tape
- 11 dicing film

Claims

1. A conductive adhesive film, which comprises two or more types of metal particles including at least Cu, and a polymer that has a polydimethylsiloxane structure, wherein said polydimethylsiloxane structure:

- i) contains -COOH, -CR_x(OH)_y, or -NR₂ as a functional group, where R is selected from H, alkyl, or aryl group, and x+y=3;
- ii) contains a double bond or
- iii) has the following structure;



and wherein the conductive adhesive film contains at least one type of flux component selected from alcohol, ketone, carboxylic acid, or amine, wherein the flux component is in a state of phase separation with the polymer that has the polydimethylsiloxane structure.

2. The conductive adhesive film according to Claim 1, wherein the two or more types of metal particles including at least Cu comprises a metal component other than Cu, , wherein the metal component has a melting point of 250°C or lower.

3. The conductive adhesive film according to any one of Claims 1 or 2, wherein the metal particles are capable of forming an intermetallic compound.

4. The conductive adhesive film according to any one of Claims 1 to 3, wherein the metal particles amount to 55 volume% or more of the entire film and the polymer

5. The conductive adhesive film according to any one of Claims 1 to 4, which comprises a radical generator with a one-hour half-life temperature of 200°C or higher.
6. A dicing die bonding film, which comprises the conductive adhesive film of any one of Claims 1 to 5 and a dicing tape laminated thereon.
7. A method for processing semiconductor wafer using the conductive adhesive film of any one of Claims 1 to 5.
8. A method for processing semiconductor wafer using the dicing die bonding film of Claim 6.