

SUPERCRITICAL WATER UPGRADING PROCESS TO PRODUCE HIGH GRADE COKE

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims priority to U.S. Provisional Application 62/267,404, filed December 15, 2015, which is incorporated by reference in its entirety.

TECHNICAL FIELD

[0002] Embodiments of the present disclosure generally relate to supercritical water upgrading processes, and more specifically relate to supercritical water upgrading processes for producing high grade coke.

BACKGROUND

[0003] Coke (often called petroleum coke or pet coke) is a carbonaceous solid produced in the oil refining process. Coking reactions follow free-radical mechanisms in which the breaking and formation of chemical bonds occur simultaneously. The most distinctive reactions are the dealkylation of aromatic compounds and the dehydrogenation of saturated compounds. Aromatization, dehydrogenative cyclization, and polymerization are also prevalent reactions.

[0004] The feedstock for coking processes is generally low economic value crude oil residue streams, such as vacuum residue or atmospheric residue. Although liquid product from the coking process needs further treatment steps, the simplicity of the coking process has attracted interest. Two major grades of coke are available in the market based on their quality: fuel grade coke, which contains a lot of impurities, such as sulfur and metals, and is often used in combustion applications to generate heat; and anode grade coke, which has fewer impurities than fuel-grade coke, and thus, is used in more applications, such as in the aluminum industry. Typical compositional properties of anode grade coke are shown in Table 1 as follows.

TABLE 1:

Component	Amount
Sulfur	<3.0 weight (wt) %
Volatile matter	<11.5 wt %
Vanadium	<250 wt parts per million (ppm)
Nickel	<150 wt ppm
Iron	<200 wt ppm
Calcium	<100 wt ppm
Sodium	<100 wt ppm
Silicon	<150 wt ppm

[0005] For suitability in industrial applications, anode grade coke requires low metal content, low sulfur content, and high aromatic content. For these reasons, pre-treatment steps in upstream of delayed coker units and other coke production processes may be required. The pre-treatment methods can be classified into two groups: solvent extraction, and hydroprocessing.

[0006] In solvent extraction processes, for example, the ROSE® (Residuum Oil Supercritical Extraction) solvent extraction process developed by Kellogg Brown & Root, Inc a Solvent Deasphalting (SDA) process is utilized that separates a resin fraction from asphaltene. The resulting resin is directed to a delayed coker for generating high-end coke such as anode grade coke. While generating feedstock suitable for the production of high-end coke, the ROSE process demonstrates poor conversion of the vacuum residue and thereby is not an economically feasible anode coke producing process. Specifically, to reduce the metal content of the vacuum residue of Arabian heavy crude oil from 250 weight parts per million (wt ppm) to 9 wt ppm by the ROSE process, over 50% of vacuum residue is rejected as asphaltene pitch. Consequently, while the ROSE process can generate feedstock suitable for anode coke; the ROSE process is ineffective at producing upgraded petroleum, because it rejects so much of the vacuum residue and lacks chemical conversion function.

SUMMARY

[0007] Accordingly, ongoing needs exist for improved systems and methods for producing high grade coke, which encompasses anode grade coke and needle coke, from heavily contaminated residue oil. Needle coke refers to highly crystalline coking products that contain needle-like shards often used in the steel industry for manufacturing graphite electrodes. While needle coke and anode coke are both produced from calcined green coke, anode grade coke generally is considered lower quality than needle coke, which has a sulfur content from 0.1 weight % (wt%) to 0.6 wt%. The present embodiments utilize supercritical water to provide improved systems and methods for producing high grade coke, while also providing a new methodology for integrating supercritical water processes into conventional solvent deasphalting to produce a higher yield of coke and also generating upgraded petroleum.

[0008] In one embodiment, a process for producing high grade coke, such as anode grade coke, from crude oil residue is provided. The process comprises at least partially separating in a solvent extraction unit crude oil residue into a deasphalted oil (DAO)-containing stream and an asphaltene containing-stream, and producing a pressurized, heated DAO-containing stream by pressurizing and heating the DAO-containing stream at a temperature greater than 75°C and a pressure greater than the critical pressure of water. The process further includes mixing a supercritical water stream with the pressurized, heated DAO-containing stream to create a combined feed stream, where the supercritical water stream has a pressure greater than the critical pressure of water and a temperature greater than the critical temperature of water, introducing the combined feed stream to an upgrading reactor system comprising one or more upgrading reactors operating at a temperature greater than the critical temperature of water and a pressure greater than the critical pressure of water to yield one or more upgrading reactor output streams comprising upgraded product and a slurry mixture, where the slurry mixture comprises sulfur and one or more additional metals, and calcining the slurry mixture at a temperature of from 700°C to 1900°C to produce a product stream comprising the high grade coke.

[0009] Additional features and advantages of the described embodiments will be set forth in the detailed description which follows, and in part will be readily apparent to those skilled in the art from that description or recognized by practicing the described embodiments, including the detailed description which follows, the claims, as well as the appended drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] FIG. 1 is a schematic illustration of a system for producing high grade coke using supercritical water upgrading in accordance with one or more embodiments of the present disclosure;

[0011] FIG. 2 is a schematic illustration of another system for producing high grade coke using supercritical water upgrading in accordance with one or more embodiments of the present disclosure;

[0012] FIG. 3 is a schematic illustration of yet another system for producing high grade coke using a dual supercritical water reactor system in accordance with one or more embodiments of the present disclosure;

[0013] FIG. 4 is a schematic illustration of a system for producing high grade coke using supercritical water upgrading and a subcritical separator in accordance with one or more embodiments of the present disclosure;

[0014] FIG. 5 is a schematic illustration of a system for producing high grade coke using supercritical water upgrading and a supercritical CO₂ separator in accordance with one or more embodiments of the present disclosure; and

[0015] FIG. 6 is a schematic illustration of a system for producing high grade coke using supercritical water upgrading and a delayed coker in accordance with one or more embodiments of the present disclosure.

DETAILED DESCRIPTION

[0016] Embodiments of the present disclosure are directed to systems for producing high grade coke from crude oil residue **105** through the utilization of supercritical water. As used throughout the disclosure, “supercritical” refers to a substance at a pressure and a temperature greater than that of its critical pressure and temperature, such that distinct phases do not exist and the substance may exhibit the diffusion of a gas while dissolving materials like a liquid. At a temperature and pressure greater than the critical temperature and pressure of water, the liquid and gas phase boundary disappears, and the fluid has characteristics of both fluid and gaseous substances. Supercritical water is able to dissolve organic compounds like an organic solvent and has excellent diffusibility like a gas. Regulation of the temperature and pressure allows for continuous "tuning" of the properties of the supercritical water to be more liquid or more gas like. Supercritical water has reduced density and lesser polarity, as compared to liquid-phase sub-critical water, thereby greatly extending the possible range of chemistry, which can be carried out in water.

[0017] Without being bound by theory, supercritical water has various unexpected properties as it reaches supercritical boundaries. Supercritical water has very high solubility toward organic compounds and has an infinite miscibility with gases. Furthermore, radical species can be stabilized by supercritical water through the cage effect (that is, a condition whereby one or more water molecules surrounds the radical species, which then prevents the radical species from interacting). The stabilization of radical species may help prevent inter-radical condensation and thereby reduces the overall coke production in the current embodiments. For example, coke production can be the result of the inter-radical condensation. In certain embodiments, supercritical water generates hydrogen gas through a steam reforming reaction and water-gas shift reaction, which is then available for the upgrading reactions.

[0018] Supercritical water has various unexpected properties as it reaches its supercritical boundaries of temperature and pressure. For instance, supercritical water may have a density of 0.123 grams per milliliter (g/mL) at 27 megapascals (MPa) and 450°C. In comparison, if the pressure was reduced to produce superheated steam, for example, at 20 MPa and 450°C, the steam would have a density of only 0.079 g/mL. Without being bound by theory, fluids

having a closer density to hydrocarbons may have better dissolution power. Additionally, at that density, the hydrocarbons may react with superheated steam to evaporate and mix into the liquid phase, leaving behind a heavy fraction that may generate coke upon heating. The formation of coke or coke precursor may plug the lines and must be removed. Therefore, supercritical water is superior to steam in some applications.

[0019] As mentioned, embodiments of the present disclosure are directed to systems for producing high grade coke from crude oil residue **105** through the utilization of supercritical water. Crude oil residue may include atmospheric residue (AR), vacuum gas oil (VGO), or vacuum residue (VR). In one or more embodiments, the crude oil residue **105** may be a residue of heavy crude oil, such as Arab Heavy crude oil.

[0020] Various compositions are contemplated for the crude oil residue **105**. In one or more embodiments, the crude oil residue **105** may be produced from the atmospheric distillation or vacuum distillation of crude oil. From a density standpoint, the crude oil residue **105** may have an American Petroleum Institute (API) Gravity value of less than 27°API, or less than 19°API. Compositionally, the crude oil residue **105** may have a sulfur content of 1.0 weight % (wt%) to 7.0 wt%, or 3.0 wt% to 6.0 wt%. Moreover, the crude oil residue **105** may contain heavy metals such as nickel and vanadium in an amount up to 500 wt ppm or less. In one or more embodiments, the crude oil residue **105** may include 2 wt ppm to 80 wt ppm, or 6 wt ppm to 65 wt ppm of nickel. Further, the crude oil residue **105** may include 10 wt ppm to 250 wt ppm, or 15 wt ppm to 200 wt ppm of vanadium. Moreover, the crude oil residue **105** may include 3 wt% to 40 wt%, or 5 wt% to 30 wt% of Conradson Carbon Residue (CCR). In other embodiments, the crude oil residue **105** may include at least 5 wt% of C₇-asphaltene compounds.

[0021] Referring to the embodiments of FIGS. 1-6, the system **100** may involve feeding crude oil residue **105** to a solvent extraction unit **110** to at least partially separate the crude oil residue **105** into a deasphalted oil (DAO)-containing stream **114** and an asphaltene containing-stream **112**. Various solvent extraction units are contemplated. In one embodiment, the solvent extraction unit **110** comprises one or more deasphalting units. Various solvents are contemplated for the solvent extraction unit **110**. In one or more

embodiments, the solvent is selected from light paraffins, for example, one or more paraffins selected from C₃-C₇ paraffins.

[0022] The DAO-containing stream **114** has a higher hydrogen/carbon (H/C) ratio and a higher oxygen content than the asphaltene containing-stream **112** which thereby provides higher polarity to the DAO-containing stream **114**. Also, the contents of heteroatoms in the DAO-containing stream **114**, such as sulfur are less than asphaltene. In some embodiments, the DAO-containing stream **114** may have a H/C ratio of greater than or equal to 1.1, such as greater than or equal to 1.2, greater than or equal to 1.4, greater than or equal to 1.6, or greater or equal to than 1.8. The DAO-containing stream **114** may have a H/C ratio of from 1.1 to 2, or from 1.2 to 2, or from 1.4 to 2, or from 1.5 to 2, or from 1.6 to 2 or from 1.8 to 2. Without being bound by any particular theory, the high polarity of the DAO-containing stream **114** may be attributed to the presence of a resin fraction in the DAO-containing stream **114**. The high polarity may allow the DAO-containing stream **114** to reject asphaltene but not resin, which may be used as a seed to produce feedstock for a coker.

[0023] For example and not by way of limitation, the DAO-containing stream **114** may include less than 5 wt% of sulfur compounds, less than 150 wt ppm of heavy metals such as nickel and vanadium, less than 10 wt% of CCR, and less than 3 wt% C₇-asphaltene compounds. In yet another embodiment, the DAO-containing stream **114** may include less than 4 wt% of sulfur compounds, less than 50 wt ppm of heavy metals, less than 8 wt% of CCR, and less than 2 wt% of C₇-asphaltene compounds. Moreover, the aromatic content of the DAO-containing stream **114** is less than that of the crude oil residue **105** feed and also less than the asphaltene containing-stream **112**. For example, the aromatic content of the DAO-containing stream **114** may be less than 30 wt% or less than 25 wt%. Without being bound by any particular theory, aromatics in asphaltene may be bonded to impurities, such as sulfur and metals. Thus, having a low aromatic content in the DAO-containing stream **114** may be a sign of asphaltene separation and a lack of impurities present in the DAO-containing stream **114**.

[0024] As shown in FIGS. 1-6, the DAO-containing stream **114** may be pressurized in a pump **116** to create a pressurized DAO-containing stream **117**. The pressure of the

pressurized DAO-containing stream **117** may be at least 22.1 MPa, which is approximately the critical pressure of water. Alternatively, the pressure of the pressurized DAO-containing stream **117** may be between 22.1 MPa and 32 MPa, or between 23 MPa and 30 MPa, or between 24 MPa and 28 MPa. In some embodiments, the pressure may be between 25 MPa and 29 MPa, 26 MPa and 28 MPa, 25 MPa and 30 MPa, 26 MPa and 29 MPa, or 23 MPa and 28 MPa.

[0025] Referring again to FIGS. 1-6, the pressurized DAO-containing stream **117** may then be heated in one or more DAO pre-heaters **120** to form a pressurized, heated DAO-containing stream **126**. In one embodiment, the pressurized, heated DAO-containing stream **126** has a pressure greater than the critical pressure of water as described previously and a temperature greater than 75°C. Alternatively, the temperature of the pressurized, heated DAO-containing stream **126** is between 10°C and 300°C, or between 50°C and 250°C, or between 75 and 200°C, or between 50°C and 150°C, or between 50°C and 100°C, or between 100°C and 200°C, or between 150°C and 250°C, or between 200°C and 300°C. In some embodiments, the temperature may be between 75°C and 225°C, or between 100°C and 250°C, or between 125°C and 175°C, or between 140°C and 160°C.

[0026] Embodiments of the DAO pre-heaters **120** may include a natural gas fired heater, heat exchanger, or an electric heater. In some embodiments, the pressurized DAO-containing stream **117** is heated in a double pipe heat exchanger.

[0027] As shown in FIGS. 1-6, the supercritical water stream **124** may be produced from any suitable water stream **115**. The water stream **115** may be any source of water, for example, a water stream having a conductivity less than 1 microsiemens/centimeters ($\mu\text{S}/\text{cm}$), such as less than 0.5 $\mu\text{S}/\text{cm}$ or less than 0.1 $\mu\text{S}/\text{cm}$. Exemplary water streams **115** include demineralized water, distilled water, boiler feed water (BFW), and deionized water. In at least one embodiment, the water stream **115** is a boiler feed water stream. As shown in FIG. 1, the water stream **115** is pressurized by pump **118** to produce a pressurized water stream **119**. The pressure of the pressurized water stream **119** is at least 22.1 MPa, which is approximately the critical pressure of water. Alternatively, the pressure of the pressurized water stream **119** may be between 22.1 MPa and 32 MPa, or between 22.9 MPa and 31.1

MPa, or between 23 MPa and 30 MPa, or between 24 MPa and 28 MPa. In some embodiments, the pressure may be 25 MPa and 29 MPa, 26 MPa and 28 MPa, 25 MPa and 30 MPa, 26 MPa and 29 MPa, or 23 MPa and 28 MPa.

[0028] Referring again to FIGS. 1-6, the pressurized water stream **119** may then be heated in the water pre-heater **122** to create a supercritical water stream **124**. The temperature of the supercritical water stream **124** is greater than about 374°C, which is approximately the critical temperature of water. Alternatively, the temperature of the supercritical water stream **124** may be between 374°C and 600°C, or between 400°C and 550°C, or between 400°C and 500°C, or between 400°C and 450°C, or between 450°C and 500°C. In some embodiments, the maximum temperature of the supercritical water stream **124** may be 600°C, as the mechanical parts in the supercritical reactor system may be affected by temperatures greater than 600°C.

[0029] Similar to the DAO pre-heater **120**, suitable water pre-heaters **122** may include a natural gas fired heater, a heat exchanger, and an electric heater. The water pre-heater **122** may be a unit separate and independent from the DAO pre-heater **120**.

[0030] Referring again to FIGS. 1-6, the supercritical water stream **124** may be mixed with the pressurized, heated DAO-containing stream **126** in a mixer **130** to create a combined feed stream **132**. The feed mixer **130** can be any type of mixing device capable of mixing the supercritical water stream **124** and the pressurized, heated DAO-containing stream **126**. In one embodiment, feed mixer **130** may be a mixing tee, an ultrasonic mixer, a small continuous stir tank reactor (CSTR), a homogenizer, or any other suitable mixer. The volumetric flow ratio of supercritical water stream **124** and the pressurized, heated DAO-containing stream **126** fed to the feed mixer **130** may vary. In one embodiment, the volumetric flow ratio may be from 10:1 to 1:1, or 10:1 to 1:10, or 5:1 to 1:1, or 4:1 to 1:1 at standard ambient temperature and pressure (SATP).

[0031] Referring to FIG. 1, the combined feed stream **132** may pass to a system **100** comprising one or more upgrading reactors **140** operating at a temperature greater than the critical temperature of water and a pressure greater than the critical pressure of water to yield

one or more upgrading reactor output streams **142** comprising upgraded product and a slurry mixture, where the slurry mixture comprises sulfur and one or more additional metals. The upgrading reactor system, whether it includes one or multiple upgrading reactors, as depicted in the various embodiments of the FIGS., employ supercritical water as the reaction medium for upgrading reactions in the absence of externally-provided hydrogen gas and in the absence of a catalyst. In certain optional embodiments, supercritical water generates hydrogen gas through a steam reforming reaction and water-gas shift reaction, which is then available for the upgrading reactions. In the embodiment of FIG. 1, the upgrading reactor **140** yields an upgrading reactor output stream **142** that includes both the upgraded product and the slurry mixture.

[0032] As stated, the upgrading reactor **140** may operate at a supercritical temperature and pressure. In one or more embodiments, the upgrading reactor **140** may have a temperature of between 450°C to 550°C, or between 470°C to 530°C as measured at the inner wall of the reactor. The temperature of fluid in the reactor is between 380°C and 450°C or between 400°C and 430°C. The upgrading reactor **140** may be an isothermal or nonisothermal reactor. The reactor may be a tubular-type vertical reactor, a tubular-type horizontal reactor, a vessel-type reactor, a tank-type reactor having an internal mixing device, such as an agitator, or a combination of any of these reactors. Moreover, additional components, such as a stirring rod or an agitation device may also be included in the upgrading reactor **140**.

[0033] As discussed previously and as shown in the embodiment of FIGS. 1, 2, 4, and 6, the upgrading reactor system may include one upgrading reactor **140**. The combined feed stream **132** is fed through an inlet port of the upgrading reactor **140**. The upgrading reactor **140** depicted in FIG. 1 is a downflow reactor where the inlet port is disposed near the top of the upgrading reactor **140** and the outlet port is disposed near the bottom of the first upgrading reactor **140A**. Alternatively, it is contemplated that the upgrading reactor **140** may be an upflow reactor where the inlet port is disposed near the bottom of the reactor. As shown by arrow **141**, a downflow reactor is a reactor where the upgrading reactions occur as the reactants travel downward through the reactor. Conversely, an upflow reactor is a reactor where the petroleum upgrading reactions occur as the reactants travel upward through the reactor.

[0034] The upgrading reactor(s) **140** may have dimensions defined by the equation L/D , where L is a length of the upgrading reactor **140** and D is the diameter of the upgrading reactor **140**. In one or more embodiments, the L/D value may be from 2.5 to 300, or from 20 to 100. Without being bound by theory, the reactor dimensions may impact the residence time within the reactors. As stated in prior paragraphs, this increased residence time may increase free-radical reactions which thereby increases coke formation. In one or more embodiments, the L/D value of the upgrading reactor(s) **140** may be sufficient to achieve a superficial velocity of fluid greater than 0.5 meter(m)/minute(min), or an L/D value sufficient to achieve superficial velocity of fluid between 1 m/min and 25 m/min, or an L/D value sufficient to achieve superficial velocity of fluid between 1 m/min and 5 m/min. The fluid flow may be defined by a Reynolds number greater than about 5000.

[0035] As shown in the embodiments of FIGS. 3 and 5, the upgrading reactor system may include two upgrading reactors: a first upgrading reactor **140A** and a second upgrading reactor **140B**. As discussed previously, the first upgrading reactor **140A** and the second upgrading reactor **140B** may be upflow or downflow upgrading reactors. As shown in FIG. 3, the first upgrading reactor **140A** and the second upgrading reactor **140B** may both be downflow reactors as indicated by downflow arrows **141**. The embodiment of FIG. 5 shows a first upgrading reactor **140A**, which is a downflow reactor, and a second upgrading reactor **140B**, which is an upflow reactor as demonstrated by upflow arrow **143**. Without being bound by theory, including additional upgrading reactors may increase the residence time in the first upgrading reactor **140A** and the second upgrading reactor **140B** may increase the formation of coke within the reactors. Whether using a single or multiple upgrading reactors, the residence time within the upgrading reactors may be from 10 seconds to 60 minutes (min), or 1 min to 30 mins. The residence time, in some embodiments, may be between 2 and 30 mins, or between 2 and 20 mins, or between 5 and 25 mins, or between 5 and 10 mins.

[0036] Referring to the embodiments of FIGS. 3 and 5, the second upgrading reactor **140B** may have a volume greater than, less than, or equal to a volume of the first upgrading reactor **140A**. In one or more embodiments, a ratio of the volume of the first upgrading reactor **140A** to the volume of the second upgrading reactor **140B** is from 0.1:1 to 1:1, or from 0.5:1 to 1:1. The volume of the first upgrading reactor **140A** and the volume of the second upgrading

reactor **140B** may be adjusted based on the desired application. For instance, without being bound by any particular theory, having a first upgrading reactor **140A** with a greater volume than the second upgrading reactor **140B** may allow for a longer residence time and lower temperature in the first upgrading reactor **140A**, allowing for a more mild upgrading process in the first upgrading reactor **140A**. The second upgrading reactor **140B** with a shorter residence time and higher temperature would allow for a deeper upgrading and could produce a DAO-containing stream **114** with a higher density (such as having an API of less than or equal to 15°) and a lower miscibility with water. Alternatively, having a first upgrading reactor **140A** with a lesser volume than the second upgrading reactor **140B** may create a smaller, hotter temperature mixing process in the first upgrading reactor **140A** with a larger, colder process in the second upgrading reactor **140B** to refine the DAO-containing stream **114**. This process may produce a lower density DAO-containing stream **114** (such as having an API of greater than or equal to 15°).

[0037] As shown in FIGS. 1 and 4-6, the upgrading reactors (**140**, **140A**, or **140B**) may have one inlet port and one outlet port. However, in the single upgrading reactor embodiment of FIG. 2, the upgrading reactor **140** may be a downflow reactor comprising an upper inlet port, a lower outlet port, and a middle outlet port disposed between the upper inlet port and lower outlet port. As shown in FIG. 2, the upgrading reactor **140** may transfer a slurry mixture **145** out of the bottom port while an upgraded product stream **146**, which is a gas-liquid-oil stream, is transferred out of the middle port of the upgrading reactor **140**. Similarly, in the two upgrading reactor system of FIG. 3, the second upgrading reactor **140B** may be a downflow reactor comprising an upper inlet port, a lower outlet port, and a middle outlet port disposed between the upper inlet port and the lower outlet port. The second upgrading reactor **140B** may transfer a slurry mixture **148** out of the bottom port while an upgraded product stream **147**, which is a gas-liquid oil-water stream, is transferred out of the middle port of the second upgrading reactor **140B**.

[0038] Regardless of whether the slurry mixture is separated from the upgraded product in the upgrading reactors or in downstream separators as described in the following paragraphs, the slurry mixture may include the following composition after excluding water and gas, which typically is present in minor amounts of, less than 1 wt%. For example and not by way

of limitation, the slurry mixture **148** may include less than 3 wt% of sulfur compounds, less than 150 wt ppm of heavy metals such as nickel and vanadium, and an aromatic content of at least 30 wt%. Referring to FIG. 3 for example, the slurry mixture **148** may have less sulfur content than the gas-liquid-oil upgraded product stream **147**, as well as a lesser H/C ratio than the upgraded product stream **147**. For example, the slurry mixture may have an H/C ratio less than 1.0, or less than 0.8. In further contrast, the gas-liquid-oil stream **147** has less aromatic content than slurry mixture **148**. Due to this higher aromatic content, the slurry mixture **148** may be readily converted into coke by the calciner **210** as described in the following paragraphs. In addition to the compositional details, it is worth noting that the slurry mixture **148** may have a melting point less than 350°C, thus the slurry mixture is in its melted phase in supercritical water.

[0039] Referring again to FIG. 1, the output stream **142** of the upgrading reactor may then be fed to a calciner **210**. Various calciner units are contemplated as suitable, for example a rotary kiln. In the calciner **210**, the output stream **142** is calcined at a temperature of from 700°C to 1900°C to produce a high grade coke product stream **214** comprising high grade coke which is transferred out of the bottom port of the calciner **210**. The calcination step may occur in an inert atmosphere, for example, an atmosphere comprising nitrogen, argon, or helium. In some embodiments, the calciner **210** may operate at a temperature from 1000°C to 1300°C. In some embodiments, the calciner **210** may operate at a temperature of from 1000°C to 1200°C, or from 800°C to 1300°C, or from 1000°C to 1900°C. Additionally, the calcined upgraded product **212**, which is a gas-liquid oil stream, is transferred out of a top port of the calciner **210**. The high grade coke product stream **214** may have a composition as listed in Table 1.

[0040] Referring to the embodiment of FIGS. 2, and 4-6, additional reaction steps may be performed upstream of the calciner **210**. Referring to FIG. 2, the slurry mixture **145** exiting upgrading reactor **140** may be cooled, depressurized, degassed and dewatered prior to being delivered to the calciner **210**. Specifically as shown in FIG. 2, the slurry mixture **145** is passed to a cooler unit **360** to produce a cooled slurry mixture **362** having a temperature less than 200°C. The cooled slurry mixture **362** is then depressurized by a depressurization unit, for example, valve **370** to produce a cooled, depressurized slurry mixture **372** having a

pressure from 0.05 MPa to 2.2 MPa. The cooled, depressurized slurry mixture **372** may then be passed to a gas-liquid separator **380** to separate the cooled, depressurized slurry mixture **372** into a gas-phase stream **382**, which is passed out of the top of the gas-liquid separator **380**, and a liquid-phase slurry stream **384**. The liquid-phase slurry stream **384** may then be fed to a centrifuge **390** to remove water **392** and produce a dried slurry mixture **394**, which may then be fed to a calciner **210**. The dried slurry mixture **394** comprises coke precursor. Coke precursor amounts in the dried slurry mixture **394** may depend upon reactor operating conditions such as temperature and residence time. For continuous operation of the process, the content may be maintained below 5 wt%, or below 1 wt% in the slurry mixture **391**.

[0041] Similarly as shown in FIG. 4, the output stream **142** may be cooled in a cooling unit **150** (for example, a heat exchanger) to produce cooled output stream **152**. The temperature of the cooled output stream **152** may be cooled to less than about 200°C. The cooled output stream **152** may then be transferred to a subcritical separator **260** upstream of the calciner **210**. The subcritical separator **260** may include any suitable two-phase separator vessel. In one embodiment, the subcritical separator **260** may be a continuous stirred tank reactor, which passes an upgraded product stream **262** out of the top of the subcritical separator **260** and passes a slurry mixture stream **261** out of the bottom of the subcritical separator **260**. Various operating parameters are contemplated for the subcritical separator **260**. In one or more embodiments, the temperature is from 100°C to 350°C. The pressure is maintained to be higher than the steam pressure at the specific separator temperature in order to prevent vaporization of water. The residence time within the subcritical separator **260** may vary, for example, from 1 min to 120 mins, or 30 mins to 60 mins. The residence time, in some embodiments, may be between 60 and 120 mins, or between 90 and 120 mins, or between 30 and 60 mins, or between 30 and 90 mins. In some embodiments, the residence time may be between 2 and 30 mins, or between 2 and 20 mins, or between 5 and 25 mins, or between 5 and 10 mins.

[0042] Referring again to FIG. 4, the slurry mixture stream **261** may be depressurized in a depressurization device **163**, for example, a valve, to produce depressurized slurry mixture **164**. In one or more embodiments, the depressurized slurry mixture **164** may have a pressure from 0.05 MPa to 2.2 MPa. Further as shown in FIG. 4, the depressurized slurry mixture **164**

may be dried in a centrifuge **200** upstream of the calciner **210**, where a water stream **202** is removed from the depressurized slurry mixture **164** to produce a dried slurry mixture **204**, which is then passed to the calciner **210**. While not shown, it is contemplated that dried slurry mixture **204** may be subjected to minor steps such as a separator to remove CO₂ before fed to calciner.

[0043] Referring to an alternative embodiment depicted in FIG. 5, the output stream **142** of the upgraded reactor system, which comprises upgraded gas-liquid-oil and slurry mixture, may be fed to a supercritical CO₂ extractor **220** upstream of the calciner **210**. As shown, the supercritical CO₂ extractor **220** may separate the output stream **144** of the second upgrading reactor **140B**, such that the upgraded gas-liquid-oil stream **222** is passed out of the top of the supercritical CO₂ extractor **220** while the slurry mixture **224** is passed out of the bottom of the supercritical CO₂ extractor **220**. The slurry mixture **224** may then be delivered to the calciner **210** for production of high grade coke product stream **214**.

[0044] In another embodiment as shown in FIG. 6, a delayed coker **240** may be disposed upstream of the calciner **210**. As shown, the delayed coker **240** may separate the output stream **142** of the upgrading reactor **140** into an upgraded gas-liquid-oil stream **242** which is passed out of the top of the delayed coker **240**, while the slurry mixture **224** is passed out of the bottom of the delayed coker **240**.

[0045] In addition to the production of high grade coke product stream **214**, further separation operations may also be conducted for the upgraded product, which is a gas-liquid oil-water stream produced by the supercritical upgrading processes. Referring to FIG. 2, the upgraded product stream **146** may be cooled in a cooler **160** to yield a cooled upgraded product **162** having a temperature less than 200°C. Various cooling devices are contemplated for the cooler **160**, such as a heat exchanger. Next, the pressure of the cooled upgraded product **162** may be reduced to create a depressurized, cooled upgraded product **172** with a pressure from 0.05 MPa to 2.2 MPa. The depressurizing can be achieved by many devices, for example, a valve **170**, as shown in FIG. 2.

-16-

[0046] The depressurized, cooled upgraded product **172** may then be fed to a gas-liquid separator **180** to separate the depressurized, cooled upgraded product **172** into a gas-phase stream **182**, which is passed out of the top of the gas-liquid separator **180**, and a liquid-phase stream **184**. The liquid-phase stream **184** may comprise water, short chain aromatics, and paraffins. Various gas-liquid separators are contemplated, for example, a flash drum.

[0047] The liquid-phase stream **184** may then be fed to an oil-water separator **190** to separate the liquid-phase stream **184** into a water-containing stream **192** and an oil-containing stream **194**, where the oil-containing stream **194** comprises paraffins and short chain aromatics. Various oil-liquid separators are contemplated, for example, a centrifugal oil-gas separator.

EXAMPLE

[0048] The following experimental example is a simulation that utilizes the system depicted in FIG. 4, where stream properties and stream compositions are listed in the tables as follows. Referring to FIG. 4, Table 2 includes data regarding the crude oil residue **105** which is fed to the asphaltene separator, solvent extraction unit **110**.

[0049] **TABLE 2**

Atmospheric Crude Oil Residue – Stream 105		
Feeding Rate	100	kilograms per hour (kg/hr)
API Gravity	3.5	° API
Sulfur	5.4	wt %
Nickel	42	wt ppm
Vanadium	134	wt ppm
CCR	24	wt %
C ₇ -Asphaltene	10	wt %

[0050] Table 3, as follows, includes stream properties and stream compositions for the DAO-containing stream **114**, which was passed out of the asphaltene separator, solvent extraction unit **110**. In this case, the ASP separator was operated to produce about 71 wt%

DAO-containing fraction to reduce sulfur and metal contents. In other instances, the DAO yield may be set to around 40 wt% to have metal contents (Ni+V) removal of about 95%. Thus, ASP separator was operated in very mild condition, where there is less rejection of asphaltene.

[0051] TABLE 3

DAO-containing stream – Stream 114		
Flow rate	71	kg/hr
API Gravity	6.3	° API
Sulfur	3	wt %
Nickel	7	wt ppm
Vanadium	16	wt ppm
CCR	6	wt %
C ₇ -Asphaltene	1	wt %

[0052] Referring to FIG. 4, the water stream **115** was pumped to 27 MPa at a flow rate of 0.2 kg/hr and then pre-heated to 400°C to yield supercritical water stream **124**. The DAO-containing stream **114** was pumped to 27 MPa at a flow rate of 0.1 kg/hr and then pre-heated to 120°C to yield a pressurized, heated DAO-containing stream **126**. As show in FIG. 4, the supercritical water stream **124** and the pressurized, heated DAO-containing stream **126** were combined by a simple tee fitting mixer **130** to yield combined feed stream **132**. The combined feed stream **132** was fed to a downflow upgrading reactor **140** having a 160 milliliter (mL) internal volume. The internal stream temperature and reactor inner wall temperature were measured by thermocouples. The heater surrounding the upgrading reactor **140** maintained the reactor wall temperature at a temperature of 460°C. The reactor internal stream temperature was 430°C. The upgrading reactor output stream **142** was cooled to 200°C by double pipe type heat exchanger cooling unit **150** where tap water was used as coolant. The cooled output stream **152** was passed to a CSTR type vessel subcritical separator **260** of 500 ml internal volume. The CSTR temperature was adjusted to be 180°C by a heater and cooling coil. The CSTR subcritical separator **260** discharged the slurry mixture stream **261** from the bottom of the CSTR subcritical separator **260** through valve **163**.

[0053] The upgraded product stream **262**, which is discharged from the top of the CSTR subcritical separator **260** was reduced to atmospheric pressure by pressure control valve **170**. The properties of liquid oil from this upgraded product stream **262** are provided in Table 4 as follows. The effluent from the valve was separated into gas, liquid oil, and water by the gas-liquid separator **180** and the oil-water separator **190**.

[0054] TABLE 4

Upgraded Product Stream 262		
Flow rate	0.08	kg/hr
API Gravity	16	° API
Sulfur	2.5	wt%
Nickel	<1	wt ppm
Vanadium	<1	wt ppm
CCR	1	wt%
C ₇ -Asphalthene	<0.1	wt%

[0055] Referring again to FIG. 4, the depressurized slurry mixture **164** contained water (around 50 wt%), which was removed by a centrifuge **200** to produce the dried slurry mixture **204**. The dried slurry mixture **204** included about 20 wt% of DAO. The properties of this dried slurry mixture **204** is provided in Table 5 as follows.

[0056] TABLE 5

Dried Slurry Mixture 204		
Flow rate	0.02	kg/hr
Sulfur	2.1	wt%
Nickel	6	wt ppm
Vanadium	10	wt ppm

[0057] The dried slurry mixture **204** was passed to a calciner **210** where it was calcined at 1,100°C under flowing nitrogen to yield a stream comprising high grade coke product stream **214**. The properties of this high grade coke product stream **214** are provided in Table 6 as follows.

[0058] TABLE 6

High Grade Coke – Stream 214		
Sulfur	1.8	wt%
Nickel	8	wt ppm
Vanadium	12	wt ppm

[0059] It should be apparent to those skilled in the art that various modifications and variations can be made to the described embodiments without departing from the spirit and scope of the claimed subject matter. Thus it is intended that the specification cover the modifications and variations of the various described embodiments provided such modification and variations come within the scope of the appended claims and their equivalents.

CLAIMS

1. A process for producing high grade coke from crude oil residue comprising:

5 at least partially separating, in a solvent extraction unit, the crude oil residue into a deasphalted oil (DAO)-containing stream and an asphaltene containing-stream;

producing a pressurized, heated DAO-containing stream by pressurizing and heating the DAO-containing stream, where the pressurized, heated DAO-containing stream is at a temperature greater than 75°C, and a pressure greater than a critical
10 pressure of water;

mixing a supercritical water stream with the pressurized, heated DAO-containing stream to create a combined feed stream, where the supercritical water stream has a pressure greater than the critical pressure of water and a temperature greater than a critical temperature of water;

15 introducing the combined feed stream to an upgrading reactor system comprising one or more upgrading reactors operating at a temperature greater than the critical temperature of water and a pressure greater than the critical pressure of water to yield at least one upgrading reactor output stream comprising upgraded product and at least one upgrading reactor output stream comprising slurry mixture, such that the
20 upgraded product and the slurry mixture are transferred out of the upgrading reactor system separately, where the slurry mixture comprises sulfur and one or more additional metals;

feeding the upgraded product to a gas-liquid separator to separate the upgraded product into a gas-phase stream and a liquid phase stream; and

25 calcining the slurry mixture at a temperature of from 700°C to 1900°C to produce a product stream comprising the high grade coke.

2. The process of claim 1, where the upgraded product is a gas-liquid-oil stream.

30

3. The process of claim 1, further comprising drying the slurry mixture in a centrifuge upstream of the calcining step.

4. The process of claim 1, further comprising passing the slurry mixture, the upgrading reactor output stream, or both to a subcritical separator upstream of the calcining step.

5

5. The process of claim 4, further comprising cooling the slurry mixture, the upgraded product, or both to a temperature of 200°C or less prior to delivery to the subcritical separator.

10

6. The process of claim 4, where the subcritical separator is a continuous stirred tank reactor.

7. The process of claim 1, further comprising delivering the slurry mixture to a supercritical CO₂ extractor upstream of the calcining step.

15

8. The process of claim 1, further comprising delivering the slurry mixture to a delayed coker unit upstream of the calcining step.

9. The process of claim 1, where the upgrading reactor system includes downflow reactors, upflow reactors, or combinations thereof.

20

10. The process of claim 1, where the upgrading reactor system lacks an external supply of hydrogen gas and a catalyst.

11. The process of claim 1, where the upgrading reactor system includes a first reactor and a second reactor downstream of the first reactor.

25

12. The process of claim 11, where the first reactor and the second reactor are isothermal or non-isothermal.

30

13. The process of claim 11, where the first reactor, the second reactor, or both include agitation or stirring devices.

14. The process of claim 11, where a ratio of a volume of the first reactor to a volume of the second reactor is 0.1:1 to 1:1.

5 15. The process of claim 11, where the ratio of the volume of the first reactor to the volume of the second reactor is 0.5:1 to 1:1.

16. The process of claim 1, where the crude oil residue comprises atmospheric residue, vacuum gas oil, or vacuum residue.

10

17. The process of claim 1, where the DAO-containing stream includes less than 30 wt % of aromatics.

18. A process for producing high grade coke from crude oil residue
15 comprising:

at least partially separating, in a solvent extraction unit, the crude oil residue into a deasphalted oil (DAO)-containing stream and an asphaltene containing-stream;

producing a pressurized, heated DAO-containing stream by pressurizing and heating the DAO-containing stream, where the pressurized, heated DAO-containing
20 stream is at a temperature greater than 75°C, and a pressure greater than a critical pressure of water;

mixing a supercritical water stream with the pressurized, heated DAO-containing stream to create a combined feed stream, where the supercritical water stream has a pressure greater than the critical pressure of water and a temperature
25 greater than a critical temperature of water;

introducing the combined feed stream to an upgrading reactor system comprising one or more upgrading reactors operating at a temperature greater than the critical temperature of water and a pressure greater than the critical pressure of water to yield at least one upgrading reactor output stream comprising upgraded product and at
30 least one upgrading reactor output stream comprising slurry mixture, such that the upgraded product and the slurry mixture are transferred out of the upgrading reactor

system separately, where the upgraded product comprises a gas-liquid-oil stream and the slurry mixture comprises sulfur and one or more additional metals; and

calcining the slurry mixture at a temperature of from 700°C to 1900°C to produce a product stream comprising the high grade coke;

5 cooling the upgraded product to yield a cooled upgraded product having a temperature of less than 200°C;

reducing the pressure of the cooled upgraded product to create a depressurized cooled upgraded product with a pressure of from 0.05 MPa to 2.2 MPa;

10 feeding the depressurized cooled upgraded product to a gas-liquid separator to separate the depressurized cooled upgraded product into a gas-phase stream and a liquid phase stream; and

feeding the liquid-phase stream to an oil-water separator to separate the liquid-phase stream into a water-containing stream and an oil-containing stream.

15 19. The process of claim 18, where the upgrading reactor system lacks an external supply of hydrogen gas and a catalyst.

20. The process of claim 18, where the upgrading reactor system includes a first reactor and a second reactor downstream of the first reactor.