

Description

This invention relates to laser systems, and particularly to laser systems comprising optical fibre amplifiers.

Single mode optical fibres doped with rare-earth ions are known to exhibit optical amplification in useful regions of the spectrum when longitudinally - pumped using light of a shorter wavelength than that at which the fibres are caused to lase. This pump wavelength corresponds to an atomic absorption of the dopant ion.

As is well known in the art, when a laser is pumped with light at the pump wavelength, the ions in the laser are excited by the pump, and the laser is caused to lase. Not all of the pump light is converted to the output light of the laser, the remainder being known as the remnant pump. The remnant pump is often unusable, and so reduces the efficiency of the system.

A silica or multi component glass fibre doped with a few hundred parts per million of erbium ions is known to show optical gain at approximately 1536 nm. Suitable absorption bands in which to pump the amplifier occur at 540 nm, 650 nm, 800 nm and 980 nm. Some of these pump bands are more efficient than others. This is due to the existence of parasitic excited state absorption (ESA) of pump photons at certain wavelengths for example, erbium in silica glass has no ESA at 650 nm and 980 nm, but has significant amounts at around 800 nm. Much more efficient performance results are achieved, therefore, using a pump wavelength of 650 nm or 980 nm, rather than a pump wavelength of 800 nm.

Unfortunately, there is a scarcity of pump lasers available which are capable of pumping in the 650 nm band. In addition, the 650 nm band is not as quantum efficient as the 980 nm, but there is also a shortage of radiation sources capable of producing an output at around 980 nm. As a result optical fibre amplifiers are generally pumped at around 800 nm by, for example, high-power GaAlAs laser diodes, even though this pump band does not give the most efficient performance results.

US-A-4589118 describes a method of optical pumping of an erbium laser in which a flash lamp generates radiation at respectively different wavelengths which side pump the erbium laser and a separate neodymium laser respectively, the output power from the neodymium laser is supplied as an end pump to the erbium laser.

It is an object of the invention to provide a laser system in which a laser may be pumped at a wavelength which has substantially no ESA.

According to the present invention, there is provided, a laser system comprising;

a first laser pumpable at a first wavelength and at a second wavelength at which it exhibits substantially no excited state absorption;

and a second laser pumpable at the first wavelength whereby it is caused to lase at the second wavelength; the output of the second laser at the second wavelength, and the remnant pump at the first wavelength both being coupled to pump the first laser.

Preferably, the first laser comprises a single mode optical fibre doped with rare earth ions, for example, a silica based optical fibre doped with erbium ions. There will therefore be no ESA at pump wavelengths of around 650 nm and 980 nm. It has a further absorption band at 800 nm.

Preferably the second laser comprises a fluorozirconate fibre doped with Erbium ions and is pumped by a GaAlAs laser. The second laser may thus be pumped at around 800nm and caused to lase at around 980 nm.

A further advantage of the invention is that the remnant pump is arranged to combine with the output of the second laser to pump the first laser. Thus the first laser may be pumped at both around 980 nm and around 800 nm, thus increasing the efficiency of the system.

Alternatively, the second laser may be a silica based fibre doped with at least two types of rare earth ions. The ions may be neodymium and ytterbium ions, and the laser may be pumped at 800 nm. Pump photons are absorbed by the neodymium ions and these excited ions then transfer their energy to the ytterbium ions via a non radiative relaxation. This may lead to a population inversion between the two ytterbium ion levels, the system lasing at 980 nm.

The invention will now be described by way of example only with reference to the following drawings in which:

Figure 1 is a schematic diagram of a laser system made in accordance with the invention; Figure 2 shows the energy levels of an erbium doped fluorozirconate fibre laser and an erbium doped silica based fibre laser.

Figure 3 is a schematic diagram of a silica based fibre laser doped with neodymium and ytterbium ions.

Referring to Figure 1, an embodiment of laser system according to the present invention comprises a first laser 1 which comprises a silica based optical fibre which has been doped with erbium ions, and a second laser 2 which comprises a fluorozirconate fibre which has been doped with erbium ions. A GaAlAs laser 3 is used to pump the laser 2 at a first wavelength λ_1 of 800nm. This causes the laser 2 to lase at a second wavelength λ_2 of 980nm. This output λ_2 , together with the remnant pump λ_1 is injected into a laser 1 and

causes the laser 1 to lase at an output λ_3 of approximately 1540nm.

In another example of the system of Figure 1, laser 2 comprised an erbium doped fluoride fibre which had a 30 μ m core diameter and a numerical aperture of 0.22. It was doped with 267 parts per million erbium ions, and was 35cm long. It was a standard Fabry-Perot cavity with 95% reflectors. The pump 3 was an argon laser which pumped the laser 2 at 488 nm although pumping at 800 nm would have produced better results. The laser 2 operated at 988 nm wavelength. In this example, better results could be achieved by using a single mode fluoride fibre for laser 2.

Referring to figure 2, the energy levels involved in the system of figure 1 are illustrated. It can be seen that laser 2 is pumped by pump 3 at 800 nm. This excites the erbium ions to the $^4I_{9/2}$ level. The ions then undergo a non-radiative decay to the $^4I_{11/2}$ level, and from there undergo a radiative transition to the $^4I_{15/2}$ level producing light at 980 nm. The output at 980 nm from this radiative decay is coupled with the pump remnant at 800nm to pump the laser 1 at both 980nm and 800nm. Non radiative decay occurs from both the $^4I_{9/2}$ level and the $^4I_{11/2}$ level to the $^4I_{13/2}$ level. From there, radiative decay producing amplification of the pump input to around 1540 nm occurs to the $^4I_{15/2}$ level.

An advantage of the system is that wavelength λ_2 , when efficiently converted from wavelength λ_1 , may provide improved gain coefficients (in terms of dB/mW) than would have been otherwise obtained by pumping laser 1 at solely wavelength λ_1 .

The radiative transition of laser 2 can be seen to be $^4I_{11/2} - ^4I_{15/2}$. In other hosts, such as silica, this transition may not be radiative, strong phonon coupling producing fast non-radiative decays from the $^4I_{11/2}$ level to the $^4I_{13/2}$ level.

Referring to Figure 3, an alternative embodiment of laser 2 is schematically illustrated. The laser 2 comprises a silica based fibre containing both neodymium ions and ytterbium ions. The laser 2 is pumped at 800nm. Pump photons are absorbed by the neodymium ions, and these excited ions then transfer their energy to the ytterbium ions via a non radiative relaxation. A population inversion is established between the two ytterbium levels and the laser is caused to lase.

Claims

1. A laser system comprising:

a first laser (1) pumpable at a first wavelength and at a second wavelength at which it exhibits substantially no excited state absorption;

and a second laser (2) pumpable at the first wavelength whereby it is caused to lase at

the second wavelength;

the output of the second laser (2) at the second wavelength, and the remnant pump at the first wavelength both being coupled to pump the first laser (1).

2. A system according to claim 1 wherein the first laser is a single mode optical fibre doped with rare-earth ions.
3. A system according to claim 2 wherein the first laser is a silica based optical fibre doped with erbium ions.
4. A system according to any of the preceding claims wherein the second laser comprises a fluorozirconate based laser doped with erbium ions.
5. A system according to Claim 4 wherein the second laser is a single mode fibre.
6. A system according to claim 1, 2 or 3 wherein the second laser is a silica based fibre doped with both neodymium and ytterbium ions.

Patentansprüche

1. Lasersystem, das aufweist:
einen ersten Laser (1), der bei einer ersten Wellenlänge und bei einer zweiten Wellenlänge pumpbar ist, bei denen dieser im wesentlichen keine Absorption im angeregten Zustand (ESA) zeigt;
und einen zweiten Laser (2), der bei der ersten Wellenlänge pumpbar ist, wodurch dieser veranlaßt wird, bei der zweiten Wellenlänge einen Laserbetrieb auszuführen;
wobei sowohl die Ausgabe des zweiten Lasers (2) bei der zweiten Wellenlänge als auch die Restpumpstrahlung bei der ersten Wellenlänge gekoppelt sind, um den ersten Laser (1) zu pumpen.
2. System nach Anspruch 1, wobei der erste Laser eine optische Ein-Moden-Faser ist, die mit Ionen der Seltenen Erden dotiert ist.
3. System nach Anspruch 2, wobei der erste Laser eine optische Faser basierend auf Siliziumoxid ist, die mit Erbium-Ionen dotiert ist.
4. System nach einem der vorhergehenden Ansprüche, wobei der zweite Laser ein Laser basierend auf Fluor-Zirkonat ist, der mit Erbium-Ionen dotiert ist.



causes the laser 1 to lase at an output λ_3 of approximately 1540nm.

In another example of the system of Figure 1, laser 2 comprised an erbium doped fluoride fibre which had a 30 μ m core diameter and a numerical aperture of 0.22. It was doped with 267 parts per million erbium ions, and was 35cm long. It was a standard Fabry-Perot cavity with 95% reflectors. The pump 3 was an argon laser which pumped the laser 2 at 488 nm although pumping at 800 nm would have produced better results. The laser 2 operated at 988 nm wavelength. In this example, better results could be achieved by using a single mode fluoride fibre for laser 2.

Referring to figure 2, the energy levels involved in the system of figure 1 are illustrated. It can be seen that laser 2 is pumped by pump 3 at 800 nm. This excites the erbium ions to the $^4I_{9/2}$ level. The ions then undergo a non-radiative decay to the $^4I_{11/2}$ level, and from there undergo a radiative transition to the $^4I_{15/2}$ level producing light at 980 nm. The output at 980 nm from this radiative decay is coupled with the pump remnant at 800nm to pump the laser 1 at both 980nm and 800nm. Non radiative decay occurs from both the $^4I_{9/2}$ level and the $^4I_{11/2}$ level to the $^4I_{13/2}$ level. From there, radiative decay producing amplification of the pump input to around 1540 nm occurs to the $^4I_{15/2}$ level.

An advantage of the system is that wavelength λ_2 , when efficiently converted from wavelength λ_1 , may provide improved gain coefficients (in terms of dB/mW) than would have been otherwise obtained by pumping laser 1 at solely wavelength λ_1 .

The radiative transition of laser 2 can be seen to be $^4I_{11/2} - ^4I_{15/2}$. In other hosts, such as silica, this transition may not be radiative, strong phonon coupling producing fast non-radiative decays from the $^4I_{11/2}$ level to the $^4I_{13/2}$ level.

Referring to Figure 3, an alternative embodiment of laser 2 is schematically illustrated. The laser 2 comprises a silica based fibre containing both neodymium ions and ytterbium ions. The laser 2 is pumped at 800nm. Pump photons are absorbed by the neodymium ions, and these excited ions then transfer their energy to the ytterbium ions via a non radiative relaxation. A population inversion is established between the two ytterbium levels and the laser is caused to lase.

Claims

1. A laser system comprising:

a first laser (1) pumpable at a first wavelength and at a second wavelength at which it exhibits substantially no excited state absorption;

and a second laser (2) pumpable at the first wavelength whereby it is caused to lase at

the second wavelength;

the output of the second laser (2) at the second wavelength, and the remnant pump at the first wavelength both being coupled to pump the first laser (1).

2. A system according to claim 1 wherein the first laser is a single mode optical fibre doped with rare-earth ions.
3. A system according to claim 2 wherein the first laser is a silica based optical fibre doped with erbium ions.
4. A system according to any of the preceding claims wherein the second laser comprises a fluorozirconate based laser doped with erbium ions.
5. A system according to Claim 4 wherein the second laser is a single mode fibre.
6. A system according to claim 1, 2 or 3 wherein the second laser is a silica based fibre doped with both neodymium and ytterbium ions.

Patentansprüche

1. Lasersystem, das aufweist:
einen ersten Laser (1), der bei einer ersten Wellenlänge und bei einer zweiten Wellenlänge pumpbar ist, bei denen dieser im wesentlichen keine Absorption im angeregten Zustand (ESA) zeigt;
und einen zweiten Laser (2), der bei der ersten Wellenlänge pumpbar ist, wodurch dieser veranlaßt wird, bei der zweiten Wellenlänge einen Laserbetrieb auszuführen;
wobei sowohl die Ausgabe des zweiten Lasers (2) bei der zweiten Wellenlänge als auch die Restpumpstrahlung bei der ersten Wellenlänge gekoppelt sind, um den ersten Laser (1) zu pumpen.
2. System nach Anspruch 1, wobei der erste Laser eine optische Ein-Moden-Faser ist, die mit Ionen der Seltenen Erden dotiert ist.
3. System nach Anspruch 2, wobei der erste Laser eine optische Faser basierend auf Siliziumoxid ist, die mit Erbium-Ionen dotiert ist.
4. System nach einem der vorhergehenden Ansprüche, wobei der zweite Laser ein Laser basierend auf Fluor-Zirkonat ist, der mit Erbium-Ionen dotiert ist.



5. System nach Anspruch 4, wobei der zweite Laser eine Ein-Moden-Faser ist.
6. System nach Anspruch 1, 2 oder 3, wobei der zweite Laser eine Faser basierend auf Siliziumoxid ist, die mit sowohl Neodym- als auch mit Ytterbium-Ionen dotiert ist.

5

Revendications

10

1. Un système à laser comprenant:
 - un premier laser (1) pompable à une première longueur d'onde et à une deuxième longueur d'onde à laquelle il ne présente sensiblement aucune absorption à l'état excité;
 - et un deuxième laser pompable (2) à la première longueur d'onde, ce qui l'amène à produire un effet laser à la deuxième longueur d'onde;
 - la sortie du deuxième laser (2) à la deuxième longueur d'onde et la pompe restante à la première longueur d'onde étant l'une et l'autre couplées afin de pomper le premier laser (1).
2. Un système selon la revendication 1 dans lequel le premier laser est une fibre optique monomode dopée à l'aide d'ions des terres rares.
3. Un système selon la revendication 2 dans lequel le premier laser est une fibre optique à base de silice dopée à l'aide d'ions d'erbium.
4. Un système selon l'une quelconque des revendications précédentes dans lequel le deuxième laser comprend un laser à base de fluorozirconate dopé à l'aide d'ions d'erbium.
5. Un système selon la revendication 4 dans lequel le deuxième laser est une fibre monomode.
6. Un système selon la revendication 1, 2 ou 3 dans lequel le deuxième laser est une fibre à base de silice dopée à la fois par des ions de néodyme et d'ytterbium.

15

20

25

30

35

40

45

50

55