

FORMATION OF SOLAR CELL-SELECTIVE EMITTER
USING IMPLANT AND ANNEAL METHOD

CROSS-REFERENCE TO RELATED APPLICATIONS

5 This application claims priority to co-pending U.S. Provisional Application Serial
Number 61/131,687, filed June 11, 2008, entitled "SOLAR CELL FABRICATION USING
IMPLANTATION," co-pending U.S. Provisional Application Serial Number 61/131,688,
filed June 11, 2008, entitled "APPLICATIONS SPECIFIC IMPLANT SYSTEM FOR USE
10 IN SOLAR CELL FABRICATIONS," co-pending U.S. Provisional Application Serial
Number 61/131,698, filed June 11, 2008, entitled "FORMATION OF SOLAR CELL-
SELECTIVE EMITTER USING IMPLANTATION AND ANNEAL METHODS," co-
pending U.S. Provisional Application Serial Number 61/133,028, filed June 24, 2008, entitled
"SOLAR CELL FABRICATION WITH FACETING AND IMPLANTATION," and co-
15 pending U.S. Provisional Application Serial Number 61/210,545, filed March 20, 2009,
entitled "ADVANCED HIGH EFFICIENCY CRYSTALLINE SOLAR CELL
FABRICATIONS METHOD," which are all hereby incorporated by reference as if set forth
herein.

FIELD OF THE INVENTION

20 The present invention relates generally to the field of solar cells. More particularly,
the present invention relates to solar cell devices and methods of their formation.

BACKGROUND OF THE INVENTION

25 There are two major steps in making solar cells. The first step is to form a substrate
that is configured to generate electron-hole pairs upon the reception of light. One example of
such a substrate includes a p-n junction. The second step is to form conductive contacts on
the substrate that are configured to conduct the charge from the separated electrons so that the
charge can be conducted and carried away.

30 Currently, diffusion is used in the first step to form p-n junctions. A paste of dopant is
placed on the surface of the substrate. It is then heated up, driving the dopant into a particular
depth and forming the junction. Alternatively, a phosphorous dominant gas is introduced to
the substrate. Heating is then used to drive the phosphorous into the substrate. In the second
step, contact lines are screen printed onto the surface of the junction.

The use of diffusion of dopant from the surface into the substrate is plagued by problems. One of the main problems is the accumulation of unactivated dopants near the surface as the dopants are driven into the bulk of the material, which can vary the resistivity at different depths and regions of the substrate and thus lead to varying light absorption and electron-hole generation performance. In particular, one problem encountered is the lack of utilization of the blue light as the result of formation of the so-called "dead layer."

Additionally, lateral positioning of the dopants across the substrate is especially difficult as the line widths and wafer thicknesses are getting smaller. For example, for selective emitter applications, the solar cell industry is expected to require dopant lateral placements from 200 microns down to less than 50 microns. Such placement can be very difficult for the present methodology of diffusion and screen printing. Moreover, as wafers get thinner, from 150-200 microns of today down to less than 20 microns, vertical and batch diffusion and screen printing becomes extremely difficult or even impossible.

Furthermore, the use of diffusion has been unable to provide the ideal levels of dopant concentration and resulting resistivity. The electron-hole pair generation region of the solar cell would ideally have a low concentration of dopant and a high resistivity level, while the contact region (near or at the surface) of the solar cell would ideally have a high concentration of dopant and a low resistivity level. Diffusion is unable to address each region separately and is limited to a sheet resistance of about 50 Ohms/square ($\Omega/\square$) for both regions, which is not quite high enough for the electron-hole pair generation region and not quite low enough for the contact region.

SUMMARY OF THE INVENTION

The present invention provides methods for addressing the various ohmic losses arising from the use of older processes of doping solar substrate. The present invention involves modifying the resistance of the substrate, contacts, busbars and fingers, the contact resistance of the metal-silicon interface, the resistance of backside metallization, and achieving the desired resistivity under the grid contact and in between the fingers. Moreover, the advantageous formation of a selective emitter and its ability to improve performance is possible through the use of the present invention. The present invention is capable of being applied to grown single or mono-crystalline silicon, poly or multi-crystalline silicon, as well as very thin silicon or very thin film deposited silicon or other materials used for solar cell

formation and other applications. It is also capable of being extended to atomic species placement for any other material used in the fabrication of junctions and/or contacts.

Application-specific ion implantation and annealing systems and methods can be employed by the present invention in order to provide the appropriate and independent placement and concentration of dopant both within the bulk of the material and laterally positioned across the substrate. The use of accurate and highly accurately placed dopant and tailoring of dopant atomic profile is described below. Methods are described that address the requirements for heavily doped (10-40 Ohms/square) regions under the grid line, as well as methods to achieve lightly doped (80-160 Ohms/square) regions in between grid fingers.

Ideal sheet resistance levels of approximately 25 Ohms/square for the contact region under the grid line, which translates to a dopant concentration of approximately $1E20$ per cubic centimeter, and approximately 100 Ohms/square for the electron-hole pair generation region between the grid fingers and/or below the contact region, which translates to a dopant concentration of approximately $1E19$ per cubic centimeter, are able to be achieved through the use of the present invention.

Additionally, through the use of tailored parameters, the atomic dopant profile is simultaneously matched to provide the electrical junctions at the appropriate depth against the substrate background doping levels and to provide the resistivity required for the formation of the contacts on the surface. Use of retrograde doping and flat atomic profile (box junctions) are also deployed, if desired. This methodology provides a simple, effective and inexpensive means for formation of a selective emitter and appropriate resistivity to enhance solar cells efficiency performance.

The dopants can be activated through the use of a traditional furnace anneal with long time anneal, the use of rapid annealing, such as rapid thermal anneal (RTA), or the use of very rapid temperature rise and cool down methods, such as laser annealing, flash lamp annealing, or employing a firing furnace at the end of the solar cell fabrication, which can employ a lower temperature when used with the implantation of the present invention. Controlled use of annealing time and temperature provides further enhancement of atomic profile within the substrate. In the present invention, shorter time anneal is preferably used to ensure that dopant placement is not altered, but that full or near full activation is achieved.

In one aspect of the invention, a method of forming a solar cell is provided. A semiconducting wafer is provided having a pre-doped region. The semiconducting wafer is a silicon substrate. A first ion implantation of a dopant into the semiconducting wafer is performed to form a first doped region over the pre-doped region. The first ion implantation has a concentration-versus-depth profile. A second

ion implantation of a dopant into the semiconducting wafer is performed to form a second doped region over the pre-doped region. The second ion implantation comprises multiple independent dopant implants having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile, and has a concentration-versus-depth profile different from that of the first ion implantation. At least one of the first doped region and the second doped region is configured to generate electron-hole pairs upon receiving light, and the first and second ion implantations are performed independently of one another.

In some embodiments, a p-n junction is formed between the pre-doped region and the at least one of the first doped region and the second doped region that is configured to generate electron-hole pairs. In some embodiments, the semiconducting wafer is provided as a silicon substrate.

In some embodiments, the first doped region formed by the first ion implantation has a sheet resistance in a range of approximately 80 Ohms/square to approximately 160 Ohms/square. In some embodiments, the second doped region formed by the second ion implantation has a sheet resistance in a range of approximately 10 Ohms/square to approximately 40 Ohms/square. In some embodiments, the first doped region formed by the first ion implantation has a sheet resistance in a range of approximately 80 Ohms/square to approximately 160 Ohms/square, and the second doped region formed by the second ion implantation has a sheet resistance in a range of approximately 10 Ohms/square to approximately 40 Ohms/square.

In some embodiments, the method further comprises the step of disposing metal contact lines on the surface of the semiconducting wafer, wherein the metal contact lines are configured to conduct electrical charge from at least one of the first and second doped regions. In some embodiments, the pre-doped region is p-type doped and the first and second doped regions are n-type doped. In some embodiments, the method further comprises the step of performing an annealing process on the semiconducting wafer after at least one of the ion implantation steps.

In another aspect of the invention, a method of forming a solar cell is provided. A semiconducting wafer is provided having a pre-doped region. A homogeneously doped region is formed in the semiconducting wafer over the pre-doped region by performing a first ion implantation of a dopant into the semiconducting wafer, wherein a p-n junction is formed between the pre-doped region and the homogeneously doped region and the homogeneously doped region is configured to generate electron-hole pairs upon receiving light. A plurality of selectively doped regions are formed in the semiconducting wafer over the homogeneously doped region by performing a second ion implantation of a dopant into the semiconducting

wafer. The second ion implantation comprises multiple independent dopant implants having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile. The first and second ion implantations are performed independently of one another, and the selectively doped regions have a higher concentration of dopant than the
5 homogeneously doped region.

In some embodiments, the semiconducting wafer is provided as a silicon substrate. In some embodiments, the homogeneously doped region formed by the first ion implantation has a sheet resistance in a range of approximately 80 Ohms/square to approximately 160 Ohms/square. In some embodiments, each one of the selectively doped regions formed by
10 the second ion implantation has a sheet resistance in a range of approximately 10 Ohms/square to approximately 40 Ohms/square. In some embodiments, the homogeneously doped region formed by the first ion implantation has a sheet resistance in a range of approximately 80 Ohms/square to approximately 160 Ohms/square, and each one of the selectively doped regions formed by the second ion implantation has a sheet resistance in a
15 range of approximately 10 Ohms/square to approximately 40 Ohms/square.

In some embodiments, the method further comprises the step of disposing metal contact lines on the surface of the semiconducting wafer, wherein the metal contact lines are aligned over the plurality of selectively doped regions and are configured to conduct electrical charge from the plurality of selectively doped regions.

20 In some embodiments, the method further comprises the step of forming a metallic seed layer near the surface of the semiconducting wafer, wherein the metallic seed layer is configured to act as a transition layer between the selectively doped regions and the metal contact lines. In some embodiments, the metallic seed layer comprises a silicide. In some embodiments, the step of forming the metallic seed layer comprises ion implanting at least
25 one material into the semiconducting wafer, wherein the at least one material is chosen from the group consisting of: Ni, Ta, Ti, W, and Cu.

In some embodiments, the pre-doped region is p-type doped and the homogeneously and selectively doped regions are n-type doped. In some embodiments, the method further comprises the step of performing an annealing process on the semiconducting wafer after at
30 least one of the ion implantation steps. In some embodiments, the method further comprises the step of forming an anti-reflective coating layer over the homogeneously doped region.

In some embodiments, the selectively doped regions are implanted in the semiconducting wafer at predetermined locations using a mask, wherein the mask comprises openings that are aligned with the predetermined location. In some embodiments, the mask is
35 a contact mask disposed on the surface of the semiconducting wafer during the second ion implantation. In some embodiments, the mask is a physical mask disposed a predetermined

distance above the surface of the semiconducting wafer during the second ion implantation. In some embodiments, the selectively doped regions are implanted in the semiconducting wafer at predetermined locations using a shaped ion beam, wherein the shaped ion beam is aligned with the predetermined locations. In some embodiments, the selectively doped regions are laterally spaced apart from one another a distance in the range of approximately 1 mm to approximately 3 mm.

In yet another aspect of the invention, a solar cell is provided. The solar cell comprises a semiconducting wafer, a homogeneously doped region, a p-n junction, a plurality of selectively doped regions, and a plurality of metal contacts. The semiconducting wafer has a background doped region. The homogeneously doped region is formed in the semiconducting wafer over the background doped region by ion implanting a dopant into the semiconducting wafer and has a sheet resistance of between approximately 80 Ohms/square and approximately 160 Ohms/square. The p-n junction is formed between the homogeneously doped region and the background doped region. The selectively doped regions are formed in the semiconducting wafer over the homogeneously doped region by ion implanting multiple dopants, having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile, into the semiconducting wafer. Each one of the selectively doped regions has a sheet resistance of between approximately 10 Ohms/square and approximately 40 Ohms/square. The metal contacts are disposed on the surface of the semiconducting wafer and are aligned over the plurality of selectively doped regions. The metal contacts are configured to conduct electrical charge from the plurality of selectively doped regions.

In some embodiments, the semiconducting wafer is a silicon substrate. In some embodiments, the homogeneously doped region formed by the first ion implantation has a sheet resistance of approximately 100 Ohms/square. In some embodiments, each one of the selectively doped regions formed by the second ion implantation has a sheet resistance of approximately 25 Ohms/square.

In some embodiments, the solar cell further comprises a metallic seed layer disposed over the selectively doped regions and under the metal contacts. In some embodiments, the metallic seed layer comprises a silicide. In some embodiments, the metallic seed layer comprises at least one material chosen from the group consisting of: Ni, Ta, Ti, W, and Cu.

In some embodiments, the pre-doped region is p-type doped and the homogeneously and selectively doped regions are n-type doped. In some embodiments, the solar cell further comprises an anti-reflective coating layer disposed over the homogeneously doped region. In some embodiments, the selectively doped regions are laterally spaced apart from one another a distance in the range of approximately 1 mm to approximately 3 mm.

In another aspect of the invention, there is provided a method of forming a solar cell, the method comprising: providing a semiconducting wafer having a pre-doped region and a surface; performing a first ion implantation of a dopant into the semiconducting wafer to form a first doped region over the pre-doped region, wherein the first ion implantation has a concentration-versus-depth profile and the first doped region extends to the surface of the semiconducting wafer; and performing a second ion implantation of a dopant into the semiconducting wafer to form a second doped region over the pre-doped region, wherein the second ion implantation comprises multiple independent dopant implants having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile, and wherein the second ion implantation has concentration-versus-depth profiles different from that of the first ion implantation and the second doped region extends across only a portion of the region where the first doped region meets the surface of the semiconducting wafer, wherein at least one of the first doped region and the second doped region is configured to generate electron-hole pairs upon receiving light, and wherein the first and second ion implantations are performed independently of one another.

In yet another aspect of the invention, there is provided a method of forming a solar cell, the method comprising: providing a semiconducting wafer having a pre-doped region; performing a first ion implantation of a dopant into the semiconducting wafer to form a first doped region over the pre-doped region, wherein the first ion implantation has a concentration-versus-depth profile; performing a second ion implantation of a dopant into the semiconducting wafer to form a second doped region over the pre-doped region, wherein the second ion implantation comprises multiple independent dopant implants having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile, and wherein the second ion implantation has concentration-versus-depth profiles different from that of the first ion implantation; and forming an electrically conductive contact to the second doped region, wherein the second doped region is not also the first doped region, wherein at least one of the first doped region and the second doped region is configured to generate electron-hole pairs upon receiving light, and wherein the first and second ion implantations are performed independently of one another.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A is a plan view of one embodiment of a solar cell in accordance with the principles of the present invention.

FIG. 1B is a cross-sectional side view of one embodiment of a solar cell in accordance with the principles of the present invention.

FIG. 2 illustrates one embodiment of a method of forming a solar cell in accordance with the principles of the present invention.

FIG. 3 illustrates one embodiment of a homogeneous implantation in accordance with the principles of the present invention.

FIGS. 4A-C illustrate different embodiments of a selective implantation in accordance with the principles of the present invention.

FIG. 5 illustrates one embodiment of a contact seed implantation in accordance with the principles of the present invention.

FIG. 6 illustrates one embodiment of a metal contact formation in accordance with the principles of the present invention.

FIG. 7 illustrates one embodiment of an anti-reflective surface coating formation in accordance with the principles of the present invention.

FIG. 8 illustrates one embodiment of a profile tailoring graph in accordance with the principles of the present invention.

FIG. 9 is a graph illustrating the deficiencies in profile tailoring ability for solar cells that are doped using diffusion.

FIGS. 10A-B are graphs illustrating the advantages in profile tailoring ability for solar cells that are doped using ion implantation in accordance with the principles of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

The following description is presented to enable one of ordinary skill in the art to make and use the invention and is provided in the context of a patent application and its requirements. Various modifications to the described embodiments will be readily apparent to those skilled in the art and the generic principles herein may be applied to other embodiments. Thus, the present invention is not intended to be limited to the embodiment shown but is to be accorded the widest scope consistent with the principles and features described herein.

FIGS. 1A-10B illustrate embodiments of a solar cell device, its characteristics, and its formation, with like elements being numbered alike.

FIGS. 1A and 1B illustrate a plan view and a cross-sectional side view, respectively, of one embodiment of a solar cell 100 drawn to different scales in accordance with the principles of the present invention. The solar cell 100 comprises a wafer 110. In some
5 embodiments, the wafer 110 is a 156 x 156 mm wafer. Preferably, the wafer 110 is formed of a semiconductor material, such as silicon (single or multi-crystalline), and comprises a p-n junction. The p-n junction is formed from a p-type doped region 150 and an n-type doped region 160 being disposed next to one another. Metal contact lines 120 are printed, or
10 otherwise formed, on the surface of the wafer 110. It is contemplated that the contact lines 120 can also be formed from conductive material other than metal. Conductive fingers 130 are also disposed on the surface of the wafer 110 to collect the electrical charge from the contact lines and carry it out to an external load. Although in FIGS. 1A-B the contact lines are represented as five vertical lines 120 and the conductive fingers are represented as two
15 horizontal lines 130, it is contemplated that other numbers, sizes, shapes, orientations, and arrangements of the contacts 120 and fingers 130 can be employed.

In operation, as light comes into the semiconductor material of the wafer 110 through the exposed surface 140 between the contact lines 120 and fingers 130, it is converted into electron-hole pairs, typically within the n-type doped region 160. The electrons go one way,
20 getting attracted into the contacts 120, while the holes go the other way, towards the p-type doped region 150. The more dopant there is within a particular region, the more the electron-hole pairs are recaptured within that region, resulting in more lost electricity. Therefore, it is beneficial to control the level of doping for different regions. In regions where the light is to be converted into electron-hole pairs, the level of doping should be relatively low. In regions
25 where the charge is to go through the contact lines 120, the level of doping should be high. In FIG. 1B, the shaded region within n-type doped region 160 represents a homogeneous emitter region that has been homogeneously doped with a low level of n-type dopant. The patterned regions 170 disposed beneath the contact lines 120 near the surface of the wafer 110 represent selective emitter regions that have been selectively doped with a relatively high level of n-
30 type dopant.

As a result of minimizing the dopant concentration (thereby, maximizing the resistivity) of the homogeneous emitter region and maximizing the dopant concentration (thereby, minimizing the resistivity) of the selective emitter regions, the ability of the solar cell to transfer the generated electrons from the homogeneous emitter region through the

selective emitter regions to the contact lines is increased, while the risk of losing electricity to electron-hole pair recombination is reduced. Additionally, although bigger contact lines can conduct more electricity, they also block more light from entering the solar cell and being converted into electrons. By maximizing the dopant concentration of the selective emitter regions near the contact lines, the contact lines can actually be made thinner, thereby allowing more light to enter the solar cell, while improving the solar cells ability to transfer the electrons from the electron-hole pair generating region to the contact lines.

In some embodiments, the homogeneously doped region is doped to have a sheet resistance in a range of approximately 80 Ohms/square to approximately 160 Ohms/square, while the selectively doped regions are doped to have a sheet resistance in a range of approximately 10 Ohms/square to approximately 40 Ohms/square. In some embodiments, the homogeneously doped region is doped to have a sheet resistance of approximately 100 Ohms/square, while the selectively doped regions are doped to have a sheet resistance of approximately 25 Ohms/square.

As previously mentioned, the prior art has been unable to attain these configurations. In order to achieve these or similar dopant concentration and sheet resistance levels, and their accompanying benefits, the present invention employs independently performed ion implantations in the formation of these different regions.

FIG. 2 illustrates one embodiment of a method 200 of forming a solar cell in accordance with the principles of the present invention. Although FIG. 2 shows one embodiment of certain steps being performed in a certain order, it is contemplated that the order of the steps can vary in other embodiments in accordance with the principles of the present invention. Additionally, the use of the terms "first" and "second" along with the terms "ion implantation" and "doped region" in the claims should not be interpreted to represent a particular order unless the claims expressly state otherwise. The terms "first" and "second" are merely used to reflect the independent nature of the implantations and regions.

At a step 210, a semiconducting wafer is provided. In some embodiments, the semiconducting wafer is provided as a silicon substrate (having a mono- or poly-crystalline structure). The semiconducting wafer is provided already having been doped. In some embodiments, the semiconducting wafer is pre-doped with a p-type dopant, thereby creating a p-type background region on which the other aspects of the solar cell can be formed. In other embodiments, the semiconducting wafer is pre-doped with an n-type dopant, thereby creating a n-type background region on which the other aspects of the solar cell can be formed. In

some embodiments, the pre-doped background region is doped to have a sheet resistance in a range of approximately 30 Ohms/square to approximately 70 Ohms/square.

At a step 220, the semiconducting wafer is homogeneously doped with a low concentration level of dopant using an ion implantation process. In some embodiments, this step is achieved through blanket implantation of dopant in the pre-doped semiconducting wafer. FIG. 3 illustrates one embodiment of a homogeneous ion implantation of dopant 305 into a semiconductor wafer 310, similar to wafer 110 in FIG. 1B. This ion implantation 305 forms a homogeneously doped region 360 in the semiconductor wafer 310 over the pre-doped region 350. This blanket homogeneous layer 360 is configured to generate electron-hole pairs as a result of the incidence of light. This homogeneous layer 360 requires a low level of dopant (high resistivity) in order to not adversely affect the formation of charge carriers. N- or p-type dopant is implanted deep into the wafer 310 at low to medium doping levels, thereby forming a junction against the pre-doped material. In some embodiments, this junction is a p-n junction formed at the junction between the pre-doped region 350 and the homogeneously doped region 360. Preferably, the pre-doped region 350 is p-type doped, while the homogeneously doped region 360 is n-type doped. However, other doping configurations are within the scope of the present invention.

The dopant is implanted and the junction is formed to and at a predetermined depth, such as according to manufacturer requirements. In some embodiments, the depth and level of dopant is determined by the specific PV manufacturer resistivity and junction requirements. Various models can be used to pre-analyze and form a tailored atomic profile for this purpose. The information can be fed into the implant and anneal systems to meet the requirements.

The distance of the junction from the surface of the wafer is determined by the amount of energy used in the ion beam during the ion implantation of the dopant. In some embodiments, the amount of energy is in the range of 1 to 150 KeV, depending on the desired specifications for the solar cell device. The dopant concentration, and consequently the sheet resistance, of any of the regions being implanted with dopant, whether they be homogeneously implanted or selectively implanted, can be determined by the beam current of the ion implantation system. The species of the gas being ionized in the ion implantation system for the ion beam determines whether the doping will be either n-type or p-type. For example, phosphorous and arsenic each result in n-type doping, while boron results in p-type doping.

It is contemplated that various ion implantation systems can be used in the present invention. In some embodiments, plasma implant technology is employed. In some embodiments, an implantation system (not shown) having a high productivity is used for the doping of the different regions. Such an implantation system is the subject of co-pending
5 U.S. Provisional Application Serial Number 61/131,688, filed June 11, 2008, entitled "APPLICATIONS SPECIFIC IMPLANT SYSTEM FOR USE IN SOLAR CELL FABRICATIONS," which is hereby incorporated by reference in its entirety as if set forth herein. In some embodiments, either a spot beam or a widened beam is used to provide full coverage across the wafer at a productivity of one-thousand or more wafers per hour.

10 At a step 230, the semiconducting wafer is selectively doped with a high concentration level of dopant using a direct and/or plasma ion implantation process, thereby forming a selective emitter region on the wafer. The ion implantation process used in the step 230 is preferably independent of the ion implantation process used in the step 220.

In this selective doping step, the appropriate depth and doping level, through the
15 adjustment of implant energy and dose, are selected to provide very high dopant concentration (low resistivity) at or near the surface of the substrate. This can be achieved through multiple implants at varying energies and doses or as a continuum of variability to provide a tailored profile, which will be discussed in further detail below with respect to FIGS. 8-10B.

20 The purpose of the selective doping is to achieve the surface resistivity required for the subsequent contact formation. As the requirements for the fabrications of the contact migrates from screen printing to lithography or ink jet printing or other novel methods, the surface resistivity can be adjusted to meet the requirements. Additionally, if any surface passivation method is deployed, the implant conditions can be adopted to cope to such
25 variations.

The placement of dopant in the appropriate lateral position underneath the subsequent grid lines and at the appropriate concentration level is extremely advantageous. The formation of a plurality of highly doped regions in the semiconducting wafer over the homogeneously doped region can be achieved through various methods. FIGS. 4A-C
30 illustrate different embodiments of a selective implantation in accordance with the principles of the present invention.

FIG. 4A illustrates one embodiment where the ion implantation 405 is performed through the use of a physical mask layer 472 within the implant system that scribes the required implant regions 470 only. The physical mask layer 472 is disposed a predetermined distance above the surface of the semiconducting wafer 310. In some embodiments, the ion beam can be shaped, such as shown in FIG. 4C, in order to improve implant efficiency.

FIG. 4B illustrates one embodiment where the ion implantation 405 is performed through a contact mask layer 474 disposed on the surface of the semiconducting wafer 310. The contact mask layer 474 only scribes the required implant regions 470. In some embodiments, the contact mask layer 474 is formed through a coating. For example, the contact mask layer 474 can be formed through the use of a lithographic, screen printing step or other deposition and removal processes.

FIG. 4C illustrates one embodiment where the ion beam 405 is tailored to dope only the required implant regions 470 on semiconducting wafer 310. In this embodiment, the implant beam 405 is formed to meet the grid line dimension, thereby only implanting the region(s) of interest.

It is noted that in some embodiments, such as in FIGS. 4A-C, the selectively doped regions extend down to the pre-doped region 350, while in some embodiments, such as in FIG. 1B, the selectively doped regions do not extend all the way down to the pre-doped region 150.

It is also noted that the implantation steps 220 and 230 can be repeated as many times as necessary to achieve the desired results.

Optionally, at a step 235, a contact seed layer, preferably metallic, is implanted over the selectively doped regions in order to create a transition layer between the semiconducting wafer and the metal (or otherwise conductive) contact that will eventually be disposed on the surface of the semiconducting wafer. The formation of this contact seed layer can serve to affect the work function of the contact/semiconductor interface, to improve the electrical contact between the semiconductor material and metal contact. FIG. 5 illustrates one embodiment of a contact seed implantation 505 in accordance with the principles of the present invention. A relatively high dose of metal implantation 580 at or very near the surface and above the selectively doped regions 470 can form a silicided layer. Various metal implantations can be used, including, but not limited to Ni, Ta, Ti, W, and Cu. Such band gap engineering can improve the overall performance of the solar cell. A contact mask layer

576 can be used to properly align the implantation. In fact, any of the implantation alignment methods shown in FIGS. 4A-C (physical mask, contact mask, and physical beam) can be used to properly align and form the contact seed region over the selective emitter region. This transition layer step can even be used to improve traditional emitter performance. In this case, the implanted region can be made slightly smaller in order to minimize the contact leakage and formation of a Schottky diode. Metal-to-semiconductor contacts are present in every Photovoltaic device including those in the prior art. They can behave either as a Schottky barrier or as an Ohmic contact dependent on the characteristics of the interface. Therefore, control and management of this interface is of benefit in improving the performance of solar cells.

At a step 240, metal (or otherwise conductive) contact lines are placed on the surface of the semiconducting wafer. In some embodiments, the metal contact lines are formed on the surface of the semiconducting wafer, such as by printing, or using photolithography and plating. However, it is contemplated that other processes can be used to dispose the metal contacts onto the semiconducting wafer. FIG. 6 illustrates one embodiment of a metal contact formation in accordance with the principles of the present invention. The metal contact lines 690 have been aligned over the plurality of selectively doped regions 470 using a contact mask 576 similar to the mask used in the seed implantation step. The contact lines 690 are configured to conduct electrical charge from the selectively doped regions 470.

Optionally, at a step 245, an anti-reflective coating layer is formed over the homogeneously doped region. In some embodiments, the anti-reflective coating layer is formed by depositing an anti-reflective coating material over the homogeneously doped region. Materials that can be used to form the anti-reflective coating layer include, but are not limited to, SiO₂ and Si₃N₄). In some embodiments, the already-formed anti-reflective coating layer on the wafer can be enhanced by applying ion implantation to it. FIG. 7 illustrates one embodiment of an anti-reflective coating layer 795 formed over the homogeneously doped region of the semiconducting wafer.

FIG. 7 also illustrates one embodiment of the spacing between the selectively doped regions 470. In some embodiments, such as that shown in FIG. 7, the selectively doped regions 470 are laterally spaced apart from one another a distance in the range of approximately 1 mm to approximately 3 mm. However, it is contemplated that other spacing dimensions are within the scope of the present invention.

At a step 250, an annealing process is performed on the wafer. In some embodiments, the annealing step heats the semiconducting wafer to a temperature near, but below, its

melting point and restores damage that was inflicted upon the crystal structure of the semiconducting wafer due to any of the ion implantation steps. The annealing step can comprise furnace annealing. Alternatively, a laser annealing or flash lamp annealing can be used in place of the furnace annealing. Although FIG. 2 shows the annealing step being performed at the end of the method, it is contemplated that it can be performed at any point. For example, in some embodiments, the annealing process is performed immediately subsequent to any or each of the ion implantation steps, while in other embodiments, a single annealing process is performed after all of the ion implantations are complete. The timing of the annealing process will not affect the subsequent steps processing, be it implant or other PV fabrication steps.

For some of the methods above, provision of a registration mark on the semiconducting wafer may be used to align the formation of features. This can be achieved prior to the implant through various methods and is dependent on the capability of the PV manufacturer and their requirements. A simple method would be to laser scribe registration marks inline to present semiconductor registration marks. However the requirements for photovoltaic applications are not as stringent as semiconductors, and thus a simple registration mark will suffice.

The doping under the grid lines can also be tailored, laterally, to form a low resistivity region that can be potentially larger or smaller than the contact grid lines. This can be advantageous as it can reduce the potential of electrical leakage from the grid lines to the rest of the wafer. Such leakage can reduce the efficiency of cell performance. An adjustment of the implant beam dimension or physical mask can provide such capability. The magnitude of such leakage can be reduced or eliminated through the advantageous placement of dopant laterally as well.

The tailoring of the atomic profile can further be enhanced by the use of additional implants at various energies (depth) and dose (doping levels) to achieve the optimal profile for best achievable cell performance. In some embodiments, such combination implants are a series of lower dose and faster implants that can provide high productivity and tailored profiles. Such methods can be extended to the formation of a box junction, providing a flat top profile with an abrupt deep junction drop in atomic distribution. Alternatively the deep junctions can be graded to provide a gentle transition from high to low doping regions, and thus prevent the formation of electrical barriers.

Additional implants can also be used at the end of the PV fabrication process as a remediation implant. This can be in the traditional sense of the retrograde implants as

deployed in semiconductor applications. It can also be used where an implant is carried out subsequent to formation of the surface and deep junction resistivity or at the final completion of the cell fabrication. If a cell does not meet the final testing specifications, a trimming implant as a remediation step can be used to improve the performance. Alternatively, a very light doping around the edges of the grid line could be used to prevent further leakage, if the final testing shows an adverse effect.

The employment by the present invention of multiple independent dopant implants through ion implantation enables the shaping of an atomic profile of a solar cell device according to the user's preferences or requirements. Some users may prefer a boxed junction (or box profile) as an ideal abrupt junction at a certain depth. Other users may prefer a rolling profile from the surface down to the junction depth (background doping). Another group of users may prefer a very peaky profile at a shallow depth, followed by a gentle rolling profile all the way to the background doping. So far, those skilled in the art have not been able to achieve the advantage of being able to efficiently and effectively control the shape of the atomic profile and have been limited to a simple Gaussian distribution. The present invention uses multiple independent dopant implants having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile of the solar cell according to the user's preferences.

FIG. 8 illustrates one embodiment of a profile tailoring graph 800 in accordance with the principles of the present invention. The graph 800 represents the atomic profile of a solar cell with respect to dopant concentration (At./cm³) versus its dopant depth (Ang.). The total atomic profile is represented by line 810. Through the use of multiple ion implants, each having a different concentration-versus-depth profile, the dopant concentration (and thus the resistivity) of the solar cell can be precisely adjusted and controlled across predetermined depths by the user. Graph 800 shows three different implantation profiles 812, 814, and 816. The combination of these three profiles results in the total profile 810 of the solar cell.

Although each individual implantation can be limited to a Gaussian or pseudo-Gaussian distribution, the present invention combines them to effectively tailor the shape of the total atomic profile. In controlling the total atomic profile through the use of multiple independent implants, the present invention enables the user to effectively control the junction depth 840, where the implanted dopant of one type (such as n-type dopant) meets the dopant of the pre-doped background region 820 (such as p-type dopant). The user is also enabled to also control the dopant concentration 830 at or near the surface of the solar cell. The present invention allows the user to control the surface concentration 830 and the

junction depth 840 independently of one another. In some embodiments, the atomic profile is tailored to have the junction depth in the range of approximately 0.01 micrometers to approximately 0.5 micrometers. In some embodiments, the atomic profile is tailored to have the surface concentration in the range of approximately $5E18$ At./cm³ to approximately $4.8E21$ At./cm³). However, it is contemplated that the atomic profile can be tailored to have different junction depths and surface concentrations.

In the prior art, the adjustment of the atomic profile is limited. FIG. 9 is a graph illustrating the deficiencies in profile tailoring ability for solar cells that are doped using diffusion. Here, line 910 represents an atomic profile for a solar cell. The use of diffusion to dope the semiconducting wafer prevents the user from being able to independently control the surface concentration and the junction depth. The user is limited to either making the profile 910 deeper by simply increasing the concentration and depth together to line 910' or making the profile 910 shallower by decreasing the concentration and depth together to line 910". The user is not able to change the shape of the atomic profile and affect one aspect of the atomic profile more than the other.

FIGS. 10A-B are graphs illustrating the advantages in profile tailoring ability for solar cells that are doped using ion implantation in accordance with the principles of the present invention. In graph 1000 of FIG. 10A, the atomic profile 1010 in terms of concentration-versus-depth is illustrated for a solar cell formed using prior art methods. Here, the profile 1010 is limited to a simple Gaussian distribution, making it difficult for the electrons generated in the electron-hole pair generating region to travel up to the contacts. The steep slope of the profile 1010 reflects the significant increase in dopant concentration (and thus resistivity) as the electrons travel towards conductive contacts at the surface of the wafer. This steep slope can make it more difficult for the electrons to reach the contacts, thus resulting in an undesirable loss of electricity.

In graph 1000' of FIG. 10B, the atomic profile 1010' in terms of concentration-versus-depth is illustrated for a solar cell formed using the multiple ion implants of the present invention. The profile 1010' can be shaped to form a more gradual (less steep) increase in concentration as the electrons travel towards the contacts at the surface of the semiconducting wafer. This tailoring of the atomic profile is made possible by the use of multiple ion implants to independently control the junction depth and the surface concentration, as well as everything in between.

In FIG. 8, the different implantations 812, 814, and 816 can determine different aspects of the solar cell. For example, in some embodiments, line 812 (the mid-range

implant) determines the homogeneous emitter, while lines 814 and 816 are added as a series of selective implants to provide the selective emitter region. These implantation steps can be performed either on blanket substrates, without any covering, or through any anti-reflective covering (e.g., nitride, oxide or any other films), as well as on surface texturing that is required for solar cell fabrications. In the case of texturing, ion implantation provides a good adherence to the surface contour, and thus improves the contact formation. Graph 800 of FIG. 8 shows surface coating 850, such as the anti-reflective coating previously discussed. This coating can be any thickness.

As discussed above, embodiments of the present invention are well suited for fabricating solar cell devices. The following co-pending patent applications, each of which is hereby incorporated by reference in its entirety as if set forth herein, describe ways of fabricating solar cell devices: "SOLAR CELL FABRICATION USING IMPLANTATION," by Babak Adibi and Edward S. Murrer, filed June 11, 2009, having Attorney Docket No. SITI-00100; "APPLICATIONS SPECIFIC IMPLANT SYSTEM FOR USE IN SOLAR CELL FABRICATIONS," by Babak Adibi and Edward S. Murrer, filed June 11, 2009, having Attorney Docket No. SITI-00200; and "SOLAR CELL FABRICATION WITH FACETING AND IMPLANTATION," by Babak Adibi and Edward S. Murrer, filed June 24, 2008, having Attorney Docket No. SITI-00400. It is contemplated that any of the features described within these co-pending patent applications can be incorporated into the present invention.

The present invention has been described in terms of specific embodiments incorporating details to facilitate the understanding of principles of construction and operation of the invention. Such reference herein to specific embodiments and details thereof is not intended to limit the scope of the claims appended hereto. It will be readily apparent to one skilled in the art that other various modifications may be made in the embodiment chosen for illustration without departing from the spirit and scope of the invention as defined by the claims.

CLAIMS

What is claimed is:

1. A method of forming a solar cell, the method comprising:
 - providing a semiconducting wafer having a pre-doped region, wherein the semiconducting wafer is a silicon substrate;
 - performing a first ion implantation of a dopant into the semiconducting wafer to form a first doped region over the pre-doped region, wherein the first ion implantation has a concentration-versus-depth profile; and
 - performing a second ion implantation of a dopant into the semiconducting wafer to form a second doped region over the pre-doped region, the second ion implantation comprises multiple independent dopant implants having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile, and wherein the second ion implantation has concentration-versus-depth profiles different from that of the first ion implantation,
 - wherein at least one of the first doped region and the second doped region is configured to generate electron-hole pairs upon receiving light, and
 - wherein the first and second ion implantations are performed independently of one another.
2. The method of Claim 1, wherein a p-n junction is formed between the pre-doped region and the at least one of the first doped region and the second doped region that is configured to generate electron-hole pairs.
3. The method of Claim 1, wherein the first doped region formed by the first ion implantation has a sheet resistance in a range of approximately 80 Ohms/square to approximately 160 Ohms/square.
4. The method of Claim 1, wherein the second doped region formed by the second ion implantation has a sheet resistance in a range of approximately 10 Ohms/square to approximately 40 Ohms/square.
5. The method of Claim 1, wherein:
 - the first doped region formed by the first ion implantation has a sheet resistance in a range of approximately 80 Ohms/square to approximately 160 Ohms/square, and
 - the second doped region formed by the second ion implantation has a sheet resistance in a range of approximately 10 Ohms/square to approximately 40 Ohms/square.

6. The method of Claim 1, further comprising the step of disposing metal contact lines on the surface of the semiconducting wafer, wherein the metal contact lines are configured to conduct electrical charge from at least one of the first and second doped regions.
7. The method of Claim 1, further comprising the step of performing an annealing process on the semiconducting wafer after at least one of the ion implantation steps.
8. A method of forming a solar cell, the method comprising:
 - providing a semiconducting wafer having a pre-doped region;
 - forming a homogeneously doped region in the semiconducting wafer over the pre-doped region by performing a first ion implantation of a dopant into the semiconducting wafer, wherein a p-n junction is formed between the pre-doped region and the homogeneously doped region and the homogeneously doped region is configured to generate electron-hole pairs upon receiving light; and
 - forming a plurality of selectively doped regions in the semiconducting wafer over the homogeneously doped region by performing a second ion implantation of a dopant into the semiconducting wafer, wherein the second ion implantation comprises multiple independent dopant implants having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile,
 - wherein the first and second ion implantations are performed independently of one another, and
 - wherein the selectively doped regions have a higher concentration of dopant than the homogeneously doped region.
9. The method of Claim 8, further comprising the step of disposing metal contact lines on the surface of the semiconducting wafer, wherein the metal contact lines are aligned over the plurality of selectively doped regions and are configured to conduct electrical charge from the plurality of selectively doped regions.
10. The method of Claim 9, further comprising the step of forming a metallic seed layer near the surface of the semiconducting wafer, wherein the metallic seed layer is configured to act as a transition layer between the selectively doped regions and the metal contact lines.
11. The method of Claim 8, further comprising the step of performing an annealing process on the semiconducting wafer after at least one of the ion implantation steps

12. The method of Claim 8, further comprising the step of forming an anti-reflective coating layer over the homogeneously doped region.

13. The method of Claim 8, wherein the selectively doped regions are implanted in the semiconducting wafer at predetermined locations using a mask, wherein the mask comprises openings that are aligned with the predetermined location.
14. The method of Claim 13, wherein the mask is a contact mask disposed on the surface of the semiconducting wafer during the second ion implantation.
15. The method of Claim 13, wherein the mask is a physical mask disposed a predetermined distance above the surface of the semiconducting wafer during the second ion implantation.
16. The method of Claim 8, wherein the selectively doped regions are implanted in the semiconducting wafer at predetermined locations using a shaped ion beam, wherein the shaped ion beam is aligned with the predetermined locations.
17. A solar cell comprising:
 - a semiconducting wafer having a background doped region;
 - a homogeneously doped region formed in the semiconducting wafer over the background doped region, wherein the homogeneously doped region has a sheet resistance of between approximately 80 Ohms/square and approximately 160 Ohms/square and is formed by ion implanting a dopant into the semiconducting wafer;
 - a p-n junction formed between the homogeneously doped region and the background doped region;
 - a plurality of selectively doped regions formed in the semiconducting wafer over the homogeneously doped region, wherein each one of the selectively doped regions has a sheet resistance of between approximately 10 Ohms/square and approximately 40 Ohms/square and is formed by ion implanting multiple dopants, having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile, into the semiconducting wafer; and
 - a plurality of metal contacts disposed on the surface of the semiconducting wafer and aligned over the plurality of selectively doped regions, wherein the plurality of metal contacts is configured to conduct electrical charge from the plurality of selectively doped regions.
18. The solar cell of Claim 17, further comprising a metallic seed layer disposed over the selectively doped regions and under the metal contacts.
19. The solar cell of Claim 18, wherein the metallic seed layer comprises a silicide.

20. The solar cell of Claim 18, wherein the metallic seed layer comprises at least one material chosen from the group consisting of: Ni, Ta, Ti, W, and Cu.

21. The solar cell of Claim 17, wherein the pre-doped region is p-type doped and the homogeneously and selectively doped regions are n-type doped.
22. The solar cell of Claim 17, further comprising an anti-reflective coating layer disposed over the homogeneously doped region.
23. The solar cell of Claim 17, wherein the selectively doped regions are laterally spaced apart from one another a distance in the range of approximately 1 mm to approximately 3 mm.
24. A method of forming a solar cell, the method comprising:
providing a semiconducting wafer having a pre-doped region and a surface;
performing a first ion implantation of a dopant into the semiconducting wafer to form a first doped region over the pre-doped region, wherein the first ion implantation has a concentration-versus-depth profile and the first doped region extends to the surface of the semiconducting wafer; and
performing a second ion implantation of a dopant into the semiconducting wafer to form a second doped region over the pre-doped region, wherein the second ion implantation comprises multiple independent dopant implants having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile, and wherein the second ion implantation has concentration-versus-depth profiles different from that of the first ion implantation and the second doped region extends across only a portion of the region where the first doped region meets the surface of the semiconducting wafer,
wherein at least one of the first doped region and the second doped region is configured to generate electron-hole pairs upon receiving light, and
wherein the first and second ion implantations are performed independently of one another.
25. A method of forming a solar cell, the method comprising:
providing a semiconducting wafer having a pre-doped region;
performing a first ion implantation of a dopant into the semiconducting wafer to form a first doped region over the pre-doped region, wherein the first ion implantation has a concentration-versus-depth profile;
performing a second ion implantation of a dopant into the semiconducting wafer to form a second doped region over the pre-doped region, wherein the second ion implantation comprises multiple independent dopant implants having predetermined different concentration-versus-depth profiles in order to tailor the total atomic profile, and wherein the second ion implantation has concentration-versus-depth profiles different from that of the first ion implantation; and

forming an electrically conductive contact to the second doped region, wherein the second doped region is not also the first doped region,

wherein at least one of the first doped region and the second doped region is configured to generate electron-hole pairs upon receiving light, and
wherein the first and second ion implantations are performed independently of one another.